

METHOD AND SYSTEM FOR LASER SOFT MARKING

CROSS-REFERENCE TO RELATED APPLICATIONS

This application claims the benefit of U.S. provisional application Serial No. 60/627,760, filed November 11, 2004. This application is related to
5 U.S. application Serial No. 10/438,501, filed May 15, 2003, which is hereby incorporated by reference herein.

BACKGROUND OF THE INVENTION

1. Field of the Invention

This invention relates to methods and systems for laser soft marking,
10 especially for semiconductor wafers and devices.

2. Background Art

Lasers have been used for laser marking semiconductor wafers for decades. A listing of representative patents and publications generally related to laser marking is now provided. U.S. patent 5,329,090 relates to dot marking of
15 wafers. The following representative patent references relate to various aspects of laser marking of wafers and electronic assemblies, illumination, and inspection/reading marks: U.S. Pat. Nos. 4,522,656; 4,945,204; 6,309,943; 6,262,388; 5,929,997; 5,690,846; 5,894,530; 5,737,122; and Japanese Patent Abstract 11135390.

20 The following representative references provide general information on various laser marking methods and system configurations and components: "Galvanometric and Resonant Low Inertia Scanners", Montagu, in Laser Beam Scanning, Marcel-Dekker, 1985, pp. 214-216; "Marking Applications now Encompass Many Materials", Hayes, in Laser Focus World, February 1997, pp.
25 153-160; "Commercial Fiber Lasers Take on Industrial Markets", Laser Focus

World, May 1997, pp. 143-150. Patent Publications: WO 96/16767, WO 98/53949, U.S. Pat. Nos. 5,965,042; 5,942,137; 5,932,119; 5,719,372; 5,635,976; 5,600,478; 5,521,628; 5,357,077; 4,985,780; 4,945,204; 4,922,077; 4,758,848; 4,734,558; 4,856,053; 4,323,755; 4,220,842; 4,156,124.

5 Published Patent Applications WO 0154854, publication date Aug. 2, 2001, entitled "Laser Scanning Method and System for Marking Articles such as Printed Circuit Boards, Integrated Circuits, and the Like" and WO 0161275, published on Aug. 23, 2001, entitled "Method and System for Automatically Generating Reference Height Data for use in a Three-Dimensional Inspection
10 System" are both assigned to the assignee of the present invention. Both applications are hereby incorporated by reference in their entirety.

 The visibility of laser marks as seen by a vision system (or by operator visual inspection) may depend on several factors including mark depth, debris, etc. which in turn depend on laser material-interaction. For certain wafer
15 marking applications the conventional wisdom leads to relatively large marking depths which may provide for good readability, but increasing susceptibility to subsurface damage.

 Wafer marking systems have long been provided by the assignee of the present invention. WaferMark™ system, produced by the assignee of the present
20 invention for several years, is believed to be the first industrial laser marking system on silicon wafer. Specifications include a 120 μm marking dot diameter hard marking for 300 nm wafers. This meets the SEMI standard specification M1.15. A "soft marking specification" exists for wafer back side soft marking, including marking rough surface back side wafers up to 200 mm wafer. On the "Sigma Clean"
25 system, a backside-marking option is provided for both front and backside marking for up to 200 mm wafer.

 There are roughly two kinds of laser marks currently used by the industry, namely soft marks and hard marks. Various marking systems for producing both "hard marks" and "soft marks" are manufactured by the assignee

of the present invention. One such currently available system is the GSILumonics Wafermark[®] Sigma Clean[®] is used to produce a type of softmark called Supersoftmark[®]. This mark is generally characterized as "debris free". These marks are typically produced with diode pumped, q-switched pulse laser systems.

5 Such Supersoftmarks[®] are produced with the laser system typically operating in a narrow "energy window", a range of energies having an upper limit and lower limit wherein acceptable marking occurs.

U.S. Patent No. 4,522,656, assigned to the assignee of the present invention, is the foundation of the current laser technology for soft marks. It

10 describes a method which is characterized by the steps of irradiating by means of a laser pulse, a surface segment which has a surface area corresponding to 1.5 times to 6.5 times the surface area of the desired surface pattern, and adjusting the energy of the laser pulse so that only in the center of the surface segment, and on a surface corresponding to the surface pattern, the semiconductor material is melted and

15 partially vaporized. The pattern generated usually has, relative to the original semiconductor surface, a raised annular rim and a recessed center, as shown in Figure 5.

According to U.S. Patent No. 4,522,656, the depth of the recess can be controlled by energy density, *i.e.*, the depth of the recess will be increased if

20 there is a corresponding increase of the energy density in the center of the pulse.

It is well known, however, that the process window for the energy density for generating such marks (commonly known as the super soft marks) is very small. Therefore, the adjustment of the depth of the recessed area by changing the energy density on the part is very limited. In addition, there are certain depth

25 ranges that cannot be achieved by simply adjusting the energy or energy density.

For example, one can increase the laser energy from 970 μj to 980 μj to get the upper energy limit of the super soft mark, shown in Figure 6. Since the energy process window for super soft mark is only around 10 μj in this case, the difference in depth between the two marks is very small. If one has to generate a

mark with a depth about 2 μm , for example, it is very difficult, and perhaps impossible, with of laser marking technology developed to date.

- As the semiconductor fabrication technologies evolve, soft marks on wafers with different mark depths are required to accommodate the new processes.
- 5 It is, therefore, very desirable to have a laser marking technique that provides easy adjustment for the marking depth of the super soft marks.

SUMMARY OF THE INVENTION

An object of the present invention is to provide an improved method and system for laser soft marking, especially for semiconductor wafers and devices.

- 10 In carrying out the above object and other objects of the present invention, a laser-marking method of marking a semiconductor wafer to form a softmark on the wafer is provided. The method includes setting a laser pulse width of one or more laser pulses to selectively provide one or more laser output pulses having one or more set pulse widths that affect the depth of a softmark that is to be
- 15 formed. The mark depth is substantially dependent on the one or more set pulse widths. The method further includes setting a pulse energy of the one or more output pulses to selectively provide the one or more output pulses having a set total output energy that is within an acceptable process energy window for producing the softmark. The method still further includes delivering the one or more output pulses
- 20 having the one or more set pulse widths and the set total output energy into a region of the wafer such that energy density within the region, as determined by the one or more set pulse widths and the set total output energy, modifies wafer material and thereby produces the softmark having the mark depth within a predetermined range.

- The mark depth may be substantially proportional to a pulse width
- 25 over a substantial range of pulse widths.

The mark depth may be in the range of about 1 micron to 6 microns.

The mark depth may be predetermined and formed with exactly one output pulse.

The mark depth may be finer than about 1 micron.

Energy in a single output pulse may be in a typical range of about 600
5 microjoules to about 1100 microjoules.

The acceptable process energy window may be centered on a central energy in a typical range having a lower limit of about 10 microjoules less than the central energy and an upper limit about 10 microjoules above the central energy.

An output pulse may have a typical set pulse width in the range of
10 about 10 nanoseconds to about 200 nanoseconds.

The step of setting the laser pulse width may be performed subsequent to the step of setting the pulse energy.

The step of setting the pulse energy may be performed subsequent to the step of setting the laser pulse width.

15 The steps of setting may be performed substantially simultaneously.

Further in carrying out the above object and other objects of the present invention, a laser-marking system for marking a semiconductor wafer to form a softmark on the wafer is provided. The system includes a laser subsystem for generating one or more laser pulses and a controller operatively connected to the
20 laser subsystem. The controller sets a laser pulse width of the one or more laser pulses to selectively provide one or more laser output pulses having one or more set pulse widths that affect the depth of a softmark that is to be formed. The mark depth is substantially dependent on the one or more set pulse widths. The controller further sets a pulse energy of the one or more output pulses to selectively provide
25 the one or more output pulses having a set total output energy that is within an

acceptable process energy window for producing the softmark. The system further includes a beam delivery system that includes an optical subsystem for delivering the one or more output pulses having the one or more set pulse widths and the set total output energy into a region of the wafer such that energy density within the region, as determined by the one or more set pulse widths and the set total pulse energy, modifies wafer material and thereby produces the softmark having the mark depth within a predetermined range.

The controller may include a subsystem of electronic components and a control program that is generally used for marking system control.

The controller may further include a subsystem of electronic components and a control program that is dedicated to control of the laser subsystem.

The laser subsystem may include a fiber-based laser having a tunable pulse width.

Yet still further in carrying out the above object and other objects of the present invention, a laser-marking method of forming a softmark on a semiconductor wafer is provided. The method includes setting a temporal characteristic of at least a portion of a pulsed laser output that affects depth of a softmark to be formed with the laser output. The method further includes setting total output energy of the pulsed laser output to correspond to energy within an acceptable process energy window so as to form the softmark on the semiconductor wafer.

The steps of setting may be performed prior to marking a batch of wafers. The temporal characteristic and the total output energy may remain set during marking of the entire batch.

The steps of setting may be performed subsequent to positioning a wafer at a marking station, and prior to marking a single wafer.

The steps of setting may be performed subsequent to positioning a wafer at a marking station and prior to marking a single wafer. The temporal characteristic and the total output energy may be varied to produce softmarks having different predetermined depths on the wafer.

- 5 The steps of setting may be performed by a laser-marking system, and the temporal characteristic and the total output energy may be set at a manufacturing site of the laser-marking system or at a site where the laser-marking system is installed.

- 10 Further in carrying out the above object and other objects of the present invention, a laser-marking method of forming a softmark on a semiconductor wafer is provided. The method includes setting one or more laser pulse widths of one or more laser pulses. The one or more set pulse widths affect depth of the softmark to be formed with the one or more laser pulses. The method further includes setting total output energy of the one or more laser pulses. The set
15 total output energy corresponds to energy within an acceptable process energy window to form the softmark on the semiconductor wafer.

Embodiments of the present invention may generally be used to produce either softmarks or supersoftmarks®.

- 20 One aspect of the invention features a semiconductor wafer having a softmark. The mark may generally be in a range of about 1 micron to about 6 microns. In at least one embodiment of the present invention a softmark depth may be finer than about 1 micron.

- 25 The above object and other objects, features, and advantages of the present invention are readily apparent from the following detailed description of the best mode for carrying out the invention when taken in connection with the accompanying drawings.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 schematically illustrates first and second softmarks produced within a localized region of a semiconductor wafer using a laser marking system of one embodiment of the present invention (simplified for illustration, not to scale);

5 FIG. 2 illustrates an exemplary laser and optical system layout which may be used in a commercial marking system for practicing at least one embodiment of the present invention;

 FIGS. 3a and 3b schematically illustrate, by way of example, a laser cavity (Figure 3a) and a modification of the cavity length to change the laser output
10 pulse width (Figure 3b);

 FIGS. 4a-4c illustrate exemplary temporal pulse characteristics of a burst of pulses, and shows an expanded view of one or more pulses within a burst;

 FIG. 5 is a top view of a prior art super soft mark, graphs and data laser pulse energy 970 μj ;

15 FIG. 6 is a top view of a prior art super soft mark, graphs and data laser pulse energy 980 μj ;

 FIG. 7 is a graph of mark depth versus laser pulse width for a given energy density;

 FIG. 8 is a top view of a super soft mark, graphs and data with the
20 mark having a depth of 2.6 μm ; and

 FIG. 9 is a top view of a super soft mark, graphs and data with the mark having a depth of 1.8 μm .

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Based on experimental results, the inventors realize that laser pulse width has much more impact on the mark depth than the energy or energy density does in a method and system of an embodiment of the present invention.

5 FIGURE 1 schematically illustrates first and second softmarks produced within a localized region of a semiconductor wafer using a laser marking system of the present invention (simplified for illustration, not to scale). By way of example, marks with depths D1 and D2 are formed with laser first and second pulsed laser outputs having pulse widths t1 and t2 and energies E1 and E2. In this
10 example a portion of the wafer is marked where the wafer optical properties are substantially constant. A laser output is directed to a marking location using a beam deflector, for instance a 2-axis galvanometer scanner. The scanner is included within the delivery system along with various other various optical components for beam expansion, focusing, attenuation, and similar operations on a laser beam.

15 FIGURE 2 illustrates an exemplary laser and optical system layout which may be used in a commercial marking system for practicing at least one embodiment of the present invention. The Sigma 100 laser refers to a commercially available, diode-pumped, solid state laser produced by the assignee of the present invention. Various combinations of beam shaping optics (e.g: beam expanders),
20 scan lenses, and scan mirror configurations may be utilized in embodiments of the present invention.

The graph of FIGURE 7 shows experimental results of mark depth dependence on the laser pulse width for a given energy density.

25 FIGURES 8 and 9 show typical super soft marks with mark depths 2.6 μm and 1.8 μm for pulse widths 124 ns and 72 ns, respectively.

The laser energy, and corresponding energy density, used in embodiments of the present invention will generally be based on wafer optical

properties. In many cases the wafers will be bare and polished. The wafer may be polished so as to conform to a surface roughness standard. The surface reflectance can be expected to vary from batch to batch, and possibly over a wafer. Oxidation can lead to a requirement for adjustment of the incident energy. Typically the
5 incident energy will be in a range of about 600 microjoules – 1100 microjoules (e.g.: nearly a 2:1 variation).

Preferably the marking will occur at the position of best focus at each marking location over a marking field. However, the marking may also occur at positions other than best focus and may occur with off-normal incident marking
10 beams.

Preferably, a laser pulse width will be easy to set, and may be programmable. One such example is a fiber laser from IPG Photonics that is used by the assignee of the present invention in certain M430 memory repair systems. Laser pulse widths can be selected over a continuous range from 4 ns to 20 ns. In
15 at least one preferred embodiment a mark depth, a corresponding laser pulse width, or laser output energy laser pulse width may be selected through the use of the user interface provided with the marking system.

Published U.S. patent application 2004/0188399, assigned to the assignee of the present invention, discloses various laser system embodiments
20 useable for creating or removing a feature on a surface. By way of example, a MOPA system having a fiber optic amplifier is disclosed. The laser processing system may include an output sub-system having an A-O modulator. The MOPA and output modulator are controlled to selectively direct one or more laser pulses to the target material based on position information. Each of the output pulses
25 incident of the surface may have a different pulsewidth.

Another way to set a pulse width is to adjust the laser cavity geometry and dimensions, as well as the reflectivity of the output coupler. FIGURE 3a shows a typical laser cavity with the output coupler reflectivity, R_1 , and a total cavity length, L_1 . A folded cavity can also be represented with an effective cavity length

in this case. FIGURE 3b shows how the laser pulse width can be changed by varying the cavity length to L2 and the output coupler reflectivity to R2. The curvatures of both cavity mirrors (the total reflector and the output coupler) can also be changed when the total cavity length is changed in order to keep the laser resonator configuration the same. Theory and operation of laser resonators can be found in many text books, handbooks, and catalogs provided by laser manufacturers. One such reference is "Lasers" by Peter Milonni and Joseph Eberly, published by John Wiley & Sons 1988. Chapter 14 entitled "Laser Resonators" describes in detail the theory and principles of the laser cavity.

Another way to set a pulse width is to take advantage of a common laser characteristic, *i.e.*, the pulse width decreases with the increase of the laser energy. So in order to achieve shallower mark depth, one can run the laser to a higher pulse energy level to obtain the needed pulse width, and then externally attenuate the beam to achieve the required energy density to get the super soft marks.

One may also exploit another common laser characteristic, *i.e.*, the pulse width increases with the repetition rate of the laser. Operating the laser at a higher repetition rate (thus, a longer pulse width), will give rise to a deeper mark depth for a given energy density.

Commercially available q-switched, diode pumped laser systems include provisions for adjusting the repetition rate. Such models are available from Lightwave Electronics and Spectra Physics. In some embodiments, the laser systems may be combined with an output attenuator to control the total energy on the surface.

Therefore, commercially available laser technology can be adapted to carry out numerous embodiments of the present invention. The laser system may be q-switched or gain switched, and various combinations thereof.

In certain embodiments various temporal laser output characteristics may be set to affect mark depth, and the total laser output energy is also to be set within an acceptable process energy window. For instance, the laser system may be operated in a "burst mode". The burst may generally be characterized with an envelope that is slowly varying with respect to a waveform or sequence of pulses within the envelope. The corresponding pulsed laser output used to form the softmark may be such a burst of pulses, and the temporal characteristic may be at least one of a burst width, burst envelope shape, burst duration, temporal spacing between bursts, a pulse width, temporal spacing between two or more pulses, temporal overlap between two or more pulses, a set delay between at least two pulses, and a pulse shape.

FIGURES 4a-4c illustrate exemplary temporal pulse characteristics that may be set in at least one embodiment of the present invention. Numerous references teach "burst mode" operation, pulse shaping, pulse stretching, pulse delay, and pulse selection. For instance, published U.S. patent application 2002/0167581 (at least Figures 15a, 15b, 15c, 18, and 19, and corresponding portions of the written specification) shows various configurations that may be used or adapted for use in embodiments of the present invention. In embodiments where multiple pulses are used to produce softmarks, a delay between pulses on the order or about ten nanoseconds or less may be best for material modification. The pulse delay or spacing may be determined based on a thermal time constant of the Silicon substrate. Published US patent application 2004/0188399, assigned to the assignee of the present invention (noted above) and various reference cited therein also generally relate to generation and manipulation of pulsed laser outputs.

In practice, the pulse temporal characteristics and energy may be set for a lot or batch wafers, without a requirement for further adjustment. Future requirements may lead to setting of the pulse characteristics for marking different depths within a field. The surface variations of the wafers lead to a requirement for "process studies" to determine the laser output energy requirement, and such variations generally determine the frequency of such measurements. Preferably, the

laser marking system includes detection and calibration hardware and software to perform any needed process studies with minimum operator intervention.

Embodiments of the present invention are typically used for “dot” formats on a first side of the wafer may be polished to a standard. Various
5 embodiments of the present invention may be integrated with the series of marking products produced by the assignee of the present invention, for instance the GSILumonics Wafermark® Sigma Clean®.

While embodiments of the invention have been illustrated and described, it is not intended that these embodiments illustrate and describe all
10 possible forms of the invention. Rather, the words used in the specification are words of description rather than limitation, and it is understood that various changes may be made without departing from the spirit and scope of the invention.

WHAT IS CLAIMED IS:

1. A laser-marking method of marking a semiconductor wafer to form a softmark on the wafer, the method comprising:
 - 5 setting a laser pulse width of one or more laser pulses to selectively provide one or more laser output pulses having one or more set pulse widths that affect the depth of a softmark that is to be formed, the mark depth to be substantially dependent on the one or more set pulse widths;
 - 10 setting a pulse energy of the one or more output pulses to selectively provide the one or more output pulses having a set total output energy that is within an acceptable process energy window for producing the softmark; and
 - 15 delivering the one or more output pulses having the one or more set pulse widths and the set total output energy into a region of the wafer such that energy density within the region, as determined by the one or more set pulse widths and the set total output energy, modifies wafer material and thereby produces the softmark having the mark depth within a predetermined range.
2. The method as claimed in claim 1, wherein the mark depth is substantially proportional to a pulse width over a substantial range of pulse widths.
3. The method as claimed in claim 1, wherein the mark depth is in the range of about 1 micron to 6 microns.
- 20 4. The method as claimed in claim 1, wherein the mark depth is predetermined and formed with exactly one output pulse.
5. The method as claimed in claim 1, wherein the mark depth is finer than about 1 micron.
- 25 6. The method as claimed in claim 1, wherein energy in a single output pulse is in a typical range of about 600 microjoules to about 1100 microjoules.

7. The method as claimed in claim 1, wherein the acceptable process energy window is centered on a central energy in a typical range having a lower limit of about 10 microjoules less than the central energy and an upper limit about 10 microjoules above the central energy.

5 8. The method as claimed in claim 1, wherein an output pulse has a typical set pulse width in the range of about 10 nanoseconds to about 200 nanoseconds.

9. The method as claimed in claim 1, wherein the step of setting the laser pulse width is performed subsequent to the step of setting the pulse energy.

10 10. The method as claimed in claim 1, wherein the step of setting the pulse energy is performed subsequent to the step of setting the laser pulse width.

11. The method as claimed in claim 1, wherein the steps of setting are performed substantially simultaneously.

12. A laser-marking system for marking a semiconductor wafer to form a softmark on the wafer, the system comprising:

15 a laser subsystem for generating one or more laser pulses;
a controller operatively connected to the laser subsystem to set:
a laser pulse width of the one or more laser pulses to selectively provide one or more laser output pulses having one or more set pulse widths that
20 affect the depth of a softmark that is to be formed, the mark depth to be substantially dependent on the one or more set pulse widths; and

a pulse energy of the one or more output pulses to selectively provide the one or more output pulses having a set total output energy that is within an acceptable process energy window for producing the softmark; and

25 a beam delivery system that includes an optical subsystem for delivering the one or more output pulses having the one or more set pulse widths and the set total output energy into a region of the wafer such that energy density within the region, as determined by the one or more set pulse widths and the set

total pulse energy, modifies wafer material and thereby produces the softmark having the mark depth within a predetermined range.

13. The system as claimed in claim 12, wherein the controller includes a subsystem of electronic components and a control program that is
5 generally used for marking system control.

14. The system as claimed in claim 12, wherein the controller includes a subsystem of electronic components and a control program that is dedicated to control of the laser subsystem.

15. A laser-marking method of forming a softmark on a
10 semiconductor wafer, the method comprising:

setting a temporal characteristic of at least a portion of a pulsed laser output that affects depth of a softmark to be formed with the laser output; and

setting total output energy of the pulsed laser output to correspond to energy within an acceptable process energy window so as to form the softmark on
15 the semiconductor wafer.

16. The method as claimed in claim 15, wherein the steps of setting are performed prior to marking a batch of wafers, and wherein the temporal characteristic and the total output energy remain set during marking of the entire batch.

17. The method as claimed in claim 15, wherein the steps of setting are performed subsequent to positioning a wafer at a marking station, and prior to marking a single wafer.
20

18. The method as claimed in claim 15, wherein the steps of setting are performed subsequent to positioning a wafer at a marking station and prior to marking a single wafer, and wherein the temporal characteristic and the
25 total output energy are varied to produce softmarks having different predetermined depths on the wafer.

19. The method as claimed in claim 15, wherein the steps of setting are performed by a laser-marking system and wherein the temporal characteristic and the total output energy are set at a manufacturing site of the laser-marking system or at a site where the laser-marking system is installed.

5 20. A laser-marking method of forming a softmark on a semiconductor wafer, the method comprising:

 setting one or more laser pulse widths of one or more laser pulses, the one or more set pulse widths affecting depth of the softmark to be formed with the one or more laser pulses; and

10 setting total output energy of the one or more laser pulses, the set total output energy corresponding to energy within an acceptable process energy window to form the softmark on the semiconductor wafer.

21. The system as claimed in claim 12 wherein the laser subsystem includes a fiber-based laser having a tunable pulse width.