



Method for producing and using storage-stable, latent-reactive layers or powders of surface-deactivated, solid polyisocyanates and dispersion polymers with functional groups.

The invention relates to a method for manufacturing and the use of storage-stable, latent-reactive layers and powders of essentially aqueous dispersions, suspensions or solutions which contain surface-deactivated polyisocyanates and isocyanate-reactive polymers.

JP 09 188, 735 describes a mixture, storage-stable at room temperature, of dispersed functional polymers with a polyisocyanate. A predispersion consisting of polyisocyanate, of polymer stabiliser and of a hydrophobic fluid (as a dispersion agent) is emulsified in a further aqueous solution or dispersion of an isocyanate-reactive polymer with the aid of an o/w emulsifier and protective colloid. After the application and the evaporation of the water the polyisocyanate reacts spontaneously under cross-linking with the functional groups of the polymer.

In DE 31 12 054, DE 32 28 723 and DE 32 28 724 powder-like, fine-particled, solid polyisocyanates with particle diameters up to 150 μ m are surface deactivated. By way of the surface coating the polyisocyanates retain their isocyanate content and their reactivity, and form a stable single component system also in water or aqueous solvents.

In DE 32 28 724 and DE 32 30 757 surface-deactivated,



powder-like diisocyanates with polyols and aqueous dispersion polymers which contain functional groups are combined to a storage-stable reactive paste. By heating this water-containing paste to 140°C, i.e. above the reaction temperature of the polyisocyanate, the two components cross-link and a slightly foamed elastic coating is obtained.

A method for manufacturing stable dispersions of fine-particled surface-deactivated isocyanate is described in DE 35 17 333. The resulting stable dispersions are suitable as cross-linking agents.

A use of the aqueous dispersions of surface-deactivated, solid, fine-particled polyisocyanates as cross-linkers in textile pigment printing pastes and liquors is disclosed in DE 35 29 530. Subsequent to the application procedure the textile pigment, printing pastes and liquors are fixed on the tissue with hot air or steam.

A disadvantage of these systems described in these documents is however that the working steps of application and curing or cross-linking may not be separated, which would appear to be desirable with a multitude of uses for economical reasons as well as logistical reasons.

Thus a substrate which carries a storage-stable, latent-reactive layer or powder would open the possibility of being deposited at the location at which the suitable apparatus are present, of being stored for a predeterminable time duration and subsequently of being transported to the location at which the processing into further intermediate products or into the end product is effected.

Storage-stable, latent-reactive masses or layers are described in WO 93/25599. These consists of isocyanate-functional polymers which have a melting point of over 40°C and of surface-deactivated polyisocyanates. For manufacturing the mixture, the components are melted on at temperatures which lie considerably above the softening point of the polymer. The expense with regard to the apparatus for the manufacture and the application of these masses, together with the energy costs are considerable. Furthermore in these systems for reasons of stability and processing only surface-deactivated polyisocyanates may be used which have a cross-linking temperature of over 80 °C. Furthermore a directed and controlled inhomogeneous mixing of the components is the subject-matter of the application. This however demands complicated working steps.

It is the object of the present invention to manufacture storage-stable, latent-reactive, largely dry layers or powder with which also deactivated polyisocyanates with reaction temperatures below 80°C may be applied, which from the point of view of environment protection behave advantageously and additionally may be inexpensively produced.

According to the invention this is achieved by the characterising part of the independent claims.

Storage-stable, latent-reactive layers or powder may accordingly be manufactured by the use of an essentially aqueous dispersion which contains at least one surface-deactivated polyisocyanate and at least one dispersed or dissolved polymer reactive with isocyanate.

Furthermore a method for the manufacture of storage-stable, latent-reactive layers or powders is the subject-matter of the invention, in which

- a) an essentially aqueous dispersion or solution of at least one polymer reactive with respect to isocyanates and
- b) at least one surface-deactivated, solid, fine-particled polyisocyanate essentially suspended in water are mixed,
- c) this mixture selectively is deposited onto a substrate in a predeterminable layer thickness and
- d) the water of the mixture is removed below the reaction temperature of the isocyanate,

so that the essentially dry and water-free layers or masses obtained by way of this, at reaction temperatures below the reaction temperature of polyisocyanate and polymer are storage-stable and latent-reactive.

Surprisingly it has been found out that the removal of the water and the drying of the mixture in the temperature region selectively may be effected at

- i) room temperature up to the softening temperature of the functional polymer or
- ii) above the softening temperature of the polymer

as long as the reaction temperature of the surface-deactivated

polyisocyanate in none of the two case is exceeded. Independently of whether the drying is effected after i) or ii) the surface-deactivated solid, fine-particled polyisocyanates after the drying are distributed or embedded unchanged and unreacted in the largely water-free polymer or in the essentially water-free layer or powder. The dispersion, suspension or solution of polymer and suspended deactivated isocyanate blends into a continuous phase of uncross-linked polymers in which the unreacted surface-deactivated, fine-particled isocyanates are suspended.

In the case i) there results a water-free, dry, latent-reactive film or a latent-reactive powder, which at room temperature or at a slightly increased temperature is capable of storage. The ability of the surface-deactivated isocyanates to react with the functional groups of the polymers remains.

In the case ii) after the vapourisation of the water there results a melted system. As an example there serves the adhering of a laminate of foils. Also in this phase the surface-deactivated isocyanates are unchanged and retain their reactivity. The adhering is based firstly on the thermoplastic properties of the polymers.

In both cases the system cross-links and it becomes unmeltable and insoluble only on exceeding the reaction temperature of the surface-deactivated isocyanate. This is effected after a predeterminable time duration.

In certain cases a short-lived exceeding of the reaction temperature is sufficient in order to trigger the cross-linking reaction. The reaction or thickening temperatures of

the deactivated polyisocyanates should with this have temperatures in the region of 30°C to 180°C, preferably lie in the region between 40°C and 150°C.

Thickening or reaction temperatures describe the temperature at which the surface-deactivating layer of the isocyanate dissolves or is destroyed in another manner. The polyisocyanate is set free and dissolved in the polymer. The end curing is effected by diffusion and reaction of the polyisocyanate with the functional groups of the polymer under a viscosity increase and cross-linking. The thickening and reaction temperature according to the type of surface-deactivated polyisocyanate lies above or below the softening temperature of the polymer.

The stability of the unreacted system, the reaction temperature and the course of the reaction are determined by the type of the polyisocyanate, by the type and the quantity of the surface stabiliser, by the solubility parameter of the functional polymer as well as by catalysers, softeners and other auxiliary means. These are largely described in the above mentioned patents.

Furthermore the processing steps of the substrate carrying the layer or the powder, subsequent to the application, are the subject-matter of the invention. These comprise steps as they are e.g. necessary for the processing of the substrate into its final form by punching, cutting, bending, folding, laminating, etc. With this furthermore it has been unexpectedly ascertained that the film or powder according to the invention may be processed in their plastic condition. Even after days and months the layer or the powder

may be heated to temperatures above the softening temperature of the polymer without there arising a reaction between the functional groups of the polymers and the surface-deactivated isocyanates. The processing in the plastic condition may with this even be effected under a frequent heating and cooling.

In a preferred embodiment form the films or powders are storage-stable, latent-reactive adhesive systems.

As polyisocyanates for the method according to the invention all diisocyanates or polyisocyanates or their mixtures are suitable as long as they have a melting point above 40°C and by way of known methods may be conveyed into powder form with particle sizes below 200 μm . They may be aliphatic, cycloaliphatic, heterocyclic or aromatic polyisocyanates. As examples there are mentioned: diphenyl methane-4,4'-diisocyanate (MDI), dimeric 4,4'-MDI, naphthalene-1,5-diisocyanate (NDI), 3,3'-dimethyl-biphenyl-4,4'-diisocyanate (TODI), dimeric 1-methyl-2,4-phenyl-4,4'-diisocyanate (TDI-U), 3,3'-diisocyanate-4,4'-dimethyl-N,N'-diphenyl urea (TDIH), addition product of 2 moles of 1-methyl-2,4-phenylene-diisocyanate with 1 mole of 1,2-ethandiol or 1,4-butandiol, addition product of 2 moles of MDI to 1 mole of diethylene glycol, the isocyanurate of isophoron diisocyanate (IPDI-T).

The mentioned addition products do not only show advantages according to the invention as aqueous dispersions. Addition products of 1-methyl-2,4-phenylene-diisocyanate and 1,4-butandiol or 1,2-ethandiol also in solid or liquid solvent-containing or solvent-free systems have very advantageous properties. They characterise themselves above

all with regard to their low curing or cross-linking temperature which lies in the temperature region below 90°C. Thus the use of this mixture whether largely based on water or polyol is very advantageous for coatings and adhesings of temperature-sensitive substrates.

The surface stabilising reaction may be carried out in various ways:

- by dispersion of the powder-like isocyanate in a solution of the deactivating agent.
- by furnishing a molten mass of a low-melting polyisocyanate into a solution of the deactivating agent in a non-dissolving liquid dispersion agent
- by adding the deactivating agent or a solution thereof, for dispersion of the solid fine-particled isocyanate.

) The solid polyisocyanates are preferably deactivated by the action of primary and secondary aliphatic amines, diamines or polyamines, hydrazine derivatives, amidines, guanidines. To have proven themselves are ethylene diamine, 1,3-propylene-diamine, diethylene triamine, triethylene tetramine, 2,5-dimethyl-piperazine, 3,3'-dimethyl-4,4'-diamino-dicycloheyl methane, methyl nonane-diamine, isophoron diamine, 4,4'-diaminodicyclohexyl methane, diamino and triamino polypropylene ether, polyamido amine, and mixures of monoamines, diamines and polyamines.

The concentration of the deactivating agent should be 0.1 to 25, preferably 0.5 to 8 equivalent percent, with respect to the total present isocyanate groups.

Often for the application according to the invention the particle size of the powder-like polyisocyanates by way of a fine dispersion or wet grinding subsequent to the synthesis must be brought to a particle size in the region of 0.5 to 20 μm . For this, dissolvers, dispersion apparatus of the rotor-stator type, stirring ball mills, bead and sand mills, ball mills and friction gap mills are suitable, at temperatures below 40°C. According to the polyisocyanate and the use, the comminution is effected on the deactivated polyisocyanate, in the presence of the deactivating agent, in the non-reactive dispersion agent or water with a subsequent deactivation. The ground and surface-stabilised polyisocyanate may also be separated from the grinding dispersions and dried.

In order to control the surface deactivation and the cross-linking reaction, also catalysers may be added. Preferred are those catalysers which in aqueous solution or dispersion are hydrolysis-stable and then later also accelerate the heat-activated reaction. Examples for urethane catalysers are organic tin, iron, lead, cobalt, bismuth, antimony and zinc compounds or their mixtures. Alkylmercaptide compounds of dibutyl tin are preferred on account of the higher hydrolysis stability.

Tertiary amines such as dimeythylbenzyl amine, diazabicyclo-undecen, as well as non-volatile polyurethane foam catalysers based on tertiary amine may be used for special purposes or in combination with metal catalysers, the

catalytic activity may however be restricted by conversion with the carbon dioxide of the air.

The concentration of the catalysers lies in the region of 0.001 to 3%, preferably 0.01 % to 1 % with respect to the reactive system.

As a reaction partner, according to the invention, of the polyisocyanate, there are considered water-soluble or water-dispersable emulsion polymers or dispersion polymers, which carry isocyanate-reactive functional groups. These are manufactured according to the state of the art by polymerisation of olefinic unsaturated monomers in solution, emulsion or suspension. The film-forming polymerisates contain 0.2 to 15%, preferably 1 to 8 % polymerised-in monomer with isocyanate-reactive groups such as hydroxyl, amino, carboxyl and carbon amide groups.

Examples of functional monomers are: allyl alcohol, hydroxyethyl or hydroxypropyl acrylate and methacrylate, butandiol monoacrylate and methacrylate, ethoxylated or propoxylated acrylates or methacrylates, N-methylol-acrylamide, tert. butylamino-ethyl-methacrylate, acrylic and methacrylic acid, maleic acid, maleic acid monoester. Also glycidyl methacrylate and allylglycidyl ether may be copolymerised. These contain an epoxy group which in a further step with amines or amine alcohols are derivatised to the secondary amine, for example with ethyl amine, ethyl hexylamine, isononyl amine, aniline, toluidine, xylidine, benzyl amine, ethanol amine, 3-amino-1-propanol, 1-amino-2-propanol, 5-amino-1-pentanol, 6-amino-1-hexanol, 2-(2-aminoethoxy) ethanol, also copolymerised acetylacetoxy ethyl

methacrylate and acrylate may take part in addition reactions with the mentioned primary amines. The conversion with primary amines increases the reactivity of the functional groups of the polymers with respect to the isocyanate groups at the expense of the side-reaction with water.

Suitable are also water-soluble hydroxyfunctional binders such as polyvinyl alcohol, part saponified polyvinyl acetate, hydroxyethyl cellulose, hydroxypropyl cellulose as well as water-dispersable hydroxy-functional polyester, hydroxy-functional sulfopolyester and polyurethane dispersions, dispersions of polyamido amines which carry carboxyl, hydroxyl, primary or secondary amino groups. Likewise aqueous colloidal dispersions or colloidal solutions with particle sizes between 1 - 100 nm may be manufactured in colloid mills, proceeding from thermoplastic polymers with isocyanate-reactive groups. Examples are higher molecular solid epoxy resins, polyethylene vinyl alcohol and polyethylene co-acrylic acid.

The ratio between the isocyanate groups in the surface-stabilised fine-particled polyisocyanates and the sum of the hydroxyl and amino groups of the polymers in the largely water-free and solid condition should be in the range of 0.1 to 1.5.

Into the resulting highly viscous paste or low viscosity mixture there may be mixed or dispersed inert or functional additions. To the functional additions there belongs hydroxyl functional or amino functional powder-like or liquid, low to high molecular compounds which may react with the solid polyisocyanates above the reaction temperature. The stoichiometric ratios are to be correspondingly adapted. Low

molecular compounds are to be understood as compounds with molecular weights between 40 and 500 g/mole, and high molecular compounds as those whose molecular weights lie between 5000 and 10000 g/mol. As examples there may be cited: low molecular to high molecular liquid polyols or/and polyamines, solid polyfunctional polyols or/and aromatic polyamines. Examples are triethanol amine, butandiol, trimethylol propane, ethoxylated bisphenol A, terminally ethoxylated polypropylene glycols, 3,5-diethyl-toluylene-2,4- and 2-6-diamine, poly-tetramethyl oxide-di-(p-aminobenzoate), tris-hydroxyethyl-isocyanurate, hydroquinone-bis-hydroxyethyl ether, pentaerythrite, 4,4'-diamino-benzanilide, 4,4'-methylene-bis-(2,6-diethyl aniline).

To the inert additions there belongs for example surface-active agents, organic or anorganic thickening agents, softeners, fillers, plastic powder, pigments, colours, light stabilisers, ageing stabilisers, biocides, defoaming agents, corrosion protection agents, flame proofing agents, sponging agents, adhering resins, organo-functional silanes, short cut fibres and where appropriate small quantities of inert solvents.

The advantages of the present invention lie in the separation of the application of the aqueous dispersion from the cross-linking reaction, i.e. the final curing. Thus e.g. at one location adhesive films may be deposited onto wood, glass or other types of substrates or underlays at one location, these premanufactured fabrications may be stored or transported and be cured to the end product at another location.

A further advantage of the method according to the invention and the use of the corresponding products lies in the use of water as a dispersion medium. The energy consumption for manufacturing the dispersions is small. The component part of organic solvent is minimal which results in a processing which is very advantageous for the environment.

If one proceeds from an aqueous polymer dispersion a further advantage lies in the fact that also surface-deactivated polyisocyanates with a melting point in the region of 40 to 150 °C may be worked in without any problem. The cross-linking temperatures may lie in the region of 35 °C to 90 °C. With these low cross-linking temperatures also temperature-sensitive substrates may be adhered to this one-component system by the heat effect.

The layer or powder obtained from the aqueous suspension, dispersion or solution may be stored for months. According to the dissolving properties of the solid film for the polyisocyanate, the storage duration at room temperature or slightly increased temperatures is however different. The storage duration of the system according to the invention in the water-free and uncross-linked condition is at least 3 times, usually more than 10 times that of the same mixture with the same polyisocyanates which are not surface-deactivated. At +2 °C the layers or powder according to the invention are storage-stable for at least six months, at room temperature however at least 1 month storage-stable and according to the invention are capable of being processed. The term latent-reactive describes the condition of the essentially water-free layer or powder in which the surface-deactivated polyisocyanate and the polymer reactive with

isocyanates are present in the essentially uncross-linked condition.

The heat supply for the thermoplastic processing as well as the cross-linking may preferably be effected with convection or irradiation heat. The storage-stable aqueous suspension, dispersion or solution of surface-deactivated fine-particled polyisocyanates and dispersed or water-soluble polymers with isocyanate groups may be applied to the surface of the substrate to be adhered or coated, in particular by brushing, spraying, injecting, doctoring, pasting, casting, submersing, extruding or by roller depositing or with the printing method.

In the case of the adhering of substrates one may selectively proceed as follows:

1. Press adhering by joining the adhering surfaces at room temperature and increasing the temperature up to over the softening temperature of the polymer, but below the reaction temperature, then cooling to room temperature. There arises a compound which is latent-reactive. This compound may be processed further and formed also in the plastic or thermoplastic region of the polymer. The adhering obtains the final cross-linked condition when the temperature is increased to above the thickening or reaction temperature.

2. Press adhering by joining the adhering surfaces at room temperature and increasing the temperature up to over the softening temperature of the polymer, forming a homogeneous adhesive film which covers and adheres the counter-surface, increasing the temperature until above the thickening or

reaction temperature and final cross-linking.

3. The coated adhesive surface is brought into the thermoplastic condition by increasing the temperature until over the softening temperature of the polymer, is joined to a second substrate and under pressing, the temperature is increased up to above the thickening or reaction temperature. Where appropriate in the thermoplastic condition of the system further processing steps may be carried out.

In a second embodiment form of the method the storage-stable, aqueous dispersion of surface-deactivated, fine-particled polyisocyanates and dispersed or water-soluble polymers with isocyanate-reactive groups is brought into the form of a latent-reactive adhesive film, adhesive tape, adhesive fleece or tissue which may build up adhesion on both sides. For manufacturing substrate-free forms, such as films or tapes, the dispersion according to the invention is applied onto a non-adhesing substrate tape or separating paper and the water at room temperature or at room temperatures up to the softening point of the polymer is volatilised. The adhesive film may after cooling be released from the substrate and up to its use may be stored free of substrate. Alternatively the adhesive film may be stored together with the substrate paper.

In the case of the adhesive fleeces or tissue the reaction-capable dispersion is applied by spraying, injecting, doctoring, casting, submersing, padding, by roller application or with the printing method, the water at room temperature or at temperatures up to the softening temperature of the polymer is volatilised, and the adhesive fleece or tissue, provided or impregnated with the latent heat-reactive adhesive layer, is

stored up to its use.

The substrate-free adhesive films, adhesive tapes, adhesive fleeces or tissue serve as an adhesive layer between substrates. It is also possible to deposit or sinter adhesive films, fleeces or tissues on one side onto a substrate surface in the plastic condition. This laminate may up to the final adhering to a second substrate surface be stored at room temperature.

In a third embodiment form of the method the storage-stable, aqueous dispersion of surface-deactivated, fine-particled polyisocyanates and dispersed or water-soluble polymers with isocyanate-reactive groups is brought into the form of a latent-reactive powder. These powders may be used as latent-reactive adhesives or for coating purposes, such as powder varnish.

For manufacturing powders from the dispersions according to the invention these may be sprayed in a spraying tower, the temperature of the air introduced from below should remain below the softening temperature of the polymer and the reaction temperature of the surface-blocked polyisocyanate.

Alternatively the dispersions according to the invention may be sprayed onto the non-adhesing surface of a revolving tape with adhesive surfaces or be applied with a printing method. After the volatilisation of the water the dry particles are scraped from the tape, where appropriate sieved or graded, and stored until use.

Latent reactive powders may also be manufactured of

substrate-free films or tapes by grinding processes, where appropriate at low temperatures. They serve as heat-reactive, cross-linkable adhesive powder or as coating powder. Application apparatus and methods belong to the state of the art and are known to the man skilled in the art.

The latent-reactive premanufactured layers manufactured according to the invention preferably serve as a thermally burdenable adhesive connection for flexible or solid substrates such as metals, plastics, glass, wood, wood compound material, cardboard, foils, synthetic surface webs, textiles.

The reactive coating powder manufactured according to the invention may also be processed with the application methods for powder lacquers. The cross-linking temperature may be so low, according to the selection of the polyisocyanate, that heat-sensitive substrates, such as plastics, textiles and wood may be coated without thermal damage.

) The method permits also the coating powder on the substrate to only be sintered or melted to a closed layer. The complete cross-linking is effected then with a later heat treatment, where appropriate after an additional mechanical or thermal processing step.

Examples

A) Application and testing method, storages:

Storage A Application of dispersions at room temperature,
extensive removal of the water by vapourisation at

room temperature and/or penetration into the underlay, after max. 3 hours joining the adhesive surfaces, storage under normal conditions for minimally 7 days, then for 0.5 hours heating to 120 °C (object temperature), wherein the cross-linking reaction is triggered. Cooling and storage for 24 hours under normal conditions.

Storage B As storage A, but without heat treatment.

Storage C Depositing onto adhesive surface, extensive removal of the water by vapourisation at room temperature and/or penetration into the underlay. Letting the surface provided with the adhesive layer dry for at least 30 days open to the air. Joining the adhesive surfaces and under clamping pressure, heating to 120°C for 0.5 hrs, wherein the cross-linking reaction is triggered. Cooling and storage for 24 hrs under normal conditions.

) Storage D Storing the fluid dispersion for 30 days at room temperature then applying to the adhesive surface. Further as with the storage A or C.

Testing the temperature stability or heat stability of the adhesings: test pieces with 100x20x5 mm³ of beech wood or 25x100xd mm³ of synthetic material were simply press adhered in an overlapping manner, overlapping 10 mm, adhesive surface 20x10 mm². In order with the hot-adhesing to exclude as much as possible of the side reactions of water with isocyanates the wood test-pieces were heated in a circulation oven under a vacuum (residual pressure 0.1 bar) for 0.5 hours to 120°C.

For determining the heat stability after storages A and C the test-pieces were hung perpendicularly in the circulation oven and loaded on one side with 3000 g. The temperature was increased by 10 °C every 15 minutes. Stability losses of the adhesions led to the falling of the weights. The upper testing temperature was limited to 150 °C.

Determining the water resistance: storage of test pieces in water at normal temperature for 4 days. Qualitative assessment of the strength in the wet condition.

The following are:

high and practically unchanged stability of the adhesing	+
noticable fall in stability	+/-
Loss in stability or falling apart of the adhesing	-

Deviating or other test conditions or tests are indicated in each case.

Abbreviation SDSI: surface deactivate solid isocyanate

B) Manufacture of the aqueous suspension from solid surface-deactivated polyisocyanate: general regulation

With the dissolver the following suspensions of surface-deactivated polyisocyanates were manufactured:

	parts by weight
(1) water	106
(2) Kelzan S, 3% solution in water (Mosanto)	33
(3) polyoxyethylene sorbite antriolate	1
(4) polyamine	2-6
(5) polyisocyanate powder, particle size < 45 μ m	80
	222 - 226

(4) polyamine

Euretek 505 (Witco) polyamido amine

Jeffamine T-403 (Huntsman) aminoterminated

polyoxy propylene

Specific examples	21		
	grams per equivalent	grams of originally weighted in quantity	% isocyanate groups deactivated

Example 1

(1) (2) (3) components as
above

(4) polyamido amine	144	2.3	5.0
---------------------	-----	-----	-----

Euretek 505

(5) IPDI-isocyanurate	243	80	
-----------------------	-----	----	--

(IPDI-T)

polyisocyanate IPDI-T

1890/100 Huels

Example 2

(1) (2) (3) components
as above

(4) Jeffamine T-403	143	6	
---------------------	-----	---	--

(Huntsman)

(5) 4,4-diphenyl methane	125	80	6.6
--------------------------	-----	----	-----

diisocyanate (MDI)

The surface-deactivated MDI by way of half an hour of grinding this suspension in a cooled open bead mill (glass beads 1 mm, 2500 revolutions per minute) was reduced in size to an average particle size of 15 μ m.

22

grams per equivalent	grams of originally weighted in quantity	% isocyanate groups deactivated
-------------------------	---	--

Example 3

(1) (2) (3) components
as above

(4) polyamido amine Euretek 505	144	3.7	5.0
------------------------------------	-----	-----	-----

(5) 3,3'-dimethyl-biphenyl- 4,4'-diisocyanate (TODI)	132	80	
---	-----	----	--

Example 4

(1) (2) (3) components
as above

(4) polyamido amine Euretek 505 or	144	3.3	5.0
---------------------------------------	-----	-----	-----

Jeffamine T-403

(5) dimeric 1-methyl-2,4- phenylene diisocyanate (TDI-U)	174	80	
--	-----	----	--

Example 5

(1) (2) (3) components
as above

(4) polyamido amine Euretek 505	144	3.3	5.8
------------------------------------	-----	-----	-----

(5) urethane of 2 moles of 1-methyl-2,4-phenylene and 1 mol of 1,2-ethylene glycol (TDI _x EG)	205	80	
---	-----	----	--

23

grams per equivalent	grams of originally weighted in quantity	% isocyanate groups deactivated
-------------------------	---	--

Example 6

(1)(2)(3) components as
above

(4) polyamido amine	144	3.3	6.3
---------------------	-----	-----	-----

Euretek 505

(5) urethane of 2 mols of 1-methyl-2,4-phenylene and 1 mol of 1,4 butandiol (TDIxBDO)	219	80	
--	-----	----	--

Comparative example 7

(5) Desmodur DA	215	trimerised hexa- methylene diisocyanate emulsifiable approx. 19.5% NCO	
-----------------	-----	--	--

C Application and testing the reactive adhesive dispersions

Used adhesive dispersions:

Jagotex KEM, Ernst Jaeger GmbH, D-Duesseldorf:

Vinyl acetate-(meth)acrylate dispersion, with hydroxyl groups in polymer and in protective colloid, 55% solid matter, contact adhesive with activation temperature 60 - 80 °C. Neutralised with ammonia.

Dispercoll U 54, Bayer AG D-Leverkusen:

PUR-dispersion, aliphatic isocyanate, 50% solid matter, with isocyanate-reactive groups.

Manufacture of the adhesive dispersions. General regulation:

With the dissolver a reactive dispersion adhesive was manufactured with the specified polyisocyanates as follows:

25

parts by weight part by weight
per 100 polymer

(1) adhesive dispersion, approx. 50% solid matter	100	
(2) suspension of de- activated polyisocyanate approx. 35%	16	approx. 11.2
(3) metatine catalyser 715; base dibutyltinalkylmercaptide (Acima AG, CH-Buchs)	1	approx. 0.2
10% diethylene glycol- dimetheylene ether	117	

The adhesive mixtures were deposited onto the adhesive surfaces of beech wood test pieces with a spiral doctor blade, then treated according to storages A - C, then tested as specified. The deposition weight was after the drying about 100g/m².

Examples 8 to 12

Cross-linking tests with adhesives based on KEM 2010 (neutralised) and various suspensions of polyisocyanates

	Comparative Example 8	Comparative Example 9	Example 10	Example 11	Example 12
	without SDSI	Desmodur DA (obs. 2)	IPDI-T Susp.	MDI Susp.	TODI Susp.
dispersion adhesive with SDSI suspension (obs. 1)			according to Example 1	according to Example 2	according to Example 3
Storage A:					
30 min/120 °C					
heat stability °C	85	> 150	> 150	> 150	> 150
water storage	--	--	--	+	+
Storage B:					
normal conditions					
heat stability °C	55	> 130	55	55	55
water storage	--	--	*	*	*

27

	Comparative Example 8	Comparative Example 9	Example 10	Example 11	Example 12
Storage C:					
1 month open, joining, then 30 min/120 °C					
heat stability °C	55	no contact	> 150	> 150	> 150
water storage	--	adhesing	+/-	+	+
dispersion adhesive with SDSI-suspension (obs. 1)	without SDSI	Desmodur DA (obs. 2)	IPDI-T Susp. according to Example 1	MDI Susp. according to Example 2	TODI Susp. according to Example 3
Storage D:					
1 month fluid at normal conditions, then storage A					
heat stability °C	*	85	*	> 150	*
water storage	*	--	*	+	*
* not tested					

- obs. 1: SDSI approx 11.2 parts per 100 parts solid polymer
 obs. 2: 13 parts Desmodur DA per 100 parts solid polymer

Examples 13 to 16:

Cross-linking tests with adhesives based on KEM 2010 (neutralised) and various suspensions of polyisocyanates

	Example 13	Example 14	Example 15	Example 16
dispersion adhesive	TDI-U	TDI _x EG	TDI _x EG	TDI _x BDO
with SDSI suspensions	Susp. according	Susp. according	Susp. according	Susp. according
(obs. 1)	to Example 4	to Example 5	to Example 5	to Example 6
			one-sided	
			depositing	

Storage A:

30 min/120 °C

heat stability °C

water storage

> 150	> 150	> 150
+	+	+

29

Example 13 Example 14 Example 15 Example 16

Storage B:

normal conditions

heat stability °C

water storage

50

*

55

*

*

*

Storage C:

1 month open, joining, then

30 min/120 °C

heat stability °C

> 150

> 150

> 150

Storage D:

1 month fluid at normal

conditions,

then storage A

heat stability °C

water storage

*

> 150

+

*

*

*

*

* not tested

obs. 1: SDSI approx 11.2 parts per 100 parts solid polymer

Examples 17 to 21:

Cross-linking tests with adhesives based on polyurethane dispersion Dispercoll U 54 and various suspensions of polyisocyanates

	Comparative Example 17	Comparative Example 18	Example 19	Example 20	Example 21
dispersion adhesive	without	Desmodur DA	IPDI-T	TDI	TDI _x EG
with SDSI suspensions	SDSI	(obs. 2)	Susp.	Susp.	Susp.
(obs. 1)			according to Example	according to Example	according to Example
			1	4	5
Storage A:					
30 min/120 °C					
heat stability °C	120	> 150	> 150	> 150	> 150
water storage	+/-	+	+	+	+
Storage B:					
normal conditions					
heat stability °C	100	> 150	*	*	*
water storage	+/-	+	*	*	*

31

Comparative	Comparative	Example 19	Example 20	Example 21
Example 17	Example 18			

Storage C:

1 month open, joining, then

30 min/120 °C

no contact

heat stability °C

120

adhesing

> 150

> 150

> 150

* not tested

obs. 1: SDSI approx 11.2 parts per 100 parts solid polymer

obs. 2: 13 parts Desmodur DA per 100 parts solid polymer

Examples 22 to 24:**Manufacturing a thermoreactive adhesive fleece**

The adhesive dispersions were deposited with a spiral doctor blade onto textile fleeces of polyethylene terephthalate (Lutradur 7225, surface weight 25 g/m², Freudenberg KG, D-Weinheim). The fleeces in the fresh condition are separated from the underlay and dried hanging perpendicularly under normal conditions.

After a 10 day storage duration the dry fleeces between two beech woods of 5 mm thickness under a mechanical pressure of 2 kp/m² were heated for 30 minutes to 120 °C (press adhering). The bond was subsequently stored for 24 hours without pressure at normal conditions. The following properties were determined of the test pieces:

	Example 22	Example 23	Example 24
Adhesive according to example	13	13	16
with polymer	KEM 2010	KEM 2010	KEM 2010
SDSI short description	TDI-U	TDI-U	TDIxBDO
deposition weight dry, g/m ²	88	25	34
heat stability of the adhesive joints °C	>150	>150	>150

Example 25:

Example 22 was repeated analogously, wherein textile fleeces were done away with. There arose on silicone paper a complete substrate-free, solid adhesive layer which after separation from the silicone paper and press-adhesing was cross-linked at 120 °C. With a testing of the heat stability it showed the values analogous to Example 22.

Example 26:**Adhesing of glass-fibre-reinforced polyester test pieces**

The reactive adhesive dispersion according to Example 14 was applied onto test pieces with the dimensions 100x25x3 mm³, dry weight approx. 100 g/m². After volatisation of the water the test pieces were stored for 3 days at normal conditions. The coated surface was heated to 80 °C (this means just over the softening point of the polymer) and a simple overlapping press adhesing, adhesive surface 200 mm², was produced. Immediately the temperature was increased to 120 °C and kept for 30 minutes. At this temperature the cross-linking was effected. Subsequently storage for 24 hours under normal conditions.

There were evaluated

- tensile shear strength (100 mm
per minute tensile speed): 2.21 MPa
- heat stability > 150°C

Example 27:

An adhesive composition was manufactured analogously to Example 13 and the aqueous dispersion deposited at room temperature. The removal of the water was effected by vapourisation at room temperature and/or penetration into the underlay. The solid layer was left lying open over a period of time of 5 months at + 2°C. The adhesive surfaces were thereafter joined together and under clamping pressure heated to 120 °C for 0.5 hours, wherein the cross-linking reaction was triggered. Subsequently there was effected a 24 hour storage at room temperature. The results with regard to heat stability and water storage corresponded to those in Example 13.

Example 28:

Manufacture, application and storage effected analogously to Example 26. Thereafter the whole system consisting of the underlay and solid adhesive layer was heated three times to 80°C over the softening point of the polymer and again cooled. Subsequently there was effected the curing by way of heating for half an hour to 120 °C. The results with regard to heat stability and water storage corresponded to those in Example 13.

Example 29:

An aqueous dispersion which corresponded to the composition of Example 13 was conveyed by way of spray drying into a solid largely water-free powder. The application, storage and cross-linking was effected analogously to Storage C. The results with regard to heat stability and water storage corresponded to those in Example 13.

(Annex to the International Preliminary Examination Report)

Claims

1. The use of an essentially aqueous dispersion which contains at least one solid surface-deactivated polyisocyanate and at least one polymer reactive with isocyanate, for manufacturing storage-stable, latent-reactive layers or powders.
2. The use of the dispersion according to claim 1, characterised in that the deactivated polyisocyanates have reaction temperatures in the region of 30 °C to 180 °C, preferably reaction temperatures between 40 °C and 150 °C.
3. The use of the dispersion according to claim 1 and 2, characterised in that the deactivated polyisocyanates have melting points in the region of 40 °C to 150 °C.
4. The use of the dispersion according to one of the preceding claims, characterised in that the polymer reactive with isocyanate is a copolymerisate of glycidyl methacrylate, allyl glycidyl ether or acetylacetoxyethyl (methy) acrylate with olefinic unsaturated monomers, said copolymerisate being modified with aliphatic, cycloaliphatic, aromatic monoamines or amino alcohols.
5. The use of the dispersion according to one of the preceding claims, characterised in that the ratio between the isocyanate groups of the surface-deactivated

polyisocyanate and the hydroxyl and amino groups of the polymers in the largely water-free, solid condition lies in the region of 0.1 and 1.5.

6. The use of a dispersion, according to one of the preceding claims, characterised in that additionally yet inert and functional additions such as hydroxy or amino functional powder-like or liquid, low to high molecular compounds, stabilisers, surface-active agents, corrosion protection agents, flame-protection agents, thickening agents, fillers and pigments are contained therein.
7. The use of the dispersion according to one of the preceding claims, characterised in that the polymer reactive with isocyanates is an anionic or cationic aqueous dispersion of polyurethane or polyurea, which carries carboxyl, hydroxyl, primary or secondary amino groups.
8. The use of the layers arising from the dispersion, according to one of the preceding claims, characterised in that the surface-deactivated polyisocyanate with the polymer, after the course of a predeterminable storage time at temperatures above the reaction temperature of the polyisocyanate cross-links and cures.
9. The use of the dispersion according to one of the preceding claims, characterised in that the layer produced therewith or the powder produced therewith at +2 °C is storage-stable and capable of reaction for at least six months.

10. The use of the dispersion according to one of the preceding claims as adhesive.
11. A method for manufacturing storage-stable, latent-reactive layers, with which at least one deactivated polyisocyanate suspended essentially in water is mixed with an essentially aqueous dispersion or solution of at least one polymer reactive with respect to isocyanates and this dispersion is deposited onto a substrate in a predeterminable layer thickness, characterised in that the water is removed at a temperature below the reaction temperature of the isocyanate, so that the essentially dry and solid layers obtained by way of this are storage-stable and latent-reactive at temperatures below the reaction temperature of the polyisocyanate and polymers.
12. A method for manufacturing storage-stable, latent-reactive powders, with which at least one deactivated polyisocyanate dispersed essentially in water is mixed with an essentially aqueous dispersion or solution of at least one polymer reactive with respect to isocyanates, characterised in that the water subsequently is removed below the reaction temperature of the isocyanate and the essentially dry and solid masses obtained by way of this are processed further to powders at temperatures below the reaction temperatures of the polyisocyanate and in particular deposited onto substrates so that the thus obtained powder at temperatures below the reaction

temperature of the polyisocyanate and polymers remain storage-stable and latent-reactive.

13. A method according to claim 11 or 12, characterised in that after a predeterminable time period the polyisocyanate with the polymer at temperatures above the reaction temperature of the polyisocyanate cross-links and cures.
14. A method according to one of claims 11 or 12, characterised in that the water is removed at temperatures above the softening temperature of the polymer.
15. A method according to claim 11 or 12, characterised in that the substrate carrying the layer or powder is processed in further method steps, in particular is brought into a predetermined form.
16. A method according to claim 11, characterised in that the essentially solid layer is dried on a first substrate, thereafter is separated from this substrate and after a predeterminable time duration is deposited onto another substrate and cross-linked.
17. A method according to claim 11 or 12, characterised in that the processing comprises a heating several times to temperatures above the softening temperature of the polymer and below the reaction temperature of the polyisocyanate.

18. A method according to claim 12, characterised in that the powder is obtained by spray-drying.
19. A layer containing deactivated polyisocyanate and at least one polymer reactive with polyisocyanate, characterised in that the layer is produced as an aqueous suspension and in the dry and solid condition is storage-stable and latent-reactive.
20. The use of a mixture containing a reaction product of 2 moles of +1-methyl-2,4-phenylene-diisocyanate and 1 mole of 1,4-butandiol or 1,2-ethandiol or of 2 moles of 4,4'-diphenyl methane diisocynate and 1 mole of diethylene glycol for manufacturing storage-stable layers or powders with a cross-linking temperature below 90°C.