CLAIMS

1. A thermoformable polymeric film comprising a polymeric layer, the polymeric layer comprising:

   at least 50% polypropylene by weight, wherein the polypropylene comprises impact polypropylene and wherein the layer comprises at least 5% impact polypropylene by weight;

   at least 5% tackifier by weight; and

   from 0.1% to 5% crosslinker by weight.

2. The film of claim 1, wherein the polymeric layer comprises from 1% to 3% of the crosslinker by weight.

3. The film of claim 1, wherein the polymeric layer comprises from 1.5% to 2.5% of the crosslinker by weight.

4. The film of claim 1, wherein the crosslinker comprises an ionic crosslinker.

5. The film of claim 1, wherein the polymeric layer comprises from 5% to 40% tackifier by weight.

6. The film of claim 1, wherein the polymeric layer comprises from 5% to 50% impact polypropylene by weight.

7. The film of claim 1, wherein the polymeric layer comprises at least 60% polypropylene by weight.

8. The film of claim 1, wherein the film consists of or consists essentially of the polymeric layer.

9. The film of claim 8, further comprising a second layer comprising polypropylene.

10. The film of claim 9, wherein the second layer comprises at least 80% polypropylene by weight.

11. The film of claim 9, further comprising a third layer comprising polypropylene.

12. The film of claim 11, wherein the third layer comprises at least 80% polypropylene by weight.

13. The film of claim 11, wherein the polymeric layer is between the second layer and the third layer.

14. The film of claim 1, wherein the film has a thermoform temperature window of 5 degrees Celsius or greater.

15. A package comprising the film of claim 1.