

Description

The present invention relates to lubricating oil concentrates of soluble novel multifunctional viscosity index improvers having dispersancy properties.

5 Polymers prepared from alpha-olefins using Ziegler catalysts have found acceptance for use in a wide range of applications including elastomers, fibers and films. Inasmuch as the polymers are essentially nonpolar, however, they have a characteristic inertness which makes them difficult to surface treat, for example, by dyeing or metallizing techniques. Additionally, they are limited in the amount of additives, such as stabilizers and plasticizers which they can accommodate without "blooming". Similar limitations are
10 found in the rubbery copolymers and terpolymers produced from alpha-olefins.

In an attempt to overcome these disadvantages, efforts have been made to introduce polar functional groups into such polyolefins, both homo and copolymers. Previous efforts in this direction have included both the direct incorporation of functionalized monomers during the polymerization process as well as post-polymerization functionalization of polymers.

15 US-A-3404091 discloses the use of polyolefin polymers containing functional groups such as nitrile, ester and carbonamide groups as viscosity index improvers in lubricants.

European Patent Application No. 295,076 relates to polyolefins incorporating carboxyl, hydroxyl, thio, amino, carbonyl and imino functional groups, masked functional group-containing monomers and methods for preparing the same, by reacting the functional group containing monomers with non-halogenated
20 organometallic compounds to form masked, functional-group containing monomers, and polymerizing polymer chain monomers with the masked monomers to produce a polymer chain. The polyolefins are disclosed for use as elastomers, fibres and films.

The novel composition of this invention comprise (A) lubricating oil, and (B) at least one amino-substituted interpolmer (e.g., an ethylene alpha-olefin interpolmer) substituted by primary amino or
25 secondary amino groups useful as viscosity index improver-dispersant. Such amino-substituted interpolymers can be prepared by co-polymerizing ethylene (and, optionally, an alpha-olefin) with a masked nitrogen-containing monomer where the primary or secondary nitrogen group of the nitrogen-containing monomer is masked with an organometallic compound (preferably, a non-halogenated organometallic compounds), followed by deashing the resulting interpolmer to remove the organometallic compound and
30 thereby form the amino-substituted interpolmer. Preferred amino-substituted interpolymers comprise amino-substituted ethylene propylene norbornene terpolymers.

Preparation of the Amino-Substituted Interpolymer

35 The amino-substituted polymers used in this invention can comprise amino-substituted interpolymers which can be prepared by the direct incorporation of masked, nitrogen-containing monomers (MNCM) into homopolymers and copolymers, such as polyolefins and particularly ethylene-propylene copolymers (EPM), to form copolymers, terpolymers and tetrapolymers containing the MNCM. The nitrogen-containing monomer (NCM) is an unsaturated compound which is copolymerizable with polymer chain monomers (PCM),
40 viz. olefins such as ethylene and propylene (described in more detail below), using a Ziegler catalyst. The nitrogen-containing monomer is preferably masked in a reaction with non-halogenated metallic compounds under controlled conditions and is then contacted with polymer chain monomers for production of the amino-substituted interpolmer. The amino-substituted polymers preferably comprise polymer chains exhibiting a generally uniform distribution of amino functionality and a low halogen content and are essentially
45 devoid of organic halides.

Polymer Chain Monomers

50 The term polymer chain monomer (PCM) as used in the specification and claims includes conventional monomers normally used in the production of polymers. The polymer chain monomers used in the method for forming an amino-substituted interpolmer in accordance with the present invention are preferably selected from a group consisting of ethylene and C₃-C₂₅ alpha-olefins. The alpha-olefins suitable for use may be branched or straight chained, cyclic, and aromatic substituted or unsubstituted, and are preferably C₃-C₁₆ alpha-olefins. Mixed olefins can be used (e.g., mixed butenes).

55 The alpha-olefins, when substituted, should not be aromatic substituted on the 2-carbon position (e.g., moieties such as CH₂=CH-Ø- should not be employed), since such an aromatic group interferes with the subsequent desired polymerization. Illustrative of such substituted alpha-olefins are compounds of the formula H₂C=CH-C_bH_{2b}-T wherein "b" is an integer from 1 to 20 carbon atoms (preferably to 10 carbon

atoms), and T comprises aryl, alkaryl, or cycloalkyl. Exemplary of such T substituents are aryl of 6 to 10 carbon atoms (e.g., phenyl, naphthyl and the like), cycloalkyl of 3 to 12 carbon atoms (e.g., cyclopropyl, cyclobutyl, cyclohexyl, cyclooctyl, cyclodecyl, cyclododecyl, and the like), alkaryl of 7 to 15 carbon atoms (e.g., tolyl, xylyl, ethylphenyl, diethylphenyl, ethyl-naphthyl, and the like). Also useful are alpha-olefins substituted by one or more such X substituents wherein the substituent(s) are attached to a non-terminal carbon atom, with the proviso that the carbon atom so substituted is not in the 1- or 2-carbon position in the olefin, in addition to alkyl-substituted bicyclic and bridged alpha-olefins of which C₁-C₃ alkylsubstituted norbornenes are preferred (e.g., 5-methyl-2-norbornene, 5-ethyl-2-norbornene, 5-(2'-ethylhexyl)-2-norbornene, and the like).

Illustrative non-limiting examples of preferred alpha-olefins are propylene, 1-butene, 1-pentene, 1-hexene, 1-octene, and 1-dodecene. The alpha-olefin is generally incorporated into the amino-substituted interpolpolymer in an amount of about 10 to about 90 wt%, more preferably at about 20 to about 70 wt%. The amino-substituted interpolpolymer may optionally contain a third type of polymer chain monomer which is an easily polymerizable non-conjugated diene. Non-conjugated dienes suitable for purposes of the present invention can be straight chain, hydrocarbon di-olefins or cycloalkenyl-substituted alkenes, having about 6 to about 15 carbon atoms, for example:

- A. straight chain acyclic dienes, such as 1,4-hexadiene and 1,6-octadiene;
- B. branched chain acyclic dienes, such as 5-methyl-1, 4-hexadiene; 3,7-dimethyl-1,6-octadiene; 3,7-dimethyl-1,7-octadiene; and the mixed isomers of dihydro-myrcene and dihydro-ocinene;
- C. single ring alicyclic dienes, such as 1,3-cyclopentadiene; 1,4-cyclohexadiene; 1,5-cyclo-octadiene and 1,5-cyclododecadiene;
- D. multi-ring alicyclic fused and bridged ring dienes, such as tetrahydroindene; methyl-tetrahydroindene; dicyclopentadiene; bicyclo-(2.2.1)-hepta-2,5-diene; alkenyl, alkylidene, cycloalkenyl and cycloalkylidene norbornenes, such as 5-methylene-2-norbornene (MNB), 5-propenyl-2-norbornene, 5-isopropylidene-2-norbornene, 5-(4-cyclo pentenyl)-2-norbornene, 5-cyclohexylidene-2-norbornene, and 5-vinyl-2-norbornene;
- E. cycloalkenyl-substituted alkenes, such as allyl cyclohexene, vinyl cyclooctene, allyl cyclodecene, vinyl cyclododecene.

Of the non-conjugated dienes typically used, the preferred dienes are dicyclopentadiene, 1,4-hexadiene, 5-methylene-2-norbornene, and 5-ethylidene-2-norbornene. Particularly preferred diolefins are 5-ethylidene-2-norbornene (ENB) and 1,4-hexadiene. The non-conjugated diene is incorporated into the amino-substituted interpolpolymer in an amount of from about 0.5 to about 15 wt%; more preferably, from about 1 to about 10 wt%, e.g., 5 wt%.


35 Nitrogen-Containing Monomers

As used in the specification and claims, the term nitrogen-containing monomer (NCM) means the unsaturated, nitrogen-containing monomers of this invention which contain at least one primary amino, secondary amino, imino, and/or cyano group having the general formula:



wherein R¹ is selected from ethylenically unsaturated hydrocarbyl radicals, and X is selected from the group consisting of amino (-N(H)R') groups, imino groups (-CH=N-R'), and cyano (-C≡N) moieties, and wherein n is an integer of at least 1, preferably 1-4, and more preferably 1-2. R' in the above groups can comprise H or hydrocarbyl (preferably H or saturated hydrocarbyl), e.g., of 1 to 15 carbon atoms, and preferably alkyl of 1 to 5 carbon atoms, cycloalkyl of from 3 to 7 carbon atoms, and the like. Exemplary of such amino groups are -NH₂ and alkyl amino groups, e.g., -NHCH₃, -NHC₂H₅, -NHC₃H₇, -NHC₄H₉, and the like.

The unsaturation in R¹ is such that it is easily polymerized by Ziegler catalysts employed in the practice of this invention. As used herein R¹ preferably contains from 2 to 25 carbon atoms, and preferably from 2 to 16 carbon atoms. In particular, R¹ is selected from the group consisting of radicals derived from ethylene, alpha-olefins, homologues of alpha-olefins, norbornene and homologues of norbornene, or from the group consisting of vinyl and allyl radicals. Representative examples of such unsaturation are alpha-olefin types shown as (M1) and the unsaturation in the norbornene system shown as (M2):



wherein R" comprises norbornyl, m is an integer of from 1 to 30, and p is an integer of from 1 to 30. Preferably m and p are integers of from 0 to 12. More preferably m is 0, 1, or 2, and p is 1, 2, or 3. It will be understood that the $-C_mH_{2m}-$ and $-C_pH_{2p}-$ groups can be branched or straight chained, and that the norbornene ring can be substituted with the $-C_pH_{2p}-$ group at the C-2 or C-7 position, i.e., R" can comprise bicyclo [2.2.1] hept-5-en-2-yl, or bicyclo [2.2.1] - hept-2-en-7-yl, respectively. R' preferably contains from 2 to 25 carbon atoms, and is selected preferably from one of the two classes shown in (M1) and (M2). Suitable examples from the alpha-olefin unsaturation type includes vinyl, allyl and the higher homologues as represented by integral values of m. Suitable examples of the norbornene unsaturation type include norbornene and its higher homologues represented by integral values for p. More preferably, R' may contain up to 16 carbon atoms. Preferably, n is the number of functionality sites per NCM and has non-zero integral values between 1 and 5, and more preferably between 1 and 3.

The NCM is preferably soluble in the liquid hydrocarbon solvent or diluent selected for use in the subsequent polymerization reaction (e.g., saturated hydrocarbon solvents, such as hexane).

Exemplary of nitrogen-containing monomers are members selected from the group consisting of norbornenyl-methyl amines and imines and preferably 5-norbornenyl-2-methylamine, 5-norbornene-2,3-dimethylamine, 5-norbornene-2-ethylamine; 5-norbornene-2-(4'-butenyl)imine and the like, and norbornenyl-nitriles, such as 5-norbornene-2-nitrile, 5-norbornene-2,3-dinitrile, and the like.

The NCM may also include multiple functionality, that is the R' moiety may be substituted by more than one "X" group, in which case the functional "X" groups may be the same or different.

The hydrocarbyl radical in the NCM will preferably be norbornyl, or vinyl, in structure with particular preference for norbornyl functionalized at the C-2 position or alpha-olefins functionalized at the C-3 position. Notwithstanding the previously mentioned preferred unsaturated, nitrogen-containing monomers, it should be understood that the nitrogen-containing groups may be located at other positions on the hydrocarbyl radical component of the monomer, and it will be further understood that mixtures of such nitrogen-containing monomers can be employed, if desired. Also, one or more NCM can be employed in combination with one or more monomer of the formula:




wherein R' is as defined above, n'' is an integer of at least 1 (e.g., 1-4, preferably 1-2) and X' is selected from the group consisting of $-CO_2H$, $-OH$, $-C(O)R^1$, $-SH$, and $-CN(R^1)_2$ wherein R' is as defined above.

The nitrogen-containing monomers useful in this invention may be prepared by conventional methods and detailed description of such NCM preparations is not needed for a complete understanding of this invention. For example, 5-norbornene-2-methyl amine can be formed by condensation of alkyl amino and cyclopentadiene as described by K. Alder and E. Windemuth, Ber. 71, 1939 (1938).

Masking Agent

Agents which have been found to be effective in masking nitrogen-containing monomers for purposes of the present invention include metal alkyls and metal alkyl hydrides and comprise at least one organometallic compound selected from the group consisting of compounds of the formula:



wherein M is a member selected from Group IIA, IB, IIB, IIIA, IVA, and the transition metals and elements, r_1 and r_2 are the same or different, are each integers of from 0 to 4 and are selected so as to satisfy the valence for metal M, "Halo" is Cl, Br or I, and Y is at least one of R^2 , R^3 , R^4 and R^5 , wherein R^2 - R^5 are (preferably independently) selected from the group consisting of hydrogen and C_1 - C_{15} hydrocarbyl and C_1 - C_{15} hydrocarbyloxy, which may or may not contain unsaturation, including C_1 - C_{15} alkyl, C_6 - C_{15} aryl, C_1 - C_{15} alkoxy, and C_6 to C_{15} aryloxy, provided that at least one of R^2 - R^5 is not hydrogen. Exemplary of preferred R^2 - R^5 groups are members selected from the group consisting of hydrogen, methyl, ethyl, propyl, isopropyl, n-butyl, isobutyl, tertiary butyl, pentyl, hexyl, phenyl tolyl, ethylphenyl, naphthyl, methoxy, ethoxy, propoxy, hexoxy, pentoxy, phenoxy, methylphenoxy, iso-butoxy and tertiary butoxy. Illustrative of M are elements comprising at least one member selected from the group consisting of Be, Mg, Ca, Sr, Ba, La, Ti, Zr, Hf, V, Nb, Ta, Cr, Mo, W, Mn, Re, Cu, Zn, Cd, Hg, Al, Ga, Sn and Pb. Preferred are members selected from the group consisting of Mg, Ca, Ti, Zr, Cu, Zn, Cd, Hg, Al, Ga, Sn and Pb. Most preferred is Al.

Preferably, when r_1 is 1 or greater, Halo is Cl. Most preferably, the masking agent is a non-halogenated compound of the above formula wherein r_1 is zero, and wherein r_2 is an integer of from 1 to 4. Suitable organometallic compounds are diethylzinc, and di-n-hexylmagnesium, triethyl aluminum, triisobutyl aluminum, diisobutyl aluminum hydride, tributyl aluminum, tripropyl aluminum, trioctylaluminum, diethyl aluminum hydride, dibutyl aluminum hydride, dihexyl aluminum hydride, trimethyl aluminum, trihexyl aluminum, tridecyl aluminum, tridodecyl aluminum, trihexadecyl aluminum, decyl aluminum dihydride, isobutyl aluminum dihydride, ethyl aluminum dihydride, didecyl magnesium, dipropyl zinc, propyl zinc hydride, diethoxy aluminum hydride, trimethoxy aluminum, sodium alkyls (e.g., NaCH_3 , NaC_8H_7), methyl magnesium hydride, di(isopropyl) magnesium, di (n-hexyl) calcium, dimethyl [bis(cyclopentadienyl)] titanium, with triisobutylaluminum, triethylaluminum, and diisobutyl aluminum hydride being most preferred. Although the masking effect using zinc and magnesium compounds is acceptable for purposes of the present invention, it has been observed that masking with aluminum compounds is more effective in controlling catalyst poisoning. Accordingly, organoaluminum compounds are preferred over organomagnesium compounds which in turn are more preferable than organozinc compounds.

Masked Functional Group-Containing Monomer

The term masked, nitrogen-containing monomer (MNCM) as used in the specification and claims, is intended to refer to the reaction products formed by the reaction of the nitrogen-containing monomer and a masking agent comprising at least one metallic organic compound (which preferably comprises a non-halogenated metallic organic compound). The masked, nitrogen-containing monomer so formed is used as the actual comonomer in the polymerization process.

The preferred non-halogenated masked nitrogen-containing monomers useful for purposes of the present invention include those having the general formula:










wherein n' is an integer of from 1 to 2, n is an integer of at least 1, preferably 1-4, and more preferably from 1 to 2; R^1 is a member selected from the group consisting of ethylenically unsaturated hydrocarbyl radicals as defined above; X is a member selected from the group consisting of amino, cyano and imino moieties as defined above; M is a member selected from Group IIA, IB, IIB, IIIA, IVA, and transition metal elements; and Y is at least one of R^2 , R^3 , R^4 and R^5 , wherein R^2 - R^5 are independently selected from the group consisting of hydrogen, C_1 - C_{16} hydrocarbyl, and C_1 - C_{16} hydrocarbyloxy, which may or may not contain unsaturation, including C_1 - C_{16} alkyl, C_6 - C_{16} aryl, C_1 - C_{16} alkoxy, and C_6 - C_{16} aryloxy, which preferably are members independently selected from the group of hydrogen, methyl, ethyl, diethyl, propyl, isopropyl, butyl, tertiary butyl, pentyl, hexyl, phenyl, tolyl, ethylphenyl, naphthyl, methoxy, ethoxy, propoxy, hexoxy, pentoxy, phenoxy, methylphenoxy, iso-butoxy, and tertiary butoxy. Preferably, M is a metal element selected from the group consisting of aluminum, magnesium and zinc.

Masking Step

The reactive functionality of the NCM's (that is, the X groups discussed above) are preferably protected, i.e., "masked", prior to introducing these monomers into the polymerization reactor to form the amino-substituted interpolymers (C). Otherwise, an unmasked functionality would tend to react almost immediately with the Ziegler-Natta polymerization catalyst, thereby leading to a loss of activity. The masking reaction provides a chemical deactivation of the reactivity of the functionalized monomer. This deactivation is believed to be both electronic and steric. Although not wishing to be bound by any particular theory, it is believed that deactivation may also involve the temporary replacement of highly reactive groups, such as acidic protons.

The organometallic masking agents are believed to react in one of two possible ways with the nitrogen-containing to form the masked, nitrogen-containing monomer. These pathways include the following representative, but not exclusive examples.

Pathway 1NCM FunctionalityM(Y)_rMNCM FunctionalityPathway 2NCM FunctionalityM(Y)_rMNCM FunctionalityPathway 3NCM FunctionalityM(Y)_rMNCM Functionality

wherein "Bu" is n-butyl, "iBu" is iso-butyl, and "Me" is methyl.

The reaction by Pathway 1 is fundamentally the replacement of an active hydrogen of the NCM functionality by a dialkyl aluminum substituent. The reaction is accompanied by loss of a mole of alkane, which in this case is isobutane. The reaction of Pathways 2 and 3 is the addition of the elements of the Al-H bond of M(Y)_r across a polarized heteroatom-carbon double bond (that is, the >C=N, or >C=N bond) of the NCM functionality. In both cases, the final MNCM functionality is for all intents and purposes the same, i.e., a masked functionality of imino, amino, or cyano. The reaction of R¹(X)_n and M(Y)_r by either of the pathways indicated above forms masked imino, amino, and cyano functional group-containing monomers having the general formula:



wherein R¹, X, M, Y, n' and n are as previously defined herein. The organometallic masking agent and NCM are preferably used in the method of the present invention in a masking agent: NCM molar ratio of 0.6-2.0:1, and most preferably in a molar ratio of about 1:1, for values of n=1. Larger integral values of n imply corresponding factor increases in the NCM to masking agent molar ratios charged to the masking reaction. For example, when the NCM comprises R¹(NH₂)₂, the masking agent is most preferably used in a molar ratio of 2 moles of masking agent per mole of such di-functional group substituted NCM. Therefore, the masking agent and NCM are preferably contacted in an amount sufficient to provide from about 0.3 to 3, more preferably from about 0.6 to 2, and most preferably from about 0.8 to 1.5 (e.g., from about 0.95 to 1.05) moles of the masking agent per reactive nitrogen equivalent of the NCM. As used herein, the "reactive nitrogen equivalents" of the NCM refers to the moles of the NCM multiplied by the sum of (a) the number of N-bonded H atoms in amino "X" group(s) in the NCM and (b) the number of cyano "X" group(s) in the NCM. For example, if a given NCM contains two secondary amino groups (or one primary amino group) per molecule, 1 mole of such a NCM contains 2 reactive nitrogen equivalents. Similarly, if a given NCM contains two primary amino groups per molecule, 1 mole of such a NCM contains 4 reactive nitrogen equivalents.

The masking reaction, which can be performed in a batchwise, continuous or semi-continuous manner, is preferably carried out by adding the NCM to the selected metal alkyl masking agent, preferably in the presence of an inert solvent or diluent. It has been observed that the desired MNCM are not formed in

acceptable yields when the reverse order of addition is used, that is, when the metal alkyl masking agent is introduced into the selected NCM; rather, such a reverse order of addition tends to form a highly viscous, sludge in the masking reactor. This sludge-like material is believed to be a result of prepolymerization of the NCM by liberation of more than one Y-H (e.g., alkane) derived from a Y group on each metal alkyl per functional group masked, due to the substantial excess of the NCM over the metal alkyl in the masking reaction zone. The masking agent and NCM should be contacted under conditions and for a time effective to form the corresponding MNCM without substantial degradation of the NCM. As used herein, the term "degradation of the NCM" is intended to include side-reactions of the NCM and any component of the masking reaction mixture, such as NCM alkylation, rearrangement and prepolymerization, which decrease the yield of MNCM obtained in contacting the selected NCM and masking agent. Preferably, the selected NCM and masking agent should be contacted at a temperature and for a time sufficient to form the MNCM in essentially quantitative yields, that is, in yields of the MNCM of at least about 95%, more preferably at least about 97%, and most preferably at least about 99%, based on the NCM fed to the masking reactor. The masking reaction should be performed in a reaction zone cooled to maintain the reactants at a temperature of less than 60°C (e.g., less than about 50°C, generally less than about 30°C, more generally from about -70°C to +30°C, e.g., from about -20°C to +20°C, and most preferably from about -15°C to +10°C. It has been found that temperatures in excess of about +60°C results in substantial degradation of the NCM even in the presence of the masking agents. The pressure employed in the masking reactor is not critical, and any convenient pressure can be employed, e.g., from about 0.05 to 20,000 kPa. Generally, the NCM and masking agent will be contacted for the masking reaction for a time of from about 0.001 to 10 hours, preferably from about 0.2 to 3 hours.

The masking reaction should be conducted in the substantial absence of molecular oxygen and water, to avoid the deleterious effects which O₂ and H₂O have upon the metal alkyl and the MNCM thus formed. Preferably, the masking reaction mixture (and the NCM, masking agent and solvent charged thereto) will contain <20 ppm H₂O, more preferably <10 ppm H₂O, and preferably <20 ppm O₂, more preferably <10 ppm O₂, by weight of the total reaction mixture. Most preferably, the masking reaction mixture (and hence the materials charged thereto) will contain <5 ppm O₂, and <5 ppm H₂O (by weight of the total reaction mixture). Preferably, reactive halides will also be substantially absent in the reactor, e.g., <10 ppm by weight reactive halide (expressed as the halide, e.g., Cl), based on the weight of the total reaction mixture. As used herein, the term "reactive halide" is intended to refer to free halogen (e.g., Cl₂), metal halides (e.g., dialkyl aluminum chloride, boron trichloride, tin tetrachloride and the like) or halogen-containing compounds (e.g., t-butyl chloride and the like) that will form metal halide under conditions of the masking reaction. Preferably the MNCM formed by the masking process of this invention are substantially free of halide, and contain less than about 0.01 wt%, more preferably less than about 10 ppm by weight, of total halide.

In the event the selected NCM was prepared by a process wherein H₂O is formed as a by-product (e.g., as in the formation of 5-norbornene-2-carboxy (N-n-butyl) imine, as described above), or is otherwise present, the NCM should be treated to remove H₂O to a level of <20 ppm, preferably <10 ppm, more preferably <5 ppm H₂O (based on the weight of the NCM). Such water removal can be accomplished by a variety of methods, such as by cooling the NCM to a temperature sufficient (e.g., <0°C) to freeze the water out of the liquid NCM. Alternatively, the NCM liquid can be contacted with an amount of molecular sieve (e.g., 3 Angstrom mol sieve) and for a time and under conditions sufficient to remove the desired amount of water. While the precise amount of mol. sieve will vary depending on its water absorption capacity, the amount of water to be removed and other factors, generally a contact time of from 1 min. to 1 hour at temperatures of 0° to +50°C, employing from 1 to 500 gms. of NCM per gram of 3 Angstrom molecular sieve will be sufficient to decrease the H₂O level to <20 ppm for a NCM liquid containing about 10 wt% H₂O. The NCM feed can also be treated for water removal by the addition of water soluble inorganic salts (such as NaCl, CaCl₂, and the like) to form two liquid phases: the lower phase containing the salts and water; and the upper phase containing the dehydrated NCM, which can then be recovered by conventional liquid-liquid phase separation techniques.

The masking reaction may be conveniently carried out under an inert gas (such as N₂, Ar, He), to exclude the presence of air in the masking reaction zone.

Any solvent useful for the polymerization of the MNCM and the PCM (as discussed below) can be employed in the masking reaction. For example, suitable solvents include hydrocarbon solvents such as aliphatics, cycloaliphatics, and aromatic hydrocarbon solvents, or halogenated versions of such solvents. Preferred are C₁₂ or lower straight-chain or branched-chain, saturated hydrocarbons, and C₅ to C₉ saturated alicyclic or aromatic hydrocarbons, or C₂ to C₆ halogenated hydrocarbons. Examples of such solvents are hexane, butane, pentane, heptane, cyclopentane, cyclohexane, cycloheptane, methyl cyclopentane, methyl cyclohexane, isooctane, benzene, toluene, xylene, chloroform, chlorobenzene, tetrachloroethylene, dich-

loroethane and trichloroethane.

The concentrations of the NCM and masking agent in the selected reaction solvent or diluent are not critical and will typically be selected to facilitate ease of handling of the reactants and reaction mixture and the cooling thereof to remove, and control, the heat of reaction. Typically, the NCM will be employed in a concentration of from about 2 to 70 wt%, and the masking agent in an amount of from about 1 to 40 wt%, based on the total reaction mixture.

It will generally not be necessary to remove any unreacted masking agent from the NCM-masking reaction zone, nor to remove any by-product Y-H from this reaction zone.

The product mixture produced in the masking reaction, containing the MNM, desirably should be maintained at a temperature of less than 60°C, (e.g., less than about 50°C), preferably less than about +30°C, preferably from about -70°C to +30°C, and more preferably from about -20°C to +20°C, until the MNM is contacted for polymerization with the polymer chain monomer in the polymerization reaction zone, as will be described in more detail below.






As indicated above, the MNM formed will have one or two -M-Y groups per functionality, and the value of n' will depend on the functionality to be masked and the masking agent employed. For example, cyano functionalities will require two -M-Y groups per cyano group when M is a trivalent, divalent or monovalent metal or element as described above. Preferably, the MNM comprises a complex of the formula:













wherein R¹, X, M, Y, n' and n are as defined above.

The masking reactions of this invention can be illustrated in the following reaction equations:

Masking Reactions for Amine Groups



Masking Reactions for Cyano Groups

Masking Reactions for Imino Groups


Therefore, when NCMs of the formula:



wherein R^1 and n are as defined above, and X^a is a functional group having an acidic hydrogen (e.g., $-\text{NHR}^1$, wherein R^1 is as defined above), are masked by masking agents of the formula:



wherein each "hydrocarb." group can be the same or different and comprises C_1 - C_{16} hydrocarbyl (as defined above for R^2 to R^5), M' is divalent, trivalent or tetravalent M (wherein M is as defined earlier), r' is an integer of from 0 to $(v-1)$, and r'' is an integer of from 1 to v , wherein $r' + r'' = v$, wherein " v " is a number of from 2 to 4 and is the valence of M' in said masking agent, the MNCM obtained comprises members selected from the group consisting of monomers of the formula:




when R¹ is hydrocarbyl, and



- 5 wherein R¹, M'', and v are as defined above, and wherein Y'' comprises at least one of R², R³ and R⁴, wherein R²-R⁴ are the same or different and are H or C₁-C₁₆ hydrocarbyl, with the proviso that at least one of R², R³ and R⁴ is hydrocarbyl.


Further, when the NCM comprises a monomer of the formula:



wherein R¹ and n are as defined above, and the masking agent comprises metal compounds of the formula:



- 15 wherein M'' is divalent or trivalent M (wherein M is as defined above), "hydrocarb." is as defined above, r' is an integer from 0 to (v'-1), r'' is an integer of from 1 to v', and the sum of r' + r'' = v', wherein v' is 2 or 3 and is the valence of M'' in the masking agent, the MNMCM obtained comprise monomers of the general formulae:



25

and




30

wherein R¹, M'' and v' are as defined above, Y^a is C₁-C₁₆ hydrocarbyl, and Y'' is R², R³ or R⁴, wherein R²-R⁴ are the same or different and are H or C₁-C₁₆ hydrocarbyl, with the proviso that at least one of R²-R⁴ is hydrocarbyl. Generally, MNMCM of formula (iii) are obtained when r' is zero and MNMCM of formula (iv) are obtained when r' is greater than zero.


- 35 When the NCM monomer comprises a cyano-monomer of the formula R¹(C-N)_n, and when these NCMs are masked with metal compounds of the formula:




- 40 wherein M''' is tetravalent M, "hydrocarb." is as defined above, and r' is an integer of from 0 to 3, r'' is an integer of from 1 to 4, wherein the sum of r' and r'' is 4; the MNMCM can comprise monomers of the formulae:



50




or




5 wherein R^1 , Y^a , and M''' are as defined above, and Y''' is C_1-C_{16} hydrocarbyl, MNCMs of formula (v) are obtained by use of $m'''(\text{hydrocarbyl})_4$, i.e., when r' is zero. When r' is 1, the MNCM is of formula (vi). When r' is 2 or 3, the MNCM is of formula (vii).

To further illustrate the above, 5-norbornene-2-carboxy(N-n-butyl) imine can be reacted with one mole of diisobutyl aluminium hydride in hydrocarbon solvent as shown below:



Addition of H-Al occurs across the polarized double bond of the imine leading to the masked nitrogen-containing monomer, i.e., MNCM entity.

25 Nitrile-substituted NCMs, e.g., 5-norbornene-2-nitrile, can be masked with two moles of masking agent, e.g., $(\text{i-Bu})_2\text{AlH}$, to generate a masked amine monomer containing two atoms of M metal (e.g., aluminum) for each nitrogen, although this is not a preferred method of masking the functionality herein. The masking of a nitrile-substituted NCM can be illustrated as follows:




40 It should be noted that the mutual compatibility of different masked monomers, i.e., MNCM arising from the reaction of different NCM with masking agents allow the formation and incorporation of different MNCM into the same polymer. A representative, non-exclusive, example would be to mask a mixture of 5-norbornene-2-amine and 5-norbornene-2-carboxylic acid and/or 5-norbornene-2-methanol with triisobutyl aluminum. Incorporation of this mixture in the polymerization reactor would lead to amine and carboxylic acid and/or alcohol residues on the same polymer and is a suitable procedure for incorporation of multiple functionality into the amino-substituted polymers.

As compared to the NCM having acidic hydrogens such as those bearing free acid, amine, or alcohol groups, the NCGM formed by these reactions has all potentially reactive functional sites either removed or complexed. Thus, the nitrogen atom in the imine NCM, which might otherwise interfere with catalyst performance by their lone pair donation, are effectively deactivated by chelation to the metal atom. The resultant MNCM is very stable in hydrocarbon solution (e.g., in hexane), both kinetically and thermodynamically, towards dissociation of the metal, in this particular case aluminum, from the NCM residue. Nevertheless, the masked amine group (and masked acid, alcohol, etc., functional group, if present) is very conveniently regenerated, as will be described in more detail below.

55 Preferably, the masking agent is non-halogenated since it has been observed that masked, nitrogen-containing monomers react in the presence of organoaluminum halides by polymerization of the norbornene double bond, leading to oligomeric, hydrocarbon-insoluble materials which are not available for incorporation into the polymer chain. Furthermore, this reaction may also involve rearrangement of the

norbornene system leading to unreactive MNCMs which are unacceptable for incorporation into the polymer. Preferably, the masking is accomplished by reacting nitrogen-containing monomer with hydrocarbyl aluminum compounds wherein the hydrocarbyl moiety is a bulky group, that is, wherein the hydrocarbyl group is substituted (e.g., alkyl-substituted) preferably in the 1- or 2-carbon position, e.g., a branched C₃ to C₅ alkyl group such as isopropyl, isobutyl or t-butyl.

In another embodiment of the process of this invention, the MNCM prepared from an alkyl-substituted masking agent is reacted with a lower alkanol (e.g., a C₂-C₅ alcohol) and preferably a C₃-C₄ alkanol, e.g., isopropyl, isobutyl or t-butyl alcohol. The alcohols used are, in the order of increasing steric crowding around the carbinol carbon, methanol, ethanol (primary), isopropanol (secondary), and t-butanol (tertiary). The reaction of a MNCM of this invention with a lower alkanol can be illustrated by the following (wherein R¹ is as defined above):



The reaction products so formed have alkoxy radicals derived from the reactant alkanol bonded to the M metal of the MNCM. The term "alcohol modified MNCM" is used herein to refer to the adducts of MNCM and alcohol prepared in accordance with this embodiment. In an illustration of this embodiment, the nitrogen-containing monomer, NBCA, is initially complexed with triisobutyl aluminum (TIBA) and the resultant hexane soluble product is further reacted with from one to two equivalents of a dry alcohol (e.g., isopropanol). The temperature and other reaction conditions employed in such alcohol modifications of MNCM can be any of those discussed above for the initial masking reaction, and preferably a temperature of from -30°C to 0°C is used, with from 1:1 to 2:1 molar equivalents of alcohol being used per masked functional group. It has been observed that such alcohol-modified MNCMs are soluble in hexane.

The resultant polymerizations with alcohol-modified NCM's demonstrate similar reactor performance than the results obtained for TIBA complexes alone. It has been found that further improvement in the degree of steric isolation of the masked NCM leading to an even lower degree of catalyst deactivation was obtained by different alcohols with the alcohol having the largest steric bulk, i.e., t-butanol, providing the most protection against poisoning with methanol providing the least, and the other alcohols being arranged between these limits in the order of their crowding around the amino group. Accordingly, the alcoholated masked, nitrogen-containing monomer has been found to result in higher polymerization efficiencies, higher polymer molecular weight and improved incorporation of nitrogen-containing monomer into the polymer.

Preparation of the Amino-Substituted Interpolymer

The polymerization process of the PCM and MNCM is performed in an otherwise conventional manner using suitable methods, including batchwise, semi-batch or continuous operations, conventional polymer chain monomers, and catalysts known to be effective for such polymerization. In this polymerization, the MNCM's behave like the non-polar homologues of these monomers. Especially preferred for use in the present invention are NCM-ethylene-propylene (EPM) terpolymers and NCM-ethylene-propylene-diene (EPDM) tetrapolymers. The polymerization process is preferably carried out in one or more conventional reactors, including mix-free reactor systems, continuous flow tubular reactors, and stirred-batch reactors. For purposes of illustration herein, when the process is described herein below with respect to a continuous flow stirred tank reactor, the reaction mixture is blended (i.e., backmixed) with the incoming feed to produce a solution of essentially uniform composition everywhere in the reactor.

The monomers which are suitable as polymer chain monomers include olefin monomers such as ethylene and C₃-C₂₀ alpha olefins, and unsaturated, non-conjugated diolefins as described above. Illustrative of amino-substituted polymers useful in this invention are homopolymers, co-polymers, terpolymers, or tetrapolymers containing the above olefins and/or diolefins, in addition to the nitrogen-containing monomers. Exemplary of amino-substituted polymers produced by this invention are functionalized polypropylenes (propylene homopolymers, propylene-ethylene copolymers containing less than about 10 wt% ethylene,

propylene-higher olefin copolymers containing up to about 10 wt% of higher alpha-olefins such as hexene-1, pentene-1, pentene-1, octene-1 and the like), functionalized polyethylenes (ethylene homopolymers and ethylene-propylene co-polymers containing greater than 90 wt%, usually 95 to 99 wt%, ethylene), ethylene-propylene copolymers (e.g., elastomeric EPM), ethylene-propylene-diene terpolymers (e.g., elastomer & EPDM) and the like. It is preferred, however, to perform the process in a copolymerization process of alpha-olefins and preferably a mixture of ethylene and propylene to result with an ethylene-propylene (EPM) polymer. The resultant polymer preferably contains about 20 wt% to 90 wt% ethylene and 10 wt% to 80 wt% propylene. It is also possible to include a non-conjugated diene, such as dicyclopentadiene, 1,4-hexadiene or ethylidene norbornene in the olefin mixture used in the polymerization process in order to introduce unsaturation into the backbone of the resultant polymer (EPDM).

The amino-substituted polymers may be formed by polymerizing polymer chain monomers with the MNCMs in the presence of a polymerization catalyst, wherein the polymerization catalyst includes at least one vanadium compound, zirconium compound or titanium compound, preferably wherein the vanadium compound has a valence of at least 3 (e.g., 3 to 5), and is preferably selected from the group consisting of vanadium halide, vanadium oxyhalide, and vanadium salts of beta-diketonates, with the vanadium halide preferably being vanadium tetrachloride and the vanadium oxyhalide compound having the general formula $\text{VOX}'_n(\text{OR}^7)_{3-n}$ where n is an integer of 2 or 3, R^7 is a hydrocarbyl radical which is preferably a C_1 - C_{10} alkyl, phenyl or benzyl and more preferably C_1 - C_4 alkyl (such as a member of the group of methyl, ethyl, and butyl), and X' is halogen which is preferably chlorine or bromine. The vanadium salts of beta-diketonates have the general formula of $\text{V}(\text{O}-\text{O})_3$ where $\text{O}-\text{O}$ represents the beta-diketonate anion. The preferred beta-diketonate is 2,4-pentanedionate.

The polymerization catalyst preferably also includes an organoaluminum co-catalyst comprising organoaluminum halides and organoaluminum compounds having the formula $\text{R}^6\text{AlX}''_{(3-x)}$ wherein X'' is a halogen, R^6 is a member selected from the group consisting of alkyl and aryl (and preferably wherein R^6 is a member selected from the group consisting of C_1 - C_{16} alkyl and phenyl, which is most preferably ethyl), and x is between 0 and 3, and preferably greater than 0 up to 2 (e.g., between 1 and 2), and more preferably from 1 to 1.2. Illustrative, non-limiting examples of the aluminum halide cocatalyst useful in the practice of this invention include an aluminum trichloride, ethyl aluminum dichloride, diethyl aluminum chloride and ethyl aluminum sesquichloride.

It is preferred to have the vanadium compound and the organoaluminum co-catalyst present in the polymerization catalyst in a molar ratio of vanadium to aluminum of about 1:2 to 1:30, with the molar ratio of vanadium to aluminum more preferably being about 1:5 to 1:15. The catalyst and the MNCM may be present in a molar ratio of vanadium to masked, nitrogen-containing monomers of about 1:5 to 1:100, with the molar ratio of vanadium to masked, nitrogen-containing monomers preferably being about 1:10 to 1:30. The titanium catalyst has a valence of 2 or greater and is preferably insoluble in the polymerization media. Representative, but not exclusive examples of these catalysts include TiCl_4 , TiCl_3 , and $\text{TiCl}_3 \cdot 1/3 \text{AlCl}_3$ - (Stauffer AA Catalysts). The V and Ti catalyst can be supported on conventional catalyst supports (e.g., on silica, MgCl_2 , zirconium, and the like). Electron donor modified versions of supported V and Ti catalytic systems can also be used.

The preferred catalysts for making elastomeric polymers include vanadium compounds, preferably having a valence of at least 3 and which are soluble in the polymerization diluent, such as VX'_4 and VOX'_3 wherein X' is halogen, i.e., vanadium halide and vanadium oxyhalide. The preferred vanadium halide is vanadium tetrachloride.

The polymerization reaction zone for polymerization of the MNCM and polar chain monomers(s) can also contain one or more of the conventional polymerization promoters, such as halogenated and non-halogenated organic polymerization promoters.

In addition to the foregoing consideration, the monomers to be selected also depends on the nature of the polymerization process and the catalyst used. The reactivity of unsaturated MNCM towards polymerization, its efficiency of incorporation into the polymer, and its distribution in the polymer is a function of the catalyst system used. Thus changes in the nature of MNCM, particularly in the type of unsaturation, are needed to accommodate the changes in polymerization catalyst.

The preferred kinds of NCM hydrocarbyl radical for some of the most common kinds of olefin polymerization for purposes of the present invention are:

NCM Hydrocarbyl		
Catalysis	Radical	Polymer Type
a. Homogeneous Ziegler Polymerization with Vanadium Catalysts	5-Norbornene functionalized at C-2 and/or C-7.	Rubbery EP
b. Heterogeneous Ziegler Polymerization with Titanium Catalysts	Acyclic alpha-olefin functionalized at C-3	Crystalline PE, PP

The difference between the requirements for heterogeneous and homogeneous Ziegler catalysts is primarily due to the much lower reactivity of the norbornene based monomers towards the heterogeneous catalysts. For example, while the incorporation of norbornene based monomers is about 50 to 90% for the vanadium catalysts, it is usually less than about 30% for the titanium catalysts. Accordingly, the polymerization process is preferably a homogeneous Ziegler polymerization because of a higher incorporation of the monomer, and where the MNCM is a norbornene carrier, it is incorporated at about 50 to 90% with vanadium catalyst and at less than 30% with titanium catalyst. The process is, therefore, often described herein with respect to homogenous polymerization using vanadium catalyst.

The polymerization reaction can be carried out at any temperature suitable for Ziegler catalysis such as a temperature of about -20°C to about 150°C, or preferably about 0°C to about 100°C and more preferably about 15°C to about 60°C. The pressure used in the polymerization process can vary from about 0 Kpa to about 3000 Kpa and preferably from about 20 Kpa to about 1500 Kpa; more preferably about 100 Kpa to about 1000 Kpa and 250 Kpa to 1000 Kpa, most preferably about 300 Kpa to about 600 Kpa.

Preferably, the MNCM is not be premixed with any halogen-containing component of the polymerization catalyst (e.g., vanadium halide or organoaluminum halide) and left to stand for any appreciable period of time since the halide-containing catalyst components have a tendency to react with the MNCM in which case the metal-bound hydrocarbyl groups of the MNCM will be displaced by halogen. The consequence will be MNCM degradation, including polymerization/rearrangement reactions similar to those encountered when the MNCM is reacted with an organoaluminum halide masking agent as described above. It has been observed that the polymerization results with a greater efficiency of incorporation of the MNCM to yield a higher molecular weight polymer, and with decreased incorporation of halogen into the resultant polymer.

Preferably, the MNCM is added to the polymerization reaction zone separately from the polymerization catalyst components, so as to first contact the polymerization catalyst in the presence of the polymer chain monomer(s), preferably under polymerization conditions.





Any known diluent or solvent for the reaction mixture that is effective for the purpose can be used in conducting polymerization of the PCM and the MNCM to form the masked functionalized (amino-substituted) polymer. For example, suitable diluents or solvents would be hydrocarbon solvents such as aliphatics, cycloaliphatics, and aromatic hydrocarbon solvents, or halogenated versions of such solvents. The preferred solvents are C₁₂ or lower straight-chain or branched-chain, saturated hydrocarbons, and C₅ to C₉ saturated alicyclic or aromatic hydrocarbons, or C₂ to C₆ halogenated hydrocarbons. Most preferred are C₁₂ or lower straight-chain or branched-chain hydrocarbons particularly hexane. Non-limiting illustrative examples of diluents or solvents are butane, pentane, hexane, heptane, cyclopentane, cyclohexane, cycloheptane, methyl cyclopentane, methyl cyclohexane, isooctane, benzene, toluene, xylene, chloroform, chlorobenzenes, tetrachloroethylene, dichloroethane and trichloroethane.

The polymerizations can be carried out in the presence of a molecular weight regulator to produce an amino-substituted polymer having any particular desired molecular weight. A molecular weight regulator commonly used in this type of process is, for example, hydrogen. The amount of molecular weight regulator to be used can easily be chosen based on principles well-known to those skilled in the art, depending upon the desired molecular weight of the amino-substituted polymer.

Hydrogen can be introduced to the polymerization zone to moderate polymer molecular weight. The hydrogen will be generally added in an amount of from about 0 to about 30 mole percent, based on the total monomer (MNCM + PCM).

After polymerization, the polymerization is quenched at the exit of the reactor. This quenching can be accomplished by the introduction into the polymerization reaction mixture (e.g., in the reactor or into polymerization product effluent stream) of water, lower alkanol, or aqueous acid (e.g., aqueous HCl) as quench liquid, generally using from 1 to 30 moles of quench liquid per mole of total V and Al in the reaction mixture.

The desired amino functional group, i.e., X, incorporated into the amino-substituted interpolymer as the masked functional group, can be regenerated by removal of the masking metal, M, through use of conventional de-ashing techniques, wherein the quenched polymerization product, containing masked-functionalized polymer, the polymerization catalysts, and unreacted monomers, is contacted with an aqueous liquid, e.g., water, aqueous solutions containing mineral acids (e.g., HCl, HBr, HNO₃, H₂SO₄, H₃PO₄, and the like), aqueous solutions containing mineral bases (e.g., caustic ammonia, sodium methoxide and the like) or mixtures thereof. The resulting hydrolysis reactions (hereinafter referred to as "de-ashing") liberate the metal masking agent and generates the amino functional group, thereby forming an amino-substituted polymer. Such hydrolysis reactions can be illustrated as follows:

Masked-Functionality PolymerFunctionalized Polymer

De-ashing to regenerate the amino group can be conveniently accomplished by contacting the quenched polymerization product with from 0.3 to 3 volumes of water per volume of polymerization reactor effluent (in equivalent units); the water may optionally contain from 1 to 30 wt% (e.g., 3 to 10 wt%) of mineral acid(s). The mixture is contacted for a time and under conditions sufficient to de-ash the polymer

and to regenerate the amino group. Generally, the contacting will be conducted for a time off from about 3 to 30 minutes, and a temperature of from about 0°C to 85°C, with vigorous stirring. The use of an acidic aqueous liquid may be followed by one or more water washes of the separated polymer to remove residual amounts of the mineral acid. The 2-phase liquids resulting in the above steps will permit recovery of a polymer-containing upper liquid phase comprising the functionalized polymer and polymerization solvent or diluent, and an aqueous lower liquid phase containing the mineral acid, and aqueous soluble salts of the catalyst and masking agent metal(s). The aqueous layer will preferably also contain unreacted NCM, due to the water solubility of the NCM attributed by the hydrophilic nature of the "X" functionality.

The polymer may be recovered from the upper phase by flash evaporation followed by drying to remove residual water. The flashing technique can involve the addition of the quenched polymerization product to a tank of hot water (50°C to 100°C) sprayed with steam to strip off the solvent and unreacted monomers. The polymer may be then dried by evaporation off water, generally at temperatures off from about 150°C to 200°C, e.g., on a hot rubber mill.

It will be understood that any cyano groups off the NCM will, upon masking, polymerization and regeneration, be regenerated as an amino group, rather than a cyano. The amino group may be either primary or secondary, and is determined by the number of carbon radicals attached to the nitrogen in the masked monomer. A single carbon radical leads to primary amine while two alkyl groups lead to a secondary amine.

The NCM is present in the resultant amino functionalized polymer in an amount of from about 0.01 to about 40 wt%, by total weight of the amino functionalized polymer preferably in an amount of from about 0.1 to about 20 wt%, more preferably in an amount of from about 0.75 to about 10 wt%, and most preferably in an amount of from about 1.0 to about 7 wt%. The preferred amino-substituted ethylene-propylene copolymers employed in this invention will, therefore, comprise from about 20 to 90 wt% ethylene, from about 10-80 wt% propylene, and from about 0.01 to 40 wt% nitrogen-containing monomer, more preferably from about 0.1 to 20 wt%, still more preferably from about 0.75 to 10 wt%, and most preferably from about 1 to 7 wt%, nitrogen-containing monomer. The preferred amino-substituted ethylene-propylene-diene terpolymers employed in this invention will therefore comprise from about 20-90 wt% ethylene, from about 10-80 wt% propylene, from about 0.5 to 15 wt% (and more preferably from about 1 to 10 wt%) non-conjugated diene, and from about 0.01 to 40 wt%, more preferably from about 0.1 to 20 wt%, still more preferably from about 0.75 to 10 wt%, and most preferably from about 1 to 7 wt%, nitrogen-containing monomer.

The amino-substituted polymers employed in this invention are oil soluble and have a number average molecular weight ($\bar{M}_n$) of from about 10,000 to 500,000. The amino-substituted polymers, when intended for use in lubricating oil compositions as viscosity index improver dispersants preferably will have $\bar{M}_n$ of from greater than 10,000 to 200,000 or more, and more preferably from 20,000 to 150,000.

Preferably, the amino-substituted polymer will have within its structure, on average, at least 0.5 (e.g., from 0.5 to 20), and preferably at least 1 (e.g., from 1 to 15) pendent reactive amine groups (i.e., primary and/or secondary amine groups) per polymer molecule.

The amino-substituted polymer will preferably also have a molecular weight distribution ($\bar{M}_w/\bar{M}_n$) of from about 1.0 to 20, and more preferably of from about 1.5 to 15.

Preferably, the amino-substituted polymers have a substantially homogeneous distribution of amino functionality between the polymer chains, that is, the wt.% concentration of amino functionality is substantially uniform for chains of all molecular weights. Furthermore, the polymers preferably cannot be separated into two or more significant fractions (e.g., >5 wt% of total polymer) which have different compositions arising from different levels of incorporation of NCM and PCM. The "level of functionality" as used herein is defined to be equivalents of amino functionality per unit weight of the amino-substituted polymer, and is commonly expressed for these polymers in milliequivalents of functionality per 100 gms of amino-substituted polymer.

The distribution of functionality in a polymer can be readily determined by methods known in the art. One technique is to tag a random fraction of the functionality with a UV-visible chromophore. The tagging is done by a specific chemical reaction (e.g., amidation) on the functionality of choice with a reagent carrying the UV-visible chromophore tag. The tagging reaction is chosen to be one where the tagged functionality will exist in that state through the subsequent investigations. The chromophore found to be particularly suitable for this purpose is the phenyl ring and procedures for derivatizing amino functionalities with suitable phenyl group containing agents are well known in the art. The derivatized polymer is analyzed by a gel permeation chromatographic procedure and the effluent is analyzed by two detectors, i.e., one for the quantity of the polymer and the other sensitive to the concentration of the chromophore. The uniformity of functionality distribution in the original polymer is observed by coincident responses of the two above

mentioned detectors.

Also, the amino-substituted polymers have a low total halogen content and are essentially devoid of any organic halide. Preferably, the amino-substituted polymers contain less than 0.10 wt%, and preferably less than 0.03 wt%, of total organic chlorine, with an organic chloride content measured by the absorbance of
 5 1/100 inch thick film of the polymer at 610 cm^{-1} of less than 0.05, and preferably 0.03, absorbance units.

Analytic Methodology Used in Examples 1-5

The polymerization rate was determined by weighing the amount of rubber obtained in a fixed time
 10 period. Monomer conversion and catalyst efficiency (weight of polymer products/wt. vanadium catalyst feed) were determined to characterize the catalyst activity. Infrared analysis (ASTM D3900) was used to measure polymer ethylene content while refractive index [I.J. Gardiner & G. Ver Strate, *Rubber Chem. Tech.*, 46, 1019 (1973)] was used for END content. In the absence of ENB in the polymer, this was also used as a semi-quantitative measure of NCM content in the polymer. Polymer Mooney viscosity was measured by
 15 ASTM D-1646.

Molecular weight (number-average, $\overline{M}_n$; weight-average, $\overline{M}_w$; z-average, $\overline{M}_z$) and molecular weight distribution ($\text{MWD} = \overline{M}_w/\overline{M}_n$) were measured using a Waters 150 gel permeation chromatograph equipped with a Chromatix KMX-6 on-line light scattering photometer. The system is used at 135°C with 1,2,4-trichlorobenzene as the mobile phase. Showadex (Showa-Denko America, Inc.) polystyrene gel columns
 20 802, 803, 804 and 805 were used. The technique utilized is described in *Liquid Chromatography of Polymers and Related Materials III*, J. Cazes, editor, Marcel Dekker, 1981, p. 257 et seq. No corrections for column spreading are employed; however, data on generally accepted standards, e.g., National Bureau of Standards Polyethylene 1484 and anionically produced hydrogenated polyisoprene demonstrate that such corrections on $\overline{M}_w/\overline{M}_n$ or $\overline{M}_z/\overline{M}_w$ are less than 0.10 units. $\overline{M}_w/\overline{M}_n$ was calculated from an elution time-molecular weight relationship, whereas $\overline{M}_z/\overline{M}_w$ is evaluated using a light scattering photometer. The $\overline{M}_w/\overline{M}_n$
 25 are used as an indication of MWD breadth (the larger the value, the broader MWD). Polymers were analyzed for amino functionality content by infra red spectroscopy.

Polymers containing amino functionality were dissolved in hexane (approx. 3 wt.% solution) and quantitatively amidated with an equal volume of acetic anhydride, according to the reaction below:
 30



After refluxing for two hours, the polymer was recovered, molded in a pad of uniform thickness between .003 to 0.02 inch thick. The infrared spectrum of the sample contained an intense absorption at 1660 cm^{-1}
 35 due to the carbonyl group. The intensity of this absorption was measured in absorbance units (A_3). This was correlated to the concentration of milliequivalents amino functionality expressed in milliequivalents per 100 gm of polymer (C_{amine}) by the following relationship:

$$C_{\text{amine}} = A_3/t_3 \times 72.9$$

40 where t_3 is the thickness of the polymer sample expressed in thousandth of an inch.

These analytical relations were obtained by measuring the infrared extinction coefficients for the carbonyl groups and closely related monomeric model compounds in hexane media. Typically the experiment was conducted with the derived NCM and repeated to cover the span of obtainable concentrations of amino functionality. In all cases, Beer's law was found to be obeyed by the chromophore between
 45 the concentration of 0-30 meq/100 gms of amino-substituted polymer.

Polymers were analyzed for the distribution of amino functionality among the polymer chains (i.e., intermolecular amino functionality concentration distribution). The distribution of amino functionality in the polymers for purposes of tests run and comparisons made in connection with this application is measured
 50 by a chromatographic technique.

Uniformity (or "homogeneity") of amino functionality distribution is measured by observing the variation in the extinction coefficient, that is the ratio of the concentration of the chromophore to the total weight of the polymer as a function of amino functionalized polymer chain molecular weight. A polymer with a substantially uniform amino functionality distribution has this ratio substantially constant over a wide range
 55 of polymer chain molecular weights. Amino-substituted polymers employed in the present invention preferably have the above-mentioned ratio varying by from about 0 to 15%, and more preferably from about 0 to 10%, in the chain molecular weight range of 10^3 to 10^5 , provided the molecular weight range is such that the polymer components contain at least 95%, and preferably 97%, of the total weight of polymer, and

that at least 95%, and preferably 97%, of the total equivalents of the amino functionality are included.

Uniformity of composition was also determined by a solvent fractionation technique. In this procedure, a polymer hexane solution containing approximately 1-2 grams of amino-substituted polymer per 100 ml. of solvent was treated judiciously with isopropanol to precipitate a fraction of the amino-substituted polymer.

5 The precipitated amino-substituted polymer was equilibrated for 30 minutes with the bulk of the solution and then removed by filtration. More fractions were obtained by further addition of aliquots of isopropanol to the filtrate until the amino-substituted polymer was almost completely precipitated. The last fraction was obtained by evaporating the filtrate to a solid residue. Typically, the amino-substituted polymer was divided into 8 or 10 fractions and these were analyzed for ethylene residue content by infrared spectroscopy and
10 for norbornene residue content by changes in refractive index. As indicated by the test results, amino-substituted polymers employed in the present invention preferably have substantially uniform compositions of NCM, within the chain molecular weight range of 10^3 to 10^9 , which amount to within 15% and more preferably within 10% of the average for the whole amino-substituted polymer. The analysis of the norbornene residue content indicated that no fraction of the amino-substituted polymer analyzed contained
15 more than 7% and preferably 5%, of the total weight of the polymer, and that no fraction of the polymer analyzed contained 35% or more of the total amount of amino functionality in the polymer.

The amino-substituted polymers were also analyzed for halogen content. For purposes of this application, the halogen content of the polymer was determined only for chlorine residues which appear to be the largest fraction of halogen contaminants. Nevertheless, the analysis can be generalized to other applicable
20 halogens, i.e., bromine. Chlorine was determined by elemental analysis according to instrumental techniques established in the art and organic chloride content in the polymer was determined by the intensity of the absorbance of a polymer film of standardized thickness at 610 cm^{-1} in the infrared spectrum where C-Cl bonds absorb strongly.

The following examples are presented below to illustrate the foregoing discussion for a better
25 understanding of the invention. All parts, proportions and percentages are by weight unless otherwise indicated. Although the examples may be directed to certain embodiments of the present invention, they are not to be viewed as limiting the invention in any specific respect. In the following examples, the following abbreviations have these meanings:


30 EADC = ethyl aluminium dichloride
EASC = ethyl aluminium sesqui chloride
DIBAL-H = di isobutyl aluminium-hydride
NBCXA = 5-norbornene-2-carboxaldehyde
PhNH₂ = aniline
BuNH₂ = n-butyl amine

35 EXAMPLE 1

In separate runs, 2.5 mmol of NBCXA dissolved in 10 ml of hexane was slowly added, with stirring, to a cold solution of 2.5 mmol of either n-butyl amine, or aniline in hexane. The addition was performed under a
40 nitrogen atmosphere and the reaction temperature was maintained at 0°C by external cooling. The reaction mixture was stirred for 30 minutes and to the resultant cloudy mixture was added 20 gms of 4 Angstrom dry molecular sieve. After 30 minutes of contact with agitation the clear solution of n-butyl imine or phenyl imine, respectively, of NBCXA was decanted off into a dry nitrogen filled flask. To this solution was added 2.6 ml of a 15% solution of DIBAL-H in hexane under nitrogen over a period of 30 seconds. The solution
45 temperature was allowed to warm to ambient temperature (25°C) and after 30 minutes a pale yellow solution of the masked amine monomer was obtained.

50

55



wherein R⁶ = nBu or Ph

The course of the reaction was identified by C-13 NMR the solutions. Solutions of the reaction with metal alkyls suitable for NMR analysis were prepared, and C-13 NMR of the solutions was observed as described earlier. The NMR results are shown in the Table below.

TABLE I
C-13 NMR Data for 5-Norbornene-2-Carboximine
Complex with Diisobutylaluminum hydride
 (Data for Principle Endo Isomer Only)

<u>Compound</u>	<u>Carbox Carbon</u>	<u>Olefinic Carbon</u>	
		<u>C-5</u>	<u>C-6</u>
5-Norbornene-2-Carboxaldehyde (1)	198 (d, 170)	136.3 (d, 173)	131 (d, 171)
1+BuNH ₂ (1:1) (2)	164.4 (d, 150)	135.9 (d, 168)	131.5 (d, 170)
1+PhNH ₂ (1:1) (3)	166.5 (d, 153)	136.1 (d, 170)	131 (d, 165)
2+(i-Bu) ₂ AlH (1:1)	72 (t, 30)	136 (d, 165)	132 (d, 170)
3+(i-Bu) ₂ AlH (1:1)	69.2 (t, 132)		


.All spectra in hexane solution only

.Data in ppm from TMS; numbers in parenthesis are coupling
¹³C-¹HC (d=doublet; t=triplet)

These experiments indicate that the reduction of 5-norbornene-2-carboximine (Products 2 or 3) with diisobutyl aluminum hydride leads to the formation of a single masked amine monomer.

EXAMPLE 2

79.0 g of 5-norbornene-2-carboxaldehyde (NBCXA), (77.6 ml, 0.647 mole) were dissolved in 500 ml of hexane. 47.3 g of n-butylamine (64 ml, 0.647 mole) was slowly added at 25°C. The solution was stirred for five minutes and cooled to -18°C for several hours. The liquid hexane layer was decanted under nitrogen to remove the precipitated water which had frozen to ice and adhered to the sides of the reaction vessel. The clean hexane solution was removed under nitrogen to a separate reactor and dried with 50 gms of dried 4A molecular sieve. After thirty minutes, the hexane layer containing the n-butyl imine of NBCXA was separated from the molecular sieves and to it was added at -10°C 80.3 gm (0.647 mole) of diisobutylaluminum hydride as a 15% solution in hexane under nitrogen. The solution was stirred under nitrogen for one hour to yield the MNCM of 5-norbornene-2-methyl-(N-n-butyl) amine. The reactions are summarized below:

**EXAMPLE 3**

In this example, the MNCM obtained by reacting 5-norbornene-2-carbox-(N-n-butyl) imine with diisobutyl aluminum hydride in an equimolar ratio was introduced into an EP polymerization reactor. The object was to determine if this MNCM was acceptable for introducing secondary amine functionality in EP. The MNCM was made according to the procedures described below.

77.6 ml of 5-norbornene-2-carboxaldehyde (NBCXA) (79.0 gm) was slowly added to a solution of 64 ml of n-butylamine (47.4 gms) in 500 ml of hexane solution. The mixture was allowed to stand for 3 hours at 0°F (-18°C) and separated from the precipitated water. The clear hexane solution was dried by standing over 4A mole sieves for 2 hours and slowly added to a solution of 80.2 gm of diisobutyl aluminum hydride in 1000 ml of hexane at -30°C under a nitrogen blanket. After 3 hours at room temperature, the resultant solution was ready for introduction into the polymerization reactor. The conditions of polymerization are shown in Table II and the results in Table III:

Table II

Conditions	
Reactor	= 3.875 liter (CFSTR)
Temperature	= 27 °C
Pressure	= 500 Kpa gauge
Agitation	= 1200 rpm
Residence	= 9 min.
Al/V Molar Ratio	= 10 for catalysts compounds
Feeds	
Hexane	= 23.9 liters/hr.
Ethylene	= 363 g/hr.
Propylene	= 643 g/hr.
VCl ₄	= 1.896 g/hr.
EASC	= 1.22 g/hr.
EADC	= 12.48 g/hr.
Hydrogen	= 120 w ppm on ethylene
NCM (masked as above)	= 23.40 g/hr.

Table III

Polymerization Parameters		Polymer Proportion		
Rate (g/hr)	Catalyst Efficiency (g/g)	Ethylene Content (wt%)	M _L (1 + 8) (100 °C)	MNCM (conv %)
766	405	45.8	18	93

The results of this example show that the MNCM generated by the addition of diisobutyl aluminum hydride to imines is an acceptable method for incorporating amine functionality in EP.

EXAMPLE 4

In this example, amino-substituted EP polymer obtained by the procedures described in Example 3 was analyzed for distribution of functionality along the polymer chains. The object was to demonstrate that the formation of MNCM by reaction with nonhalogenated aluminum alkyls lead to a substantially uniform distribution of functionality in the polymer chain. The polymer was analyzed by (i) the gel permeation chromatography method and (ii) the solvent-nonsolvent fractionation method according to the procedures outlined earlier and described in detail below.

10.2 gms of the polymer made in Example 3, with diisobutyl aluminum hydride as the masking agent, was dissolved in 500 ml of hexane. To the clear solution was added with magnetic stirring isopropanol from a burette. After addition of approximately 35 ml of isopropanol a slight white precipitate was obtained. The rate of addition of isopropanol was slowed to - 1 drop/minute and agitation continued until a sizeable amount of polymer was precipitated. The precipitated polymer was equilibrated with the remaining solution by slow agitation at room temperature for 30 minutes. The slurry was filtered through a weighed filter paper and the residue dried to obtain the first fraction. To the filtrate was added a further amount of isopropanol (approx. 7 ml) to precipitate the second fraction which was removed in an identical manner. Continuing this process eight fractions of approximately equal weight were obtained with the last fraction being obtained by evaporation of the filtrate of the seventh precipitation. The fractions were labelled in their order of precipitation and each aliquot was recovered, dried and analyzed according to the techniques described above by a combination of infrared spectroscopy and refractive index.

Table IV

Fraction	wt (gms)	NCM Content (wt %) ⁽¹⁾
1	1.2	1.3
2	1.0	1.4
3	1.4	1.5
4	1.0	1.4
5	1.3	1.5
6	1.1	1.3
7	1.7	1.5
8	1.5	1.3

Note (1): NCM content determined by refractive index, which is proportional to the actual weight percent.

The analysis of the amino-substituted polymer shows that the polymer has a substantially uniform distribution of amino functionality among the polymer chains.

EXAMPLE 5

In this example, the amino-substituted EP polymer made by the procedures set forth in Example 3 was analyzed for chlorine. Chlorine content was determined by two procedures, i.e., (i) a total chlorine content by elemental analysis, and (ii) a measure of organic chlorine by infrared spectroscopy.

5.1 gms of the polymer was dissolved in 200 ml of hexane. The solution was filtered to remove all suspended impurities. Sufficient isopropanol to precipitate all the polymer was then slowly added with stirring to the clear filtrate. The precipitated polymer was recovered by filtration, dried and analyzed by chlorine content. The amino-substituted polymer was found to contain 101 ppm Cl by elemental analysis, and to provide 0.03 absorbance at 610 cm^{-1} by infrared spectroscopy (absorbance measured for a film of uniform thickness of 2,100 inch (0.5 mm) with similar film of nonfunctionalized EP as reference).

OLEAGINOUS COMPOSITIONS

The additives of the present invention can be incorporated into a lubricating oil (in any convenient way. Thus, these mixtures can be added directly to the lubricating oil by dispersing or dissolving the same in the lubricating oil at the desired level of concentration of the viscosity index improver dispersant. Such blending into the additional lubricating oil can occur at room temperature or elevated temperatures. Alternatively, the additives can be blended with a suitable oil-soluble solvent/diluent (such as benzene, xylene, toluene, lubricating base oils and petroleum distillates, including the various normally liquid fuels described in detail below) to form a concentrate, and then blending the concentrate with a lubricating oil to obtain the final formulation. Such additive concentrates will typically contain (on an active ingredient (A.I.) basis) from about 0.01 to about 10 wt.%, and preferably from about 0.25 to about 3 wt.%, of the additives of the present invention, with the balance comprising base oil.

The additives of the present invention find their primary utility in lubricating oil compositions which employ a base oil in which the additives are dissolved or dispersed. Such base oils may be natural or synthetic. Base oils suitable for use in preparing the lubricating oil compositions of the present invention include those conventionally employed as crankcase lubricating oils for spark-ignited and compression-ignited internal combustion engines, such as automobile and truck engines, marine and railroad diesel engines, and the like. Advantageous results are also achieved by employing the additives of the present invention in base oils conventionally employed in and/or adapted for use as power transmitting fluids, universal tractor fluids and hydraulic fluids, heavy duty hydraulic fluids, power steering fluids and the like. Gear lubricants, industrial oils, pump oils and other lubricating oil compositions can also benefit from the incorporation therein of the additives of the present invention.

These lubricating oil formulations conventionally contain several different types of additives that will supply the characteristics that are required in the formulations. Among these types of additives are included viscosity index improvers, other V.I. improver dispersants, antioxidants, corrosion inhibitors, detergents, ashless dispersants, pour point depressants, antiwear agents, friction modifiers, etc., as described in U. S. Patent 4,797,219. Some of these numerous additives can provide a multiplicity of effects, e.g., a dispersant-

oxidation inhibitor. This approach is well known and need not be further elaborated herein.

The multi-functional viscosity index improvers of the instant invention may be utilized in a concentrate form, e.g., from about 5 wt.% up to about 50 wt.%, preferably 7 to 25 wt.%, in oil, e.g., mineral lubricating oil, for ease of handling.

The additives of the present invention will be generally used in admixture with a lube oil. basestock, comprising an oil of lubricating viscosity, including natural and synthetic lubricating oils and mixtures thereof.

Natural oils include animal oils and vegetable oils (e.g., castor, lard oil) liquid petroleum oils and hydrotreated, solvent-treated or acid-treated mineral lubricating oils of the paraffinic, naphthenic and mixed paraffinic-naphthenic types. Oils of lubricating viscosity derived from coal or shale are also useful base oils.

Alkylene oxide polymers and interpolymers and derivatives thereof where the terminal hydroxyl groups have been modified by esterification, etherification, etc., constitute another class of known synthetic lubricating oils. These are exemplified by polyoxyalkylene polymers prepared by polymerization of ethylene oxide or propylene oxide, the alkyl and aryl ethers of these polyoxyalkylene polymers (e.g., methyl-polyisopropylene glycol ether having an average molecular weight of 1000, diphenyl ether of poly-ethylene glycol having a molecular weight of 500-1000, diethyl ether of polypropylene glycol having a molecular weight of 1000-1500); and mono- and polycarboxylic esters thereof, for example, the acetic acid esters, mixed C₃-C₈ fatty acid esters and C₁₃ Oxo acid diester of tetraethylene glycol.

Another suitable class of synthetic lubricating oils comprises the esters of dicarboxylic acids (e.g., phthalic acid, succinic acid, alkyl succinic acids and alkenyl succinic acids, maleic acid, azelaic acid, suberic acid, sebacic acid, fumaric acid, adipic acid, linoleic acid dimer, malonic acid, alkylmalonic acids, alkenyl malonic acids) with a variety of alcohols (e.g., butyl alcohol, hexyl alcohol, dodecyl alcohol, 2-ethylhexyl alcohol, ethylene glycol, diethylene glycol monoether, propylene glycol). Specific examples of these esters include dibutyl adipate, di(2-ethylhexyl)sebacate, di-n-hexyl fumarate, dioctyl sebacate, diisooctyl azelate, diisodecyl azelate, dioctyl phthalate, didecyl phthalate, dieicosyl sebacate, the 2-ethylhexyl diester of linoleic acid dimer, and the complex ester formed by reacting one mole of sebacic acid with two moles of tetraethylene glycol and two moles of 2-ethylhexanoic acid.

Esters useful as synthetic oils also include those made from C₅ to C₁₂ monocarboxylic acids and polyols and polyol ethers such as neopentyl glycol, trimethylolpropane, pentaerythritol, dipentaerythritol and tripentaerythritol.

Silicon-based oils such as the polyalkyl-, polyaryl-, polyalkoxy-, or polyaryloxysiloxane oils and silicate oils comprise another useful class of synthetic lubricants; they include tetraethyl silicate, tetraisopropyl silicate, tetra-(2-ethylhexyl)silicate, tetra-(4-methyl-2-ethylhexyl)silicate, tetra-(p-tertbutylphenyl)silicate, hexa-(4-methyl-2-pentoxyl)disiloxane, poly(methyl)siloxanes and poly(methylphenyl)siloxanes. Other synthetic lubricating oils include liquid esters of phosphorus-containing acids (e.g., tricresyl phosphate, trioctyl phosphate, diethyl ester of decylphosphonic acid) and polymeric tetrahydrofurans.

Unrefined, refined and rerefined oils can be used in the lubricants of the present invention. Unrefined oils are those obtained directly from a natural or synthetic source without further purification treatment. For example, a shale oil obtained directly from retorting operations, a petroleum oil obtained directly from distillation or ester oil obtained directly from an esterification process and used without further treatment would be an unrefined oil. Refined oils are similar to the unrefined oils except they have been further treated in one or more purification steps to improve one or more properties. Many such purification techniques, such as distillation, solvent extraction, acid or base extraction, filtration and percolation are known to those skilled in the art. Rerefined oils are obtained by processes similar to those used to obtain refined oils applied to refined oils which have been already used in service. Such rerefined oils are also known as reclaimed or reprocessed oils and often are additionally processed by techniques for removal of spent additives and oil breakdown products.

Compositions when containing these conventional additives are typically blended into the base oil in amounts effective to provide their normal attendant function. Representative effective amounts of such additives (as the respective active ingredients) in the fully formulated oil are illustrated as follows:

Compositions	Wt.% A.I. (Preferred)	Wt.% A.I. (Broad)
Viscosity Modifier	0.01-4	0.01-12
Detergents	0.01-3	0.01-20
Corrosion Inhibitor	0.01-1.5	.01-5
Oxidation Inhibitor	0.01-1.5	.01-5
Dispersant	0.1-8	.1-20
Pour Point Depressant	0.01-1.5	.01-5
Anti-Foaming Agents	0.001-0.15	.001-3
Anti-Wear Agents	0.001-1.5	.001-5
Friction Modifiers	0.01-1.5	.01-5
Mineral Oil Base	Balance	Balance

All of said weight percents expressed herein (unless otherwise indicated) are based on active ingredient (A.I.) content of the additive, and/or upon the total weight of any additive-package, or formulation which will be the sum of the A.I. weight of each additive plus the weight of total oil or diluent.

This invention will be further understood by reference to the following examples, wherein all parts are parts by weight, unless otherwise noted and which include preferred embodiments of the invention.

EXAMPLE 6

13.2 ml. of 5-norbornene-2-methylamine (NBMA) (12.8 gm.) was added to 200 ml of hexane. To this solution was added 81 ml. of a 20 wt.% solution of diisobutyl aluminum hydride (DIBAL-H) in hexane at 20 °C under a nitrogen blanket over a period of 90 seconds. The resultant solution containing the MNCM was introduced into the polymerization reactor to prepare an amino-substituted EP interpolymer. The conditions of polymerization are shown in Table V and the results in Table VI:

Table V

Conditions	
Reactor	= 1 liter (CFSTR)
Temperature	= 30 °C
Pressure	= 500 kPa gauge
Agitation	= 1200 rpm
Residence Time	= 9 min.
Al/V Molar Ratio	= 10 for catalyst compounds
Feeds	
Hexane	= 4.22 kg/hr.
Ethylene	= 67.5 g/hr.
Propylene	= 162.1 g/hr.
VCl ₄	= 0.53 g/hr.
EADC	= 3.42 g/hr.
Hydrogen	= 20 w ppm on ethylene
NCM (masked as above)	= 2.214 g/hr.

Table VI

Polymerization Parameters		Polymer Proportion	
Rate (g/hr)	Catalyst Efficiency (g/g)	Ethylene Content (wt%)	MNCM (conv %)
155	292	39	32

The resulting amine grafted ethylene propylene polymer was isolated as follows. 500 ml. of the hexane solution was mixed with a 10% solution of diluted HCl in 500 ml. of 1:1 water and i-PA at 65°C for 1 hour. At the end of the period, the water layer was removed and the supernatant hexane layer was washed with 500 ml. of water. The pH of the hexane layer was adjusted to 7 and the polymer recovered by evaporation of solvent. The deashed polymer was found to contain 0.06 wt.% N (as primary amine).

The amino-substituted polymer product of Example 6 was then tested for sludge inhibition (via the SIB test) and varnish inhibition (via the VIB test), as described below.

The SIB test has been found, after a large number of evaluations, to be an excellent test for assessing the dispersing power of lubricating oil dispersant additives.

The medium chosen for the SIB test was a used crankcase mineral lubricating oil composition having an original viscosity of about 325 SUS at 38°C that had been used in a taxicab that was driven generally for short trips only, thereby causing a buildup of a high concentration of sludge precursors. The oil that was used contained only a refined base mineral lubricating oil, a viscosity index improver, a pour point depressant and zinc dialkyldithiophosphate anti-wear additive. The oil contained no sludge dispersant. A quantity of such used oil was acquired by draining and refilling the taxicab crankcase at 1000-2000 mile (1610-3220 Km) intervals.

The SIB test was conducted in the following manner: the aforesaid used crankcase oil, which was milky brown in color, was freed of sludge by centrifuging for one hour at about 39,000 gravities (gs.). The resulting clear bright red supernatant oil was then decanted from the insoluble sludge particles thereby separate out. However, the supernatant oil still contained oil-soluble sludge precursors which on heating under the conditions employed by this test will tend to form additional oil-insoluble deposits of sludge. The sludge inhibiting properties of the additives being tested were determined by adding to portions of the supernatant used oil, a small amount of the particular additive being tested. Ten grams of each blend being tested were placed in a stainless steel centrifuge tube and were heated at 135°C for 16 hours in the presence of air. Following the heating, the tube containing the oil being tested was cooled and then centrifuged for about 30 minutes at room temperature at about 39,000 gs. Any deposits of new sludge that form in this step were separated from the oil by decanting the supernatant oil and then carefully washing the sludge deposits with 25 ml of heptane to remove all remaining oil from the sludge and further centrifuging. The weight of the new solid sludge that forms in the test, in milligrams, was determined by drying the residue and weighing it. The results were reported as amount of precipitated sludge in comparison with the precipitated sludge of a blank not containing any additional additive, which blank was normalized to a rating of 10. The less new sludge precipitated in the presence of the additive, the lower the SIB value and the more effective was the additive as a sludge dispersant. In other words, if the additive gave half as much precipitated sludge as the blank, then it would be rated 5.0 since the blank will be normalized to 10.

The VIB test was used to determine varnish inhibition. Here, each test sample consists of 10 grams of lubricating oil containing a small amount of the additive being tested. The test oil to which the additive was admixed was of the same type as used in the above-described SIB test. Each ten gram sample was heat soaked overnight at about 140°C and thereafter centrifuged to remove the sludge. The supernatant fluid of each sample was subjected to heat cycling from about 150°C to room temperature over a period of 3.5 hours at a frequency of about 2 cycles per minute. During the heating phase, gas which was a mixture of about 0.7 volume percent SO₂, 1.4 volume percent NO and balance air was bubbled through the test samples. During the cooling phase, water vapor was bubbled through the test samples. At the end of the test period, which testing cycle can be repeated as necessary to determine the inhibiting effect of any additive, the wall surfaces of the test flasks in which the samples are contained are visually evaluated as to the varnish inhibition. The amount of varnish imposed on the walls was rated to values of from 1 to 11 with the higher number being the greater amount of varnish, in comparison with a blank with no additive that is rated 11.

10.00 grams of SIB test oil are mixed with the selected amount of the products of Example 6 and tested in the aforescribed SIB and VIB tests. The data thereby obtained are summarized in Table VI below.


Table VI

Example 6 Product:		
Charge Amount	SIB, mg	VIB rating
0.16 g	4.17	3
0.50 g	1.26	1-2
None	10.0	--

The above data illustrate the sludge and varnish inhibiting properties of the products of this invention.

Claims

1. A lubricating oil composition comprising a major amount of lubricating oil and a minor amount of a dispersant-viscosity index improver comprising an amino-substituted interpolymer formed by a process which comprises:
 - (a) reacting at a temperature of less than 60°C, (i) at least one nitrogen-containing monomer having a general formula of:



wherein p is an integer of at least one, n is an integer of at least 1, and X is selected from the group consisting of imino, primary amino, secondary amino, and cyano groups with (ii) a masking agent comprising at least one metallic compound to form the corresponding masked nitrogen-containing monomers; and

(b) polymerizing polymer chain monomers with said masked, nitrogen-containing monomer to produce a polymerization product comprising a polymer chain including masked, nitrogen-containing monomer, wherein said polymer chain monomers comprise members selected from the group consisting of ethylene and C₃ to C₂₅ alpha-olefins; and

(c) deashing said polymerization product and recovering said amino-substituted interpolymer.

2. The composition according to claim 1 wherein said amino-substituted interpolymer is present in a concentration of from about 0.01 to 10 wt.%.
 3. The composition of claim 2, wherein said amino-substituted interpolymer comprises less than 0.03% by weight of halogen.
 4. The composition of any of claims 1 to 3, wherein said nitrogen-containing monomer is selected from the group consisting of norbornene methyl amines and norbornene carboximines.
 5. The composition of any of claims 1 to 4, wherein said masking agent comprises a non-halogenated metallic compound and said amino-substituted interpolymer comprises less than 0.10% by weight of halogen.
 6. The composition of claim 5, wherein said non-halogenated metallic compound is an organometallic compound of the formula:



wherein M is a member selected from Group IB, IIA, IIB, IIIA, IVA, and the transition metals elements, Y is at least one of R², R³, R⁴ and R⁵, wherein R²-R⁵ are independently selected from the group consisting of hydrogen, and non-halogenated C₁-C₁₆ hydrocarbyl radicals, and non-halogenated C₁-C₁₆ hydrocarbyloxy radicals and r is an integer of from 1 to 4.




Table VI

Example 6 Product:		
Charge Amount	SIB, mg	VIB rating
0.16 g	4.17	3
0.50 g	1.26	1-2
None	10.0	--

The above data illustrate the sludge and varnish inhibiting properties of the products of this invention.

Claims

1. A lubricating oil composition comprising a major amount of lubricating oil and a minor amount of a dispersant-viscosity index improver comprising an amino-substituted interpolpolymer formed by a process which comprises:
 - (a) reacting at a temperature of less than 60 °C, (i) at least one nitrogen-containing monomer having a general formula of:



- wherein p is an integer of at least one, n is an integer of at least 1, and X is selected from the group consisting of imino, primary amino, secondary amino, and cyano groups with (ii) a masking agent comprising at least one metallic compound to form the corresponding masked nitrogen-containing monomers; and
- (b) polymerizing polymer chain monomers with said masked, nitrogen-containing monomer to produce a polymerization product comprising a polymer chain including masked, nitrogen-containing monomer, wherein said polymer chain monomers comprise members selected from the group consisting of ethylene and C₃ to C₂₅ alpha-olefins; and
 - (c) deashing said polymerization product and recovering said amino-substituted interpolpolymer.

2. The composition according to claim 1 wherein said amino-substituted interpolpolymer is present in a concentration of from about 0.01 to 10 wt. %.
3. The composition of claim 2, wherein said amino-substituted interpolpolymer comprises less than 0.03% by weight of halogen.
4. The composition of any of claims 1 to 3, wherein said nitrogen-containing monomer is selected from the group consisting of norbornene methyl amines and norbornene carboximines.
5. The composition of any of claims 1 to 4, wherein said masking agent comprises a non-halogenated metallic compound and said amino-substituted interpolpolymer comprises less than 0.10% by weight of halogen.
6. The composition of claim 5, wherein said non-halogenated metallic compound is an organometallic compound of the formula:




- wherein M is a member selected from Group IB, IIA, IIB, IIIA, IVA, and the transition metals elements, Y is at least one of R², R³, R⁴ and R⁵, wherein R²-R⁵ are independently selected from the group consisting of hydrogen, and non-halogenated C₁-C₁₆ hydrocarbyl radicals, and non-halogenated C₁-C₁₆ hydrocarbyloxy radicals and r is an integer of from 1 to 4.



7. The composition of any of claims 1 to 6, wherein said polymer chain monomers are a mixture consisting essentially of ethylene and propylene.
8. The composition of any of claims 1 to 7, wherein said masked, nitrogen-containing monomers are present in a range of 0.01 wt.% to 40 wt.% by total weight of said amino-substituted interpolpolymer.
9. The composition of any of claims 1 to 8, wherein said masked amino-substituted interpolpolymer is contacted with an aqueous liquid in said de-ashing step.
10. The composition of any of claims 1 to 9, wherein said amino-substituted interpolpolymer has a number average molecular weight of from 10,000 to 200,000.
11. The lubricating oil composition of claim 10, wherein said amino-substituted interpolpolymer has a molecular weight distribution of from 1.0 to 20.0.
12. The lubricating oil composition of any of claims 1 to 9, wherein said amino-substituted interpolpolymer has a number average molecular weight of from 800 to 5,000.
13. The lubricating oil composition of claim 12, wherein said amino-substituted polymer has a molecular weight distribution of from 1.5 to 15.0.

Patentansprüche

1. Schmierölzusammensetzung, die eine größere Menge Schmieröl und eine geringere Menge eines Dispergiermittel-Viskositätsindexverbesserers umfaßt, der ein aminosubstituiertes Interpolymer umfaßt, das nach einem Verfahren gebildet worden ist, bei dem
 - (a) bei einer Temperatur von weniger als 60 °C (i) mindestens ein stickstoffhaltiges Monomer mit der allgemeinen Formel



- , in der p eine ganze Zahl von mindestens eins ist, n eine ganze Zahl von mindestens 1 ist und X ausgewählt ist aus der Gruppe bestehend aus Imino-, primären Amino-, sekundären Amino- und Cyanogruppen, mit (ii) einem mindestens eine Metallverbindung umfassenden Maskierungsmittel unter Bildung der entsprechenden maskierten stickstoffhaltigen Monomere umgesetzt wird, und
- (b) Polymerkettenmonomere mit dem maskierten stickstoffhaltigen Monomer unter Bildung eines Polymerisationsprodukts polymerisiert werden, das eine Polymerkette einschließlich maskierter stickstoffhaltiger Monomere umfaßt, wobei die Polymerkettenmonomere Mitglieder ausgewählt aus der Gruppe bestehend aus Ethylen und C₃- bis C₂₅-α-Olefinen umfassen, und
- (c) das Polymerisationsprodukt entascht und das aminosubstituierte Interpolymer gewonnen wird.

2. Zusammensetzung nach Anspruch 1, bei der das aminosubstituierte Interpolymer in einer Konzentration von etwa 0,01 bis 10 Gew.% vorhanden ist.
3. Zusammensetzung nach Anspruch 2, bei der das aminosubstituierte Interpolymer weniger als 0,03 Gew.% Halogen umfaßt.
4. Zusammensetzung nach einem der Ansprüche 1 bis 3, bei der das stickstoffhaltige Monomer ausgewählt ist aus der Gruppe bestehend aus Norbornenmethyminen und Norbornencarboximininen.
5. Zusammensetzung nach einem der Ansprüche 1 bis 4, bei der das Maskierungsmittel eine nicht-halogenierte Metallverbindung umfaßt und das aminosubstituierte Interpolymer weniger als 0,10 Gew.%



Halogen umfaßt.

6. Zusammensetzung nach Anspruch 5, bei der die nicht-halogenierte Metallverbindung eine Organometallverbindung mit der Formel



ist, in der M ein Mitglied ausgewählt aus Gruppe IB, IIA, IIB, IIIA, IVA und den Übergangsmetallelementen ist, Y mindestens einer von R^2 , R^3 , R^4 und R^5 ist, wobei R^2 bis R^5 unabhängig ausgewählt sind aus der Gruppe bestehend aus Wasserstoff und nicht-halogenierten C_1 - bis C_{15} -Kohlenwasserstoffresten und nicht-halogenierten C_1 - bis C_{15} -Kohlenwasserstoffoxyresten, und r eine ganze Zahl von 1 bis 4 ist.

7. Zusammensetzung nach einem der Ansprüche 1 bis 6, bei der die Polymerkettenmonomere eine im wesentlichen aus Ethylen und Propylen bestehende Mischung sind.

8. Zusammensetzung nach einem der Ansprüche 1 bis 7, bei der die maskierten stickstoffhaltigen Monomere im Bereich von 0,01 Gew.% bis 40 Gew.%, bezogen auf das Gesamtgewicht des aminosubstituierten Interpolymers, vorhanden sind.

9. Zusammensetzung nach einem der Ansprüche 1 bis 8, bei der das maskierte aminosubstituierte Interpolymer in der Entschungsstufe mit einer wäßrigen Flüssigkeit kontaktiert wird.

10. Zusammensetzung nach einem der Ansprüche 1 bis 9, bei der das aminosubstituierte Interpolymer ein durchschnittliches Molekulargewicht (Zahlenmittel) von 10 000 bis 200 000 aufweist.

11. Schmierölzusammensetzung nach Anspruch 10, bei der das aminosubstituierte Interpolymer eine Molekulargewichtsverteilung von 1,0 bis 20,0 hat.


12. Zusammensetzung nach einem der Ansprüche 1 bis 9, bei der das aminosubstituierte Interpolymer ein durchschnittliches Molekulargewicht (Zahlenmittel) von 800 bis 5 000 aufweist.

13. Schmierölzusammensetzung nach Anspruch 12, bei der das aminosubstituierte Interpolymer eine Molekulargewichtsverteilung von 1,5 bis 15,0 hat.

Revendications

1. Composition d'huile lubrifiante comprenant une quantité dominante d'huile lubrifiante et une petite quantité d'un agent dispersant améliorant l'indice de viscosité comprenant un interpolymère à substituant amino formé par un procédé qui comprend les étapes consistant :

(a) à faire réagir à une température inférieure à 60°C , (i) au moins un monomère azoté répondant à la formule générale :



dans laquelle p est un nombre entier au moins égal à 1, n est un nombre entier au moins égal à 1 et X est choisi dans le groupe consistant en groupes imino, amino primaire, amino secondaire et cyano, avec (ii) un agent de masquage comprenant au moins un composé métallique pour former les monomères azotés masqués correspondants ; et

(b) à polymériser les monomères d'une chaîne polymérique avec ledit monomère azoté masqué pour former un produit de polymérisation comprenant une chaîne polymérique renfermant le monomère azoté masqué, lesdits monomères de chaîne polymérique comprenant des membres du groupe consistant en l'éthylène et des alpha-oléfinés en B_3 à C_{25} ; et

(c) à éliminer les cendres du produit de polymérisation et à recueillir l'interpolymère à substituant amino.



2. Composition suivant la revendication 1, dans laquelle l'interpolymère à substituant amino est présent en une concentration d'environ 0,01 à 10 % en poids.
- 5 3. Composition suivant la revendication 2, dans laquelle l'interpolymère à substituant amino comprend moins de 0,03 % en poids d'halogène.
4. Composition suivant l'une quelconque des revendications 1 à 3, dans laquelle le monomère azoté est choisi dans le groupe consistant en norbornène-méthylamines et norbornène-carboximines.
- 10 5. Composition suivant l'une quelconque des revendications 1 à 4, dans laquelle l'agent de masquage comprend un composé métallique non halogéné et l'interpolymère à substituant amino comprend moins de 0,10 % en poids d'halogène.
- 15 6. Composition suivant la revendication 5, dans laquelle le composé métallique non halogéné est un composé organométallique de formule :
- $M(Y)_r$
- 20 dans laquelle M représente un élément faisant partie des Groupes IB, IIA, IIB, IIIA, IVA et des métaux de transition, Y représente au moins un des groupes R^2 , R^3 , R^4 et R^5 , les groupes R^2 à R^5 étant choisis indépendamment dans le groupe consistant en l'hydrogène et des radicaux hydrocarbyle en C_1 à C_{16} non halogénés et des radicaux hydrocarbyloxy en C_1 à C_{16} non halogénés, et r est un nombre entier de 1 à 4.
- 25 7. Composition suivant l'une quelconque des revendications 1 à 6, dans laquelle les monomères de chaîne polymérique consistent en un mélange formé essentiellement d'éthylène et de propylène.
8. Composition suivant l'une quelconque des revendications 1 à 7, dans laquelle les monomères azotés masqués sont présents en une quantité de 0,01 % en poids à 40% en poids sur la base du poids total de l'interpolymère à substituant amino.
- 30 9. Composition suivant l'une quelconque des revendications 1 à 8, dans laquelle l'interpolymère à substituant amino masqué est mis en contact avec un liquide aqueux dans l'étape d'élimination des cendres.
- 35 10. Composition suivant l'une quelconque des revendications 1 à 9, dans laquelle l'interpolymère à substituant amino a une moyenne numérique du poids moléculaire de 10 000 à 200 000.
- 40 11. Composition d'huile lubrifiante suivant la revendication 10, dans laquelle l'interpolymère à substituant amino a une distribution des poids moléculaires de 1,0 à 20,0.
12. Composition d'huile lubrifiante suivant l'une quelconque des revendications 1 à 9, dans laquelle l'interpolymère à substituant amino a une moyenne numérique du poids moléculaire de 800 à 5000.
- 45 13. Composition d'huile lubrifiante suivant la revendication 12, dans laquelle le polymère à substituant amino a une distribution des poids moléculaires de 1,5 à 15,0.

50

55