

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
29 January 2004 (29.01.2004)

PCT

(10) International Publication Number
WO 2004/009674 A1

- (51) International Patent Classification⁷: **C08G 75/02**
- (21) International Application Number:
PCT/JP2003/008852
- (22) International Filing Date: 11 July 2003 (11.07.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
2002-209346 18 July 2002 (18.07.2002) JP
- (71) Applicant (*for all designated States except US*):
KUREHA CHEMICAL INDUSTRY COMPANY, LIMITED [JP/JP]; 9-11, Nihonbashi Horidome-Cho 1-Chome, Chuo-Ku, Tokyo 103-8552 (JP).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **MATSUZAKI, Mitsuhiko** [JP/JP]; c/o KUREHA CHEMICAL INDUSTRY COMPANY, LIMITED, 16, Ochiai, Nishiki-Machi, Iwaki-Shi, Fukushima 974-8686 (JP). **KAGOSHIMA, Masaru** [JP/JP]; c/o KUREHA CHEMICAL INDUSTRY COMPANY, LIMITED, 16, Ochiai, Nishiki-Machi, Iwaki-Shi, Fukushima 974-8686 (JP).
- (74) Agent: **ENDO, Yukio**; TOKYO INTERNATIONAL PATENT FIRM, 2nd Floor, Miyata Building, 17-16, Nishi-Shimbashi 1-Chome, Minato-Ku, Tokyo 105-0003 (JP).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— *with international search report*
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: PROCESS FOR PRODUCING POLYARYLENE SULFIDE

(57) Abstract: A process for producing polyarylene sulfide includes: steps of reacting an aromatic dihalide compound and an alkaline metal compound in a polar organic solvent for polymerization under heating and cooling a system including the reaction mixture to recover particulate polyarylene sulfide (PAS). The system after the reaction is gradually cooled at an average cooling speed of 0.2 to 1.0 deg.C/min. selectively in a temperature range of from 1 deg.C below to 1 deg.C above a maximum system-viscosity temperature. As a result, the process can be operated at a relatively short polymerization cycle and yet provides the product PAS particles with a high and stable bulk density as to exhibit good processability in the transportation and storage, and excellent transportability in a hopper or a screw of an extruder or a molding machine.

WO 2004/009674 A1