ABSTRACT

Provided are an initial treatment agent for circulation cooling water and an initial treatment method for a circulation cooling water system by which an excellent corrosion-preventing effect can be obtained in an initial treatment of a circulation cooling water system with no use of a phosphate-based corrosion inhibitor. The initial treatment method for a circulation cooling water system of the present invention has a step of adding one or more tartaric acid compounds selected from the group consisting of tartaric acid and tartrates, and a slime control agent into a circulation cooling water system.