

METHODS FOR FORMING A DIELECTRIC LAYER WITHIN TRENCHES

ABSTRACT OF THE DISCLOSURE

A method for forming a semiconductor structure includes reacting a silicon precursor and an atomic oxygen precursor at a processing temperature of about 150°C or less to form a silicon oxide layer over a substrate. The silicon oxide layer is ultra-violet (UV) cured within an oxygen-containing environment.

FIG. 1