

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: B32B 7/12, 15/04	A1	(11) International Publication Number: WO 97/42027 (43) International Publication Date: 13 November 1997 (13.11.97)
(21) International Application Number: PCT/US97/07611 (22) International Filing Date: 5 May 1997 (05.05.97) (30) Priority Data: 60/016,917 6 May 1996 (06.05.96) US (71) Applicant: AMERON INTERNATIONAL CORPORATION [US/US]; 245 South Los Robles Avenue, Pasadena, CA 91101-2894 (US). PLS CHECKED PFB (71)(72) Applicants and Inventors: MOWRER, Norman, R. [US/US]; 1570 Coarch Wood Street, La Habra, CA 90631 (US). KANE, John, F. [US/US]; 8 Cambria Street #301, Clearwater Beach, FL 34630 (US). HULL, Colin, G. [US/US]; 2145 Via Pacheco, Palos Verdes Estates, CA 90274-2638 (US). PLS CHECKED PFB (74) Agent: LANGTON, Grant, T.; Christie, Parker & Hale, LLP, P.O. Box 7068, Pasadena, CA 91109-7068 (US).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, <u>SG</u> , SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>
(54) Title: SILOXANE-MODIFIED ADHESIVE/ADHEREND SYSTEMS (57) Abstract Adhesive/adherend systems (10) of this invention comprise a siloxane-modified adhesive component (14) and a siloxane-modified adherend component (12, 16). The siloxane-modified adhesive component (14) is prepared by combining an epoxy resin with an organosilane ingredient, a polysiloxane resin, an amine hardener, an organometallic catalyst, a base catalyst, and any thickener and extender pigment. The siloxane-modified adherend component (12, 16) is prepared using a polysiloxane resin and may also contain other resins such as epoxy, phenolic, polyester, vinyl ester, polyurethane, polyamide, melamine, furan, acrylate, thermoplastic polyvinyl chloride, polyethylene, polycarbonate, ABS, polystyrene, ethylene vinyl acetate, polyvinyl acetate, polyamide, and polypropylene resins. When placed into contact with one another, the siloxane groups in the siloxane-modified adhesive (14) and siloxane-modified adherend components (12, 16) form Si-O-Si bonds between themselves to form an attachment force that both occurs at ambient temperature within a reasonable amount of time, and that is greater than otherwise possible using adhesive/adherend systems having unmodified adhesive and/or adherend components.		