

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
21 April 2005 (21.04.2005)


PCT

(10) International Publication Number
WO 2005/035608 A2

- (51) International Patent Classification⁷: **C08G** (74) Agent: CARMEN, Dennis, V.; P.O. Box 511, Kingsport, TN 37662-5075 (US).
- (21) International Application Number: PCT/US2004/027248 (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (22) International Filing Date: 23 August 2004 (23.08.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
10/663,856 16 September 2003 (16.09.2003) US
- (71) Applicant: EASTMAN CHEMICAL COMPANY [US/US]; 100 North Eastman Road, Kingsport, TN 37660 (US).
- (72) Inventor: BONNER, Richard, Gill; 5309 Canova Ct, Kingsport, TN 37664 (US).
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,

[Continued on next page]

(54) Title: DIRECT COUPLING OF MELT POLYMERIZATION AND SOLID STATE PROCESSING FOR PET



(57) Abstract: Strands of molten polyethylene terephthalate (PET) from a PET polycondensation reactor are solidified, pelletized, and cooled only to a temperature in the range of 50°C to a temperature near the polymer T_g by contact with water. The still hot pellets are conveyed, optionally followed by drying to remove water, to a PET crystallizer. By avoiding cooling the amorphous pellets to room temperature with water and cool air, significant savings of energy are realized.

WO 2005/035608 A2



SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Published:

- *without international search report and to be republished upon receipt of that report*