

ALKALI FREE GLASS, PRODUCTION METHOD THEREFOR, AND FLAT DISPLAY
PANEL USING THE SAME

Field of the Invention

5 The present invention relates to an alkali free glass
preferable for various kinds of flat display panels such as
a TFT (Thin Film Transistor) liquid crystal display panel,
various kinds of flat display panel using the same, and a method
for producing the alkali free glass. Moreover, it ultimately
10 relates to an alkali free glass not containing an arsenic or
an antimony oxide, which is ordinarily used as a refining agent,
various kinds of flat display panel using the same, and a method
for producing the alkali free glass.

15 Background of the Invention

At the time of melting a glass material, in general, a
so-called refining agent having an effect of growing bubbles
by a gas generation by the decomposition thereof and promoting
removal of the bubbles contained in the molten glass, is added
20 in the initial stage of a step for melting the batch. Moreover,
the components also have an effect of absorbing the gas in
residual minute bubbles and promoting elimination thereof.

As such a refining agent, in the case of an alkali free
glass, in general, an arsenious oxide (As_2O_3) and an antimony
25 trioxide (Sb_2O_3) are used. The As_2O_3 provides a refining function

owing to the effect that the As_2O_3 added to the batch derives the oxygen from the vicinity in a temperature raising process so as to be an As_2O_5 , and releases the oxygen at the time of returning to the As_2O_3 at a higher temperature. Therefore, in the case of using an arsenious oxide as a refining agent, in order to promote the change from the As_2O_3 to the As_2O_5 at an initial stage of the material melting reaction, a nitrate is also added in the glass batch as an oxidizing agent. The same is applied to the case of the Sb_2O_3 .

10 Recently, in various fields, use of hazardous substances tends to be reduced. Also in the field of the glass refining agent, movement of replacing the poisonous and highly hazardous As_2O_3 with the less hazardous Sb_2O_3 is being spread. Moreover, this movement is remarkable in the field of alkali free glass
15 mainly used as an optical glass or a TFT liquid crystal display glass substrate, wherein the As_2O_3 has been used ordinarily as the refining agent.

 Moreover, in the field of the alkali free glass among the fields wherein the replacement of the As_2O_3 with the Sb_2O_3
20 is promoted, according to the performance of the TFT liquid crystal or change of the production step thereof, a composition with a higher thermal resistance is used. That leads to rise of the glass melting temperature. Accordingly, in the case the Sb_2O_3 is used as the refining agent for refining a glass
25 requiring a high melting temperature, the Sb_2O_3 is required to

be added in a larger amount. Furthermore, in order to strengthen the refining effect of the Sb_2O_3 , it may be used in combination with other components.

For example, in the alkali free glass and the production method therefor disclosed in JP-A-10-114538 (the term "JP-A" as used herein means an "unexamined published Japanese Patent"), 0.05 to 3% of an Sb_2O_3 and 0.05 to 2% of an SnO_2 based on % by weight are added as the refining agent.

In the alkali free glass and the production method therefor disclosed in JP-A-10-231139, 0.05 to 3% of an Sb_2O_3 and 0.01 to 2% of a chloride in terms of Cl_2 are added as the refining agent.

Moreover, although it is not as serious as the case of the As_2O_3 , the Sb_2O_3 also is hazardous, and an alkali free glass using neither the As_2O_3 nor Sb_2O_3 and a production method therefor have been proposed.

For example, in the alkali free glass disclosed in JP-A-9-110460, 0.5% by weight or less of a fluoride in terms of F is added at the time of preparing the glass batch.

In the alkali free glass and the production method therefor disclosed in JP-A-10-25132, 0.005 to 1.0% by weight of a sulfate in terms of SO_3 and 0.01 to 2.0% by weight of a chloride in terms of Cl_2 are added as the refining agent.

Moreover, in the alkali free glass and the production method therefor disclosed in JP-A-10-59741, 0.05 to 2.0% by

weight of an SnO_2 is added as a refining agent.

In the alkali free glass disclosed in the U. S. Patent No. 6,096,670, it is described that use of an SnO_2 and a CeO_2 in combination is effective as a refining agent in a production
5 method using a float method and a dawn drawing method.

However, in the alkali free glass and the production method therefor disclosed in JP-A-10-114538, although the SnO_2 is added at the same time for reinforcing the refining effect of the Sb_2O_3 , the refining effect comparable to that of the As_2O_3 cannot
10 be obtained by addition in a small amount, but phase separation of the glass or devitrification by precipitation of the SnO_2 itself are brought about in the case of addition in a large amount.

Moreover, in the alkali free glass and the production
15 method therefor disclosed in JP-A-10-231139, although a chloride is added at the same time as a refining agent in order to reinforce the refining effect of the Sb_2O_3 , the refining effect of a chloride is not so remarkable. Furthermore, since hazardous chlorine gas and hydrogen chloride gas are generated
20 by the decomposition thereof, a countermeasure therefor is required.

In the alkali free glass and the production method therefor disclosed in JP-A-9-110460, although a fluoride is added as a refining agent, the effect thereof is not so remarkable.
25 Moreover, since hazardous fluorine gas and hydrogen fluoride

gas are generated by the decomposition thereof, a countermeasure therefor is required.

Furthermore, in the alkali free glass and the production method therefor disclosed in JP-A-10-25132, although a sulfate
5 and a chloride are added as the refining agent, the refining effect there of is not sufficient. Moreover, also in this case, similar to the case of the alkali free glass and the production method therefor disclosed in JP-A-10-231139, since hazardous chlorine gas and hydrogen chloride gas are generated by the
10 decomposition of the chloride, a countermeasure therefor is required.

Moreover, in the alkali free glass and the production method therefor disclosed in JP-A-10-59741, although an SnO_2 is added as the refining agent, similar to the case of the alkali
15 free glass and the production method therefor disclosed in JP-A-10-114538, the refining effect comparable to that of the As_2O_3 cannot be obtained by addition in a small amount, but phase separation of the glass or devitrification by precipitation of the SnO_2 itself are brought about in the case of addition
20 in a large amount.

Furthermore, in the alkali free glass disclosed in the U. S. Patent No. 6,096,670, although use of an SnO_2 and a CeO_2 in combination as the refining agent is disclosed. It is said that the cerium oxide exists in the form of a CeO_2 in the glass
25 disclosed in the patent. However, even in an amount of about

0.5% of the upper limit, in the case the cerium exists in a tetravalent form, the glass is colored in yellow so that it is not preferable as a substrate for display, such as a TFT liquid crystal display. Moreover, a ZrO_2 is an essential component, and it is said to improve the chemical resistance and stabilize the SnO_2 and the CeO_2 . However, the ZrO_2 tends to be precipitated in the glass as the devitrification. In particular, in the case of the down drawing method wherein the molten glass is cooled down to a low temperature until forming, the devitrification can be brought about by the precipitation.

Summary of the Invention

Accordingly, an object of the invention is to provide an alkali free glass capable of solving the problems of the As_2O_3 substituent or As_2O_3 , Sb_2O_3 substituent refining agents for the alkali free glass, with a quality usable as a substrate for a flat panel display, and a production method therefor.

A first aspect of the invention is an alkali free glass comprising:

(A) a composition including:

- 50 to 70wt% of SiO_2 ;
- 7.5 to 20wt% of Al_2O_3 ;
- 4 to 15wt% of B_2O_3 ;
- 0 to 5wt% ZnO ; and
- 5 to 30wt% in total of at least one of MgO , CaO , SrO and BaO , in which an amount of MgO is 0 to 8wt%, an

amount of CaO is 0 to 10wt% of CaO, an amount of SrO is 0 to 8wt% and an amount of BaO is 0 to 15wt%,

wherein the composition shows a temperature for a viscosity at 10^2 dPas being equal to or higher than 1,615°C, and the composition does not substantially contain each of ZrO₂ and an alkali metal oxide;

(B) total tin oxide in an amount of 0.1 to 2wt%, as a refining agent, based on the weight of the composition (A); and

(C) at least one of total cerium oxide, total manganese oxide, total tungsten oxide, total tantalum oxide and total niobium oxide in an amount of 0.1 to 1wt%, as a refining agent, based on the weight of the composition (A).

A second aspect of the invention is a method for producing an alkali free glass, comprising the steps of:

i) preparing a glass batch comprising: in terms of an oxide

50 to 70wt% of SiO₂;

7.5 to 20wt% of Al₂O₃;

4 to 15wt% of B₂O₃;

0 to 5wt% of ZnO; and

5 to 30wt% in total of at least one of MgO, CaO, SrO and BaO, in which an amount of MgO is 0 to 8wt%, an amount of CaO is 0 to 10wt% of CaO, an amount of SrO is 0 to 8wt%, and an amount of BaO is 0 to 15wt%,

wherein the glass batch shows a temperature for

a viscosity at 10^2 dPas being equal to or higher than $1,615^\circ\text{C}$, and the glass batch does not substantially contain each of ZrO_2 and an alkali metal oxide;

ii) melting the glass batch; and

5 iii) forming the melted batch,

wherein SnO_2 and at least one of CeO_2 , MnO_2 , WO_3 , Ta_2O_5 and Nb_2O_5 are added to the glass batch as a refining agent in amounts of 0.1 to 2wt% and 0.1 to 1wt%, respectively, based on the weight of the glass batch.

10 In the invention, meaning of the total tin oxide and the SnO_2 in the invention is described (hereinafter the same is applied to the other refining components). These refining agents are added to the batch in the form of the highest valence number oxide (SnO_2 in the case of the tin oxide) among the stable
15 oxides. These oxides provide the refining effect by releasing the oxygen at the time of temperature rise because the low valence number oxide becomes stable. Moreover, at the time of temperature reduce, since the original high valence number oxide becomes stable, a part thereof bonds with the residual oxygen
20 remaining in the surrounding molten glass again so as to return to the original high valence number oxide. Therefore, the high valence number oxide and the low valence number oxide co-exist in the cooled glass, but it is difficult to determine the quantity of them independently. Here, in the glass composition, these
25 oxides are described as the total tin oxide, and the content

thereof is described by the amount in the case that all thereof exist as the high valence number oxide for the convenience.

The phrase: "do not substantially contain each of ZrO_2 and an alkali metal oxide" in the present specification means
5 that each of ZrO_2 and an alkali metal oxide is not contained except for being contained as an impurity. The alkali free glass of the present invention does not include a glass batch, to which each of ZrO_2 and an alkali metal oxide is intentionally added.

10 In the alkali free glass of the invention, it is preferable that the total tin oxide content is 0.4 to 0.8wt%, based on the weight of the composition (A).

Furthermore, it is preferable that at least one of the refining components used together with the total tin oxide is
15 a cerium oxide, and the content thereof is more than 0.5%, based on the weight of the composition (A).

Moreover, in the method for producing an alkali free glass of the invention, it is preferable that the amount of the SnO_2 added as the refining agent is 0.4 to 0.8% by weight, based
20 on the weight of the glass batch.

Furthermore, it is preferable that at least one of the refining components added together with the SnO_2 is a CeO_2 , and the addition amount thereof is more than 0.5%, based on the weight of the glass batch.

25 Moreover, in the method for producing an alkali free glass,

it is preferable that the forming step iii) is carried out by a down draw method.

A third aspect of the invention is a flat display panel comprising a pair of glass substrates opposed to each other and a closed space formed between the pair of glass substrates, wherein at least one of the pair of glass substrates is the alkali free glass according to the present invention.

Detailed Description of the Invention

Hereinafter, the reason for limitation of the alkali free glass of the invention will be explained. The compositions mentioned below are described based on % by weight.

The SiO_2 is a component for forming a glass network. In the case the content thereof is less than 50%, the chemical resistance of the glass is deteriorated as well as the strain point is lowered so that a sufficient thermal resistance cannot be obtained. In the case it is more than 70%, the viscosity in the high temperature range becomes higher so that the melting operation becomes difficult.

The Al_2O_3 is a component for restraining the devitrification tendency of the glass as well as for improving the thermal resistance. In the case the content thereof is less than 7.5%, devitrification occurs easily. In the case it is more than 20%, the acid resistance is lowered as well as the melting become difficult.

The B_2O_3 is a component for improving the glass melting

tendency, for restraining devitrification tendency, and for improving the chemical resistance, in particular the resistance to a buffered hydrofluoric acid. In the case the content thereof is less than 4%, the melting tendency of the glass is deteriorated
5 as well as the resistance to a buffered hydrofluoric acid becomes insufficient. In the case it is more than 15%, the strain point is lowered so that the thermal resistance becomes insufficient.

At least one selected from the group consisting of MgO, CaO, SrO and the BaO is contained, and the total amount thereof
10 is 5 to 30%. In the case it is less than 5%, the glass melting operation becomes difficult. In the case it is more than 30%, the expansion coefficient of the glass becomes too large.

The MgO is a component for improving the melting tendency of the glass without much lowering the strain point. However,
15 in the case it is more than 8%, the devitrification temperature of the glass becomes higher. The preferable range is less than 5%. The CaO is a component having the same effect as that of the MgO. In the case it is contained more than 10%, the devitrification temperature of the glass becomes higher. The
20 SrO is a component capable of improving the melting tendency without deteriorating the devitrification tendency of the glass. In the case it is contained by more than 8%, the expansion coefficient of the glass becomes too large. The preferable range is less than 5%. The BaO is a component capable of
25 restraining the devitrification property of the glass. In the

case it is more than 15%, the expansion coefficient of the glass becomes too large.

The ZnO is a component capable of restraining the devitrification tendency of the glass as well as improving the melting tendency. In the case it is contained by more than 5%, the strain point is lowered.

Moreover, the TiO₂ can be added up to about 5% within the range not deteriorating the function as a display substrate.

Next, the characteristic of the refining effect in the method for producing an alkali free glass according to the invention will be explained.

It is characteristic of the invention that the SnO₂ is used as the main refining agent, and the CeO₂, the MnO₂, the WO₃, the Ta₂O₅, and the Nb₂O₅ are used alone or a combination of a plurality in order to reinforce the function thereof and obtain a larger refining effect.

The SnO₂ provides the same refining effect as that of the As₂O₃ and the Sb₂O₃ of releasing the oxygen by the change of the stable state from the tetravalent to divalent by temperature rise, and thereby promoting a defoaming by growing bubbles existing in the glass molten liquid. However, since the temperature range of releasing the oxygen is higher than that of the As₂O₃ and the Sb₂O₃, it is most preferable for refining of glass of a composition having a temperature for a viscosity at 10² dPas being equal to or higher than 1,615°C; glass having

a composition to be melted hardly, which is aimed at in the invention. In the case the amount of SnO_2 is less than 0.1%, the refining effect is insufficient even if the auxiliary components co-exist. In the case it is more than 2%, the glass
5 is phase separated or devitrified by precipitation thereof. The preferable range thereof is 0.4 to 0.8%.

Moreover, in the case the glass forming method is a method of rapidly cooling the molten glass thereof from a temperature higher than the glass phase separation temperature or the
10 devitrification temperature by a rate higher than the rate of causing the phase separation or the devitrification, such as a rollout method, by adding the SnO_2 in an amount close to the upper limit amount, it is possible to refine a glass of a highly thermally resistant composition, such as a composition having
15 a temperature for viscosity at 10^2 dPas being equal to or higher than $1,615^\circ\text{C}$. However, in the draw method, the float method, and in particular, the down drawing method capable of obtaining a high quality substrate glass, which are presently used as a forming method for such an alkali free glass, the cooling
20 rate of the molten glass is slower than the rate of causing the phase separation or the devitrification in most cases. Therefore, it is substantially difficult to refine by only adding the SnO_2 .

In the down drawing method, a molten glass is downwardly
25 drawing from a slot so as to form the molten glass into a plate-like

shape.

On the other hand, by use of at least one selected from the group consisting of CeO_2 , MnO_2 , WO_3 , Ta_2O_5 and Nb_2O_5 in combination with the SnO_2 , which is characteristic of the invention, a larger refining effect can be obtained by reinforcing the refining function. Forming can be enabled also in the case of the draw method, wherein the cooling rate of the molten glass is low, without the risk of phase separation or devitrification. The reason why the refining effect is promoted by adding these components alone or in a plurality in combination with the SnO_2 is not known. But it is considered that since the temperature range of releasing the oxygen by these oxides is lower than that of the SnO_2 , the oxygen activity of the molten glass is made higher at the time of melting the material by the release of the oxygen by these components, and thereby the SnO_2 oxygen release is executed at a higher temperature and a lower rate so that it contributes further effectively to refining of a hardly melted composition with a high viscosity at a high temperature.

Moreover, as to the relationship between the tin oxide and the other oxides in terms of the valence number, since the glass is colored into yellow in the case the CeO_2 is added alone, it is considered to exist mainly in the tetravalent form on the higher valence number side. In contrast, since the glass can be transparent in the case it is added together with the

SnO₂, it is considered that the Ce continues to exist mainly in the trivalent form on the lower valence number side, and the Sn returns to be in the tetravalent form on the higher valence number side by partially bonding with a dissolved oxygen again.

5 In the case of the other oxides, although it cannot be presumed easily by the color, or the like, it is presumed that similarly the Sn is in the state partially returned to the tetravalent form on the higher valence number side, and the other oxides remain to exist mainly on the lower valence number side.

10 As a refining agent other than these, an As₂O₃, an Sb₂O₃, a chloride (such as a barium chloride), a fluoride (such as a calcium fluoride), a sulfate (such as a calcium sulfate), or the like, which are commonly used refining agents, may be added. However, since these refining agents are hazardous and
15 generate a hazardous gas, it is preferable substantially not to added the same.

The flat display panel in the present invention includes a flat display panel such as a glass panel for TFT liquid crystal display.

20 Hereinafter, based on examples, the invention will be explained. A batch to have the composition shown in the Table 1 in terms of the oxides was prepared using a silica powder, an alumina, a boric acid, a basic magnesium carbonate, a calcium carbonate, a strontium nitrate, and a barium nitrate. To the
25 batch, the additives shown in the Tables 2 and 3 were added

and mixed well. (The tables are indicated by % by weight.)

TABLE 1

SiO ₂	Al ₂ O ₃	B ₂ O ₃	MgO	CaO	SrO	BaO
59.5	14.5	10.0	1.5	4.5	4.0	6.0

5 TABLE 2

		SnO ₂	CeO ₂	MnO ₂	WO ₃	Ta ₂ O ₅	Nb ₂ O ₅
Example	1	0.4%	0.3%	0	0	0	0
	2	0.4%	0.6%	0	0	0	0
	3	0.5%	0	0.5%	0	0	0
	4	0.6%	0	0	0.6%	0	0
	5	0.7%	0	0	0	0.7%	0
	6	0.7%	0	0	0	0	1.0%

TABLE 3

		As ₂ O ₃	SnO ₂	CeO ₂	MoO ₃
Comparative Example	1	0	0	0	0
	2	0.5%	0	0	0
	3	0	0.5%	0	0
	4	0	0	0.5%	0
	5	0	0.5%	0	0.5%

The batches prepared as mentioned above were melted at
 10 1,600°C for 4 hours using a platinum crucible. Then, the molten

glass were poured onto a stainless steel plate and formed into a plate-like form. Then, they were cooled down gradually to a room temperature. Measurement results of the number and the size of bubbles contained in the obtained glasses are shown in the Tables 4 and 5. Since the density of the existing bubbles in the glass differs by the portion, and it is not homogeneous, the number of bubbles was measured at the same position by 1 to 5 cm square area at the center of the plate-like glass, and was converted to the number per 100 g. The temperature at which the glasses of the examples 1 to 6 and the comparative examples 1 to 3 have a viscosity of 10^2 dPas was about 1,650°C in all cases.

TABLE 4

		number of bubbles (pieces/100 g)	maximum bubble size (μm)	coloring
Example	1	2670	about 800	none
	2	860	about 800	none
	3	2650	about 1000	slightly greenish
	4	2330	about 1000	none
	5	2490	about 1000	none
	6	1250	about 1000	none

TABLE 5

		number of bubbles (pieces/100 g)	maximum bubble size (μm)	coloring
Comparative		10700	about 100	none
Example	1			
	2	670	about 700	none
	3	5300	about 1000	none
	4	8000	about 200	yellow
	5	10700	about 100	slightly yellowish

As it is apparent from the examples 1 to 6 and the comparative examples 1 to 5 shown in the Tables 4 and 5, it is observed that the bubble elimination is promoted by adding the SnO_2 in combination with at least one selected from the group consisting of CeO_2 , MnO_2 , WO_3 , Ta_2O_5 and Nb_2O_5 , compared with the case of not adding an additive, the case of adding the CeO_2 , the MoO_3 , and the SnO_2 in an amount of 0.5% as the additive, or the case of adding the SnO_2 and the MoO_3 each in an amount of 0.5%. In particular, in the case of adding 0.4% of the SnO_2 and 0.6% of the CeO_2 in the example 2, it is observed that the refining effect comparable to the case of adding 0.5% of the As_2O_3 in the comparative example 2 can be obtained.

Moreover, the bubble size of the examples are larger than the case of not adding a refining agent, and the case of adding

the CeO_2 alone, or adding the MoO_3 together with the SnO_2 , and it is anticipated that the difference of the refining effect can further be widened by further prolonging the melting time.

Furthermore, since the glass is colored into yellow in the case of adding the CeO_2 alone by 0.5% in the comparative example 4, it is learned that the Ce in the glass exists mainly in the tetravalent form. In contrast, in the case of adding the SnO_2 and the CeO_2 in a combination in the examples 1 and 2, coloring is hardly observed in the glass, and thus it is learned that the Ce in the glass exists mainly in the trivalent form.

According to the invention, by adding the SnO_2 as a refining agent in combination with at least one of the CeO_2 , the MnO_2 , the WO_3 , the Ta_2O_5 , and the Nb_2O_5 , bubble can be eliminated from a glass substantially not containing an alkali metal oxide, having a composition requiring a high melting temperature.

The entire disclosure of each and every foreign patent application from which the benefit of foreign priority has been claimed in the present application is incorporated herein by reference, as if fully set forth.



What is claimed is:

1. An alkali free glass comprising:

(A) a composition including:

50 to 70wt% of SiO_2 ;

5 7.5 to 20wt% of Al_2O_3 ;

4 to 15wt% of B_2O_3 ;

0 to 5wt% ZnO ; and

5 to 30wt% in total of at least one of MgO , CaO ,
10 SrO and BaO , in which an amount of MgO is 0 to 8wt%, an
amount of CaO is 0 to 10wt% of CaO , an amount of SrO is
0 to 8wt% and an amount of BaO is 0 to 15wt%,

wherein the composition shows a temperature for
a viscosity at 10^2 dPas being equal to or higher than
1,615°C, and the composition does not substantially
15 contain each of ZrO_2 and an alkali metal oxide;

(B) total tin oxide in an amount of 0.1 to 2wt%, as a
refining agent, based on the weight of the composition (A);
and

(C) at least one of total cerium oxide, total manganese
20 oxide, total tungsten oxide, total tantalum oxide and total
niobium oxide in an amount of 0.1 to 1wt%, as a refining agent,
based on the weight of the composition (A).

2. The alkali free glass according to claim 1, which
25 comprises the total tin oxide (B) in an amount of 0.4 to 0.8wt%



based on the weight of the composition (A).

3. The alkali free glass according to claim 1, which comprises the total cerium oxide in an amount of more than 0.5wt%,
5 based on the weight of the composition (A).

4. A flat display panel comprising a pair of glass substrates opposed to each other and a closed space formed between the pair of glass substrates, wherein at least one of
10 the pair of glass substrates is the alkali free glass according to claim 1.

5. A method for producing an alkali free glass, comprising the steps of:

15 i) preparing a glass batch comprising: in terms of an oxide

50 to 70wt% of SiO_2 ;

7.5 to 20wt% of Al_2O_3 ;

4 to 15wt% of B_2O_3 ;

0 to 5wt% of ZnO ; and

20 5 to 30wt% in total of at least one of MgO , CaO , SrO and BaO , in which an amount of MgO is 0 to 8wt%, an amount of CaO is 0 to 10wt% of CaO , an amount of SrO is 0 to 8wt%, and an amount of BaO is 0 to 15wt%,

wherein the glass batch shows a temperature for
25 a viscosity at 10^2 dPas being equal to or higher than



1,615°C, and the glass batch does not substantially contain each of ZrO_2 and an alkali metal oxide;

ii) melting the glass batch; and

iii) forming the melted batch,

5 wherein SnO_2 and at least one of CeO_2 , MnO_2 , WO_3 , Ta_2O_5 and Nb_2O_5 are added to the glass batch as a refining agent in amounts of 0.1 to 2wt% and 0.1 to 1wt%, respectively, based on the weight of the glass batch.

10 6. The method for producing an alkali free glass according to claim 5, wherein SnO_2 in an amount of 0.4 to 0.8wt% based on the weight of the glass batch is added to the glass batch.

15 7. The method for producing an alkali free glass according to claim 5, wherein CeO_2 in an amount of more than 0.5wt% based on the weight of the glass batch is added to the glass batch.

20 8. The method for producing an alkali free glass according to claim 5, wherein the forming step iii) is carried out by a down drawing method.