

WELDING METHOD

The invention relates to a method for welding a first hose end at a joint with a second hose end in a seam that extends on a circumference of the first hose end, wherein a protective layer is initially applied at the joint in the first hose end, the second hose end is pushed beyond the joint over the first hose end and the hose ends are eventually pressed together flat at the joint between two clamping jaws that are being moved towards each other and welded together in this position, wherein the protective layer prevents a welding of an inside of the first hose end.

US 6,090,233 A proposes to insert a protective layer configured as a flat heat shield made from starch, wax paper, fiber glass, cotton, wool, asbestos or Teflon® into an interior of a hose end of a watering hose in order to weld two hose ends. Welding the hose ends with the known method causes leakage at both lateral edges of the heat shield.

OBJECT

It is an object of the invention to improve the tightness of the hose connection.

SOLUTION

Based on the known method it is proposed according to the invention that the protective layer is applied to an inside of the first hose end. Leakage at edges of the known heat shield is thus prevented.

The protective layer can be limited to half of a circumference according to the method according to the invention. In order to prevent a welding of the inside the position of the protective layer along the circumference has to be considered when inserting the protective layer between the clamping jaws.

Advantageously the hose ends are initially erected according to the method according to the invention after welding two first partial seams and then pressed together flat again

transversal to the first partial seams and welded in two additional partial seams, wherein the first partial seams and the additional partial seams form the seam. During flat compression of the hose so called “cat eyes” are formed at both ends of the cross section with increasing wall thickness of the hose ends. The hose is deflected by 180° in a small circumferential section wherein the outside is stretched and the inside is compressed. During opening of the hose the inside is stretched accordingly. A weld seam applied at this location would thus be weakened. The two step welding prevents the weakening at the “cat eyes”. Leak tightness is thus increased further in particular at larger wall thicknesses of the hose ends.

Advantageously the first partial seams and the additional partial seams cover different portions of the circumference according to this method. Simultaneously with the welding a lettering or another marking can be applied to the second hose end. The size of the marking is limited to the size of the clamping jaws, thus to the size of the respective partial seam. The asymmetrical welding in two steps with different length partial seams facilitates a larger marking on the hose end due to the longer partial seam.

Advantageously the first partial seams and the second partial seams overlap. Thus gaps between the first and the second partial seams are avoided. Further advantageously the first and the second partial seams cover up to 120% of the circumference in combination.

Advantageously the longer clamping jaws and thus the longer partial seams cover at least 60% of the circumference. Further advantageously the longer clamping jaws do not cover more than 80% of the circumference in order to prevent an excessive mechanical load and thus damages to the extruded material in the “cat eyes”.

Advantageously the first hose end and/or the second hose end is made from a thermoplastic polyurethane material in a method according to the invention. Thermoplastic polyurethane (TPU) is particularly suited for extrusion. The method

according to the invention can also be used in particular also to weld a TPU hose without burr with a hose made from another thermoplastic material.

Advantageously the hose ends are thermally welded in a method according to the invention. Thermal welding methods, thus methods where the surfaces to be welded are heated far enough so that they flow together and form a bonded unit are performed particular by high frequency, by laser or by electron beam. Alternatively the hose ends can also be welded chemically in particular by temporarily partially dissolving the surfaces to be welded.

Advantageously the clamping jaws are transparent in a method according to the invention. Transparent clamping jaws are permeable for a laser or electron beam.

Advantageously the protective layer is applied to the inside by a roller in a method according to the invention. Alternatively the protective layer can be applied to the inside using a different method, e.g. sprayed on. Further advantageously the protective layer can be loosely applied to the inside.

Advantageously the protective layer cures before welding according to the method according to the invention. Alternatively the protective layer can be made from a material that is already hard during application.

Advantageously the protective layer is made from a lacquer that is temperature resistant up to at least 250 °C after curing in a method according to the invention. Temperature resistant lacquers based on polyester, PVC-mix, mix polymerisates, polyvinyl acetate, polyvinyl butyral, nitro cellulose, acetyl cellulose or cellulose acetate are well known. Alternatively the protective layer can be made from a temperature resistant foil, e.g. a metal foil, in particular aluminum which is applied to the inside before the welding.

The invention furthermore proposes a method for producing an inner tube for a vehicle wheel wherein a blank is cut from an endless hose shaped extruded material and

closed into a torus shape and two hose ends of the blank are welded to form the inner tube as described supra. A generic method of this type for producing inner tubes is known in the art.

EMBODIMENT

The invention is subsequently described based on an embodiment with reference to drawing figures, wherein:

FIG. 1 illustrates a cut through an inner tube; and

FIG. 2 illustrates a detail of the method according to the invention

In a method according to the invention an inner tube 1 for a non-illustrated 29" wheel of a bicycle is produced. The inner tube 1 is not illustrated to scale in FIG. 1 in a sectional view of the joint. The inner tube 1 has an outer diameter 2 of 30 mm. The wall thickness 3 of the inner tube 1 is 350 μm . The inner tube 1 is fabricated endless by blow foil extrusion from thermoplastic polyurethane (TPU) on a polyester base.

The extruded material is cut into non-illustrated blanks of 2030mm respectively precisely orthogonal to the longitudinal hose axis 4.

A first hose end 5 of the blank is opened so that the inside 6 becomes visible and easily accessible. A protective layer 7 made from a heat resistant clear lacquer (e.g. with the trade name MOTIP 04033) with a thickness of approximately 5 μm is applied to the inside 6 circumferentially to a depth of 20 mm in a direction of the longitudinal hose axis 4 using a small felt roller.

The protective layer 7 wets an entire circumference of the inside 6. Thus locally limited welds are avoided which would degrade a quality of the weld seam and would even lead to not being able to separate the two inner foils from each other.

After a drying time of approximately 30 minutes during which the protective layer 7 cures the first hose end 5 is inserted into the second hose end 9 so that the two overlap by approximately 10 mm. The protective layer 7 is temperature resistant up to 800 °C.

The first hose end 5 and the second hose end 9 are pressed together flat as illustrated in FIG. 2 and are initially welded together by high frequency between two first clamping jaws 10 with a length 11 of approximately 33 mm which corresponds to approximately 70% of the hose width. Simultaneously the first clamping jaws 10 emboss and print the logo of the manufacturer and technical specifications and test seals of the inner tube 1 onto the joint.

Then the inner tube 1 is erected in the portion of the cat eyes 12, pressed together again flat transversal to the first partial seams 13 and welded together again between two second clamping jaws 14 over a length 15 of approximately 19 mm which corresponds to approximately 40% of the hose width. The electrodes are made from brass and have a non-illustrated width of 5 mm in a direction of the hose longitudinal axis 4. The clamping jaws 10, 14 and thus the first partial seams 13 and the second partial seams cover 110% of the circumference in combination.

REFERENCE NUMERALS AND DESIGNATIONS

1	inner tube
2	outer diameter
3	wall thickness
4	longitudinal hose axis
5	first hose end
6	inside
7	protective layer
8	thickness
9	second hose end
10	first clamping jaw
11	length
12	cat eye
13	first partial seam
14	second clamping jaw
15	length

Patent Claims

What is claimed is:

1. A method for welding a first hose end (5) at a joint with a second hose end (9) in a seam that extends on a circumference of the first hose end (5),
wherein a protective layer (7) is initially applied at the joint in the first hose end (5),
thereafter the second hose end (9) is pushed beyond the joint over the first hose end (5) and the hose ends (5, 9) are eventually pressed together flat at the joint between two clamping jaws (10, 14) that are moved towards each other and the hose ends are welded together in this position, wherein the protective layer (7) prevents a welding of an inside (6) of the first hose end (5),
characterized in that the protective layer (7) is applied to an inside (6) of the first hose end (5).
2. The method according to the preceding claim, characterized in that the hose ends (9) are initially erected after welding the two first partial seams (13) and then pressed together again flat transversal to the first partial seams (13) and welded in two additional partial seams wherein the first partial seams (13) and the additional partial seams form the seam.
3. The method according to the preceding claim, characterized in that the first partial seams (13) and the additional partial seams cover different portions of the circumference.
4. The method according to one of the preceding claims, characterized in that the first hose end (5) and/or the second hose end (9) are made from thermoplastic polyurethane.

5. The method according to one of the preceding claims, characterized in that the hose ends (5, 9) are thermally welded.
6. The method according to one of the preceding claims, characterized in that the clamping jaws are transparent.
7. The method according to one of the preceding claims, characterized in that the protective layer (7) is applied by a roller to the inside (6).
8. The method according to one of the preceding claims, characterized in that the protective layer (7) cures before the welding.
9. The method according to the preceding claim, characterized in that the protective layer (7) is made from a lacquer that is heat resistant up to at least 250 °C after curing.
10. The method for producing the inner tube (1) for a vehicle wheel, characterized in that a blank is cut from an endless hose shaped extruded material and closed into a torus shape and the two hose ends (5, 9) of the blank are welded together according to one of the preceding claims to form the inner tube (1).