

Description

Background of the Invention

Field of the invention

The present invention relates to a superconducting thin film and a method for preparing the same. More particularly, it relates to a superconducting thin film of compound oxide having a high critical temperature and also possessing lasting stability for a long period and a method for preparing the same.

Description of the related art

The superconductivity is a phenomenon which is explained to be a phenomenon of a kind of phase change of electrons under which the electrical resistance become zero and the perfect diamagnetism is observed. Thus, under the superconducting condition, electric current of a very high current density can be delivered without any loss of power.

Therefore, if the superconducting power cable is realized, the power loss of the order of 7 % which is inevitable in the conventional power cables can be reduced greatly. Realization of superconducting coils for generating a very high magnetic field is expected to accelerate development in the field of fusion power generation in which the electric power is consumed beyond its output under the present technology, as well as in the field of MHD power generation or motor-generators. The development of superconductivity are demanded also in the other industrial fields such as in the field of electric power reservation; in the field of transportation for example magnetic levitation trains, or magnetically propelling ships; in the medical field such as high-energy beam radiation unit; or in the field of science such as NMR or high-energy physics.

In addition to the abovementioned power electric applications, the superconducting materials can be used in the field of electronics, for example, as a device using the Josephson effect in which quantum efficiency is observed macroscopically when an electric current is passed through a weak junction arranged between two superconductors. Tunnel junction type Josephson device which is a typical application of the Josephson effect is expected to be a high-speed and low-power consuming switching device owing to smaller energy gap of the superconducting material. It is also expected to utilize the Josephson device as a high sensitive sensors or detectors for sensing very weak magnetic field, microwave, radiant ray or the like since variation of electromagnetic wave or magnetic field is reflected in variation of Josephson effect and can be observed as a quantum phenomenon precisely. Development of the superconducting devices is also demanded in the field of high-speed computers in which the power consumption per unit area is reaching to the upper limit of the cooling capacity with increment of the integration density in order to reduce energy consumption.

However, the critical temperature could not exceed 23.2 K of Nb_3Ge which was the the highest T_c for all studies for the past ten years.

Possibility of existence of a new type of superconducting materials having much higher T_c was revealed by Bednorz and Müller who discovered a new oxide type superconductor in 1986 [Z. Phys. B64 (1986) 189]

It had been known that certain ceramics material of compound oxides exhibit the property of superconductivity. For example, U. S. patent No. 3,932,315 discloses Ba-Pb-Bi type compound oxide which shows superconductivity and Japanese patent laid-open No. 60-173,885 discloses that Ba-Bi type compound oxides also show superconductivity. These superconductors, however, possess rather lower transition temperatures of about 10 K and hence usage of liquidized helium (boiling point of 4.2 K) as cryogen is indispensable to realize superconductivity.

The new type compound oxide superconductor discovered by Bednorz and Müller is represented by $[\text{La}, \text{Sr}]_2\text{CuO}_4$ which is called as the K_2NiF_4 -type oxide having a crystal structure which is similar to known perovskite type oxides. The K_2NiF_4 -type oxides show such higher T_c as 30 K which are extremely higher than known superconducting materials.

It was also reported in the news paper that C. W. Chu et al discovered in the United States of America another superconducting material so called YBCO type represented by $\text{YBa}_2\text{Cu}_3\text{O}_{7-x}$ having the critical temperature of in the order of 90 K in February 1987. Still another type new superconducting material is a compound oxide of Bi-Sr-Ca-Cu-O system and Ti-Ba-Ca-Cu-O system which exhibit such high T_c as more than 100 K and which are chemically much stable than the abovementioned YBCO type compound oxide or the like.

And hence, possibility of existence of high-temperature superconductors have burst on the scene.

The new type superconductor of compound oxide, however, is not stable and hence their superconductivity is lost or deteriorated with the passing of time. In fact, there is such a tendency that their critical temperature and critical current density drop gradually with the passing of time. This tendency is noticeable in case of a thin film prepared by physical vapour deposition technique. This fact is explained by defectiveness of oxygen deficiency, in other words, imperfect oxygen contents in the crystal. It is known that its superconducting property is influenced by the oxygen contents or oxygen deficiency in the crystalline structure. In order to overcome such drawback, it is a usual practice that the deposited thin film prepared by the physical vapour deposition technique is heat-treated or annealed, particularly in the final stage of preparation, under a higher partial pressure of oxygen gas. In fact, if the deposited thin film is not heat-treated, its superconducting property is very poor.

However, even if the deposited thin film is heat-treated, it is impossible to prevent the thin film from deterioration of superconducting property which occur with the passing of time. Such deterioration may be caused by the abovementioned defectiveness of oxygen deficiency resulting from that the compound oxide react with water in air and that oxygen in the crystal escape with the passing of time or so on, so that quasi-stable phase of the superconducting compound oxide is transformed to a non-superconducting phase. The deterioration of superconductivity, in other words a phenomenon that the superconducting property is lost gradually in time is a big problem of compound oxide type superconductors in their actual use.

Therefore, an object of the present invention is to overcome the abovementioned problems of the conventional technique and to provide a superconducting thin film improved in stability during storage or during actual use and a method for preparing the same.

WO- 89/00343 which is comprised in the state of the art according to Article 54(3) EPC and cannot be considered in deciding whether there has been an inventive step in the present invention, discloses the use of an inert, passivating layer of Si_3N_4 , SiO_2 or AlN on a superconducting material of the YBaCuO type.

Summary of the Invention

The present invention provides a method for protecting an outer surface of a superconducting thin film wherein a superconducting thin film of a copper oxide compound having a crystal structure of perovskite or quasi-perovskite and being deposited on a substrate by physical vapour deposition is covered with a protective layer of inorganic glass deposited on said outer surface of the superconducting thin film by physical vapour deposition while said substrate is heated at a temperature between 230°C and $1,410^\circ\text{C}$.

The abovementioned inorganic glass can produce a hard and high density protective layer. Since they are chemically stable and can be deposited on the superconducting thin film layer at a lower temperature such as room temperature, they do not exert a bad influence upon the superconducting thin film so that they can advantageously maintain the superconducting property of the thin film. Since the inorganic glass has not special crystalline structure, the protective layer can be deposited uniformly and the preparation of such amorphous protective layer is relatively easier than that of crystalline protective layer.


According to a preferred embodiment, the inorganic glass is preferably phosphorous-silicate glass or a low-melting point glass such as the glass comprising 85% by weight of PbO , 7.5% by weight of SiO_2 and 7.5% by weight of B_2O_3 . The protective layer of inorganic glass has a very high density and is chemically stable so that it can suppress liberation of oxygen from the crystalline superconducting thin film and prevent a reaction between the oxygen in the superconducting compound oxide and water in air.

The protective layer of inorganic glass can be prepared by the conventional physical vapour deposition (PVD) technique, such as vacuum deposition, sputtering, ion plating or the like.

Selection of the abovementioned protective layers depend on type or system of the copper oxide compound used.

The superconducting thin film can be composed of compound oxide of an element α selected from IIa group of the Periodic Table, an element β selected from IIIa group of the Periodic Table, and copper.

Particularly, the superconducting thin film is preferably a compound oxide represented by the general formula:



in which α and β means the same definition as above, x is an atomic ratio of β with respect to $(\alpha + \beta)$ and has a range of $0.1 \leq x \leq 0.9$, and y and z are respective atomic ratios with respect to $(\alpha_{1-x}\beta_x)$ which is considered to be equal to 1 and each satisfy ranges of $0.4 \leq y \leq 3.0$ and $1 \leq z \leq 5$ respectively.

According to a preferred embodiment of the present invention, the element α is Ba or Sr and the element β is at least one element selected from a group comprising Y, La, Gd, Dy, Ho, Er, Tm, Yb, Nd, Sm,

Eu and Lu. From 10 to 80 % of the element α may be substituted by one or more than one of other elements selected from IIa group of the Periodic Table. The element β may be a combination of more than two other elements selected from IIIa group of the Periodic. A portion of these components may be substituted if necessary by at least one of elements selected from a group comprising Al, Fe, Co, Ni, Zn, Ag and Ti.

An atomic ratio of α to β depends on the type or system of the compound oxide or on the combination of α and β . Following atomic ratios are preferably used in case of Ba-Y system, Ba-La system and Sr-La system respectively:

Y/(Y + Ba)	0.06 to 0.94, more preferably 0.1 to 0.4
Ba/(La + Ba)	0.04 to 0.96, more preferably 0.08 to 0.45
Sr/(La + Sr)	0.03 to 0.95, more preferably 0.05 to 0.1

Thus, the preferable compound oxides are Y-Ba-Cu-O system, La-Ba-Cu-O system and La-Sr-Cu-O system including the following special cases:

$Y_1 Ba_2 Cu_3 O_{7-x}$	$Ho_1 Ba_2 Cu_3 O_{7-x}$	$Lu_1 Ba_2 Cu_3 O_{7-x}$
$Sm_1 Ba_2 Cu_3 O_{7-x}$	$Nd_1 Ba_2 Cu_3 O_{7-x}$	$Gd_1 Ba_2 Cu_3 O_{7-x}$
$Eu_1 Ba_2 Cu_3 O_{7-x}$	$Er_1 Ba_2 Cu_3 O_{7-x}$	$Dy_1 Ba_2 Cu_3 O_{7-x}$
$Tm_1 Ba_2 Cu_3 O_{7-x}$	$Yb_1 Ba_2 Cu_3 O_{7-x}$	$La_1 Ba_2 Cu_3 O_{7-x}$
$(La, Sr)_2 CuO_{4-x}$		

in which x is a number which satisfies a range of $0 < x < 1$.

The abovementioned compound oxides possess preferably perovskite type or quasi-perovskite type crystal structure. The term of quasi-perovskite type means a structure which can be considered to have such a crystal structure that is similar to Perovskite-type oxides and includes an orthorhombically distorted perovskite or a distorted oxygen-deficient perovskite or the like.

The superconducting thin film may be also another type of superconductor consisting mainly of a compound oxide represented by the formula:



in which Θ stands for Bi or Tl, Φ stands for Sr when Θ is Bi and stands for Ba when Θ is Tl, m and n are numbers each satisfying ranges of $6 \leq m \leq 10$ and $4 \leq n \leq 8$ respectively, $p = (6 + m + n)$, q is a number which satisfies a range of $0 < q < 1$, and r is a number which satisfies a range of $-2 \leq r \leq +2$. This system is considered to be a single phase of the following compound oxide or a mixed phase consisting mainly thereof:

$Bi_4 Sr_4 Ca_4 Cu_5 O_{20-r}$	$Bi_2 Sr_2 Ca_2 Cu_3 O_{10-r}$
$Tl_4 Ba_4 Ca_4 Cu_5 O_{20-r}$	$Tl_2 Ba_2 Ca_2 Cu_3 O_{10-r}$

in which r is a number which satisfies a range of $-2 \leq r \leq +2$.

The substrate may be made of glass, quartz, silicon, sapphire, stainless steel or other ceramics. Particularly, the substrate consists preferably of a single crystal of MgO or SrTiO₃. Desirably, the superconducting thin film is deposited on a (001) plane or (110) plane of a single crystal of MgO or SrTiO₃.

The thin film of superconductor and the protective layer can be prepared by the conventional physical vapour deposition technique, such as sputtering, vacuum deposition, ion plating, molecular beam epitaxial growth or the like. Generally, the thin film of compound oxide is prepared by sputtering technique.

According to the present invention, more than two protective layers may be formed successively on the superconducting thin film layer. Each protective layer may be different in type and composition from adjacent layers.

According to a preferred embodiment of the present invention, the superconducting thin film is deposited on a substrate by sputtering technique and then a protective layer is deposited on a surface of the superconducting thin film in a common sputtering unit. Namely, the sputtering is preferably carried out by such a manner that, at first, both targets for the superconducting thin film and for the protective layer are

set on respective target holders in a chamber, and then the target for the superconducting thin film is sputtered with argon gas or the like while the target for the protective layer is not sputtered. After a superconducting thin film is deposited on a substrate, the target for the protective layer is sputtered to deposit a protective layer on the superconducting thin film.

Such superconducting thin film can be prepared by sputtering technique described in our co-pending United States of America patent serial No. 152,714 filed on May 2, 1988.

In case of PVD, a vapour source may be elements of α , β and γ themselves, oxides or carbonates thereof. An atomic ratio of these elements in the vapour source is adjusted in function of evaporation rates of these elements on the basis of a atom ratio of these elements in the thin film to be produced. For example, the atomic ration of the elements α , β and γ in the vapor source is preferably selected from following range for typical compound oxide systems:

Y/(Y + Ba)	0.06 to 0.94, more preferably 0.1 to 0.4
Ba/(La + Ba)	0.04 to 0.96, more preferably 0.08 to 0.45
Sr/(La + Sr)	0.03 to 0.95, more preferably 0.05 to 0.1

The vapour source may be a sintered mass or a powder which is prepared by pulverizing the sintered mass which is prepared by sintering a powder mixture of Y_2O_3 , CuO and $BaCuO_2$ and which may have a crystal structure of perovskite or quasi-perovskite type. For example, the sintering can be carried out at a temperature selected in the following range:

Y/(Y + Ba)	220 to 1,230 °C
Ba/(La + Ba)	234 to 1,260 °C

The vapour source may be divided into more than two segments, for example two segments consisting of a copper target and a target composed of Ba-Y compound oxide, three targets consisting of Cu, Y and Ba.

The superconducting property can be improved by heat-treatment which is effected after the thin film of compound oxide is deposited on the substrate in oxygen containing atmosphere. The heat-treatment is preferably effected under a partial pressure of oxygen ranging from 0.1 to 150 atm at a temperature between 300 and 1,500 °C. After this temperature is maintained for more than one hour, the resulting thin film is cooled slowly at a rate of less than 100 °C/min, preferably at a rate of less than 10 °C/min.

Advantage of the heat-treatment can not be obtained if the heat-treatment is effected outside the abovementioned conditions. For example, if the thin film is heated at a temperature which is higher than 1,500 °C, the abovementioned advantage can not be obtained but the superconductivity will be disappeared.

In case of the compound oxide type superconductor, oxygen deficiency in its crystal is a critical factor for realizing the superconductivity, so that the heat-treatment under a relatively higher partial pressure of oxygen is very preferable and is considered to be indispensable to realize superior superconductivity.

However, it is impossible to prevent the thin film of compound oxide from deterioration which occur during storage even if the thin film is heat-treated completely. The deterioration of superconductivity, in other words a phenomenon that the superconducting property is lost gradually in time may be caused by disappearance or liberation of oxygen in the crystal because the superconductivity of compound oxide is observed in unstable or quasi-stable phase. This is a big problem of compound oxide type superconductors in their actual use.

This problem is solved by the present invention in which an outer surface of the thin film of superconductor is covered by a stable and hard protective layer of chemically stable inorganic glass which can be prepared at a relatively low temperature and which has a high density to prevent oxygen from escaping from its crystal structure.

In a stage of deposition of the protective layer of inorganic glass onto the superconducting thin film, the substrate on which the thin film is deposited should not be heated at a temperature which is higher than 500 °C.

The thin film of compound oxide is preferably deposited on a (001) plane or (110) plane of a single crystal of MgO or $SrTiO_3$, so that the c-axis is orientated to a predetermined direction to improve the critical current density (J_c).

It is apparent from the description abovementioned that the superconducting thin film of compound oxide according to the present invention have improved stability than conventional superconducting thin film and hence they can be utilized advantageously in applications of thin film devices, such as Matisoo switching elements or Josephson device, Anacker memory device or Superconducting Quantum Interference Device (SQUID).

Now, the present invention will be described with reference to attached drawings which illustrate an apparatus used for carrying out the present invention. But, the present invention is not limited thereto.

Brief Description of the drawing

FIG. 1 is a illustrative view of a magnetron sputtering unit which is used in the present invention.

Referring to FIG. 1 illustrating a magnetron sputtering unit which is used in the present invention, the sputtering unit includes, in a chamber 1, two target holders for a target 2 for a superconducting thin film and a target 3 for a protective layer, a pair of magnetron electrodes 4 each surrounding respective targets 2 and 3, high-frequency power sources 5 for actuating the magnetron electrodes 5 and a substrate holder on which a substrate is secured. The chamber 1 has an exhaust port 8 which is connected to a vacuum source (not shown) and a gas inlet port 7 for introducing an atmosphere gas. The substrate holder is provided with a heater 9 for controlling a temperature of the substrate 6. Such sputtering unit itself are known and used in a variety of applications.

In operation, after a substrate 6 is secured to the substrate holder and targets 2 and 3 are set on respective target holder in the chamber 1, vacuum is created in the chamber 1 and a suitable gas such as argon and/or oxygen at a predetermined pressure is introduced into the chamber 1. After the substrate 6 is heated to a predetermined temperature by the heater 9, high-frequency power is applied to one of the magnetron electrode 4 surrounding the target 2 for the superconducting thin film to start sputtering operation. Introduction of the atmosphere gas in the chamber 1 is controlled at a predetermined pressure during the sputtering operation. The deposition of the superconducting thin film of compound oxide is carried out by the conventional sputtering technique.

After the thin film of compound oxide is deposited, another the magnetron electrode 4 surrounding the target 3 for the protective layer is energized so that a thin film of the protective layer is deposited on the superconducting thin film.

Now, several embodiments of the method according to the present invention will be described by Examples, but the scope of the present invention should not be limited thereto.

In the following Examples, both of the superconducting thin film and the protective layer are prepared in the sputtering unit shown in Fig. 1. For comparison, two series of samples are prepared in such manner that the first series possesses the protective layer while second series do not possess the same.

Example 1

Powders of Y_2O_3 and $BaCO_3$ were mixed in a atomic ratio of $Y : Ba = 1 : 2$. Then, a powder of CuO was added to the resulting powder mixture in a proportion which is 10 % excess with respect to an atomic ratio of $Y : Ba : Cu = 1 : 2 : 3$. The resulting powder mixture was sintered at $950^\circ C$ to obtain a sintered block of $YBa_2Cu_3O_7$ which will be used as a target 2 for a superconducting thin film.

The resulting target 2 and a target 3 composed of silicon nitride are set on respective target holder and a substrate 6 consisting of a single crystal of MgO are secured on the substrate holders. The MgO crystal is set in such manner that its surface on which the thin film is deposited has a (001) plane.

After the chamber 1 is vacuumed, argon gas with a partial pressure of 6.75 Pa ($5.0 \times 10^{-2} \text{ Torr}$) and oxygen gas with a partial pressure of 1.35 Pa ($1.0 \times 10^{-2} \text{ Torr}$) are introduced and the substrate is heated at $650^\circ C$. Then, the magnetron electrode 4 for the target 2 is energized with high frequency of 3 W/cm^2 to prepare a thin film of compound oxide of $1 \mu m$ on the substrate at a film forming rate of 5.10^{-2} nm/sec ($0.50 \text{ \AA/sec}$).

After deposition of the thin film of compound oxide complete, oxygen gas of 1 atom is introduced in the chamber 1 and the temperature of the substrate is adjusted at $650^\circ C$. The deposited thin film is left under this condition for 15 hour and then cooled slowly at a cooling rate of $7^\circ C/min$.

Then, another magnetron electrode for the protective layer 3 is energized so that silicon nitride is sputtered under a partial pressure of Ar gas of 0.405 Pa ($3.0 \times 10^{-3} \text{ Torr}$) to deposit a protective layer of 200 nm ($2,000 \text{ \AA}$) on the thin film of compound oxide which is prepared in the abovementioned step.

Resistance of the resulting thin film is measured on a sample on which aluminum electrodes are vacuum-deposited at opposite ends of the thin film of compound oxide deposited on the substrate 6.

Measurement of the critical temperature T_c and T_{cf} was carried out by a conventional four probe method in which the sample was immersed in liquidized helium to cool the sample down to a temperature of 8 K in a cryostat. Then, the temperature dependence of resistance of the sample was determined with rising the temperature gradually to determine a temperature of T_{cf} at which the perfect superconductivity start to be lost and a resistance begin to appear and a temperature of T_c at which the superconductivity is lost and an ordinary resistance begin to appear.

Changes of T_{cf} and T_c are determined by comparing two values observed on same sample just after the protective layer is deposited and after one month.

The result as well as main operational parameters are shown in Table 1.

Example 2

The same procedure as Example 1 is repeated except that a sintered block of $\text{LaBa}_2\text{Cu}_3\text{O}_7$ is used as a target for a thin film of compound oxide which is prepared by following procedure:

Powders of La_2O_3 and BaCO_3 were mixed at an atomic ratio of $\text{La} : \text{Ba} = 1 : 2$ and then a powder of CuO was added to the resulting powder mixture in 10 % excess of a atomic ratio of $\text{Y} : \text{Ba} : \text{Cu} = 1 : 2 : 3$. Then, the resulting powder mixture was sintered at 970°C to obtain a sintered block of $\text{LaBa}_2\text{Cu}_3\text{O}_7$ which is used as a target 2 for a superconducting thin film.

The result as well as main operations parameters are shown in Table 1.

Table 1

No.	Partial pressure of O ₂ (Pa)	Temperature of Substrate (°C)	Protective Layer	Just after deposition		One month later	
				T _c (K)	T _{cf} (K)	T _c (K)	T _{cf} (K)
1	1.35 (1.0×10 ⁻² Torr)	650	SiN	78	67	77	67
			—	77	68	12	--
2	9.45 (7.0×10 ⁻³ Torr)	620	SiN	56	39	57	38
			—	57	40	1	--

(Note)
-- : Superconductivity is not observed in liquid helium

Example 3

The same procedure as Example 1 is repeated except that the target of silicon nitride is replaced by a target of zirconium oxide and that the surrounding gas is changed to argon gas with a partial pressure of $0.540 \text{ Pa} (4 \times 10^{-3} \text{ Torr})$ and oxygen gas with a partial pressure of $0.135 \text{ Pa} (1 \times 10^{-3} \text{ Torr})$.

The result as well as main operational parameters are shown in Table 2.

Example 4

The same procedure as Example 2 is repeated except that the target of silicon nitride is replaced by a target of zirconium oxide and that the surrounding gas is changed to argon gas with a partial pressure of $0.540 \text{ Pa} (4 \times 10^{-3} \text{ Torr})$ and oxygen gas with a partial pressure of $0.135 \text{ Pa} (1 \times 10^{-3} \text{ Torr})$.

The result as well as main operational parameters are shown in Table 2.

Table 2

No.	Partial pressure of O ₂ (Pa)	Temperature of Substrate (°C)	Protective Layer	Just after deposition		One month later	
				T _c (K)	T _{cf} (K)	T _c (K)	T _{cf} (K)
3	1.08 Pa (8.0×10 ⁻³ Torr)	700	ZrO ₂	88	77	87	78
			—	90	79	29	—
4	0.675 Pa (5.0×10 ⁻³ Torr)	640	ZrO ₂	48	35	49	35
			—	47	36	3	—

(Note)

-- : Superconductivity is not observed in liquid helium

Example 5

Powders of Y₂O₃ and BaCuO₂ which is prepared by sintering powders of BaCO₃ and CuO are mixed at an atomic ratio of Y : Ba : Cu = 1 : 2 : 3.2 (copper is added excessively because the sputtering rate of copper is higher than the other two) and then sintered at 950 °C to obtain a sintered block of YBa₂Cu₃O₇ which will be used as a target 2 for a superconducting thin film.

The resulting target 2 and a glass target 3 composed of SiO₂ containing very small amount of P₂O₅ are set on respective target holders and a substrate 6 consisting of a single crystal of MgO is secured on the substrate holder. The MgO crystal is set in such manner that its surface on which the thin film is deposited has a (001) plane.

After the chamber 1 is vacuumed, argon gas at a partial pressure of 6.75 Pa (5.0 × 10⁻² Torr) and oxygen gas at a partial pressure of 1.35 Pa (1.0 × 10⁻² Torr) are introduced and the substrate is heated at 650 °C. Then, the magnetron electrode 4 for the target 2 is energized with high frequency of 3 W/cm² to prepare a thin film of compound oxide of 1 μm on the substrate at a film forming rate of 5.10⁻² nm/sec (0.50 Å/sec).

After deposition of the thin film of compound oxide complete, oxygen gas of 1 atm is introduced in the chamber 1 and the temperature of the substrate is adjusted at 650 °C. The deposited thin film is left under this condition for 15 hour and then cooled slowly at a cooling rate of 7 °C/min.

Then, another magnetron electrode for the protective layer 3 is energized so that a glass composed of SiO₂ containing very small amount of P₂O₅ is sputtered with argon gas under a pressure of 0.405 Pa (3.0 × 10⁻³ Torr) to deposit a protective layer of 200 nm (2,000 Å) on the thin film of compound oxide which is prepared in the abovementioned step.

Measurement of the critical temperature T_c and T_{cf} was carried out by the same method as Example 1. The result as well as main operational parameters are shown in Table 3.

Example 6

The same procedure as Example 5 is repeated except that the glass target composed of SiO₂ containing very small amount of P₂O₅ is replaced by another glass target composed of 85% by weight of PbO, 7.5 % by weight of SiO₂ and 7.5 % by weight of B₂O₃ and that the atmosphere gas for the protective layer is changed to a gas mixture of argon under a partial pressure of 0.54 Pa (4 × 10⁻³ Torr) and oxygen gas under a partial pressure of 0.135 Pa (1 × 10⁻³ Torr).

The result as well as main operational parameters are shown in Table 3.

Table 3

No.	Partial pressure of O ₂ (Pa)	Temperature of Substrate (°C)	Protective Layer	Just after deposition		One month later	
				T _c (K)	T _c f (K)	T _c (K)	T _c f (K)
5	1.35 Pa (1.0×10 ⁻² Torr)	650	glass (1)	78	67	77	68
			—	77	68	12	—
6	0.945 Pa (7.0×10 ⁻³ Torr)	620	glass (2)	72	63	73	62
			—	74	65	11	—

(Note)

Glass (1) : Phosphorous silicate glass

Glass (2) : Low-melting point glass

-- : Superconductivity is not observed in liquid helium

Claims

1. A method for protecting an outer surface of a superconducting thin film wherein a superconducting thin film of a copper oxide compound having a crystal structure of perovskite or quasi-perovskite and being deposited on a substrate by physical vapour deposition is covered with a protective layer of inorganic glass deposited on said outer surface of the superconducting thin film by physical vapour deposition while said substrate is heated at a temperature between 230°C and 1,410°C.
2. The method set forth in claim 1 wherein said inorganic glass is phosphorous-silicate glass.
3. The method set forth in claim 1 wherein said inorganic glass is a low melting point glass comprising 85% by weight of PbO, 7.5% by weight of SiO₂ and 7.5% by weight of B₂O₃.
4. The method set forth in anyone of claims 1 to 3 wherein said substrate is maintained at a temperature lower than 500 °C during the deposition of said protective layer.
5. The method set forth in any one of claims 1 to 4 wherein after the thin film of copper oxide compound is deposited, the deposited thin film is heat-treated at a temperature between 300 °C to 1,500 in oxygen containing atmosphere before said protective layer is deposited.
6. The method set forth in claim 5 wherein the heat-treated thin film is cooled slowly at a rate of less than 100 °C/min.
7. The method set forth in any one of claims 1 to 6 wherein said copper oxide compound is represented by the general formula (1):

$$(\alpha_{1-x}\beta_x)\text{Cu}_y\text{O}_z \quad (1)$$
 in which α is a IIa group element, β is a IIIa group element, x is an atomic ratio of β with respect to $(\alpha + \beta)$ and has a range of $0.1 \leq x \leq 0.9$, and y and z are respective atomic ratios with respect to $(\alpha_{1-x}\beta_x)$ which is considered to be equal to 1 and each satisfy ranges of $0.4 \leq y \leq 3.0$ and $1 \leq z \leq 5$ respectively.
8. The method set forth in claim 7 wherein said element α is Ba and said element β is at least one elements selected from a group comprising Y, La, Gd, Dy, Ho, Er, Tm, Yb, Nd, Sm, Eu and Lu.
9. The method set forth in any one of claim 1 to 6 wherein said copper oxide compound is represented by the general formula (2):



Table 3

No.	Partial pressure of O ₂ (Pa)	Temperature of Substrate (°C)	Protective Layer	Just after deposition		One month later	
				T _c (K)	T _c _f (K)	T _c (K)	T _c _f (K)
5	1.35 Pa (1.0×10 ⁻² Torr)	650	glass (1)	78	67	77	68
			—	77	68	12	—
6	0.945 Pa (7.0×10 ⁻³ Torr)	620	glass (2)	72	63	73	62
			—	74	65	11	—

(Note)

Glass (1) : Phosphorous silicate glass

Glass (2) : Low-melting point glass

-- : Superconductivity is not observed in liquid helium

Claims

1. A method for protecting an outer surface of a superconducting thin film wherein a superconducting thin film of a copper oxide compound having a crystal structure of perovskite or quasi-perovskite and being deposited on a substrate by physical vapour deposition is covered with a protective layer of inorganic glass deposited on said outer surface of the superconducting thin film by physical vapour deposition while said substrate is heated at a temperature between 230 °C and 1,410 °C.
2. The method set forth in claim 1 wherein said inorganic glass is phosphorous-silicate glass.
3. The method set forth in claim 1 wherein said inorganic glass is a low melting point glass comprising 85% by weight of PbO, 7.5% by weight of SiO₂ and 7.5% by weight of B₂O₃.
4. The method set forth in anyone of claims 1 to 3 wherein said substrate is maintained at a temperature lower than 500 °C during the deposition of said protective layer.
5. The method set forth in any one of claims 1 to 4 wherein after the thin film of copper oxide compound is deposited, the deposited thin film is heat-treated at a temperature between 300 °C to 1,500 in oxygen containing atmosphere before said protective layer is deposited.
6. The method set forth in claim 5 wherein the heat-treated thin film is cooled slowly at a rate of less than 100 °C/min.
7. The method set forth in any one of claims 1 to 6 wherein said copper oxide compound is represented by the general formula (1):

$$(\alpha_{1-x}\beta_x)\text{Cu}_y\text{O}_z \quad (1)$$
 in which α is a IIa group element, β is a IIIa group element, x is an atomic ratio of β with respect to $(\alpha + \beta)$ and has a range of $0.1 \leq x \leq 0.9$, and y and z are respective atomic ratios with respect to $(\alpha_{1-x}\beta_x)$ which is considered to be equal to 1 and each satisfy ranges of $0.4 \leq y \leq 3.0$ and $1 \leq z \leq 5$ respectively.
8. The method set forth in claim 7 wherein said element α is Ba and said element β is at least one elements selected from a group comprising Y, La, Gd, Dy, Ho, Er, Tm, Yb, Nd, Sm, Eu and Lu.
9. The method set forth in any one of claim 1 to 6 wherein said copper oxide compound is represented by the general formula (2):



in which Θ stands for Bi or Tl, Φ stands for Sr when Θ is Bi and stands for Ba when Θ is Tl, m and n are numbers each satisfying ranges of $6 \leq m \leq 10$ and $4 \leq n \leq 8$ respectively, $p = (6+m+n)$, q is a number which satisfies a range of $0 < q < 1$, and r is a number which satisfies a range of $-2 \leq r \leq +2$.

10. The method set forth in any one of claim 1 to 9 wherein said substrate is made of glass, quartz, silicon, sapphire, stainless steel or other ceramics.

11. The method set forth in claim 10 wherein said substrate is a single crystal of MgO or SrTiO₃.

12. The method set forth in claim 11 wherein said superconducting thin film is deposited on a {001} plane or {110} plane of a single crystal of MgO or SrTiO₃.

Patentansprüche

1. Verfahren zum Schutz einer äußeren Oberfläche einer supraleitenden Dünnschicht, bei dem eine supraleitende Dünnschicht aus einer Kupferoxidverbindung mit einer Perovskit- oder Quasi-Perovskit-Kristallstruktur, die mittels physikalischer Dampfabcheidung auf einem Substrat abgeschieden ist, mit einer Schutzschicht aus anorganischem Glas bedeckt wird, die auf der äußeren Oberfläche der supraleitenden Dünnschicht mittels physikalischer Dampfabcheidung abgeschieden wird, während das Substrat auf eine Temperatur zwischen 230 °C und 1410 °C aufgeheizt wird.

2. Verfahren nach Anspruch 1, bei dem das anorganische Glas ein phosphorhaltiges Silikatglas ist.

3. Verfahren nach Anspruch 1, bei dem das anorganische Glas ein niedrigschmelzendes Glas mit, mit 85 Gew.% PbO, 7,5 Gew.-% SiO₂ und 7,5 Gew.-% B₂O₃.

4. Verfahren nach einem der Ansprüche 1 bis 3, bei dem das Substrat während der Abscheidung der Schutzschicht auf einer Temperatur von weniger als 500 °C gehalten wird.

5. Verfahren nach einem der Ansprüche 1 bis 4, bei dem nach der Abscheidung der Dünnschicht aus einer Kupferoxidverbindung die abgeschiedene Dünnschicht auf eine Temperatur aufgeheizt wird zwischen 300 °C und 1500 °C in einer sauerstoffhaltigen Atmosphäre, bevor die Schutzschicht abgeschieden wird.

6. Verfahren nach Anspruch 5, bei dem die wärmebehandelte Dünnschicht langsam mit einer Geschwindigkeit von weniger als 100 °C/min abgekühlt wird.

7. Verfahren nach einem der Ansprüche 1 bis 6, bei dem die Kupferoxidverbindung durch die allgemeine Formel (1) dargestellt wird:



wobei α ein Element der IIa-Gruppe ist, β ein Element der IIIa-Gruppe ist, x das Atomverhältnis von β bezüglich $(\alpha + \beta)$ ist und im Bereich von $0,1 \leq x \leq 0,9$ liegt und y und z die entsprechenden Atomverhältnisse bezüglich $(\alpha_{1-x}\beta_x)$ sind, welches gleich 1 gesetzt wird und die die Bereiche $0,4 \leq y \leq 3,0$ bzw. $1 \leq z \leq 5$ erfüllen.

8. Verfahren nach Anspruch 7, bei dem α für Ba steht und β wenigstens ein Element ist, das ausgewählt ist aus der Gruppe, welche Y, La, Gd, Dy, Ho, Er, Tm, Yb, Nd, Sm, Eu und Lu umfaßt.

9. Verfahren nach einem der Ansprüche 1 bis 6, bei dem die Kupferoxidverbindung durch die allgemeine Formel (2) dargestellt wird:



wobei Θ für Bi oder Tl steht, Φ für Sr steht, wenn Θ Bi ist und für Ba steht, wenn Θ Tl ist, m und n



Zahlen sind, die die Bereiche $6 \leq m \leq 10$ bzw. $4 \leq n \leq 8$ erfüllen, $p = (6+m+n)$ ist, q eine Zahl ist, welche im Bereich $0 < q < 1$ liegt und r eine Zahl ist, welche im Bereich $-2 \leq r \leq +2$ liegt.

10. Verfahren nach einem der Ansprüche 1 bis 9, bei dem das Substrat aus Glas, Quarz, Silikon, Saphir, Edelstahl oder anderen Keramiken besteht.
11. Verfahren nach Anspruch 10, bei dem das Substrat ein Einkristall aus MgO oder $SrTiO_3$ ist.
12. Verfahren nach Anspruch 11, bei dem die supraleitende Dünnschicht auf einer $\{001\}$ -Ebene oder einer $\{110\}$ -Ebene eines Einkristalls aus MgO oder $SrTiO_3$ abgeschieden wird.

Revendications

1. Procédé pour protéger une surface externe d'une pellicule mince supraconductrice, dans lequel une pellicule mince supraconductrice en oxyde composé au cuivre ayant la structure cristalline de la perovskite ou quasiment de la perovskite, déposée sur un substrat par dépôt physique en phase vapeur, est recouverte avec une couche protectrice de verre inorganique déposée sur ladite surface externe de la pellicule mince supraconductrice par dépôt physique en phase vapeur, tandis que ledit substrat est chauffé à une température entre $230^\circ C$ et $1410^\circ C$.
2. Procédé selon la revendication 1, dans lequel ledit verre inorganique est du verre de silicate phosphoré.
3. Procédé selon la revendication 1, dans lequel ledit verre inorganique est un verre à point de fusion bas comprenant 85 % en poids de PbO , 7,5 % en poids de SiO_2 et 7,5 % en poids de B_2O_3 .
4. Procédé selon l'une quelconque des revendication 1 à 3, dans lequel ledit substrat est maintenu à une température inférieure à $500^\circ C$ durant le dépôt de ladite couche protectrice.
5. Procédé selon l'une quelconque des revendication 1 à 4, dans lequel après le dépôt de la pellicule mince en oxyde composé au cuivre, la pellicule mince déposée est traitée thermiquement à une température entre $300^\circ C$ et $1500^\circ C$ dans une atmosphère contenant de l'oxygène, avant le dépôt de ladite couche protectrice.
6. Procédé selon la revendication 5, dans lequel la pellicule mince traitée thermiquement est refroidie lentement à une vitesse de moins de $100^\circ C/min$.
7. Procédé selon l'une quelconque des revendication 1 à 6, dans lequel ledit oxyde composé au cuivre est représenté par la formule générale (1) :



où α est un élément du groupe IIa, β est un élément du groupe IIIa, x est un rapport atomique de β par rapport à $(\alpha + \beta)$ et a une gamme de $0,1 \leq x \leq 0,9$, et y et z sont les rapports atomiques respectifs par rapport à $(\alpha_{1-x}\beta_x)$, qui est considéré être égal à 1, et chacun satisfait aux gammes de $0,4 \leq y \leq 3,0$ et $1 \leq z \leq 5$ respectivement.

8. Procédé selon la revendication 7, dans lequel ledit élément α est Ba et ledit élément β est au moins un élément choisi dans le groupe comprenant Y, La, Gd, Dy, Ho, Er, Tm, Yb, Nd, Sm, Eu et Lu.
9. Procédé selon l'une quelconque des revendication 1 à 6, dans lequel ledit oxyde composé au cuivre est représenté par la formule générale (2) :



où Θ représente Bi ou Tl, Φ représente Sr lorsque Θ est Bi et représente Ba lorsque Θ est Tl, m et n sont des nombres satisfaisant chacun aux gammes de $6 \leq m \leq 10$ et $4 \leq n \leq 8$ respectivement, $p = (6+m+n)$, q est un nombre qui satisfait à la gamme de $0 < q < 1$, et r est un nombre qui satisfait à la



gamme de $-2 \leq r \leq +2$.

- 5
10. Procédé selon l'une quelconque des revendications 1 à 9, dans lequel ledit substrat est réalisé en verre, quartz, silicium, saphir, acier inoxydable ou d'autres céramiques.
11. Procédé selon la revendication 10, dans lequel ledit substrat est un monocristal de MgO ou SrTiO₃.
12. Procédé selon la revendication 11, dans lequel ladite pellicule mince supraconductrice est déposée sur le plan (001) ou le plan (110) d'un monocristal de MgO ou SrTiO₃.
- 10
- 15
- 20
- 25
- 30
- 35
- 40
- 45
- 50
- 55