

Abstract

A lubricant for injection is provided which is capable of penetrating into a micro-gap to enable low friction without protruding outside and without allowing adhesion of a foreign substance to the surroundings. The lubricant for injection consists only of tungsten disulfide powder and a volatile solvent. A percentage of the tungsten disulfide powder content is at or below 25wt%.

Fig. 2