

SPECIFICATION

TITLE: ETCHING GAS

TECHNICAL FIELD

[0001] The present invention relates to an etching gas used for producing thin film devices represented by IC, LSI, TFT and the like, and particularly to an etching gas that accomplishes both environmental performances and micro-patterning performances.

BACKGROUND OF THE INVENTION

[0002] In processes for producing semiconductor thin film devices, optical devices, super steel materials and the like, there have been produced various thin films, thick films and the like by means of CVD method, sputtering method, sol-gel method, vapor deposition method and the like. Moreover, in order to form a circuit pattern, gas etching for partially removing a thin film material has been conducted on semiconductors or in fabrication of semiconductors for IC, LSI, TFT and the like.

[0003] Hitherto, perfluorocarbons (PFCs) such as CF_4 , C_2F_6 , C_3F_8 and the like have been used as an etching gas in etching for forming circuits, in fabrication of thin film devices. However, these gases exist in the environment stably for a long period of time and therefore regarded as having high global warming potentials, so that their adverse influence on the environment has come to an issue.

[0004] For example, their GWPs known from the IPCC Fourth Assessment Report are as follows (on a 100 year scale):

CF_4 : 7390

C_2F_6 : 12200

C_3F_8 : 8830

An etching gas partially having the structure of CF_3 group e.g. C_2F_6 , C_3F_8 and the like generates active species exemplified by CF_3 radicals, ions and the like in a deposition room (a chamber) thereby exhibiting the etching effect; however, CF_3 active species are brought into contact with fluorine radicals or with fluorine active species of ions to be recombined thereto, thereby forming

CF₄ as a by-product.

[0005] Guidelines on the destruction of PFCs issued by Office of Fluorocarbons Control Policy, Global Environmental Issues Division of the Global Environment Bureau of the Ministry of the Environment (issued in March 2009) states that CF₄ is the most undecomposable PFC in the environment and therefore it may not be sufficiently destructed under the destructing conditions similar to those for other fluorocarbons.

[0006] As a fluorine-containing etching gas having low global warming potentials and substitutable for PFC, there have been proposed COF₂, CHF₂OF (Patent Publication 1), CF₃COF (Patent Publications 2 and 3) and the like. These publications state it is possible to reduce by-production of CF₄, for example, by optimizing an etching condition for CF₃COF.

REFERENCES ABOUT PRIOR ART

Patent Publication

[0007] Patent Publication 1: Japanese Patent Application Publication No. 2000-63826

Patent Publication 2: Japanese Patent Application Publication No. 2000-265275

Patent Publication 3: Japanese Patent Application Publication No. 2002-158181

SUMMARY OF THE INVENTION

[0008] As mentioned above, Patent Publications 1 and 2 state that by-production of CF₄ can be reduced by optimizing an etching condition for CF₃COF. However, it is considered difficult to fundamentally avoid a recombination of the CF₃ active species and the fluorine active species so long as the etching gas partially having the structure of CF₃ group is used. In view of the above, the optimized etching condition is found not to be optimized in respect of the micro-patterning speed and the patterning accuracy, which means that the aimed patterning accuracy and the like are restricted by the rate of CF₄ by-production. In fact, there are not a few cases difficult to constantly reduce by-production of CF₄ under a condition satisfying required

performances such as the etching rate, the anisotropy, the aspect ratio, the resist ratio and the like.

[0009] In order to obtain a good anisotropy in etching that requires micro-patterning performances, a compound having a ratio of fluorine number to carbon number (F/C) close to 1 is demanded. For example, in the case of perfluorocarbons, F/C of CF_4 is 4, F/C of C_2F_6 is 3 and F/C of C_3F_8 is 2.7. As the carbon number gets increased, F/C thus approaches 1 or the above-mentioned requirement, but the boiling point also gets increased so as to become difficult to handle as gas. Moreover, F/C of CF_3COF is 2 and therefore it is not a satisfying value too.

[0010] In view of the above, an object of the present invention is to provide a novel etching gas which is not only excellent in etching performances but also easily available and does not substantially by-produce CF_4 that places a burden on the environment.

[0011] The present inventors had eagerly made studies on the above-mentioned object and thereby found that CHF_2COF can accomplish both the environmental performances and the environmental safety, with which the present invention has come to completion. More specifically, the present invention is as follows.

[0012] [Invention 1]

An etching gas used for etching semiconductors, dielectric substances or thin films formed of metals, the etching gas containing CHF_2COF .

[0013] [Invention 2]

An etching gas of Invention 1, wherein the semiconductors or the dielectric substances are a silicon-containing substance.

[0014] [Invention 3]

An etching gas of Invention 1 or 2, wherein the etching gas contains at least one kind of gas selected from O_2 , O_3 , CO , CO_2 , F_2 , NF_3 , Cl_2 , Br_2 , I_2 , XF_n (In this formula, X represents Cl, I or Br. n represents an integer satisfying $1 \leq n \leq 7$), CH_4 , CH_3F , CH_2F_2 , CHF_3 , N_2 , He, Ar, Ne and Kr, as an additive.

[0015] [Invention 4]

An etching gas of Invention 1 or 2, wherein the etching gas contains at least one kind of gas selected from CH_4 , C_2H_2 , C_2H_4 , C_2H_6 , C_3H_4 , C_3H_6 , C_3H_8 , HI , HBr , HCl , CO , NO , NH_3 , H_2 , N_2 , He , Ar , Ne and Kr , as an additive.

[0016] [Invention 5]

An etching gas of Inventions 1 to 3, wherein the etching gas contains at least one kind of gas selected from CH_4 , CH_3F , CH_2F_2 , CHF_3 , as an additive.

[0017] [Invention 6]

A method for etching semiconductor films, dielectric films or metal films, the method using an etching gas of Inventions 1 to 4.

[0018] [Invention 7]

A method for etching, the method including conducting an etching method of Invention 6 and then ashing by F_2 or O_2 .

BRIEF EXPLANATION OF THE DRAWINGS

[0019] [Fig. 1A] A schematic cross section of a sample for etching used in Examples and Comparative Examples.

[Fig. 1B] A schematic cross section of a sample after etching (showing a case of having facets).

[Fig. 2] A schematic cross section of a remote plasma apparatus used in Examples and Comparative Examples.

DETAILED DESCRIPTION

[0020] The etching gas according to the present invention is not only characterized by placing a slight burden on the environment by virtue of its containing CHF_2COF but also exhibits good etching performances in semiconductor film-forming process, i.e., a performance of high etching rates, a performance of not bringing corrosion to the apparatus and the like. Hence the etching gas is useful for micro-patterning conducted on thin films by etching in semiconductor film-forming process.

[0021] The present invention will be hereinafter discussed in detail.


CHF_2COF can be readily and rationally synthesized by catalytic cracking of 1-alkoxy-1,1,2,2-tetrafluoroethane represented by $\text{CHF}_2\text{CF}_2\text{OR}$ (where R is an alkyl group including Me, Et, n-Pr, iso-Pr, n-Bu, sec-Bu, iso-Bu,

tert-Bu and the like) and used as a cleaning agent, a foaming agent or the like such as HFE-254pc ($\text{CHF}_2\text{CF}_2\text{OMe}$), HFE-374pc-f ($\text{CHF}_2\text{CF}_2\text{OEt}$) and the like. Moreover, HFE-254pc and HFE-374pc-f can be synthesized by adding methanol or ethanol to an industrially mass-produced tetrafluoroethylene so as to be greatly available compounds.

[0022] CHF_2COF has a boiling point of 0°C and therefore serves as a highly convenient cleaning gas that can be handled as either liquid or gas. Additionally, CHF_2COF is reacted with water to be decomposed into difluoroacetic acid (CHF_2COOH) and hydrogen fluoride (HF), so that usually its hazard can be eliminated by using a water scrubber. It is also preferable to use an alkaline water scrubber. Even in the event of passing the hazard-eliminating step so as to be emitted into the air, CHF_2COF is reacted with rain and steam in the air thereby being readily decomposed. Thus its environmental impact is extremely minimal.

[0023] As a point where CHF_2COF of the present invention is significantly different from the existing CF_3COF in property, it is possible to cite an easiness to establish a ketene structure. CHF_2COF is known to be able to take on a ketene structure represented by $\text{CF}_2=\text{C}=\text{O}$ as shown in the following equation. In the case of CF_3COF , a reaction for taking on the ketene structure is an endothermic reaction calculated at 165.9 kcal. In order to develop this reaction a further activation energy is required in addition to the above free energy, so that the likelihood of this reaction can be said to be actually remarkably little.

[0024]



The heat of reaction is a value calculated by B3LYP/6-311G+**.

[0025] As will be discussed in Examples, in the cases of using CHF_2COF as the etching gas, CF_4 was not detected at all even under variously modified conditions. It can be supposed from this fact that cleaning was developed

through a vastly different mechanism from CF_3COF .

[0026] Furthermore, in the case of using CF_3COF , once generated CF_3 active species are brought into contact with fluorine active species with a certain probability to cause recombination thereby by-producing CF_4 (in an etching process employing plasma, for example). On the contrary, in the case of using CHF_2COF , by-production remains at CHF_3 which is relatively reasonably decomposable even if CHF_2 active species and fluorine active species are brought into contact with each other. Stochastically there is the possibility that CHF_3 is so decomposed as to form CF_3 active species and it is bonded to the fluorine active species again thereby to by-produce CF_4 ; however, it is easily supposed that such a probability is extremely small as compared to etching gases partially having the structure of CF_3 group (CF_3COF , etc.). For the above reasons CHF_2COF is considered not to substantially by-produce CF_4 . As a matter of fact, by-production of CF_4 was not recognized in any of the Examples.

[0027] The etching gas containing CHF_2COF according to the present invention can be particularly preferably used for etching of: semiconductors when manufacturing semiconductor devices; dielectric substances; or thin films formed of metals.

[0028] As substances able to be etched by the etching gas containing CHF_2COF according to the present invention, it is possible to cite B, P, W, Si, Ti, V, Nb, Ta, Se, Te, Mo, Re, Os, Ru, Ir, Sb, Ge, Au, Ag, As, Cr, Hf, Zr, Ni, Co and their compounds deposited on semiconductor substrates such as silicon wafers, GaAs wafers and the like, metal substrates such as W, Ta, Mo and the like, insulating or dielectric substrates such as SiO_2 , Al_2O_3 , Ta_2O_5 and the like, glasses such as soda-lime glasses, borosilicate glasses and the like, or substrates formed of single crystals or polycrystals of other compounds or the like. Among them, this etching gas is particularly effective at etching oxides, nitrides, carbides, or composites of them. It is particularly preferable to use W, WSi_x , Ti, TiN, Ta_2O_5 , Mo, Re, Ge, Si_3N_4 , Si, SiO_2 or the like, more preferably silicon-containing substances such as WSi_x , Si_3N_4 , Si, SiO_2 and the like, and

much more preferably Si or SiO₂. The above-mentioned substances may be any of single crystal, polycrystal and amorphous form.

[0029] The etching gas of the present invention can be used for etching exemplified by RIE (reactive-ion etching), ECR (electron cyclotron resonance) plasma etching, microwave etching and the like, but not limited to these. Additionally, these kinds of etching processes are a common knowledge among the skilled in the art and can be referred to from publications as needed. The reaction conditions are not required particularly. When CHF₂COF is used, fluorine radicals reach recessed portions of channels and then CF_y ions (where y represents an integer of from 1 to 3) enter there, with which etching develops in a longitudinal direction. Side walls are protected by deposition of a fluorocarbon polymer, thereby preventing an isotropic etching due to fluorine radicals and allowing an anisotropic etching. Moreover, since CHF₂COF contains oxygen (O), there is an advantage that the anisotropic etching can be developed while efficiently removing fluorocarbon films deposited on the side walls.

[0030] As a reason for the specifically good micro-patterning of CHF₂COF, it is possible to cite not only the fact that a ratio represented by F/C is 1.5 in the case of CHF₂COF while it is 2 in the case of CF₃COF but also the effect of the above-mentioned ketene which is polymerized to protect the side walls. It is also possible to remove organic substances including polymers, in such a manner as to carry out heating by using an oxidizing gas such as F₂, O₂ and the like or to carry out plasma ashing after conducting etching by using the etching gas of the present invention,

[0031] An etching method of the present invention is practicable under various dry etching conditions and allows the addition of various additives depending on the property, productivity, micro-patterning accuracy and the like of the target film. Inert gases exemplified by N₂, He, Ar, Ne, Kr and the like are usable as a diluent, and more particularly, Ar is effective at stabilizing plasma and therefore provides an enhanced etching rate by a synergistic effect with CHF₂COF. Though the amount of the added inert gases depends on the

configuration and performances of the apparatus such as the output, the amount of discharged gas and the like or on the properties of the target film, it is preferably 1/10 to 30 times the amount of flow of CHF_2COF .

[0032] With the addition of the oxidizing gas to CHF_2COF , it becomes possible to increase the etching rate and to enhance the productivity. Concrete examples thereof are O_2 , O_3 , CO_2 , F_2 , NF_3 , Cl_2 , Br_2 , I_2 , XF_n (In this formula, X represents Cl, I or Br. n represents an integer satisfying $1 \leq n \leq 7$. Concrete examples are ClF , ClF_3 , BrF , BrF_3 , IF_5 and IF_7). Though the amount of the added oxidizing gas depends on the configuration and performances of the apparatus such as the output and the like or on the properties of the target film, it is usually 1/20 to 30 times the amount of flow of CHF_2COF , more preferably 1/10 to 10 times the amount of flow of CHF_2COF . The addition exceeding 30 times impairs the excellent anisotropic etching performance of CHF_2COF and therefore not preferable. In the case of less than 1/20, the effect of the addition of the oxidizing gas cannot be sufficiently exhibited and therefore not preferable. In particular, the addition of oxygen allows selectively accelerating the etching rate on metals, and more specifically, greatly improves the selection ratio of the etching rate on metals thereby allowing a selective etching on metals. It is a matter of course that the addition of inert gases such as N_2 , He, Ar, Ne, Kr and the like in addition to the oxidizing gas is acceptable as desired.

[0033] If reduction of the amount of fluorine radicals that accelerates the isotropic etching is required, the addition of a reducing gas exemplified by CH_4 , C_2H_2 , C_2H_4 , C_2H_6 , C_3H_4 , C_3H_6 , C_3H_8 , HI, HBr, HCl, CO, NO, NH_3 and H_2 provides a good effect. The amount of the addition is preferably not larger than 10 times. When the addition exceeds the above, fluorine radicals that work on etching is significantly reduced thereby decreasing the productivity. Particularly, the addition of H_2 or C_2H_2 decreases the etching rate on Si while the etching rate on SiO_2 is not changed, so that the selectivity is enhanced. Thus it becomes possible to etch SiO_2 selectively against a foundation silicon.

[0034] Furthermore, gases having a carbon number of 1 such as CH_4 , CH_3F ,

CH_2F_2 and CHF_3 are effective in a fine-tuning of the ratio of fluorine to carbon in the etching gas. The amount of the addition thereof also is preferably not larger than 10 times the amount of CHF_2COF . When the addition exceeds the above, the excellent etching performances of CHF_2COF get impaired. CO traps HF (which has been by-produced, for example when ketene is generated) in the form of HCOF and works as an etching agent in itself, so as to be efficiently used. The amount of CO to be added is from 10:1 to 1:5, preferably from 5:1 to 1:1 in a mole ratio represented by $\text{CHF}_2\text{COF}:\text{CO}$.

[0035] The pressure in the case of using the etching gas of the present invention is preferably not higher than 660 Pa (5 Torr) in order to perform anisotropic etching; however, pressures of not higher than 0.13 Pa (0.001 Torr) reduce the etching rate and therefore not preferable. The flow rate of gas to be used depends on the volume of a reactor of the etching apparatus and on the size of the wafer, but it is preferable to carry out etching at a flow rate of between 10 to 10000 SCCM. Moreover, the temperature for etching is preferably not greater than 400°C. High temperatures exceeding 400°C are not preferable since etching tends to develop isotropically so that a desired patterning accuracy cannot be obtained and since a resist is excessively etched.

EXAMPLES

[0036] The present invention will be more readily understood with reference to the following Examples.

[Examples 1 to 3 and Comparative Examples 1 and 2]

There are shown examples where etching was conducted on an interlaminar insulating film (SiO_2) by using an etching gas of the present invention for contact hole-fabrication.

[0037] As a sample, a SiO_2 interlaminar insulating film 22 was formed on a single crystal silicon wafer 21. The sample was put to use upon forming on the SiO_2 film a resist mask 23 having apertures to serve as an etching mask. A sample before etching is shown in Fig. 1A.

[0038] A schematic cross section of an apparatus used in the experiment is shown in Fig. 2. By using a high-frequency source 3 (13.56 MHz, 50 W),

etching gases (difluoroacetyl fluoride (CHF_2COF), oxygen (O_2), argon (Ar)) having been supplied from a gas inlet at flow rates shown in Table 1 were excited in a sapphire tube 7 attached to the top of a reaction chamber 1 thereby generating active species. The active species were supplied into the chamber by the flow of gas, upon which etching was conducted on a sample 12 fixed by a sample holder 10. Among the gas specimens, CHF_2COF , CF_3COF and CF_4 were introduced from a first gas inlet while O_2 was introduced from a second gas inlet, through a mass flow controller (though not shown).

[0039] The temperature of the substrate (or the sample holder 11) was set at 25°C , the pressure was set at 2.67 Pa (0.02 Torr), and the RF power density was set at 2.2 W/cm^2 . A discharged gas was diluted with nitrogen supplied at 5 L/min on a discharge side of a mechanical booster pump, and then the concentration of CF_4 was quantified by calibration curve method with the use of FT-IR. Results of the above are shown in Table 1. Incidentally, "ND" shown in the Table refers to less than the floor limit for detection (0.05 volume%). The etching rate ($\text{\AA}/\text{min}$) was determined in such a manner as to divide film thicknesses obtained before and after etching by an etching time. The film thicknesses were measured by an optical interferotype film thickness meter. A sample after etching (in the case of having facets) is shown in Fig. 1B.

[0040] [Table 1]

	Gas 1	Flow Rate of Gas 1 SCCM	Gas 2	Flow Rate of Gas 2 SCCM	Etching Rate Å/min	Selection Ratio to Resist	Aspect Ratio	Patterning Profile	CH ₄ Concentration in Discharged Gas
Example 1	CHF ₂ COF	50	None	-	4058	6	6 or more	No facet, Good side wall	Less than floor limit for detection
Example 2	CHF ₂ COF	10	Ar	200	4121	6	6 or more	No facet, Good side wall	Less than floor limit for detection
Example 3	CHF ₂ COF	50	O ₂	10	15598	7	6 or more	No facet, Good side wall	Less than floor limit for detection
Comparative Example 1	CF ₃ COF	50	None	-	3218	5	6 or more	Partially having facets and gouges in side wall	0.11%
Comparative Example 2	CF ₄	50	None	-	608	4	5	Partially having facets and gouges in side wall	0.18%

CHF₂COF: Difluoroacetyl fluorideCF₃COF: Trifluoroacetyl fluorideO₂: Oxygen

Ar: Argon

CF₄: Carbon tetrafluoride

EXPLANATION OF REFERENCE NUMERALS

- [0041]
- 1 Chamber
 - 2 Earth
 - 3 High-frequency source
 - 4 First gas inlet
 - 5 Second gas inlet
 - 6 Third gas inlet
 - 7 Sapphire tube
 - 8 Induction coil
 - 9 Electronic pressure meter

- 10 Discharged-gas line
- 11 Sample holder
- 12 Sample
- 21 Silicon wafer
- 22 SiO₂ interlaminar insulating film
- 23 Resist mask
- 24 Facets

CLAIMS

[Claim 1] An etching gas used for etching semiconductors, dielectric substances or thin films formed of metals, the etching gas containing CHF_2COF .

[Claim 2] An etching gas as claimed in Claim 1, wherein the semiconductors or the dielectric substances are a silicon-containing substance.

[Claim 3] An etching gas as claimed in Claim 1 or 2, wherein the etching gas contains at least one kind of gas selected from O_2 , O_3 , CO , CO_2 , F_2 , NF_3 , Cl_2 , Br_2 , I_2 , XF_n (In this formula, X represents Cl, I or Br. n represents an integer satisfying $1 \leq n \leq 7$), CH_4 , CH_3F , CH_2F_2 , CHF_3 , N_2 , He, Ar, Ne and Kr, as an additive.

[Claim 4] An etching gas as claimed in Claim 1 or 2, wherein the etching gas contains at least one kind of gas selected from CH_4 , C_2H_2 , C_2H_4 , C_2H_6 , C_3H_4 , C_3H_6 , C_3H_8 , HI, HBr, HCl, CO, NO, NH_3 , H_2 , N_2 , He, Ar, Ne and Kr, as an additive.

[Claim 5] An etching gas as claimed in any one of Claims 1 to 3, wherein the etching gas contains at least one kind of gas selected from CH_4 , CH_3F , CH_2F_2 , CHF_3 , as an additive.

[Claim 6] A method for etching semiconductor films, dielectric films or metal films, the method using an etching gas as claimed in any one of Claims 1 to 4.

[Claim 7] A method for etching, the method including conducting an etching method as claimed in Claim 6 and then ashing by F_2 or O_2 .