

ABSTRACT

The present disclosure provides an adhesive sheet including an acrylic adhesive layer is formed of an adhesive composition comprising an acrylic polymer (A), wherein a stress relaxation rate is 0.25 or more, and wherein the stress relaxation rate is calculated by the following equation (I) from an initial modulus of elasticity ($G'(0)$) at 0.1 seconds after application of a strain of 25% to the acrylic adhesive layer at a temperature of 70°C and a relaxation modulus of elasticity ($G'(300)$) at 300 seconds after application of a strain of 25% to the acrylic adhesive layer at a temperature of 70°C:

$$\text{Stress relaxation rate} = (G'(300)/G'(0)) \cdots (I).$$