



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : H01L 21/285, C23C 16/34, 16/52	A1	(11) International Publication Number: WO 99/00830 (43) International Publication Date: 7 January 1999 (07.01.99)
(21) International Application Number: PCT/US98/13305 (22) International Filing Date: 26 June 1998 (26.06.98) (30) Priority Data: 08/884,811 30 June 1997 (30.06.97) US 09/067,429 27 April 1998 (27.04.98) US (71) Applicant: APPLIED MATERIALS, INC. [US/US]; 3050 Bowers Avenue, Santa Clara, CA 95054 (US). (72) Inventors: CHEN, Ling; 784 Dartshire Way, Sunnyvale, CA 94087 (US). GANGULI, Seshadri; Apartment 150, 3480 Grenada Avenue, Santa Clara, CA 95051 (US). MAK, Alfred; 32722 Fellows Court, Union City, CA 94587 (US). (74) Agents: MOSER, Raymond, R., Jr. et al.; Applied Materials, Inc., Patent Counsel, P.O. Box 450A, Santa Clara, CA 95052 (US).	(81) Designated States: JP, KR, SG, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>	

(54) Title: **IMPROVED DEPOSITION OF TUNGSTEN NITRIDE USING PLASMA PRETREATMENT IN A CHEMICAL VAPOR DEPOSITION CHAMBER**

(57) Abstract

A layer of tungsten nitride is deposited on the upper surface of a wafer with improved adhesion. The deposition is performed by first pretreating the wafer with a hydrogen plasma prior to performing tungsten nitride deposition.

