

DESCRIPTION

POLISHING COMPOSITION AND METHOD FOR PRODUCING SEMICONDUCTOR SUBSTRATE

5

TECHNICAL FIELD

The present invention relates to a polishing composition
and a semiconductor substrate production method in which a
10 semiconductor substrate is polished with the polishing
composition.

BACKGROUND ART

15 The surface of a semiconductor substrate, such as silicon
wafer, is polished several times including primary polishing.
The edge of a semiconductor substrate is also polished. For
these types of polishing, a polishing composition is used that
contains, for example, silicon dioxide having an average
20 primary particle diameter of 40 nm or more and a water-soluble
polymer (see Patent document 1).

Due to high-performance and high-density integration of a
semiconductor device, the improvement in the surface quality
25 of a semiconductor substrate is recently required. In view of
improving the quality of a polished product, it is important,
in particular, to maintain the edge shape of a polishing
object and to reduce the surface roughness or the difference
in level. In these circumstances, for example, a polishing
30 composition is known that contains relatively small silica
particles for reducing the roll-off (end face sagging) of a
hard disk substrate (see Patent document 2). A polishing
composition is also known that contains colloidal silica and a
water-soluble polymer compound for reducing the irregularities
35 of a substrate surface (see Patent document 3). A polishing

composition is also known that contains polyvinylpyrrolidone
for reducing surface defects (see Patent document 4). A
polishing composition is also known that contains a surfactant
for reducing etching of regions on a silicon wafer not to be
5 processed (see Patent document 5).

PRIOR ART DOCUMENTS

Patent document 1: Japanese Laid-Open Patent Publication No.
10 2004-128069

Patent document 2: Japanese Laid-Open Patent Publication No.
2009-160676

Patent document 3: Japanese Laid-Open Patent Publication No.
2-158684

15 Patent document 4: Japanese Laid-Open Patent Publication No.
2008-53415

Patent document 5: International Publication No. WO
2005/029563

20 SUMMARY OF THE INVENTION

Problems that the Invention is to Solve

In view of improving the quality of a polished product,
25 it is important to maintain the edge shape of a polishing
object and to reduce the surface roughness or the difference
in level, as described above. On the other hand, in view of
responding to the increased quantity demanded for a polished
product, it is important to provide a polishing composition
30 for achieving a high polishing rate.

Accordingly, it is an objective of the present invention
to provide a polishing composition that easily improves the
quality of a polished product by maintaining the edge shape of
35 a polishing object and reducing the surface roughness or the

difference in level and easily achieves a high polishing rate. It is another objective of the present invention to provide a semiconductor substrate production method using the polishing composition.

5

Means for Solving the Problems

In order to achieve the objectives described above and in accordance with a first aspect of the present invention, provided is a polishing composition to be used for polishing both surfaces of a semiconductor substrate. The polishing composition contains silicon dioxide, a nitrogen-containing water-soluble polymer, and a basic compound. The silicon dioxide has an average primary particle diameter of 40 nm or more as calculated from the specific surface area determined by the BET method. The value of B/A is 1 or more and less than 7,000 and the value of C/A is 5,000 or more and less than 1,500,000 when in one liter of the polishing composition, A is defined as the number of silicon dioxide, B is defined as the number of monomer units of the nitrogen-containing water-soluble polymer, and C is defined as the number of molecules of the basic compound.

In accordance with a second aspect of the present invention, provided is a polishing composition containing silicon dioxide, a nitrogen-containing water-soluble polymer, and a basic compound. The silicon dioxide has an average primary particle diameter of 40 nm or more as calculated from the specific surface area determined by the BET method. The value of B/A is 1 or more and less than 7,000 and the value of C/A is 5,000 or more and less than 100,000 when in one liter of the polishing composition, A is defined as the number of silicon dioxide, B is defined as the number of monomer units of the nitrogen-containing water-soluble polymer, and C is defined as the number of molecules of the basic compound.

The nitrogen-containing water-soluble polymer has a weight average molecular weight of preferably less than 1,500,000.

5

The silicon dioxide has true specific gravity of preferably 1.7 or more.

The basic compound preferably includes a potassium compound and a quaternary ammonium compound.

In accordance with a third aspect of the present invention, a method for producing a semiconductor substrate is provided that includes polishing a semiconductor substrate with the polishing composition of the first or second aspect described above.

15

Effects of the Invention

According to the polishing composition and the method for producing a semiconductor substrate of the present invention, the quality of a polished product can be easily improved by maintaining the edge shape of a polishing object and reducing the surface roughness or the difference in level, and a high polishing rate can be easily obtained.

25

MODES FOR CARRYING OUT THE INVENTION

A first embodiment of the present invention will be described below.

30

(First embodiment)

The polishing composition of the present embodiment is prepared by mixing silicon dioxide, a nitrogen-containing

35

water-soluble polymer, and a basic compound with water. Accordingly, the polishing composition contains silicon dioxide, a nitrogen-containing water-soluble polymer, a basic compound, and water. The polishing composition is used, for example, for polishing both surfaces of a semiconductor substrate, such as silicon substrate.

<Silicon dioxide>

Silicon dioxide contained in the polishing composition functions to physically polish a surface to be polished.

Examples of silicon dioxide for use include colloidal silica, fumed silica, and sol-gel silica. Use of colloidal silica or fumed silica, and in particular use of colloidal silica is preferable for reducing scratches occurring on the surface of a polished semiconductor substrate. One type of silicon dioxides may be used alone or in combination with other one or more types.

The silicon dioxide in the polishing composition has an average primary particle diameter of 40 nm or more, preferably 45 nm or more, and more preferably 70 nm or more, as calculated from the specific surface area determined by the BET method. When the average primary particle diameter of the silicon dioxide is 40 nm or more, the surface roughness or the difference in level is easily reduced.

The average primary particle diameter of the silicon dioxide in the polishing composition is also preferably less than 100 nm. When the average primary particle diameter of the silicon dioxide is less than 100 nm, the storage stability of the polishing composition is further improved. The storage stability means the stability of the physical properties of the composition itself before and after storage of the

polishing composition in a container for a predetermined period and the stability of polishing characteristics when the composition is used in polishing.

5 The ratio of the major axis to the minor axis of the silicon dioxide in the polishing composition is preferably 1.10 or more, and more preferably 1.15 or more. When the silicon dioxide has a ratio of the major axis to the minor axis of 1.10 or more, a high polishing rate is easily obtained
10 and the effect for reducing the surface roughness or the difference in level is enhanced.

 The ratio of the major axis to the minor axis of the silicon dioxide means an average of the values each obtained
15 by dividing the length of the long side of a minimum rectangle circumscribing one of silicon dioxide particles within the visual field of a scanning electron microscope by the length of the short side of the same rectangle. The average can be obtained by using common image analysis software program.

20 The ratio of the major axis to the minor axis of the silicon dioxide in the polishing composition is also preferably less than 3.00, and more preferably less than 2.00. When the silicon dioxide has a ratio of the major axis to the
25 minor axis of less than 3.00, the storage stability of the polishing composition is further improved.

 The true specific gravity of the silicon dioxide in the polishing composition is preferably 1.7 or more, more
30 preferably 2.0 or more, and still more preferably 2.1 or more. As the true specific gravity of the silicon dioxide increases, a high polishing rate can be easily obtained and the effect for reducing the surface roughness or the difference in level can be easily enhanced.

35

The true specific gravity of the silicon dioxide is calculated from the dry weight of the silicon dioxide particles and the gross weight of the silicon dioxide particles after immersed in a known volume of ethanol.

5

The content of the silicon dioxide in the polishing composition is preferably 0.6% by mass or more, more preferably 0.8% by mass or more, and still more preferably 1.0% by mass or more. As the content of the silicon dioxide increases, a high polishing rate is easily obtained with more enhanced effect for reducing the surface roughness or the difference in level.

The content of the silicon dioxide in the polishing composition is preferably less than 10% by mass. When the content of the silicon dioxide is less than 10% by mass, the storage stability of the polishing composition is further improved and an economic advantage is obtained.

20 <Nitrogen-containing water-soluble polymer>

A nitrogen-containing water-soluble polymer contained in the polishing composition functions to maintain the flatness of a semiconductor substrate along the central part to the edge.

The nitrogen-containing water-soluble polymer for use is not specifically limited as long as one or more nitrogen atoms are contained in a monomer unit, or one or more nitrogen atoms are contained in a side chain. For example, an amine, an imine, an amide, an imide, a carbodiimide, a hydrazide, or a urethane compound may be used. The nitrogen-containing water-soluble polymer may be any of chain-type, ring-type, primary-type, secondary-type, and tertiary-type. The nitrogen-containing water-soluble polymer may include a salt structure

having a nitrogen atom as a cation. Examples of a nitrogen-containing water-soluble polymer including a salt structure include a quaternary ammonium salt. Examples of other nitrogen-containing water-soluble polymers include a

5 polycondensation-type polyamide (such as water-soluble nylon), a polycondensation-type polyester (such as water-soluble polyester), a polyaddition-type polyamine, a polyaddition-type polyimine, a polyaddition-type (meth)acrylic amide, a water-soluble polymer having a nitrogen atom in at least a part of
10 main alkyl chain, and a water-soluble polymer having a nitrogen atom in at least a part of side chain. The water-soluble polymer having a nitrogen atom in a side chain may include a water-soluble polymer having a quaternary nitrogen in a side chain.

15 Specific examples of polyaddition-type nitrogen-containing water-soluble polymers include polyvinylimidazole, polyvinylcarbazole, polyvinylpyrrolidone, polyvinylcaprolactam, and polyvinylpiperidine. The nitrogen-containing water-soluble polymer may partially include a structure having
20 hydrophilicity, such as a vinyl alcohol structure, a methacrylic acid structure, vinyl sulfonic acid structure, a vinyl alcohol carboxylic acid ester structure, and an oxyalkylene structure. The polymer may include two or more
25 structures thereof, such as a di-block type, a tri-block type, a random type, and an alternate type. A part or all of the molecules of the nitrogen-containing water-soluble polymer may include cations, anions, both of anions and cations, or nonions. One type of nitrogen-containing water-soluble
30 polymers may be used alone or in combination with other one or more types.

Among nitrogen-containing water-soluble polymers, polyvinylpyrrolidone, a copolymer including
35 polyvinylpyrrolidone in a part of structure,

polyvinylcaprolactam, and a copolymer including polyvinylcaprolactam in a part of structure are preferable because of excellent controllability for polishing the edge of a semiconductor substrate. In particular,
5 polyvinylpyrrolidone is most preferred.

The weight average molecular weight of the nitrogen-containing water-soluble polymer in the polishing composition is preferably less than 1,500,000, more preferably less than
10 500,000, still more preferably less than 100,000, yet still more preferably less than 80,000, and most preferably less than 50,000, in terms of polyethylene oxide. When the nitrogen-containing water-soluble polymer has a weight average molecular weight of less than 1,500,000, the storage stability
15 of the polishing composition is easily improved.

The weight average molecular weight of the nitrogen-containing water-soluble polymer in the polishing composition is also preferably 1,000 or more, and more preferably 20,000
20 or more. When the nitrogen-containing water-soluble polymer has a weight average molecular weight of 1,000 or more, the edge shape of a semiconductor substrate is more easily maintained.

25 The content of the nitrogen-containing water-soluble polymer in the polishing composition is preferably 0.0001% by mass or more. When the content of the nitrogen-containing water-soluble polymer is 0.0001% by mass or more, the edge shape of a semiconductor substrate is more easily maintained.

30 The content of the nitrogen-containing water-soluble polymer in the polishing composition is also preferably less than 0.002% by mass, more preferably less than 0.001% by mass, and still more preferably less than 0.0005% by mass. When the
35 content of the nitrogen-containing water-soluble polymer is

less than 0.002% by mass, a high polishing rate is more easily obtained.

<Basic compound>

5

The basic compound functions to chemically polish a surface to be polished, and to improve the storage stability of the polishing composition.

10 Specific examples of basic compounds include a hydroxide or salt of an alkaline metal, a quaternary ammonium hydroxide or a salt thereof, ammonia, and an amine. Examples of the alkaline metal include potassium and sodium. Examples of the salt include a carbonate, hydrogen carbonate, sulfate, and
15 acetate. Examples of the quaternary ammonium include tetramethylammonium, tetraethylammonium, and tetrabutylammonium.

 A quaternary ammonium hydroxide compound means a
20 quaternary ammonium hydroxide or a salt thereof, and specific examples thereof include tetramethylammonium hydroxide, a tetraethylammonium hydroxide, and tetrabutylammonium hydroxide.

 Specific examples of the amine include methylamine,
25 dimethylamine, trimethylamine, ethylamine, diethylamine, triethylamine, ethylenediamine, monoethanolamine, N-(β -aminoethyl)ethanolamine, hexamethylenediamine, diethylenetriamine, triethylenetetramine, anhydrous piperazine, piperazine hexahydrate, 1-(2-aminoethyl)piperazine, N-
30 methylpiperazine, and guanidine. One type of basic compounds may be used alone or in combination with other one or more types.

 Among basic compounds, at least one selected from ammonia,
35 an ammonium salt, an alkaline metal hydroxide, an alkaline

metal salt, and a quaternary ammonium hydroxide compound is preferably used, and at least one selected from ammonia, a potassium compounds sodium hydroxide, a quaternary ammonium hydroxide compound, ammonium hydrogen carbonate, ammonium carbonate, sodium hydrogen carbonate, and sodium carbonate is more preferably used.

The polishing composition preferably contains a potassium compound and a quaternary ammonium hydroxide compound as basic compounds. Examples of the potassium compound include a hydroxide or salt of potassium, such as potassium hydroxide, potassium carbonate, potassium hydrogen carbonate, potassium sulfate, potassium acetate, and potassium chloride. Most preferably, the polishing composition contains potassium hydroxide, potassium carbonate, and tetramethyl ammonium hydroxide as basic compounds.

The content of the basic compound in the polishing composition is preferably 0.01% by mass or more, and more preferably 0.03% by mass or more. As the content of the basic compound increases, a high polishing rate is easily obtained.

The content of the basic compound in the polishing composition is also preferably less than 0.2% by mass, and more preferably less than 0.1% by mass. As the content of the basic compound decreases, the edge shape of a semiconductor substrate is easily maintained.

The polishing composition of the present embodiment satisfies the following conditions X1 and X2 when in one liter of the polishing composition, A is defined as the number of silicon dioxide, B is defined as the number of monomer units of the nitrogen-containing water-soluble polymer, and C is defined as the number of molecules of the basic compound.

Condition X1: the value of B/A is 1 or more and less than 7,000; and

Condition X2: the value of C/A is 5,000 or more and less than 1,500,000.

5

The value of B/A defined in condition X1 represents the degree of protection against the physical action of the polishing composition. By setting the degree of protection to a proper range against the physical action of the polishing composition, both of the quality of a polished product and the polishing rate are easily enhanced.

When the polishing composition has a value of B/A of 1 or more, the effect for reducing the surface roughness or the difference in level and the effect for maintaining the edge shape of a semiconductor substrate are enhanced. From the view point of the effects, the value of B/A is preferably 10 or more, more preferably 30 or more, and most preferably 100 or more.

20

When the polishing composition has a value of B/A of less than 7,000, the effect for reducing the surface roughness or the difference in level and the effect for improving the polishing rate are enhanced. From the view point of the effects, the value of B/A is preferably less than 4,000, more preferably less than 1,000, still more preferably less than 500, and most preferably less than 200.

The value of A , which is defined as the number of silicon dioxide in one liter of the polishing composition, and the value of B , which is defined as the number of monomer units of the nitrogen-containing water-soluble polymer, are given by the following expressions (1) and (2).

35

Expression 1

$$A = 1.91 \times 10^{22} \times \frac{\text{Content of silicon dioxide [\% by mass]}}{(\text{BET particle diameter of silicon dioxide [nm]})^3 \times (\text{True specific gravity of silicon dioxide [g/cm}^3\text{)])} \quad \dots (1)$$

In Expression (1), 1.91×10^{22} is a constant determined by the expression for calculating the volume of silicon dioxide and the conversion of units. When the polishing composition contains two or more kinds of silicon dioxide, the number of silicon dioxide is calculated for each kind and summation thereof is regarded as A.

Expression 2

$$B = 6.02 \times 10^{24} \times \frac{\text{Content of nitrogen-containing water-soluble polymer [\% by mass]}}{\text{Molecular weight of monomer of nitrogen-containing water-soluble polymer [g/mol]}} \quad \dots (2)$$

In Expression (2), 6.02×10^{24} is a constant determined by the Avogadro constant and the conversion of units. When the polishing composition contains two or more kinds of nitrogen-containing water-soluble polymer, the number of monomer units of the nitrogen-containing water-soluble polymer is calculated for each kind and summation thereof is regarded as B.

The value of C/A defined in condition X2 represents the ratio of the chemical action to the physical action of the polishing composition. By setting the ratio of the chemical action to the physical action of the polishing composition to a proper range, both of the quality of a polished product and the polishing rate are easily enhanced.

When the polishing composition has a value of C/A of 5,000 or more, the effect for reducing the surface roughness or the difference in level and the effect for improving the polishing rate are enhanced. From the view point of the

effects, the value of C/A is preferably 10,000 or more, more preferably 20,000 or more, and most preferably 40,000 or more.

When the polishing composition has a value of C/A of less than 1,500,000, the effect for reducing the surface roughness or the difference in level and the effect for maintaining the edge shape of a semiconductor substrate are enhanced. From the view point of the effects, the value of C/A is preferably less than 600,000, more preferably less than 300,000, still more preferably less than 100,000, and most preferably less than 60,000.

The value of C, which is defined as the number of molecules of the basic compound, is given by the following expression (3).

Expression 3

$$C = 6.02 \times 10^{24} \times \frac{\text{Content of basic compound [\% by mass]}}{\text{Molecular weight of basic compound [g/mol]}} \quad \dots(3)$$

In Expression (3), 6.02×10^{24} is a constant determined by the Avogadro constant and the conversion of units. When the polishing composition contains two or more kinds of basic compounds, the number of molecules of the basic compound is calculated for each kind and summation thereof is regarded as C.

<Chelating agent>

The polishing composition may contain a chelating agent. The chelating agent in the polishing composition functions to capture metal impurities in the polishing system so as to form a complex, preventing the metal impurities from remaining on a semiconductor substrate.

Examples of chelating agents include an aminocarboxylic acid chelating agent and an organic phosphonic acid chelating agent. Specific examples of aminocarboxylic acids chelating agent include ethylenediaminetetraacetic acid, sodium ethylenediaminetetraacetate, nitrilotriacetic acid, sodium nitrilotriacetate, ammonium nitrilotriacetate, hydroxyethyl ethylenediaminetriacetic acid, sodium hydroxyethyl ethylenediaminetriacetate, diethylenetriaminepentaacetic acid, sodium diethylenetriaminepentaacetate, triethylenetetraaminehexaacetic acid, and sodium triethylenetetraaminehexaacetate.

Specific examples of organic phosphonic acid chelating agent include 2-aminoethylphosphonic acid, 1-hydroxyethylidene-1,1-diphosphonic acid, aminotri(methylenephosphonic acid), ethylenediaminetetrakis(methylenephosphonic acid), diethylenetriaminepenta(methylenephosphonic acid), triethylenetetraminehexa(methylenephosphonic acid), ethane-1,1-diphosphonic acid, ethane-1,1,2-triphosphonic acid, ethane-1-hydroxy-1,1-diphosphonic acid, ethane-1-hydroxy-1,1,2-triphosphonic acid, ethane-1,2-dicarboxy-1,2-diphosphonic acid, methanehydroxy phosphonic acid, 2-phosphonobutane-1,2-dicarboxylic acid, 1-phosphonobutane-2,3,4-tricarboxylic acid, and α -methyl phosphonosuccinic acid. One type of chelating agents may be used alone or in combination with other one or more types.

Among chelating agents, an organic phosphonic acid chelating agent is preferred, and ethylenediaminetetrakis(methylenephosphonic acid) is more preferred.

The content of the chelating agent in the polishing

composition is preferably 0.0001% by mass or more, and more preferably 0.0005% by mass or more. As the content of the chelating agent increases, the effect for preventing metal impurities from remaining on a semiconductor substrate is enhanced.

The content of the chelating agent in the polishing composition is also preferably less than 0.01% by mass, and more preferably less than 0.005% by mass. As the content of the chelating agent decreases, the storage stability of the polishing composition is further maintained.

<Water>

Water contained in the polishing composition functions to dissolve or disperse the other components. Water in which the total content of transition metal ions is 100 ppb or less is preferably used in order not to inhibit the actions of the other components. The purity of water can be enhanced by an operation such as removal of impurity ions using an ion exchange resin, removal of foreign matters using a filter, and distillation. Specifically, ion-exchange water, pure water, ultrapure water, or distilled water is preferably used.

The pH of the polishing composition is preferably within the range of 8 to 12, and more preferably within the range of 9 to 11.

In preparation of the polishing composition, a well-known mixing apparatus such as a blade-type stirrer, an ultrasonic disperser, and a homomixer can be used. The raw materials of the polishing composition may be mixed all together at the same time or may be sequentially mixed in any order.

In the following, the method for polishing a

semiconductor substrate using the polishing composition is described together with the operation of the polishing composition.

5 In polishing the surface of a semiconductor substrate with the polishing composition, a polishing pad is pressed against the semiconductor substrate surface while the polishing composition is supplied onto the semiconductor substrate surface, and the semiconductor substrate and the
10 polishing pad are rotated. As a polishing machine, a double side polishing machine is used that polishes simultaneously both surfaces of a semiconductor substrate.

 The polishing composition of the present embodiment
15 contains silicon dioxide having an average primary particle diameter of 40 nm or more as calculated from the specific surface area determined by the BET method, a nitrogen-containing water-soluble polymer, and a basic compound, and satisfies the conditions X1 and X2 described above.
20 Accordingly, the polishing composition applies a suitable physical action and a suitable chemical action to the surface of a semiconductor substrate, and imparts a suitable protection against the physical action to the semiconductor substrate surface. As a result, the surface roughness and the
25 difference in level of a semiconductor substrate is easily reduced. For example, a semiconductor substrate to be polished has an engraved mark part produced with a laser marker in some cases. The polishing composition of the present embodiment is suitably used for reducing the surface
30 roughness or the difference in level of the engraved mark part of a semiconductor substrate. Furthermore, the polishing composition allows the control of polishing at the edge of a semiconductor substrate. More specifically, the edge of a semiconductor substrate is prevented from being excessively
35 polished, so that the edge shape of a semiconductor substrate

is easily maintained. As a result, for example, the occurrence of edge roll-off of a semiconductor substrate to be polished is easily reduced. In addition, a high polishing rate is easily obtained.

5

The present embodiment described in detail above provides the following effects.

(1) In comparison between double side polishing and one
10 side polishing of a semiconductor substrate, the double side polishing is performed to give priority to polishing efficiency in many cases. In the case of double side polishing requiring high polishing rate, it is difficult to maintain the edge shape of a semiconductor substrate (or to
15 control the edge shape). The polishing composition of the present embodiment is used for polishing both surfaces of a semiconductor substrate. The polishing composition contains silicon dioxide having an average primary particle diameter of 40 nm or more as calculated from the specific surface area
20 determined by the BET method, a nitrogen-containing water-soluble polymer, and a basic compound, and satisfies the conditions X1 and X2 described above. Accordingly, the edge shape of a semiconductor substrate is maintained, while the surface roughness or the difference in level is easily reduced
25 and a high polishing rate is easily obtained. That is, the polishing composition of the present embodiment has excellent effects for easily maintaining the edge shape of a semiconductor substrate and easily reducing the surface roughness or the difference in level even in double side
30 polishing with priority given to polishing rate.

(2) When the weight average molecular weight of the nitrogen-containing water-soluble polymer is less than 1,500,000, the storage stability of the polishing composition
35 is easily improved.

(3) When the specific gravity of the silicon dioxide is 1.7 or more, a high polishing rate is more easily obtained and the effect for reducing the surface roughness or the difference in level is more easily enhanced.

(4) The method for manufacturing a semiconductor substrate using the polishing composition of the present embodiment maintains the edge shape of a semiconductor substrate, while easily reducing the surface roughness or the difference in level and easily obtaining a high polishing rate.

(Second embodiment)

A second embodiment of the present invention will be described below, with a focus on the difference from the first embodiment. The polishing composition of the second embodiment has a value of C/A in the range different from that of the polishing composition of the first embodiment. The polishing composition of the present embodiment can be used not only in double side polishing of a semiconductor substrate, but also in one side polishing or edge polishing of a semiconductor substrate.

The polishing composition of the present embodiment satisfies the following conditions Y1 and Y2 when in one liter of the polishing composition, A is defined as the number of silicon dioxide, B is defined as the number of monomer units of the nitrogen-containing water-soluble polymer, and C is defined as the number of molecules of the basic compound.

Condition Y1: the value of B/A is 1 or more and less than 7,000; and

Condition Y2: the value of C/A is 5,000 or more and less than 100,000.

The polishing composition of the present embodiment contains silicon dioxide having an average primary particle diameter of 40 nm or more as calculated from the specific surface area determined by the BET method, a nitrogen-containing water-soluble polymer, and a basic compound, and satisfies the conditions Y1 and Y2 described above. Accordingly, the edge shape of a polishing object is maintained, while the surface roughness or the difference in level is easily reduced and a high polishing rate is easily obtained. In particular, having a value of C/A of less than 100,000, the present embodiment facilitates further enhancing the effect for reducing the surface roughness or the difference in level and the effect for maintaining the edge shape of a semiconductor substrate. The polishing composition of the present embodiment also can achieve the similar effects (2) to (4) described in the first embodiment.

Polishing of one or both surfaces of a semiconductor substrate is divided into a plurality of stages including a first polishing step as an initial step, a second polishing step that is performed subsequent to the first polishing step, and a final polishing step that is performed for the purpose of finishing. Among the steps, polishing steps on and after the second polishing step are performed for each surface of a semiconductor substrate in many cases. In such one side polishing, it is further required to maintain the edge shape of a semiconductor substrate and reduce the surface roughness or the difference in level in some cases, causing difficulty in obtaining a high polishing rate. In this circumstance, the polishing composition of the present embodiment is suitably used in one side polishing, for example, in any of polishing steps on and after the second polishing step from the viewpoint of improvement in the quality of a polished semiconductor substrate and improvement in the polishing

efficiency.

The embodiments described above may be modified as follows.

5

- The polishing composition may further contain a known additive such as a preservative agent and an antifungal agent, if needed. Specific examples of preservative agents and antifungal agents include isothiazoline compounds, para-
10 oxybenzoates, and phenoxyethanol.

- The polishing composition may further contain a hydrate, chloride, carbonate, hydrogen carbonate, sulfate, or acetate of sodium, if needed.

15

- The polishing composition may be of a one-pack type, or may be a multi-pack type including two or more packs.

- The polishing composition may be prepared by diluting
20 an undiluted solution of the polishing composition with water. For example, by diluting an undiluted solution of the polishing composition after storage or transportation, the polishing composition can be prepared when used.

25 - The polishing composition may be reused for polishing after once used for polishing. When a used polishing composition is reused for polishing, a component or components lacking in the polishing composition may be complemented.

30 - The polishing pad used in polishing using the polishing composition is not particularly limited. The polishing pad may be of a polyurethane type, a nonwoven type, a suede type, an abrasive grain-containing type, or a no abrasive grain-containing type.

35

- The polishing composition of the second embodiment may be used not only for polishing a semiconductor substrate, such as a silicon substrate and a silicon oxide substrate, but also for producing a polished product by polishing, for example, a plastic substrate, a glass substrate, or a quartz substrate.

Examples

Next, the embodiments will be more specifically described with reference to examples and comparative Examples in the following.

(A. Double side polishing of semiconductor substrate)

Polishing compositions of Examples A1 to A13 and Comparative Examples A1 to A9 were prepared by mixing silicon dioxide, a nitrogen-containing water-soluble polymer, and a basic compound with ion-exchange water. The details for each of the polishing compositions are shown in Table 1.

The "BET particle diameter" column of Table 1 shows the average primary particle diameter calculated from the specific surface area (BET method) determined using "Flow SorbII 2300", made by Micromeritics Instrument Corporation. The "A" column of Table 1 shows the number of silicon dioxide in one liter of a polishing composition. In the "water-soluble polymer" column of Table 1, "PVP" represents polyvinylpyrrolidone, "PVCL" represents polyvinylcaprolactam, "PAA" represents polyacrylic acid, "PVA" represents polyvinyl alcohol, and "PEG" represents polyethylene glycol. The "B" column of Table 1 shows the number of monomer units of a nitrogen-containing water-soluble polymer in one liter of a polishing composition or the number of monomer units of a water-soluble polymer in one liter of a polishing composition. In the "basic compound" column of Table 1, "KOH" represents potassium hydroxide,

"K₂CO₃" represents potassium carbonate, and "TMAH" represents tetramethylammonium hydroxide. The "C" column in the "basic compound" column of Table 1 shows the number of molecules of a basic compound in one liter of a polishing composition.

5

A silicon substrate was polished under the polishing condition 1 described in Table 2 with each of the polishing compositions of Examples A1 to A13 and Comparative Examples A1 to A9. The silicon substrate used had a diameter of 300 mm, p-type conduction, a crystal orientation of <100>, and a resistivity of 0.1 Ω·cm or more and less than 100 Ω·cm.

<Polishing rate>

15 The thickness of a silicon substrate before polishing and the thickness of the silicon substrate after polishing under the polishing condition 1 were measured with Nanometro 300TT, made by Kuroda Precision Industries Ltd., and the difference in thickness before and after polishing was divided by
20 polishing time so as to calculate the polishing rate. In the "polishing rate" column of Table 1, "oo" represents a polishing rate of 0.40 μm/min or more, "o" represents a polishing rate of 0.35 μm/min or more and less than 0.40 μm/min, "Δ" represents a polishing rate of 0.30 μm/min or more
25 and less than 0.35 μm/min, and "x" represents a polishing rate of less than 0.30 μm/min.

<Surface roughness or difference in level>

30 The surface roughness Ra of a silicon substrate after polishing under the polishing condition 1 was measured with "ZYGO New View 5010", made by Zygo Corporation. The surface roughness Ra is a parameter that indicates the average of amplitude in the height direction of a roughness curve,
35 representing the arithmetic average of surface height of a

silicon substrate within a fixed visual field. In the
"surface roughness Ra" column of Table 1, "oo" represents a
surface roughness Ra of less than 7.0 Å, "o" represents 7.0 Å
or more and less than 8.0 Å, "Δ" represents 8.0 Å or more and
less than 10.0 Å, and "x" represents 10.0 Å or more.

The surface roughness Rt of a silicon substrate after
polishing under the polishing condition 1 was measured with
HRP340, made by KLA-Tencor Corporation. The surface roughness
Rt is a parameter that indicates the maximum sectional height
of a roughness curve, representing the difference between the
highest part and the lowest part of the surface height of a
silicon substrate within a fixed visual field. In the
"surface roughness Rt" column of Table 1, "oo" represents a
surface roughness Rt of less than 300 Å, "o" represents 300 Å
or more and less than 700 Å, "Δ" represents 700 Å or more and
less than 1,500 Å, and "x" represents 1,500 Å or more.

<Edge shape A1>

The SFQR value indicating the flatness of a substrate was
measured for each of the silicon substrates before polishing
and the silicon substrates after polishing under the polishing
condition 1, so that the edge shape of the silicon substrate
after polishing was evaluated based on the difference in the
SFQR value before and after polishing. More specifically, 30
pieces of 25 mm square regions were arranged on each of the
substrates, excluding notches on the periphery of the
substrate, for measurement of the SFQR value for each of the
regions with Nanometro 300TT, made by Kuroda Precision
Industries Ltd., and the average of the difference in the SFQR
value between before and after polishing was obtained. In the
"edge shape A1" column of Table 1, "oo" represents an average
of less than 1.0 μm, "o" represents an average of 1.0 μm or
more and less than 1.5 μm, "Δ" represents 1.5 μm and more and

less than 2.0 μm , and "x" represents 2.0 μm or more.

<Edge shape A2>

5 A silicon substrate was polished under the polishing
condition 2 described in Table 3 with each of the polishing
compositions of Examples A1, A2, and A12 and Comparative
Example A8. The silicon substrate used had a diameter of 300
mm, p-type conduction, a crystal orientation of <100>, and a
10 resistivity of 0.1 $\Omega\cdot\text{cm}$ or more and less than 100 $\Omega\cdot\text{cm}$. The
thickness of a silicon substrate before polishing and the
thickness of the silicon substrate after polishing each were
measured at a position 1 mm inside from the periphery of the
substrate with Nanometro 300TT, made by Kuroda Precision
15 Industries Ltd., and the edge shape of the silicon substrate
after polishing was evaluated based on the difference before
and after polishing. In the "edge shape A2" column of Table 1,
"oo" represents a difference value of less than 0.02 μm , "o"
represents 0.02 μm or more and less than 0.04 μm , " Δ "
20 represents 0.04 μm or more and less than 0.06 μm , and "x"
represents 0.06 μm or more.

Table 1

	Silicon dioxide			Water-soluble polymer				Basic compound			B/A	C/A	Polishing rate	Surface roughness Ra	Surface roughness Rt	Edge shape A1	Edge shape A2
	BET particle diameter [nm]	True specific gravity [g/cm ³]	Content [% by mass]	A	Kind	Weight average molecular weight	Content [% by mass]	B	Kind	Content [% by mass]	C						
Example A1	50	2.2	1.2	8.33×10 ¹⁶	PVP	45000	0.0003	1.62×10 ¹⁹	KOH K ₂ CO ₃ TMAH	0.004 0.04 0.03	4.15×10 ²¹	195	49800	○○	○○	○○	○○
Example A2	55	1.8	1.2	7.65×10 ¹⁶	PVP	45000	0.0003	1.62×10 ¹⁹	KOH K ₂ CO ₃ TMAH	0.004 0.04 0.03	4.15×10 ²¹	212	54300	○	○○	○	○
Example A3	55	1.8	1.9	1.19×10 ¹⁷	PVP	10000	0.001	5.42×10 ¹⁹	TMAH	0.2	1.32×10 ²²	447	109000	○	Δ	○	Δ
Example A4	90	1.8	1.2	1.75×10 ¹⁶	PVP	45000	0.0003	1.62×10 ¹⁹	KOH K ₂ CO ₃ TMAH	0.004 0.04 0.03	4.15×10 ²¹	930	238000	○○	Δ	○	Δ
Example A5	90	1.8	1.2	1.75×10 ¹⁶	PVP	45000	0.0003	1.62×10 ¹⁹	KOH K ₂ CO ₃ TMAH	0.002 0.01 0.01	1.31×10 ²¹	930	75000	○○	○	○	○
Example A6	100	2.2	1.2	1.04×10 ¹⁶	PVP	45000	0.0003	1.62×10 ¹⁹	TMAH	0.2	1.32×10 ²²	1560	1270000	○	Δ	○○	Δ
Example A7	50	2.2	1.2	8.33×10 ¹⁶	PVCL	90000	0.0003	1.30×10 ¹⁹	KOH K ₂ CO ₃ TMAH	0.004 0.04 0.03	4.15×10 ²¹	156	49800	○○	○○	○	○
Example A8	50	2.2	1.2	8.33×10 ¹⁶	PVP	9000	0.0003	1.62×10 ¹⁹	KOH K ₂ CO ₃ TMAH	0.004 0.04 0.03	4.15×10 ²¹	195	49800	○○	○○	○○	○
Example A9	50	2.2	1.2	8.33×10 ¹⁶	PVP	450000	0.0003	1.62×10 ¹⁹	KOH K ₂ CO ₃ TMAH	0.004 0.04 0.03	4.15×10 ²¹	195	49800	○	○○	○○	○
Example A10	50	2.2	1.2	8.33×10 ¹⁶	PVP	1400000	0.0003	1.62×10 ¹⁹	KOH K ₂ CO ₃ TMAH	0.004 0.04 0.03	4.15×10 ²¹	195	49800	Δ	○○	○○	○○
Example A11	50	2.2	1.2	8.33×10 ¹⁶	PVP	45000	0.001	5.42×10 ¹⁹	KOH K ₂ CO ₃ TMAH	0.004 0.04 0.03	4.15×10 ²¹	650	49800	Δ	○○	○	○○
Example A12	50	2.2	1.2	8.33×10 ¹⁶	PVP	45000	0.0003	1.62×10 ¹⁹	KOH	0.07	7.51×10 ²¹	195	90100	Δ	○○	○○	○○
Example A13	50	2.2	1.2	8.33×10 ¹⁶	PVP	45000	0.0003	1.62×10 ¹⁹	TMAH	0.07	4.62×10 ²¹	195	55400	○	○○	○○	○

Table 1 (continued)

	Silicon dioxide				Water-soluble polymer				Basic compound			B/A	C/A	Polishing rate	Surface roughness Ra	Surface roughness Rt	Edge shape A1	Edge shape A2
	BET particle diameter [nm]	True specific gravity [g/cm ³]	Content [% by mass]	A	Kind	Weight average molecular weight	Content [% by mass]	B	Kind	Content [% by mass]	C							
Comparative Example A1	12	1.8	1.2	7.37×10 ¹⁸	PVP	45000	0.0003	1.62×10 ¹⁹	KOH K ₂ CO ₃ TMAH	0.004 0.04 0.03	4.15×10 ²¹	2	563	○	○○	×	○○	-
Comparative Example A2	35	1.8	1.2	2.70×10 ¹⁷	PVP	45000	0.0003	1.62×10 ¹⁹	KOH K ₂ CO ₃ TMAH	0.004 0.04 0.03	4.15×10 ²¹	55	14000	○	○○	×	○○	-
Comparative Example A3	50	2.2	1.2	8.33×10 ¹⁶	PVP	45000	0.0003	1.62×10 ¹⁹	TMAH	0.002	1.32×10 ²⁰	195	1580	×	Δ	○	○○	-
Comparative Example A4	50	2.2	0.2	1.39×10 ¹⁶	PVP	45000	0.0003	1.62×10 ¹⁹	TMAH	0.4	2.64×10 ²²	1170	1900000	Δ	×	○	×	-
Comparative Example A5	50	2.2	1.2	8.33×10 ¹⁶	PAA	25000	0.0003	2.51×10 ¹⁹	KOH K ₂ CO ₃ TMAH	0.004 0.04 0.03	4.15×10 ²¹	301	49800	○	○○	Δ	×	-
Comparative Example A6	50	2.2	1.2	8.33×10 ¹⁶	PVA	53000	0.0003	4.10×10 ¹⁹	KOH K ₂ CO ₃ TMAH	0.004 0.04 0.03	4.15×10 ²¹	492	49800	×	○○	Δ	Δ	-
Comparative Example A7	50	2.2	1.2	8.33×10 ¹⁶	PEG	20000	0.0003	4.10×10 ¹⁹	KOH K ₂ CO ₃ TMAH	0.004 0.04 0.03	4.15×10 ²¹	492	49800	×	○○	Δ	Δ	-
Comparative Example A8	50	2.2	1.2	8.33×10 ¹⁶	-	-	-	-	KOH K ₂ CO ₃ TMAH	0.004 0.04 0.03	4.15×10 ²¹	-	49800	○○	×	○○	×	×
Comparative Example A9	50	2.2	1.2	8.33×10 ¹⁶	-	-	-	-	TMAH	0.07	4.62×10 ²¹	-	55400	○	×	○○	×	-

Table 2

Polishing condition 1	
Polisher:	Double side polishing machine (LPD-300: made by Fujikoshi Machinery Corp.)
Load:	25 kPa
Rotation speed of upper platen:	20 rpm
Rotation speed of lower platen:	15 rpm
Polishing pad:	MH-S15A (made by Nitta Haas Incorporated)
Feeding rate of Polishing composition:	6 L/min
Amount of polishing:	10 μm
Holding temperature of polishing composition:	25°C

Table 3

Polishing condition 2	
Polisher:	Double side polishing machine (DSM20B-5P-4D: made by Speedfam Co., Ltd.)
Load:	15 kPa
Rotation speed of upper platen:	13 rpm
Rotation speed of lower platen:	35 rpm
Rotation speed of internal gear:	7 rpm
Rotation speed of sun gear:	25 rpm
Polishing pad:	MH-S15A (made by Nitta Haas Incorporated)
Feeding rate of polishing composition:	4.5 L/min
Amount of polishing:	15 μ m
Holding temperature of polishing composition:	20°C

As shown in Table 1, in Examples A1 to A13, all of the evaluation results of the polishing rate, the surface roughness Ra, the surface roughness Rt, and the edge shape A1 were "oo", "o", or "Δ", which was satisfactory. In contrast, in Comparative Examples A1 to A9, some of the evaluation results of the polishing rate, the surface roughness Ra, the surface roughness Rt, and the edge shape A1 were "x", which was unsatisfactory. It was found from the results that setting the value of B/A and the value of C/A of a polishing composition including silicon dioxide, a nitrogen-containing water-soluble polymer, and a basic compound to a predetermined range allowed the edge shape of a polishing object to be maintained, the surface roughness or the difference in level to be easily reduced, and a high polishing rate to be easily obtained.

It was found that although the evaluation of the edge shape A2 was based on the evaluation of the edge shape of a silicon substrate by a different method from the method for the edge shape A1, the evaluation results had the similar tendency in the evaluation results of the edge shape A1.

(B. One side polishing of semiconductor substrate)

Polishing compositions of Examples B1 to B10 and Comparative Examples B1 to B12 were prepared by mixing silicon dioxide, a nitrogen-containing water-soluble polymer compound, and a basic compound with ion-exchange water. The details for each of the polishing compositions are shown in Table 4. The abbreviations in Table 4 are the same in Table 1.

A silicon substrate was polished under the polishing condition 3 described in Table 5 with each of the polishing compositions. The silicon substrate used had a diameter of 300 mm, p-type conduction, a crystal orientation of <100>, and a resistivity of 0.1 $\Omega\cdot\text{cm}$ or more and less than 100 $\Omega\cdot\text{cm}$.

<Polishing rate>

The thickness of a silicon substrate before polishing and the thickness of the silicon substrate after polishing under the polishing condition 3 were measured with Nanometro 300TT, made by Kuroda Precision Industries Ltd., and the difference in thickness before and after polishing was divided by polishing time so as to calculate the polishing rate. In the "polishing rate" column of Table 4, "oo" represents a polishing rate of 0.30 $\mu\text{m}/\text{min}$ or more, "o" represents a polishing rate of 0.25 $\mu\text{m}/\text{min}$ or more and less than 0.30 $\mu\text{m}/\text{min}$, " Δ " represents a polishing rate of 0.20 $\mu\text{m}/\text{min}$ or more and less than 0.25 $\mu\text{m}/\text{min}$, and "x" represents a polishing rate of less than 0.20 $\mu\text{m}/\text{min}$.

<Surface roughness or difference in level>

The surface roughness R_a of a silicon substrate after polishing under the polishing condition 3 was measured with "ZYGO New View 5010", made by Zygo Corporation. The surface roughness R_a is a parameter that indicates the average of

amplitude in the height direction of a roughness curve,
representing the arithmetic average of surface height of a
silicon substrate within a fixed visual field. In the
"surface roughness Ra" column of Table 4, "oo" represents a
5 surface roughness Ra of less than 6.0 Å, "o" represents 6.0 Å
or more and less than 7.0 Å, "Δ" represents 7.0 Å or more and
less than 8.0 Å, and "x" represents 8.0 Å or more.

The surface roughness Rt of a silicon substrate after
10 polishing under the polishing condition 3 was measured with
HRP340, made by KLA-Tencor Corporation. The surface roughness
Rt is a parameter that indicates the maximum sectional height
of a roughness curve, representing the difference between the
highest part and the lowest part of the surface height of a
15 silicon substrate within a fixed visual field. In the
"surface roughness Rt" column of Table 4, "oo" represents a
surface roughness Rt of less than 300 Å, "o" represents 300 Å
or more and less than 700 Å, "Δ" represents 700 Å or more and
less than 1,500 Å, and "x" represents 1,500 Å or more.

20
<Edge shape B1>

The SFQR value indicating the flatness of a substrate was
measured for each of the silicon substrates before polishing
25 and the silicon substrates after polishing under the polishing
condition 3, so that the edge shape of the silicon substrate
after polishing was evaluated based on the difference in SFQR
value before and after polishing. More specifically, 30
pieces of 25 mm square regions were arranged on each of the
30 substrates, excluding notches on the periphery of the
substrate, for measurement of the SFQR value for each of the
regions with Nanometro 300TT, made by Kuroda Precision
Industries Ltd., and the average of the difference in SFQR
value between before and after polishing was obtained. In the
35 "edge shape B1" column of Table 4, "oo" represents an average

of less than 0.2 μm , "o" represents an average of 0.2 μm or more and less than 0.3 μm , " Δ " represents 0.3 μm and more and less than 0.4 μm , and "x" represents 0.5 μm or more.

5 Table 4

	Silicon dioxide				Water-soluble polymer				Basic compound			B/A	C/A	Polishing rate	Surface roughness Ra	Surface roughness Rt	Edge shape B1
	BET particle diameter [nm]	True specific gravity [g/cm³]	Content [% by mass]	A	Kind	Weight average molecular weight	Content [% by mass]	B	Kind	Content [% by mass]	C						
Example B1	50	2.2	1.2	8.33×10 ⁻¹⁶	PVP	45000	0.0003	1.62×10 ⁻¹⁹	KOH K2CO3 TMAH	0.004 0.04 0.03	4.15×10 ²¹	195	49800	○○	○○	○○	○○
Example B2	55	1.8	1.2	7.65×10 ⁻¹⁶	PVP	45000	0.0003	1.62×10 ⁻¹⁹	KOH K2CO3 TMAH	0.004 0.04 0.03	4.15×10 ²¹	212	54300	○	○○	○	○
Example B3	90	1.8	1.2	1.75×10 ⁻¹⁶	PVP	45000	0.0003	1.62×10 ⁻¹⁹	KOH K2CO3 TMAH	0.002 0.01 0.01	1.31×10 ²¹	930	75000	○○	Δ	○	○
Example B4	50	2.2	1.2	8.33×10 ⁻¹⁶	PVCL	90000	0.0003	1.30×10 ⁻¹⁹	KOH K2CO3 TMAH	0.004 0.04 0.03	4.15×10 ²¹	156	49800	○○	○○	○	○
Example B5	50	2.2	1.2	8.33×10 ⁻¹⁶	PVP	9000	0.0003	1.62×10 ⁻¹⁹	KOH K2CO3 TMAH	0.004 0.04 0.03	4.15×10 ²¹	195	49800	○○	○	○○	○
Example B6	50	2.2	1.2	8.33×10 ⁻¹⁶	PVP	450000	0.0003	1.62×10 ⁻¹⁹	KOH K2CO3 TMAH	0.004 0.04 0.03	4.15×10 ²¹	195	49800	○	○○	○○	○○
Example B7	50	2.2	1.2	8.33×10 ⁻¹⁶	PVP	1400000	0.0003	1.62×10 ⁻¹⁹	KOH K2CO3 TMAH	0.004 0.04 0.03	4.15×10 ²¹	195	49800	Δ	○○	○○	○○
Example B8	50	2.2	1.2	8.33×10 ⁻¹⁶	PVP	45000	0.001	5.42×10 ⁻¹⁹	KOH K2CO3 TMAH	0.004 0.04 0.03	4.15×10 ²¹	650	49800	Δ	○○	○	○○
Example B9	50	2.2	1.2	8.33×10 ⁻¹⁶	PVP	45000	0.0003	1.62×10 ⁻¹⁹	KOH	0.07	7.51×10 ²¹	195	90100	Δ	○○	○○	○○
Example B10	50	2.2	1.2	8.33×10 ⁻¹⁶	PVP	45000	0.0003	1.62×10 ⁻¹⁹	TMAH	0.07	4.62×10 ²¹	195	55400	○	○	○○	○

Table 4 (continued)

	Silicon dioxide			Water-soluble polymer				Basic compound			B/A	C/A	Polishing rate	Surface roughness Ra	Surface roughness Rt	Edge shape B1	
	BET particle diameter [nm]	True specific gravity [g/cm ³]	Content [% by mass]	A	Kind	Weight average molecular weight	Content [% by mass]	B	Kind	Content [% by mass]							C
Comparative Example B1	12	1.8	1.2	7.37×10 ¹⁸	PVP	45000	0.0003	1.62×10 ¹⁹	KOH K2CO3 TMAH	0.004 0.04 0.03	4.15×10 ²¹	2	563	○	○○	×	○○
Comparative Example B2	35	1.8	1.2	2.70×10 ¹⁷	PVP	45000	0.0003	1.62×10 ¹⁹	KOH K2CO3 TMAH	0.004 0.04 0.03	4.15×10 ²¹	55	14000	○	○○	×	○○
Comparative Example B3	50	2.2	1.2	8.33×10 ¹⁶	PVP	45000	0.0003	1.62×10 ¹⁹	TMAH	0.002	1.32×10 ²⁰	195	1580	×	×	○	○○
Comparative Example B4	50	2.2	0.2	1.39×10 ¹⁶	PVP	45000	0.0003	1.62×10 ¹⁹	TMAH	0.4	2.64×10 ²²	1170	1900000	Δ	×	○	×
Comparative Example B5	50	2.2	1.2	8.33×10 ¹⁶	PAA	25000	0.0003	2.51×10 ¹⁹	KOH K2CO3 TMAH	0.004 0.04 0.03	4.15×10 ²¹	301	49800	○	○	×	×
Comparative Example B6	50	2.2	1.2	8.33×10 ¹⁶	PVA	53000	0.0003	4.10×10 ¹⁹	KOH K2CO3 TMAH	0.004 0.04 0.03	4.15×10 ²¹	492	49800	×	○	Δ	Δ
Comparative Example B7	50	2.2	1.2	8.33×10 ¹⁶	PEG	20000	0.0003	4.10×10 ¹⁹	KOH K2CO3 TMAH	0.004 0.04 0.03	4.15×10 ²¹	492	49800	×	○	Δ	Δ
Comparative Example B8	50	2.2	1.2	8.33×10 ¹⁶	-	-	-	-	KOH K2CO3 TMAH	0.004 0.04 0.03	4.15×10 ²¹	-	49800	○○	×	○○	×
Comparative Example B9	50	2.2	1.2	8.33×10 ¹⁶	-	-	-	-	TMAH	0.07	4.62×10 ²¹	-	55400	○	×	○○	×
Comparative Example B10	55	1.8	1.9	1.19×10 ¹⁷	PVP	10000	0.001	5.42×10 ¹⁹	TMAH	0.2	1.32×10 ²²	447	109000	○	×	○	Δ
Comparative Example B11	90	1.8	1.2	1.75×10 ¹⁶	PVP	45000	0.0003	1.62×10 ¹⁹	KOH K2CO3 TMAH	0.004 0.04 0.03	4.15×10 ²¹	930	238000	○○	×	○	Δ
Comparative Example B12	100	2.2	1.2	1.04×10 ¹⁶	PVP	45000	0.0003	1.62×10 ¹⁹	TMAH	0.2	1.32×10 ²²	1560	1270000	○	×	○○	Δ

Table 5

Polishing condition 3	
Polisher:	One side polishing machine (PNX-332B: made by Okamoto Machine Tool Works, Ltd.)
Load:	20 kPa
Rotation speed of platen:	30 rpm
Rotation speed of polishing object:	30 rpm
Polishing pad:	MH-S15A (made by Nitta Haas Incorporated)
Feeding rate of Polishing composition:	2 L/min
Polishing time:	5 min/batch
Holding temperature of polishing composition:	20°C

As shown in Table 4, in Examples B1 to B10, all of the evaluation results of the polishing rate, the surface roughness Ra, the surface roughness Rt, and the edge shape B1 were "oo", "o", or "Δ", which was satisfactory. In contrast, in Comparative Examples B1 to B12, some of the evaluation results of the polishing rate, the surface roughness Ra, the surface roughness Rt, and the edge shape B1 were "x", which was unsatisfactory. It was found from the results that setting the value of B/A and the value of C/A of a polishing composition including silicon dioxide, a nitrogen-containing water-soluble polymer, and a basic compound to a predetermined range allowed the edge shape of a polishing object to be maintained, the surface roughness or the difference in level to be easily reduced, and a high polishing rate to be easily obtained.

CLAIMS

1. A polishing composition to be used for polishing both surfaces of a semiconductor substrate, comprising silicon dioxide, a nitrogen-containing water-soluble polymer, and a basic compound, wherein

the silicon dioxide has an average primary particle diameter of 40 nm or more as calculated from the specific surface area determined by the BET method, and

the value of B/A is 1 or more and less than 7,000 and the value of C/A is 5,000 or more and less than 1,500,000 when in one liter of the polishing composition, A is defined as the number of silicon dioxide, B is defined as the number of monomer units of the nitrogen-containing water-soluble polymer, and C is defined as the number of molecules of the basic compound.

2. A polishing composition comprising silicon dioxide, a nitrogen-containing water-soluble polymer, and a basic compound, wherein

the silicon dioxide has an average primary particle diameter of 40 nm or more as calculated from the specific surface area determined by the BET method, and

the value of B/A is 1 or more and less than 7,000 and the value of C/A is 5,000 or more and less than 100,000 when in one liter of the polishing composition, A is defined as the number of silicon dioxide, B is defined as the number of monomer units of the nitrogen-containing water-soluble polymer, and C is defined as the number of molecules of the basic compound.

3. The polishing composition according to claim 1 or 2, wherein the nitrogen-containing water-soluble polymer has a weight average molecular weight of less than 1,500,000.

4. The polishing composition according to any one of claims 1 to 3, wherein the silicon dioxide has true specific gravity of 1.7 or more.

5 5. The polishing composition according to any one of claims 1 to 4, wherein the basic compound includes a potassium compound and a quaternary ammonium compound.

10 6. A method for producing a semiconductor substrate, comprising polishing a semiconductor substrate with the polishing composition according to any one of claims 1 to 5.