



G00002



150150

SYNTHESIS OF MAGNETITE NANOPARTICLES AND THE PROCESS OF FORMING FE-BASED NANOMATERIALS

BACKGROUND OF THE INVENTION

Field of the Invention

[0001] The present invention generally relates to nanoparticle synthesis, and more particularly to size controlled synthesis of iron-based nanoparticles, especially iron oxide, iron sulfide nanoparticle materials that can have many important technological applications.

Description of the Related Art

[0002] Magnetite, Fe_3O_4 , is one of the three common iron oxides, FeO , Fe_2O_3 , and Fe_3O_4 , which have found many important technological applications. Magnetic iron oxide nanoparticle dispersions, commercially known as "Ferrofluid", have been used widely in, for example, rotary shaft sealing for vacuum vessels, oscillation damping for various electronic instruments, and position sensing for avionics, robotics, machine tool, and automotive [K. Raj, R. Moskowitz, *J. Magn. Mag Mater.*, 85, 233 (1990).]. The magnetite is a semimetallic material. Its dark colored particle dispersion has been used in printing applications as high quality toners or inks [US Patent 4991191, US Patent 5648170, and US Patent 6083476, incorporated herein by reference]. Magnetite dispersion is also useful for the manufacture of liquid crystal devices, including color displays, monochromatic light switches, and tunable wavelength filter [US Patent 3648269, US Patent 3972595, and US Patent 5948321, US Patent 6086780, and US Patent 6103437,

incorporated herein by reference]. As a semiconducting ferrimagnet with high Curie temperature (858K), the magnetite has shown great potential in tunneling device fabrication. [G. Gong, et al, Phys. Rev. B, 56, 5096(1997). J. M. D. Coey, et al, Appl. Phys. Lett., 72, 734(1998). X. Li, et al, J. Appl. Phys., 83, 7049(1998). T. Kiyomura, et al, J. Appl. Phys., 88, 4768(2000). R. G. C. Moore, et al, Physica E, 9, 253(2001). S. Soeya, et al, Appl. Phys. Lett., 80, 823(2002).] The use of magnetite nanoparticles in clinical medicine is an important field in diagnostic medicine and drug delivery. Magnetite nanoparticles, with size of 10-20 nm, are superparamagnetic. These particles interfere with an external homogeneous magnetic field and can be positioned magnetically in a living body, facilitating magnetic resonance imaging (MRI) for medical diagnosis [US 6123920, US6048515, US6203777, US6207134, incorporated herein by reference, D. K. Kim, et al, J. Magn. Mag. Mater., 225, 256(2001)], and AC magnetic field induced excitation for cancer therapy [US6165440, US6167313, incorporated herein by reference, A. Jordan, et al, J. Magn. Mag. Mater., 201, 413(1999)].

[0003] All of these medicinal and technological applications of magnetic iron oxide fluids require that the magnetic particle size is within the single domain size range and the overall particle size distribution is narrow so that the particles have uniform physical properties, biodistribution, bioelimination and contrast effects. For example, for medicinal applications, mean particle sizes should generally be in the range 2 to 15 nm and, for use as blood pool agents, the mean overall particle size including any coating materials should preferably be below 30 nm. However, producing particles with the desired size, acceptable size distribution without particle aggregation has constantly been a problem.

[0004] Two general methods for producing magnetite ferrofluid have been used in the prior art. In the first method, the magnetic fluid was prepared by grinding of magnetite in a ball mill for a long time with a surfactant and carrier solvent, as exemplified in US 3215572, and US3917538, incorporated herein by reference. In the second approach, stable dispersion of magnetite fluid was obtained by transferring co-precipitated magnetite covered with an oleate monolayer into a non-polar solvent. The main characteristics of this method are to obtain an ultrafine magnetic oxide by a chemical reaction from the aqueous solution containing ferrous (Fe^{2+}) and ferric (Fe^{3+}) ions, and to accomplish strong adsorption of surfactants on the magnetic

particles in a water solution, as exemplified in US4019994, US4855079, US6086780, incorporated by reference, and other publications [Y. S. Kang, et al., Chem. Mater. 8, 2209(1996). C.-Y. Hong, et al, J. Appl. Phys. 81, 4275(1997). T. Fried, et al, Adv. Mater. 13, 1158(2001).]. This method does not need a long preparation time like the grinding method and is suitable for mass production of magnetic fluid. But, it does need constant adjustments on pH value of the solution to ensure the particle formation and stabilization. Recently, a third sonochemical synthesis of Fe_3O_4 from Fe(II) salt was reported [R. Vijayakumar, et al, Materials Sci. Eng. A286, 101(2000). G. B. Biddlecombe, et al., J. Mater. Chem., 11, 2937(2001).]. The major disadvantage of all these techniques is heterogeneity in the size distribution of the resulting magnetic particles, the composition of these particles, and/or the interaction forces between the particles. The process towards smaller magnetite nanocrystals has very limited success.

SUMMARY OF THE INVENTION

[0005] The present invention presents an approach that makes magnetite nanoparticle materials by mixing iron salt with alcohol, carboxylic acid and amine in an organic solvent and heating the mixture to 200-360°C. The size of the particles can be controlled either by changing the iron salt to acid/amine ratio or by coating small nanoparticles with more iron oxide. Magnetite nanoparticles in the size ranging from 2 nm to 20 nm with a narrow size distribution are obtained with the invention. The invention can be readily extended to other iron oxide based nanoparticle materials, including $\text{M Fe}_2\text{O}_4$ ($\text{M} = \text{Co, Ni, Cu, Zn, Cr, Ti, Ba, Mg}$) MRFeO_x ($\text{R} = \text{rare earth metal}$) nanomaterials, and iron oxide coated nanoparticle materials. The invention also leads to the synthesis of iron sulfide based nanoparticle materials by replacing alcohol with thiol in the reaction mixture. The magnetite nanoparticles can be oxidized to $\gamma\text{-Fe}_2\text{O}_3$, or $\alpha\text{-Fe}_2\text{O}_3$, or can be reduced to bcc-Fe nanoparticles, while iron oxide based materials can be used to make binary iron based metallic nanoparticles, such as CoFe , NiFe , and FeCoSm_x nanoparticles.

[0006] An object of the present invention is to provide a method for synthesizing Fe_3O_4 nanoparticle materials, with controlled particle sizes. A second object of the invention is to

make other types of iron oxide nanoparticle materials, such as MFe_2O_4 , $RFeO_3$, or $MFeO_x$ nanoparticle materials. A third object of the invention is to make iron oxide coated nanoparticle materials. A fourth object of the invention is to make iron sulfide and iron sulfide coated nanoparticle materials, and another object of the invention is to make metallic nanomaterials.

[0007] To make Fe_3O_4 with the invention, iron salt is mixed in solvent with alkyl alcohol, alphabetic acid, and primary amine. The mixture is heated at a temperature in the range of 200°C to 360°C. After cooling, the magnetite nanoparticles are precipitated out from their dispersion and redispersed into the solvent. The size the particles is controlled by adjusting either the iron to acid/amine ratio or the reaction temperature. Large sized particles can also be obtained by adding small Fe_3O_4 nanoparticles to the mixture and heating to reflux. Adding a different metal salt to the mixture will lead to MFe_2O_4 nanomaterials, while adding a different type of nanoparticle to the mixture will yield iron oxide coated core-shell particle materials. By replacing alcohol with thiol in the mixture, both iron sulfide nanomaterials and iron sulfide coated core-shell nanomaterials can be made. Passing oxygen through the Fe_3O_4 materials will result in either $\gamma-Fe_2O_3$ or $\alpha-Fe_2O_3$, depending on the reaction temperature applied, while passing hydrogen-containing gas through the Fe_3O_4 particles will lead to bcc-Fe nanoparticle materials.

BRIEF DESCRIPTION OF THE DRAWINGS

[0008] The foregoing and other objects, aspects and advantages will be better understood from the following detailed description of a preferred embodiment(s) of the invention with reference to the drawings, in which:

[0009] Figure 1 is a schematic that shows a generalized scheme for the preparation of Fe_3O_4 nanoparticles via iron salt reduction/decomposition;

[0010] Figure 2 shows a TEM image of 6 nm Fe_3O_4 particles prepared from the Scheme shown in Figure1;

[0011] Figure 3 shows a TEM image of 8 nm Fe_3O_4 nanoparticles prepared according to the scheme shown in Figure 1 via coating 6 nm Fe_3O_4 nanoparticles with more iron oxide;

[0012] Figure 4 shows a TEM image of 12 nm Fe_3O_4 nanoparticles prepared according to the scheme shown in Figure 1 via coating 8 nm Fe_3O_4 nanoparticles with more iron oxide;

[0013] Figures 5A-5C show three TEM images of 16 nm Fe_3O_4 nanocrystals prepared according to the scheme shown in Figure 1 via coating 12 nm Fe_3O_4 nanoparticles with more iron oxide; Figure 5A is a low resolution image of a 2D nanocrystal assembly; Figure 5B is a low resolution image of a 3D superlattice nanocrystal assembly, and Figure 5C is a high resolution atomic lattice image of several nanocrystals;

[0014] Figure 6 shows the X-ray diffraction patterns of (A) 4 nm, (B) 8 nm, (C) 12 nm, and (D) 16 nm Fe_3O_4 nanocrystal assemblies. The samples were deposited on glass substrate from their hexane dispersions. Diffraction patterns were collected on a Siemens D-500 diffractometer under Co K α radiation ($\lambda = 1.788965 \text{ \AA}$);

[0015] Figure 7A and 7B show hysteresis loops of Fe_3O_4 nanocrystal materials at room temperature (e.g., 15°C - 30°C), Figure 7A is from 4 nm Fe_3O_4 and 7B is from 8 nm Fe_3O_4 ;

[0016] Figure 8 shows the X-ray diffraction pattern of iron sulfide nanocrystal materials;

[0017] Figure 9 is a schematic that indicates that, starting with Fe_3O_4 nanoparticles, a variety of other iron based nanoparticle materials can be made; and

[0018] Figure 10 shows the X-ray diffraction patterns of (A) 16 nm Fe_3O_4 nanocrystals and (B) $\gamma\text{-Fe}_2\text{O}_3$ nanocrystals obtained from O_2 oxidation of 16 nm Fe_3O_4 at 250°C for 2h, and (C) bcc-Fe nanocrystal assembly from the reduction of Fe_3O_4 under $\text{Ar}+\text{H}_2(5\%)$ at 400°C for 2h.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS OF THE INVENTION

[0019] As mentioned above, a first object of the present invention is to provide a method for synthesizing Fe_3O_4 nanoparticles, with controlled particle sizes and size distribution. As shown in Figure 1, iron oxide nanoparticle materials can be made by mixing iron salt, alcohol,

carboxylic acid and amine in an ether solvent and heating the mixture to reflux. A black solution is formed. After being cooled to room temperature (e.g., 15°C-30°C), the mixture is treated with ethanol and black magnetic materials was precipitated out from the solution. The black product is dissolved in hexane in the presence of acid and amine, and re-precipitated with ethanol. This way, high boiling solvent and other organic impurities can be removed from the nanoparticle product, yielding pure Fe₃O₄ nanoparticle materials. The materials can disperse into various solvents to give a black-brown solution. TEM analysis shows that particles are nearly monodisperse. Using this procedure by varying the stabilizer/iron ratio, or increasing reaction temperature, the magnetite nanoparticles with sizes ranging from 2 nm to 12 nm can be made. Fig.2 is a TEM image of 6 nm Fe₃O₄ nanocrystals prepared according to Figure 1 and deposited from their hexane dispersion on an amorphous carbon surface. Such nanocrystals can serve as seeds for large Fe₃O₄ nanocrystal formations.

[0020] The larger Fe₃O₄ nanocrystals can also be made by seed mediated growth. The small Fe₃O₄ nanocrystals, the seeds, are mixed with more materials shown in Figure 1 and heated to reflux. By controlling the amount of small nanocrystal seeds, variously sized Fe₃O₄ nanocrystals can be formed. The method leads to Fe₃O₄ nanoparticles in the size ranging from 4 nm to 20 nm, depending on the relative weight of small Fe₃O₄ and iron salt mixture used. For example, mixing and heating 62 mg of 8 nm Fe₃O₄ nanoparticles with 2 mmol of iron salt, 10 mmol alcohol, 2 mmol of carboxylic acid and 2 mmol amine led to 12 nm Fe₃O₄ nanoparticles, while mixing and heating 15 mg of 8 nm Fe₃O₄ with the same amount of iron salts and other organic precursors led to 16 nm Fe₃O₄ nanoparticles.

[0021] Figs. 3-5C are TEM images of variously sized Fe₃O₄ nanocrystals prepared using the seed-mediated growth method. Compared with the magnetite nanocrystals shown in Fig.2, these images demonstrate that the seed-mediated growth not only yields larger nanocrystals, it also narrows the size distribution of the nanocrystals, leading to more uniform nanocrystal materials and facilitating the formation of nanocrystal superlattices, as shown in Fig.5B. The high quality of crystal nature of these nanocrystals (fcc spinel structure) is revealed by both high-resolution TEM for a single nanocrystal and X-ray diffractometry for a group of nanocrystals. The atomic lattices corresponding to lattice constant of $d(111) = 4.86$ angstroms

are clearly seen in high-resolution TEM image (Fig. 5C). The unit cell parameter from this fcc spinel structure is 8.41 angstroms, which agrees with that of standard Fe_3O_4 . Fig.6 shows the X-ray diffraction patterns of variously sized Fe_3O_4 nanocrystal assemblies made from Figure 1 pattern (A) and seed mediated growth patterns (B-D). From x-ray line broadening in Fig.6, the average diameter of the particles can be estimated from Scherrer's formula:

$$L_{hkl} = K\lambda/\beta\cos\theta$$

in which L is the average crystallite size along the direction of the Miller indices (hkl), λ is the wavelength of the x-rays used, K is Scherrer's constant and has a value of about 0.9. θ is the Bragg angle, and β is the peak width at half-height in radians. The calculation confirms that the particle dimensions match the average particle size determined by statistical analysis of the TEM images, indicating that each particle is an individual single crystal.

[0022] Due to the small size of Fe_3O_4 nanocrystals, they are superparamagnetic at room temperature. Figs.7A and 7B illustrate hysteresis loops of two different Fe_3O_4 nanocrystal materials at room temperature. Fig.7A is from 4 nm Fe_3O_4 nanocrystals, and Fig.7B is from 8 nm Fe_3O_4 nanocrystals. It can be seen that smaller particles (4 nm) need stronger magnetic fields to align them due to the thermal agitation (kT) of the small particles with low magnetic anisotropy energy (KV).

[0023] The process shown in Figure 1 can be readily extended to the synthesis of more complicated nanoparticle materials, such as MFe_2O_4 nanoparticle materials. This involves mixing M (or R) salt and iron salt in a solvent with alkyl alcohol, alphabetic acid, and primary amine and heating the mixture to reflux. Metal salts can be from any of following salts: Zn, Cu, Ni, Co, Mn, Cr, V, Ti, Mg, Ba and rare earth metals. And, iron salt can be any of $\text{Fe}(\text{OOCCH}_3)_2$, $\text{Fe}(\text{acac})_2$, $\text{Fe}(\text{acac})_3$, FeC_2O_4 , $\text{Fe}_2(\text{C}_2\text{O}_4)_3$. Some non-stoichiometric nanomaterials such as FeMo_xO_y , $\text{CoSm}_x\text{Fe}_y\text{O}_z$ can also be made in a similar way.

[0024] The same process shown in Figure 1 can also produce iron oxide coated nanoparticle materials. For example, mixing iron salt and FePt nanoparticles with alkyl alcohol, alphabetic acid, and primary amine in a solvent and heating the mixture to reflux will give Fe_3O_4

coated FePt nanoparticles. The process is rather general and can be applied to other iron oxide coated nanoparticle syntheses, including magnetic Co, Ni, Fe, FePt, etc and non magnetic Au, Ag, Cu, Pt, Pd, etc.

[0025] Replacing alcohol (ROH) in the Fe_3O_4 synthesis with alkane thiol (RSH) leads to iron sulfide nanomaterials. Fig. 8 is the X-ray diffraction pattern of as synthesized iron sulfide nanocrystal materials. It matches with pyrrhotite FeS phase. Similar to the iron oxide coating experiments, iron sulfide coated nanoparticles can also be made by mixing nanoparticles with iron salt, thiol, carboxylic acid, and amine in a solvent and heating to reflux. The core nanoparticles include not only magnetic nanoparticles, but also non-magnetic nanoparticles. The process can be extended to produce other complicated nanomaterials as well, including non stoichiometric FeMoS_x , and CoMoS_x nanomaterials.

[0026] The Fe_3O_4 based nanocrystal materials can be used as starting materials for other iron oxide nanocrystal materials and metallic nanocrystal materials. Figure 9 shows an example of various transformations of Fe_3O_4 . For example, passing oxygen through Fe_3O_4 nanocrystal assembly at 250C gives $\gamma\text{-Fe}_2\text{O}_3$ nanocrystal assembly, and at 500C, yields $\alpha\text{-Fe}_2\text{O}_3$ nanocrystal assembly. Passing reducing gas [$\text{Ar}+\text{H}_2(5\%)$] through a Fe_3O_4 nanocrystal assembly at 400C leads to bcc-Fe nanocrystal assembly. The transformation is illustrated in Fig. 10, in which line A is from starting Fe_3O_4 , Line B is from the annealed Fe_3O_4 under O_2 at 250C for 2h, and Line C is from the annealed Fe_3O_4 under $\text{Ar}+\text{H}_2(5\%)$ at 400C for 2h. Line B matches with the well-known $\gamma\text{-Fe}_2\text{O}_3$, while Line C relates to typical bcc-Fe. Similarly, other oxide nanomaterials such as CoFeO_x , NiFeO_x , or SmCoFeO_x etc nanomaterials can also be used as starting materials for the synthesis of some metallic nanomaterials, CoFe, NiFe, or SmCoFe_x.

[0027] The following shows how the invention is useful with the general synthesis of 4 nm Fe_3O_4 nanocrystal materials. Iron (III) acetylacetonate (706 mg, 2 mmol), 1,2-hexadecanediol (2.58g, 10 mmol), oleic acid (6 mmol), oleyl amine (6 mmol) and dioctyl ether (20 mL) should be mixed in a glass vessel and heated to reflux for 30 minutes. The heating source should then be removed and the black-brown reaction mixture allowed to cool to room temperature. Ethanol should then be added. The black product should be precipitated and separated by centrifugation. Yellow-brown supernatant should be discarded and the black

product dispersed in hexane in the presence of oleic acid and oleyl amine. Any unsolved precipitation should be removed by centrifugation. The Fe_3O_4 nanocrystals should be precipitated out by adding ethanol and centrifugation and are easily re-dispersed in an alkane solvent, aromatic solvent, or chlorinated solvent. Various sized Fe_3O_4 up to 12 nm in diameter can be made in a similar way by changing the stabilizer/iron salt ratio or the reaction temperature.

[0028] The following shows how the invention is useful with the general synthesis of 16 nm Fe_3O_4 nanocrystal materials. Iron (III) acetylacetonate (706 mg, 2 mmol), 1-octadecanol (2.70g, 10 mmol), oleic acid (2 mmol), oleyl amine (2 mmol), phenyl ether (20 mL), and 8 nm Fe_3O_4 nanoparticles (15 mg) dispersed in hexane should be mixed in a glass vessel under nitrogen, stirred and heated to 100°C to remove hexane. The mixture should be then heated to reflux for 30 minutes. The heating source should be removed and the black-brown reaction mixture cooled to room temperature. Ethanol should be added. The black product should be precipitated and separated by centrifugation. The yellow-brown supernatant should be discarded and the black product dispersed in hexane in the presence of oleic acid and oleyl amine. Any unsolved precipitation should be removed by centrifugation. The Fe_3O_4 nanocrystals should be precipitated out by adding ethanol and centrifugation. They can be easily re-dispersed in alkane solvent, aromatic solvent and chlorinated solvent. Such seed mediated growth method can be used to make variously sized Fe_3O_4 nanoparticle materials with sizes ranging from 4 nm to 20 nm.

[0029] The following shows how the invention is useful with the general synthesis of CoFe_2O_4 nanocrystal materials. Iron (III) acetylacetonate (706 mg, 2 mmol), cobalt (II) acetylacetonate (1 mmol), 1-octadecanol (2.70g, 10 mmol), oleic acid (2 mmol) and oleyl amine (2 mmol) and phenyl ether (20 mL) should be mixed in a glass vessel and heated to reflux for 30 minutes. The heating source should be removed and the black-brown reaction mixture be cooled to room temperature. Ethanol should be added. The black product should be precipitated and separated by centrifugation. The yellow-brown supernatant should be discarded and the black product dispersed in hexane in the presence of oleic acid and oleyl amine. Any unsolved precipitation should be removed by centrifugation. The CoFe_2O_4 nanocrystals should be precipitated out by adding ethanol and centrifugation. They can be easily re-dispersed in alkane

solvent, aromatic solvent and chlorinated solvent. By changing the cobalt salt to other metal salts, various MFe_2O_4 nanocrystal materials can be made, in which $M = Zn, Cu, Ni, Co, Mn, Cr, V, Ti, Mg, \text{ or } Ba$.

[0030] The following shows how the invention is useful with the general process for making Fe_3O_4 coated FePt nanomaterials. Iron (III) acetylacetonate (706 mg, 2 mmol), 1-octadecanol (2.70g, 10 mmol), oleic acid (2 mmol), oleyl amine (2 mmol), phenyl ether (20 mL), and 4 nm FePt nanoparticles dispersed in hexane should be mixed in a glass vessel under nitrogen, stirred and heated to 100°C to remove hexane. The mixture should be then heated to reflux for 30 minutes. The heating source should be removed and the black-brown reaction mixture cooled to room temperature. Ethanol should be added. The black product should be precipitated and separated by centrifugation. The yellow-brown supernatant should be discarded and the black product dispersed in hexane in the presence of oleic acid and oleyl amine. Any unsolved precipitation should be removed by centrifugation. The nanocrystals should be precipitated out by adding ethanol and centrifugation. They can be easily re-dispersed in alkane solvent, aromatic solvent and chlorinated solvent. The process can be readily extended to other types of iron oxide coated nanomaterials with core including magnetic (Co, Ni, Fe) and nonmagnetic (Ag, Au, Pd, Pt, Cu, or other polymer based particles) nanoparticles.

[0031] The following shows how the invention is useful with the general synthesis of iron sulfide nanocrystal materials. Iron (III) acetylacetonate (706 mg, 2 mmol), 1-hexadecane thiol (6 mmol), oleic acid (2 mmol), oleyl amine (2 mmol) and phenyl ether (20 ml) should be mixed and heated to reflux for 30 minutes. The heating source should be removed and the black-brown reaction mixture cooled to room temperature. Ethanol should be added. The black product should be precipitated and separated by centrifugation. The yellow-brown supernatant should be discarded and the black product dispersed in hexane in the presence of oleic acid and oleyl amine. Any unsolved precipitation should be removed by centrifugation. The iron sulfide nanocrystals should be precipitated out by adding ethanol and centrifugation. The process can be used to make other metal sulfides, such as cobalt sulfide, nickel sulfide, etc., as well as metal sulfide coated nanoparticle materials.

[0032] The above made iron oxide and iron sulfide based nanoparticle materials could have many important applications in such as ferrofluid, data storage, sensor, medicinal imaging, drug delivery, catalysis, and magnetic and optical devices.

[0033] Therefore, as shown above, the present invention presents an approach that makes magnetite nanoparticle materials by mixing iron salt with alcohol, carboxylic acid and amine in an organic solvent and heating the mixture to 200-360C. The size of the particles can be controlled either by changing the iron salt to acid/amine ratio or by coating small nanoparticles with more iron oxide. Magnetite nanoparticles in the size ranging from 2 nm to 20 nm with a narrow size distribution are obtained with the invention. The invention can be readily extended to other iron oxide based nanoparticle materials, including MFe_2O_4 ($M = Co, Ni, Cu, Zn, Cr, Ti, Ba, Mg$) nanomaterials, and iron oxide coated nanoparticle materials. The invention also leads to the synthesis of iron sulfide based nanoparticle materials by replacing alcohol with thiol in the reaction mixture. The magnetite nanoparticles can be oxidized to $\gamma-Fe_2O_3$, or $\alpha-Fe_2O_3$, or can be reduced to bcc-Fe nanoparticles, while iron oxide based materials can be used to make binary iron based metallic nanoparticles, such as CoFe, NiFe, and $FeCoSm_x$ nanoparticles.

[0034] While the invention has been described in terms of preferred embodiments, those skilled in the art will recognize that the invention can be practiced with modification within the spirit and scope of the context.

CLAIMS

1. A process of making an iron oxide nanoparticle material comprising:
mixing an iron salt with an alcohol, an organic acid, and an organic amine in an organic solvent to produce a mixture;
heating said mixture;
cooling said mixture to room temperature;
precipitating a product from said mixture; and
dispersing said product in a solvent to produce a nanocrystal dispersion.
2. The process of claim 1, wherein said heating comprises heating said mixture to a temperature between 200°C and 360°C.
3. The process of claim 1 or 2, wherein said iron salt comprises one of $\text{Fe}(\text{OOCCH}_3)_2$, $\text{Fe}(\text{acac})_2$, $\text{Fe}(\text{acac})_3$, FeC_2O_4 , $\text{Fe}_2(\text{C}_2\text{O}_4)_3$,
where $\text{acac} = \text{CH}_3\text{COCHCOCH}_3$.
4. The process of any one of claims 1 to 3, wherein said alcohol comprises an organic alcohol having a basic formula of $\text{R}(\text{OH})$, and includes mono-alcohol and poly-alcohol.
5. The process of any one of claims 1 to 4, wherein said organic acid comprises an organic acid having a basic formula of RCOOH , RSOH , RPOH .
6. The process of any one of claims 1 to 5, wherein said amine comprises one of RNH_2 , R_2NH , and R_3N .
7. The process of any one of claims 1 to 6, wherein said solvent comprises one of ROH , R-O-R , and R-N-R .
8. The process of any one of claims 1 to 7, wherein said dispersion comprises one of water, alcohol, acetone, alkane, aromatic solvent, and chlorinated solvent.
9. An iron oxide nanoparticle material made according to the process of any one of claims 1 to 8.
10. A process of making a metal doped iron oxide nanoparticle material comprising:
mixing an iron salt with a metal salt, an alcohol, an organic acid, and an organic amine in an organic solvent to produce a mixture;
heating said mixture;
cooling said mixture to room temperature;
precipitating a product from said mixture; and
dispersing said product in a solvent to produce a nanocrystal dispersion.

11. The process of claim 10, wherein said heating comprises heating said mixture to a temperature between 200°C and 360°C.

12. The process of claim 10 or 11, wherein said metal salt comprises one of the following and their derivatives: $\text{Co}(\text{OOCCH}_3)_2$, $\text{Co}(\text{acac})_2$, $\text{Co}_3(\text{citrate})_2$, $\text{Ni}(\text{OOCCH}_3)_2$, $\text{Ni}(\text{acac})_2$, $\text{Ni}(\text{oxalate})$, $\text{Cu}(\text{OOCCH}_3)_2$, $\text{Cu}(\text{acac})_2$, $\text{Cu}(\text{oxalate})$, $\text{Zn}(\text{OOCCH}_3)_2$, $\text{Zn}(\text{acac})_2$, $\text{Zn}(\text{oxalate})$, $\text{Mn}(\text{OOCCH}_3)_2$, $\text{Mn}(\text{acac})_2$, $\text{Mg}(\text{OOCCH}_3)_2$, $\text{Mg}(\text{acac})_2$, $\text{Ba}(\text{OOCCH}_3)_2$, $\text{Ba}(\text{acac})_2$, $\text{Sm}(\text{OOCCH}_3)_3$, $\text{Sm}(\text{acac})_3$, $\text{MoO}_2(\text{acac})_2$, where $\text{acac} = \text{CH}_3\text{COCHCOCH}_3$.

13. The process of any one of claims 10 to 12, wherein said nanomaterials comprise one of stoichiometric MFe_2O_4 , non-stoichiometric MFe_xO_y , FeMo_xO_y , and $\text{CoSm}_x\text{Fe}_y\text{O}_z$.

14. A metal doped iron oxide nanoparticle made according to the process of any one of claims 10 to 13.

15. A process of making an iron oxide coated nanoparticle material comprising:
mixing nanoparticles with an iron salt, an organic alcohol, an organic acid, and an organic amine in an organic solvent to produce a mixture;

heating said mixture;

cooling said mixture to room temperature;

precipitating a product from said mixture; and

dispersing said product in a solvent to produce a nanocrystal dispersion.

16. The process of claim 15, wherein said heating comprises heating said mixture to a temperature between 200°C and 360°C.

17. The process of claim 15 or 16, wherein said nanoparticles comprise one of a metal oxide, a metal, and a polymer.

18. The process of claim 17, wherein said metal oxide comprises an oxide of one of Fe, Co, Ni, Cu, Zn, Mn, Cr, V, Ti, Mg, Ca, Ba, and Sm_2O_3 .

19. The process of claim 17, wherein said metal comprises one of Fe, Co, Ni, Cu, Ag, Au, Pd, and Pt.

20. The process of claim 17, wherein said polymer comprises one of silica and polyhydrocarbon.

21. The process of any one of claims 15 to 20, wherein said iron oxide comprises one of FeO_x and MFe_xO_y .

22. An iron oxide coated nanoparticle material made by the process of any one of claims 15 to 21.

23. A process of making an iron sulfide nanoparticle material comprising:

mixing an iron salt with an organic thiol, an organic acid, and an organic amine in an organic solvent to produce a mixture;

heating said mixture;

cooling said mixture to room temperature;

precipitating a product from said mixture; and

dispersing said product in a solvent to produce a nanocrystal dispersion.

24. The process of claim 23, wherein said heating comprises heating said mixture to a temperature between 200°C and 360°C.

25. The process of claim 23 or 24, wherein said thiol comprises any thiols from a basic formula: RSH.

26. An iron sulfide nanoparticle material made according to the process of any one of claims 23 to 25.

27. A process of making a metal doped iron sulfide nanoparticle material comprising:

mixing an iron salt with a metal salt, an organic thiol, an organic acid, and an organic amine in an organic solvent to produce a mixture;

heating said mixture;

cooling said mixture to room temperature;

precipitating a product from said mixture; and

dispersing said product in a solvent.

28. The process of claim 27, wherein said heating comprises heating said mixture to a temperature between 200°C and 360°C.

29. The process of claim 27 or 28, wherein said metal salt comprises one of the following and their derivatives: $\text{MoO}_2(\text{acac})_2$, $\text{Mo}(\text{OOCCH}_3)_2$, $\text{Co}(\text{OOCCH}_3)_2$, $\text{Co}(\text{acac})_2$.

30. A metal doped iron sulfide nanoparticle material made by the process of any one of claims 27 to 29.

31. A process of making an iron sulfide coated nanoparticle material comprising:

mixing nanoparticles with a metal salt, an organic thiol, an organic acid, and an organic amine in an organic solvent to produce a mixture;

heating said mixture;

cooling said mixture to room temperature;

precipitating a product from said mixture; and

dispersing said product in solvent to produce a nanocrystal dispersion.

32. The process of claim 31, wherein said heating comprises heating said mixture to a temperature between 200°C and 360°C.

33. An iron-sulfide coating nanoparticle material made according to the process of claim 31 or 32.

34. A process of making Fe_2O_3 nanocrystals comprising:

oxidizing Fe_3O_4 nanocrystals with an oxidizing agent, at a temperature above 30°C .

35. The process of claim 34, wherein said temperature is between 200°C and 500°C .

36. The process of claim 34 or 35, wherein said oxidizing agent comprises one of oxygen and peroxide.

37. Fe_2O_3 nanocrystals made according to the process of any one of claims 34 to 36.

38. A process of making Fe-based nanocrystals comprising:

reducing one of Fe_3O_4 and MFeO_x nanocrystals with a reducing agent at a temperature above 30°C .

39. The process of claim 38, wherein said temperature is between 250°C and 500°C .

40. The process of claim 38 or 39, wherein said Fe nanocrystals comprise one of a bimetallic FeM , where $\text{M} = \text{Co}$, and Ni , Cu , Zn , Cr , and a multi-metallic CoFeSm_x , CoFeMo_x .

41. The process of any one of claims 38 to 40, wherein said reducing agent comprises one of hydrogen, a metal hydride, and a unit adapted to give out electrons.

42. Fe-based nanocrystals made according to the process of any one of claims 38 to 41.