

## PROCESS FOR THE INJECTION OF AN ELECTRIC MOTOR ROTOR

Field of the Invention

The present invention refers to a process for providing the injection, by centrifugation, of the cage made of aluminum, or other adequate metal, into the stack of steel laminations of the rotor of an electric motor, particularly the rotor of small electric motors, such as those used in the hermetic compressors of small refrigeration systems.

10 Background of the Invention

It is already known from the prior art the injection, by centrifugation, of the aluminum cages in rotors, which are formed by a stack of overlapped identical annular steel laminations provided with openings that are longitudinally aligned with the openings of other laminations of the stack, in order to define a plurality of axial channels interconnecting the external faces of the end laminations of the stack and which are angularly spaced from each other along a circular alignment, which is concentric to the longitudinal axis of the lamination stack, but radially spaced back in relation to the lateral face of the latter.

As illustrated in figures 1-5 representative of the state of the art, the lamination stack 10, with the vertically disposed longitudinal axis, is positioned inside a mold 20, which defines a lower annular cavity 22 close to the external face of the lower end lamination, and an upper cavity 21, which is substantially cylindrical or frusto-conical, close to the external face of the upper end lamination and opened to the inlet channel 23 for the admission of aluminum into the mold 20.

During the pouring of the aluminum or of the selected metallic alloy, the lamination stack 10 has its

central axial bore 11, into which will be later mounted the shaft of the electric motor, filled with a core 25, having an upper end substantially leveled with the upper end lamination of the lamination stack 10, and having a widened lower end portion seated on a  
5 10, and having a widened lower end portion seated on a respective lower end widening 11a of the central axial bore 11 of the lamination stack 10 and against the mold that defines the lower cavity 22.

The aluminum is poured into the upper cavity 21, passing through the axial channels 12 of the  
10 lamination stack 10 to the lower cavity 22, filling the latter, the axial channels 12, and the upper cavity 21, in this order, and solidifying in a radial inward upward pattern, as the mold 20 rotates around  
15 its vertical axis and the metal cools.

Upon completion of the aluminum pouring and solidification, the mold 20 is opened and the formed rotor is submitted to machining operations, in order to eliminate a projection 36 that has solidified in  
20 the inlet channel 23 (figure 4) and, subsequently, the aluminum plate that has molten against the upper end lamination of the lamination stack 10, in order to unobstruct the adjacent end of the central axial bore 11 of the lamination stack 10, and to define the  
25 correct internal profile for the upper ring 31 of the aluminum cage, which further comprises, in a single piece, a lower ring 32 already formed by the mold 20, and a plurality of bars 33 formed inside the axial channels 12 of the lamination stack 10.

30 In the centrifugation injection of these rotors, the upper cavity 21 and the lower cavity 22 of the mold 20 and the lamination stack 10 itself are heated, so that the molten aluminum passes through the upper cavity 21 and through the axial channels 12 of the lamination  
35 stack 10 without solidifying, gravitationally reaching

the lower cavity 22, filling the latter and starting to solidify from the outside to the inside and from the bottom upwardly. Therefore, the upper cavity 21 and the lamination stack 10 are usually heated at a temperature much lower than the melting temperature of the aluminum, while the lower cavity 22 is heated at a lower temperature, allowing the aluminum to be solidified lastly at the hottest upper region of the mold 20. In order that the air existing in both the upper cavity 21 and the lower cavity 22, and in the axial channels 12 be conducted outwardly from the mold by the aluminum supplied to said mold, the lower cavity 22 is provided with an air outlet of any adequate construction (not illustrated).

As illustrated in figures 1-5, the pouring of the aluminum into the mold 20 is effected through the inlet channel 23 and to the interior of the upper cavity 21, whose lower wall is defined by the upper end lamination of the lamination stack 10, and by the upper end of the rod 25 introduced in the central axial bore 11 of the lamination stack 10.

However, the liquid aluminum poured into the upper cavity 21 comes into direct contact with the internal marginal region of the upper end lamination of the lamination stack 10, which causes deformations in this region and allows the aluminum to penetrate between the upper laminations of the lamination stack 10.

Besides requiring extensive machining operations to form the upper ring 31, this prior art injection process requires a difficult machining of the central region of the upper ring 31 in order to adapt the oil pump of the compressor, due to the deformation of the upper end lamination in the uncovered central region of the upper ring 31. These machining operations reduce the productivity and increase the production

cost of the rotors, particularly the rotors of small dimensions with a large volume of production. Furthermore, the penetration of aluminum between the laminations radially outwardly from the upper end region of the central axial bore 11 impairs the  
5 electromagnetic efficiency of the rotor.

#### Object of the Invention

By reason of the above-mentioned problems related to the process for injecting rotors by centrifugation, it  
10 is the object of the present invention to provide a process for injecting these parts by centrifugation, which considerably reduces the machining operations to form the upper ring of the cage made of aluminum or other conductive material of the rotor, and eliminates  
15 the problem of deformation of the upper end lamination and consequently the penetration of aluminum between the upper laminations of the lamination stack.

#### Summary of the Invention

Aiming at attaining the above-mentioned objective, the  
20 injection process of the present invention is applied to obtain a rotor comprising: a lamination stack provided with a central axial bore and a plurality of axial channels; and a cage, which is made of molten metal and formed by an upper end ring and by a lower  
25 end ring, which are respectively seated against the upper and lower end laminations of the lamination stack, and interconnected, in a single piece, by a plurality of bars that are molten in the axial channels.

30 According to the invention, the injection process of the cage comprises the steps of:

- filling the lower end of the central axial bore with a respective core; mounting, at the upper end portion of the central axial bore, a stamping pin, which has a  
35 widened head seated against the upper end lamination

of the lamination stack and presents a circular contour with a diametrical cross section that defines part of the height of the diametrical cross section of the central opening of the upper ring of the cage;

5 - heating the lamination stack at a first temperature that is lower than the melting temperature of the metal to be injected;

- heating, at said first temperature, an upper cavity of a mold to be positioned close to the upper end  
10 lamination of the lamination stack and, at a second temperature, substantially lower than the first, a lower cavity of the mold to be positioned close to the lower end lamination of the lamination stack;

- positioning the lamination stack, with its  
15 vertically disposed longitudinal axis, inside the mold;

- rotating the mold and pouring the metal therein, through the inlet channel, in order to fill the lower cavity, the axial channels, and the upper cavity;

20 - allowing the metal to solidify, stopping the mold and opening it to remove the rotor and the core from the interior thereof, with the cage already formed and comprising the lower ring, the bars, and an upper plate that covers the stamping pin; and

25 - axially extracting the stamping pin, in order to break, centrally, the upper plate, transforming it in the upper ring of the cage.

As it can be noted, the present process eliminates the harmful effects of the liquid metal contacting, at a  
30 high temperature, the exposed central portion of the upper end lamination, as well as the necessity of machining a large quantity of aluminum to form the central opening of the upper ring of the cage. The removal of the stamping pin causes the rupture of the  
35 upper plate of the metal, practically defining the

central opening of the upper ring of the cage and only requiring, if needed, a slight machining (chamfering) for the finishing of the sharp edge to eliminate the barbs originated from the extraction of the stamping  
5 pin.

Brief Description of the Drawings

The invention will be described below, with reference to the enclosed drawings, in which:

Figure 1 is a diametrical longitudinal sectional view  
10 of a lamination stack mounted inside a mold, for the subsequent injection of aluminum or other metal by centrifugation, according to a prior art process;

Figure 2 is a view similar to that of figure 1, but illustrating the lamination stack already carrying the  
15 cage formed in the interior of the two cavities of the mold, and in the axial channels of the lamination stack;

Figure 3 is a longitudinal sectional view of the rotor obtained by the prior art process and after it has  
20 been removed from the mold illustrated in figure 2, said view further illustrating the deformation that usually occurs in the upper end lamination of the lamination stack;

Figures 4-5 are views similar to that of figure 3, but  
25 illustrating two machining operations that the prior art requires to form the upper ring of the cage;

Figure 6 is a view similar to that of figure 2, but illustrating the cage injected in the lamination stack, according to the process of the present  
30 invention;

Figure 7 is a view similar to that of figure 3, but illustrating the rotor as extracted from the mold and released from the lower core, according to a further step of the new process; and

35 Figure 8 is a view similar to that of figure 7, but

illustrating the step of removing the stamping pin, in order to form the central opening of the upper ring of the cage.

Detailed Description of the Invention

5 As already mentioned, in the process of injection by centrifugation shown in figures 1-5, the injection of liquid aluminum (or other metal) into the upper cavity is directly made over the whole external annular surface of the upper end lamination of the lamination  
10 stack 10, producing deformations on said surface.

Besides the problem above, the upper cavity 21 of the mold 20 is configured to provide the melting of a plate 35, incorporating an upper axial projection 36 defined inside the inlet channel 23, and which is  
15 partially used to compensate the contraction of the aluminum during the solidification.

This solution requires the machining operations schematically illustrated in figures 4-5.

According to the process of the present invention, the  
20 lamination stack 10 has the lower end widening 11a of the central axial bore 11 filled with a respective core 25, which is fitted inside part of the extension of the central axial bore 11 of the lamination stack 10.

25 In the upper end portion of the central axial bore 11 is fitted a stamping pin 40, which presents a widened head 41 of circular contour, seated on the upper end lamination of the lamination stack 10. The widened head 41 of the stamping pin 40 is dimensioned so that  
30 its diametrical cross section coincides with the diametrical cross section of the central opening of the upper ring 31 of the cage 30.

The lamination stack 10 thus prepared is heated at an adequate temperature, generally quite lower than that  
35 of the melting point of the aluminum, and positioned

inside the mold 20, whose upper cavity 21 is previously heated generally at the same temperature of the lamination stack 10, and the lower cavity 22 is previously heated at a lower heating temperature of the upper cavity.

The lamination stack 10 is mounted inside the mold 20 with its longitudinal axis being vertically disposed, and then the mold 20 is rotated around its axis, while the molten aluminum is poured through the inlet channel 23 into the interior of the upper and lower cavities 21, 22 and into the axial channels 12 of the lamination stack 10.

After the cavities 21 and 22 of the mold 20 and the axial channels 12 of the lamination stack have been filled, the aluminum starts its process of solidification from the outside to the inside, while the mold remains rotating.

When the solidification of the aluminum is completed, the mold is immobilized and opened for removing the rotor R from the interior thereof, and so that the core 25 can be drawn from the inside of the lamination stack 10. The injected rotor R comprises the lower ring 32 of the cage 30, the bars already shaped, and an upper plate that covers the widened head 41 of the stamping pin 40, and incorporating the upper axial projection 36, as illustrated in figure 8.

The dimensioning of the head 41 of the stamping pin 40 is made so as to define, with the upper cavity 21 of the mold 20, an annular passage, which is sufficient for the liquid aluminum to flow toward the axial channels 12, but focusing this peripheral region, in which the plate 35 joins the axial projection 36.

This construction allows, when the stamping pin 40 is axially outwardly forced, the upper plate 35 to be ruptured around the peripheral edge of the widened

head 41. Thus, the axial extraction of the stamping pin 40 causes the formation of the central opening of the upper ring 31 of the cage 30, without requiring machining operations for removing large quantities of  
5 aluminum.

In general, only a slight internal machining of the upper ring 31 is required, which is characterized as a chamfering operation to eliminate the barbs originated from the extraction (stamping) of the aluminum during  
10 the extraction of the pin.

It should be understood that the previous heating temperatures of the mold cavities and of the lamination stack can vary, according to other parameters involved in the process, provided that the  
15 heating of the lower cavity is inferior to that imposed to the upper cavity and to the lamination stack.

CLAIMS

1. A process for the injection of an electric motor rotor, said rotor comprising: a lamination stack (10), which is provided with a central axial bore (11) and a plurality of axial channels (12); and a cage (30) of molten metal that is formed by an upper end ring (31) and a lower end ring (32), which are respectively seated against the upper and lower end laminations of the lamination stack (10), and interconnected, in a single piece, by a plurality of bars (33) molten in the axial channels (12), characterized in that it comprises the steps of:
- filling the lower end of the central axial bore (11) with a respective core (25);
  - 15 - mounting, at the upper end portion of the central axial bore (11), a stamping pin (40), which has a widened head (41) seated against the upper end lamination of the lamination stack (10) and presents a circular contour with a diametrical cross section coinciding with the diametrical cross section of the central opening of the upper ring (31) of the cage (30);
  - heating the lamination stack at a first temperature that is lower than the melting temperature of the metal to be injected;
  - 25 - heating, at said first temperature, an upper cavity (21) of a mold (20), to be positioned close to the upper end lamination of the lamination stack (10) and, at a second temperature substantially lower than the first temperature, a lower cavity (22) of the mold (20), to be positioned close to the lower end lamination of the lamination stack (10);
  - 30 - positioning the lamination stack (10), with its vertically disposed longitudinal axis, inside the mold (20);
  - 35

- rotating the mold (20) and pouring the metal to the inside thereof through the inlet channel (23), in order to fill the lower cavity (22), the axial channels (12), and the upper cavity (21);
  - 5 - allowing the metal to solidify, stopping the mold (20) and opening it to remove the rotor and the core (25) from the inside thereof, with the cage (30) already formed and comprising the lower ring (32), the bars (33), and an upper plate (35) that covers the
  - 10 stamping pin (40); and
  - axially extracting the stamping pin (40) in order to break, centrally, the upper plate (35), transforming it in the upper ring (31) of the cage (30).
2. The process, according to claim 1, characterized in
- 15 that it includes the additional step of internally machining the upper ring to the final form.
3. The process, according to any one of the claims 1-2, characterized in that the metal is aluminum and that the first temperature for heating the lamination
- 20 stack (10) and the upper cavity (21) of the mold (20) is much lower than the melting temperature of the aluminum, whereas the second temperature for heating the lower cavity (22) of the mold (20) is much lower than that for heating the upper cavity (21).