CLAIMS

1. A perfluoroelastomer composition comprising:

a perfluoroelastomer;

a peroxide crosslinking agent;

a co-crosslinking agent that is a diolefin compound; and

an organic pigment,

wherein

the diolefin compound is represented by the following formula (1):

$$CH_2=CH-(CF_2)_n-CH=CH_2 \quad (1)$$

where n in the formula (1) is an integer of 4 to 12; and

a content of the organic pigment is greater than or equal to 0.05 parts by weight and less than 2 parts by weight with respect to 100 parts by weight of the perfluoroelastomer.

2. The perfluoroelastomer composition according to claim 1, wherein the perfluoroelastomer does not contain an inorganic filler.

3. A sealing material comprising a crosslinked product of the perfluoroelastomer composition according to claim 1 or 2.