

ABSTRACT

Method for producing mineral-bearing cover layers for floor coverings

The present invention relates to a method for producing cover layers for roads, streets, and other traffic surfaces, wherein a mixture, containing mineral material and a polyurethane reaction mixture, and optionally further additives, is produced, applied to an underlying surface material, compacted using a contact pressure of at least 5 N/cm², and cured, the work being performed substantially without the use of solvents. Furthermore, the present invention relates to cover layers for roads, streets, and other traffic surfaces, obtainable according to such a method.

No suitable figure.