

RECOMBINANT COLLAGEN AND ELASTIN MOLECULES AND USES THEREOF

CROSS-REFERENCE TO RELATED APPLICATIONS AND APPLICATIONS INCORPORATED BY REFERENCE

5 [0001] This application claims priority to U.S. Patent Application No. 16/144,914, filed September 27, 2018, titled, "RECOMBINANT COLLAGEN AND ELASTIN MOLECULES AND USES THEREOF," which claims the benefit under 35 USC 119(e) of U.S. Provisional Patent Application 62/564,964, filed September 28, 2017, 10 and U.S. Provisional Patent Application 62/657,591, filed April 13, 2018, both titled, "RECOMBINANT COLLAGEN AND ELASTIN MOLECULES AND USES THEREOF," the disclosures of which are incorporated by reference herein in their entirety.

FIELD

15 [0002] The present disclosure relates to non-naturally occurring full-length and truncated collagen molecules and full-length and truncated elastin molecules and uses thereof.

BACKGROUND

20 [0003] Collagens and similar proteins are the most abundant proteins in the biosphere. Collagens and elastins are structural proteins found in the skin, connective tissue and bone of animals and other tissues. In humans, the amount of collagen present in the body is approximately one third of the total proteins and accounts for about three fourths of the dry weight of skin. Elastin is a highly elastic protein found in connective tissue and other types of tissue.

25 [0004] The structure of collagen is a triple helix in which three polypeptide strands together form a helical coil. The individual polypeptide strands are composed of repeating triplet amino acid sequences designated as GLY-X-Y. X and Y can be any amino acid and the third amino acid is glycine. The amino acids proline and hydroxyproline are found in high concentrations in collagen. The most common 30 triplet is proline-hydroxyproline-glycine (Gly-Pro-Hyp) accounting for approximately 10.5% of the triplets in collagen.

[0005] Gelatin is a product obtained by partial hydrolysis of collagen. Typically, gelatin is produced by acid hydrolysis, alkaline hydrolysis, and enzymatic hydrolysis

or by exposing collagen to heat in an aqueous solution (e.g., boiling the bones and skins of animal, boiling fish scales, etc.).

[0006] Gelatin is used in many products including cosmetics, foods, pharmaceuticals, medical devices, photographic films, adhesives, binders and many others. The physical and chemical properties of gelatin are tuned to the particular application. These physical/chemical properties include gel strength, melting point temperature, viscosity, color, turbidity, pH, isoelectric point and others.

[0007] Elastin is an elastic protein that is crucial for the proper functioning of arteries, lung, tendons, ligament, skin and other tissue. Elastin provides the tissues with the ability to stretch and return to its original shape. The protein tropoelastin is the building block of elastin. In contrast to collagen that include a family of genes, there is one tropoelastin gene in humans. When expressed, the single elastin gene is spliced to produce different forms of the tropoelastin protein. Many tropoelastin molecules associate together to form elastin.

[0008] L-form bacteria, or L-forms, are bacterial strains derived from parent species (N-forms) that are able to grow as cell wall-deficient (spheroplast type) or as cell wall-less (protoplast type) cells. See, Madoff S (Ed): The Bacterial L-Forms. New York: Marcel Dekker Inc., 1986; Mattmann LH (Ed): Cell Wall Deficient Forms. Boca Raton: CRC Press; 1993; and Gumpert J, Taubeneck U: Characteristic properties and biological significance of stable protoplast type L-forms. In Protoplasts, Lecture Proceedings of the 6th International Protoplast Symposium: Basel. Experientia 1983, 46(suppl):227-241.

[0009] Protoplast type L-forms have been cultivated in the cell wall-less state and represent genetically stable mutants showing extreme pleiotropic changes, including the inability to form cell walls, capsules, flagella, pili, spores and mesosomes, altered colony and cell morphology, qualitative and quantitative changes in the lipid and protein components of the cytoplasmic membrane, the absence of extracellular proteolytic activities, resistance against bacteriophages and the incapability to propagate outside laboratory conditions. See, Gumpert and Taubeneck (supra); and Hoischen et al., Lipid and fatty acid composition of cytoplasmic membranes from *Streptomyces hygroscopicus* and its stable protoplast type L-form. J Bacteriol 1997, 179:3430-3436.

SUMMARY

- [0010] In one aspect, a non-naturally occurring collagen produced by a host cell is provided. The non-naturally occurring collagen is jellyfish (Hydrozoan) collagen, human collagen, *Chondrosia reniformis* (kidney sponge) collagen, or *Rhincodon* 5 *typus* (whale shark) collagen. In an embodiment, the non-naturally occurring collagen is a full-length or a truncated collagen. In one embodiment, the collagen is truncated by an internal truncation of between 50 amino acids and 500 amino acids. In another embodiment, the truncation is at the C-terminal end or the N-terminal end of the collagen polypeptide. The non-naturally occurring collagens are SEQ ID NO: 10, 10 SEQ ID NO: 12, SEQ ID NO: 14, SEQ ID NO: 16, SEQ ID NO: 18, SEQ ID NO: 20, SEQ ID NO: 74, SEQ ID NO: 76, SEQ ID NO: 78, SEQ ID NO: 80, SEQ ID NO: 82, SEQ ID NO: 84, SEQ ID NO: 86, SEQ ID NO: 89, SEQ ID NO: 91, SEQ ID NO: 92, SEQ ID NO: 94, SEQ ID NO: 96, SEQ ID NO: 102, SEQ ID NO: 104, SEQ ID NO: 106, SEQ ID NO: 108, SEQ ID NO: 110, or SEQ ID NO: 112.
- 15 [0011] In another aspect, the non-naturally occurring collagen further comprises amino acid sequences including a secretion tag, a histidine tag, a green fluorescent protein tag, a protease cleavage site, a Beta-lactamase and/or GEK amino acid trimer repeats and/or GDK amino acid trimer repeats. When the non-naturally occurring collagen comprises one or more amino acid trimer repeats of the sequence glycine- 20 glutamic acid-lysine (GEK) and/or glycine-aspartic acid-lysine (GDK), the number of GEK and/or GDK trimer repeats can range from 2 to 50 trimer repeats. In one aspect, the secretion tag is DsbA, PelB, OmpA, TolB, MalE, lpp, TorA, or Hy1A, or a hybrid secretion tag that comprises a portion of one secretion tag fused to a portion of a second secretion tag. An exemplary secretion tag is DsbA.
- 25 [0012] In one aspect, provided are compositions that comprise between 0.005% and 30% w/w non-naturally occurring collagen. The compositions can further comprise at least one additional ingredient comprising a topical carrier or a preservative.
- [0013] Compositions comprising non-naturally occurring collagen are in one aspect topical compositions for applying to skin. The topical compositions are used for 30 decreasing skin damage or promoting the repair of damaged skin.
- [0014] One aspect provides methods for decreasing skin damage or promoting the repair of damaged skin. The method comprises applying the composition comprising elastin to the skin of a subject. The method increases the viability of the fibroblast cells or keratinocytes of the skin of the subject. In another aspect the application of

the composition increases the synthesis of procollagen by the fibroblast cells of the subject's skin. In another aspect the topical application of the composition protects skin or keratinocytes against UV damage. In yet another embodiment, thymine-thymine (TT) dimer formation is decreased by the collagens or elastins disclosed
 5 herein.

[0015] Another aspect provided herein are methods of increasing the viability of skin cells. The method comprises applying collagen or elastin molecules to the skin or skin cell. The collagen or elastin as provided increases the viability of keratinocytes and/or fibroblasts is increased upon exposure to UV radiation, urban
 10 dust or other damaging stimuli.

[0016] In another aspect provided herein are methods for decreasing the production of inflammatory cytokines in a skin cell. In one embodiment the skin cell is a keratinocyte. The method comprises applying a collagen or elastin molecule to a skin cell. The production of inflammatory cytokines including $\text{TNF}\alpha$, IL-1 α , IL-1 β , IL-3, IL-6, IL-7, IL-8, IL-10, IL-18, and IL-1RA.
 15

[0017] In another aspect, provided are methods of protecting skin cells against the effect of exposure to urban dust. The method comprises the step of applying the collagen or elastin disclosed herein to the skin cell. The exposure of skin cell to collagen or elastin increases the viability of the skin cell. In an embodiment, the skin
 20 cell is a keratinocyte or a fibroblast.

[0018] In one aspect, a non-naturally occurring elastin produced by a host cell is provided. The non-naturally occurring elastin is jellyfish elastin, human elastin, *Chondrosia reniformis* (kidney sponge) elastin, or *Rhincodon typus* elastin. In an embodiment, the non-naturally occurring elastin is a full-length or truncated elastin.
 25 In one embodiment, the elastin is truncated by an internal truncation of between 50 amino acids and 500 amino acids. In another embodiment, the truncation is at the C-terminal end or the N-terminal end of the elastin polypeptide. The non-naturally occurring elastins are SEQ ID NO: 31, SEQ ID NO: 33, SEQ ID NO: 35, SEQ ID NO: 37, SEQ ID NO: 39, SEQ ID NO: 41, SEQ ID NO: 43, SEQ ID NO: 45, SEQ ID NO: 47, SEQ ID NO: 49, SEQ ID NO: 51, SEQ ID NO: 53, SEQ ID NO: 55, SEQ ID NO: 57, SEQ ID NO: 59, SEQ ID NO: 61, SEQ ID NO: 63, SEQ ID NO: 65, SEQ ID NO: 67, SEQ ID NO: 69, SEQ ID NO: 71, SEQ ID NO: 98, or SEQ ID NO: 110.
 30

[0019] In another aspect, the non-naturally occurring elastin further comprises amino acid sequences including a secretion tag, a histidine tag, a green fluorescent

protein tag, a protease cleavage site, a Beta-lactamase and/or GEK amino acid trimer repeats and/or GDK amino acid trimer repeats. When the non-naturally occurring collagen comprises one or more amino acid trimer repeats of the sequence glycine-glutamic acid-lysine (GEK) and/or glycine-aspartic acid-lysine (GDK), the number of
5 GEK and/or GDK trimer repeats can range from 2 to 50 trimer repeats. In one aspect, the secretion tag is DsbA, PelB, OmpA, TolB, MalE, lpp, TorA, or Hy1A, or a hybrid secretion tag that comprises a portion of one secretion tag fused to a portion of a second secretion tag. An exemplary secretion tag is DsbA.

[0020] In another embodiment, compositions that comprise between 0.005% and
10 30% w/w non-naturally occurring elastin are provided. The compositions can further comprise at least one additional ingredient comprising a topical carrier or a preservative.

[0021] Compositions comprising non-naturally occurring elastin are in one aspect topical compositions for applying to skin. The topical compositions are used for
15 decreasing skin damage or promoting the repair of damaged skin.

[0022] One embodiment provides methods for decreasing skin damage or promoting the repair of damaged skin. The method comprises applying the composition comprising elastin to the skin of a subject. The method increases the viability of the fibroblast cells of the skin of the subject. In another aspect the
20 application of the composition increases the synthesis of procollagen by the fibroblast cells of the subject's skin. In another aspect the topical application of the compositions protects skin or keratinocytes against UV damage. In yet another embodiment, thymine-thymine (TT) dimer formation is decreased by the collagens or elastins disclosed herein.

[0023] Another embodiment provides polynucleotides that encode a non-naturally occurring collagen or a non-naturally occurring elastin. The polynucleotides encode collagen or elastin from jellyfish, human, *Chondrosia reniformis* (kidney sponge), or *Rhincodon typus*. The encoded collagen or elastin may be full length or truncated. In one embodiment, the collagen or elastin is truncated by an internal truncation of
25 30 between 50 amino acids and 500 amino acids.

[0024] In one embodiment polynucleotides that encode fusion proteins comprising a secretion tag, a histidine tag, a green fluorescent protein tag, a protease cleavage site, a Beta-lactamase along and/or GEK amino acid trimer repeat and/or GDK amino acid trimer repeats together with collagen or elastin are provided. The non-naturally

occurring collagen or elastin may comprise one or more amino acid trimer repeats of the sequence glycine-glutamic acid-lysine (GEK) and/or glycine-aspartic acid-lysine (GDK), the number of GEK and/or GDK trimer repeats can range from 2 to 50 trimer repeats. In one aspect, the secretion tag is DsbA, PelB, OmpA, TolB, MalE, lpp, TorA, or HylA, or a hybrid secretion tag that comprises a portion of one secretion tag fused to a portion of a second secretion tag. An exemplary embodiment secretion tag is DsbA.

[0025] The polynucleotides and vectors can be used to transform host cells and express the polynucleotides. Polynucleotides encoding a non-naturally occurring collagen, wherein the polynucleotide is SEQ ID NO: 9, SEQ ID NO: 11, SEQ ID NO: 13, SEQ ID NO: 15, SEQ ID NO: 17, SEQ ID NO: 19, SEQ ID NO: 73, SEQ ID NO: 75, SEQ ID NO: 77, SEQ ID NO: 79, SEQ ID NO: 81, SEQ ID NO: 83, SEQ ID NO: 85, SEQ ID NO: 90, SEQ ID NO: 93, SEQ ID NO: 95, SEQ ID NO: 97, SEQ ID NO: 103, SEQ ID NO: 105, SEQ ID NO: 107, SEQ ID NO: 109, SEQ ID NO: 111, SEQ ID NO: 113, or SEQ ID NO: 105 are provided. Polynucleotides encoding a non-naturally occurring elastin, wherein the polynucleotide is SEQ ID NO: 34, SEQ ID NO: 36, SEQ ID NO: 38, SEQ ID NO: 40, SEQ ID NO: 42, SEQ ID NO: 44, SEQ ID NO: 46, SEQ ID NO: 48, SEQ ID NO: 50, SEQ ID NO: 52, SEQ ID NO: 54, SEQ ID NO: 56, SEQ ID NO: 58, SEQ ID NO: 60, SEQ ID NO: 62, SEQ ID NO: 64, SEQ ID NO: 66, SEQ ID NO: 68, SEQ ID NO: 70, and SEQ ID NO: 72, SEQ ID NO: 99, or SEQ ID NO: 101 provided.

[0026] Host cells that express the polynucleotides of the invention are disclosed. Host cells can be any host cell including bacterial cells, yeast cells, fungal cells, insect cells, mammalian cells, plant cells and any other cells used to express exogenous polynucleotides.

[0027] Bacterial host cells in which the cells have been modified to inhibit cell division and the periplasmic space is increased are provided. An exemplary host cell is *E. coli*.

[0028] One embodiment provides a method of producing a non-naturally occurring collagen or a non-naturally occurring elastin. The method comprises the steps of inoculating a culture medium with a recombinant host cell comprising polynucleotides that encode the collagen or elastin, cultivating the host cell, and isolating the non-naturally occurring collagen or the non-naturally occurring elastin from the host cell.

BRIEF DESCRIPTION OF THE DRAWINGS

- [0029] Fig. 1 depicts the physiological state difference between switched and unswitched cells. A) Unswitched *Escherichia coli* cells. B) Same *Escherichia coli* population as figure A but has undergone the physiological switch. C) Phase contrast of switched *Escherichia coli* cell containing cytoplasmic RFP and periplasmic GFP. D) Fluorescent imaging of cell in figure C illustrates targeted protein localization.
- [0030] Fig. 2 depicts enhanced protein production in switched cells. A-B) Target protein for T7 inducible protein production is periplasmic expressed GFP, produced in *Escherichia coli* BL21. The same population of cells was used and induced at OD 1.1. A) Protein ladder (lane 1), IPTG induced protein production (lane 2), IPTG induced protein production with physiological switch (lane 3). B) Two vials of the cell GFP induced cultures with IPTG only on left and IPTG+Switch on right. C) Expression of a 22 kDa collagen using switched cells showing protein ladder (lane 1), supernatant after protein production (lane 2), cell pellet (lane 3).
- [0031] Fig. 3 depicts a time-lapse of *Escherichia coli* cell switching over time. Fig. 4 illustrates other organisms undergoing the physiological switch. A) *Agrobacterium tumefaciens* normal physiology. B) *Agrobacterium tumefaciens* switched physiology. C) *Pseudomonas aeruginosa* PAO1 normal physiology. D) *Pseudomonas aeruginosa* PAO1 switched physiology. E) *Brevundimonas diminuta* normal physiology. F) *Brevundimonas diminuta* switched physiology. G) *Agrobacterium tumefaciens* normal physiology. H) *Agrobacterium tumefaciens* switched physiology.
- [0032] Fig. 4 illustrates other organisms undergoing the physiological switch. A) *Agrobacterium tumefaciens* normal physiology. B) *Agrobacterium tumefaciens* switched physiology. C) *Pseudomonas aeruginosa* PAO1 normal physiology. D) *Pseudomonas aeruginosa* PAO1 switched physiology. E) *Brevundimonas diminuta* normal physiology. F) *Brevundimonas diminuta* switched physiology. G) *Agrobacterium tumefaciens* normal physiology. H) *Agrobacterium tumefaciens* switched physiology.
- [0033] Fig. 5 illustrates the reduction in TT dimer formation by treatment of human keratinocytes with truncated collagen.

DESCRIPTION

[0034] In the following description, certain specific details are set forth in order to provide a thorough understanding of various embodiments of the disclosure.

However, one skilled in the art will understand that the disclosure may be practiced
5 without these details.

[0035] As used herein the term “about” refers to $\pm 10\%$.

[0036] The term “consisting of” means “including and limited to”.

[0037] The term “consisting essentially of” means that the composition, method or structure may include additional ingredients, steps and/or parts, but only if the
10 additional ingredients, steps and/or parts do not materially alter the basic and novel characteristics of the claimed composition, method or structure.

[0038] As used herein, the singular form “a”, “an” and “the” include plural references unless the context clearly dictates otherwise. For example, the term “a compound” or “at least one compound” may include a plurality of compounds,
15 including mixtures thereof.

[0039] Throughout this application, various embodiments of this disclosure may be presented in a range format. It should be understood that the description in range format is merely for convenience and brevity and should not be construed as an inflexible limitation on the scope of the disclosure. Accordingly, the description of a
20 range should be considered to have specifically disclosed all the possible subranges as well as individual numerical values within that range. For example, description of a range such as from 1 to 6 should be considered to have specifically disclosed subranges such as from 1 to 3, from 1 to 4, from 1 to 5, from 2 to 4, from 2 to 6, from 3 to 6 etc., as well as individual numbers within that range, for example, 1, 2, 3, 4, 5,
25 and 6. This applies regardless of the breadth of the range.

[0040] Whenever a numerical range is indicated herein, it is meant to include any cited numeral (fractional or integral) within the indicated range. The phrases “ranging/ranges between” a first indicate number and a second indicate number and “ranging/ranges from” a first indicate number “to” a second indicate number are used
30 herein interchangeably and are meant to include the first and second indicated numbers and all the fractional and integral numerals there between.

[0041] As used herein the term “method” refers to manners, means, techniques and procedures for accomplishing a given task including, but not limited to, those manners, means, techniques and procedures either known to, or readily developed

from known manners, means, techniques and procedures by practitioners of the chemical, pharmacological, biological, biochemical and medical arts.

[0042] The term “collagen” or “collagen-like” as used herein refers to a monomeric polypeptide that can associate with one or more collagen or collagen-like polypeptides to form a quaternary structure. Collagen can be treated with acid, base or heat to prepare gelatin. The quaternary structure of natural collagen is a triple helix typically composed of three polypeptides. Of the three polypeptides that form natural collagen, two are usually identical and are designated as the alpha chain. The third polypeptide is designated as the beta chain. Thus a typical natural collagen can be designated as AAB, wherein the collagen is composed of two alpha (“A”) strands and one beta (“B”) strand. The term “procollagen” as used herein refers to polypeptides produced by cells that can be processed to naturally occurring collagen.

[0043] The terms “elastin” as used herein refers to a polypeptide that is elastic and functions to stretch or contract and return to its original shape. Elastin is found naturally in connective tissue.

[0044] The term “expression vector” or “vector” as used herein refers to a nucleic acid assembly which is capable of directing the expression of the exogenous gene. The expression vector may include a promoter which is operably linked to the exogenous gene, restriction endonuclease sites, nucleic acids that encode one or more selection markers, and other nucleic acids useful in the practice of recombinant technologies.

[0045] The term “fibroblast” as used herein refers to a cell that synthesizes procollagen and other structural proteins. Fibroblasts are widely distributed in the body and found in skin, connective tissue and other tissues.

[0046] The term “fluorescent protein” is a protein that is commonly used in genetic engineering technologies used as a reporter of expression of an exogenous polynucleotide. The protein when exposed to ultraviolet or blue light fluoresces and emits a bright visible light. Proteins that emit green light is green fluorescent protein (GFP) and proteins that emit red light is red fluorescent protein (RFP).

[0047] The term “gelatin” as used herein refers to collagen that has been further processed by exposure to acid, base or heat. While not wishing to be bound by theory or mechanism, treatment of collagen with acid, base or heat is thought to denature the collagen polypeptides. Aqueous denatured collagen solutions form reversible gels

used in foods, cosmetics, pharmaceuticals, industrial products, medical products, laboratory culture growth media, and many other applications.

[0048] The term “gene” as used herein refers to a polynucleotide that encodes a specific protein, and which may refer to the coding region alone or may include
5 regulatory sequences preceding (5’ non-coding sequences) and following (3’ non-coding sequences) the coding sequence.

[0049] The term “histidine tag” is a 2-30 contiguous series of histidine residues on a recombinant polypeptide.

[0050] The term “host cell” is a cell that is engineered to express an introduced
10 exogenous polynucleotide.

[0051] The term “keratinocyte” is a cell that produces keratins found in the epidermal layer of the skin.

[0052] The term “lactamase” as used herein refer to enzymes that hydrolyze antibiotics that contain a lactam (cyclic amide) moiety. “Beta-lactamase” or “β-lactamase” are enzymes that hydrolyze antibiotics that contain a β-lactam moiety.
15

[0053] The term “non-naturally occurring” as used herein refers to collagen or elastin that is not normally found in nature. The non-naturally occurring collagen or elastin are recombinantly prepared. The non-naturally occurring collagen is a recombinant collagen or recombinant elastin. The non-naturally occurring collagen
20 is in one embodiment a truncated collagen. Other non-naturally occurring collagen polypeptides include chimeric collagens. A chimeric collagen is a polypeptide wherein one portion of a collagen polypeptide is contiguous with a portion of a second collagen polypeptide. For example, a collagen molecule comprising a portion of a jellyfish collagen contiguous with a portion of a human collagen is a chimeric
25 collagen. In another embodiment, the non-naturally occurring collagen comprises a fusion polypeptide that includes additional amino acids such as a secretion tag, histidine tag, green fluorescent protein, protease cleavage site, GEK repeats, GDK repeats, and/or beta-lactamase. The non-naturally occurring elastin in one embodiment a truncated elastin. Other non-naturally occurring elastin polypeptides
30 include chimeric elastins. A chimeric elastin is a polypeptide wherein one portion of an elastin polypeptide is contiguous with a portion of a second elastin polypeptide. For example, a collagen molecule comprising a portion of a jellyfish elastin contiguous with a portion of a human elastin is a chimeric elastin. In another embodiment, the non-naturally occurring elastin comprises a fusion polypeptide that

includes additional amino acids such as a secretion tag, histidine tag, green fluorescent protein, protease cleavage site and/or beta-lactamase. The chimeric gelatin or the chimeric elastin can comprise additional amino acids such as a secretion tag, histidine tag, green fluorescent protein, protease cleavage site, GEK repeats,

5 GDK repeats, and/or beta-lactamase.

[0054] The term “protease cleavage site” is an amino acid sequence that is cleaved by a specific protease.

[0055] The term “secretion tag” or “signal peptide” refers to an amino acid sequence that recruits the host cell’s cellular machinery to transport an expressed protein to a particular location or cellular organelle of the host cell.

10 **[0056]** The term “truncated collagen” refers to a monomeric polypeptide that is smaller than a full-length collagen wherein one or more portions of the full-length collagen is not present. Collagen polypeptides are truncated at the C-terminal end, the N-terminal end, or truncated by removal of internal portion(s) of the full-length collagen polypeptide.

15 **[0057]** The term “truncated elastin” refers to a monomeric polypeptide that is smaller than a full-length elastin wherein one or more portions of the full-length elastin is not present. Elastin polypeptides are truncated at the C-terminal end, the N-terminal end, or truncated by removal of internal portion(s) of the full-length elastin polypeptide.

20 **[0058]** In co-owned application PCT/US17/24857, incorporated by reference, an expression system that uses modified bacterial cells (switched cells) in which cell division is inhibited and growth of the periplasmic space is greatly enhanced was disclosed. In this expression system, the expressed proteins are targeted to the periplasmic space. Recombinant protein production in these switched cells is dramatically increased compared with that in non-switched cells. Structurally, the cells comprise both inner and outer membranes but lack a functional peptidoglycan cell wall, while the cell shape is spherical and increases in volume over time. Notably, while the periplasmic space normally comprises only 10-20% of the total cell volume, 25 the periplasmic compartment of the switched state described herein can comprise more than 20%, 30%, 40% or 50% and up to 60%, 70%, 80% or 90% of the total cell volume.

30 **[0059]** The modified bacterial cells of PCT/US17/24857 are derived from Gram-negative bacteria, e.g. selected from: gammaproteobacteria and alphaproteobacteria.

In some embodiments, the bacterium is selected from: *Escherichia coli*, *Vibrio natriegens*, *Pseudomonas fluorescens*, *Caulobacter crescentus*, *Agrobacterium tumefaciens*, and *Brevundimonas diminuta*. In specific embodiments, the bacterium is *Escherichia coli*, e.g. strain BL21(DE3).

5 **[0060]** In another aspect, the host bacterial cells have an enlarged periplasmic space in a culture medium comprising a magnesium salt, wherein the concentration of magnesium ions in the medium is at least about 3, 4, 5 or 6 mM. In further embodiments, the concentration of magnesium ions in the medium is at least about 7, 8, 9 or 10 mM. In some embodiments, the concentration of magnesium ions in the
10 medium is between about 5 mM and 25 mM, between about 6 mM and/or about 20, 15 or 10 mM. In some embodiments, the magnesium salt is selected from: magnesium sulfate and magnesium chloride.

[0061] In other embodiments, the culture medium further comprises an osmotic stabilizer, including, e.g. sugars (e.g., arabinose, glucose, sucrose, glycerol, sorbitol,
15 mannitol, fructose, galactose, saccharose, maltotriose, erythritol, ribitol, pentaerythritol, arabitol, galactitol, xylitol, iditol, maltotriose, and the like), betaines (e.g., trimethylglycine), proline, sodium chloride, wherein the concentration of the osmotic stabilizer in the medium is at least about 4%, 5%, 6%, or 7% (w/v). In further embodiments, the concentration of osmotic stabilizer is at least about 8%, 9%,
20 or 10% (w/v). In some embodiments, the concentration of the osmotic stabilizer in the medium is between about 5% to about 20% (w/v).

[0062] In some embodiments, the cell culture may further comprise ammonium chloride, ammonium sulfate, calcium chloride, amino acids, iron(II) sulfate, magnesium sulfate, peptone, potassium phosphate, sodium chloride, sodium
25 phosphate, and yeast extract.

[0063] The host bacterial cell may be cultured continuously or discontinuously; in a batch process, a fed-batch process or a repeated fed-batch process.

[0064] In some embodiments, the antibiotic is selected from: β -lactam antibiotics (e.g. penicillins, cephalosporins, carbapenems, and monobactams), phosphonic acid
30 antibiotics, polypeptide antibiotics, and glycopeptide antibiotics. In particular embodiments, the antibiotic is selected from alafosfalin, amoxicillin, ampicillin, aztreonam, bacitracin, carbenicillin, cefamandole, cefotaxime, cefsulodin, cephalothin, fosmidomycin, methicillin, nafcillin, oxacillin, penicillin G, penicillin V, fosfomycin, primaxin, and vancomycin.

[0065] Without being bound by theory, the cell morphology that promotes recombinant protein production and inhibits cell division appears to be driven by the removal of the cell wall under the media conditions stated above. In some embodiments, the methods for removal/inhibition of cell wall synthesis can be
5 through the use of antibiotics that inhibit peptidoglycan synthesis (such as ampicillin, carbenicillin, penicillins or fosfomycin), or other methods known in the art.

[0066] When having an appropriate periplasmic targeting signal sequence, recombinantly produced polypeptides can be secreted into the periplasmic space of bacterial cells. Joly, J.C. and Laird, M.W., in *The Periplasm* ed. Ehrmann, M., ASM
10 Press, Washington D.C., (2007) 345-360. In the chemically oxidizing environment of the periplasm the formation of disulfide bonds and thereby the functionally correct folding of polypeptides is favored.

[0067] In general, the signal sequence may be a component of the expression vector, or it may be a part of the exogenous gene that is inserted into the vector. The
15 signal sequence selected should be one that is recognized and processed (i.e., cleaved by a signal peptidase) by the host cell. For bacterial host cells that do not recognize and process the native signal sequence of the exogenous gene, the signal sequence is substituted by any commonly known bacterial signal sequence. In some
20 embodiments, recombinantly produced polypeptides can be targeted to the periplasmic space using the DsbA signal sequence. Dinh and Bernhardt, *J Bacteriol*, Sept. 2011, 4984-4987.

[0068] In one aspect, a non-naturally occurring collagen or elastin is produced by a host cell is provided. The non-naturally occurring collagen or elastin is jellyfish collagen or elastin, t, human collagen or elastin, or *Chondrosia reniformis* (kidney
25 sponge) collagen or elastin, or *Rhincodon typus* collagen or elastin. The non-naturally occurring collagen or elastin is a truncated collagen. The truncation is an internal truncation, a truncation at the N-terminal portion of the collagen or elastin, or a truncation at the C-terminal portion of the collagen or elastin. The collagen or elastin is truncated by a truncation of between 50 amino acids and 1000 amino acids,
30 between, 50 amino acids and 950 amino acids, between 50 amino acids and 900 amino acids, between 50 amino acids and 850 amino acids, between 50 amino acids and 800 amino acids, between 50 amino acids and 850 amino acids, between 50 amino acids and 800 amino acids, between 50 amino acids and 750 amino acids, between 50 amino acids and 700 amino acids, between 50 amino acids and 650 amino

acids, between 50 amino acids and 600 amino acids, between 50 amino acids and 650 amino acids, between 50 amino acids and 500 amino acids, between 50 amino acids and 450 amino acids, between 50 amino acids and 400 amino acids, between 50 amino acids and 350 amino acids, between 50 amino acids and 300 amino acids, between 50 amino acids and 250 amino acids, between 50 amino acids and 200 amino acids, between 50 amino acids and 150 amino acids, or between 50 amino acids and 100 amino acids. In another embodiment, the collagen or elastin is truncated by 50, 60, 70, 80, 90, 100, 110, 120, 130, 140, 150, 160, 170, 180, 190, 200, 210, 220, 230, 240, 250, 260, 270, 280, 290, 300, 310, 320, 330, 340, 350, 360, 370, 380, 390, 400, 410, 420, 430, 440, 450, 460, 470, 480, 490, 500, 510, 520, 530, 540, 550, 560, 570, 580, 590, 600, 650, 700, 750, 800, 850, 900, 950, or 1000 amino acids. The non-naturally occurring collagen or elastin are encoded by a portion of a polynucleotide sequence or the entire polynucleotide sequence disclosed herein.

[0069] The non-naturally occurring collagen or elastin further comprises amino acid sequences including a secretion tag. The secretion tag directs the collagen or elastin to the periplasmic space of the host cell. In particular embodiments, the signal peptide is derived from DsbA, PelB, OmpA, TolB, MalE, lpp, TorA, or Hy1A, or a hybrid secretion tag that comprises a portion of one secretion tag fused to a portion of a second secretion tag. In one aspect the secretion tag is attached to the non-naturally occurring collagen or elastin. In another aspect the secretion tag is cleaved from the non-naturally occurring collagen or elastin.

[0070] The non-naturally occurring collagen or the non-naturally occurring elastin further comprises a histidine tag. The histidine tag or polyhistidine tag is a sequence of 2 to 20 histidine residues that are attached to the collagen or elastin. The histidine tag comprises 2 to 20 histidine residues, 5 to 15 histidine residues, 5 to 18 histidine residues, 5 to 16 histidine residues, 5 to 15 histidine residues, 5 to 14 histidine residues, 5 to 13 histidine residues, 5 to 12 histidine residues, 5 to 11, 5 to 10 histidine residues, 6 to 12 histidine residues, 6 to 11 histidine residues, or 7 to 10 histidine residues. The histidine tags are useful in purification of proteins by chromatographic methods utilizing nickel based chromatographic media. Exemplary fluorescent proteins include green fluorescent protein (GFP) or red fluorescent protein (RFP). Fluorescent proteins are well known in the art. In one embodiment the non-naturally occurring collagen or the on-naturally occurring elastin comprises a GFP and/or RFP. In one embodiment a superfolder GFP is fused to the on-naturally occurring collagen

or elastin. The superfolder GFP is a GFP that folds properly even when fused to a poorly folded polypeptide. In one aspect the histidine tag is attached to the non-naturally occurring collagen or elastin. In another aspect the histidine tag is cleaved from the non-naturally occurring collagen or elastin.

- 5 **[0071]** The non-naturally occurring collagen or non-naturally occurring elastin further comprises a protease cleavage site. The protease cleavage site is useful to cleave the recombinantly produced collagen or elastin to remove portions of the polypeptide. The portions of the polypeptide that may be removed include the secretion tag, the histidine tag, the fluorescent protein tag and/or the Beta-lactamase.
- 10 The proteases comprise endoproteases, exoproteases, serine proteases, cysteine proteases, threonine proteases, aspartic proteases, glutamic proteases, and metalloproteases. Exemplary protease cleavage sites include amino acids that are cleaved by Thrombin, TEV protease, Factor Xa, Enteropeptidase, and Rhinovirus 3C
- 15 Protease. In one aspect the cleavage tag is attached to the non-naturally occurring collagen or elastin. In another aspect the cleavage tag is removed by an appropriate protease from the non-naturally occurring collagen or elastin.
- 20 **[0072]** The non-naturally occurring collagen or non-naturally occurring elastin further comprises an enzyme that is a Beta-lactamase. The beta-lactamase is useful as a selection marker. In one aspect the beta-lactamase is attached to the non-naturally
- 25 occurring collagen or elastin. In another aspect the beta-lactamase is cleaved from the non-naturally occurring collagen or elastin.
- 30 **[0073]** The non-naturally occurring collagen or non-naturally occurring elastin further comprises GEK amino acid trimer repeats and/or GDK amino acid trimer repeats. The GEK and the GDK trimer repeats facilitate the gelling of the collagen and/or the gelatin. In one embodiment, the non-naturally occurring collagen or the non-naturally occurring elastin comprises 2-50 GEK and/or 2-50 GDK trimer repeats, 2-40 GEK and/or 2-40 GDK trimer repeats, 2-30 GEK and/or 2-30 GDK trimer repeats, 2-20 GEK and/or 2-20 GDK trimer repeats, 2-15 GEK and/or 2-15 GDK trimer repeats, 2-10 GEK and/or 2-10 GDK trimer repeats, 2-9 GEK and/or 2-9 GDK trimer repeats, 2-8 GEK and/or 2-8 GDK trimer repeats, 2-7 GEK and/or 2-7 GDK trimer repeats, 2-6 GEK and/or 2-6 GDK trimer repeats, 2-5 GEK and/or 2-5 GDK trimer repeats, or 2-4 GEK and/or 2-4 GDK trimer repeats. In one aspect the GEK trimer repeat or the GDK trimer repeat is attached to the non-naturally occurring

collagen or elastin. In another aspect the GEK trimer repeat or the GDK trimer repeat is cleaved from the non-naturally occurring collagen or elastin.

[0074] Provided herein are compositions that comprise between 0.005% and 30% w/w non-naturally occurring collagen and/ or non-naturally occurring elastin. The composition comprises between 0.005% and 20% w/w non-naturally occurring collagen and/ or non-naturally occurring elastin, between 0.005% and 10% w/w non-naturally occurring collagen and/ or non-naturally occurring elastin, between 0.005% and 5% w/w non-naturally occurring collagen and/ or non-naturally occurring elastin, between 0.005% and 2% w/w non-naturally occurring collagen and/ or non-naturally occurring elastin, between 0.005% and 1% w/w non-naturally occurring collagen and/ or non-naturally occurring elastin, between 0.005% and 0.5% w/w non-naturally occurring collagen and/ or non-naturally occurring elastin, and between 0.005% and 0.2% w/w non-naturally occurring collagen and/ or non-naturally occurring elastin.

[0075] The compositions that comprise the between non-naturally occurring collagen and/or non-naturally occurring elastin are personal care products. In some embodiments the compositions are formulated for topical administration. The compositions can contain other cosmetic ingredients suitable for human use. The personal care products are useful for preventing or treating ultraviolet radiation damage to human skin or hair. The personal care products are applied to skin or hair. The compositions include, for example, masks, skin cleaners such as soap, cleansing creams, cleansing lotions, cleansing milks, cleansing pads, facial washes, hair shampoo, hair conditioner and body shampoos.

[0076] The compositions that comprise the non-naturally occurring collagen and/ or non-naturally occurring elastin can further comprise at least one additional ingredient comprising a topical carrier or a preservative. The topical carrier comprises a topical carrier selected from the group consisting of liposome, biodegradable microcapsule, lotion, spray, aerosol, dusting powder, biodegradable polymer, mineral oil, triglyceride oil, silicone oil, glycerin, glycerin monostearate, alcohols, emulsifying agents, liquid petroleum, white petrolatum, propylene glycol, polyoxyethylene, polyoxypropylene, wax, sorbitan monostearate, polysorbate, cetyl ester wax, cetearyl alcohol, 2-octyldodecanol, benzyl alcohol, cyclomethicone, cyclopentasiloxane, and water. The preservative comprises a preservative selected from the group consisting of tocopherol, diiodomethyl-p-tolylsulfone, 2-Bromo-2-nitropropane-1,3-diol, cis isomer 1-(3-chloroallyl)-3,5,7-triaza-1-azoniaadamantane chloride, glutaraldehyde,

4,4-dimethyl oxazolidine, 7-Ethylbicyclooxazolidine, methyl paraben, sorbic acid, Germaben II, rosemary extract, and EDTA

[0077] Provided are methods of decreasing skin damage, promoting the repair of damaged skin, protecting skin against UV damage, protecting skin cells against the effects of exposure to urban dust.. The method comprises the step of applying the composition comprising the non-naturally occurring collagen and/ or non-naturally occurring elastin to the skin of a subject. Without being bound to a particular theory or mechanism, the collagen and/or the elastin in the composition decrease skin damage by protecting against UV damage, and/or promotes the repair of damaged skin by increasing the viability of cells and/or increasing procollagen synthesis when applied to skin, and/or promotes the viability of skin cells. The collagens and elastins in one aspect decrease the formation of thymine-thymine (TT) dimer formation.

[0078] One aspect provides polynucleotides that encode a non-naturally occurring collagen or a non-naturally occurring elastin. The polynucleotides encode collagen or elastin from jellyfish, human, *Chondrosia reniformis* (kidney sponge), or *Rhincodon typus*. The polynucleotides encode for collagen or elastin that is full length or truncated.

[0079] Another aspect provides polynucleotides that encode collagen or elastin fusion proteins. The elastin or collagen fusion proteins comprise a secretion tag, a histidine tag, a fluorescent protein tag, a protease cleavage site, a Beta-lactamase along and/or GEK amino acid trimer repeats and/or GDK amino acid trimer repeats together with collagen or elastin.

[0080] The polynucleotides are in one aspect vectors used to transform host cells and express the polynucleotides. The polynucleotides further comprise nucleic acids that encode enzymes that permit the host organism to grow in the presence of a selection agent. The selection agents include certain sugars including galactose containing sugars or antibiotics including ampicillin, hygromycin, G418 and others. Enzymes that are used to confer resistance to the selection agent include β -galactosidase or a β -lactamase.

[0081] In one aspect host cells that express the polynucleotides of the invention are provided. Host cells can be any host cell including gram negative bacterial cells, gram positive bacterial cells, yeast cells, insect cells, mammalian cells, plant cells or any other cells used to express exogenous polynucleotides. An exemplary gram-negative host cell is *E. coli*.

[0082] Bacterial host cells in which the cells have been modified to inhibit cell division and the periplasmic space is increased are taught. As discussed herein and taught in example 1, Beta-lactam antibiotics are useful as a switch to convert wild-type bacterial cells to a modified bacterial cell in which cell replication is inhibited
5 and the periplasmic space is increased. Exemplary Beta-lactam antibiotics including penicillins, cephalosporins, carbapenems, and monobactams.

[0083] The switched form of bacteria (L-form) are cultivated in culture media that include certain salts and other nutrients. Salts and media compositions that support the physiological switch physiology that have been tested are M63 salt media, M9 salt
10 media, PYE media, and Luria-Bertani (LB) media. Any necessary supplements besides carbon, nitrogen, and inorganic phosphate sources may also be included at appropriate concentrations introduced alone or as a mixture with another supplement or medium such as a complex nitrogen source. In certain embodiments, the medium further comprises one or more ingredients selected from: ammonium chloride,
15 ammonium sulfate, calcium chloride, casamino acids, iron(II) sulfate, magnesium sulfate, peptone, potassium phosphate, sodium chloride, sodium phosphate, and yeast extract.

[0084] Beta-lactamases are enzymes that confer resistance to lactam antibiotics in prokaryotic cells. Typically when Beta-lactamases are expressed in bacterial host
20 cells, the expressed Beta-lactamase protein also includes targeting sequences (secretion tag) that direct the Beta-lactamase protein to the periplasmic space. Beta-lactamases are not functional unless they are transported to the periplasmic space. Beta-lactamase targeted to the periplasmic without the use of an independent secretion tag that targets the enzyme to the periplasmic space are provided. By
25 creating a fusion protein in which a periplasmic secretion tag added to the N-terminus of a protein such as GFP, collagen, or GFP/collagen chimeras, the functionality of the Beta-lactamase lacking a native secretion tag can be used to select for full translation and secretion of the N-terminal fusion proteins. Using this approach, we have used a DsbA-GFP-Collagen-Beta-lactamase fusion to select for truncation products in the
30 target collagens that favor translation and secretion.

[0085] Another embodiment provides methods of producing a non-naturally occurring collagen or a non-naturally occurring elastin. The method comprises the steps of inoculating a culture medium with a recombinant host cell comprising polynucleotides that encode the collagen or elastin, cultivating the host cell, and

isolating the non-naturally occurring collagen or the non-naturally occurring elastin from the host cell.

[0086] A process for fermentative preparation of a protein is provided. The process comprises the steps of:

- 5 a) culturing a recombinant Gram-negative bacterial cell in a medium comprising a magnesium salt, wherein the concentration of magnesium ions in the medium is at least about 6 mM, and wherein the bacterial cell comprises an exogenous gene encoding the protein;
- b) adding an antibiotic to the medium, wherein the antibiotic inhibits
10 peptidoglycan biogenesis in the bacterial cell; and
- c) harvesting the protein from the medium.

[0087] The bacteria may be cultured continuously—as described, for example, in WO 05/021772—or discontinuously in a batch process (batch cultivation) or in a fed-batch or repeated fed-batch process for the purpose of producing the target protein. In
15 some embodiments, protein production is conducted on a large-scale. Various large-scale fermentation procedures are available for production of recombinant proteins. Large-scale fermentations have at least 1,000 liters of capacity, preferably about 1,000 to 100,000 liters of capacity. These fermentors use agitator impellers to distribute oxygen and nutrients, especially glucose (the preferred carbon/energy source). Small-
20 scale fermentation refers generally to fermentation in a fermentor that is no more than approximately 20 liters in volumetric capacity.

[0088] For accumulation of the target protein, the host cell is cultured under conditions sufficient for accumulation of the target protein. Such conditions include, e.g., temperature, nutrient, and cell-density conditions that permit protein expression
25 and accumulation by the cell. Moreover, such conditions are those under which the cell can perform basic cellular functions of transcription, translation, and passage of proteins from one cellular compartment to another for the secreted proteins, as are known to those skilled in the art.

[0089] The bacterial cells are cultured at suitable temperatures. For *E. coli* growth,
30 for example, the typical temperature ranges from about 20 °C to about 39 °C. In one embodiment, the temperature is from about 20° C to about 37° C. In another embodiment, the temperature is at about 30 °C. In one embodiment, the host cells, in the non-switched state or switched state are cultivated at one temperature and switched to a different temperature to induce protein production. The host cells are

cultivated first at one temperature to propagate the cells, then to induce protein production the cell are cultivated at a lower temperature. The first temperature is 23°, 24°, 25°, 26°, 27°, 28°, 29°, 30°, 31°, 32°, 33°, 34°, 35°, 36°, or 37° C. The second temperature is 20°, 21°, 22°, 23°, 24°, 25°, 26°, 27°, 28°, 29°, 30°, 31°, 32°, 33°, 34°, 5 35° or 36° C. The cultivation at the second temperature is conducted between 1 hour and 100 hours, between 5 hours and 90 hours, between 5 hours and 80 hours, between 5 hours and 80 hours, between 5 hours and 70 hours, between 10 hours and 70 hours, between 15 hours and 70 hours, between 15 hours and 65 hours, between 15 hours and 60 hours, between 20 hours and 60 hours, between 20 hours and 55 hours, 10 between 20 hours and 50 hours, between 24 hours and 50 hours, between 24 hours and 48 hours, between 30 hours and 50 hours, between 30 hours and 45 hours, or between 30 hours and 40 hours.

[0090] The pH of the culture medium may be any pH from about 5-9, depending mainly on the host organism. For *E. coli*, the pH is from about 6.8 to about 7.4, or 15 about 7.0.

[0091] For induction of gene expression, typically the cells are cultured until a certain optical density is achieved, e.g., an OD600 of about 1.1, at which point induction is initiated (e.g., by addition of an inducer, by depletion of a repressor, suppressor, or medium component, etc.) to induce expression of the exogenous gene 20 encoding the target protein. In some embodiments, expression of the exogenous gene is inducible by an inducer selected from, e.g. isopropyl- β -d-1-thiogalactopyranoside, lactose, arabinose, maltose, tetracycline, anhydrotetracycline, vavlycin, xylose, copper, zinc, and the like. The induction of gene expression can also be accomplished by decreasing the dissolved oxygen levels during fermentation. The dissolved oxygen 25 levels of the fermentation during cell propagation is between 10% and 30%. To induce gene expression the dissolved oxygen level is reduced to below 10%, 9%, 8%, 7%, 6%, 5%, 4%, 3%, 2%, 1%, or 0%. In host cells, in either the physiological state or the switched state, protein production can be induced by lowering the temperature of the fermentation as disclosed herein.

30 [0092] After product accumulation, the cells are vortexed and centrifuged in order to induce lysis and release of recombinant proteins. The majority of the proteins is found in the supernatant but any remaining membrane bound proteins can be released using detergents (such as triton X-100).

[0093] In a subsequent step, the target protein, as a soluble or insoluble product released from the cellular matrix, is recovered in a manner that minimizes co-recovery of cellular debris with the product. The recovery may be done by any means, but in one embodiment, can comprise histidine tag purification through a nickel column.

- 5 See, e.g., Purification of Proteins Using Polyhistidine Affinity Tags, Methods Enzymology. 2000 ; 326: 245–254.

Examples

Example 1: Expression System

Materials and methods:

- 10 **Strains:**

[0094] Tested physiological switch and protein production:

E. coli BL21(DE3)- From NEB, product #c2527

E. coli K12 NCM3722- From The Coli Genetic Stock Center, CGSC# 12355

[0095] Tested physiological switch:

- 15 **Gamma**proteobacteria:

Vibrio natriegens - From ATCC, product #14048

Pseudomonas fluorescens - From ATCC, product # 31948

Pseudomonas aeruginosa PAO1- From ATCC, product # BAA-47

[0096] Alphaproteobacteria:

- 20 *Caulobacter crescentus* - From ATCC, product #19089

Agrobacterium tumefaciens/Rhizobium radiobacter - From ATCC, product #33970

Brevundimonas diminuta - From ATCC, product #13184

Media compositions:

[0097] 1 liter 5x m63 salts:

- 25 10 g (NH₄)₂SO₄ – From P212121, product #7783-20-2

68 g KH₂PO₄ – From P212121, product #7778-77-0

2.5 mg FeSO₄·7H₂O – From Sigma Aldrich, product #F7002

Bring volume up to 1 liter with milliQ water

Adjust to pH 7 with KOH (From P212121, product #1310-58-3)

- 30 Autoclave mixture

[0098] 1 liter of 1M MgSO₄:

246.5 g MgSO₄·7H₂O – From P212121, (Sigma Aldrich, product #10034-99-8)

Bring volume up to 1 liter with milliQ water.

Autoclave mixture.

[0099] 1 liter of switch media 1:

133.4 mL 5X m63 salts

10 mL 1M MgSO₄

5 38.6 g Glucose – From P212121, product #50-99-7

66.6 g Sucrose – From P212121, product #57-50-1

8.33 g LB mix – From P212121, product #lb-miller

Bring volume up to 1 liter with milliQ water.

Filter sterilize mixture through a 0.22 µm pore vacuum filter (Sigma Aldrich, product

10 #CLS430517).

[0100] 1 liter of switch media 2:

133.4 mL 5X m63 salts

10 mL 1M MgSO₄

38.6 g Glucose – From P212121, product #50-99-7

15 66.6 g Sucrose – From P212121, product #57-50-1

10 g Yeast Extract – From FisherSci.com, product #J60287A1

Bring volume up to 1 liter with milliQ water.

Filter sterilize mixture through a 0.22 µm pore vacuum filter (Sigma Aldrich, product #CLS430517).

20 **[0101] For Bioreactor growth:**

5 liter of bioreactor media MGZ12:

1) Autoclave 1L of Glucose at concentration of 500g/L in DI water. (VWR, product #97061-170).

25 2) Autoclave 1L of Sucrose at concentration of 500g/L in DI water. (Geneseesci.com, product #62-112).

3) Autoclave in 3946mL of DI water:

20 g (NH₄)₂HPO₄. (VWR, product # 97061-932).

66.5 g KH₂PO₄. (VWR, product # 97062-348).

22.5 g H₃C₆H₅O₇. (VWR, product #BDH9228-2.5KG).

30 2.95 g MgSO₄·7H₂O. (VWR, product # 97062-134).

10 mL Trace Metals (Teknova), 1000x. (Teknova, product #T1001).

After autoclaving add 400 mL of (1) to (3), 65 mL of 10M NaOH (VWR, product #97064-480) to (3), and 666 mL of (2) to (3).

A feed of 500g/L of glucose can be used during fermentation run as needed.

At induction add:

50mL of 1M MgSO₄·7H₂O to a 5 L bioreactor

1 to 10mM concentration of IPTG. (carbosynth.com, product # EI05931).

Add Fosfomycin (50 µg/mL or higher) and Carbenicillin (100 µg/mL or higher).

5 **Physiological switch:**

[0102] The physiological switch is optimally flipped at an OD 600 of 1 to 1.1 for *E. coli* for growth in shake flasks at volumes up to 1L. For the other species tested, cultures were grown in switch media and subcultured once cultures reached maximal OD 600. In all cases the physiological switch is flipped through the addition of 100-
10 200ug/mL Carbenicillin (From P212121, product #4800-94-6) and 50-100ug/mL Fosfomycin (From P212121, product #26016-99-9). The majority of the population is in the switched state within a few hours. To confirm that cells underwent a physiological switch, cells were imaged on a Nikon Ti-E with perfect focus system, Nikon CFI60 Plan Apo 100X NA 1.45 objective, Prior automated filter wheels and
15 stage, LED-CFP/YFP/mCherry and LED-DA/FI/TX filter sets (Semrock), a Lumencor Sola II SE LED illumination system, and a Hamamatsu Flash 4.0 V2 CMOS camera.

Image analysis of physiological switch:

[0103] Images were analyzed using ImageJ to measure dimensions. In the switched
20 state, the spherical outline of the outer membrane is treated as a sphere to calculate total volume ($V = (4/3)\pi r^3$). The cytoplasmic volume is calculated as an ellipsoid that exists within the sphere ($V = (4/3)\pi * (\text{longest radius}) * (\text{short radius})^2$). To calculate the periplasmic volume, the cytoplasmic volume is subtracted from the total volume of the cell.

25 **Protein Expression and quantification:**

[0104] *E. coli* BL21(DE3) (NEB product #c2527) containing pET28a (emd Millipore product #69864) and its derivatives carrying GFP or collagen derivatives were grown in a shaking incubator at 37°C overnight in switch media containing 50mg/mL kanamycin (p212121 product # 2251180). Next day, subcultures are started
30 with a 1:10 dilution of the overnight culture into fresh switch media containing 50mg/mL kanamycin. The culture is then physiologically switched and protein production is induced simultaneously at an OD 600 of 1 to 1.1 (Read on a Molecular Devices Spectramax M2 microplate reader). The physiologically switch and protein production are flipped through the addition of 100ug/mL Carbenicillin, 50ug/mL

Fosfomycin, and 100ug/mL IPTG (p212121 product #367-93-1). Protein expression is continued in the switched state from between 8 hours to overnight at room temperature (approximately 22oC) on an orbital shaker. In order to quantify total protein levels, Quick Start™ Bradford Protein Assay was used on mixed portion of culture and standard curves are quantitated on a Molecular Devices Spectramax M2 microplate reader. In order to quantitate the relative intensity of target protein production relative to the rest of the protein population the mixed portion of the cultures were run on Mini-PROTEAN® TGX™ Gels and stained with Bio-Safe™ Coomassie Stain.

10 **Induction of protein production:**

[0105] Standard procedures have been followed to induce protein production in the physiological state. We have been using the strain BL21(DE3) containing the plasmid pET28a driving the IPTG/lactose inducible production of recombinant proteins and targeting them to the periplasmic space using the DsbA signal sequence. Using the GFP protein, targeted to the periplasmic space as described above, we have demonstrated the ability to gain and increase of 5-fold in protein production when compared to un-switched cell populations induced at the same optical density, for the same amount of time (figures). The induction was optimal at an OD600 of 1.1 and induction was continued for 10 hours at which point the protein produced was measured at about 200 mg/mL.

Example 2: Production of Full-Length Collagen

[0106] Full length jellyfish collagen was produced using the expression system discussed in Example 1 herein. The wild-type, full length amino acid sequence of *Podocoryna carnea* (jellyfish or Hydrozoan) collagen is provided in SEQ ID NO: 1.

25 GPQGVVGADGKDGTPEKGEQRTGAAGKQGSPGADGARGPLGSIGQQGA
RGE PGDPGSPGLRGDTGLAGVKGVAGPSGRPGQPGANGLPGVNNGRGLRGK
P GAKGLAGSDGEAGESGAPGQSGPTGPRGQRGPSGEDGNPGLQGLPGSDGEP
GEEGQPGRSGQPQQGPRGSPGEVGPGRSGKPSGDRGDRGERGVPGQTGSA
GNVGEDGEQGGKGVDGASGPSGALGARGPPGSRGDTGAVGPPGPTGRSGLP
30 GNAGQKGPSGEPGSPGKAGSAGEQPPGKDGSNGEPGSPGKEGERGLAGPPG
PDGRRGETGSPGIAGALGKPGLEGPKGYPLRGRDGTNGKRGEQGETGPDGV
RGIPGNDGQSGKPGIDGIDGTNGQPGEAGYQGGRGTRGQLGETGDVGQNGD
RGAPGPDGSKGSAGRPGLR (SEQ ID NO: 1)

//www.ncbi.nlm.nih.gov/protein/4379341?report=genbank&log\$=proalign&blast_rank=1&RID=T1N9ZEUW014

[0107] The non-codon optimized polynucleotide sequence encoding the full length jellyfish collagen is disclosed in SEQ ID NO: 2.

5 ggaccacaaggtgttaggagctgatggcaaagatggaacaccgggagagaaaggtgagcaaggacgaaccggagc
 tgcaggaaaacagggaagccctggagcagatggagcaagaggccctcttgatcaattggacaacaaggtgctcgtgga
 gaacctggtgatccaggatctcccgcttaagaggagatactggattggctggagtcaaaggagtagcaggaccatctgg
 tcgacctggacaacccggtgcaaatggattacctggtgtaatggcagaggcggttgagaggcaaacctggtgctaaag
 gaattgctggcagtgatggagaagcgggagaatctggcgacactggacagtcggacctaccgggtccacgtggtcaacg
 10 aggaccaagtgtgaggatgtaatcctggattacagggattgctggtctgatggagagcccgagaggaaagacaa
 cctggaagatctggtcaaccaggacagcaaggaccacgtggttccctggagaggtaggaccaagaggatctaaagtc
 catcaggagatcgtggtgacaggggagagagaggtgttctggacaacagggtcggctggaatgtaggagaagatgg
 agagcaaggaggcaaaaggtgctgatggagcagtggaaccaagtggagctcttggtgctcgtggtccccaggaaagtag
 aggtgacaccggggcagtgggacctcccgacactactggcgatctggtttacctggaacgcaggacaaaagggacc
 15 aagtgtgaaccaggtagtccaggaaaagcaggatcagctggtgaacagggctcctcctgtaaacaggatcaaattgt
 gaacctggatcctcggcaaagagggtgaacgtggtcttctggtccaccagggtccagatggcagacgtggtgaacgg
 gatctccaggatcgtggtgctcttgtaaacagggttgggaaggacctaaagggtatccaggattaagaggaagatgg
 aaccaatggcaaacaggagagaacaaggagaaactggtcctgatggagtcagaggtattcctggaatgatgacaatctg
 gcaaaccaggattgatgtattgacggaacaaatggtcaaccaggtaggctggataccaaggtgtagaggtacacgt
 20 ggtcagttaggtgaaactggtgatgtcggacagaaatggagatcgaggagctcctggtcctgatggtctaaaggttctgctg
 gtagaccaggactcgtgg (SEQ ID NO:

2) [https://www.ncbi.nlm.nih.gov/nucleotide/3355656?report=genbank&log\\$=nuclalign&blast_rank=1&RID=TSYP7CMV014](https://www.ncbi.nlm.nih.gov/nucleotide/3355656?report=genbank&log$=nuclalign&blast_rank=1&RID=TSYP7CMV014)

[0108] Two different codon optimized polynucleotide sequences encoding the wild-
 25 type, full-length jellyfish collagen were synthesized. The two polynucleotide
 sequences were slightly different due to slightly different codon optimization
 methods. In addition to the non-truncated, full-length jellyfish collagen, the
 polynucleotides also encoded a secretion tag, a 9 amino acid his tag, a short linker,
 and a thrombin cleavage site. The DsbA secretion tag is encoded by nucleotides 1-71.
 30 The histidine tag comprising 9 histidine residues is encoded by nucleotides 73-99 and
 encodes amino acids 25-33. The linker is encoded by nucleotides 100-111. The
 thrombin cleavage tag is encoded by nucleotides 112-135 and encodes amino acids
 38-45. The truncated collagen is encoded by nucleotides 136-1422. The two
 polynucleotides are disclosed below in SEQ ID NO: 3 and 4.

ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
TCGGCGGGCGCAGTATGAAGATCACCATCACCACCACCACCATCACCCTC
TGGCTCGAGCCTGGTGCCGCGCGGCAGCCATATGGGTCCGCAGGGTGTTG
TTGGTGCAGATGGTAAAGACGGTACCCCGGGTGAAAAAGGAGAACAGGG
5 ACGTACAGGTGCAGCAGGTAAACAGGGCAGCCCGGGTGCCGATGGTGCC
CGTGGCCCGCTGGGTAGCATTGGTCAGCAGGGTGCAAGAGGGCGAACCGG
GCGATCCGGGTAGTCCGGGCCTGCGTGGTGATACGGGTCTGGCCGGTGTT
AAAGGCGTTGCAGGTCCTTCAGGTCGTCCAGGTCAACCGGGTGCAAATGG
TCTGCCGGGTGTTAATGGTCGTGGCGGTCTGCGTGGCAAACCGGGAGCAA
10 AAGGTATTGCAGGTAGCGATGGAGAAGCCGGTGAAAGCGGTGCCCCGGG
TCAGAGTGGTCCGACCGGTCCGCGCGGTGAGCGTGGTCCGTCTGGTGAAG
ATGGCAATCCGGGTCTGCAGGGTCTGCCTGGTAGTGATGGCGAACAGGT
GAAGAAGGTCAGCCGGGTCGTTGAGGCCAGCCGGGCCAGCAGGGCCCCGC
GTGGTAGCCCGGGCGAAGTTGGCCCGCGGGGTAGTAAAGGTCCTAGTGGC
15 GATCGCGGTGATCGTGGTGAACGCGGTGTTCTTGGTCAGACCGGTAGCGC
AGGTAATGTTGGCGAAGATGGTGAACAGGGTGGCAAAGGTGTTGATGGTG
CAAGCGGTCCGAGCGGTGCACTGGGTGCACGTGGTCTCCGGGCAGCCGT
GGTGACACCGGTGCAGTTGGTCCGCCTGGCCCGACCGGCCGTAGTGGCTT
ACCGGGTAATGCAGGTCAGAAAGGTCCGTGAGGTGAACCTGGCAGCCCTG
20 GTAAAGCAGGTAGTGCCGGTGAGCAGGGTCCGCCGGGCAAAGATGGTAG
TAATGGTGAGCCGGGTAGCCCTGGCAAAGAAGGTGAACGTGGTCTGGCAG
GACCGCCGGGTCTGATGGTCGCCGCGGTGAAACGGGTTCACCGGGTATT
GCCGGTGCCCTGGGTAAACCAGGTCTGGAAGGTCCGAAAGGTTATCCTGG
TCTGCGCGGTGATGATGGTACCAATGGCAAACGTGGCGAACAGGGCGAAA
25 CCGGTCCAGATGGTGTTCTGTGGTATTCCGGGTAACGATGGTCAGAGCGGT
AAACCGGGCATTGATGGTATTGATGGCACCAATGGTCAGCCTGGCGAAGC
AGGTTATCAGGGTGGTCGCGGTACCCGTGGTCAGCTGGGTGAAACAGGTG
ATGTTGGTCAGAATGGTGATCGCGGCGCACCGGGTCCGGATGGTAGCAAA
GGTAGCGCCGGTTCGTCCGGGTTTACGT_{taa} (SEQ ID NO: 3)
30 ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
TCGGCGGGCGCAGTATGAAGATCACCATCACCACCACCACCATCACCCTC
TGGCTCGAGCCTGGTGCCGCGCGGCAGCCATATGGGTCCGCAGGGTGTTG
TTGGTGCAGATGGTAAAGACGGTACCCCGGGTGAAAAAGGtGAACAGGGt
CGTACcGGTGCAGCAGGTAAACAGGGCAGCCCGGGTGCCGATGGTGCCCG

TGGCCCGCTGGGTAGCATTGGTCAGCAGGGTGC A_{cg}tGGCGAACCGGGCGA
 TCCGGGTAG_cCCGGGCCTGCGTGGTGATACGGGTCTGGCCGGTGTTAAAG
 GCGTTGCAGGTCCTTC_tGGTCGTCCAGGTCAACCGGGTGCAAATGGTCTGC
 CGGGTGTTAATGGTCGTGGCGGTCTGCGTGGCAAACCGGG_tGCAAAAGGT
 5 ATTGCAGGTAGCGATGG_cGAAGCCGGTGAAAGCGGTGCCCCGGGTGAGAG
_cGGTCCGACCGGTCCGCGCGGTACGCGTGGTCCGTCTGGTGAAGATGGCA
 ATCCGGGTCTGCAGGGTCTGCCTGGT_{ag}cGATGGCGAACCAGGTGAAGAAG
 GTCAGCCGGGTGCTTC_tGGCCAGCCGGGCCAGCAGGGCCCCGCGTGGTAGC
 CCGGGCGAAGTTGGCCCCGCG_cGGT_tcTAAAGGTCCTAG_cGGCGATCGCGGT
 10 GATCGTGGTGAACGCGGTGTTCTTGGTCAGACCGGTAGCGCAGGTAATGT
 TGGCGAAGATGGTGAACAGGGTGGCAAAGGTGTTGATGGTGCAAGCGGT
 CCGAGCGGTGCACTGGGTGCACGTGGTCTCCGGGCAGCCGTGGTGACAC
 CGGTGCAGTTGGTCCGCCTGGCCCCGACCGGCCGTAG_cGGC_{ctg}CCGGGTAAAT
 GCAGGTCAGAAAGGTCCGT_ctGGTGAACCTGGCAGCCCTGGTAAAGCAGG
 15 TAG_cGCCGGTGAGCAGGGTCCGCCGGGCAAAGATGGTAG_cAATGGTGAGC
 CGGGTAGCCCTGGCAAAGAAGGTGAACGTGGTCTGGCAGG_tCCGCCGGGT
 CCTGATGGTCGCCGCGGTGAAACGGGTTC_tCCGGGTATTGCCGGTGCCCTG
 GGTAACACAGGTCTGGAAGGTCCGAAAGGTTATCCTGGTCTGCGCGGTGCG
 TGATGGTACCAATGGCAAACGTGGCGAACAGGGCGAAACCGGTCCAGAT
 20 GGTGTTCTGTGGTATTCCGGGTAAACGATGGTCAGAGCGGTAAACCGGGCAT
 TGATGGTATTGATGGCACCAATGGTCAGCCTGGCGAAGCAGGTTATCAGG
 GTGGTCGCGGTACCCGTGGTCAGCTGGGTGAAAC_cGGTGATGTTGGTCAG
 AATGGTGATCGCGGCGCACCGGGTCCGGATGGTAGCAAAGGTAGCGCCG
 GTCGTCCGGGT_{ctg}CGT_{taa} (SEQ ID NO: 4)

25 **[0109]** The amino acid sequence encoded by the polynucleotides of SEQ ID NO: 3
 and SEQ ID NO:4 is disclosed in SEQ ID NO:5 below. In SEQ ID NO: 5 the DsbA
 secretion tag is encoded by nucleotides 1-71 and encodes amino acids 1-24; the
 histidine tag comprising 9 histidine residues is encoded by nucleotides 73-99 and
 encodes amino acids 25-33; the linker is encoded by nucleotides 100-111 and encodes
 30 amino acids 34-37; the thrombin cleavage tag is encoded by nucleotides 112-135 and
 encodes amino acids 38-45; the full-length collagen is encoded by nucleotides 136-
 1422 and encodes amino acids 46-474.

MKKIWLALAGLVLAFSASAAQYEDHHHHHHHHHSGSSLVPRGSHMGPQGV
 VGADGKDGTGPEKGEGQRTGAAGKQGSPGADGARGPLGSIGQQGARGEPGD

PGSPGLRGDTGLAGVKGVAGPSGRPGQPGANGLPGVNNGRGGRLRGKPGAKGI
 AGSDGEAGESGAPGQSGPTGPRGQRGPSGEDGNPGLQGLPGSDGEPGEEGQP
 GRSGQPGQQGPRGSPGEVGPRGSKGPSGDRGDRGERGVPGQTGSAGNVGED
 GEQGGKGVDGASGPSGALGARGPPGSRGDTGAVGPPGPTGRSGLPGNAGQK
 5 GPSGEPGSPGKAGSAGEQGPPEGKDGSDNGEPGSPGKEGERGLAGPPGPDGRRG
 ETGSPGIAGALGKPGLEGPKGYPLRGRDGTNGKRGEQGETGPDGVRGIPGN
 DGQSGKPGIDGIDGTNGQPGEAGYQGGRGTRGQLGETGDVGQNGDRGAPGP
 DGSKGSAGRPLR(SEQ ID NO: 5)

[0110] The full length jellyfish collagen without the DsbA secretion tag, the histidine
 10 tag, linker and thrombin cleavage site is disclosed in SEQ ID NO: 89.

GPQGVVGADGKDGTGPEKGEQGRGAAGKQGSPGADGARGPLGSIGQQGA
 RGEPGDPGSPGLRGDTGLAGVKGVAGPSGRPGQPGANGLPGVNNGRGGRLRGK
 PGIAGSDGEAGESGAPGQSGPTGPRGQRGPSGEDGNPGLQGLPGSDGEP
 GEEGQPGRSGQPGQQGPRGSPGEVGPRGSKGPSGDRGDRGERGVPGQTGSA
 15 GNVGEDGEQGGKGVDGASGPSGALGARGPPGSRGDTGAVGPPGPTGRSGLP
 GNAGQKGPSGEPGSPGKAGSAGEQGPPEGKDGSDNGEPGSPGKEGERGLAGPPG
 PDGRRGETGSPGIAGALGKPGLEGPKGYPLRGRDGTNGKRGEQGETGPDGV
 RGIPGNDGQSGKPGIDGIDGTNGQPGEAGYQGGRGTRGQLGETGDVGQNGD
 RGAPGPDGSKGSAGRPLR(SEQ ID NO: 89)

[0111] The polynucleotides of SEQ ID NO: 3 and SEQ ID NO: 4 were synthesized
 by Gen9 DNA, now Ginkgo Bioworks internal synthesis. Overlaps between the
 pET28 vector and SEQ ID NO: 3 and SEQ ID NO: 4 were designed to be between 30
 and 40bp long and added using PCR with the enzyme PrimeStar GXL polymerase
 (http://www.clontech.com/US/Products/PCR/GC_Rich/PrimeSTAR_GXL_DNA_Pol
 25 ymerase?sitex=10020:22372:US). The opened pET28a vector and insert DNA (SEQ
 ID NO: 3 or SEQ ID NO: 4) were then assembled together into the final plasmid
 using SGI Gibson assembly ([https://us.vwr.com/store/product/17613857/gibson-](https://us.vwr.com/store/product/17613857/gibson-assembly-hifi-1-step-kit-synthetic-genomics-inc)
[assembly-hifi-1-step-kit-synthetic-genomics-inc](https://us.vwr.com/store/product/17613857/gibson-assembly-hifi-1-step-kit-synthetic-genomics-inc)). Sequence of plasmid was then
 verified through sanger sequencing through Eurofins Genomics
 30 (www.eurofinsgenomics.com).

[0112] The transformed cells were cultivated in minimal media and frozen in 1.5
 aliquots with glycerol at a ratio of 50:50 of cells to glycerol. One vial of this frozen
 culture was revived in 50ml of minimal media overnight at 37 °C, 200rpm. Cells were

transferred into 300ml of minimal media and grown for 6-9 hours to reach an OD600 of 5-10.

[0113] Minimal media used in this example and throughout this application is prepared as follows. The minimal media (Table 1) was autoclaved in several separate fractions, Salts mix (Ammonium Phosphate dibasic, Potassium phosphate monobasic, Citric acid anhydrous, Magnesium sulfate heptahydrate), the Sucrose at 500g/L, the Glucose at 55%, the Trace Metals TM5 (table 2), and Sodium Hydroxide 10M. The minimal media was then mixed together at the above concentrations post-autoclaving in the hood.

10

Table 1 Minimal media recipe for shake flask cultures

chemical	Formula	MW	Conc (g/L)
Ammonium Phosphate dibasic	$(\text{NH}_4)_2\text{HPO}_4$	133	4
Potassium phosphate monobasic	KH_2PO_4	137	13.3
Citric acid anhydrous	$\text{H}_3\text{C}_6\text{H}_5\text{O}_7$	192.14	4.5
Magnesium sulfate heptahydrate	$\text{MgSO}_4 \cdot 7\text{H}_2\text{O}$	246	0.59
Trace Metals TM5			2
Glucose	$\text{C}_6\text{H}_{12}\text{O}_6$	500	40
Sodium Hydroxide 10M	NaOH	400	5.2
Sucrose 500g/L	$\text{C}_{12}\text{H}_{22}\text{O}_{11}$	500	66.6

Table 2 Trace Metals TM5 composition

chemical	Formula	MW	Conc (g/L)
Ferrous Sulfate Heptahydrate	$\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$	278.02	27.8
Calcium Chloride	$\text{CaCl}_2 \cdot 2\text{H}_2\text{O}$	147	2.94
Manganese Chloride	MnCl_2	125.84	1.26
Zinc Sulfate	$\text{ZnSO}_4 \cdot \text{H}_2\text{O}$	179.5	1.8
Nickel Chloride	$\text{NiCl}_2 \cdot 6\text{H}_2\text{O}$	237.69	0.48
Sodium Molybdate	$\text{Na}_2\text{MoO}_4 \cdot 2\text{H}_2\text{O}$	241.95	0.48
Sodium Selenite	Na_2SeO_3	172.94	0.35
Boric Acid	H_3BO_3	61.83	0.12

[0114] The harvested cells were disrupted in a homogenizer at 14,000 psi pressure in 2 passes. Resulting slurry contained the collagen protein along with other proteins.

- 5 [0115] The collagen was purified by acid treatment of homogenized cell broth. The pH of the homogenized slurry was decreased to 3 using 6M Hydrochloric acid. Acidified cell slurry was incubated overnight at 4° C with mixing, followed by centrifugation. Supernatant of the acidified slurry was tested on a polyacrylamide gel and found to contain collagen in relatively high abundance compared to starting
- 10 pellet. The collagen slurry thus obtained was high in salts. To obtain volume and salt reduction, concentration and diafiltration steps were performed using an EMD Millipore Tangential Flow Filtration system with ultrafiltration cassettes of 0.1 m² each. Total area of filtration was 0.2 m² using 2 cassettes in parallel. A volume reduction of 5x and a salt reduction of 19x was achieved in the TFF stage. Final
- 15 collagen slurry was run on an SDS-PAGE gel to confirm presence of the collagen. This slurry was dried using a multi-tray lyophilizer over 3 days to obtain a white, fluffy collagen powder.

- [0116] The purified collagen was analyzed on an SDS-PAGE gel and a thick and clear band was observed at the expected size of 42 kilodaltons. The purified collagen
- 20 was also analyzed by mass spectrometry and it was confirmed that the 42 kilodalton protein was jellyfish collagen.

[0117] The fermentations were performed at various temperature ranging from 25° to 28° C. For some fermentations, the temperature of the fermentation was maintained at a constant temperature and immediately upon completion of

fermentation (OD600 of 5-10) the collagen was purified. For other fermentations, the temperature of the fermentations was maintained for a desired period of time and when cell densities of OD600 of 5-10 were reached, the temperature was reduced to induce protein production. Typically, the temperature was reduced from 28° C to 25° C. After the fermentation at 25° C was continued for 40-60 hours, the collagen was isolated.

Additional full length jellyfish collagens

[0118] A full length jellyfish collagen without a His tag, linker, and thrombin cleavage site is disclosed below. Two codon-optimized nucleotide sequence encoding this collagen are provided in SEQ ID NO: 6 and SEQ ID NO: 7. The differences in the nucleotide sequences are due to different codon-optimization strategies but encode the same protein. The amino acid sequence is disclosed in SEQ ID NO: 8. The Dsba secretion tag is encoded by nucleotides 1-72 and encodes amino acids 1-24. The collagen sequence is encoded by nucleotides 73-1359 and encodes amino acids 25-453.

ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
TCGGCGGCGCAGTATGAAGATGGTCCGCAGGGTGTGTTGGTGCAGATGG
TAAAGACGGTACCCCGGGTGAAAAAGGAGAACAGGGACGTACAGGTGCA
GCAGGTAAACAGGGCAGCCCGGGTGCCGATGGTGCCCGTGGCCCGCTGG
GTAGCATTGGTCAGCAGGGTGCAAGAGGCGAACC GGCGATCCGGGTAG
TCCGGGCCTGCGTGGTGATACGGGTCTGGCCGGTGTTAAAGGCGTTGCAG
GTCCTTCAGGTCGTCCAGGTCAACCGGGTGCAAATGGTCTGCCGGGTGTT
AATGGTCGTGGCGGTCTGCGTGGCAAACCGGGAGCAAAAGGTATTGCAGG
TAGCGATGGAGAAGCCGGTGAAAGCGGTGCCCCGGGTCAGAGTGGTCCG
ACCGGTCCGCGCGGTTCAGCGTGGTCCGTCTGGTGAAGATGGCAATCCGGG
TCTGCAGGGTCTGCCTGGTAGTGATGGCGAACCAGGTGAAGAAGGTCAGC
CGGGTCGTTTCAGGCCAGCCGGGCCAGCAGGGCCCGCGTGGTAGCCCGGGC
GAAGTTGGCCCGCGGGGTAGTAAAGGTCCTAGTGGCGATCGCGGTGATCG
TGGTGAACGCGGTGTTCCCTGGTCAGACCGGTAGCGCAGGTAATGTTGGCG
AAGATGGTGAACAGGGTGGCAAAGGTGTTGATGGTGCAAGCGGTCCGAG
CGGTGCACTGGGTGCACGTGGTCCTCCGGGCAGCCGTGGTGACACCGGTG
CAGTTGGTCCGCCTGGCCCGACCGGCCGTAGTGGCTTACCGGGTAATGCA
GGTCAGAAAGGTCCGTCAGGTGAACCTGGCAGCCCTGGTAAAGCAGGTAG
TGCCGGTGAGCAGGGTCCGCCGGGCAAAAGATGGTAGTAATGGTGAGCCG

GGTAGCCCTGGCAAAGAAGGTGAACGTGGTCTGGCAGGACCGCCGGGTCC
TGATGGTCGCCGCGGTGAAACGGGTTCACCGGGTATTGCCGGTGCCCTGG
GTAAACCAGGTCTGGAAGGTCCGAAAGGTTATCCTGGTCTGCGCGGTTCGT
GATGGTACCAATGGCAAACGTGGCGAACAGGGCGAAACCGGTCCAGATG
5 GTGTTCGTGGTATTCCGGGTAAACGATGGTCAGAGCGGTAAACCGGGCATT
GATGGTATTGATGGCACCAATGGTCAGCCTGGCGAAGCAGGTTATCAGGG
TGGTCGCGGTACCCGTGGTCAGCTGGGTGAAACAGGTGATGTTGGTCAGA
ATGGTGATCGCGGCGCACCGGGTCCGGATGGTAGCAAAGGTAGCGCCGGT
CGTCCGGGTTTACGT_{taa} (SEQ ID NO: 6)

10 ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
TCGGCGGCGCAGTATGAAGATGGTCCGCAGGGTGTGTTGGTGCAGATGG
TAAAGACGGTACCCCGGGTGAAAAAGGtGAACAGGGtCGTACcGGTGCAGC
AGGTAAACAGGGCAGCCCGGGTGCCGATGGTGCCCGTGGCCCGCTGGGTA
15 GCATTGGTCAGCAGGGTGCAcgtGGCGAACCGGGCGATCCGGGTAGcCCGG
GCCTGCGTGGTGATACGGGTCTGGCCGGTGTAAAGGC GTTGCAGGTCTCT
TCtGGTCGTCCAGGTCAACCGGGTGCAAATGGTCTGCCGGGTGTTAATGGT
CGTGGCGGTCTGCGTGGCAAACCGGGtGCAAAGGTATTGCAGGTAGCGA
TGGcGAAGCCGGTGAAAGCGGTGCCCCGGGTCAGAGcGGTCCGACCGGTC
20 CGCGCGGTACGCGTGGTCCGTCTGGTGAAGATGGCAATCCGGGTCTGCAG
GGTCTGCCTGGT_{agc}GATGGCGAACCGGTGAAGAAGGTCAGCCGGGTCTGT
TCtGGCCAGCCGGGCCAGCAGGGCCCCGCGTGGTAGCCCGGGCGAAAGTTGG
CCCGCGcGGT_{tc}TAAAGGTCCTAGcGGCGATCGCGGTGATCGTGGTGAACGC
GGTGTTCTCTGGTCAGACCGGTAGCGCAGGTAATGTTGGCGAAGATGGTGA
25 ACAGGGTGGCAAAGGTGTTGATGGTGCAAGCGGTCCGAGCGGTGCACTGG
GTGCACGTGGTCCTCCGGGCAGCCGTGGTGACACCGGTGCAGTTGGTCCG
CCTGGCCCGACCGGCCGTAGcGGC_{ctg}CCGGGTAAATGCAGGTGAGAAAGGT
CCGTCTGGTGAACCTGGCAGCCCTGGTAAAGCAGGTAGcGCCGGTGAGCAG
GGTCCGCCGGGCAAAGATGGTAGcAATGGTGAGCCGGGTAGCCCTGGCAA
30 AGAAGGTGAACGTGGTCTGGCAGGtCCGCCGGGTCTGATGGTCGCCGCG
GTGAAACGGGTTCtCCGGGTATTGCCGGTGCCCTGGGTAAACCAGGTCTGG
AAGGTCCGAAAGGTTATCCTGGTCTGCGCGGTCTGTGATGGTACCAATGGC
AAACGTGGCGAACAGGGCGAAACCGGTCCAGATGGTGTTCTGTGGTATTCC
GGGTAAACGATGGTCAGAGCGGTAAACCGGGCATTGATGGTATTGATGGCA

CCAATGGTCAGCCTGGCGAAGCAGGTTATCAGGGTGGTCGCGGTACCCGT
GGTCAGCTGGGTGAAACcGGTGATGTTGGTCAGAATGGTGATCGCGGCCG
ACCGGGTCCGGATGGTAGCAAAGGTAGCGCCGGTCGTCCGGGTctgCGTtaa
(SEQ ID NO: 7)

5 MKKIWLALAGLVLAFFSASAAQYEDGPQGVVGADGKDGTGPEKGEQGRGTGA
AGKQGS PGADGARGPLGSIGQQGARGE PGDPGSPGLRGDTGLAGVKGVAGP
SGRPGQPGANGLPGVNRRGGLRGKPGAKGIAGSDGEAGESGAPGQSGPTGPR
GQRGPSGEDGNPGLQGLPGSDGEPGEEGQPRSGQPGQQGPRGSPGEVGPGR
10 SKGPSGDRGDRGERGVPGQTGSAGNVGEDGEQGGKGVDGASGPSGALGAR
GPPGSRGDTGAVGPPGPTGRSGLPGNAGQKGPSGEPGSPGKAGSAGEQGPPG
KDGSNGEPGSPGKEGERGLAGPPGPDGRRGETGSPGIAGALGKPGLEGPKGY
PGLRGRDGTNGKRGEQGETGPDGVRGIPGNDGQSGKPGIDGIDGTNGQPGEA
GYQGGRGTRGQLGETGDVGQNGDRGAPGPDGSKGSAGRPLR (SEQ ID NO:
15 8)

Example 3: Production of Truncated Collagen

[0119] A codon optimized DNA sequence, optimized for expression in *E. coli*,
encoding a jellyfish collagen with a truncation of 240 internal amino acids was
synthesized and expressed. The DNA sequence is shown below in SEQ ID NO: 9. In
20 SEQ ID NO: 9, The DsbA secretion tag is encoded by nucleotides 1-72 and encodes
amino acids 1-24 of SEQ ID NO: 10. The histidine tag comprising 9 histidine
residues is encoded by nucleotides 73-99 and encodes amino acids 25-33 of SEQ ID
NO: 10. The linker is encoded by nucleotides 100-111 and encodes amino acids 34-
37 of SEQ ID NO: 10. The thrombin cleavage site is encoded by nucleotides 112-135
25 and encodes amino acids 38-45 of SEQ ID NO: 10. The truncated collagen is
encoded by nucleotides 136-822 and encodes amino acids 46-274 of SEQ ID NO: 10.
ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
TCGGCGGCGCAGTATGAAGATCACCATCACCACCACCACCATCACCCTC
TGGCTCGAGCCTGGTGCCGCGCGGCAGCCATATGGGTCCGCAGGGTGTTG
30 TTGGTGACAGATGGTAAAGACGGTACCCCGGGTGAAAAAGGAGAACAGGG
ACGTACAGGTGCAGCAGGTAAACAGGGCAGCCCGGGTGCCGATGGTGCC
CGTGGCCCCGCTGGGTAGCATTGGTCAGCAGGGTGCAAGAGGCGAACCGG
GCGATCCGGGTAGTCCGGGCCTGCGTGGTGATACGGGTCTGGCCGGTGTT

AAAGGCGTTGCAGGTCCTTCAGGTCGTCCAGGTCAACCGGGTGCAAATGG
 TCTGCCGGGTGTTAATGGTCGTGGCGGTCTGGAACGTGGTCTGGCAGGAC
 CGCCGGGTCCTGATGGTCGCCGCGGTGAAACGGGTTCACCGGGTATTGCC
 GGTGCCCTGGGTAAACCAGGTCTGGAAGGTCCGAAAGGTTATCCTGGTCT
 5 GCGCGGTCTGTGATGGTACCAATGGCAAACGTGGCGAACAGGGCGAAACC
 GGTCCAGATGGTGTTCGTGGTATTCCGGGTAAACGATGGTCAGAGCGGTAA
 ACCGGGCATTGATGGTATTGATGGCACCAATGGTCAGCCTGGCGAAGCAG
 GTTATCAGGGTGGTCGCGGTACCCGTGGTCAGCTGGGTGAAACAGGTGAT
 GTTGGTCAGAATGGTGATCGCGGCGCACCGGGTCCGGATGGTAGCAAAGG
 10 TAGCGCCGGTCGTCCGGGTTTACGTtaa (SEQ ID NO: 9)

[0120] The truncated collagen is approximately 54% of the full length collagen and is disclosed below in SEQ ID NO:10.

MKKIWLALAGLVLAFFSASAAQYEDHHHHHHHHHSGSSLVPRGSHMGPQGV
 VGADGKDGTPGEKGEQRTGAAGKQGSPGADGARGPLGSIGQQGARGEPPG
 15 PGSPGLRGDTGLAGVKGVAGPSGRPGQPGANGLPGVNGRGGLERGLAGPPG
 PDGRRGETGSPGIAGALGKPGLEGPKGYPLRGRDGTNGKRGEQGETGPDGV
 RGIPGNDGQSGKPGIDGIDGTNGQPGEAGYQGGRGTRGQLGETGDVGQNGD
 RGAPGPDGSKGSAGRPGLR (SEQ ID NO: 10)

[0121] The polynucleotide encoding the truncated jellyfish collagen without the DsbA
 20 secretion tag, the histidine tag, linker and thrombin cleavage site is disclosed in SEQ
 ID NO: 85

GTCCGCAGGGTGTTGTTGGTGCAGATGGTAAAGACGGTACCCCGGGTGAA
 AAAGGAGAACAGGGACGTACAGGTGCAGCAGGTAAACAGGGCAGCCCGG
 GTGCCGATGGTGCCCGTGGCCCGCTGGGTAGCATTGGTCAGCAGGGTGCA
 25 AGAGGCGAACCAGGGCGATCCGGGTAGTCCGGGCCTGCGTGGTGATACGG
 GTCTGGCCGGTGTTAAAGGCGTTGCAGGTCCTTCAGGTCGTCCAGGTCAA
 CCGGGTGCAAATGGTCTGCCGGGTGTTAATGGTCGTGGCGGTCTGGAACG
 TGGTCTGGCAGGACCGCCGGTCTGATGGTCGCCGCGGTGAAACGGGTT
 CACCGGGTATTGCCGGTGCCCTGGGTAAACCAGGTCTGGAAGGTCCGAAA
 30 GGTTATCCTGGTCTGCGCGGTCTGTGATGGTACCAATGGCAAACGTGGCGA
 ACAGGGCGAAACCGGTCCAGATGGTGTTCGTGGTATTCCGGGTAACGATG
 GTCAGAGCGGTAAACCGGGCATTGATGGTATTGATGGCACCAATGGTCAG
 CCTGGCGAAGCAGGTTATCAGGGTGGTCGCGGTACCCGTGGTCAGCTGGG

TGAAACAGGTGATGTTGGTCAGAATGGTGATCGCGGCGCACCGGGTCCGG
ATGGTAGCAAAGGTAGCGCCGGTCGTCCGGGTTTACGTaa (SEQ ID NO: 85)

[0122] The truncated jellyfish collagen without the DsbA secretion tag, the histidine tag, linker and thrombin cleavage site is disclosed in SEQ ID NO: 86

5 GPQGVVVGADGKDGTPGEKGEQGRGAAGKQGSPGADGARGPLGSIGQQGA
RGEPPDGPSPGLRGDTGLAGVKGVAGPSGRPGQPGANGLPGVNNGRGGLERG
LAGPPGPDGRRGETGSPGIAGALGKPGLEGPKGYPLRGRDGTNGKRGEQGE
TGPDPGVRGIPGNDGQSGKPGIDGIDGTNGQPGEAGYQGGRGTRGQLGETGDV
GQNGDRGAPGPDGSKGSAGRPLR (SEQ ID NO: 86)

10 [0123] The polynucleotides of SEQ ID NO: 9 was codon optimized and synthesized by Gen9 DNA, now Ginkgo Bioworks internal synthesis. Overlaps between the pET28 vector and SEQ ID NO: 9 were designed to be between 30 and 40bp long and added using PCR with the enzyme PrimeStar GXL polymerase (http://www.clontech.com/US/Products/PCR/GC_Rich/PrimeSTAR_GXL_DNA_Polymerase?site=10020:22372:US). The opened pET28a vector and insert DNA (SEQ ID NO: 9) was then assembled together into the final plasmid using SGI Gibson assembly (<https://us.vwr.com/store/product/17613857/gibson-assembly-hifi-1-step-kit-synthetic-genomics-inc>). Sequence of plasmid was then verified through sanger sequencing through Eurofins Genomics (www.eurofinsgenomics.com).

20 [0124] The transformed cells were cultivated in minimal media and frozen in 1.5 aliquots with glycerol at a ratio of 50:50 of cells to glycerol. One vial of this frozen culture was revived in 50ml of minimal media overnight at 37 °C, 200rpm. Cells were transferred into 300ml of minimal media and grown for 6-9 hours to reach an OD600 of 5-10.

25 [0125] A bioreactor was prepared with 2.7L of minimal media + glucose and 300 ml of OD600 of 5-10 culture was added to bring the starting volume to 3L. Cells were grown at 28°C, pH7 with Dissolved Oxygen maintained at 20% saturation using a cascade containing agitation, air and oxygen. pH was controlled using 28% w/w Ammonium hydroxide solution. Fermentation was run in a fed-batch mode using a
30 DO-stat based feeding algorithm once the initial bolus of 40g/L was depleted around 13hours. After 24-26hours of initial growth, the OD600 reached above 100. At this point, 300mL of 500g/L sucrose was added and temperature was reduced to 25C. High density culture was induced for protein production using 1mM IPTG. Fermentation was continued for another 20-24 hours and cells were harvested using a

bench top centrifuge at 9000 rcf, 15C for 60 minutes. Cell pellet recovered from centrifugation was resuspended in a buffer containing 0.5M NaCl and 0.1M KH₂PO₄ at pH8 in a weight by weight ratio of 2x buffer to 1x cells.

5 [0126] The harvested cells were disrupted in a homogenizer at 14,000 psi pressure in 2 passes. Resulting slurry contained the collagen protein along with other proteins.

[0127] The fermentations were performed at various temperature ranging from 25° to 28° C. For some fermentations, the temperature of the fermentation was maintained at a constant temperature and immediately upon completion of fermentation (OD600 of 5-10) the collagen was purified. For other fermentations, the
10 temperature of the fermentations was maintained for a desired period of time and when cell densities of OD600 of 5-10 were reached, the temperature was reduced to induce protein production. Typically, the temperature was reduced from 28° C to 25° C. After the fermentation at 25° C was continued for 40-60 hours, the collagen was isolated.

15 [0128] The collagen was purified by acid treatment of homogenized cell broth. Additionally, acid treatment was also performed on non-homogenized whole cells recovered from the bioreactor after centrifugation and resuspension in the buffer described above. The pH of either the homogenized slurry of the resuspended whole cells was decreased to 3 using 6M Hydrochloric acid. Acidified cell slurry was
20 incubated overnight at 4° C with mixing, followed by centrifugation. Supernatant of the acidified slurry was tested on a polyacrylamide gel and found to contain collagen in relatively high abundance compared to starting pellet. The collagen slurry thus obtained was high in salts. To obtain volume and salt reduction, concentration and diafiltration steps were performed using an EMD Millipore Tangential Flow Filtration
25 system with ultrafiltration cassettes of 0.1 m² each. Total area of filtration was 0.2 m² using 2 cassettes in parallel. A volume reduction of 5x and a salt reduction of 19x was achieved in the TFF stage. Final collagen slurry was run on an SDS-PAGE gel to confirm presence of the collagen. This slurry was dried using a multi-tray lyophilizer over 3 days to obtain a white, fluffy collagen powder.

30 [0129] The purified truncated collagen obtained from homogenized cell broth or non-homogenized cells were analyzed on an SDS-PAGE gel and a thick and clear band was observed at the expected size of 27 kilodaltons. The purified collagen was also analyzed by mass spectrometry and it was confirmed that the 27 kilodalton protein was jellyfish collagen.

[0130] An alternative purification method of the full length and truncated collagens is provided below.

- [0131] The fermentation broth was mixed with 0.3-0.5% w/v of Poly Ethyl Imine (PEI). After 15 minutes of incubation with PEI, the fermentation broth was
- 5 centrifuged at 9000 ref for 15 minutes to recover the supernatant, which contained the collagen protein. The pellet containing the cells was discarded and the PEI-treated collagen containing supernatant was mixed with Sodium Bentonite (0.2% final w/v) (Wyopure®, Wyoming Bentonite) and centrifuged. The bentonite containing pellet was discarded and the supernatant was recovered.
- 10 [0132] The Bentonite treated supernatant was concentrated between 3-6 fold on a tangential flow filtration system (TFF) (EMD Millipore) using a 5kDa cassette. The collagen was retained with almost no losses in the permeate stream. To remove salts, the retentate from the concentration step was diafiltered using the same TFF set-up. Final conductivity of the protein solution was < 10 milliSiemens. The typical
- 15 conductivity was between 400 microsiemens and 1.5 millisiemens. Highly concentrated collagen solutions had higher conductivities approaching 4 milliSiemens. A skilled artisan will understand that conductivities higher than 10 milliSiemens may be observed depending on the concentration of the collagen. Next, the desalted and concentrated protein was subjected to treatment with activated
- 20 carbon using the W-L 9000 10 x 40 granulated resin (Carbon Activated Corporation). 5% w/v of the carbon resin was mixed with collagen containing protein feed and mixed at 45-50°C with mild agitation. The carbon-treated slurry was filtered using a Buchner funnel lined with an Ertel Filter Press Pad M-953 (Ertel Alsop) in presence or absence of a filtration aid such as Diatomaceous Earth (Sigma Aldrich). Post-
- 25 filtration, the collagen solution was filtered through a 0.2 micron filter followed by one to several hours of treatment with Sodium Bentonite (0.2% w/v final) (Wyopure®, Wyoming Bentonite) and centrifuged at 9000 ref, 15-30 minutes to obtain a highly pure, clear and particulate free collagen solution. When removal of endotoxin proteins was desired, the protein was passed through a chromatographic
- 30 filter like Sartobind-Q (Sartorius-Stedim) to specifically remove endotoxin proteins.
- [0133] The purified collagen was analyzed on an SDS-PAGE gel and a thick and clear band was observed at 30 kilodaltons. The upshift in size is due to the structure of the collagen molecule and the high glycine/proline amino acid content. The

purified collagen was also analyzed by mass spectrometry and it was confirmed that the 30 kilodalton protein was the truncated collagen.

[0134] The truncated collagens were further analyzed by HPLC using an Agilent 1100 series HPLC. The column was the 50mm Agilent PLRP-S reverse phase
5 column with an inner diameter of 4.6mm, μ M particle size and 1000 Angstrom pore size.

[0135] The sample was prepared by diluting 1:1 in a 0.04% sodium azide solution in HPLC-grade water. After dilution, the resulting mixture was filtered through a 0.45 μ m filter to remove any large particles that can clog the HPLC column. For analysis,
10 the samples are diluted appropriately with a 20 mM ammonium acetate buffer in HPLC-grade water at a pH of about 4.5. After mixing the sample, it was transferred to a 300 μ L microvial that was then placed in the autosampler. Using ChemStation, the software that operates the HPLC, the analysis parameters such as sample flowrate, column temperature, mobile phase flowrate, mobile phase composition, etc. can be
15 altered. In one exemplary, but non-limiting analysis the parameters were: sample flow rate of 1 mL/min, column temperature of 80°C, column pressure of 60-70 bar, mobile phase composition of 97.9% water/1.9% acetonitrile with 0.2% trifluoroacetic acid; UV wavelength for analysis of 214.4 nm, injection volume of 10 μ L, and sample run time of 10 minutes.

[0136] Under these conditions, the truncated jellyfish collagen of SEQ ID NO: 91 has an elution time of about 5.4 minutes. ChemStation quantifies the peak area of the elution peak and calculates the protein concentration using a calibration curve that directly relates peak area to protein concentration. The calibration curve is generated using a known collagen solution that is serially diluted to contain collagen
25 concentration ranges of 0.06 mg/mL to 1.00 mg/mL.

Truncated Collagen Without His Tag-Linker-Thrombin Cleavage Site

[0137] A truncated jellyfish collagen without a His tag, linker, and thrombin cleavage site is disclosed below. The codon-optimized nucleotide sequence encoding this collagen is provided in SEQ ID NO: 11. The amino acid sequence is disclosed in
30 SEQ ID NO: 12. The DsbA secretion tag is encoded by nucleotides 1-72 and encodes amino acids 1-24. The truncated collagen sequence is encoded by nucleotides 73-639 and encodes amino acids 25-213.

ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
TCGGCGGCGCAGTATGAAGATGGTCCGCAGGGTGTGTGTTGGTGCAGATGG

TAAAGACGGTACCCCGGGTAATGCAGGTCAGAAAGGTCCGTCAGGTGAAC
 CTGGCAGCCCTGGTAAAGCAGGTAGTGCCGGTGAGCAGGGTCCGCCGGGC
 AAAGATGGTAGTAATGGTGAGCCGGGTAGCCCTGGCAAAGAAGGTGAAC
 GTGGTCTGGCAGGACCGCCGGGTCTGATGGTCGCCGCGGTGAAACGGGT
 5 TCACCGGGTATTGCCGGTGCCCTGGGTAAACCAGGTCTGGAAGGTCCGAA
 AGGTTATCCTGGTCTGCGCGGTCTGATGGTACCAATGGCAAACGTGGCG
 AACAGGGCGAAACCGGTCCAGATGGTGTTCTGTGGTATTCCGGGTAAACGAT
 GGTCAGAGCGGTAAACCGGGCATTGATGGTATTGATGGCACCAATGGTCA
 GCCTGGCGAAGCAGGTTATCAGGGTGGTCGCGGTACCCGTGGTCAGCTGG
 10 GTGAAACAGGTGATGTTGGTCAGAAATGGTGATCGCGGCGCACCGGGTCCG
 GATGGTAGCAAAGGTAGCGCCGGTCTGCCGGGTTTACGT_{taa} (SEQ ID NO:
 11)

MKKIWLALAGLVLAFFSASAAQYEDGPQGVVGADGKDGTGNAGQKGPSGE
 PGSPGKAGSAGEQPPGKDGSNGEPGSPGKEGERGLAGPPGPDGRRGETGSP
 15 GIAGALGKPGLEGPKGYPLRGRDGTNGKRGEQGETGPDGVRGIPGNDGQS
 GKPGIDGIDGTNGQPGEAGYQGGRGTRGQLGETGDVGQNGDRGAPGPDGSK
 GSAGRPGLR (SEQ ID NO: 12)

[0138] A polynucleotide encoding a truncated jellyfish collagen without a His tag, linker and thrombin cleavage site disclosed in SEQ ID NO: 90

GGTCCGCAGGGTGTTGTTGGTGCAGATGGTAAAGACGGTACCCCGGGTAA
 20 TGCAGGTCAGAAAGGTCCGTCAGGTGAACCTGGCAGCCCTGGTAAAGCAG
 GTAGTGCCGGTGAGCAGGGTCCGCCGGGCAAAGATGGTAGTAATGGTGA
 GCCGGGTAGCCCTGGCAAAGAAGGTGAACGTGGTCTGGCAGGACCGCCG
 GGTCCTGATGGTCGCCGCGGTGAAACGGGTTCACCGGGTATTGCCGGTGC
 25 CCTGGGTAAACCAGGTCTGGAAGGTCCGAAAGGTTATCCTGGTCTGCGCG
 GTCGTGATGGTACCAATGGCAAACGTGGCGAACAGGGCGAAACCGGTCC
 AGATGGTGTTCTGTGGTATTCCGGGTAAACGATGGTCAGAGCGGTAAACCGG
 GCATTGATGGTATTGATGGCACCAATGGTCAGCCTGGCGAAGCAGGTTAT
 CAGGGTGGTCGCGGTACCCGTGGTCAGCTGGGTGAAACAGGTGATGTTGG
 30 TCAGAATGGTGATCGCGGCGCACCGGGTCCGGATGGTAGCAAAGGTAGCG
 CCGGTCTGCCGGGTTTACGT_{taa} (SEQ ID NO: 90)

[0139] A truncated jellyfish collagen without a His tag, linker and thrombin cleavage site disclosed in SEQ ID NO: 91

GPQGVV GADGKDGTPGNAGQKGPSGEPGSPGKAGSAGEQGPPGKDGSNGEP
 GSPGKEGERGLAGPPGPDGRRGETGSPGIAGALGKPGLEGPKGYPLRGRDGT
 TNGKRGEQGETGPDGVRGIPGNDGQSGKPGIDGIDGTNGQPGEAGYQGGRGT
 RGQLGETGDVGQNGDRGAPGPDGSKGSAGRPLR (SEQ ID NO: 91)

5 Truncated Collagen With GEK Repeats

[0140] A jellyfish collagen with GEK repeats is disclosed below. The codon-
 optimized nucleotide sequence encoding this collagen is provided in SEQ ID NO: 13.
 The amino acid sequence is disclosed in SEQ ID NO: 14. The DsbA secretion tag is
 encoded by nucleotides 1-72 and encodes amino acids 1-24. The GEK repeat is
 10 encoded by nucleotides 73-126 and encodes the GEK repeats of amino acids 25-42.
 The truncated collagen sequence is encoded by nucleotides 127-693 and encodes
 amino acids 43-231.

ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
 TCGGCGGCGCAGTATGAAGATGGTGAAAAAGGTGAaAAGGGCGAGAAAG
 15 GTGAGAAAGGCGAAAAGGGTGAAAAAGGTCCGCAGGGTGTTGTTGGTGC
 AGATGGTAAAGACGGTACCCCGGGTAATGCAGGTCAGAAAGGTCCGTCA
 GGTGAACCTGGCAGCCCTGGTAAAGCAGGTAGTGCCGGTGAGCAGGGTCC
 GCCGGGCAAAGATGGTAGTAATGGTGAGCCGGGTAGCCCTGGCAAAGAA
 GGTGAACGTGGTCTGGCAGGACCGCCGGGTCCTGATGGTCGCCGCGGTGA
 20 AACGGGTTACCGGGTATTGCCGGTGCCCTGGGTAAACCAGGTCTGGAAG
 GTCCGAAAGGTTATCCTGGTCTGCGCGGTCTGTATGGTACCAATGGCAAA
 CGTGGCGAACAGGGCGAAACCGGTCCAGATGGTGTTCTGGTATTCCGGG
 TAACGATGGTCAGAGCGGTAAACCGGGCATTGATGGTATTGATGGCACCA
 ATGGTCAGCCTGGCGAAGCAGGTTATCAGGGTGGTCGCGGTACCCGTGGT
 25 CAGCTGGGTGAAACAGGTGATGTTGGTCAGAATGGTGATCGCGGCGCACC
 GGGTCCGGATGGTAGCAAAGGTAGCGCCGGTCGTCCGGGTTTACGTtaa
 (SEQ ID NO: 13)

MKKIWLALAGLVLAFSASAAQYEDGEKGEKGEKGEKGEKGEKGPQGVVGA
 DGKDGTPGNAGQKGPSGEPGSPGKAGSAGEQGPPGKDGSNGEPGSPGKEGE
 30 RGLAGPPGPDGRRGETGSPGIAGALGKPGLEGPKGYPLRGRDGTNGKRGEQ
 GETGPDGVRGIPGNDGQSGKPGIDGIDGTNGQPGEAGYQGGRGTRGQLGETG
 DVGQNGDRGAPGPDGSKGSAGRPLR (SEQ ID NO: 14)

[0141] The polynucleotides of SEQ ID NO: 13 was codon optimized and
 synthesized by Gen9 DNA, now Ginkgo Bioworks internal synthesis. Overlaps

between the pET28 vector and SEQ ID NO: 13 was designed to be between 30 and 40bp long and added using PCR with the enzyme PrimeStar GXL polymerase (http://www.clontech.com/US/Products/PCR/GC_Rich/PrimeSTAR_GXL_DNA_Polymerase?site=10020:22372:US). The opened pET28a vector and insert DNA (SEQ ID NO: 13) was then assembled together into the final plasmid using SGI Gibson assembly (<https://us.vwr.com/store/product/17613857/gibson-assembly-hifi-1-step-kit-synthetic-genomics-inc>). Sequence of plasmid was then verified through Sanger sequencing through Eurofins Genomics (www.eurofinsgenomics.com).

[0142] The transformed cells were cultivated in minimal media and frozen in 1.5 aliquots with glycerol at a ratio of 50:50 of cells to glycerol. One vial of this frozen culture was revived in 50ml of minimal media overnight at 37 °C, 200rpm. Cells were transferred into 300ml of minimal media and grown for 6-9 hours to reach an OD600 of 5-10.

[0143] A bioreactor was prepared with 2.7L of minimal media + glucose and 300 ml of OD600 of 5-10 culture was added to bring the starting volume to 3L. Cells were grown at 28°C, pH7 with Dissolved Oxygen maintained at 20% saturation using a cascade containing agitation, air and oxygen. pH was controlled using 28% w/w Ammonium hydroxide solution. Fermentation was run in a fed-batch mode using a DO-stat based feeding algorithm once the initial bolus of 40g/L was depleted around 13hours. After 24-26 hours of initial growth, the OD600 reached above 100. At this point, 300mL of 500g/L sucrose was added and temperature was reduced to 25C. High density culture was induced for protein production using 1mM IPTG. Fermentation was continued for another 20-24 hours and cells were harvested using a bench top centrifuge at 9000 ref, 15C for 60 minutes. Cell pellet recovered from centrifugation was resuspended in a buffer containing 0.5M NaCl and 0.1M KH₂PO₄ at pH8 in a weight by weight ratio of 2x buffer to 1x cells.

[0144] The harvested cells were disrupted in a homogenizer at 14,000 psi pressure in 2 passes. Resulting slurry contained the collagen protein along with other proteins.

[0145] The collagen was purified by acid treatment whole cells recovered from bioreactor after centrifugation and resuspension in a buffer as described above- The pH of either the homogenized slurry or the resuspended suspension was decreased to 3 using 6M Hydrochloric acid. Acidified cell slurry was incubated overnight at 4° C with mixing, followed by centrifugation. Supernatant of the acidified slurry was tested on a polyacrylamide gel and found to contain collagen in relatively high abundance

compared to starting pellet. The collagen slurry thus obtained was high in salts. To obtain volume and salt reduction, concentration and diafiltration steps were performed using an EMD Millipore Tangential Flow Filtration system with ultrafiltration cassettes of 0.1 m² each. Total area of filtration was 0.2 m² using 2 cassettes in parallel. A volume reduction of 5x and a salt reduction of 19x was achieved in the TFF stage. Final collagen slurry was run on an SDS-PAGE gel to confirm presence of the collagen. This slurry was dried using a multi-tray lyophilizer over 3 days to obtain a white, fluffy collagen powder.

[0146] The purified collagen was analyzed on an SDS-PAGE gel and was observed to run at an apparent molecular weight of 35 kilodaltons. The 35 kilodalton band does not correspond to the expected size of 22 kilodaltons. The upshift between the expected size and the apparent size is thought to be due to the GEK repeats interacting with the gel matrix. The 35 kDa band was confirmed by mass spectrometry to be the correct collagen with the GEK repeats.

15 Truncated Collagen With GDK Repeats

[0147] A jellyfish collagen with GDK repeats is disclosed below. The codon-optimized nucleotide sequence encoding this collagen is provided in SEQ ID NO: 15. The amino acid sequence is disclosed in SEQ ID NO: 16. The DsbA secretion tag is encoded by nucleotides 1-72 and encodes amino acids 1-24. The GDK repeat is encoded by nucleotides 73-126 and encodes the GDK repeats of amino acids 25-42. The truncated collagen sequence is encoded by nucleotides 127-693 and encodes amino acids 43-231.

ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
 TCGGCGGCGCAGTATGAAGATGGTGATAAAGGTGATAAGGGCGACAAAG
 25 GTGACAAAGGCGATAAGGGTGATAAAGGTCCGCAGGGTGTTGTTGGTGCA
 GATGGTAAAGACGGTACCCCGGGTAATGCAGGTCAGAAAGGTCCGTCAG
 GTGAACCTGGCAGCCCTGGTAAAGCAGGTAGTGCCGGTGAGCAGGGTCCG
 CCGGGCAAAGATGGTAGTAATGGTGAGCCGGGTAGCCCTGGCAAAGAAG
 GTGAACGTGGTCTGGCAGGACCGCCGGGTCCTGATGGTCGCCGCGGTGAA
 30 ACGGGTTCACCGGGTATTGCCGGTGCCCTGGGTAAACCAGGTCTGGAAGG
 TCCGAAAGGTTATCCTGGTCTGCGCGGTCGTGATGGTACCAATGGCAAAC
 GTGGCGAACAGGGCGAAACCGGTCCAGATGGTGTTTCGTGGTATTCCGGGT
 AACGATGGTCAGAGCGGTAAACCGGGCATTGATGGTATTGATGGCACCAA
 TGGTCAGCCTGGCGAAGCAGGTTATCAGGGTGGTCGCGGTACCCGTGGTC

AGCTGGGTGAAACAGGTGATGTTGGTCAGAATGGTGATCGCGGCGCACCG
GGTCCGGATGGTAGCAAAGGTAGCGCCGGTCTCCGGGTTTACGTtaa (SEQ
ID NO: 15)

MKKIWLALAGLVLAFFSASAAQYEDGDKGDKGDKGDKGDKGDKGPQGVVG
5 ADGKDGTGPNAGQKGPSGEPGSPGKAGSAGEQGPPGKDGSNGEPGSPGKEG
ERGLAGPPGPDGRRGETGSPGIAGALGKPGLEGPKGYPLRGRDGTNGKRGE
QGETGPDGVRGIPGNDGQSGKPGIDGIDGTNGQPGEAGYQGGRGTRGQLGET
GDVGQNGDRGAPGPDGSKGSAGRPGLR (SEQ ID NO: 16)

[0148] The polynucleotides of SEQ ID NO: 15 was codon optimized and
10 synthesized by Gen9 DNA, now Ginkgo Bioworks internal synthesis. Overlaps
between the pET28 vector and SEQ ID NO: 15 was designed to be between 30 and
40bp long and added using PCR with the enzyme PrimeStar GXL polymerase
(http://www.clontech.com/US/Products/PCR/GC_Rich/PrimeSTAR_GXL_DNA_Polymerase?site=10020:22372:US). The opened pET28a vector and insert DNA (SEQ
15 ID NO: 15) was then assembled together into the final plasmid using SGI Gibson
assembly (<https://us.vwr.com/store/product/17613857/gibson-assembly-hifi-1-step-kit-synthetic-genomics-inc>). Sequence of plasmid was then verified through sanger
sequencing through Eurofins Genomics (www.eurofinsgenomics.com).

[0149] The transformed cells were cultivated in minimal media and frozen in 1.5
20 aliquots with glycerol at a ratio of 50:50 of cells to glycerol. One vial of this frozen
culture was revived in 50ml of minimal media overnight at 37 °C, 200rpm. Cells were
transferred into 300ml of minimal media and grown for 6-9 hours to reach an OD600
of 5-10.

[0150] A bioreactor was prepared with 2.7L of minimal media + glucose and 300
25 ml of OD600 of 5-10 culture was added to bring the starting volume to 3L. Cells were
grown at 28°C, pH7 with Dissolved Oxygen maintained at 20% saturation using a
cascade containing agitation, air and oxygen. pH was controlled using 28% w/w
Ammonium hydroxide solution. Fermentation was run in a fed-batch mode using a
DO-stat based feeding algorithm once the initial bolus of 40g/L was depleted around
30 13hours. After 24-26hours of initial growth, the OD600 reached above 100. At this
point, 300mL of 500g/L sucrose was added and temperature was reduced to 25C.
High density culture was induced for protein production using 1mM IPTG.
Fermentation was continued for another 20-24 hours and cells were harvested using a
bench top centrifuge at 9000 rcf, 15C for 60 minutes. Cell pellet recovered from

centrifugation was resuspended in a buffer containing 0.5M NaCl and 0.1M KH₂PO₄ at pH8 in a weight by weight ratio of 2x buffer to 1x cells.

[0151] The harvested cells were disrupted in a homogenizer at 14,000 psi pressure in 2 passes. Resulting slurry contained the collagen protein along with other proteins.

5 [0152] The collagen was purified by acid treatment of whole cells recovered from bioreactor after centrifugation and resuspension in a buffer as described above. The pH of either the homogenized slurry was decreased to 3 using 6M Hydrochloric acid. Acidified cell slurry was incubated overnight at 4° C with mixing, followed by centrifugation. Supernatant of the acidified slurry was tested on a polyacrylamide gel
10 and found to contain collagen in relatively high abundance compared to starting pellet. The collagen slurry thus obtained was high in salts. To obtain volume and salt reduction, concentration and diafiltration steps were performed using an EMD Millipore Tangential Flow Filtration system with ultrafiltration cassettes of 0.1 m² each. Total area of filtration was 0.2 m² using 2 cassettes in parallel. A volume
15 reduction of 5x and a salt reduction of 19x was achieved in the TFF stage. Final collagen slurry was run on an SDS-PAGE gel to confirm presence of the collagen. This slurry was dried using a multi-tray lyophilizer over 3 days to obtain a white, fluffy collagen powder.

[0153] The purified collagen was analyzed on an SDS-PAGE gel and was observed
20 to run at an apparent molecular weight of 35 kilodaltons. The 35 kilodalton band does not correspond to the expected size of 22 kilodaltons. The upshift between the expected size and the apparent size is thought to be due to the GDK repeats interacting with the gel matrix. The 35 kDa band was confirmed by mass spectrometry to be the correct collagen with the GDK repeats.

25 **Truncated Collagen with DsbA secretion tag-His tag-Linker-Thrombin cleavage site and GFP Beta-lactamase fusion (version 1):**

[0154] A jellyfish collagen with DsbA secretion tag-His tag-Linker-Thrombin cleavage site and GFP Beta-lactamase fusion is disclosed below. The codon-optimized nucleotide sequence encoding this collagen is provided in SEQ ID NO: 17.
30 The amino acid sequence is disclosed in SEQ ID NO: 18. The DsbA secretion tag is encoded by nucleotides 1-72 and encodes amino acids 1-24. The His tag is encoded by nucleotides 73-99 and encodes a 9 histidine tag of amino acids 25-33. The linker is encoded by nucleotides 100-111 and encodes amino acids 34-37. The thrombin cleavage side is encoded by nucleotides 112-135 and encodes amino acids 38-45. The

- green fluorescent protein (GFP) with linker is encoded by nucleotides 136-873 and encodes amino acids 46-291. The truncated collagen sequence is encoded by nucleotides 874-1440 and encodes amino acids 292-480. The Beta-lactamase with linker is encoded by nucleotides 1441-2232 and encodes amino acids 481-744. The
- 5 Beta-lactamase was properly targeted to the periplasmic space even though the polypeptide did not have an independent secretion tag. The DsbA secretion tag directed the entire transcript (Truncated Collagen with DsbA secretion tag-His tag-Linker-Thrombin cleavage site and GFP Beta-lactamase fusion protein) to the periplasmic space and the Beta-lactamase functioned properly.
- 10 ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
TCGGCGGCGCAGTATGAAGATCACCATCACCACCACCACCATCACCCTC
TGGCTCGAGCCTGGTGCCGCGCGGCAGCCATATGTCTGGCTCGAGCAGTA
AAGGTGAAGAACTGTTCAACGGTGTGTTCCGATCCTGGTTGAACTGGAT
GGTGATGTTAACGGCCACAAATTCTCTGTTCGTGGTGAAGGTGAAGGTGA
15 TGCAACCAACGGTAAACTGACCCTGAAATTCATCTGCACTACCGGTAAAC
TGCCGGTTCATGGCCGACTCTGGTGACTACCCTGACCTATGGTGTTCAGT
GTTTTTCTCGTTACCCGGATCACATGAAGCAGCATGATTTCTTCAAATCTG
CAATGCCGGAAGGTTATGTACAGGAGCGCACCATTCTTTCAAAGACGAT
GGCACCTACAAAACCCGTGCAGAGGTTAAATTTGAAGGTGATACTCTGGT
20 GAACCGTATTGAACTGAAAGGCATTGATTTCAAAGAGGACGGCAACATCC
TGGGCCACAACTGGAATATAACTTCAACTCCCATAACGTTTACATCACC
GCAGACAAACAGAAGAACGGTATCAAAGCTAACTTCAAAATTCGCCATAA
CGTTGAAGACGGTAGCGTACAGCTGGCGGACCACTACCAGCAGAACACTC
CGATCGGTGATGGTCCGGTCTGCTGCCGGATAACCACTACCTGTCCACCC
25 AGTCTaaaCTGTCCAAAGACCCGAACGAAAAGCGCGACCACATGGTGCTGC
TGGAGTTCGTTACTGCAGCAGGTATCACGCACGGCATGGATGAACTCTAC
AAATCTGGCGCGCCGGGCGGTCCGCAGGGTGTGTTGGTGCAGATGGTAA
AGACGGTACCCCGGGTAATGCAGGTCAGAAAGGTCCGTCAGGTGAACCTG
GCAGCCCTGGTAAAGCAGGTAGTGCCGGTGAGCAGGGTCCGCCGGGCAA
30 AGATGGTAGTAATGGTGAGCCGGTAGCCCTGGCAAAGAAGGTGAACGT
GGTCTGGCAGGACCGCCGGGTCCTGATGGTCGCCGCGGTGAAACGGGTTC
ACCGGGTATTGCCGGTGCCCTGGGTAAACCAGGTCTGGAAGGTCCGAAAG
GTTATCCTGGTCTGCGCGGTCTGTGATGGTACCAATGGCAAACGTGGCGAA
CAGGGCGAAACCGGTCCAGATGGTGTTTCGTGGTATTCGGGGTAACGATGG

- TCAGAGCGGTAAACCGGGCATTGATGGTATTGATGGCACCAATGGTCAGC
 CTGGCGAAGCAGGTTATCAGGGTGGTCGCGGTACCCGTGGTCAGCTGGGT
 GAAACAGGTGATGTTGGTCAGAATGGTGATCGCGGCGCACCGGGTCCGGA
 TGGTAGCAAAGGTAGCGCCGGTCTCCGGGTTTACGTcaccagaaacgtggtgaaa
 5 gtaaaagatgctgaagatcagttgggtgcacgagtggttacatgaactggatctcaacagcggtaagatcctgagagtt
 ttgccccgaagaacgtttccaatgatgagcacttttaagttctgctatgtggcgcggtattatccgtattgacgccgggc
 aagagcaactcggtcgcccatatactattctcagaatgacttggtgagtactaccagtcacagaaaagcatcttacgga
 tggcatgacagtaagagaattatgcagtgtgccataacctagtgataaactgcggccaacttactctgacaacgac
 ggaggaccgaaggagctaaccgctttttgcacaacatgggggatcatgtaactcgcttgatcgttgggaaccgggagctg
 10 aatgaaggcatacacaacgacgagcgtgacaccacgatgcctgtagcaatggcaacaacgttcgcaactattaactgg
 cgaactacttacttagcttccccgcaacaattaatagactggatggaggcggataaagttgcaggaccacttctgcgctcg
 gcccttcgggtggtgtgttattgctgataaatctggagccggtgagcgtgggtctcgcggtatcattgcagcactggggc
 cagatggtaagccctcccgtagttagtctacacgacggggagtcaggcaactatggatgaacgaaatagacagatcg
 ctgagataggtgcctcactgattaagcattggtaa (SEQ ID NO: 17)
- 15 MKKIWLALAGLVLAFSASAAQYEDHHHHHHHHHSGSSLVPRGSHMSGSSSK
 GEELFTGVVPILVELDGDVNGHKFSVRGEGEGDATNGKLTLKFICTTGKLPVP
 WPTLVTTLTYGVCFSRYPDHMKQHDFFKSAMPEGYVQERTISFKDDGTYK
 TRAEVKFEGDTLVNRIELKGIDFKEDGNILGHKLEYNFNNSHNVYITADKQKNG
 IKANFKIRHNVEDGSVQLADHYQQNTPIGDGPVLLPDNHYLSTQSKLSKDPNE
 20 KRDHMLLEFVTAAGITHGMDELKSGAPGGPQGVVADGKDGTGPNAGQ
 KGPSGEPGSPGKAGSAGEQGPPGKDGSNGEPGSPGKEGERGLAGPPGPDGRR
 GETGSPGIAGALGKPGLEGPKGYPLRGRDGTNGKRGEQGETGPDGVRGIPG
 NDGQSGKPGIDGIDGTNGQPGEAGYQGGRGTRGQLGETGDVGQNGDRGAPG
 PDGSKGSAGRPLRHPETLVKVKDAEDQLGARVGYIELDLNSGKILESFRPEE
 25 RFPMMSSTFKVLLCGAVLSRIDAGQEQLGRRHYQNLDLVEYSPVTEKHLTDG
 MTVRELCSAAITMSDNTAANLLLTIGGPKELTAF LHNMGDHSVTRLDRWEPE
 LNEAIPNDERDTMPVAMATTLRKLLTGELLTLASRQQLIDWMEADKVAGPL
 LRSALPAGWFIADKSGAGERGSRGIIAALGPDGKPSRIVVIYTTGSQATMDER
 NRQIAEIGASLIKHW (SEQ ID NO: 18)
- 30 **[0155]** The polynucleotides of SEQ ID NO: 17 was constructed by assembling
 several DNA fragments. The collagen containing sequence was codon optimized and
 synthesized by Gen9 DNA, now Ginkgo Bioworks internal synthesis. The GFP was
 also synthesized by Gen9. The Beta-lactamase was cloned out of the plasmid pKD46
 (<http://cgsc2.biology.yale.edu/Strain.php?ID=68099>) using PCR with the enzyme

PrimeStar GXL polymerase

(http://www.clontech.com/US/Products/PCR/GC_Rich/PrimeSTAR_GXL_DNA_Polymerase?sitex=10020:22372:US). Overlaps between the pET28 vector, GFP, Collagen, and Beta-lactamase was designed to be between 30 and 40bp long and added using PCR with the enzyme PrimeStar GXL polymerase. The opened pET28a vector and inserts were then assembled together into the final plasmid using SGI Gibson assembly (<https://us.vwr.com/store/product/17613857/gibson-assembly-hifi-1-step-kit-synthetic-genomics-inc>). Sequence of plasmid was then verified through sanger sequencing through Eurofins Genomics (www.eurofinsgenomics.com).

10 [0156] The transformed cells were cultivated in minimal media and frozen in 1.5 aliquots with glycerol at a ratio of 50:50 of cells to glycerol. One vial of this frozen culture was revived in 50ml of minimal media overnight at 37 °C, 200rpm. Cells were transferred into 300ml of minimal media and grown for 6-9 hours to reach an OD600 of 5-10.

15 [0157] A bioreactor was prepared with 2.7L of minimal media + glucose and 300 ml of OD600 of 5-10 culture was added to bring the starting volume to 3L. Cells were grown at 28°C, pH7 with Dissolved Oxygen maintained at 20% saturation using a cascade containing agitation, air and oxygen. pH was controlled using 28% w/w Ammonium hydroxide solution. Fermentation was run in a fed-batch mode using a DO-stat based feeding algorithm once the initial bolus of 40g/L was depleted around 20 13hours. After 24-26hours of initial growth, the OD600 reached above 100. At this point, 300mL of 500g/L sucrose was added and temperature was reduced to 25C. High density culture was induced for protein production using 1mM IPTG. Fermentation was continued for another 20-24 hours and cells were harvested using a bench top centrifuge at 9000 ref, 15C for 60 minutes. Cell pellet recovered from 25 centrifugation was resuspended in a buffer containing 0.5M NaCl and 0.1M KH₂PO₄ at pH8 in a weight by weight ratio of 2x buffer to 1x cells.

[0158] The harvested cells were disrupted in a homogenizer at 14,000 psi pressure in 2 passes. Resulting slurry contained the collagen protein along with other proteins.

30 [0159] The collagen was purified by acid treatment of non-homogenized whole cells recovered from the bioreactor after centrifugation and resuspension in the buffer described above. The pH of the resuspended suspension was decreased to 3 using 6M Hydrochloric acid. Acidified cell slurry was incubated overnight at 4° C with mixing, followed by centrifugation. The pH was then raised to 9 using 10N NaOH and the

supernatant of the slurry was tested on a polyacrylamide gel and found to contain collagen in relatively high abundance compared to starting pellet. The collagen slurry thus obtained was high in salts. To obtain volume and salt reduction, concentration and diafiltration steps were performed using an EMD Millipore Tangential Flow

5 Filtration system with ultrafiltration cassettes of 0.1 m² each. Total area of filtration was 0.2 m² using 2 cassettes in parallel. A volume reduction of 5x and a salt reduction of 19x was achieved in the TFF stage. Final collagen slurry was run on an SDS-PAGE gel to confirm presence of the collagen. This slurry was dried using a multi-tray lyophilizer over 3 days to obtain a white, fluffy collagen powder.

- 10 **[0160]** The purified collagen-GFP-Beta-lactamase fusion protein was analyzed on an SDS-PAGE gel and was observed to run at an apparent molecular weight of 90 kilodaltons. The expected size of the fusion protein is 85 kd. The 90 kDa band was confirmed by mass spectrometry to be the correct collagen fusion protein.

Truncated Collagen with DsbA secretion tag-His tag-Linker-Thrombin cleavage site and GFP Beta-lactamase fusion (version 2):

15

- [0161]** A jellyfish collagen with DsbA secretion tag-His tag-Linker-Thrombin cleavage site and GFP Beta-lactamase fusion is disclosed below. The codon-optimized nucleotide sequence encoding this collagen is provided in SEQ ID NO: 19. The amino acid sequence is disclosed in SEQ ID NO: 20. The DsbA secretion tag is
- 20 encoded by nucleotides 1-72 and encodes amino acids 1-24. The His tag is encoded by nucleotides 73-99 and encodes a 9 histidine tag of amino acids 25-33. The linker is encoded by nucleotides 100-111 and encodes amino acids 34-37. The thrombin cleavage site is encoded by nucleotides 112-135 and encodes amino acids 38-45. The green fluorescent protein (GFP) with linker is encoded by nucleotides 136-873 and
- 25 encodes amino acids 46-291. The truncated collagen sequence is encoded by nucleotides 874-1440 and encodes amino acids 292-480. The Beta-lactamase with linker is encoded by nucleotides 1441-2232 and encodes amino acids 481-744.

ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
TCGGCGGCGCAGTATGAAGATCACCATCACCACCACCACCATCACCCTC
30 TGGCTCGAGCCTGGTGCCGCGCGGCAGCCATATGTCTGGCTCGAGCAGTA
AAGGTGAAGAACTGTTCAACGGTGTGTTCCGATCCTGGTTGAACTGGAT
GGTGATGTTAACGGCCACAAATTCTCTGTTCGTGGTGAAGGTGAAGGTGA
TGCAACCAACGGTAACTGACCCTGAAATTCATCTGCACTACCGGTAAAC
TGCCGGTTCCATGGCCGACTCTGGTGACTACCCTGACCTATGGTGTTCAGT

GTTTTTCTCGTTACCCGGATCACATGAAGCAGCATGATTTCTTCAAATCTG
CAATGCCGGAAGGTTATGTACAGGAGCGCACCATTTCTTTCAAAGACGAT
GGCACCTACAAAACCCGTGCAGAGGTTAAATTTGAAGGTGATACTCTGGT
GAACCGTATTGAACTGAAAGGCATTGATTTCAAAGAGGACGGCAACATCC
5 TGGGCCACAACTGGAATATAACTTCAACTCCCATAACGTTTACATCACC
GCAGACAAACAGAAGAACGGTATCAAAGCTAACTTCAAAATTCGCCATAA
CGTTGAAGACGGTAGCGTACAGCTGGCGGACCACTACCAGCAGAACACTC
CGATCGGTGATGGTCCGGTCTGTCTGCCGGATAACCACTACCTGTCCACCC
AGTCT^{aaa}CTGTCCAAAGACCCGAACGAAAAGCGCGACCACATGGTGCTGC
10 TGGAGTTCGTTACTGCAGCAGGTATCACGCACGGCATGGATGAACTCTAC
AAATCTGGCGCGCCGGGCGGTCCGCAGGGTGTTGTTGGTGCAGATGGTAA
AGACGGTACCCCGGGTAATGCAGGTCAGAAAGGTCCGTCAGGTGAACCTG
GCAGCCCTGGTAAAGCAGGTAGTGCCGGTGAGCAGGGTCCGCCGGGCAA
AGATGGTAGTAATGGTGAGCCGGGTAGCCCTGGCAAAGAAGGTGAACGT
15 GGTCTGGCAGGACCGCCGGGTCCTGATGGTCGCCGCGGTGAAACGGGTTC
ACCGGGTATTGCCGGTGCCCTGGGTAAACCAGGTCTGGAAGGTCCGAAAG
GTTATCCTGGTCTGCGCGGTCTGTGATGGTACCAATGGCAAACGTGGCGAA
CAGGGCGAAACCGGTCCAGATGGTGTTCTGTGGTATTCCGGGTAAACGATGG
TCAGAGCGGTAAACCGGGCATTGATGGTATTGATGGCACCAATGGTCAGC
20 CTGGCGAAGCAGGTTATCAGGGTGGTCGCGGTACCCGTGGTCAGCTGGGT
GAAACAGGTGATGTTGGTCAGAATGGTGATCGCGGCGCACCGGGTCCGGA
TGGTAGCAAAGGTAGCGCCGGTCTGCCGGGTTTACGT^caccagaaacgtggtgaa
gtaaaagatgctgaagatcagttgggtgcacgagtggggttacatgaactggatctcaacagcggtgaagatccttgagagtt
ttcgccccgaagaacgtttccaatgatgagcacttttaaagttctctatgtggcggtattatccgtattgacgcggg
25 aagagcaactcggtcgccgatacactattctcagaatgacttgggtgagtactaccagtcacagaaaagcatcttacgga
tggeatgacagtaagagaattatgcagtgctgccataacctgagtgataacactgcggccaacttactctgacaacgate
ggaggaccgaaggagctaaccgctttttgcacaacatgggggatcatgtaactgccttgatcgttgggaaccggagctg
aatgaagccataccaaacgacgagcgtgacaccagatgcctgtagcaatggcaacaacgttgcgcaactattaactgg
cgaactacttactctagcttcccggaacaataatagactggatggaggcggataaagttgcaggaccacttctgcgctcg
30 gcccttcggctggctggtttattgtgataaatctggagccggtgagcgtgggtctcgcggtatcattgagcactggggc
cagatggtgaagccccccgtatcgtatctacacgacggggagtcaggcaactatggatgaacgaaatagacagatcg
ctgagataggtgcctcactgattaagcattggtaa (SEQ ID NO: 19)
MKKIWLALAGLVLAFSASAAQYEDHHHHHHHHHSGSSLVPRGSHMSGSSSK
GEELFTGVVPILVELDGDVNGHKFSVRGEGEGDATNGKLTLKFICTTGKLPVP

WPTLVTTLTYGVCFSRYPDHMKQHDFFKSAMPEGYVQERTISFKDDGTYK
 TRAEVKFEGDTLVNRIELKGIDFKEDGNILGHKLEYNFNHNVYITADKQKNG
 IKANFKIRHNVEDGSVQLADHYQQNTPIGDGPVLLPDNHYLSTQSKLSKDPNE
 KRDHMVLLFVTAAGITHGMDELKSGAPGGPQGVVGADGKDGTGPNAGQ
 5 KGPSGEPGSPGKAGSAGEQGPPGKDGSNGEPGSPGKEGERGLAGPPGPDGRR
 GETGSPGIAGALGKPGLEGPKGYPLRGRDGTNGKRGEQGETGPDGVRGIPG
 NDGQSGKPGIDGIDGTNGQPGEAGYQGGRGTRGQLGETGDVGQNGDRGAPG
 PDGSKGSAGRPGLRHPETLVKVKDAEDQLGARVGYIELDLNSGKILESFRPEE
 RFPMMSTFKVLLCGAVLSRIDAGQEQLGRRRIHYSQNDLVEYSPVTEKHLTDG
 10 MTVRELCSAAITMSDNTAANLLLTIGGPKELTAFLEHNMGDHVTRLDRWEPE
 LNEAIPNDERDTTMPVAMATTLRKLLTGELLTLASRQQLIDWMEADKVAGPL
 LRSALPAGWFIADKSGAGERGSRGIIAALGPDGKPSRIVVIYTTGSQATMDER
 NRQIAEIGASLIKHW (SEQ ID NO: 20)

Example 4: Production of Full-Length Elastin

15 **[0162]** Full length human elastin were expressed as described below. The wild-
 type, full length amino acid sequence of human elastin is provided below.
 MAGLTAAAPRPGVLLLLLSILHPSRPGGVPGAIPGGVPGGVFYPGAGLGALG
 GGALGPGGKPLKVPVGGLAGAGLGAGLGAFPAVTFPGALVPGGVADAAAAY
 KAAKAGAGLGGVPGVGGLGVSAAGVVPQPGAGVKPGKVPGVGLPGVYPGG
 20 VLPGARFPGVGVLPGVPTGAGVKPKAPGVGGAFAGIPGVGPFGGPQPGVPLG
 YPIKAPKLPGGYGLPYTTGKLPYGYGPGGVAGAAGKAGYPTGTGVGPQAAA
 AAAAKAAAKFGAGAAGVLPGVGGAGVPGVPGAIPGIGGIAGVGTPAAAAAA
 AAAAKAAKYGAAAGLVPGGPGFGPGVVGVPAGVPGVGVPGAGIPVPGA
 GIPGAAPGVVSPEAAAKAAAKAAKYGARPGVGVGGIPTYGVGAGGFPGFG
 25 VGVGGIPGVAGVPGVGGVPGVGGVPGVGSPEAQAAAAAKAAKYGAAGAG
 VLGGLVPGPQAAVPGVPGTGGVPGVGTAAAAAKAAAKAAQFGLVPGVGV
 APGVGVAPGVGVAPGVGLAPGVGVAPGVGVAPGVGVAPGIGPGGVAAAAK
 SAAKVAAKAQLRAAAGLGAGIPGLGVGVGPGLGVGAGVPGLGVGAGVPG
 FGAGADEGVRRSLSPELREGDPSSSQHLPSTPSSPRVPGALAAAKAAKYGAA
 30 VPGVLGGLGALGGVGIPGGVVAGPAAAAAAKAAAKAAQFGLVGAAGLG
 GLGVGGLGVPGVGGGIPPAAAAKAAKYGAAGLGGVLGGAGQFPLGGVA
 ARPGFGLSPIFPGGACLGKACGRKRK (SEQ ID NO: 21)

<http://www.uniprot.org/uniprot/P15502>

[0163] The non-codon optimized polynucleotide sequence encoding the full length elastin is disclosed below. In SEQ ID NO: 22, nucleotides 1-78 encode the DsbA secretion tag and nucleotides 79-2358 encode the full length human elastin.

```
ATGGCGGGTCTGACGGCGGCGGCCCGCGGCCCGGAGTCCTCCTGCTCCT
5  GCTGTCCATCCTCCACCCCTCTCGGCCTGGAGGGGTCCCTGGGGCCATTCC
  TGGTGGAGTTCTTGGAGGAGTCTTTTATCCAGGGGCTGGTCTCGGAGCCCT
  TGGAGGAGGAGCGCTGGGGCCTGGAGGCAAACCTCTTAAGCCAGTTCCCG
  GAGGGCTTGCGGGTGCTGGCCTTGGGGCAGGGCTCGGCGCCTTCCCCGCA
  GTTACCTTTCCGGGGGCTCTGGTGCCTGGTGGAGTGGCTGACGCTGCTGCA
10  GCCTATAAAGCTGCTAAGGCTGGCGCTGGGCTTGGTGGTGTCCAGGAGT
  TGGTGGCTTAGGAGTGTCTGCAGGTGCGGTGGTTCCCTCAGCCTGGAGCCG
  GAGTGAAGCCTGGGAAAGTGCCGGGTGTGGGGCTGCCAGGTGTATACCCA
  GGTGGCGTGCTCCCAGGAGCTCGGTTCCCCGGTGTGGGGGTGCTCCCTGG
  AGTTCCTTCCAGTGGAGCAGGAGTTAAGCCCAAGGCTCCAGGTGTAGGTGGAG
15  CTTTTGCTGGAATCCCAGGAGTTGGACCTTTGGGGGACCGCAACCTGGA
  GTCCCACTGGGGTATCCCATCAAGGCCCCCAAGCTGCCTGGTGGCTATGG
  ACTGCCCTACACCACAGGGAACTGCCCTATGGCTATGGGCCCCGGAGGAG
  TGGCTGGTGCAGCGGGCAAGGCTGGTTACCCAACAGGGACAGGGGTTGGC
  CCCCAGGCAGCAGCAGCAGCGGCAGCTAAAGCAGCAGCAAAGTTCGGTG
20  CTGGAGCAGCCGGAGTCCTCCCTGGTGTGGAGGGGCTGGTGTTCCTGGC
  GTGCCTGGGGCAATTCCTGGAATTGGAGGCATCGCAGGCGTTGGGACTCC
  AGCTGCAGCTGCAGCTGCAGCAGCAGCCGCTAAGGCAGCCAAAGTATGGA
  GCTGCTGCAGGCTTAGTGCCTGGTGGGCCAGGCTTTGGCCCCGGGAGTAGT
  TGGTGTCCCAGGAGCTGGCGTTCCAGGTGTTGGTGTCCCAGGAGCTGGGA
25  TTCCAGTTGTCCCAGGTGCTGGGATCCCAGGTGCTGCGGTTCCAGGGGTTG
  TGTCACCAGAAGCAGCTGCTAAGGCAGCTGCAAAGGCAGCCAAATACGG
  GGCCAGGCCCGGAGTCGGAGTTGGAGGCATTCTACTTACGGGGTTGGAG
  CTGGGGGCTTTCCCGGCTTGGTGTGCGGAGTCGGAGGTATCCCTGGAGTCG
  CAGGTGTCCCTGGTGTGCGGAGGTGTTCCCGGAGTCGGAGGTGTCCCGGGA
30  GTTGGCATTTCCCCCGAAGCTCAGGCAGCAGCTGCCGCCAAGGCTGCCAA
  GTACGGTGCTGCAGGAGCAGGAGTGCTGGGTGGGCTAGTGCCAGGTCCCC
  AGGCGGCAGTCCCAGGTGTGCCGGGCACGGGAGGAGTGCCAGGAGTGGG
  GACCCCAGCAGCTGCAGCTGCTAAAGCAGCCGCCAAAGCCGCCAGTTTG
  GGTTAGTTCCTGGTGTGCGCGTGGCTCCTGGAGTTGGCGTGGCTCCTGGTG
```

TCGGTGTGGCTCCTGGAGTTGGCTTGGCTCCTGGAGTTGGCGTGGCTCCTG
 GAGTTGGTGTGGCTCCTGGCGTTGGCGTGGCTCCCGGCATTGGCCCTGGTG
 GAGTTGCAGCTGCAGCAAAATCCGCTGCCAAGGTGGCTGCCAAAGCCCAG
 CTCCGAGCTGCAGCTGGGCTTGGTGCTGGCATCCCTGGACTTGGAGTTGGT
 5 GTCGGCGTCCCTGGACTTGGAGTTGGTGCTGGTGTTCCCTGGACTTGGAGTT
 GGTGCTGGTGTTCCCTGGCTTCGGGGCAGGTGCAGATGAGGGAGTTAGGCG
 GAGCCTGTCCCTGAGCTCAGGGAAGGAGATCCCTCCTCCTCTCAGCACC
 TCCCCAGCACCCCTCATCACCCAGGGTACCTGGAGCCCTGGCTGCCGCT
 AAAGCAGCCAAATATGGAGCAGCAGTGCCTGGGGTCCTTGGAGGGCTCGG
 10 GGCTCTCGGTGGAGTAGGCATCCCAGGCGGTGTGGTGGGAGCCGGACCCG
 CCGCCGCCGCTGCCGCAGCCAAAGCTGCTGCCAAAGCCGCCAGTTTGGC
 CTAGTGGGAGCCGCTGGGCTCGGAGGACTCGGAGTCCGAGGGCTTGGAGT
 TCCAGGTGTTGGGGGCCTTGGAGGTATACCTCCAGCTGCAGCCGCTAAAG
 CAGCTAAATACGGTGCTGCTGGCCTTGGAGGTGTCCTAGGGGGTGCCGGG
 15 CAGTTCCCAGTTGGAGGAGTGGCAGCAAGACCTGGCTTCGGATTGTCTCC
 CATTTTCCCAGGTGGGGCCTGCCTGGGGAAAGCTTGTGGCCGGAAGAGAA
 AATGA (SEQ ID NO: 22)

Codon optimized Elastin with DsbA secretion tag-His tag-Linker-Thrombin cleavage site

20 **[0164]** The codon optimized polynucleotide sequence encoding the full length
 human elastin with DsbA secretion tag-His tag-Linker-Thrombin cleavage site is
 disclosed below. In SEQ ID NO: 23: nucleotides 1-72 encode the DsbA secretion tag
 encoding amino acids 1-24 of SEQ ID NO: 24; nucleotides 73-99 encode the 9 His
 tag encoding amino acids 25-33 of SEQ ID NO: 24; nucleotides 100-111 encode the
 25 linker encoding amino acids 34-37 of SEQ ID NO: 24; nucleotides 112-135 encode
 the thrombin cleavage tag encoding amino acids 38-45 of SEQ ID NO: 24;
 nucleotides 136-2415 encode the amino acids 46-805 of the full length human elastin
 of SEQ ID NO: 24.

ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
 30 TCGGCGGCGCAGTATGAAGATCACCATCACCACCACCACCATCACCCTC
 TGGCTCGAGCCTGGTGCCGCGCGGCAGCCATATGGGTGGCGTACCAGGCG
 CAATTCCTGGGGTGTCCCAGGCGGTGTTTTTTATCCGGGCGCCGGTCTTG
 GCGCACTGGGTGGCGGTGCACTGGGCCCCGGGCGGCAAACCGCTGAAACC
 GGTACCAGGTGGTTTAGCAGGCGCCGGCTTAGGCGCAGGTCTGGGAGCAT

TTCCGGCAGTTACCTTTCCAGGGGCACTGGTTCCTGGAGGTGTGGCCGATG
CAGCCGCGGCATATAAAGCCGCTAAAGCCGGTGCGGGTTTAGGAGGCGTC
CCAGGTGTCGGTGGCCTGGGTGTTAGCGCCGGTGCAGTTGTTCCGCAGCC
GGGAGCAGGGGTAAACCTGGTAAAGTGCCGGGAGTAGGTCTGCCAGGC
5 GTTTATCCTGGTGGTGTGTTTGCCGGGTGCCCCGTTTCCGGGCGTTGGTGTTC
TTCCAGGCGTGCCGACCGGAGCCGGTGTTAAACCGAAAGCCCCCGGTGTT
GGAGGTGCATTTGCAGGCATCCCGGGAGTTGGCCCCGTTTGGTGGTCCGCA
ACCTGGGGTTCCGTTAGGTTATCCGATTAAAGCACCGAAACTGCCCGGCG
GTTATGGTCTGCCGTACACAACCGGTAAACTGCCGTATGGTTATGGCCCCG
10 GGTGGAGTTGCGGGTGACAGCAGGTAAAGCGGGTTATCCTACCGGAACCGG
TGTAAGTCCGCAGGCCGCTGCTGCCGCCGCCGCAAAAGCAGCGGCTAAAT
TTGGCGCCGGAGCAGCGGGTGTTCTGCCTGGAGTTGGTGGTGCGGGCGTG
CCAGGGGTACCTGGTGCAATTCCGGGTATTGGTGGTATTGCCGGTGTCGG
CACCCCGGCCGCGGCAGCTGCGGCAGCGGCGGCTGCCAAAGCTGCTAAAT
15 ACGGTGCCGCGGCGGGTCTGGTGCCAGGAGGTCCGGGTTTTGGTCCGGGA
GTGGTTGGCGTGCTGGCGCAGGCGTTCCTGGTGTGGGCGTTCAGGTGC
AGGGATTCCTGTTGTGCCTGGTGCCGGTATTCCCGGCGCGGCCGTTCCGGG
GGTGGTTAGCCCGGAAGCCGCAGCGAAGGCTGCGGCAAAGGCAGCAAAG
TATGGCGCACGCCCAGGAGTCGGCGTGGGTGGTATCCCGACCTATGGGGT
20 GGGCGCAGGGGGTTTTCTGGTTTCGGCGTAGGTGTAGGAGGTATACCGG
GCGTGGCCGGTGTACCAGGGGTTGGTGGCGTCCCTGGTGTGGCGGTGTG
CCAGGTGTTGGTATTTACCGGAAGCACAGGCAGCAGCCGCAGCTAAGGC
AGCGAAATATGGTGCCGCCGGCGCAGGAGTTTTAGGTGGGCTGGTTCGGG
GCCCGCAGGCAGCTGTGCCGGGGGTTCCAGGCACCGGTGGTGTCCCTGGA
25 GTCGGTACGCCGGCTGCAGCGGCAGCCAAAGCGGCTGCGAAAGCAGCAC
AGTTTGGCTTAGTACCGGGTGTGGGAGTTGCCCCCGGCGTTGGCGTTGCTC
CAGGGGTGGGTGTTGCTCCTGGCGTCGGTCTGGCTCCTGGAGTGGGCGTA
GCACCCGGTGTGGGGGTGGCCCCGGGTGTTGGGGTTGCACCGGGTATCGG
TCCGGGCGGTGTCGCAGCAGCAGCTAAAAGCGCGGCGAAAGTTGCGGCC
30 AAAGCCCAACTGCGCGCCGCCGCGGGCCTCGGTGCAGGTATTCCGGGGCT
GGGTGTCGGAGTTGGAGTCCCGGGTTTGGGCGTGGGCGCGGGAGTTCCGG
GACTGGGAGTGGGTGCCGGAGTTCCTGGCTTTGGTGCAGGCGCAGATGAA
GGTGTTCGTCTAGCCTGAGTCCGGAAGTGCCTGAAGGTGATCCGAGTAG
CAGCCAGCATCTGCCGAGCACCCCGAGCAGCCCGCGTGTCCGGGTGCAT

- TAGCTGCAGCAAAAGCCGCCAAGTATGGTGCAGCCGTGCCGGGCGTCTTA
GGTGGTCTGGGCGCCCTGGGTGGTGTAGGCATTCCGGGAGGTGTTGTGGG
TGCAGGACCGGCCGCCGCAGCTGCGGCCGCCAAAGCAGCTGCAAAAGCG
GCCCAGTTTGGTTTAGTGGGCGCCGCAGGTTTAGGCGGTTTAGGTGTGGGT
5 GGACTGGGTGTACCTGGCGTAGGCGGTCTGGGTGGAATTCGCCCGCAGC
GGCCGCGAAAGCGGCAAAATATGGCGCGGCAGGCCTGGGCGGCGTGCTG
GGTGGGGCAGGTCAGTTTCCGCTGGGCGGGGTTGCCGCACGTCCGGGATT
TGGTCTGAGCCCGATTTTCCCTGGCGGCGCATGTCTGGGTAAAGCATGTGG
TCGTAAACGTAAAtaa (SEQ ID NO: 23)
- 10 MKKIWLALAGLVLAFSASAAQYEDHHHHHHHSGSSLVPRGSHMGGVPG
AIPGGVPGGVFYPGAGLGALGGGALGPGGKPLKVPVPGGLAGAGLGAGLGAF
PAVTFPGALVPGGVADAAAAYKAAKAGAGLGGVPGVGGGLGVSAGAVVPQP
GAGVKPGKVPVGLPGVYPGGVLPGARFPGVGVLPGVPTGAGVKPKAPGVG
GAFAGIPGVGPFGGPQPGVPLGYPIKAPKLPGGYGLPYTTGKLPYGYGPGGV
15 AGAAGKAGYPTGTGVGPQAAAAAAKAAAKFGAGAAGVLPGVGGAGVPG
VPGAIPGIGGIAGVGTPAAAAAAKAAKYGAAAGLVPGGPFGPGVVG
VPGAGVPGVGPVPGAGIPVVPAGIPGAAVPGVVSPEAAKAAAKAAKYGAR
PGVGVGGIPTYGVGAGGFPGFGVGVGGIPGVAGVPGVGGVPGVGGVPGVGI
SPEAQAAAAKAAKYGAAGAGVLGGLVPGPQAAVPGVPGTGGVPGVGTGA
20 AAAAKAAKAAQFGLVPGVGVAPGVGVAPGVGVAPGVGLAPGVGVAPGV
GVAPGVGVAPGIGPGGVAAAKSAAKVAKAQLRAAAGLGAGIPGLGVGV
GVPGLGVGAGVPGLGVGAGVPFGAGADEGVRRLSPELREGDPSSSQHLPS
TPSSPRVPGALAAKAAKYGAAPGVLGGLGALGGVGIPGGVVGAGPAAAA
AAAKAAKAAQFGLVGAAGLGGLGVGGLGVPGVGGLGGIPAAAAKAAKY
25 GAAGLGGVLGGAGQFPLGGVAARPGFGLSPIFPGGACLGKACGRKRK (SEQ
ID NO: 24)

[0165] The polynucleotide encoding the full length human elastin without the native sequence tag is disclosed in SEQ ID NO: 87.

- GGTGGCGTACCAGGCGCAATTCCTGGGGGTGTCCCAGGCGGTGTTTTTAT
30 CCGGGCGCCGGTCTTGCGCACTGGGTGGCGGTGCACTGGGCCCGGGCGG
CAAACCGCTGAAACCGGTACCAGGTGGTTTAGCAGGCGCCGGCTTAGGCG
CAGGTCTGGGAGCATTTCCGGCAGTTACCTTTCCAGGGGCACTGGTTCCTG
GAGGTGTGGCCGATGCAGCCGCGGCATATAAAGCCGCTAAAGCCGGTGCG
GGTTTAGGAGGCGTCCCAGGTGTCCGTGGCCTGGGTGTTAGCGCCGGTGC

AGTTGTTCCGCAGCCGGGAGCAGGGGTAAACCTGGTAAAGTGCCGGGAG
TAGGTCTGCCAGGCGTTTATCCTGGTGGTGT TTTGCCGGGTGCCCGTTTTC
CGGGCGTTGGTGTCTTCCAGGCGTGCCGACCGGAGCCGGTGTAAACCG
AAAGCCCCCGGTGTTGGAGGTGCATTTGCAGGCATCCCGGGAGTTGGCCC
5 GTTTGGTGGTCCGCAACCTGGGGTTCGGT TAGGTTATCCGATTAAAGCACC
GAAACTGCCCCGGCGGTATGGTCTGCCGTACACAACCGGTAAACTGCCGT
ATGTTTATGGCCCCGGTGGAGTTGCGGGTGCAGCAGGTAAAGCGGGTTAT
CCTACCGGAACCGGTGTAGGTCCGCAGGCCGCTGCTGCCGCCGCCGCAAA
AGCAGCGGCTAAATTTGGCGCCGGAGCAGCGGGTGTCTGCCTGGAGTTG
10 GTGGTGCGGGCGTGCCAGGGGTACCTGGTGCAATTCCGGGTATTGGTGGT
ATTGCCGGTGTGCGCACCCCGGCCGCGGCAGCTGCGGCAGCGGCGGCTGC
CAAAGCTGCTAAATACGGTGCCGCGGCGGGTCTGGTGCCAGGAGGTCCGG
GTTTTGGTCCGGGAGTGGTTGGCGTGCCTGGCGCAGGCGTTCCTGGTGTGG
GCGTTCAGGTGCAGGGATTCTGTGTGCCTGGTGCCGGTATTCCCGGCG
15 CGGCCGTTCGGGGGTGGTTAGCCCGGAAGCCGCAGCGAAGGCTGCGGC
AAAGGCAGCAAAGTATGGCGCACGCCAGGAGTCGGCGTGGGTGGTATC
CCGACCTATGGGGTGGGCGCAGGGGGTTTTCTGGTTTCGGCGTAGGTGT
AGGAGGTATACCGGGCGTGGCCGGTGTACCAAGGGTTGGTGGCGTCCCTG
GTGTTGGCGGTGTGCCAGGTGTTGGTATTTACCGGAAGCACAGGCAGCA
20 GCCGCAGCTAAGGCAGCGAAATATGGTGCCGCCGGCGCAGGAGTTTTAGG
TGGGCTGGTTCCGGGCCCCGCAGGCAGCTGTGCCGGGGGTTCAGGCACCG
GTGGTGTCCCTGGAGTCGGTACGCCGGTGCAGCGGCAGCCAAAGCGGCT
GCGAAAGCAGCACAGTTTGGCTTAGTACCGGGTGTGGGAGTTGCCCCCGG
CGTTGGCGTTGCTCCAGGGGTGGGTGTGCTCCTGGCGTCGGTCTGGCTCC
25 TGGAGTGGGCGTAGCACCCGGTGTGGGGGTGGCCCCGGGTGTTGGGGTTG
CACCGGGTATCGGTCCGGGCGGTGTGCGAGCAGCAGCTAAAAGCGCGGC
GAAAGTTGCGGCCAAAGCCCAACTGCGCGCCGCCGCGGGCCTCGGTGCAG
GTATTCGGGGCTGGGTGTGCGAGTTGGAGTCCCGGGTTTGGGCGTGGGC
GCGGGAGTTCCGGGACTGGGAGTGGGTGCCGGAGTTCCTGGCTTTGGTGC
30 AGGCGCAGATGAAGGTGTTTCGTCTGAGCTGAGTCCGGAAGTGCCTGAAG
GTGATCCGAGTAGCAGCCAGCATCTGCCGAGCACCCCGAGCAGCCCGCGT
GTTCCGGGTGCATTAGCTGCAGCAAAAGCCGCCAAGTATGGTGCAGCCGT
GCCGGGCGTCTTAGGTGGTCTGGGCGCCCTGGGTGGTGTAGGCATTCCGG
GAGGTGTTGTGGGTGCAGGACCGGCCCGCGCAGCTGCGGCCGCCAAAGC

AGCTGCAAAAGCGGCCCCAGTTTGGTTTGTAGTGGGCGCCGCAGGTTTAGGCG
 GTTTAGGTGTGGGTGGACTGGGTGTACCTGGCGTAGGCGGTCTGGGTGGA
 ATCCGCCCCGCAGCGGCCGCGAAAGCGGCAAAATATGGCGCGGCAGGCC
 TGGGCGGCGTGTCTGGGTGGGGCAGGTCAGTTTCCGCTGGGCGGGGTTGCC
 5 GCACGTCCGGGATTTGGTCTGAGCCCGATTTTCCCTGGCGGCGCATGTCTG
 GTAAAGCATGTGGTCGTAAACGTAAAtaa (SEQ ID NO: 87)

[0166] The full length human elastin sequence without the native sequence tag is disclosed in SEQ ID NO: 88.

GGVPGAIPGGVPGGVFYPGAGLGALGGGALGPGGKPLKVPVPGGLAGAGLGA
 10 GLGAFAVTFPGALVPGGVADAAAAYKAAKAGAGLGGVPGVGGGLGVSA
 VVPQPGAGVKPGKVPVGLPGVYPGGVLPGARFPGVGVLPVPTGAGVKPK
 APGVGGAFAGIPGVGPFGGPQPGVPLGYPIKAPKLPGGYGLPYTTGKLPYGY
 GPGGVAGAAGKAGYPTGTGVGPQAAAAAAKAAKFGAGAAGVLPVGG
 AGVPGVPGAIPGIGGIAGVGTPAAAAAAKAAKYGAAAGLVPGGPGFG
 15 PGVVGVPAGVPGVPGVPGAGIPVVPAGIPGAAVPGVVSPEAAKAAAKAA
 KYGARPGVGVGGIPTYGVGAGGFPFGVGVGGIPGVAGVPGVGGVPGVGGV
 PGVGISPEAQAAAAKAAKYGAAGAGVLGGLVPGPQAAVPGVPGTGGVPG
 VGTPAAAAKAAKAAQFGLVPGVGVAPGVGVAPGVGVAPGVGLAPGVGV
 APGVGVAPGVGVAPGIGPGGVAATAKSAKVAKAQLRAAAGLGAGIPGL
 20 GVGVPGLVGVAGVPGLGVGAGVPFGAGADEGVRRSLSPELREGDPSSS
 QHLPSTPSSPRVPGALAAKAAKYGAAVPGVLGGLGALGGVGIPGGVVGAG
 PAAAAAAKAAKAAQFGLVGAAGLGGLGVGGLVPGVGGGLGIPAAAA
 KAAKYGAAGLGVLGGAGQFPLGGVAARPGFGLSPIFPGGACLGKACGRKR
 K (SEQ ID NO: 88)

25 Codon optimized Elastin with DsbA secretion tag

[0167] The codon optimized polynucleotide sequence encoding the full length human elastin with a DsbA secretion tag is disclosed in SEQ ID NO: 25. In SEQ ID NO: 25; nucleotides 1-72 encode the DsbA secretion tag encoding amino acids 1-24 of SEQ ID NO: 26; nucleotides 73-2355 encode the amino acids 25-785 of the full length human elastin of SEQ ID NO: 26.

ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
 TCGGCGGCGCAGTATGAAGATATGGGTGGCGTACCAGGCGCAATTCCTGG
 GGGTGTCCCAGGCGGTGTTTTTATCCGGGCGCCGGTCTTGGCGCACTGGG
 TGGCGGTGCACTGGGCCCCGGGCGGCAAAACCGCTGAAACCGGTACCAGGT

GGTTTAGCAGGCGCCGGCTTAGGCGCAGGTCTGGGAGCATTTCGGGCAGT
TACCTTTCCAGGGGCACTGGTTCCTGGAGGTGTGGCCGATGCAGCCGCGG
CATATAAAGCCGCTAAAGCCGGTGCGGGTTTAGGAGGCGTCCCAGGTGTC
GGTGGCCTGGGTGTTAGCGCCGGTGCAGTTGTTCCGCAGCCGGGAGCAGG
5 GGTTAAACCTGGTAAAGTGCCGGGAGTAGGTCTGCCAGGCGTTTATCCTG
GTGGTGTTTTGCCGGGTGCCCCGTTTTCCGGGCGTTGGTGTTCTTCCAGGCG
TGCCGACCGGAGCCGGTGTTAAACCGAAAGCCCCCGGTGTTGGAGGTGCA
TTTGCAGGCATCCCAGGAGTTGGCCCGTTTGGTGGTCCGCAACCTGGGGTT
CCGTTAGGTTATCCGATTAAAGCACCGAAACTGCCCCGGCGGTTATGGTCT
10 GCCGTACACAACCGGTAAACTGCCGTATGGTTATGGCCCGGGTGGAGTTG
CGGGTGCAGCAGGTAAAGCGGGTTATCCTACCGGAACCGGTGTAGGTCCG
CAGGCCGCTGCTGCCGCCGCCGCAAAAGCAGCGGCTAAATTTGGCGCCGG
AGCAGCGGGTGTTCTGCCTGGAGTTGGTGGTGCGGGCGTGCCAGGGGTAC
CTGGTGCAATTCCGGGTATTGGTGGTATTGCCGGTGTCGGCACCCCGGCCG
15 CGGCAGCTGCGGCAGCGGCGGCTGCCAAAGCTGCTAAATACGGTGCCGCG
GCGGGTCTGGTGCCAGGAGGTCCGGGTTTTGGTCCGGGAGTGGGTTGGCGT
GCCTGGCGCAGGCGTTCCTGGTGTGGGCGTTCCAGGTGCAGGGATTCCTG
TTGTGCCTGGTGCCGGTATCCCCGGCGCGGCCGTTCCGGGGGTGGTTAGCC
CGGAAGCCGCAGCGAAGGCTGCGGCAAAGGCAGCAAAGTATGGCGCACG
20 CCCAGGAGTCGGCGTGGGTGGTATCCCGACCTATGGGGTGGGCGCAGGGG
GTTTTCTTGGTTTCGGCGTAGGTGTAGGAGGTATACCGGGCGTGGCCGGT
GTACCAGGGGTGGTGCGTCCCTGGTGTTGGCGGTGTGCCAGGTGTTGG
TATTTACCGGAAGCACAGGCAGCAGCCGCAGCTAAGGCAGCGAAATATG
GTGCCGCCGGCGCAGGAGTTTTAGGTGGGCTGGTTCCGGGGCCCGCAGGCA
25 GCTGTGCCGGGGGTTCAGGCACCGGTGGTGTCCCTGGAGTCGGTACGCC
GGCTGCAGCGGCAGCCAAAGCGGCTGCGAAAGCAGCACAGTTTGGCTTAG
TACCGGGTGTGGGAGTTGCCCCCGGCGTTGGCGTTGCTCCAGGGGTGGGT
GTTGCTCCTGGCGTCGGTCTGGCTCCTGGAGTGGGCGTAGCACCCGGTGTG
GGGGTGGCCCCGGGTGTTGGGGTTGCACCGGGTATCGGTCCGGGCGGTGT
30 CGCAGCAGCAGCTAAAAGCGCGGCGAAAGTTGCGGCCAAAGCCCAACTG
CGCGCCGCCCGCGGGCCTCGGTGCAGGTATTCCGGGGCTGGGTGTCGGAGT
TGGAGTCCCGGGTTTTGGGCGTGGGCGCGGGAGTTCCGGGACTGGGAGTGG
GTGCCGGAGTTCCTGGCTTTGGTGCAGGCGCAGATGAAGGTGTTTCGTCTG
AGCCTGAGTCCGGAAGTGCCTGAAGGTGATCCGAGTAGCAGCCAGCATCT

GCCGAGCACCCCGAGCAGCCCGCGTGTTCGGGTGCATTAGCTGCAGCAA
 AAGCCGCCAAGTATGGTGCAGCCGTGCCGGGCGTCTTAGGTGGTCTGGGC
 GCCCTGGGTGGTGTAGGCATTCCGGGAGGTGTTGTGGGTGCAGGACCGGC
 CGCCGCAGCTGCGGCCGCCAAAGCAGCTGCAAAAGCGGCCAGTTTGGTT
 5 TAGTGGGCGCCGCAGGTTTAGGCGGTTTAGGTGTGGGTGGACTGGGTGTA
 CCTGGCGTAGGCGGTCTGGGTGGAATTCCGCCCCGAGCGGCCCGCAAAGC
 GGCAAAATATGGCGCGGCAGGCCTGGGCGGCGTGCTGGGTGGGGCAGGT
 CAGTTTCCGCTGGGCGGGGTTGCCGCACGTCCGGGATTTGGTCTGAGCCC
 GATTTTCCCTGGCGGCGCATGTCTGGGTAAAGCATGTGGTCGTAAACGTA
 10 AAtaa (SEQ ID NO: 25)

MKKIWLALAGLVLAFFSASAAQYEDMGGVPGAIPGGVPGGVFYFPGAGLGALG
 GGALGPGGKPLKVPVGGLAGAGLGAGLGAFPAVTFPGALVPGGVADAAAAY
 KAAKAGAGLGGVPGVGGGLGVSAGAVVPQPGAGVKPGKVPVGLPGVYPGG
 15 VLPGARFPGVGVLPVPTGAGVKPKAPGVGGAFAGIPGVGPFGGPQPGVPLG
 YPIKAPKLPGGYGLPYTTGKLPYGYGPGGVAGAAGKAGYPTGTGVGPQAAA
 AAAAKAAAKFGAGAAGVLPVGGAGVPGVPGAIPGIGGIAGVGTAAAAAA
 AAAAKAAKYGAAAGLVPGGPGFGPGVVGVPAGVPGVGVPGAGIPVPGA
 GIPGAAVPGVVSPEAAAKAAAKAAKYGARPGVGVGGIPTYGVGAGGFPGFG
 20 VGVGGIPGVAGVPGVGGVPGVGGVPGVGSPEAQAAAAAKAAKYGAAGAG
 VLGGLVPGPQAAVPGVPGTGGVPGVGTAAAAAKAAAKAAQFGLVPGVGV
 APGVGVAPGVGVAPGVGLAPGVGVAPGVGVAPGVGVAPGIGPGGVAAAAK
 SAAKVAAKAQLRAAAGLGAGIPGLGVGVGPGLGVGAGVPGLGVGAGVPG
 FGAGADEGVRRSLSPELREGDPSSSQHLPSTPSSPRVPGALAAKAAKYGAA
 25 VPGVLGGLGALGGVGIPGGVVAGPAAAAAAKAAAKAAQFGLVGAAGLG
 GLGVGGLGVPGVGGGLGGIPAAAAAKAAKYGAAGLGGVLGGAGQFPLGGVA
 ARPGFGLSPIFPGGACLGKACGRKRK (SEQ ID NO: 26)

[0168] The polynucleotides of SEQ ID NO: 22 was codon optimized and
 synthesized by Gen9 DNA, now Ginkgo Bioworks internal synthesis. Overlaps
 30 between the pET28 vector and SEQ ID NO: 22 was designed to be between 30 and
 40bp long and added using PCR with the enzyme PrimeStar GXL polymerase
 (http://www.clontech.com/US/Products/PCR/GC_Rich/PrimeSTAR_GXL_DNA_Polymerase?sitex=10020:22372:US). The opened pET28a vector and insert DNA (SEQ
 ID NO: 22) was then assembled together into the final plasmid using SGI Gibson

assembly (<https://us.vwr.com/store/product/17613857/gibson-assembly-hifi-1-step-kit-synthetic-genomics-inc>). Sequence of plasmid was then verified through sanger sequencing through Eurofins Genomics (www.eurofinsgenomics.com).

5 [0169] The transformed cells were cultivated in minimal media and frozen in 1.5 aliquots with glycerol at a ratio of 50:50 of cells to glycerol. One vial of this frozen culture was revived in 50ml of minimal media overnight at 37 °C, 200rpm. Cells were transferred into 300ml of minimal media and grown for 6-9 hours to reach an OD600 of 5-10.

10 [0170] A bioreactor was prepared with 2.7L of minimal media + glucose and 300 ml of OD600 of 5-10 culture was added to bring the starting volume to 3L. Cells were grown at 28°C, pH7 with Dissolved Oxygen maintained at 20% saturation using a cascade containing agitation, air and oxygen. pH was controlled using 28% w/w Ammonium hydroxide solution. Fermentation was run in a fed-batch mode using a DO-stat based feeding algorithm once the initial bolus of 40g/L was depleted around 15 13hours. After 24-26hours of initial growth, the OD600 reached above 100. At this point, 300mL of 500g/L sucrose was added and temperature was reduced to 25C. High density culture was induced for protein production using 1mM IPTG. Fermentation was continued for another 20-24 hours and cells were harvested using a bench top centrifuge at 9000 ref, 15C for 60 minutes. Cell pellet recovered from 20 centrifugation was resuspended in a buffer containing 0.5M NaCl and 0.1M KH₂PO₄ at pH8 in a weight by weight ratio of 2x buffer to 1x cells.

[0171] The fermentations were performed at various temperature ranging from 25° to 28° C. For some fermentations, the temperature of the fermentation was maintained at a constant temperature and immediately upon completion of 25 fermentation (OD600 of 5-10) the elastin was purified. For other fermentations, the temperature of the fermentations is maintained for a desired period of time and when cell densities of OD600 of 5-10 are reached, the temperature is reduced to induce protein production. Typically, the temperature is reduced from 28° C to 25° C. After the fermentation at 25° C is continued for 40-60 hours, the elastin is isolated.

30 [0172] The harvested cells were disrupted in a homogenizer at 14,000 psi pressure in 2 passes. Resulting slurry contained the collagen protein along with other proteins.

[0173] The supernatant from the homogenized cells was analyzed on an SDS-PAGE gel and a clear band was observed at around 70 kilodaltons corresponding to

the expected size of 68 kilodaltons. The purified elastin is analyzed by mass spectrometry.

Full Length Elastin with DsbA secretion tag-His tag-Linker-Thrombin cleavage site and GFP Beta-lactamase fusion

- 5 [0174] A human elastin with DsbA secretion tag-His tag-Linker-Thrombin cleavage site and GFP Beta-lactamase fusion is disclosed below. The codon-optimized nucleotide sequence encoding this elastin is provided in SEQ ID NO: 27. The amino acid sequence is disclosed in SEQ ID NO: 28. The DsbA secretion tag is encoded by nucleotides 1-72 and encodes amino acids 1-24. The His tag is encoded by
- 10 nucleotides 73-99 and encodes a 9 histidine tag of amino acids 25-33. The linker is encoded by nucleotides 100-111 and encodes amino acids 34-37. The thrombin cleavage site is encoded by nucleotides 112-135 and encodes amino acids 38-45. The green fluorescent protein (GFP) with linker is encoded by nucleotides 136-873 and encodes amino acids 46-291. The full-length elastin sequence is encoded by
- 15 nucleotides 874-3153 and encodes amino acids 292-1051. The Beta-lactamase with linker is encoded by nucleotides 3154-3945 and encodes amino acids 1052-1315.

ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTAGTTTTAGCGTTTAGCGCA
TCGGCGGCGCAGTATGAAGATCACCATCACCACCACCACCATCACCCTC
TGGCTCGAGCCTGGTGCCGCGCGGCAGCCATATGTCTGGCTCGAGCAGTA
20 AAGGTGAAGAACTGTTCAACGGTGTGTTCCGATCCTGGTTGAAGTGGAT
GGTGATGTAAACGGCCACAAATTCTCTGTTCGTGGTGAAGGTGAAGGTGA
TGCAACCAACGGTAAACTGACCCTGAAATTCATCTGCACTACCGGTAAAC
TGCCGGTTCCATGGCCGACTCTGGTGACTACCCTGACCTATGGTGTTCAGT
GTTTTTCTCGTTACCCGGATCACATGAAGCAGCATGATTCTTCAAATCTG
25 CAATGCCGGAAGGTTATGTACAGGAGCGCACCATTTCTTTCAAAGACGAT
GGCACCTACAAAACCCGTGCAGAGGTTAAATTTGAAGGTGATACTCTGGT
GAACCGTATTGAACTGAAAGGCATTGATTTCAAAGAGGACGGCAACATCC
TGGGCCACAACTGGAATATAACTTCAACTCCCATAACGTTTACATCACC
GCAGACAAACAGAAGAACGGTATCAAAGCTAACTTCAAATTCGCCATAA
30 CGTTGAAGACGGTAGCGTACAGCTGGCGGACCACTACCAGCAGAACACTC
CGATCGGTGATGGTCCGGTTCTGCTGCCGGATAACCACTACCTGTCCACCC
AGTCTaaaCTGTCCAAGACCCGAACGAAAAGCGCGACCACATGGTGCTGC
TGGAGTTCGTTACTGCAGCAGGTATCACGCACGGCATGGATGAACTCTAC
AAATCTGGCGCGCCGGGGCGGTGGCGTACCAGGCGCAATTCCTGGGGGTGT

CCCAGGCGGTGTTTTTATCCGGGCGCCGGTCTTGGCGCACTGGGTGGCGG
TGC ACTGGGCCCCGGGCGGCAAACCGCTGAAACCGGTACCAGGTGGTTTAG
CAGGCGCCGGCTTAGGCGCAGGTCTGGGAGCATTTCGGGCAGTTACCTTT
CCAGGGGCACTGGTTCCTGGAGGTGTGGCCGATGCAGCCGCGGCATATAA
5 AGCCGCTAAAGCCGGTGCGGGTTTAGGAGGCGTCCCAGGTGTCGGTGGCC
TGGGTGTTAGCGCCGGTGCA GTTGTTCGCGAGCCGGGAGCAGGGGTTAAA
CCTGGTAAAGTGCCGGGAGTAGGTCTGCCAGGCGTTTATCCTGGTGGTGT
TTGCCGGGTGCCCGTTTTCCGGGCGTTGGTGTTCCTCCAGGCGTGCCGACC
GGAGCCGGTGTTAAACCGAAAGCCCCCGGTGTTGGAGGTGCATTTCAGG
10 CATCCCGGGAGTTGGCCCGTTTGGTGGTCCGCAACCTGGGGTTCGGTTAGG
TTATCCGATTAAAGCACCGAAACTGCCCCGGCGGTTATGGTCTGCCGTACA
CAACCGGTAAACTGCCGTATGGTTATGGCCCCGGGTGGAGTTGCGGGTGCA
GCAGGTAAAGCGGGTTATCCTACCGGAACCGGTGTAGGTCCGCGAGGCCGC
TGCTGCCGCCGCCGCAAAAGCAGCGGCTAAATTTGGCGCCGGAGCAGCGG
15 GTGTTCTGCCTGGAGTTGGTGGTGCGGGCGTGCCAGGGGTACCTGGTGCA
ATTCCGGGTATTGGTGGTATTGCCGGTGTCGGCACCCCGGCCGCGGCAGC
TGCGGCAGCGGCGGCTGCCAAAGCTGCTAAATACGGTGCCGCGGCGGGTC
TGGTGCCAGGAGGTCCGGGTTTTGGTCCGGGAGTGGTTGGCGTGCCTGGC
GCAGGCGTTCCTGGTGTGGGCGTTCCAGGTGCAGGGATTCTGTGTGCCT
20 GGTGCCGGTATTCCCGGCGCGGCCGTTCCGGGGGTGGTTAGCCCGGAAGC
CGCAGCGAAGGCTGCGGCAAAGGCAGCAAAGTATGGCGCACGCCAGGA
GTCGGCGTGGGTGGTATCCCGACCTATGGGGTGGGCGCAGGGGGTTTTCC
TGGTTTCGGCGTAGGTGTAGGAGGTATACCGGGCGTGGCCGGTGTACCAG
GGGTTGGTGGCGTCCCTGGTGTGGCGGTGTGCCAGGTGTTGGTATTTAC
25 CGGAAGCACAGGCAGCAGCCGCAGCTAAGGCAGCGAAATATGGTGCCGC
CGGCGCAGGAGTTTTAGGTGGGCTGGTTCCGGGGCCCGCAGGCAGCTGTGC
CGGGGGTTCCAGGCACCGGTGGTGTCCCTGGAGTCGGTACGCCGGCTGCA
GCGGCAGCCAAAGCGGCTGCGAAAGCAGCACAGTTTGGCTTAGTACCGGG
TGTGGGAGTTGCCCCCGGCGTTGGCGTTGCTCCAGGGGTGGGTGTTGCTCC
30 TGGCGTCCGGTCTGGCTCCTGGAGTGGGCGTAGCACCCGGTGTGGGGGTGG
CCCCGGGTGTTGGGGTTGCACCGGGTATCGGTCCGGGCGGTGTGCGAGCA
GCAGCTAAAGCGCGGCGAAAGTTGCGGCCAAAGCCCAACTGCGCGCCG
CCGCGGGCCTCGGTGCAGGTATTCGGGGGCTGGGTGTGCGAGTTGGAGTC
CCGGGTTTGGGCGTGGGCGCGGGAGTTCCGGGACTGGGAGTGGGTGCCGG

AGTTCCTGGCTTTGGTGCAGGCGCAGATGAAGGTGTTTCGTCTAGCCTGA
 GTCCGGAAGTGCCTGAAGGTGATCCGAGTAGCAGCCAGCATCTGCCGAGC
 ACCCCGAGCAGCCCGCGTGTTCGGGTGCATTAGCTGCAGCAAAAGCCGC
 CAAGTATGGTGCAGCCGTGCCGGGCGTCTTAGGTGGTCTGGGCGCCCTGG
 5 GTGGTGTAGGCATTCCGGGAGGTGTTGTGGGTGCAGGACCGGCCGCCGCA
 GCTGCGGCCGCCAAAGCAGCTGCAAAAGCGGCCAGTTTGGTTTGTGGG
 CGCCGCAGGTTTAGGCGGTTTAGGTGTGGGTGGACTGGGTGTACCTGGCG
 TAGGCGGTCTGGGTGGAATTCGCCCCGCAGCGGCCGCGAAAGCGGCAAA
 ATATGGCGCGGCAGGCCTGGGCGGCGTGCTGGGTGGGGCAGGTCAGTTTC
 10 CGCTGGGCGGGGTTGCCGCACGTCCGGGATTTGGTCTGAGCCCGATTTTCC
 CTGGCGGCGCATGTCTGGGTAAAGCATGTGGTCGTAAACGTAAAcaccagaa
 acgctggtgaaagtaaagatgctgaagatcagttgggtgcacgagtggttacatgaactggatcgaacagcggtgaa
 atccttgagagttttgccccgaagaacgtttccaatgatgagcacttttaaagttctgctatgtggcggtattatcccgat
 tgacgccccgcaagagcaactcggtcgccgcatacactattctcagaatgacttggtgagtactaccagtcacagaaaa
 15 gcatcttacgtaggcatgacagtaagagaattatgcagtgtccataaccatgagtataaactgcggccaactacttc
 tgacaacgacgaggagaccgaaggagctaaccgctttttgcacaacatgggggatcatgtaactgccttgatcgttggga
 accggagctgaatgaagccataccaaacgacgagcgtgacaccacgatgcctgtagcaatggcaacaacgttgcgcaaa
 ctattaactggcgaaactactacttagcttcccgcaacaattaatagactggatggaggcggtataaagtgcaggaccact
 tctgcgctcgccctccggctggctggtttattgctgataaatctggagccggtgagcgtgggtctcgcggtatcattgcag
 20 cactggggccagatgtaagccctcccgatctgtagttatctacacgacggggagttaggcaactatggatgaacgaata
 gacagatcgctgagatagtgctcactgattaagcattggttaa (SEQ ID NO: 27)
 MKKIWLALAGLVLAFSASAAQYEDHHHHHHHHHSGSSLVPRGSHMSGSSSK
 GEELFTGVVPILVELDGDVNGHKFSVRGEGEGDATNGKLTLKFICTTGKLPVP
 WPTLVTTLTYGVCFSRYPDHMKQHDFFKSAMPEGYVQERTISFKDDGTYK
 25 TRAEVKFEGDTLVNRIELKGIDFKEDGNILGHKLEYNFNShNVYITADKQKNG
 IKANFKIRHNVEDGSVQLADHYQNTPIGDGPVLLPDNHYLSTQSKLSKDPNE
 KRDHMVLLFVTAAGITHGMDELKSGAPGGGVPGAIPGGVPGGVFYPGAG
 LGALGGGALGPGGKPLKPVPGGLAGAGLGAGLGAFPAVTFPGALVPGGVAD
 AAAAYKAAKAGAGLGGVPGVGG LGVSAGAVVPQPGAGVKPGKVPVGLPG
 30 VYPGGVLPGARFPGVGVLPVPTGAGVKPKAPGVGGAFAGIPGVGPFGGPQP
 GVPLGYPIKAPKLPGGYGLPYTTGKLPYGYGPGGVAGAAGKAGYPTGTGVG
 PQAAAAAAKAAKAFGAGAAGVLPVGGAGVPGVPGAIPGIGGIAGVGTGA
 AAAAAAAKAAKYGAAAGLVPGGPGFGPGVVGVPGAGVPGVGVPGAGIP
 VVPAGIPGAAVPGVVSPEAAKAAKAAKYGARPGVGVGGIPTYGVGAGG

FPGFGVGVGGIPGVAGVPGVGGVPGVGGVPGVGISPEAQAAAAAKAAKYGA
 AGAGVLGGLVPGPQAAVPGVPGTGGVPGVGTAAAAAKAAKAAQFGLVP
 GVGVA PGVGVAPGVGVAPGVGLAPGVGVAPGVGVAPGVGVAPGIGPGGVA
 AAKSAAKVA AKAQLRAAAGLGAGIPGLGVGVGVPGLVGAGVPGLGVGA
 5 GVPFGGAGADEGVRRSLSPELREGDPSSSQHLPSTPSSPRVPGALAAKAAKY
 GAAVPGVLGGLGALGGVGIPGGVVGAGPAAAAAAKAAKAAQFGLVGAA
 GLGGLGVGGLGVPGVGGGLGGIPAAAAKAAKYGAAGLGGVLGGAGQFPLG
 GVAARPGFGLSPIFPGGACLGKACGRKRKHPETLVKVKDAEDQLGARVGYIE
 LDLNSGKILESFRPEERFPM MSTFKVLLCGAVLSRIDAGQEQLGRRIHYSQND
 10 LVEYSPVTEKHLTDGMTVRELCSAAITMSDNTAANLLLTIGGPKELTAFLHN
 MGDHVTSLDRWEPELNEAIPNDERDTTMPVAMATTLRKLLTGELLTLASRQ
 QLIDWMEADKVAGPLLRSLPAGWFIADKSGAGERGSRGIIAALGPDGKPSRI
 VVIYTTGSQATMDERNRQIAEIGASLIKHW (SEQ ID NO: 28)

Example 5: Production of Truncated Elastin

15 **[0175]** Truncated human elastin is produced using the expression system as
 described in Example 4. The full length amino acid sequence lacking the native
 secretion tag is disclosed in SEQ ID NO: 29.

GGVPGAIPGGVPGGVFYPGAGLGALGGGALGPGGKPLKVPVPGGLAGAGLGA
 GLGAFAVTFPGALVPGGVADAAAAYKAAKAGAGLGGVPGVGGGLGV SAGA
 20 VVPQPGAGVKPGKVPGVGLPGVYPGGVLPGARFPGVGVLPGVPTGAGVKPK
 APGVGGAFAGIPGVGPFGGPQPGVPLGYPIKAPKLPGGYGLPYTTGKLPYGY
 GPGGVAGAAGKAGYPTGTGVGPQAAAAAAKAAKFGAGAAGVLPGVGG
 AGVPGVPGAIPGIGGIAGVGTAAAAAAKAAKYGAAAGLVPGGPGFG
 PGVVGVPAGVPGVGVPGAGIPVPGAGIPGAAVPGVVSPEAAKAAKAA
 25 KYGARPGVGVGGIPTYGVGAGGFPFGVGVGGIPGVAGVPGVGGVPGVGGV
 PGVGISPEAQAAAAKAAKYGAAGAGVLGGLVPGPQAAVPGVPGTGGVPG
 VGTPAAAAKAAKAAQFGLVPGVGVAPGVGVAPGVGVAPGVGLAPGVGV
 APGVGVAPGVGVAPGIGPGGVA AAKSAAKVA AKAQLRAAAGLGAGIPGL
 GVGVPGLGVGAGVPGLGVGAGVPGFGAGADEGVRRSLSPELREGDPSSS
 30 QHLPSTPSSPRVPGALAAKAAKYGAAVPGVLGGLGALGGVGIPGGVVGAG
 PAAAAAAKAAKAAQFGLVGAAAGLGGLVGGLGVPGVGGGLGGIPAAAA
 KAAKYGAAGLGGVLGGAGQFPLGGVAARPGFGLSPIFPGGACLGKACGRKR
 K (SEQ ID NO: 29)

[0176] The codon optimized polynucleotide sequence encoding the full length human elastin lacking the native secretion tag is disclosed in SEQ ID NO: 30.

GGTGGCGTACCAGGCGCAATTCCTGGGGGTGTCCCAGGCGGTGTTTTTAT
CCGGGCGCCGGTCTTGCGCACTGGGTGGCGGTGCACTGGGCCCCGGGCGG
5 CAAACCGCTGAAACCGGTACCAGGTGGTTTAGCAGGCGCCGGCTTAGGCG
CAGGTCTGGGAGCATTTCGGCAGTTACCTTTCCAGGGGCACTGGTTCCTG
GAGGTGTGGCCGATGCAGCCGCGGCATATAAAGCCGCTAAAGCCGGTGCG
GGTTTAGGAGGCGTCCCAGGTGTCGGTGGCCTGGGTGTTAGCGCCGGTGC
AGTTGTTCCGCAGCCGGGAGCAGGGGTAAACCTGGTAAAGTGCCGGGAG
10 TAGGTCTGCCAGGCGTTTATCCTGGTGGTGTGTTTGCCGGGTGCCGTTTTTC
CGGGCGTTGGTGTCTTCCAGGCGTGCCGACCGGAGCCGGTGTAAACCG
AAAGCCCCCGGTGTTGGAGGTGCATTTGCAGGCATCCCGGGAGTTGGCCC
GTTTGGTGGTCCGCAACCTGGGGTTCGGTTAGGTTATCCGATTAAAGCACC
GAAACTGCCCGGCGGTTATGGTCTGCCGTACACAACCGGTAAACTGCCGT
15 ATGGTTATGGCCCCGGTGGAGTTGCGGGTGCAGCAGGTAAAGCGGGTTAT
CCTACCGGAACCGGTGTAGGTCCGCAGGCCGCTGCTGCCGCCGCCGCAAA
AGCAGCGGCTAAATTTGGCGCCGGAGCAGCGGGTGTCTGCCTGGAGTTG
GTGGTGCGGGCGTGCCAGGGGTACCTGGTGCAATTCCGGGTATTGGTGGT
ATTGCCGGTGTGCGCACCCCGGCCGCGGCAGCTGCGGCAGCGGCGGCTGC
20 CAAAGCTGCTAAATACGGTGCCGCGGCGGGTCTGGTGCCAGGAGGTCCGG
GTTTTGGTCCGGGAGTGGTTGGCGTGCTGGCGCAGGCGTTCCTGGTGTGG
GCGTTCCAGGTGCAGGGATTCTGTTGTGCCTGGTGCCGGTATTCCCGGCG
CGGCCGTTCCGGGGGTGGTTAGCCCCGAAGCCGCAGCGAAGGCTGCGGC
AAAGGCAGCAAAGTATGGCGCACGCCAGGAGTCGGCGTGGGTGGTATC
25 CCGACCTATGGGGTGGGCGCAGGGGGTTTTCTGGTTTCGGCGTAGGTGT
AGGAGGTATACCGGGCGTGGCCGGTGTACCAGGGGTGGTGGCGTCCCTG
GTGTTGGCGGTGTGCCAGGTGTTGGTATTTACCGGAAGCACAGGCAGCA
GCCGCAGCTAAGGCAGCGAAATATGGTGCCGCCGGCGCAGGAGTTTTAGG
TGGGCTGGTTCCGGGCCCCGAGGCAGCTGTGCCGGGGGTTCAGGCACCG
30 GTGGTGTCCCTGGAGTCGGTACGCCGGCTGCAGCGGCAGCCAAAGCGGCT
GCGAAAGCAGCACAGTTTGGCTTAGTACCGGGTGTGGGAGTTGCCCCCGG
CGTTGGCGTTGCTCCAGGGGTGGGTGTTGCTCCTGGCGTCGGTCTGGCTCC
TGGAGTGGGCGTAGCACCCGGTGTGGGGGTGGCCCCGGGTGTTGGGGTTG
CACCGGGTATCGGTCCGGGCGGTGTCGCAGCAGCAGCTAAAAGCGCGGC

GAAAGTTGCGGCCAAAGCCCAACTGCGCGCCGCCGCGGGCCTCGGTGCAG
 GTATTCGGGGCTGGGTGTCCGAGTTGGAGTCCCGGGTTTGGGCGTGGGC
 GCGGGAGTTCCGGGACTGGGAGTGGGTGCCGGAGTTCCTGGCTTTGGTGC
 AGGCGCAGATGAAGGTGTTTCGTCTAGCCTGAGTCCGGAAGTGCCTGAAG
 5 GTGATCCGAGTAGCAGCCAGCATCTGCCGAGCACCCCGAGCAGCCCGCGT
 GTTCCGGGTGCATTAGCTGCAGCAAAAGCCGCCAAGTATGGTGCAGCCGT
 GCCGGGCGTCTTAGGTGGTCTGGGCGCCCTGGGTGGTGTAGGCATTCCGG
 GAGGTGTTGTGGGTGCAGGACCGGCCGCCGCAGCTGCGGCCGCCAAAGC
 AGCTGCAAAAGCGGCCCAAGTTTGGTTTGTAGTGGGCGCCGCAGGTTTAGGCG
 10 GTTTAGGTGTGGGTGGACTGGGTGTACCTGGCGTAGGCGGTCTGGGTGGA
 ATTCCGCCCCtaa (SEQ ID NO: 30)

[0177] The amino acid sequence of a 60.7 kDa human elastin truncated at the C-terminal is disclosed in SEQ ID NO: 31. The 60.7 kDa truncated elastin has amino acids 706-761 deleted from the full length elastin.

15 GGVPGAIPGGVPGGVFYPGAGLGALGGGALGPGGKPLKVPVPGGLAGAGLGA
 GLGAFAVTFPGALVPGGVADAAAAYKAAKAGAGLGGVPGVGGGLVVSAGA
 VVPQPGAGVKPGKVPGVGLPGVYPGGVLPGARFPGVGVLPGVPTGAGVKPK
 APGVGGAFAAGIPGVGPFGGPQPGVPLGYPIKAPKLPGGYGLPYTTGKLPYGY
 GPGGVAGAAGKAGYPTGTGVGPQAAAAAAKAAKFGAGAAGVLPGVGG
 20 AGVPGVPGAIPGIGGIAGVGTAAAAAAAKAAKYGAAAGLVPGGPGFG
 PGVVGVPAGVPGVPGVPGAGIPVPGAGIPGAAPGVVSPEAAKAAAKAA
 KYGARPGVGVGGIPTYGVGAGGFPFGVGVGGIPGVAGVPGVGGVPGVGGV
 PGVGISPEAQAAAAKAAKYGAAGAGVLGGLVPGPQAAVPGVPGTGGVPG
 VGTPAAAAKAAKAAQFGLVPGVGVAPGVGVAPGVGVAPGVGLAPGVGV
 25 APGVGVAPGVGVAPGIGPGGVAAAAKSAKVAAKAQLRAAAGLGAGIPGL
 GVGVPGLGVGAGVPGLGVGAGVPGFGAGADEGVRRSLSPELREGDPSSS
 QHLPSTPSSPRVPGALAAKAAKYGAAPGVLGGLGALGGVGIPGGVVGAG
 PAAAAAAKAAKAAQFGLVGAAGLGGLGVGGLGVPGVGGGLGGIPP (SEQ
 ID NO: 31)

30 **[0178]** The codon optimized polynucleotide sequence encoding the truncated 60.7 kDa human elastin is disclosed in SEQ ID NO: 32.

GGTGGCGTACCAGGCGCAATTCCTGGGGGTGTCCCAGGCGGTGTTTTTAT
 CCGGGCGCCGGTCTTGCGCACTGGGTGGCGGTGCACTGGGCCCCGGCGG
 CAAACCGCTGAAACCGGTACCAGGTGGTTTAGCAGGCGCCGGCTTAGGCG

CAGGTCTGGGAGCATTTCGGCAGTTACCTTTCCAGGGGCACTGGTTCCTG
GAGGTGTGGCCGATGCAGCCGCGGCATATAAAGCCGCTAAAGCCGGTGCG
GGTTTAGGAGGCGTCCCAGGTGTCGGTGGCCTGGGTGTTAGCGCCGGTGC
AGTTGTTCCGCAGCCGGGAGCAGGGGTAAACCTGGTAAAGTGCCGGGAG
5 TAGGTCTGCCAGGCGTTTATCCTGGTGGTGTTTTGCCGGGTGCCCGTTTTC
CGGGCGTTGGTGTTCCTCCAGGCGTGCCGACCGGAGCCGGTGTTAAACCG
AAAGCCCCCGGTGTTGGAGGTGCATTTGCAGGCATCCCGGGAGTTGGCCC
GTTTGGTGGTCCGCAACCTGGGGTTCGGTTAGGTTATCCGATTAAAGCACC
GAAACTGCCCCGGCGGTATGGTCTGCCGTACACAACCGGTAAACTGCCGT
10 ATGGTTATGGCCCCGGGTGGAGTTGCGGGTGCAGCAGGTAAAGCGGGTTAT
CCTACCGGAACCGGTGTAGGTCCGCAGGCCGCTGCTGCCGCCGCCGCAAA
AGCAGCGGCTAAATTTGGCGCCGGAGCAGCGGGTGTTCTGCCTGGAGTTG
GTGGTGCGGGCGTGCCAGGGGTACCTGGTGCAATTCCGGGTATTGGTGGT
ATTGCCGGTGTCGGCACCCCGGCCGCGGCAGCTGCGGCAGCGGCGGGCTGC
15 CAAAGCTGCTAAATACGGTGCCGCGGCGGGTCTGGTGCCAGGAGGTCCGG
GTTTTGGTCCGGGAGTGGTTGGCGTGCTGGCGCAGGCGTTCCTGGTGTGG
GCGTTCCAGGTGCAGGGATTCTGTTGTGCCTGGTGCCGGTATTCCCGGCG
CGGCCGTTCCGGGGGTGGTTAGCCCGGAAGCCGCAGCGAAGGCTGCGGC
AAAGGCAGCAAAGTATGGCGCACGCCAGGAGTCGGCGTGGGTGGTATC
20 CCGACCTATGGGGTGGGCGCAGGGGGTTTTCTGGTTTCGGCGTAGGTGT
AGGAGGTATACCGGGCGTGGCCGGTGTACCAGGGGTGGTGGCGTCCCTG
GTGTTGGCGGTGTGCCAGGTGTTGGTATTTACCGGAAGCACAGGCAGCA
GCCGCAGCTAAGGCAGCGAAATATGGTGCCGCCGGCGCAGGAGTTTTAGG
TGGGCTGGTTCCGGGGCCCGCAGGCAGCTGTGCCGGGGGTTCAGGCACCG
25 GTGGTGTCCCTGGAGTCGGTACGCCGGCTGCAGCGGCAGCCAAAGCGGCT
GCGAAAGCAGCACAGTTTGGCTTAGTACCGGGTGTGGGAGTTGCCCCCGG
CGTTGGCGTTGCTCCAGGGGTGGGTGTTGCTCCTGGCGTCGGTCTGGCTCC
TGGAGTGGGCGTAGCACCCGGTGTGGGGGTGGCCCCGGGTGTTGGGGTTG
CACCGGGTATCGGTCCGGGCGGTGTGCGCAGCAGCAGCTAAAAGCGCGGC
30 GAAAGTTGCGGCCAAAGCCCAACTGCGCGCCGCCGCGGGCCCTCGGTGCAG
GTATTCCGGGGCTGGGTGTGCGAGTTGGAGTCCCGGGTTTGGGCGTGGGC
GCGGGAGTTCCGGGACTGGGAGTGGGTGCCGGAGTTCCTGGCTTTGGTGC
AGGCGCAGATGAAGGTGTTTCGTCTAGCCTGAGTCCGGAAGTGCCTGAAG
GTGATCCGAGTAGCAGCCAGCATCTGCCGAGCACCCCGAGCAGCCCGCGT

GTTCCGGGTGCATTAGCTGCAGCAAAAGCCGCCAAGTATGGTGCAGCCGT
 GCCGGGCGTCTTAGGTGGTCTGGGCGCCCTGGGTGGTGTAGGCATTCCGG
 GAGGTGTTGTGGGTGCAGGACCGGCCCGCAGCTGCGGCCGCCAAAGC
 AGCTGCAAAAGCGGCCCAAGTTTGGTTTGTAGTGGGCGCCGCAGGTTTAGGCG
 5 GTTTAGGTGTGGGTGGACTGGGTGTACCTGGCGTAGGCGGTCTGGGTGGA
 ATTCCGCCCTaa (SEQ ID NO: 32)

[0179] The amino acid sequence of a 58.8 kDa human elastin truncated at the N-terminal is disclosed in SEQ ID NO: 33. The 58.8 kDa truncated elastin has amino acids 2-85 deleted from the full length elastin.

10 GLGGVPGVGGLGVSAAGVVPQPGAGVKPGKVPGVGLPGVYPGGVLPGARFP
 GVGVLPGVPTGAGVKPKAPGVGGAFAAGIPGVGPFGGPQPGVPLGYPIKAPKL
 PGGYGLPYTTGKLPYGYGPGGVAGAAGKAGYPTGTGVGPQAAAAAAKAA
 AKFGAGAAGVLPGVGGAGVPGVPGAIPGIGGIAGVGTPAAAAAAKAA
 KYGAAAGLVPGGPGFGPGVVGVPAGVPGVPGVPGAGIPVVPAGIPGAAMP
 15 GVVSPAAAAKAAKAAKYGARPGVGVGGIPTYGVGAGGFPGFGVGVGGIPG
 VAGVPGVGGVPGVGGVPGVGISPEAQAAAAKAAKYGAAGAGVLGGLVPG
 PQAAVPGVPGTGGVPGVGTAAAAKAAKAAQFGLVPGVGVAPGVGVAP
 GVGVAAPGVGLAPGVGVAPGVGVAPGVGVAPGIGPGGVAAAKSAKVAAK
 AQLRAAAGLGAGIPGLGVGVVPGLGVGAGVPGLGVGAGVPFGAGADEG
 20 VRRSLPELREGDPSSSQHLPSTPSSPRVPGALAAKAAKYGAAMPVGLGGLG
 ALGGVGIPGGVVGAGPAAAAAAKAAKAAQFGLVGAAGLGGLGVGGLG
 VPGVGGGLGGIPAAAAKAAKYGAAGLGVLGGAGQFPLGGVAARPGFGLSP
 IFPGGACLGKACGRKRK (SEQ ID NO: 33)

[0180] The codon optimized polynucleotide sequence encoding the 58.8 kDa truncated human elastin is disclosed in SEQ ID NO: 34.

25 GGTTTAGGAGGCGTCCCAGGTGTCGGTGGCCTGGGTGTTAGCGCCGGTGC
 AGTTGTTCCGCAGCCGGGAGCAGGGGTAAACCTGGTAAAGTGCCGGGAG
 TAGGTCTGCCAGGCGTTATCCTGGTGGTGTGTTTCCCGGGTGCCCGTTTTC
 CGGGCGTTGGTGTCTTCCAGGCGTGCCGACCGGAGCCGGTGTAAACCG
 30 AAAGCCCCCGGTGTTGGAGGTGCATTTGCAGGCATCCCGGGAGTTGGCCC
 GTTTGGTGGTCCGCAACCTGGGGTTCGGTTAGGTTATCCGATTAAAGCACC
 GAAACTGCCCCGGCGGTTATGGTCTGCCGTACACAACCGGTAAACTGCCGT
 ATGGTTATGGCCCCGGGTGGAGTTGCGGGTGCAGCAGGTAAAGCGGGTTAT
 CCTACCGGAACCGGTGTAGGTCCGCAGGCCGCTGCTGCCGCCGCCGCAAA

AGCAGCGGCTAAATTTGGCGCCGGAGCAGCGGGTGTTCCTGCCTGGAGTTG
GTGGTGCGGGCGTGCCAGGGGTACCTGGTGCAATCCGGGTATTGGTGGT
ATTGCCGGTGTCCGGACCCCGGCCGGCAGCTGCGGCAGCGGCGGCTGC
CAAAGCTGCTAAATACGGTGCCCGGGCGGGTCTGGTGCCAGGAGGTCCGG
5 GTTTTGGTCCGGGAGTGGTTGGCGTGCCTGGCGCAGGCGTTCCTGGTGTGG
GCGTTCAGGTGCAGGGATTCTGTGTGCCTGGTGCCGGTATTCCCGGCG
CGGCCGTTCGGGGGGTGGTTAGCCCGGAAGCCGCAGCGAAGGCTGCGGC
AAAGGCAGCAAAGTATGGCGCACGCCAGGAGTCGGCGTGGGTGGTATC
CCGACCTATGGGGTGGGCGCAGGGGGTTTTCTGGTTTCGGCGTAGGTGT
10 AGGAGGTATACCGGGCGTGGCCGGTGTACCAGGGGTTGGTGGCGTCCCTG
GTGTTGGCGGTGTGCCAGGTGTTGGTATTTACCGGAAGCACAGGCAGCA
GCCGCAGCTAAGGCAGCGAAATATGGTGCCGCCGGCGCAGGAGTTTTAGG
TGGGCTGGTTCGGGGCCCGCAGGCAGCTGTGCCGGGGGTTCAGGCACCG
GTGGTGTCCCTGGAGTCGGTACGCCGGCTGCAGCGGCAGCCAAAGCGGCT
15 GCGAAAGCAGCACAGTTTGGCTTAGTACCGGGTGTGGGAGTTGCCCCCGG
CGTTGGCGTTGCTCCAGGGGTGGGTGTTGCTCCTGGCGTCGGTCTGGCTCC
TGGAGTGGGCGTAGCACCCGGTGTGGGGGTGGCCCCGGGTGTTGGGGTTG
CACCGGGTATCGGTCCGGGCGGTGTGCGCAGCAGCAGCTAAAAGCGCGGC
GAAAGTTGCGGCCAAAGCCCAACTGCGCGCCGCCGCGGGCCTCGGTGCAG
20 GTATTCGGGGGTGGGTGTGCGAGTTGGAGTCCCGGGTTTGGGCGTGGGC
GCGGGAGTTCCGGGACTGGGAGTGGGTGCCGGAGTTCCTGGCTTTGGTGC
AGGCGCAGATGAAGGTGTTTCGTCTAGCCTGAGTCCGGAAGTGCCTGAAG
GTGATCCGAGTAGCAGCCAGCATCTGCCGAGCACCCCGAGCAGCCCGCGT
GTTCCGGGTGCATTAGCTGCAGCAAAAGCCGCCAAGTATGGTGCAGCCGT
25 GCCGGGCGTCTTAGGTGGTCTGGGCGCCCTGGGTGGTGTAGGCATTCCGG
GAGGTGTTGTGGGTGCAGGACCGGCCGCCGAGCTGCGGCCGCCAAAGC
AGCTGCAAAAGCGGCCCAAGTTTGGTTTAGTGGGCGCCGCAGGTTTAGGCG
GTTTAGGTGTGGGTGGACTGGGTGTACCTGGCGTAGGCGGTCTGGGTGGA
ATTCCGCCCCGAGCGGCCCGCAAAGCGGC AAAATATGGCGCGGCAGGCC
30 TGGGCGGCGTGCTGGGTGGGGCAGGTCAGTTTCCGCTGGGCGGGGTTGCC
GCACGTCCGGGATTTGGTCTGAGCCCGATTTTCCCTGGCGGCGCATGTCTG
GGTAAAGCATGTGGTCGTAAACGTAAAtaa (SEQ ID NO: 34)

[0181] The amino acid sequence of a 57 kDa human elastin truncated at the C-terminal is disclosed in SEQ ID NO: 35. The 57 kDa truncated elastin has amino acids 661-761 deleted from the full length elastin.

GGVPGAIPGGVPGGVFYPGAGLGALGGGALGPGGKPLKPVPGGLAGAGLGA
 5 GLGAFAVTFPGALVPGGVADAAAAYKAAKAGAGLGGVPGVGGGLGVSAGA
 VVPQPGAGVKPGKVPVGLPGVYPGGVLPGARFPVGVLPVPTGAGVKPK
 APGVGGAFAGIPGVGPFGGPQPGVPLGYPIKAPKLPGGYGLPYTTGKLPYGY
 GPGGVAGAAGKAGYPTGTGVGPQAAAAAAKAAKFGAGAAGVLPVGG
 AGVPGVPGAIPGIGGIAGVGTAAAAAATAKAAKYGAAAGLVPGGPGFG
 10 PGVVGVPGAGVPGVGPVPGAGIPVVPAGIPGAAVPGVVSPEAAKAAKAA
 KYGARPGVGVGGIPTYGVGAGGFPFGVGVGGIPGVAGVPGVGGVPGVGGV
 PGVGISPEAQAAAAKAAKYGAAGAGVLGGLVPGPQAAVPGVPGTGGVPG
 VGTPAAAAKAAKAAQFGLVPGVGVAPGVGVAPGVGVAPGVGLAPGVGV
 APGVGVAPGVGVAPGIGPGGVAAAKSAKVAKAQLRAAAGLGAGIPGL
 15 GVGVPGLGVGAGVPGLGVGAGVPGFAGAGADEGVRRSLPELREGDPSSS
 QHLPSTPSSRPVPGALAAKAAKYGAAVPGVLGGLGALGGVGPVGGVAG
 P (SEQ ID NO: 35)

[0182] The codon optimized polynucleotide sequence encoding the 57 kDa truncated human elastin is disclosed in SEQ ID NO: 36

GGTGGCGTACCAGGCGCAATTCCTGGGGGTGTCCCAGGCGGTGTTTTTAT
 20 CCGGGCGCCGGTCTTGCGCACTGGGTGGCGGTGCACTGGGCCCCGGCGG
 CAAACCGCTGAAACCGGTACCAGGTGGTTTAGCAGGCGCCGGCTTAGGCG
 CAGGTCTGGGAGCATTTCCGGCAGTTACCTTTCCAGGGGCACTGGTTCCTG
 GAGGTGTGGCCGATGCAGCCGCGGCATATAAAGCCGCTAAAGCCGGTGCG
 25 GGTTTAGGAGGCGTCCCAGGTGTCCGTGGCCTGGGTGTTAGCGCCGGTGC
 AGTTGTTCCGCAGCCGGGAGCAGGGGTAAACCTGGTAAAGTGCCGGGAG
 TAGGTCTGCCAGGCGTTTATCCTGGTGGTGTGTTTGCCGGGTGCCCGTTTTT
 CGGGCGTTGGTGTCTTCCAGGCGTGCCGACCGGAGCCGGTGTTAAACCG
 AAAGCCCCCGGTGTTGGAGGTGCATTTGCAGGCATCCCGGGAGTTGGCCC
 30 GTTTGGTGGTCCGCAACCTGGGGTTCGTTAGGTTATCCGATTAAAGCACC
 GAAACTGCCCCGGCGGTTATGGTCTGCCGTACACAACCGGTAAACTGCCGT
 ATGGTTATGGCCCGGGTGGAGTTGCGGGTGCAGCAGGTAAAGCGGGTTAT
 CCTACCGGAACCGGTGTAGGTCCGCAGGCCGCTGCTGCCGCCGCCGCAAA
 AGCAGCGGCTAAATTTGGCGCCGGAGCAGCGGTGTTCTGCCTGGAGTTG

GTGGTGC GGCGGTGCCAGGGGTACCTGGTGCAATTCCGGGTATTGGTGGT
 ATTGCCGGTGT CGGCACCCCGGCCGCGGCAGCTGCGGCAGCGGCGGCTGC
 CAAAGCTGCTAAATACGGTGCCGCGGCGGGTCTGGTGCCAGGAGGTCCGG
 GTTTTGGTCCGGGAGTGGTTGGCGTGCCTGGCGCAGGCGTTCCTGGTGTGG
 5 GCGTTCAGGTGCAGGGATTCTGTGTGCCTGGTGCCGGTATTCCCGGCG
 CGGCCGTTCCGGGGGTGGTTAGCCCGGAAGCCGCAGCGAAGGCTGCGGC
 AAAGGCAGCAAAGTATGGCGCACGCCAGGAGTGGCGTGGGTGGTATC
 CCGACCTATGGGGTGGGCGCAGGGGGTTCCTGGTTTCGGCGTAGGTGT
 AGGAGGTATACCGGGCGTGGCCGGTGTACCAGGGGTTGGTGGCGTCCCTG
 10 GTGTTGGCGGTGTGCCAGGTGTTGGTATTTACCGGAAGCACAGGCAGCA
 GCCGCAGCTAAGGCAGCGAAATATGGTGCCGCCGGCGCAGGAGTTTTAGG
 TGGGCTGGTTCGGGGCCCGCAGGCAGCTGTGCCGGGGGTTCAGGCACCG
 GTGGTGTCCCTGGAGTCGGTACGCCGGCTGCAGCGGCAGCCAAAGCGGCT
 GCGAAAGCAGCACAGTTTGGCTTAGTACCGGGTGTGGGAGTTGCCCCCG
 15 CGTTGGCGTTGCTCCAGGGGTGGGTGTTGCTCCTGGCGTCGGTCTGGCTCC
 TGGAGTGGGCGTAGCACCCGGTGTGGGGGTGGCCCCGGGTGTTGGGGTTG
 CACCGGGTATCGGTCCGGGCGGTGTCGCAGCAGCAGCTAAAAGCGCGGC
 GAAAGTTGCGGCCAAAGCCCAACTGCGCGCCGCCGCGGGCCTCGGTGCAG
 GTATTCCGGGGCTGGGTGTCCGAGTTGGAGTCCCGGGTTTGGGCGTGGGC
 20 GCGGGAGTTCCGGGACTGGGAGTGGGTGCCGGAGTTCCTGGCTTTGGTGC
 AGGCGCAGATGAAGGTGTTTCGTCTAGCCTGAGTCCGGAAGTGCCTGAAG
 GTGATCCGAGTAGCAGCCAGCATCTGCCGAGCACCCCGAGCAGCCCGCGT
 GTTCCGGGTGCATTAGCTGCAGCAAAAGCCGCCAAGTATGGTGCAGCCGT
 GCCGGGCGTCTTAGGTGGTCTGGGCGCCCTGGGTGGTGTAGGCATTCCGG
 25 GAGGTGTTGTGGGTGCAGGACCGtaa (SEQ ID NO: 36)

[0183] The amino acid sequence of a 53.9 kDa human elastin truncated at the C-terminal is disclosed in SEQ ID NO: 37. The 53.9 kDa truncated elastin has amino acids 624-761 deleted from the full length elastin.

GGVPGAIPGGVPGGVFYPGAGLGALGGGALGPGGKPLKPVPGGLAGAGLGA
 30 GLGAFPVAVTFPGALVPGGVADAAAAYKAAKAGAGLGGVPGVGGGLVVSAGA
 VVPQPGAGVKPGKVPVGLPGVYPGGVLPGARFPGVGVLPVPTGAGVKPK
 APGVGGAFAIPGVGPFGGPQPGVPLGYPIKAPKLPGGYGLPYTTGKLPYGY
 GPGGVAGAAGKAGYPTGTGVGPQAAAAAAKAAAKFGAGAAGVLPVGG
 AGVPGVPGAIPGIGGIAGVGTAAAAAAAKAAKYGAAAGLVPGGPGFG

PGVVGVPGAGVPGVGVPGAGIPVVPAGIPGAAVPGVVSPEAAAKAAAKAA
KYGARPGVGVGGIPTYGVLGAGGFPFGVGVGGIPGVAGVPGVGGVPGVGGV
PGVGISPEAQAAAAAKAAKYGAAGAGVLGGLVPGPQAAVPGVPGTGGVPG
VGTPAAAAAKAAAKAAQFGLVPGVGVAPGVGVAPGVGVAPGVGLAPGVGV
5 APGVGVAPGVGVAPGIGPGGVAAAAKSAAKVAAKAQLRAAAGLGAGIPGL
GVGVGVPGLVGAGVPGLGVGAGVPGFGAGADEGVRRSLSPELREGDPSSS
QHLPSTPSSPRVPGA (SEQ ID NO: 37)

[0184] The codon optimized polynucleotide sequence encoding the 53.9 kDa truncated human elastin is disclosed in SEQ ID NO: 38

10 GGTGGCGTACCAGGCGCAATTCCTGGGGGTGTCCCAGGCGGTGTTTTTAT
CCGGGCGCCGGTCTTGCGCACTGGGTGGCGGTGCACTGGGCCCCGGGCGG
CAAACCGCTGAAACCGGTACCAGGTGGTTTAGCAGGCGCCGGCTTAGGCG
CAGGTCTGGGAGCATTTCGGCAGTTACCTTTCCAGGGGCACTGGTTCCTG
GAGGTGTGGCCGATGCAGCCGCGGCATATAAAGCCGCTAAAGCCGGTGCG
15 GGTTTAGGAGGCGTCCCAGGTGTGGTGGCCTGGGTGTTAGCGCCGGTGC
AGTTGTTCCGCAGCCGGGAGCAGGGGTAAACCTGGTAAAGTGCCGGGAG
TAGGTCTGCCAGGCGTTTATCCTGGTGGTGTGTTTGCCGGGTGCCCGTTTT
CGGGCGTTGGTGTTCTTCAGGCGTGCCGACCGGAGCCGGTGTTAAACCG
AAAGCCCCCGGTGTTGGAGGTGCATTTGCAGGCATCCCGGGAGTTGGCCC
20 GTTTGGTGGTCCGCAACCTGGGGTTCGTTAGGTTATCCGATTAAAGCACC
GAAACTGCCCCGGCGGTTATGGTCTGCCGTACACAACCGGTAAACTGCCGT
ATGGTTATGGCCCCGGTGGAGTTGCGGGTGACAGCAGGTAAAGCGGGTTAT
CCTACCGGAACCGGTGTAGGTCCGCAGGCCGCTGCTGCCGCCGCCGCAAA
AGCAGCGGCTAAATTTGGCGCCGGAGCAGCGGGTGTTCTGCCTGGAGTTG
25 GTGGTGCGGGCGTGCCAGGGGTACCTGGTGCAATTCGGGTATTGGTGGT
ATTGCCGGTGTGCGCACCCCGGCCGCGGCAGCTGCGGCAGCGGCGGCTGC
CAAAGCTGCTAAATACGGTGCCGCGGCGGGTCTGGTGCCAGGAGGTCCGG
GTTTTGGTCCGGGAGTGGTTGGCGTGCTGGCGCAGGCGTTCCTGGTGTGG
GCGTTCAGGTGCAGGGATTCTGTTGTGCCTGGTGCCGGTATTCCCGGCG
30 CGGCCGTTCCGGGGGTGGTTAGCCCGGAAGCCGCAGCGAAGGCTGCGGC
AAAGGCAGCAAAGTATGGCGCACGCCAGGAGTCGGCGTGGGTGGTATC
CCGACCTATGGGGTGGGCGCAGGGGGTTTTCTGGTTTCGGCGTAGGTGT
AGGAGGTATACCGGGCGTGGCCGGTGTACCAGGGGTGGTGGCGTCCCTG
GTGTTGGCGGTGTGCCAGGTGTTGGTATTTACCGGAAGCACAGGCAGCA

GCCGCAGCTAAGGCAGCGAAATATGGTGCCGCCGGCGCAGGAGTTTTAGG
 TGGGCTGGTTCCGGGGCCGCAGGCAGCTGTGCCGGGGGTCCAGGCACCG
 GTGGTGTCCCTGGAGTCGGTACGCCGGCTGCAGCGGCAGCCAAAGCGGCT
 GCGAAAGCAGCACAGTTTGGCTTAGTACCGGGTGTGGGAGTTGCCCCCGG
 5 CGTTGGCGTTGCTCCAGGGGTGGGTGTTGCTCCTGGCGTCCGTCTGGCTCC
 TGGAGTGGGCGTAGCACCCGGTGTGGGGGTGGCCCCGGGTGTTGGGGTTG
 CACCGGGTATCGGTCCGGGCGGTGTCGCAGCAGCAGCTAAAAGCGCGGC
 GAAAGTTGCGGCCAAAGCCCAACTGCGCGCCGCCGCGGGCCTCGGTGCAG
 GTATTCCGGGGCTGGGTGTCGGAGTTGGAGTCCCGGGTTTGGGCGTGGGC
 10 GCGGGAGTTCCGGGACTGGGAGTGGGTGCCGGAGTTCCTGGCTTTGGTGC
 AGGCGCAGATGAAGGTGTTTCGTCTAGCCTGAGTCCGGAAGTGCCTGAAG
 GTGATCCGAGTAGCAGCCAGCATCTGCCGAGCACCCCGAGCAGCCCGCGT
 GTTCCGGGTGCAtaa (SEQ ID NO: 38)

[0185] The amino acid sequence of a 45.3 kDa human elastin truncated at the C-
 15 terminal is disclosed in SEQ ID NO: 39. The 45.3 kDa truncated elastin has amino
 acids 529-761 deleted from the full length elastin.

GGVPGAIPGGVPGGVFYPGAGLGALGGGALGPGGKPLKVPVPGGLAGAGLGA
 GLGAFAVTFPGALVPGGVADAAAAYKAAKAGAGLGGVPGVGGGLVVSAGA
 VVPQPGAGVKPGKVPGVGLPGVYPGGVLPGARFPGVGVLPVPTGAGVKPK
 20 APGVGGAFAIPGVGPFGGPQPGVPLGYPIKAPKLPGGYGLPYTTGKLPYGY
 GPGGVAGAAGKAGYPTGTGVGPQAAAAAAKAAKFGAGAAGVLPVGG
 AGVPGVPGAIPGIGGIAGVGTPAAAAAAKAAKYGAAAGLVPGGPGFG
 PGVVGVPAGVPGVPGVPGAGIPVVPAGIPGAAPVPGVVSPEAAKAAKAA
 KYGARPGVGVGGIPTYGVGAGGFPFGVGVGGIPGVAGVPGVGGVPGVGGV
 25 PGVGISPEAQAAAAKAAKYGAAGAGVLGGLVPGPQAAVPGVPGTGGVPG
 VGTPAAAAKAAKAAQFGLVPGVGVAPGVGVAPGVGVAPGVGLAPGVGV
 APGVGVAPGVGVAPGIGPGGV (SEQ ID NO: 39)

[0186] The codon optimized polynucleotide sequence encoding the 45.3 kDa
 truncated human elastin is disclosed in SEQ ID NO: 40

GGTGGCGTACCAGGCGCAATTCCTGGGGGTGTCCCAGGCGGTGTTTTTAT
 30 CCGGGCGCCGGTCTTGCGCACTGGGTGGCGGTGCACTGGGCCCCGGGCGG
 CAAACCGCTGAAACCGGTACCAGGTGGTTTAGCAGGCGCCGGCTTAGGCG
 CAGGTCTGGGAGCATTTCCGGCAGTTACCTTTCCAGGGGCACTGGTTCCTG
 GAGGTGTGGCCGATGCAGCCGCGGCATATAAAGCCGCTAAAGCCGGTGCG

GGTTTAGGAGGCGTCCCAGGTGTCGGTGGCCTGGGTGTTAGCGCCGGTGC
 AGTTGTTCCGCAGCCGGGAGCAGGGGTAAACCTGGTAAAGTGCCGGGAG
 TAGGTCTGCCAGGCGTTTATCCTGGTGGTGTGTTTGGCCGGGTGCCC GTTTTC
 CGGGCGTTGGTGTCTTCCAGGCGTGCCGACCGGAGCCGGTGTTAAACCG
 5 AAAGCCCCCGGTGTTGGAGGTGCATTTGCAGGCATCCCGGGAGTTGGCCC
 GTTTGGTGGTCCGCAACCTGGGGTTCGGTTAGGTTATCCGATTAAAGCACC
 GAAACTGCCCCGGCGGTATGGTCTGCCGTACACAACCGGTAAACTGCCGT
 ATGGTTATGGCCCCGGTGGAGTTGCGGGTGCAGCAGGTAAAGCGGGTAT
 CCTACCGGAACCGGTGTAGGTCCGCAGGCCGCTGCTGCCGCCGCCGCAAA
 10 AGCAGCGGCTAAATTTGGCGCCGGAGCAGCGGGTGTTCTGCCTGGAGTTG
 GTGGTGCGGGCGTGCCAGGGGTACCTGGTGCAATTCCGGGTATTGGTGGT
 ATTGCCGGTGTGCGCACCCCGGCCGCGGCAGCTGCGGCAGCGGCGGCTGC
 CAAAGCTGCTAAATACGGTGCCGCGGCGGGTCTGGTGCCAGGAGGTCCGG
 GTTTTGGTCCGGGAGTGGTTGGCGTGCTGGCGCAGGCGTTCCCTGGTGTGG
 15 GCGTTCAGGTGCAGGGATTCTGTGTGCCTGGTGCCGGTATTCCCGGCG
 CGGCCGTTCCGGGGGTGGTTAGCCCGGAAGCCGCAGCGAAGGCTGCGGC
 AAAGGCAGCAAAGTATGGCGCACGCCAGGAGTCGGCGTGGGTGGTATC
 CCGACCTATGGGGTGGGCGCAGGGGGTTTTCTGGTTTCGGCGTAGGTGT
 AGGAGGTATACCGGGCGTGGCCGGTGTACCAGGGGTGGTGGCGTCCCTG
 20 GTGTTGGCGGTGTGCCAGGTGTTGGTATTTACCGGAAGCACAGGCAGCA
 GCCGCAGCTAAGGCAGCGAAATATGGTGCCGCCGGCGCAGGAGTTTTAGG
 TGGGCTGGTTCCGGGGCCCGCAGGCAGCTGTGCCGGGGGTTCAGGCACCG
 GTGGTGTCCCTGGAGTCGGTACGCCGGCTGCAGCGGCAGCCAAAGCGGCT
 GCGAAAGCAGCACAGTTTGGCTTAGTACCGGGTGTGGGAGTTGCCCCCGG
 25 CGTTGGCGTTGCTCCAGGGGTGGGTGTTGCTCCTGGCGTCGGTCTGGCTCC
 TGGAGTGGGCGTAGCACCCGGTGTGGGGGTGGCCCCGGGTGTTGGGGTTG
 CACCGGGTATCGGTCCGGGCGGTGTctaa (SEQ ID NO: 40)

[0187] The amino acid sequence of a 44.4 kDa human elastin truncated at the N-
 terminal is disclosed in SEQ ID NO: 41. The 44.4 kDa truncated elastin has amino
 30 acids 2-246 deleted from the full length elastin.

GVLPGVGGAGVPGVPGAIPGIGGIAGVGTAAAAA AAKA AAKYGAAAGL
 VPGGPGFGPGVVGVPAGVPGVGPAGIPVPGAGIPGAAPGVVSPEAAA
 KAAAKAAKYGARPGVGVGGIPTYGVGAGGFPGFGVGVGGIPGVAGVPGVG
 GVPGVGGVPGVGISPEAQAAAAA AAKYGAAGAGVLGGLVPGPQAAVPGV

PGTGGVPGVGTAAAAKAAKAAQFGLVPGVGVAPGVGVAPGVGVAPGV
 GLAPGVGVAPGVGVAPGVGVAPGIGPGGVAAAASAAKVAAKAQLRAAAG
 LGAGIPGLGVGVGPGLGVGAGVPGLGVGAGVPGFGAGADEGVRRSLSP
 REGDPSSSQHLPSTPSSPRVPGALAAKAAKYGAAVPGVLGGLGALGGVGIP
 5 GGVVGAGPAAAAAAKAAKAAQFGLVGAAGLGGLGVGGLGVPGVGGLG
 GIPAAAAKAAKYGAAGLGGLVGGAGQFPLGGVAARPGFGLSPIFPGGACLG
 KACGRKRK (SEQ ID NO: 41)

[0188] The codon optimized polynucleotide sequence encoding the 44.4 kDa truncated human elastin is disclosed in SEQ ID NO: 42

10 GGTGTTCTGCCTGGAGTTGGTGGTGCAGGGGTACCTGGTGC
 AATTCGGGTATTGGTGGTATTGCCGGTGTCCGCACCCCGCCGCGGCAG
 CTGCGGCAGCGCGGCTGCCAAAGCTGCTAAATACGGTGCAGCGCGCGGT
 CTGGTGCCAGGAGGTCCGGGTTTTGGTCCGGGAGTGGTTGGCGTGCCTGG
 CGCAGGCGTTCCTGGTGTGGGCGTTCAGGTGCAGGGATTCTGTGTGCC
 15 TGGTGCCGGTATTCCCGGCGCGGCCGTTCCGGGGGTGGTTAGCCCGGAAG
 CCGCAGCGAAGGCTGCGGCAAAGGCAGCAAAGTATGGCGCACGCCAGG
 AGTCGGCGTGGGTGGTATCCCGACCTATGGGGTGGGCGCAGGGGGTTTC
 CTGGTTTTCGGCGTAGGTGTAGGAGGTATACCGGGCGTGCCCGGTGTACCA
 GGGGTTGGTGGCGTCCCTGGTGTGGCGGTGTGCCAGGTGTTGGTATTTCA
 20 CCGGAAGCACAGGCAGCAGCCGAGCTAAGGCAGCGAAATATGGTGCCG
 CCGGCGCAGGAGTTTTAGGTGGGCTGGTTCCGGGGCCCGCAGGCAGCTGTG
 CCGGGGGTTCCAGGCACCGGTGGTGTCCCTGGAGTCGGTACGCCGGCTGC
 AGCGGCAGCCAAAGCGGCTGCGAAAGCAGCACAGTTTGGCTTAGTACCGG
 GTGTGGGAGTTGCCCGCGGCTTGCGGCTGCTCCAGGGGTGGGTGTTGCTC
 25 CTGGCGTCGGTCTGGCTCCTGGAGTGGGCGTAGCACCCGGTGTGGGGGTG
 GCGCCGGGTGTTGGGGTTGCACCGGGTATCGGTCCGGGCGGTGTGCAGC
 AGCAGCTAAAAGCGCGGCGAAAGTTGCGGCCAAAGCCCAACTGCGCGCC
 GCCGCGGGCCTCGGTGCAGGTATTCCGGGGCTGGGTGTGCGAGTTGGAGT
 CCCGGGTTTGGGCGTGGGCGCGGGAGTTCCGGGACTGGGAGTGGGTGCCG
 30 GAGTTCCTGGCTTTGGTGCAGGCGCAGATGAAGGTGTTCTCGTCGTAGCCTG
 AGTCCGGAACTGCGTGAAGGTGATCCGAGTAGCAGCCAGCATCTGCCGAG
 CACCCCGAGCAGCCCGCGTGTTCGGGGTGCATTAGCTGCAGCAAAAGCCG
 CCAAGTATGGTGCAGCCGTGCCGGGCGTCTTAGGTGGTCTGGGCGCCCTG
 GGTGGTGTAGGCATTCCGGGAGGTGTTGTGGGTGCAGGACCGGCCGCCG

AGCTGCGGCCGCCAAAGCAGCTGCAAAAGCGGCCAGTTTGGTTTAGTGG
 GCGCCGCAGGTTTAGGCGGTTTAGGTGTGGGTGGACTGGGTGTACCTGGC
 GTAGGCGGTCTGGGTGGAATCCGCCCGCAGCGGCCGCGAAAGCGGCAA
 AATATGGCGCGGCAGGCCTGGGCGGCGTGCTGGGTGGGGCAGGTCAGTTT
 5 CCGCTGGGCGGGGTTGCCGCACGTCCGGGATTTGGTCTGAGCCCGATTTTC
 CCTGGCGGCGCATGTCTGGGTAAAGCATGTGGTCTGTAACGTAAAtaa
 (SEQ ID NO: 42)

[0189] The amino acid sequence of a 40.4 kDa human elastin truncated at the N-terminal is disclosed in SEQ ID NO: 43. The 40.4 kDa truncated elastin has amino
 10 acids 2-295 deleted from the full length elastin.

GLVPGGPGFGPGVVGVPGAGVPGVGVPGAGIPVVPAGIPGAAVPGVVSPEA
 AAKAAKAAKYGARPGVGVGGIPTYGVGAGGFPGFGVGVGGIPGVAGVPG
 VGGVPGVGGVPGVGISPEAQAAAAKAAKYGAAGAGVLGGLVPGPQAAVP
 GVPGTGGVPGVGTAAAAKAAKAAQFGLVPGVGVAPGVGVAPGVGVAP
 15 GVGLAPGVGVAPGVGVAPGVGVAPGIGPGGVAAAKSAKVAKAQLRAA
 AGLGAGIPGLGVGVVPGLVGAGVPGLVGAGVPGFAGADEGVRRLSP
 ELREGDPSSSQHLPSTPSSPRVPGALAAKAAKYGAAVPGVLGGLGALGGVG
 IPGGVVGAGPAAAAAAKAAKAAQFGLVGAAGLGLGVGGLVPGVGG
 GGIPAAAAKAAKYGAAGLGGVLGGAGQFPLGGVAARPGFGLSPIFPGGACL
 20 GKACGRKRK (SEQ ID NO: 43)

[0190] The codon optimized polynucleotide sequence encoding the 40.4 kDa truncated human elastin is disclosed in SEQ ID NO: 44

GGTCTGGTGCCAGGAGGTCCGGGTTTTGGTCCGGGAGTGGTTGGCGTGCC
 TGCGCGAGGCGTTCCTGGTGTGGGCGTTCCAGGTGCAGGGATTCTGTGT
 25 GCCTGGTGCCGGTATTCCCGGCGCGGCCGTTCCGGGGGTGGTTAGCCCGG
 AAGCCGCAGCGAAGGCTGCGGCAAAGGCAGCAAAGTATGGCGCACGCCC
 AGGAGTCGGCGTGGGTGGTATCCCGACCTATGGGGTGGGCGCAGGGGGTT
 TTCCTGGTTTCGGCGTAGGTGTAGGAGGTATACCGGGCGTGGCCGGTGTA
 CCAGGGGTTGGTGGCGTCCCTGGTGTGGCGGTGTGCCAGGTGTTGGTATT
 30 TCACCGGAAGCACAGGCAGCAGCCGCAGCTAAGGCAGCGAAATATGGTG
 CCGCCGGCGCAGGAGTTTTAGGTGGGCTGGTTCCGGGCCCCGCAGGCAGCT
 GTGCCGGGGTTCCAGGCACCGGTGGTGTCCCTGGAGTCGGTACGCCGGC
 TGCAGCGGCAGCCAAAGCGGCTGCGAAAGCAGCACAGTTTGGCTTAGTAC
 CGGGTGTGGGAGTTGCCCCCGGCGTTGGCGTTGCTCCAGGGGTGGGTGTT

GCTCCTGGCGTCGGTCTGGCTCCTGGAGTGGGCGTAGCACCCGGTGTGGG
 GGTGGCCCCGGGTGTTGGGGTTGCACCGGGTATCGGTCCGGGCGGTGTGCG
 CAGCAGCAGCTAAAAGCGCGGCGAAAGTTGCGGCCAAAGCCCAACTGCG
 CGCCGCCGCGGGCCTCGGTGCAGGTATTCCGGGGCTGGGTGTGCGAGTTG
 5 GAGTCCCGGGTTTGGGCGTGGGCGCGGGAGTTCCGGGACTGGGAGTGGGT
 GCCGGAGTTCCTGGCTTTGGTGCAGGCGCAGATGAAGGTGTTTCGTCGTAG
 CCTGAGTCCGGAAGTGCCTGAAGGTGATCCGAGTAGCAGCCAGCATCTGC
 CGAGCACCCCGAGCAGCCGCGTGTTCGGGTGCATTAGCTGCAGCAAAA
 GCCGCCAAGTATGGTGCAGCCGTGCCGGGCGTCTTAGGTGGTCTGGGCGC
 10 CCTGGGTGGTGTAGGCATTCCGGGAGGTGTTGTGGGTGCAGGACCGGCCG
 CCGCAGCTGCGGCCGCCAAAGCAGCTGCAAAAGCGGCCAGTTTGGTTTA
 GTGGGCGCCGAGGTTTAGGCGGTTTAGGTGTGGGTGGACTGGGTGTACC
 TGGCGTAGGCGGTCTGGGTGGAATTCCGCCCCGAGCGGCCGCGAAAGCGG
 CAAAATATGGCGCGGCAGGCCTGGGCGGCGTGCTGGGTGGGGCAGGTCA
 15 GTTTCGCTGGGCGGGGTTGCCGCACGTCCGGGATTTGGTCTGAGCCCGAT
 TTTCCCTGGCGGCGCATGTCTGGGTAAAGCATGTGGTCGTAAACGTAAAtaa
 (SEQ ID NO: 44)

[0191] The amino acid sequence of a 39.8 kDa human elastin truncated at the C-
 terminal is disclosed in SEQ ID NO: 45. The 39.8 kDa truncated elastin has amino
 20 acids 462-761 deleted from the full length elastin.

GGVPGAIPGGVPGGVFYPGAGLGALGGGALGPGGKPLKPVPGGLAGAGLGA
 GLGAFAVTFPGALVPGGVADAAAAYKAAKAGAGLGGVPGVGGLGVSAGA
 VVPQPGAGVKPGKVPGVGLPGVYPGGVLPGARFPGVGVLPGVPTGAGVKPK
 APGVGGAFAGIPGVGPFGGPQPGVPLGYPIKAPKLPGGYGLPYTTGKLPYGY
 25 GPGGVAGAAGKAGYPTGTGVGPQAAAAAAKAAAKFGAGAAGVLPGVGG
 AGVPGVPGAIPGIGGIAGVGTPAAAAAAKAAKYGAAAGLVPGGPFGF
 PGVVGVPAGVPGVPGVPGAGIPVPGAGIPGAAPGVVSPEAAKAAAKAA
 KYGARPGVGVGGIPTYGVGAGGFPFGVGVGGIPGVAGVPGVGGVPGVGGV
 PGVGISPEAQAAAAKAAKYGAAGAGVLGGLVPGPQAAVPGVPGTGGVPG
 30 VGTP (SEQ ID NO: 45)

[0192] The codon optimized polynucleotide sequence encoding the 39.8 kDa
 truncated human elastin is disclosed in SEQ ID NO: 46

GGTGGCGTACCAGGCGCAATTCCTGGGGGTGTCCCAGGCGGTGTTTTTAT
 CCGGGCGCCGGTCTTGCGCACTGGGTGGCGGTGCACTGGGCCCCGGGCGG

CAAACCGCTGAAACCGGTACCAGGTGGTTTAGCAGGCGCCGGCTTAGGCG
 CAGGTCTGGGAGCATTTCGGCAGTTACCTTTCAGGGGCACTGGTTCCTG
 GAGGTGTGGCCGATGCAGCCGCGGCATATAAAGCCGCTAAAGCCGGTGCG
 GGTTTAGGAGGCGTCCCAGGTGTCGGTGGCCTGGGTGTTAGCGCCGGTGC
 5 AGTTGTTCCGCAGCCGGGAGCAGGGGTAAACCTGGTAAAGTGCCGGGAG
 TAGGTCTGCCAGGCGTTTATCCTGGTGGTGTGTTTGCCGGGTGCCCGTTTTC
 CGGGCGTTGGTGTCTTCCAGGCGTGCCGACCGGAGCCGGTGTTAAACCG
 AAAGCCCCCGGTGTTGGAGGTGCATTTGCAGGCATCCCGGGAGTTGGCCC
 GTTTGGTGGTCCGCAACCTGGGGTTCGGTTAGGTTATCCGATTAAAGCACC
 10 GAAACTGCCCCGGCGGTATGGTCTGCCGTACACAACCGGTAAACTGCCGT
 ATGGTTATGGCCCCGGGTGGAGTTGCGGGTGCAGCAGGTAAAGCGGGTAT
 CCTACCGGAACCGGTGTAGGTCCGCAGGCCGCTGCTGCCGCCGCCGCAAA
 AGCAGCGGCTAAATTTGGCGCCGGAGCAGCGGGTGTCTGCCTGGAGTTG
 GTGGTGCGGGCGTGCCAGGGGTACCTGGTGCAATTCCGGGTATTGGTGGT
 15 ATTGCCGGTGTCCGCACCCCGGCCGCGGCAGCTGCGGCAGCGGCGGCTGC
 CAAAGCTGCTAAATACGGTGCCGCGGCGGGTCTGGTGCCAGGAGGTCCGG
 GTTTTGGTCCGGGAGTGGTTGGCGTGCCTGGCGCAGGCGTTCCTGGTGTGG
 GCGTTCAGGTGCAGGGATTCTGTGTGCCTGGTGCCGGTATTCCCGGCG
 CGGCCGTTCGGGGGTGGTTAGCCCGGAAGCCGCAGCGAAGGCTGCGGC
 20 AAAGGCAGCAAAGTATGGCGCACGCCAGGAGTCGGCGTGGGTGGTATC
 CCGACCTATGGGGTGGGCGCAGGGGGTTTTCTGGTTTCGGCGTAGGTGT
 AGGAGGTATACGGGCGTGGCCGGTGTACCAGGGGTTGGTGGCGTCCCTG
 GTGTTGGCGGTGTGCCAGGTGTTGGTATTTACCGGAAGCACAGGCAGCA
 GCCGCAGCTAAGGCAGCGAAATATGGTGCCGCCGGCGCAGGAGTTTTAGG
 25 TGGGCTGGTTCCGGGCCCCGCAGGCAGCTGTGCCGGGGGTCCAGGCACCG
 GTGGTGTCCCTGGAGTCGGTACGCCGtaa (SEQ ID NO: 46)

[0193] The amino acid sequence of a 36.1 kDa human elastin truncated at the C-terminal is disclosed in SEQ ID NO: 47. The 36.1 kDa truncated elastin has amino acids 418-761 deleted from the full length elastin.

30 GGVPGAIPGGVPGGVFYPGAGLGALGGGALPGGKPLKPVPGGLAGAGLGA
 GLGAFPVAVTFPGALVPGGVADAAAAYKAAKAGAGLGGVPGVGGLGVSAGA
 VVPQPGAGVKPGKVPGVGLPGVYPGGVLPGARFPGVGVLPGVPTGAGVKPK
 APGVGGAFAIPGVGPFGGPQPGVPLGYPIKAPKLPGGYGLPYTTGKLPYGY
 GPGGVAGAAGKAGYPTGTGVGPQAAAAAAKAAAKFGAGAAGVLPGVGG

AGVPGVPGAIPGIGGIAGVGTAAAAAATAAKYGAAGLVPGGPGFG
PGVVGVPGAGVPGVGPAGIPVVPAGIPGAAPGVVSPEAAAKAAKAA
KYGARPGVGVGGIPTYGVGAGGFPFGVGVGGIPGVAGVPGVGGVPGVGGV
PGVGISPEAQ (SEQ ID NO: 47)

- 5 [0194] The codon optimized polynucleotide sequence encoding the 36.1 kDa truncated human elastin is disclosed in SEQ ID NO: 48

GGTGGCGTACCAGGCGCAATTCCTGGGGGTGTCCCAGGCGGTGTTTTTAT
CCGGGCGCCGGTCTTGCGCACTGGGTGGCGGTGCACTGGGCCCCGGGCGG
CAAACCGCTGAAACCGGTACCAGGTGGTTTAGCAGGCGCCGGCTTAGGCG
10 CAGGTCTGGGAGCATTTCCGGCAGTTACCTTTCCAGGGGCACTGGTTCCTG
GAGGTGTGGCCGATGCAGCCGCGGCATATAAAGCCGCTAAAGCCGGTGCG
GGTTTAGGAGGCGTCCCAGGTGTCGGTGGCCTGGGTGTTAGCGCCGGTGC
AGTTGTTCCGCAGCCGGGAGCAGGGGTAAACCTGGTAAAGTGCCGGGAG
TAGGTCTGCCAGGCGTTTATCCTGGTGGTGTTTTGCCGGGTGCCGTTTTTC
15 CGGGCGTTGGTGTTCCTCCAGGCGTGCCGACCGGAGCCGGTGTAAACCG
AAAGCCCCCGGTGTTGGAGGTGCATTTGCAGGCATCCCGGGAGTTGGCCC
GTTTGGTGGTCCGCAACCTGGGGTTCGGTTAGGTTATCCGATTAAAGCACC
GAAACTGCCCCGGCGGTTATGGTCTGCCGTACACAACCGGTAAACTGCCGT
ATGGTTATGGCCCCGGGTGGAGTTGCGGGTGCAGCAGGTAAAGCGGGTAT
20 CCTACCGGAACCGGTGTAGGTCCGCAGGCCGCTGCTGCCGCCGCCGCAAA
AGCAGCGGCTAAATTTGGCGCCGGAGCAGCGGGTGTTCGCCTGGAGTTG
GTGGTGCGGGCGTGCCAGGGGTACCTGGTGCATTCGGGGTATTGGTGGT
ATTGCCGGTGTCCGCACCCCGGCCGCGGCAGCTGCGGCAGCGGCGGCTGC
CAAAGCTGCTAAATACGGTGCCGCGGCGGGTCTGGTGCCAGGAGGTCCGG
25 GTTTTGGTCCGGGAGTGGTTGGCGTGCTGGCGCAGGCGTTCCTGGTGTGG
GCGTTCAGGTGCAGGGATTCTGTGTGCCTGGTGCCGGTATCCCGGCG
CGGCCGTTCCGGGGGTGGTTAGCCCGGAAGCCGCAGCGAAGGCTGCGGC
AAAGGCAGCAAAGTATGGCGCACGCCAGGAGTCGGCGTGGGTGGTATC
CCGACCTATGGGGTGGGCGCAGGGGGTTTTCTGGTTTCGGCGTAGGTGT
30 AGGAGGTATACCGGGCGTGGCCGGTGTACCAGGGGTGGTGGCGTCCCTG
GTGTTGGCGGTGTGCCAGGTGTTGGTATTTACCGGAAGCACAGtaa (SEQ
ID NO: 48)

[0195] The amino acid sequence of a 34.9 kDa human elastin truncated at the N-terminal is disclosed in SEQ ID NO: 49. The 34.9 kDa truncated elastin has amino acids 2-360 deleted from the full length elastin.

RPGVGVGGIPTYGVGAGGFPFGVGVGGIPGVAGVPGVGGVPGVGGVPGVG
 5 ISPEAQAAAAKAAKYGAAGAGVLGGLVPGPQAAVPGVPGTGGVPGVGT
 AAAKAAKAAQFGLVPGVGVAPGVGVAPGVGVAPGVGLAPGVGVAPGV
 GVAPGVGVAPGIGPGGVAAAKSAAKVAKAQLRAAAGLGAGIPGLGVGV
 GVPGLGVGAGVPGLGVGAGVPGFGAGADEGVRRSLSPELREGDPSSSQHLPS
 TPSSPRVPGALAAKAAKYGAAVPGVLGGLGALGGVGIPGGVVGAGPAAAA
 10 AAKAAKAAQFGLVGAAGLGGLGVGGLGVPGVGGLGGIPAAAAKAAKY
 GAAGLGGVLGGAGQFPLGGVAARPGFGLSPIFPGGACLGKACGRKRK (SEQ
 ID NO: 49)

[0196] The codon optimized polynucleotide sequence encoding the 34.9 kDa truncated human elastin is disclosed in SEQ ID NO: 50

CGCCCAGGAGTCGGCGTGGGTGGTATCCCGACCTATGGGGTGGGCGCAGG
 15 GGGTTTTCTGGTTTCGGCGTAGGTGTAGGAGGTATACCGGGCGTGGCCG
 GTGTACCAGGGGTGGTGGCGTCCCTGGTGTGGCGGTGTGCCAGGTGTT
 GGTATTTACCGGAAGCACAGGCAGCAGCCGACAGCTAAGGCAGCGAAAT
 ATGGTGCCGCCGGCGCAGGAGTTTTAGGTGGGCTGGTTCGGGGCCCGCAG
 20 GCAGCTGTGCCGGGGTTCCAGGCACCGGTGGTGTCCCTGGAGTCGGTAC
 GCCGGCTGCAGCGGCAGCCAAAGCGGCTGCGAAAGCAGCACAGTTTGGC
 TTAGTACCGGGTGTGGGAGTTGCCCGCGCGTTGGCGTTGCTCCAGGGGT
 GGGTGTGCTCCTGGCGTCGGTCTGGCTCCTGGAGTGGGCGTAGCACCCG
 GTGTGGGGGTGGCCCCGGGTGTTGGGGTTGCACCGGGTATCGGTCCGGGC
 25 GGTGTGCGCAGCAGCAGCTAAAAGCGCGGCGAAAGTTGCGGCCAAAGCCC
 AACTGCGCGCCGCCGCGGGCCTCGGTGCAGGTATTCGGGGGCTGGGTGTC
 GGAGTTGGAGTCCCGGGTTTGGGCGTGGGCGCGGGAGTTCCGGGACTGGG
 AGTGGGTGCCGAGTTCCTGGCTTTGGTGCAGGCGCAGATGAAGGTGTTT
 GTCGTAGCCTGAGTCCGGAAGTGCAGTGAAGGTGATCCGAGTAGCAGCCAG
 30 CATCTGCCGAGCACCCCGAGCAGCCCGCGTGTTCGGGGTGCATTAGCTGC
 AGCAAAAGCCGCCAAGTATGGTGCAGCCGTGCCGGGCGTCTTAGGTGGTC
 TGGGCGCCCTGGGTGGTGTAGGCATTCCGGGAGGTGTTGTGGGTGCAGGA
 CCGGCCGCCGAGCTGCGGCCGCCAAAGCAGCTGCAAAAGCGGCCAGTT
 TGGTTTAGTGGGCGCCGAGGTTTAGGCGGTTTAGGTGTGGGTGGACTGG

GTGTACCTGGCGTAGGCGGTCTGGGTGGAATTCGCCCCGAGCGGCCGCG
 AAAGCGGCAAAATATGGCGCGGCAGGCCTGGGCGGCGTGCTGGGTGGGG
 CAGGTCAGTTTCCGCTGGGCGGGGTTGCCGCACGTCCGGGATTTGGTCTG
 AGCCCGATTTTCCCTGGCGGCGCATGTCTGGGTAAAGCATGTGGTCGTAA
 5 ACGTAAAtaa (SEQ ID NO: 50)

[0197] The amino acid sequence of a 32 kDa human elastin truncated at the C-terminal is disclosed in SEQ ID NO: 51. The 32 kDa truncated elastin has amino acids 373-761 deleted from the full length elastin.

GGVPGAIPGGVPGGVFYPGAGLGALGGGALGPGGKPLKVPVPGGLAGAGLGA
 10 GLGAFAVTFPGALVPGGVADAAAAYKAAKAGAGLGGVPGVGGGLGVSAGA
 VVPQPGAGVKPGKVPVGLPGVYPGGVLPGARFPGVGVLPVPTGAGVKPK
 APGVGGAFAPIPGVGPFGGPQPGVPLGYPIKAPKLPGGYGLPYTTGKLPYGY
 GPGGVAGAAGKAGYPTGTGVGPQAAAAAAKAAKFGAGAAGVLPVGG
 AGVPGVPGAIPGIGGIAGVGTPAAAAAAKAAKYGAAAGLVPGGPGFG
 15 PGVVGVPAGVPGVPGVPGAGIPVPGAGIPGAAVPGVVSPEAAKAAAKAA
 KYGARPGVGVGGIPTY (SEQ ID NO: 51)

[0198] The codon optimized polynucleotide sequence encoding the 32 kDa truncated human elastin is disclosed in SEQ ID NO: 52

GGTGGCGTACCAGGCGCAATTCCTGGGGGTGTCCCAGGCGGTGTTTTTAT
 20 CCGGGCGCCGGTCTTGGCGCACTGGGTGGCGGTGCACTGGGCCCGGGCGG
 CAAACCGCTGAAACCGGTACCAGGTGGTTTAGCAGGCGCCGGCTTAGGCG
 CAGGTCTGGGAGCATTTCCGGCAGTTACCTTTCCAGGGGCACTGGTTCCTG
 GAGGTGTGGCCGATGCAGCCGCGGCATATAAAGCCGCTAAAGCCGGTGCG
 GGTTTAGGAGGCGTCCCAGGTGTCGGTGGCCTGGGTGTTAGCGCCGGTGC
 25 AGTTGTTCCGCAGCCGGGAGCAGGGGTAAACCTGGTAAAGTGCCGGGAG
 TAGGTCTGCCAGGCGTTATCCTGGTGGTGTGTTTGCCGGGTGCCCGTTTTT
 CGGGCGTTGGTGTCTTCCAGGCGTGCCGACCGGAGCCGGTGTAAACCG
 AAAGCCCCCGGTGTTGGAGGTGCATTTGCAGGCATCCCGGGAGTTGGCCC
 GTTTGGTGGTCCGCAACCTGGGGTTCCTTAGGTTATCCGATTAAAGCACC
 30 GAAACTGCCCCGGCGGTTATGGTCTGCCGTACACAACCGGTAAACTGCCGT
 ATGGTTATGGCCCCGGGTGGAGTTGCGGGTGCAGCAGGTAAAGCGGGTTAT
 CCTACCGGAACCGGTGTAGGTCCGCAGGCCGCTGCTGCCGCCGCCGCAAA
 AGCAGCGGCTAAATTTGGCGCCGGAGCAGCGGGTGTCTGCCTGGAGTTG
 GTGGTGCGGGCGTGCCAGGGGTACCTGGTGCAATTCGGGTATTGGTGGT

ATTGCCGGTGTCTGGCACCCCGGCCGCGGCAGCTGCGGCAGCGGCGGCTGC
CAAAGCTGCTAAATACGGTGCCGCGGCGGGTCTGGTGCCAGGAGGTCCGG
GTTTTGGTCCGGGAGTGGTTGGCGTGCCTGGCGCAGGCGTTCCTGGTGTGG
GCGTTCAGGTGCAGGGATTCTGTGTGCCTGGTGCCGGTATTCCCCGCGC
5 CGGCCGTTCCGGGGGTGGTTAGCCCGGAAGCCGCAGCGAAGGCTGCGGC
AAAGGCAGCAAAGTATGGCGCACGCCAGGAGTCGGCGTGGGTGGTATC
CCGACCTATtaa (SEQ ID NO: 52)

[0199] The amino acid sequence of a 29.9 kDa human elastin truncated at the C-terminal is disclosed in SEQ ID NO: 53. The 60.7 kDa truncated elastin has amino
10 acids 347-761 deleted from the full length elastin.

GGVPGAIPGGVPGGVFYPGAGLGALGGGALGPGGKPLKVPVPGGLAGAGLGA
GLGAFAVTFPGALVPGGVADAAAAYKAAKAGAGLGGVPGVGGGLGVSA
VVPQPGAGVKPGKVPVGLPGVYPGGVLPGARFPGVGVLPGVPTGAGVKPK
APGVGGAFAIPGVGPFGGPQPGVPLGYPIKAPKLPGGYGLPYTTGKLPYGY
15 GPGGVAGAAGKAGYPTGTGVGPQAAAAAAKAAKFGAGAAGVLPVGG
AGVPGVPGAIPGIGGIAGVGTPAAAAAAKAAKYGAAAGLVPGGPGFG
PGVVGVPAGVPGVPGVPGAGIPVPGAGIPGAAPGVVSPE (SEQ ID NO:
53)

[0200] The codon optimized polynucleotide sequence encoding the 29.9 kDa
20 truncated human elastin is disclosed in SEQ ID NO: 54

GGTGGCGTACCAGGCGCAATTCCTGGGGGTGTCCCAGGCGGTGTTTTTAT
CCGGGCGCCGGTCTTGCGCACTGGGTGGCGGTGCACTGGGCCCGGGCGG
CAAACCGCTGAAACCGGTACCAGGTGGTTTAGCAGGCGCCGGCTTAGGCG
CAGGTCTGGGAGCATTTCCGGCAGTTACCTTTCCAGGGGCACTGGTTCCTG
25 GAGGTGTGGCCGATGCAGCCGCGGCATATAAAGCCGCTAAAGCCGGTGCG
GGTTTAGGAGGCGTCCCAGGTGTGGTGGCCTGGGTGTTAGCGCCGGTGC
AGTTGTTCCGCAGCCGGGAGCAGGGGTAAACCTGGTAAAGTGCCGGGAG
TAGGTCTGCCAGGCGTTATCCTGGTGGTGTGTTTGCCGGGTGCCGTTTTT
CGGGCGTTGGTGTCTTCCAGGCGTGCCGACCGGAGCCGGTGTAAACCG
30 AAAGCCCCCGGTGTTGGAGGTGCATTTGCAGGCATCCCGGGAGTTGGCCC
GTTTGGTGGTCCGCAACCTGGGGTTCGGTTAGGTTATCCGATTAAAGCACC
GAAACTGCCCCGGCGGTTATGGTCTGCCGTACACAACCGGTAAACTGCCGT
ATGGTTATGGCCCCGGGTGGAGTTGCGGGTGCAGCAGGTAAAGCGGGTTAT
CCTACCGGAACCGGTGTAGGTCCGCAGGCCGCTGCTGCCGCCGCCGCAAA

AGCAGCGGCTAAATTTGGCGCCGGAGCAGCGGGTGTCTGCCTGGAGTTG
 GTGGTGCAGGGCGTGCCAGGGGTACCTGGTGCAATCCGGGTATTGGTGGT
 ATTGCCGGTGTCTGGCAGCCCGGCCGCGGCAGCTGCGGCAGCGGCGGGCTGC
 CAAAGCTGCTAAATACGGTGCCGCGGCGGGTCTGGTGCCAGGAGGTCCGG
 5 GTTTTGGTCCGGGAGTGGTTGGCGTGCCTGGCGCAGGCGTTCCTGGTGTGG
 GCGTTCAGGTGCAGGGATTCTGTGTGCCTGGTGCCGGTATTCCCGGCG
 CGGCCGTTCCGGGGGTGGTTAGCCCGGAataa (SEQ ID NO: 54)

[0201] The amino acid sequence of a 29.4 kDa human elastin truncated at the N-terminal is disclosed in SEQ ID NO: 55. The 29.4 kDa truncated elastin has amino
 10 acids 2-425 deleted from the full length elastin.

KYGAAGAGVLGGLVPGPQAAVPGVPGTGGVPGVGTAAAAKAAAKAAQF
 GLVPGVGVAPGVGVAPGVGVAPGVGLAPGVGVAPGVGVAPGVGVAPGIGP
 GGVAANKSAKVAAKAQLRAAAGLGAGIPGLGVGVGPGLGVGAGVPGL
 GVGAGVPFGAGADEGVRRSLSPELREGDPSSSQHLPSTPSSPRVPGALAAK
 15 AAKYGAAVPGVLGGLGALGGVGIPGGVVGAGPAAAAAAKAAAKAAQFGL
 VGAAGLGGLGVGGLVPGVGGLGGIPAAAAKAAKYGAAGLGGLGGAGQ
 FPLGGVAARPGFGLSPIFGGACLGKACGRKRK (SEQ ID NO: 55)

[0202] The codon optimized polynucleotide sequence encoding the 29.4 kDa truncated human elastin is disclosed in SEQ ID NO: 56

AAATATGGTGCCGCCGGCGCAGGAGTTTATAGGTGGGCTGGTTCCGGGCCC
 20 GCAGGCAGCTGTGCCGGGGGTTCAGGCACCGGTGGTGTCCCTGGAGTCG
 GTACGCCGGCTGCAGCGGCAGCCAAAGCGGCTGCGAAAGCAGCACAGTT
 TGGCTTAGTACCGGGTGTGGGAGTTGCCCCGGCGTTGGCGTTGCTCCAG
 GGGTGGGTGTTGCTCCTGGCGTCGGTCTGGCTCCTGGAGTGGGCGTAGCA
 25 CCCGGTGTGGGGGTGGCCCCGGGTGTTGGGGTTGCACCGGGTATCGGTCC
 GGGCGGTGTGCGCAGCAGCAGCTAAAAGCGCGGCGAAAGTTGCGGCCAAA
 GCCCAACTGCGCGCCGCCGCGGGCCTCGGTGCAGGTATTCCGGGGCTGGG
 TGTCGGAGTTGGAGTCCCGGGTTTGGGCGTGGGCGCGGGAGTTCCGGGAC
 TGGGAGTGGGTGCCGGAGTTCCTGGCTTTGGTGCAGGCGCAGATGAAGGT
 30 GTTCGTCTAGCCTGAGTCCGGAAGTGCCTGAAGGTGATCCGAGTAGCAG
 CCAGCATCTGCCGAGCACCCGAGCAGCCCGCGTGTTCGGGTGCATTAG
 CTGCAGCAAAAGCCGCCAAGTATGGTGCAGCCGTGCCGGGCGTCTTAGGT
 GGTCTGGGCGCCCTGGGTGGTGTAGGCATTCCGGGAGGTGTTGTGGGTGC
 AGGACCGGCCGCCGAGCTGCGGCCGCCAAAGCAGCTGCAAAAGCGGCC

CAGTTTGGTTTAGTGGGCGCCGCAGGTTTAGGCGGTTTAGGTGTGGGTGG
 ACTGGGTGTACCTGGCGTAGGCGGTCTGGGTGGAATTCCGCCCCGACGCG
 CCGCGAAAGCGGCAAAATATGGCGCGGCAGGCCTGGGCGGCGTGCTGGG
 TGGGGCAGGTCAGTTTCCGCTGGGCGGGGTTGCCGCACGTCCGGGATTTG
 5 GTCTGAGCCCCGATTTTCCCTGGCGGCGCATGTCTGGGTAAAGCATGTGGTC
 GTAAACGTAAAtaa (SEQ ID NO: 56)

[0203] The amino acid sequence of a 25.3 kDa human elastin truncated at the N-terminal is disclosed in SEQ ID NO: 57. The 25.3 kDa truncated elastin has amino acids 2-473 deleted from the full length elastin.

10 QFGLVPGVGVAPGVGVAPGVGVAPGVGLAPGVGVAPGVGVAPGVGVAPGI
 GPGGVAAAASAAKVAAKAQLRAAAGLGAGIPGLGVGVGVPGLVGAGVP
 GLGVGAGVPGFGAGADEGVRRSLSPELREGDPSSSQHLPSTPSSPRVPGALAA
 AKAAYGAAVPGVLGGLGALGGVGIPGGVVGAGPAAAAAATAAAKAAQ
 FGLVGAAGLGGLGVGGLGVPGVGGLGIPPAATAAAKAAAYGAAGLGGVLGG
 15 AGQFPLGGVAARPGFGLSPIFPGGACLGKACGRKRK (SEQ ID NO: 57)

[0204] The codon optimized polynucleotide sequence encoding the 25.3 kDa truncated human elastin is disclosed in SEQ ID NO: 58

CAGTTTGGCTTAGTACCGGTGTGGGAGTTGCCCCGGCGTTGGCGTTGCT
 CCAGGGGTGGGTGTTGCTCCTGGCGTCGGTCTGGCTCCTGGAGTGGGCGT
 20 AGCACCCGGTGTGGGGGTGGCCCCGGGTGTTGGGGTTGCACCGGGTATCG
 GTCCGGGCGGTGTCGCAGCAGCAGCTAAAAGCGCGGCGAAAGTTGCGGC
 CAAAGCCCAACTGCGCGCCGCCGCGGGCCTCGGTGCAGGTATTCCGGGGC
 TGGGTGTCGGAGTTGGAGTCCCGGGTTTGGGCGTGGGCGCGGGAGTTCCG
 GGACTGGGAGTGGGTGCCGGAGTTCCTGGCTTTGGTGCAGGCGCAGATGA
 25 AGGTGTTTCGTCTAGCCTGAGTCCGGAAGTGCCTGAAGGTGATCCGAGTA
 GCAGCCAGCATCTGCCGAGCACCCGAGCAGCCCGCGTGTTCCGGGTGCA
 TTAGCTGCAGCAAAAGCCGCCAAGTATGGTGCAGCCGTGCCGGGCGTCTT
 AGGTGGTCTGGGCGCCCTGGGTGGTGTAGGCATTCCGGGAGGTGTTGTGG
 GTGCAGGACCGGCCGCCGAGCTGCGGCCGCCAAAGCAGCTGCAAAAGC
 30 GGCCAGTTTGGTTTAGTGGGCGCCGCAGGTTTAGGCGGTTTAGGTGTGG
 GTGGACTGGGTGTACCTGGCGTAGGCGGTCTGGGTGGAATTCCGCCCCGA
 GCGGCCGCGAAAGCGGCAAAATATGGCGCGGCAGGCCTGGGCGGCGTGC
 TGGGTGGGGCAGGTCAGTTTCCGCTGGGCGGGGTTGCCGCACGTCCGGGA

TTTGGTCTGAGCCCGATTTTCCCTGGCGGCGCATGTCTGGGTAAAGCATGT
GGTCGTAAACGTAAAtaa (SEQ ID NO: 58)

[0205] The amino acid sequence of a 24.1 kDa human elastin truncated at the C-terminal is disclosed in SEQ ID NO: 59. The 24.1 kDa truncated elastin has amino acids 277-761 deleted from the full length elastin.

GGVPGAIPGGVPGGVFYPGAGLGALGGGALGPGGKPLKPVPGGLAGAGLGA
GLGAFAVTFPGALVPGGVADAAAAYKAAKAGAGLGGVPGVGGLGVSAGA
VVPQPGAGVKPGKVPVGLPGVYPGGVLPGARFPGVGVLPVPTGAGVKPK
APGVGGAFAAGIPGVGPFGGPQPGVPLGYPIKAPKLPGGYGLPYTTGKLPYGY
GPGGVAGAAGKAGYPTGTGVGPQAAAAAAKAAAKFGAGAAGVLPVGG
AGVPGVPGAIPGIGGIAGVGTP (SEQ ID NO: 59)

[0206] The codon optimized polynucleotide sequence encoding the 24.1 kDa truncated human elastin is disclosed in SEQ ID NO: 60

GGTGGCGTACCAGGCGCAATTCCTGGGGGTGTCCCAGGCGGTGTTTTTAT
CCGGGCGCCGGTCTTGCGCACTGGGTGGCGGTGCACTGGGCCCCGGGCGG
CAAACCGCTGAAACCGGTACCAGGTGGTTTAGCAGGCGCCGGCTTAGGCG
CAGGTCTGGGAGCATTTCGGCAGTTACCTTTCCAGGGGCACTGGTTCCTG
GAGGTGTGGCCGATGCAGCCGCGGCATATAAAGCCGCTAAAGCCGGTGCG
GGTTTAGGAGGCGTCCCAGGTGTCGGTGGCCTGGGTGTTAGCGCCGGTGC
AGTTGTTCCGCAGCCGGGAGCAGGGGTAAACCTGGTAAAGTGCCGGGAG
TAGGTCTGCCAGGCGTTTATCCTGGTGGTGTGTTTGCCGGGTGCCCGTTTTT
CGGGCGTTGGTGTTCTTCCAGGCGTGCCGACCGGAGCCGGTGTTAAACCG
AAAGCCCCCGGTGTTGGAGGTGCATTTGCAGGCATCCCGGGAGTTGGCCC
GTTTGGTGGTCCGCAACCTGGGGTTCGTTAGGTATCCGATTAAAGCACC
GAAACTGCCCCGGCGGTTATGGTCTGCCGTACACAACCGGTAAACTGCCGT
ATGGTTATGGCCCCGGGTGGAGTTGCGGGTGCAGCAGGTAAAGCGGGTTAT
CCTACCGGAACCGGTGTAGGTCCGCAGGCCGCTGCTGCCGCCGCCGCAAA
AGCAGCGGCTAAATTTGGCGCCGGAGCAGCGGGTGTCTGCCTGGAGTTG
GTGGTGCGGGCGTGCCAGGGGTACCTGGTGCAATTCGGGTATTGGTGGT
ATTGCCGGTGTCCGGCACCCCGtaa (SEQ ID NO:60)

[0207] The amino acid sequence of a 20.3 kDa human elastin truncated at the C-terminal is disclosed in SEQ ID NO: 61. The 20.3 kDa truncated elastin has amino acids 229-761 deleted from the full length elastin.

GGVPGAIPGGVPGGVFYYPGAGL GALGGALGPGGKPLKPVPGGLAGAGLGA
 GLGAFAVTFPGALVPGGVADAAAAYKAAKAGAGLGGVPGVGGLGV SAGA
 VVPQPGAGVKPGKVPGLPGVYPGGVLPGARFPGVGVLPGVPTGAGVKPK
 APGVGGAFAGIPGVGPFGGPQPGVPLGYPIKAPKLPGGYGLPYTTGKLPYGY
 5 GPGGVAGAAGKAGYPTGTGVGPQ (SEQ ID NO: 61)

[0208] The codon optimized polynucleotide sequence encoding the 20.3 kDa truncated human elastin is disclosed in SEQ ID NO: 62

GGTGGCGTACCAGGCGCAATTCCTGGGGGTGTCCCAGGCGGTGTTTTTAT
 CCGGGCGCCGGTCTTGCGCACTGGGTGGCGGTGCACTGGGCCCCGGGCGG
 10 CAAACCGCTGAAACCGGTACCAGGTGGTTTAGCAGGCGCCGGCTTAGGCG
 CAGGTCTGGGAGCATTTCGGCAGTTACCTTTCCAGGGGCACTGGTTCCTG
 GAGGTGTGGCCGATGCAGCCGCGGCATATAAAGCCGCTAAAGCCGGTGCG
 GGTTTAGGAGGCGTCCCAGGTGTCGGTGGCCTGGGTGTTAGCGCCGGTGC
 AGTTGTTCCGCAGCCGGGAGCAGGGGTTAAACCTGGTAAAGTGCCGGGAG
 15 TAGGTCTGCCAGGCGTTTATCCTGGTGGTGTGTTTGCCGGGTGCCCCGTTTT
 CCGGGCGTTGGTGTTCTTCCAGGCGTGCCGACCGGAGCCGGTGTTAAACCG
 AAAGCCCCCGGTGTTGGAGGTGCATTTGCAGGCATCCCGGGAGTTGGCCC
 GTTTGGTGGTCCGCAACCTGGGGTTCGGTTAGGTTATCCGATTAAAGCACC
 GAAACTGCCCCGGCGGTTATGGTCTGCCGTACACAACCGGTAAACTGCCGT
 20 ATGGTTATGGCCCCGGTGGAGTTGCGGGTGACAGCAGGTAAAGCGGGTTAT
 CCTACCGGAACCGGTGTAGGTCCGCAGtaa (SEQ ID NO: 62)

[0209] The amino acid sequence of a 19.6 kDa human elastin truncated at the N-terminal is disclosed in SEQ ID NO: 63. The 19.6 kDa truncated elastin has amino acids 2-542 deleted from the full length elastin.

QLRAAAGLGAGIPGLGVGVGPGLGVGAGVPGLGVGAGVPFGAGADEGV
 RRSLSPELREGDPSSSQHLPSTPSSPRVPGALAAAKAAKYGAAVPGVLGGLGA
 LGGVGIPGGVVGAGPAAAAAATAAAKAAQFGLVGAAGLGGLVGGLGVP
 GVGGLGGIPAAAAAATAKYGAAGLGGVLGGAGQFPLGGVAARPGFGLSPIFP
 GGACLGKACGRKRK (SEQ ID NO: 63)

30 **[0210]** The codon optimized polynucleotide sequence encoding the 19.6 kDa truncated human elastin is disclosed in SEQ ID NO: 64

CAACTGCGCGCCGCGCGGGCCTCGGTGCAGGTATCCGGGGCTGGGTGT
 CGGAGTTGGAGTCCCGGGTTTGGGCGTGGGCGCGGAGTTCCGGGACTGG
 GAGTGGGTGCCGAGTTCCTGGCTTTGGTGCAGGCGCAGATGAAGGTGTT

CGTCGTAGCCTGAGTCCGGAAGTGCCTGAAGGTGATCCGAGTAGCAGCCA
 GCATCTGCCGAGCACCCCGAGCAGCCCGCGTGTTCCGGGTGCATTAGCTG
 CAGCAAAAGCCGCCAAGTATGGTGCAGCCGTGCCGGGCGTCTTAGGTGGT
 CTGGGCGCCCTGGGTGGTGTAGGCATTCCGGGAGGTGTTGTGGGTGCAGG
 5 ACCGGCCGCCGAGCTGCGGCCGCCAAAGCAGCTGCAAAAGCGGCCAG
 TTTGGTTTGTAGTGGGCGCCGCAGGTTTAGGCGGTTTAGGTGTGGGTGGACTG
 GGTGTACCTGGCGTAGGCGGTCTGGGTGGAATTCGCCCGCAGCGGCCGC
 GAAAGCGGCAAAATATGGCGCGGCAGGCCTGGGCGGCGTGCTGGGTGGG
 GCAGGTCAGTTTCCGCTGGGCGGGGTGCCGCACGTCCGGGATTTGGTCT
 10 GAGCCCGATTTTCCCTGGCGGCGCATGTCTGGGTAAAGCATGTGGTCGTA
 AACGTAAAtaa (SEQ ID NO: 64)

[0211] The amino acid sequence of a 11 kDa human elastin truncated at the N-terminal is disclosed in SEQ ID NO: 65. The 11 kDa truncated elastin has amino acids 2-635 deleted from the full length elastin.

15 VPGVLGGLGALGGVGIPGGVVAGPAAAAAAKAAKAAQFGLVGAAGLG
 GLGVGGLGVPGVGGLGGIPPAAAKAAKYGAAGLGGVLGGAGQFPLGGVA
 ARPGFGLSPIPGGACL GKACGRKRK (SEQ ID NO: 65)

[0212] The codon optimized polynucleotide sequence encoding the 11 kDa truncated human elastin is disclosed in SEQ ID NO: 66

20 GTGCCGGGCGTCTTAGGTGGTCTGGGCGCCCTGGGTGGTGTAGGCATTCC
 GGGAGGTGTTGTGGGTGCAGGACCGGCCCGCCGAGCTGCGGCCGCCAAA
 GCAGCTGCAAAAGCGGCCAGTTTGGTTTGTAGTGGGCGCCGCAGGTTTAGG
 CGGTTTAGGTGTGGGTGGACTGGGTGTACCTGGCGTAGGCGGTCTGGGTG
 GAATTCGCCCGCAGCGGCCCGCAAAGCGGCAAAATATGGCGCGGCAGG
 25 CCTGGGCGGCGTGCTGGGTGGGGCAGGTCAGTTTCCGCTGGGCGGGGTG
 CCGCACGTCCGGGATTTGGTCTGAGCCCGATTTTCCCTGGCGGCGCATGTC
 TGGGTAAAGCATGTGGTCGTAAACGTAAAtaa (SEQ ID NO: 66)

[0213] The amino acid sequence of a 7.9 kDa human elastin truncated at the N-terminal is disclosed in SEQ ID NO: 67. The 7.9 kDa truncated elastin has amino acids 2-674 deleted from the full length elastin.

30 QFGLVGAAGLGGGLGVGGLGVPGVGGLGGIPPAAAKAAKYGAAGLGGVLG
 GAGQFPLGGVAARPGFGLSPIPGGACL GKACGRKRK (SEQ ID NO: 67)

[0214] The codon optimized polynucleotide sequence encoding the 7.9 kDa truncated human elastin is disclosed in SEQ ID NO: 68

CAGTTTGGTTTAGTGGGCGCCGCAGGTTTAGGCGGTTTAGGTGTGGGTGG
 ACTGGGTGTACCTGGCGTAGGCGGTCTGGGTGGAATTCGCCCCGCAGCGG
 5 CCGCGAAAGCGGCAAAATATGGCGCGGCAGGCCTGGGCGGCGTGCTGGG
 TGGGGCAGGTCAGTTTCCGCTGGGCGGGGTTGCCGCACGTCCGGGATTTG
 GTCTGAGCCCGATTTTCCCTGGCGGCGCATGTCTGGGTAAAGCATGTGGTC
 GTAAACGTAAAtaa (SEQ ID NO: 68)

[0215] The amino acid sequence of a 6.3 kDa human elastin truncated at the C-terminal is disclosed in SEQ ID NO: 69. The 6.3 kDa truncated elastin has amino acids 74-761 deleted from the full length elastin.

GGVPGAIPGGVPGGVFYFPGAGLALGGGALGPGGKPLKPVPGGLAGAGLGA
 GLGAFAVTFPGALVPGGVAD (SEQ ID NO: 69)

[0216] The codon optimized polynucleotide sequence encoding the 6.3 kDa truncated human elastin is disclosed in SEQ ID NO: 70:

GGTGGCGTACCAGGCGCAATTCCTGGGGGTGTCCCAGGCGGTGTTTTTAT
 CCGGGCGCCGGTCTTGGCGCACTGGGTGGCGGTGCACTGGGCCCCGGGCGG
 CAAACCGCTGAAACCGGTACCAGGTGGTTTAGCAGGCGCCGGCTTAGGCG
 CAGGTCTGGGAGCATTTCCGGCAGTTACCTTTCCAGGGGCACTGGTTCCTG
 20 GAGGTGTGGCCGATtaa (SEQ ID NO: 70)

[0217] The amino acid sequence of a 4.3 kDa human elastin truncated at the N-terminal is disclosed in SEQ ID NO: 71. The 4.3 kDa truncated elastin has amino acids 2-717 deleted from the full length elastin.

GLGGVLGGAGQFPLGGVAARPGFGLSPIFPGGACLGKACGRKRK (SEQ ID
 25 NO: 71)

[0218] The codon optimized polynucleotide sequence encoding the 4.3 kDa truncated human elastin is disclosed in SEQ ID NO: 72

GGCCTGGGCGGCGTGCTGGGTGGGGCAGGTCAGTTTCCGCTGGGCGGGGT
 TGCCGCACGTCCGGGATTTGGTCTGAGCCCGATTTTCCCTGGCGGCGCATG
 30 TCTGGGTAAAGCATGTGGTTCGTAAACGTAAAtaa (SEQ ID NO: 72)

Truncated Human Elastin 1 with DsbA secretion and FLAG tag

[0219] The amino acid sequence of truncated human elastin 1 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 98. The DsbA secretion tag is encoded by nucleotides 1-57 of SEQ ID NO: 99 and the amino acid sequences are amino acids 1-

19 of SEQ ID NO: 98. The elastin nucleotide sequences are nucleotides 58-657 of SEQ ID NO: 99 and the amino acid sequences are amino acids 20-219 of SEQ ID NO: 98. The FLAG nucleotide sequences are nucleotides 658-684 of SEQ ID NO: 99 and the amino acid sequences are amino acids 220-228 of SEQ ID NO: 98.

5 MKKIWLALAGLVLAFFSASAGGVPGAIPGGVPGGVFYPGAGLGALGGGALGP
GGKPLKPVPGGLAGAGLGAGLGAFPAVTFPGALVPGGVADAAAAYKAAKA
GAGLGGVPGVGGGLGVSAAGVVPQPGAGVKPGKVPGVGLPGVYPGGVLPGA
RFPGVGVLPGVPTGAGVKPKAPGVGGAFAGIPGVGPFGGPQPGVPLGYPIKA
PKLPGGYGLPYTTGKLGDYKDDDDK (SEQ ID NO: 98)

10 **[0220]** The nucleic acid sequence of truncated human elastin 1 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 99.

ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
TCGGCGGGTGGCGTACCAGGCGCAATTCCTGGGGGTGTCCCAGGCGGTGT
TTTTTATCCGGGCGCCGGTCTTGCGCGACTGGGTGGCGGTGCACTGGGCCC
15 GGGCGGCAAACCGCTGAAACCGGTACCAGGTGGTTTAGCAGGCGCCGGCT
TAGGCGCAGGTCTGGGAGCATTTCGGCAGTTACCTTCCAGGGGCGACTG
GTTCTTGAGGTGTGGCCGATGCAGCCGCGGCATATAAAGCCGCTAAAGC
CGGTGCGGGTTTAGGAGGCGTCCCAGGTGTCGGTGGCCTGGGTGTTAGCG
CCGGTGCAGTTGTTCCGCAGCCGGGAGCAGGGGTAAACCTGGTAAAGTG
20 CCGGGAGTAGGTCTGCCAGGCGTTTATCCTGGTGGTGTGTTTGCCGGGTGCC
CGTTTTCCGGGCGTTGGTGTCTTCCAGGCGTGCCGACCGGAGCCGGTGT
AAACCGAAAGCCCCCGGTGTTGGAGGTGCATTTGCAGGCATCCCGGGAGT
TGGCCCGTTTGGTGGTCCGCAACCTGGGGTTCCGTTAGGTTATCCGATTAA
AGCACCGAAACTGCCCGGCGGTTATGGTCTGCCGTACACAACCGGTAAAC
25 TGGGTGACTACAAAGACGACGACGACAAAtaa (SEQ ID NO: 99)

[0221] The polynucleotide of SEQ ID NO: 99 was subcloned into vector pET28a, expressed host *E. coli* cells and the truncated elastin was purified as described herein. The purified elastin produced a clear band on SDS-PAGE and an anti-FLAG western was observed at around 25 kilodaltons. There were no existing bands that appear at
30 that location on the gel in the absence of expression of this protein.

Truncated Human Elastin 2 with DsbA secretion and FLAG tag

[0222] The amino acid sequence of truncated human elastin type 2 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 100. The DsbA secretion tag is encoded by nucleotides 1-57 of SEQ ID NO: 101 and the amino acid sequences are

amino acids 1-19 of SEQ ID NO: 100. The elastin nucleotide sequences are nucleotides 58-657 of SEQ ID NO: 101 and the amino acid sequences are amino acids 20-219 of SEQ ID NO: 100. The FLAG nucleotide sequences are nucleotides 658-684 of SEQ ID NO: 101 and the amino acid sequences are amino acids 220-228 of

5 SEQ ID NO: 100.

MKKIWLALAGLVLAFFSASAPYGYGPGGVAGAAGKAGYPTGTGVGPQAAAA
 AAKAAAKFGAGAAGVLPGVGGAGVPGVPGAIPGIGGIAGVGTTPAAAAAAA
 AAKAAKYGAAAGLVPGPGFGPGVVGVPGAGVPGVGVPGAGIPVVPAGI
 PGAAPVPGVVSPEAAAKAAAKAAKYGARPGVGVGGIPTYGVGAGGFPFGFV
 10 GVGIGIPGVAGVPGVGGVGDYKDDDDK (SEQ ID NO: 100)

[0223] The nucleic acid sequence of truncated human elastin 2 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 101.

ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
 TCGGCGCCGTATGGTTATGGCCCGGGTGGAGTTGCGGGTGCAGCAGGTAA
 15 AGCGGGTTATCCTACCGGAACCGGTGTAGGTCCGCAGGCCGCTGCTGCCG
 CCGCCGCAAAGCAGCGGCTAAATTTGGCGCCGGAGCAGCGGGTGTCTG
 CCTGGAGTTGGTGGTGCGGGCGTGCCAGGGGTACCTGGTGCAATTCCGGG
 TATTGGTGGTATTGCCGGTGTCCGCACCCCGGCCGCGGCAGCTGCGGCAG
 CGGCGGCTGCCAAAGCTGCTAAATACGGTGCCGCGGCGGGTCTGGTGCCA
 20 GGAGGTCCGGGTTTTGGTCCGGGAGTGGTTGGCGTGCCTGGCGCAGGCGT
 TCCTGGTGTGGGCGTTCCAGGTGCAGGGATTCTGTGTGCCTGGTGCCGG
 TATTCCCGGCGCGGCCGTTCCGGGGGTGGTTAGCCCGGAAGCCGCAGCGA
 AGGCTGCGGCAAAGGCAGCAAAGTATGGCGCACGCCAGGAGTCGGCGT
 GGGTGGTATCCCGACCTATGGGGTGGGCGCAGGGGGTTTTCTGTGTTTCG
 25 GCGTAGGTGTAGGAGGTATACCGGGCGTGGCCGGTGTACCAGGGGTGGT
 GCGTGGTGAATAAAAGACGACGACGACAAAtaa (SEQ ID NO: 101)

[0224] The polynucleotide of SEQ ID NO: 101 was subcloned into vector pET28a, expressed host *E. coli* cells and the truncated elastin was purified as described herein. The purified elastin produced a clear band on SDS-PAGE and an anti-FLAG western

30 was observed at around 25 kilodaltons. There were no existing bands that appear at that location on the gel in the absence of expression of this protein.

Example 6: Effect of Truncated Collagen on fibroblast Cell Viability, Procollagen Synthesis, and Elastin Synthesis

[0225] A human fibroblast cell culture was used to assess the ability of the truncated jellyfish collagen molecule of Example 2 to determine its effect on
5 procollagen, and elastin synthesis. The human fibroblast cell culture was also used to determine the increased viability of the human fibroblast cells after exposure to the truncated jellyfish collagen.

[0226] A stock solution of 2% w/w truncated collagen was prepared from the histidine tagged truncated collagen of example 3. Aliquots from the 2% stock
10 truncated collagen solution were then used in the experiments described below.

Preparation of Fibroblasts

[0227] Fibroblasts were seeded into the individual wells of a 24-well plate in 0.5 ml of Fibroblast Growth Media (FGM) and incubated overnight at $37 \pm 2^\circ \text{C}$ and $5 \pm 1\%$ CO_2 . On the following day the media was removed via aspiration to eliminate any
15 non-adherent cells and replaced with 0.5 ml of fresh FGM. The cells were grown until confluent, with a media change every 48 to 72 hours. Upon reaching confluency the cells were treated for 24 hours with DMEM supplemented with 1.5% FBS to wash out any effects from the growth factors included in the normal culture media. After the 24-hour wash out period the cells were treated with the truncated jellyfish collagen at
20 specified concentrations dissolved in FGM with 1.5% FBS. Transforming Growth Factor Beta ($\text{TGF-}\beta$) (20 ng/ml) was used as a positive control for collagen and elastin synthesis. Untreated cells (negative controls) just received DMEM with 1.5% FBS. The cells were incubated for 48 hours and at the end of the incubation period cell culture medium was collected and either stored frozen (-75°C) or assayed
25 immediately. Materials were tested in triplicate.

MTT Assay

[0228] The MTT (3-(4,5-Dimethylthiazol-2-yl)-2,5-diphenyltetrazolium bromide, a tetrazole) assay is a colorimetric assay used to determine the metabolic activity of cells. Changes in cell number were assessed via an MTT assay. When cells are
30 exposed to MTT, reduction of MTT by mitochondria in viable cells results in the formation of insoluble purple formazin crystals that are extracted from the cells with isopropanol and quantified spectrophotometrically. Non-living cells cannot reduce MTT and therefore cannot produce the purple formazin crystals. The intensity of the purple color is directly proportional to the number of living cells (metabolically active

cells). The intensity of the purple color is directly proportional to the metabolic activity of the cells and is inversely proportional to the toxicity of the test material.

[0229] After the 2-day incubation discussed above, the cell culture medium was removed (see above) and the fibroblasts were washed twice with PBS to remove any remaining jellyfish glycogen molecules. After the final wash, 500 μ l of DMEM supplemented with 0.5 mg/ml MTT was added to each well and the cells were incubated for 1 hour at $37 \pm 2^\circ$ C and $5 \pm 1\%$ CO₂. After the incubation, the DMEM/MTT solution was removed and the cells were washed again once with PBS and then 0.5 ml of isopropyl alcohol was added to the well to extract the purple formazin crystals. Two hundred microliters of the isopropyl extracts was transferred to a 96-well plate and the plate was read at 540 nm using isopropyl alcohol as a blank.

[0230] The mean MTT absorbance value for the negative control cells was calculated and used to represent 100% cell viability. The individual MTT absorbance values from the cells undergoing the various treatments were then divided by the mean value for the negative control cells and expressed as a percent to determine the change in cell viability caused by each treatment.

[0231] In Tables 1, 2 and 3 of this example, the experiments were performed by using the designated aliquots of the 2% stock truncated collagen solution in the assays. For example, in the samples that tested the “10% Collagen Solution,” an aliquot of the 2% truncated collagens in an amount sufficient to provide 10% of the assay volume was used. For a total assay volume of 1.0 ml, 100 μ l of the 2% stock truncated collagen solution was used. In Tables 1, 2 and 3, “10% Collagen Solution” is 0.2% collagen, “5% Collagen Solution” is 0.1% collagen, “1% Collagen Solution” is 0.02% collagen, “0.5% Collagen Solution” is 0.01% collagen, “0.1% Collagen Solution” is 0.002% collagen, “0.05% Collagen Solution” is 0.001% collagen, “0.01% Collagen Solution” is 0.0002% collagen, “0.005% Collagen Solution” is 0.0001% collagen, f

[0232] The results for the MTT assay are presented in Table 3. The values are presented as the mean percent viability $\pm$ the deviation from the mean.

[0233] **Table 3. MTT Assay**

Untreated	100 $\pm$ 6.1
20 ng/ml TGF-B	110 $\pm$ 2.9
10% Collagen Solution	131 $\pm$ 7.8*
5% Collagen Solution	140 $\pm$ 8.3*
1% Collagen Solution	116 $\pm$ 0.9
0.5% Collagen Solution	105 $\pm$ 4.8

0.1% Collagen Solution	102 ± 1.1
0.05% Collagen Solution	106 ± 3.4
0.01% Collagen Solution	112 ± 1.9
0.005% Collagen Solution	103 ± 3.9

*Denotes values that are significantly different from the Untreated group ($p < 0.05$).

[0234] The histidine tagged truncated jellyfish collagen showed protective effect by increasing the cell viability of human fibroblast cells. As can be seen in Table 3, the highest value in the MTT assay was observed when the fibroblast cells were exposed to 0.02% to 0.2% truncated jellyfish collagen.

Procollagen Synthesis

[0235] Fibroblasts are the main source of the extracellular matrix peptides, including the structural proteins collagen and elastin. Procollagen is a large peptide synthesized by fibroblasts in the dermal layer of the skin and is the precursor for collagen. As the peptide is processed to form a mature collagen protein, the propeptide portion is cleaved off (type I C-peptide). Both the mature collagen protein and the type I C-peptide fragment are then released into the extracellular environment. As collagen is synthesized the type I C-peptide fragment accumulates into the tissue culture medium. Since there is a 1:1 stoichiometric ratio between the two parts of the procollagen peptide, assaying for type I C-peptide will reflect the amount of collagen synthesized. Type I C-peptide can be assayed via an ELISA based method.

[0236] A series of type I C-peptide standards was prepared ranging from 0 ng/ml to 640 ng/ml. Next, an ELISA microplate was prepared by removing any unneeded strips from the plate frame followed by the addition of 100 μ l of peroxidase-labeled anti procollagen type I-C peptide antibody to each well used in the assay. Twenty (20) μ l of either sample (collected tissue culture media) or standard was then added to appropriate wells and the microplate was covered and allowed to incubate for 3 ± 0.25 hours at 37°C. After the incubation the wells were aspirated and washed three times with 400 μ l of wash buffer. After the last wash was removed 100 μ l of peroxidase substrate solution (hydrogen peroxide + tetramethylbenzidine as a chromagen) was added to each well and the plate was incubated for 15 ± 5 minutes at room temperature. After the incubation 100 μ l of stop solution (1 N sulfuric acid) was added to each well and the plate was read using a microplate reader at 450 nm.

[0237] To quantify the amount of each substance present, a standard curve was generated using known concentrations of each substance. A regression analysis was performed to establish the line that best fits these data points. Absorbance values for

the test materials and untreated samples were used to estimate the amount of each substance present in each sample.

[0238] The results for the ELISA assays are presented in Table 4.

[0239] **Table 4. Type I Collagen Assay.** The values presented are mean

5 concentration (ng/ml) $\pm$ the deviation from the mean.

Treatment	Type I C-Peptide (ng/ml)
Untreated	1718 $\pm$ 94
20 ng/ml TGF- β	3028 $\pm$ 332*
10% Collagen Solution	1940 $\pm$ 100
5% Collagen Solution	2394 $\pm$ 125*
1% Collagen Solution	1773 $\pm$ 183
0.5% Collagen Solution	1127 $\pm$ 19*
0.1% Collagen Solution	1158 $\pm$ 10*
0.05% Collagen Solution	1416 $\pm$ 64
0.01% Collagen Solution	1835 $\pm$ 404
0.005% Collagen Solution	1551 $\pm$ 149

*Denotes values that are significantly different from the Untreated group

($p < 0.05$).

10 [0240] The truncated histidine tagged jellyfish collagen was observed to have a biphasic effect on collagen synthesis. At the 1%, 5% and the 10% levels, collagen synthesis increased. At the 5% concentration truncated jellyfish collagen significantly increased collagen synthesis with a p-value of less than 0.05.

Elastin Synthesis

15 [0241] Elastin is the main component of a network of elastic fibers that give tissues their ability to recoil after a transient stretch. This protein is released by fibroblasts (soluble elastin) into the extracellular space where it is then cross-linked to other elastin proteins to form an extensive network of fibers and sheets (insoluble elastin). Soluble elastin can be readily measured from cell culture medium via an ELISA based
20 method.

[0242] Soluble α -elastin was dissolved in 0.1 M sodium carbonate (pH 9.0) at a concentration of 1.25 μ g/ml. 150 μ l of this solution was then applied to the wells of a 96-well maxisorp Nunc plate and the plate was incubated overnight at 4°C. On the following day the wells were saturated with PBS containing 0.25% BSA and 0.05%
25 Tween 20. The plate was then incubated with this blocking solution for 1 hour at 37°C and then washed two times with PBS containing 0.05% Tween 20.

- [0243] A set of α -elastin standards was generated ranging from 0 to 100 ng/ml. 180 μ l of either standard or truncated jellyfish collagen was then transferred to a 650 μ l microcentrifuge tube. An anti-elastin antibody solution was prepared (the antibody was diluted 1:100 in PBS containing 0.25% BSA and 0.05% Tween 20) and 20 μ l of the solution was added to the tube. The tubes were then incubated overnight at $4 \pm 2^\circ\text{C}$. On the following day, 150 μ l was transferred from each tube to the 96-well elastin ELISA plate, and the plate was incubated for 1 hour at room temperature. The plate was then washed 3 times with PBS containing 0.05% Tween 20. After washing, 200 μ l of a solution containing a peroxidase linked secondary antibody diluted in PBS containing 0.25% BSA and 0.05% Tween 20 was added, and the plate was incubated for 1 hour at room temperature. After washing the plate three times, 200 μ l of a substrate solution was added and the plate was incubated for 10 to 30 minutes in the dark at room temperature. After this final incubation the plate was read at 460 nm using a plate reader.
- [0244] **Table 5.** The values are also presented as mean concentration (ng/ml) $\pm$ deviation from the mean.

Treatment	Elastin (ng/ml)
Untreated	79 $\pm$ 19
20 ng/ml TGF β 1	243 $\pm$ 35*
10% Collagen Solution	68 $\pm$ 18
5% Collagen Solution	99 $\pm$ 13
1% Collagen Solution	126 $\pm$ 21
0.5% Collagen Solution	145 $\pm$ 21*
0.1% Collagen Solution	76 $\pm$ 14
0.05% Collagen Solution	58 $\pm$ 6
0.01% Collagen Solution	53 $\pm$ 5
0.005% Collagen Solution	56 $\pm$ 24

*Denotes values that are significantly different from the Untreated group ($p < 0.05$).

- [0245] Truncated his-tagged jellyfish collagen significantly increased elastin production when it was used at the 0.5% concentration as shown in Table 5.

Example 7: Effect of Truncated Collagen on Keratinocyte Proliferation and UVB Protection

- [0246] A human keratinocyte cell culture model was used to assess the ability of the test materials to exert an effect on cell proliferation. In addition, the impact of the test materials on the cell viability after an exposure to UVB was also assessed.

[0247] A stock solution of 2% w/w truncated collagen was prepared from the truncated collagen of example 1. Aliquots from the 2% stock truncated collagen solution was then used in the experiments described below.

[0248] This study was conducted in two parts. In the first part cultured
5 keratinocytes were incubated with the test materials for 48 hours, after which changes in the number of viable cells were assessed using an MTT assay. In the second part of the study cultured keratinocytes were irradiated with UVB and then treated with the test materials for 48 hours. At the end of the 48 hour period the number of viable cells was again assessed via an MTT assay.

10 [0249] Changes in cell number of viable cells can be determined using an MTT (3-(4,5-Dimethylthiazol-2-yl)-2,5- diphenyltetrazolium bromide, a tetrazole) assay. The MTT assay is a colorimetric analysis of the metabolic activity of the cell, which is a reflection of the number of viable cells. Reduction of MTT by mitochondria in viable cells results in the formation of insoluble purple formazin crystals that are extracted
15 from the cells with isopropanol and quantified spectrophotometrically. The intensity of the purple color is directly proportional to the number of metabolically active cells.

Proliferation Assay

[0250] For the proliferation assay the keratinocytes were seeded into 96-well plates using without growth factors and incubated for 24 hours at $37\pm 2^{\circ}\text{C}$ and $5\pm 1\%$ CO_2 .
20 After this initial incubation the media was replaced with media supplemented with the test materials. Normal media (with growth factors) was used as a positive control. After the addition of the test materials the cells were cultured for 48 hours as described above. At the end of the incubation period changes in the number of viable cells was determined using an MTT assay.

UVB Protection Assay

[0251] For the UVB protection assay the keratinocytes were seeded into 96-well plates using normal media and incubated for 24 hours at $37\pm 2^{\circ}\text{C}$ and $5\pm 1\%$ CO_2 .
After this initial incubation the media was replaced with 100 μl of phosphate buffered saline (PBS) and the cells were exposed to UVB (40 mJ/cm^2). After the UVB
30 exposure, the PBS was replaced with fresh media supplemented with the test materials (ascorbic acid at 100 $\mu\text{g}/\text{ml}$ served as the positive control) and the cells were cultured for 48 hours at $37\pm 2^{\circ}\text{C}$ and $5\pm 1\%$ CO_2 . At the end of the 48 hour incubation cell viability was determined using an MTT assay.

MTT Assay

[0252] After the 48-hour incubation the cell culture medium was removed and replaced with 200 μ l of culture media supplemented with 0.5 mg/ml MTT. The well plates were incubated for 1 hour at $37 \pm 2^\circ\text{C}$ and $5 \pm 1\%$ CO_2 . After the incubation, the MTT solution was removed and the cells were washed once with phosphate buffered saline and then 200 μ l of isopropyl alcohol was added to the well to extract the purple formazin crystals. The 96-well plate was read at 540 nm using isopropyl alcohol as a blank.

[0253] The mean absorbance value for the cells not treated with test materials (proliferation assay: Untreated Group) or not exposed to UVB (UVB protection assay: Non-UVB Exposed Group) was calculated and used to represent 100% cell viability. The individual absorbance values from the cells undergoing the various treatments were then divided by the mean absorbance value representing 100% cell viability and expressed as a percent to determine the change in cell viability caused by each treatment.

[0254] The results for the Proliferation assay using the his-tagged truncated jellyfish collagen are presented in Table 6. The results for the UVB Protection assay using the his-tagged truncated jellyfish collagen are presented in Table 7. The values for both assays are presented as mean viability $\pm$ standard deviation.

[0255] **Table 6. Proliferation Assay**

Untreated	100	$\pm$	3.4
Positive Control (Growth Factors)	139	$\pm$	3.8*
10% Collagen Solution	103	$\pm$	9.4
5% Collagen Solution	97	$\pm$	7.3
1% Collagen Solution	94	$\pm$	5.0
0.5% Collagen Solution	93	$\pm$	7.0
0.1% Collagen Solution	95	$\pm$	2.5
0.05% Collagen Solution	99	$\pm$	6.0
0.01% Collagen Solution	96	$\pm$	6.4
0.005% Collagen Solution	96	$\pm$	2.8

* Denotes values which are significantly different from the Untreated Group ($p < 0.05$)

[0256] **Table 7. UVB Protection Assay**

Non-UVB Exposed	100	$\pm$	1.7*
Untreated	77	$\pm$	1.8
100 $\mu\text{g/ml}$ Trolox	92	$\pm$	2.0*
10% Collagen Solution	76	$\pm$	8.6
5% Collagen Solution	92	$\pm$	3.9*
1% Collagen Solution	91	$\pm$	2.9*
0.5% Collagen Solution	100	$\pm$	4.5*

0.1% Collagen Solution	86	±	4.8
0.05% Collagen Solution	91	±	1.6*
0.01% Collagen Solution	83	±	7.5
0.005% Collagen Solution	82	±	4.7

* Denotes values which are significantly different from the Untreated Group ($p < 0.05$)

[0257] For the proliferation assay the Untreated group was used to represent 100% cell viability. Values above 100% reflect an increase in the number of viable cells and hence are indicative of cell proliferation. In this study, the test material was not observed to promote cell proliferation.

[0258] In addition, the keratinocyte proliferation assay was performed using the truncated collagen of SEQ ID NO: 91. A 1% and 0.5% collagen solution of a 5% stock solution was prepared according to Example 8 and tested. The truncated collagen of SEQ ID NO: 91 had keratinocyte cell viability assay values of 102 ± 2.9 and 102 ± 2.0 , respectively. The observed values were statistically significant ($p < 0.05$).

[0259] In addition to its effects on cell proliferation, the test material was also screened to determine if it had an impact on cell recovery after UVB exposure. In this study, exposure to UVB was observed to result in a significant reduction in the number of viable cells 48 hours post exposure. However, treatment with the test material prevented this decrease in cell viability. The effect was evident within a concentration range between 0.05% and 5% of the test material, with an optimal effect at a concentration of 0.05%. Within this range of concentrations cell viability was significantly greater than the untreated group (with the lone exception of the 0.01% concentration), demonstrating that the material has UVB protective effect. Since this material was added after the UVB exposure it could be acting to reduce the damaging effects of the UVB irradiation, or it could be helping the damaged cells to recover at a faster rate. With respect to the latter, then truncated collagen is beneficial when applied topically to the skin and has a regenerative effect on skin cells damaged by UVB.

[0260] In addition, the UVB protection assay was performed using the truncated collagen of SEQ ID NO: 91. A 1% and 0.5% collagen solution of SEQ ID NO: 91 had keratinocyte cell viability assay values of 80 ± 4.6 and 78 ± 2.5 , respectively. The observed values were statistically significant ($p < 0.05$).

Example 8: Effect of Truncated Collagen on Thymine Dimer Formation

[0261] Upon exposure to ultraviolet radiation the thymine dimer (TT dimer) content in DNA present in cells increases. Increases in TT dimer formation are correlated with skin damage and certain types of cell proliferative diseases including skin
5 cancer.

[0262] The polynucleotide of SEQ ID NO: 11 was expressed in the expression system of Example 1 and purified as described in this example. The encoded polypeptide includes the DsbA secretion tag. As the polypeptide is processed through the secretion pathway, the DsbA tag, amino acids 1-24 of SEQ ID NO: 12 is cleaved
10 by the host cell. The truncated collagen without the DsbA secretion tag is provided in SEQ ID NO: 91.

[0263] The truncated collagen of SEQ ID NO: 91 was tested to determine if it could reduce TT dimer formation in human epidermal keratinocytes. For this study, the cells were exposed to UVB (25 mJ/cm²). Following the exposures cells were treated
15 with the test materials or Trolox (100 µg/ml) and incubated overnight. On the following day cellular DNA was extracted and assayed for thymine dimer content using an ELISA based method.

[0264] Human keratinocytes were seeded into 12-well plates using normal media and incubated for 24 hours at 37±2°C and 5±1% CO₂. After this initial incubation the
20 media was replaced with 100 µl of phosphate buffered saline (PBS) and the cells were exposed to UVB (25 mJ/cm²). After the UVB exposure, the PBS was replaced with fresh media supplemented with the test materials or Trolox (100 µg/ml, this served as the positive control) and the cells were cultured overnight at 37±2°C and 5±1% CO₂. At the end of the incubation cellular DNA was extracted.

[0265] After the overnight incubation the cell culture media was removed from the wells and replaced with 200 µl of PBS and 20 µl of Proteinase K. After swirling the plate to mix the PBS and Proteinase K, 200 µl of buffer AL was added to each well. After again swirling the plate to mix the reagents, the plates were incubated for 10 minutes at 55±2°C. After cooling the plate to room temperature, the DNA was
30 precipitated by the addition of 200 µl of 100% ethanol. The precipitated DNA mixtures were then transferred to DNEasy Spin Columns in 2 ml collection tubes and centrifuged at 8,000 RPM for 1 minute. The flow through and collection tubes were discarded, and 500 µl of Wash Buffer One was added to the spin column and the column was placed into a new collection tube and centrifuged at 8,000 RPM for 1

minute. The flow through and collection tube were again discarded, and 500 µl of Wash Buffer Two was added to the spin column and the column was placed into a new collection tube and centrifuged at 14,000 RPM for 3 minutes. The spin column was then placed into a new 1.5 ml centrifuge tube and 110 µl of ultrapure water was added to the column. The column was incubated for 1 minute at room temperature and then centrifuged at 8,000 RPM for 1 minute.

[0266] Extracted DNA was quantified via a fluorometric assay. A 2 µl aliquot of the DNA sample was mixed with 100 µl TE buffer in a 96-well plate. A series of DNA standards was also transferred to wells in a 96-well plate (in duplicate). Finally, 100 µl of dilute Cyquant Green dye was added to each well and the fluorescence intensity of each well was determined using an excitation wavelength of 480 nm and an emission wavelength of 520 nm.

[0267] Thymine Dimer Detection was determined using an OxiSelect™ UV-Induced DNA Damage ELISA Kit)

[0268] Aliquots of genomic DNA samples or standards were converted to single stranded DNA by incubating the samples at 95°C for 10 minutes and then chilled on ice. 100 µl of each sample or standard was transferred to a DNA binding ELISA plate and incubated overnight at 4°C. On the following day the wells were rinsed once with 100 µl of PBS and then blocked with 150 µl of Assay Diluent for one hour at room temperature. After removing the Assay Diluent, 100 µl of anti-CPD antibody was added to each well and the plate was incubated for one hour at room temperature. After this incubation, the plate was washed three times with 250 µl of wash buffer per well, and then 150 µl of Blocking Reagent was added to the plate. The plate will be blocked again for one hour at room temperature, and then washed three times as described before. 100 µl of Secondary Antibody was then added to each well and the plate was incubated for 1 hour at room temperature. After washing the plate again, 100 µl of substrate was added to each well and the plate was incubated for 5-20 minutes to allow for color generation in the plate. The color generation reaction was stopped by the addition of 100 µl of stop solution and the plate was read at 460 nm using a plate reader.

[0269] To quantify the amount of DNA present, a standard curve was generated using known concentrations of DNA and their respective fluorescence intensity (measured in RFUs or relative fluorescence units). A regression analysis was performed to establish the line that best fits these data points. The Relative

Fluorescence Units (RFU) for each unknown sample was then used to estimate the amount of DNA.

[0270] A series of DNA standards with known amounts of thymine dimer content were used to generate a standard curve. This standard curve was used to determine the amount of DNA damage in the sample DNA. Means for each treatment group were calculated and compared using an ANOVA. In table 8 and Fig. 5, a standard 5% collagen solution (5g truncated collagen in 95 ml deionized water was further diluted with phosphate buffered saline (PBS) to the indicated percent solution.

[0271] **Table 8. Thymine Dimer Assay**

Treatment	Thymine Dimer, ng/ml
Non-UVB Exposed	0.1 ± 0.2*
Untreated	10.7 ± 1.4*
100 µg/ml Trolox	1.6 ± 0.3*
5% Truncated Collagen	3.5 ± 0.3*
1% Truncated Collagen	5.5 ± 1.0*
0.5% Truncated Collagen	8.9 ± 0.8
0.1% Truncated Collagen	9.2 ± 0.9
0.05% Truncated Collagen	9.2 ± 0.3

10 *Denotes values which are statistically significantly different from untreated with P<0.05

[0272] Table 8 shows that the 5% and the 1% truncated collagen solution reduced TT dimer formation with statistical significance ($p < 0.05$). The data is presented graphically in Fig. 5.

15 [0273] The experiment was repeated with a different lot of truncated collagen (SEQ ID NO: 91). The amount of TT dimer in ng/ml in non-UVB exposed cells was 1.3 ± 1.2 , untreated cells was 18.1 ± 0.4 , 100 µg/ml Trolox treated cells was 7.9 ± 0.3 , 5% collagen was 13.1 ± 0.2 , and 1% collagen was 17.4 ± 0.7 . The reduction in TT dimer formation for non-UVB exposed cells, Trolox treated cells, 5% collagen treated cells
20 and 1% collagen treated cells was statistically significant compared to untreated cells ($p < 0.05$).

Example 9: Human Collagens

Truncated Human Collagen Type 21 alpha 1

[0274] A truncated human collagen type 21 alpha 1 without a His tag, linker, and thrombin cleavage site is disclosed below. The codon-optimized nucleotide sequence encoding this collagen and the amino acid sequence are disclosed below. In SEQ ID NOs: 73 and 74, the DsbA secretion tag is encoded by nucleotides 1-72 and encodes amino acids 1-24. In SEQ ID NOs: 73 and 74, the truncated collagen sequence is encoded by nucleotides 73-633 and encodes amino acids 25-211.

[0275] The codon-optimized nucleotide sequence encoding this collagen is provided in SEQ ID NO: 73.

ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
 10 TCGGCGGCGCAGTATGAAGATGCAGGTTTTCCGGGTCTGCCTGGTCCGGC
 AGGCGAACCGGGTCGTCATGGTAAAGATGGTCTGATGGGTAGTCCGGGT
 TTAAAGGTGAAGCAGGTTACCGGGTGACCTGGTCAGGATGGCACCCGT
 GGTGAACCGGGTATTCCGGGATTTCCGGGTAATCGTGGCCTGATGGGTCA
 GAAAGGTGAAATTGGTCCGCCTGGTCAGCAGGGTAAAAAAGGCGCACCG
 15 GGTATGCCAGGACTGATGGGTTCAAATGGCAGTCCGGGTCAGCCAGGCAC
 ACCGGGTTCAAAAGGTAGCAAAGGCGAACCTGGTATTCAGGGTATGCCTG
 GTGCAAGCGGTCTGAAAGGCGAGCCAGGTGCCACCGGTTCTCCGGGTGAA
 CCAGGTTATATGGGTCTGCCAGGTATCCAAGGCAAAAAAGGTGATAAAGG
 TAATCAGGGCGAAAAAGGCATTACAGGGCCAGAAAGGCGAAAATGGCCGT
 20 CAGGGTATTCCAGGCCAGCAGGGCATCCAGGGTCATCATGGTGCAAAAGG
 TGAACGTGGTGAAAAGGGCGAACCCAGGTGTTTCGTtaa (SEQ ID NO: 73)

[0276] The amino acid sequence is disclosed in SEQ ID NO: 74.

MKKIWLALAGLVLAFFSASAAQYEDAGFPGLPGPAGEPGRHGKDGLMGSPGF
 KGEAGSPGAPGQDGTREGPGIPGFPNGRLMGQKGEIGPPGQQGKKGAPGM
 25 PGLMGSNGSPGQPGTPGSKGSKGEPGIQGMPGASGLKGEPGATGSPGEPGYM
 GLPGIQGKKGDKGNQGEKGIQGQKGENGRQGIPGQQGIQGHGAKGERGEK
 GEPGVR (SEQ ID NO: 74)

[0277] The codon-optimized nucleotide sequence encoding the truncated human collagen type 21 alpha 1 without the DsbA secretion tag collagen is provided in SEQ ID NO: 75.

TGCAGGTTTTCCGGGTCTGCCTGGTCCGGCAGGCGAACCGGGTCGTCATG
 GTAAAGATGGTCTGATGGGTAGTCCGGGTTTTAAAGGTGAAGCAGGTTCA
 CCGGGTGACCTGGTCAGGATGGCACCCGTGGTGAACCGGGTATTCCGGG
 ATTTCCGGGTAATCGTGGCCTGATGGGTCAGAAAGGTGAAATTGGTCCGC

CTGGTCAGCAGGGTAAAAAAGGCGCACCGGGTATGCCAGGACTGATGGG
 TTCAAATGGCAGTCCGGGTCAGCCAGGCACACCGGGTTCAAAGGTAGCA
 AAGGCGAACCTGGTATTCAGGGTATGCCTGGTGCAAGCGGTCTGAAAGGC
 GAGCCAGGTGCCACCGGTTCTCCGGGTGAACCAGGTTATATGGGTCTGCC
 5 AGGTATCCAAGGCAAAAAAGGTGATAAAGGTAATCAGGGCGAAAAAGGC
 ATTCAGGGGCCAGAAAGGCGAAAAATGGCCGTACAGGGTATTCAGGGCCAGC
 AGGGCATCCAGGGTCATCATGGTGCAAAAGGTGAACGTGGTGAAAAGGG
 CGAACCAGGTGTTCGTtaa (SEQ ID NO: 75)

[0278] The amino acid sequence of truncated human collagen type 21 alpha 1
 10 without the DsbA secretion tag is disclosed in SEQ ID NO: 76.

AGFPLPGPAGEPGRHKGKDLGMSGPGFKGEAGSPGAPGQDGRGEPGIPGFP
 GNRGLMGQKGEIGPPGQQGKKGAPGMPGLMGSNGSPGQPGTPGSKGSKGEP
 GIQMPGASGLKGEPGATGSPGEPGYMGLPGIQGKKGDKGNQGEKGIQGQK
 GENGRQGIPGQQGIQGHGAKGERGEKGEPGVR (SEQ ID NO: 76)

15 **Truncated Human Collagen type 1 alpha 2 (1)**

[0279] A truncated human collagen type 1 alpha 2 without a His tag, linker, and
 thrombin cleavage site is disclosed below. The codon-optimized nucleotide sequence
 and the amino acid sequences are disclosed below. In SEQ ID NOs: 78 and 79, The
 DsbA secretion tag is encoded by nucleotides 1-72 and encodes amino acids 1-24.

20 The truncated collagen sequence is encoded by nucleotides 73-636 and encodes
 amino acids 25-212.

[0280] The codon-optimized nucleotide sequence encoding this collagen is
 provided in SEQ ID NO: 77.

ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
 25 TCGGCGGCGCAGTATGAAGATATGGGTCCGCCTGGTAGCCGTGGTGCAAG
 TGGTCCGGCAGGCGTTCGTGGTCCGAATGGTGATGCAGGTCGTCCGGGTG
 AACCGGGTCTGATGGGTCCTCGTGGTCTGCCTGGTTCACCGGGTAATATTG
 GTCCTGCAGGTAAAGAAGGTCCGGTTGGTCTGCCAGGTATTGATGGCCGT
 CCGGGTCCGATTGGTCCAGCCGGTGACGTGGTGAACCTGGCAATATTGG
 30 TTTTCCGGGTCCTAAAGGTCCGACCGGTGATCCGGGTAAAAATGGTGATA
 AAGGTCATGCAGGTCTGGCAGGCGCACGCGGTGCACCTGGTCCGGATGGT
 AATAATGGTGCACAGGGTCCACCGGGTCCGCAGGGTGTTCAAGGTGGTAA
 AGGCGAACAGGGTCCTGCCGGTCTCCGGGTTTTTCAGGGACTGCCTGGTC
 CGAGCGGTCTGCGGGTGAAGTTGGTAAACCTGGTGAACGCGGTCTGCAT

GGTGAATTTGGCCTGCCTGGGCCTGCAGGTCCGCGTGGCGAACGTGGTCC
GCCAGGTGAAAGCGGTGCAGCAGGTCCGACAGGT_{taa} (SEQ ID NO: 77)

[0281] The amino acid sequence is disclosed in SEQ ID NO: 78.

MKKIWLALAGLVLA_{FSASAAQYEDMGPPGSRGASGPAGVRGPNGDAGRPGE}
5 PGLMGPRGLPGSPGNIGPAGKEGPVGLPGIDGRPGPIGPAGARGE_{PGNIGFPGP}
KGPTGDPGKNGDKGHAGLAGARGAPGPDGNNGAQGPPGPQGVQGGKGEQ
PAGPPGFQGLPGPSGPAGEVGKPGERGLHGEFGLPGPAGPRGERGPPGESGAA
GPTG (SEQ ID NO: 78)

[0282] The nucleic acid sequence of truncated human collagen type 1 alpha 2(1)
10 without the DsbA secretion tag is disclosed in SEQ ID NO: 79.
ATGGGTCCGCCTGGTAGCCGTGGTGCAAGTGGTCCGGCAGGCGTTCGTGG
TCCGAATGGTGATGCAGGTTCGTCGGGTGAACCGGTCTGATGGGTCTCTC
GTGGTCTGCCTGGTTCACCGGGTAATATTGGTCCTGCAGGTAAAGAAGGT
CCGGTTGGTCTGCCAGGTATTGATGGCCGTCCGGGTCCGATTGGTCCAGCC
15 GGTGCACGTGGTGAACCTGGCAATATTGGTTTTCCGGGTCCTAAAGGTCC
GACCGGTGATCCGGGTAAAAATGGTGATAAAGGTCATGCAGGTCTGGCAG
GCGCACGCGGTGCACCTGGTCCGGATGGTAATAATGGTGCACAGGGTCCA
CCGGGTCCGCAGGGTGTTCAGGTGGTAAAGGCGAACAGGGTCCTGCCGG
TCCTCCGGGTTTTCAGGGACTGCCTGGTCCGAGCGGTCCTGCCGGTGAAGT
20 TGGTAAACCTGGTGAACGCGGTCTGCATGGTGAATTTGGCCTGCCTGGGC
CTGCAGGTCCGCGTGGCGAACGTGGTCCGCCAGGTGAAAGCGGTGCAGCA
GGTCCGACAGGT_{taa} (SEQ ID NO: 79)

[0283] The amino acid sequence of truncated human collagen type 1 alpha 2(1)
without the DsbA secretion tag is disclosed in SEQ ID NO: 80.

25 MGPPGSRGASGPAGVRGPNGDAGRPGE_{PGLMGPRGLPGSPGNIGPAGKEGPV}
GLPGIDGRPGPIGPAGARGE_{PGNIGFPGPKGPTGDPGKNGDKGHAGLAGARG}
APGPDGNNGAQGPPGPQGVQGGKGEQGPAGPPGFQGLPGPSGPAGEVGKPG
ERGLHGEFGLPGPAGPRGERGPPGESGAAGPTG (SEQ ID NO: 80)

Truncated Human Collagen type 1 alpha 2 (2)

30 [0284] A truncated human collagen type 1 alpha 2 without a His tag, linker, and
thrombin cleavage site is disclosed below. The codon-optimized nucleotide sequence
and the amino acid sequences are disclosed below. in SEQ ID NO: 82 and 83, the
DsbA secretion tag is encoded by nucleotides 1-72 and encodes amino acids 1-24.

The truncated collagen sequence is encoded by nucleotides 73-609 and encodes amino acids 25-203.

[0285] The codon-optimized nucleotide sequence encoding this collagen is provided in SEQ ID NO: 81.

5 ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
TCGGCGGCGCAGTATGAAGATGGTTTTAGGGTCCTGCCGGTGAACCGGG
TGAACCTGGTCAGACAGGTCCGGCAGGCGCACGTGGTCCTGCAGGTCTC
CTGGTAAAGCCGGTGAAGATGGTCATCCGGGTAAACCGGGTCGTCCTGGT
GAACGTGGTGTGTTGGTCCGCAGGGTGCCCGTGGTTTTCCGGGTACTCCG
10 GGTCTGCCAGGTTTTAAAGGTATTCGTGGTCATAATGGTCTGGATGGTCTG
AAAGGTCAGCCTGGTGCACCGGGTGTTAAAGGTGAACCAGGTGCTCCGGG
TGAAAATGGCACACCGGGTCAGACCGGTGCGCGTGGTCTGCCTGGCGAAC
GCGGTCGTGTTGGTGCACCTGGTCCAGCCGGTGCACGCGGTAGTGATGGT
AGCGTTGGTCCGGTTGGTCCAGCGGGTCCGATTGGTAGCGCAGGTCCACC
15 GGGTTTTCCAGGCGCACCGGGTCCGAAAGGTGAAATTGGTGCAGTTGGTA
ATGCAGGCCCTGCCGGTCCAGCAGGACCGCGTGGTGAAGTTGGCCTGCCT
GGTCTGtaa (SEQ ID NO: 81)

[0286] The amino acid sequence is disclosed in SEQ ID NO: 82.

MKKIWLALAGLVLAFFSASAAQYEDGFQGPAGEPGEPGQTGPAGARGPAGPP
20 GKAGEDGHPGKPRPGERGVVGPQGARGFPGTPGLPGFKGIRGHNLGLDLK
GQPGAPGVKGEPGAPGENGTPGQTGARGLPGERGRVGAPGPAGARGSDGSV
GPVGPAGPIGSAGPPGFPAPGPKGEIGAVGNAGPAGPAGPRGEVGLPGL
(SEQ ID NO: 82)

[0287] The nucleic acid sequence of truncated human collagen type 1 alpha 2(2) without the DsbA secretion tag is disclosed in SEQ ID NO: 83.

GGTTTTAGGGTCCTGCCGGTGAACCGGGTGAACCTGGTCAGACAGGTCC
GGCAGGCGCACGTGGTCCTGCAGGTCTCCTGGTAAAGCCGGTGAAGATG
GTCATCCGGGTAAACCGGGTCGTCCTGGTGAACGTGGTGTGTTGGTCCGC
AGGGTGCCCGTGGTTTTCCGGGTACTCCGGGTCTGCCAGGTTTTAAAGGTA
30 TTCGTGGTCATAATGGTCTGGATGGTCTGAAAGGTCAGCCTGGTGCACCG
GGTGTTAAAGGTGAACCAGGTGCTCCGGGTGAAAATGGCACACCGGGTCA
GACCGGTGCGCGTGGTCTGCCTGGCGAACGCGGTGCGTGTGTTGGTGCACCTG
GTCCAGCCGGTGCACGCGGTAGTGATGGTAGCGTTGGTCCGGTTGGTCCA
GCGGGTCCGATTGGTAGCGCAGGTCCACCGGGTTTTCCAGGCGCACCGGG

TCCGAAAGGTGAAATTGGTGCAGTTGGTAATGCAGGCCCTGCCGGTCCAG
CAGGACCGCGTGGTGAAGTTGGCCTGCCTGGTCTGtaa (SEQ ID NO: 83)

[0288] The amino acid sequence of truncated human collagen type 1 alpha 2(2) without the DsbA secretion tag is disclosed in SEQ ID NO: 84.

5 GFQGPAGEPGEPGQTGPAGARGPAGPPGKAGEDGHPGKPRPGERGVVGPQ
GARGFPPTPGLPGFKGIRGHNGLDGLKGQPGAPGVKGEPGAPGENGTPGQTG
ARGLPGERGRVGAPGPAGARGSDGSVGPVGPAGPIGSAGPPGFPAPGPKGEI
GAVGNAGPAGPAGPRGEVGLPGL (SEQ ID NO: 84)

[0289] The polynucleotides of SEQ ID NO: 73, 77 or 81 were subcloned in vector
10 pET28a as described herein to prepare a transformation vector. Host cells were
transformed with the vector the polynucleotides were expressed as described in
Example 2.

[0290] After the fermentation was completed, the truncated human collagen was
purified from the fermentation broth using the procedures disclosed in Example 3.

15 The purified truncated human collagens were analyzed using SDS-PAGE and HPLC
as disclosed in Example 3.

[0291] All three truncated human collagens ran at the expected molecular weights in
the SDS-PAGE analysis. In analyzing the truncated human collagens using HPLC, a
standard curve using the jellyfish collagen of Example 3 was utilized. The retention
20 times of the human collagens were slightly different than the jellyfish collagen. The
retention time of SEQ ID NO: 76 was 5.645 minutes, the retention time of SEQ ID
NO: 80 was 5.631 minutes, and SEQ ID NO: 84 ran at two peaks and the retention
times were 5.531 and 5.7 minutes.

**Truncated Human Collagen Type 1 alpha 2 truncation 5 with DsbA secretion
25 and FLAG tag**

[0292] The amino acid sequence of truncated human collagen type 1 alpha 2
truncation 5 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 92. The
DsbA secretion tag is encoded by nucleotides 1-57 of SEQ ID NO: 93 and the amino
acid sequences are amino acids 1-19 of SEQ ID NO: 92. The collagen nucleotide
30 sequences are nucleotides 58-657 of SEQ ID NO: 93 and the amino acid sequences
are amino acids 20-219 of SEQ ID NO: 92. The FLAG nucleotide sequences are
nucleotides 658-684 of SEQ ID NO: 93 and the amino acid sequences are amino acids
220-228.

MKKIWLALAGLVLAFSASAGDQGPVGRTGEVGAVGPPGFAGEKGPSGEAGT
 AGPPGTPGPQGLLGAPGILGLPGSRGERGLPGVAGAVGEPGLGIAGPPGARG
 PPGAVGSPGVNGAPGEAGRDGNPGNDGPPGRDGQPGHKGERGYPGNIGPVG
 AAGAPGPHGPVGPAGKHGNRGETGPSGPVGPAGAVGPRGPSGPQGIRGDKG
 5 EPGEKGPRGLPGLGDYKDDDDK (SEQ ID NO: 92)
 [0293] The nucleic acid sequence of truncated human collagen type 1 alpha 2
 truncation 5 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 93.
 ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
 TCGGCGGGTGATCAGGGTCCGTTGGTCGTACCGGTGAAGTTGGTGCAGT
 10 CGGGCCGCCGGGTTTTGCGGGTGAAAAAGGCCCGTCAGGTGAAGCAGGC
 ACCGCTGGCCCTCCTGGCACGCCTGGCCACAGGGTTTACTGGGCGCACC
 TGGAATTCTGGGACTGCCGGGCAGCCGTGGAGAACGCGGTTTACCAGGTG
 TTGCCGGTGCCGTTGGTGAACCTGGTCCACTGGGCATTGCAGGGCCGCCT
 GGCGCACGGGGACCGCCTGGTGCTGTTGGTAGTCCGGGTGTGAATGGTGC
 15 TCCGGGTGAAGCCGGTCGTGACGGTAATCCGGGAAATGACGGCCCCGCCAG
 GCCGCGATGGTCAGCCGGGTCATAAAGGTGAGCGTGTTACCCAGGTAAT
 ATTGGTCCAGTCGGTGCCGCCGGTGCGCCGGGTCCTCATGGCCCTGTCGGT
 CCAGCCGGTAAACATGGTAATCGCGGTGAGACAGGTCCGTGAGGACCAGT
 GGGCCCTGCTGGCGCAGTCGGTCCGCGCGGGCCGAGTGGCCCTCAGGGTA
 20 TTCGTGGCGATAAAGGGGAACCGGGCGAAAAAGGGCCGCGGGGTCTGCC
 AGGCCTGGGTGACTACAAAGACGACGACGACAAAtaa (SEQ ID NO: 93)

[0294] The polynucleotide of SEQ ID NO: 93 was subcloned into vector pET28a,
 expressed host *E. coli* cells and the truncated collagen was purified as described
 herein. The purified collagen produced a clear band on SDS-PAGE and an anti-
 25 FLAG western was observed at around 100 kilodaltons. There were no existing bands
 that appear at that location on the gel in the absence of expression of this protein.

**Truncated Human Collagen Type 1 alpha 2 truncation 6 with DsbA secretion
and FLAG tag**

[0295] The amino acid sequence of truncated human collagen type 1 alpha 2
 30 truncation 6 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 94. The
 DsbA secretion tag is encoded by nucleotides 1-57 of SEQ ID NO: 95 and the amino
 acid sequences are amino acids 1-19 of SEQ ID NO: 94. The collagen nucleotide
 sequences are nucleotides 58-657 of SEQ ID NO: 95 and the amino acid sequences
 are amino acids 20-219 of SEQ ID NO: 94. The FLAG nucleotide sequences are

nucleotides 658-684 of SEQ ID NO: 95 and the amino acid sequences are amino acids 220-228 of SEQ ID NO: 94.

MKKIWLALAGLVLAFSASAKGHNGLQGLPGIAGHHGDQGAPGSVGPAGPRG
 PAGPSGPAGKDGRGTGHPGTVGPAGIRGPQGHQGPAGPPGPPGPPGPPGVSGG
 5 GYDFGYDGDIFYRADQPRSAPSLRPKDYEVDATLKSLNNQIETLLTPEGSRKN
 PARTCRDLRLSHPEWSSGYWIDPNQGCTMDAIAKVCDFSTGETCIRAQPENI
 PAKNWYRSSKDGDYKDDDDK (SEQ ID NO: 94)

[0296] The nucleic acid sequence of truncated human collagen type 1 alpha 2 truncation 6 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 95.

10 ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
 TCGGCGAAAGGTCACAATGGACTGCAAGGCCTGCCAGGTATTGCAGGTCA
 TCATGGTGATCAAGGTGCCCCGGGAAGCGTTGGTCCGGCGGGGCCGAGAG
 GCCCTGCGGGACCTTCAGGTCCGGCAGGCAAAGATGGTCGGACAGGCCAT
 CCGGGCACCGTTGGCCCTGCAGGAATTCGTGGACCGCAGGGTCATCAGGG
 15 ACCTGCTGGTCCGCCAGGTCCCCCGGGCCCTCCGGGACCACCGGGTGTTA
 GTGGTGGTGGTTATGATTTTGGCTATGATGGTGATTTTTATCGTGCAGATC
 AGCCGCGTAGCGCACCGAGCCTGCGTCCTAAAGATTATGAAGTTGATGCA
 ACCCTGAAAAGCCTGAATAATCAGATTGAAACACTGCTGACACCGGAAGG
 TAGCCGTAAAAATCCGGCCCCGTACCTGTCGTGATCTGCGTCTGAGCCACC
 20 CGGAATGGAGCAGCGGTTATTATTGGATTGATCCGAATCAAGGTTGTACC
 ATGGATGCAATTAAAGTTTATTGTGATTTTAGCACAGGTGAAACATGTATC
 CGTGCACAGCCGGAATAATATCCGGCCAAAAATTGGTATCGTAGTAGCAA
 AGATGGTGACTACAAAGACGACGACGACAAAtaa (SEQ ID NO: 95)

[0297] The polynucleotide of SEQ ID NO: 94 was subcloned into vector pET28a,
 25 expressed host *E. coli* cells and the truncated collagen was purified as described
 herein. The purified collagen produced a clear band on SDS-PAGE and an anti-
 FLAG western was observed at around 25 kilodaltons. There were no existing bands
 that appear at that location on the gel in the absence of expression of this protein.

**Truncated Human Collagen Type 1 alpha 2 truncation 7 with DsbA secretion
 and FLAG tag**
 30

[0298] The amino acid sequence of truncated human collagen type 1 alpha 2 truncation 7 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 96. The DsbA secretion tag is encoded by nucleotides 1-57 of SEQ ID NO: 97 and the amino acid sequences are amino acids 1-19 of SEQ ID NO: 96. The collagen nucleotide

sequences are nucleotides 58-759 of SEQ ID NO: 96 and the amino acid sequences are amino acids 20-253 of SEQ ID NO: 96. The FLAG nucleotide sequences are nucleotides 760-786 of SEQ ID NO: 97 and the amino acid sequences are amino acids 254-262 of SEQ ID NO: 96.

- 5 MKKIWLALAGLVLAFSASAYEVDATLKSLNNQIETLLTPEGSRKNPARTCRD
LRLSHPEWSSGY YWIDPNQGCTMDAIKVYCDFSTGETCIRAQPENIPAKNWWY
RSSKDKKHVWLGETINAGSQFEYNVEGVTSKEMATQLAFMRLLANYASQNI
TYHCKNSIAYMDEETGNLKKAVILQGSNDVELVAEGNSRFTYTVLVDGCSKK
TNEWGKTHIEYKTNKPSRLPFLDIAPLDIGGADQEFFVDIGPVCFKGDYKDDD
10 DK (SEQ ID NO: 96)

[0299] The nucleic acid sequence of truncated human collagen type 1 alpha 2 truncation 7 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 97.

- TGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCAT
CGGCGTATGAAGTTGATGCAACCCTGAAAAGCCTGAATAATCAGATTGAA
15 AACTGCTGACACCGGAAGGTAGCCGTAAAAATCCGGCCCGTACCTGTCTG
TGATCTGCGTCTGAGCCACCCGGAATGGAGCAGCGGTTATTATTGGATTG
ATCCGAATCAAGGTTGTACCATGGATGCAATTAAAGTTTATTGTGATTTTA
GCACAGGTGAAACATGTATCCGTGCACAGCCGGAATAATTCCGGCCAAA
AATTGGTATCGTAGTAGCAAAGATAAAAAACATGTGTGGCTGGGTGAAAC
20 CATTAATGCAGGTAGCCAGTTTGAATACAATGTTGAAGGTGTTACCAGCA
AAGAAATGGCAACACAGCTGGCATTATGCGTCTGCTGGCAAATTATGCA
AGCCAGAATATTACATATCATTGTAAAAATAGCATTGCATATATGGATGA
AGAAACCGGTAATCTGAAAAAAGCAGTTATTCTGCAGGGTAGCAATGATG
TTGAACTGGTTGCCGAAGGTAATAGCCGTTTTACATATACCGTTCTGGTTG
25 ATGGTTGTAGCAAAAAAACC AATGAATGGGGTAAAACCATCATTGAATAT
AAAACCAACAAACCGAGCCGTCTGCCGTTTCTGGATATCGCTCCGCTGGA
TATTGGTGGTGCCGATCAGGAATTTTTTGTTCGATATCGGTCCTGTGTGTTTT
AAAGGTGACTACAAAGACGACGACGACAAAtaa (SEQ ID NO: 97)

- [0300]** The polynucleotide of SEQ ID NO: 97 was subcloned into vector pET28a,
30 expressed host *E. coli* cells and the truncated collagen was purified as described
herein. The purified collagen produced a clear band on SDS-PAGE and an anti-
FLAG western was observed at around 30 kilodaltons. There were no existing bands
that appear at that location on the gel in the absence of expression of this protein.

Example 10: Protective Effect of Truncated Human Collagen on Fibroblasts

[0301] The effect of truncated human collagen on fibroblast cell viability, procollagen synthesis, and elastin Synthesis is determined according to the methods of Example 6.

5 [0302] The effect of truncated human collagen on Keratinocyte proliferation and UVB protection is determined according to the methods of Example 7.

[0303] The effect of truncated collagen on thymine dimer formation after exposure to UV radiation is determined according to the methods of Example 8.

10 [0304] It is understood that the examples and embodiments described herein are for illustrative purposes only and that various modifications or changes in light thereof will be suggested to persons skilled in the art and are to be included within the spirit and purview of this application and scope of the appended claims. All publications, patents, and patent applications cited herein are hereby incorporated by reference in their entirety for all purposes.

15 **Example 11: Effect of Truncated Collagen on Inflammatory Cytokines**

[0305] Keratinocytes and dermal fibroblasts play an important role in the immune response of the skin. In response to irritating chemicals or UV radiation (pro-inflammatory/pro-irritation stimuli), keratinocytes can release a vast array of cytokines. These cytokines are thought to help engage immune cells to the site of inflammation. Cytokines released by the keratinocytes include TNF α , IL-1 α , IL-1 β ,
20 IL-3, IL-6, IL-7, IL-8, IL-10, IL-18, and IL-1RA.

[0306] The testing model used for this study was the MatTek EpiDerm. This skin model consists of normal human-derived epidermal keratinocytes that have been cultured to form a multilayered, highly differentiated model of the human epidermis.

25 Ultrastructural analysis has revealed the presence of keratohyalin granules, tonofilament bundles, desmosomes, and a multi-layered stratum corneum containing intercellular lamellar lipid layers arranged in patterns characteristic of in vivo epidermis. Markers of mature epidermis specific differentiation such as pro-filaggrin, the K1/K10 cytokeratin pair, involucrin, and type I epidermal transglutaminase have
30 been localized in this model. The MatTek EpiDerm is also mitotically and metabolically active.

[0307] The MatTek EpiDerm tissues were used to assess the ability of various test materials to inhibit the release the inflammatory mediator IL-1 α . Test materials were

compared to an over the counter topical hydrocortisone preparation (positive control) as well as to untreated tissues (negative control 1) and untreated, non-inflamed tissues (negative control 2). This test was also used to assess the viability of the tissues after exposure to the test materials.

- 5 **[0308]** IL-1 α , IL-6 and IL-8 are synthesized and stored in keratinocytes and have been identified as a mediators of skin irritation and inflammation. Release of these cytokines can be directly measured in tissue culture media via a colorimetric based enzyme linked immunosorbent assay (ELISA). Briefly, antibodies covalently linked to a solid support will bind IL-1 α , IL-6 or IL-8 present in spent culture media samples.
- 10 A second antibody that is covalently attached to an acetylcholinesterase enzyme will in turn detect the specific bound cytokines. Upon addition of an appropriate color substrate the acetylcholinesterase enzyme will generate a colored end product that can be measured spectrophotometrically.

- [0309]** MatTek EpiDerm Tissues were purchased from MatTek corporation and
- 15 were stored at 4°C until used. Prior to use, the tissues to be used were removed from the agarose-shipping tray and placed into a 6-well plate containing 0.9 ml of hydrocortisone free assay medium (37 $\pm$ 2°C). The tissues were allowed to incubate overnight at 37 $\pm$ 2°C and 5 $\pm$ 1% CO₂. After this initial incubation, the assay medium was replaced with 0.9 ml of fresh hydrocortisone free medium (37 $\pm$ 2°C). Three
- 20 tissues were prepared for each test material.

- [0310]** An inflammatory response in the tissues was initiated via UV irradiation (UVB). A UV lamp was used to give a 300 mJ/cm² dose of UVB radiation to the tissues. Immediately after the application of the inflammatory stimuli 50 μ l or mg of test material was applied directly onto the surface of the tissue. An over the counter
- 25 hydrocortisone cream was used as a positive control. For a negative control tissues were exposed to the inflammatory stimuli but were not treated with any type of anti-inflammatory material. One additional set of tissues was left without exposure to the inflammatory stimuli to provide a baseline measurement for the cytokines. The tissues were incubated at 37 $\pm$ 2°C and 5 $\pm$ 1% CO₂ for 24 hours after exposure to the
- 30 inflammatory stimuli. After the 24-hour incubation the cell culture medium was collect and stored at -75° C until analyzed for cytokines.

[0311] The ELISA plates were prepared by diluting the appropriate capture antibody in PBS. Next, 100 μ l of the diluted capture antibody was added to the wells of a 96-well ELISA plate and the plate was incubated overnight at room temperature.

On the following day the plate was washed three times with 300 µl wash buffer (0.05% Tween 20 in PBS) and then blocked by adding 300 µl of blocking buffer (1% BSA in PBS) to each well. The plate was incubated with the blocking buffer for at least one hour. After the incubation the blocking buffer was removed and the plate
5 was washed three times as described above.

[0312] A series of standards was prepared and 100 µl of each of these standards was dispensed into two wells (duplicates) in the appropriate 96-well plate. Subsequently, 100 µl of each sample was added to additional wells and the plate was incubated for two hours at room temperature. After the incubation the plate was washed three times
10 as described above. Once the last wash was removed, 100 µl of a biotin conjugated detection antibody was added. After incubating the plate for two hours at room temperature the plate was washed again as described above. 100 µl of HRP-streptavidin was then added to each well and the plate was incubated for 20 minutes at room temperature. Once the last wash was removed, 100µl of substrate solution
15 (hydrogen peroxide + tetramethylbenzidine as a chromagen) was added to each well. Once a sufficient level of color development had occurred, 50 µl of stop solution (2N sulfuric acid) was added to each well and the plate was read at 460 nm.

[0313] After the 24 hour incubation, the tissues were rinsed twice with at least 100 µl of phosphate buffered saline to remove the test material and then transferred to a 6-
20 well plate containing 1.0 ml of assay medium supplemented with MTT (1 mg/ml) and allowed to incubate for 3 ± 0.25 hours at $37 \pm 2^\circ\text{C}$ and $5 \pm 1\%$ CO₂. After the incubation, the tissues were rinsed at least twice with 100 µl of phosphate buffered saline, blotted dry, and then placed into a 24-well plate containing 2 ml of isopropanol per well. The 24- well plate was covered and allowed to incubate at room
25 temperature for at least 2 hours on a rocking platform to extract the reduced MTT from the tissues. After the extraction, a 200 µl sample of the isopropanol/MTT mixture was transferred to a 96-well plate and the absorbance of the sample was read at 540 nm with a plate reader using 200 µl of isopropanol as the blank. The MTT assay is described in Example 6 herein. The cell viability results of the MTT assay
30 were similar to the results obtained in Example 6

[0314] The results of the IL-1a assay are shown in Table 9 below. A 2% stock solution of the jellyfish collagen of SEQ ID NO: 91 is Sample 4 and Sample 3 is a 2% stock solution of the truncated jellyfish collagen of SEQ ID NO: 10. In Table 9 below, the indicated percentage is the percent dilution of the stock solution used for

- the test. For example, the 1% Sample 4 treatment is a 1% solution of the 2% stock truncated collagen solution. The untreated cells produced 18.2 pg/ml of IL-1a. Upon treatment with truncated collagen, all samples showed decreases in IL-1a production. The 1% Sample 4 treatment reduced IL-1A production to 13.4 pg/ml, which is
- 5 significant with a p value of less than 0.05. The decrease in IL-1a production indicates that the truncated collagen has anti-inflammatory effects.

Table 9 IL-1a Assay

Treatment	IL-1a pg/ml
Non-UVB Exposed	4.9±2.1
Untreated	18.2±1.4
1% Hydrocortisone	6.7±0.6
5% Sample 4	18.1±1.1
1% Sample 4	13.4±0.9*
0.5% Sample 4	15.7±0.7
0.1% Sample 4	13.9±1.7*
5% Sample 3	15.8±2.0

Denotes values that are significantly different from Untreated (p<0.05)

Example 12: Urban Dust Protection by Truncated Collagen

- 10 **[0315]** A keratinocyte cell culture model was used to assess the ability of truncated collagens to exert a protective effect by promoting cell survival after exposure to urban dust.

- [0316]** Human epidermal keratinocytes were pretreated with the test materials and then exposed to urban dust. At the end of the treatment period changes in cell
- 15 viability were then determined via an MTT assay.

- [0317]** Keratinocytes were seeded into the individual wells of a 96 well plate in 100 µl of medium and incubated overnight at 37±2°C and 5±1% CO₂. On the following day the media was removed via aspiration to eliminate any non-adherent cells and replaced with 100 µl of fresh medium. The cells were grown until confluent, with a
- 20 media change every 48 to 72 hours.

Pretreatment with Test Material followed by Urban Dust Treatment

- [0318]** Test materials were prepared at 2x their final desired concentrations in cell culture media. Urban dust (NIST 1649B from Sigma Chemicals) was also prepared at 2x solutions. For the pretreatment, 50 µl of 2x test material was combined with 50 µl

of culture media and the cells were incubated for 24 hours. At the end of the pretreatment period the test material containing culture media was removed and replaced with 50 μ l of 2x urban dust and 50 μ l of media. Another set of cells was treated with media alone (non-dust exposed) and used as a reference control to represent 100% cell viability. The cells were then incubated for 24 hours and then subjected to an MTT assay to determine changes in cell viability.

[0319] At the end of the treatment period, the cell culture medium was removed and the cells were washed with PBS. After the wash, 100 μ l of cell culture media supplemented with 0.5 mg/ml MTT was added to each well and the cells were incubated for 30 minutes at 37+2oC and 5+1% CO₂. After the incubation, the media/MTT solution was removed and the cells were washed again once with PBS and then 100 μ l of isopropyl alcohol was added to the wells to extract the purple formazin crystals. The 96-well plate was then read at 540 nm using isopropyl alcohol as a blank.

[0320] The mean MTT absorbance value for the non-dust exposed cells was calculated and used to represent 100% value for cell number. The individual MTT values from the cells undergoing the various treatments was then divided by the mean value for the non-dust exposed cells and expressed as a percent to determine the change in cell number caused by each treatment.

[0321] The MTT results for the pretreatment with the test material then dust treatments are presented in Table 10. Table 10 shows that as the cells were treated with increasing amounts of collagen, cell viability increased upon pretreatment with truncated collagen and subsequent exposure to urban dust. These results show that truncated collagen protects against the decline in cell viability associated with urban dust exposure.

Table 10 MTT Assay, Truncated Collagen Pretreatment

Treatment	Viability (% Non-Dust Exposed) 4 mg/ml Urban Dust	Viability (% Non-Dust Exposed) 2 mg/ml Urban Dust
Non-Dust Exposed	100 $\pm$ 4.4*	100 $\pm$ 1.8
Untreated	59 $\pm$ 3.8	70 $\pm$ 0.9
0.1% Collagen	61 $\pm$ 4.7	72 $\pm$ 3.5

0.5% Collagen	59±2.2	73±2.2
1% Collagen	58±0.5	74±2.6
5% Collagen	66±1.0	83±6.5*

* Denotes values that are significantly different from untreated group (p<0.05)

Example 12: Truncated *Chondrosia reniformis* (Kidney sponge) Collagen

Truncated *Chondrosia reniformis* (Kidney sponge) Fibrillar Collagen 1 with DsbA secretion and FLAG tag

- 5 [0322] The amino acid sequence of truncated *Chondrosia reniformis* fibrillar collagen 1 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 102. The DsbA secretion tag is encoded by nucleotides 1-57 of SEQ ID NO: 103 and the amino acid sequences are amino acids 1-19 of SEQ ID NO: 102. The fibrillary collagen nucleotide sequences are nucleotides 58-792 of SEQ ID NO: 103 and the amino acid sequences are amino acids 20-264 of SEQ ID NO: 102. The FLAG nucleotide sequences are nucleotides 793-819 of SEQ ID NO: 103 and the amino acid sequences are amino acids 265-273 of SEQ ID NO: 102.

MKKIWLALAGLVLAFAASAPVGRRGPKGSRGDPGDGGAAGPKGPEGVDGLI
GEPGQPGPIGAEGSSGLEGLGDKGSKGARGGPGNRGRPGQDGVPGQDGRA
15 GEKGEGETGDRGQQGLRGKVGDPGLVGDLAGQGPQGSQGLVGPPGIPGEP
GSGGEPGDQGPRGPEGPQGSPGVRGGRGERGTPGAVGPKGPPGKNGADGPR
GLPGASGPPGSPGNQGPEGSRGADGNNGFPGDDGENGLVGIPGEPGPKGARG
TRGELGKTGDYKDDDDK (SEQ ID NO: 102)

- 20 [0323] The nucleic acid sequence of truncated *Chondrosia reniformis* fibrillar collagen 1 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 103.
ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
TCGGCGCCGGTTGGTCGTCGTGGTCCGAAAGGTAGCCGTGGTGATCCTGG
TGATGGTGGTGCAGCAGGTCCTAAAGGTCCGGAAGGTGTTGATGGTCTGA
TTGGTGAACCGGGTCAGCCTGGTCCGATTGGCGCAGAAGGTAGCAGCGGT
25 CTGGAAGGTTTTCTGGGTGATAAAGGTAGCAAAGGTGCACGTGGTGGTCC
GGGTAATCGCGGTCGTCCTGGTCAGGATGGTGTTCGGGTCAAGATGGTC
GTGCCGGTGAAAAAGGTGAAGGTGGTGAAACCGGTGATCGCGGTCAGCA
GGGTCTGCGTGGTAAAGTTGGTGATCCAGGTCTGGTGGGTGATCTGGGTG
CACAGGGTCCGCAGGGTAGCCAAGGTCTGGTTGGTCCGCCTGGTATCCG
30 GGTGAACCTGGTAGCGGTGGCGAACCGGGTGATCAGGGTCCTCGCGGTCC

AGAAGGTCCTCAGGGTTCACCGGGTGTTCGCGGTGGTCGTGGTGAACGTG
 GTACACCGGGTGCAGTTGGACCGAAAGGTCGCCAGGTAAAAATGGTGCA
 GATGGTCCGCGTGGTCTGCCTGGTGCAAGCGGTCTCCGGGTAGTCCTGGT
 AACCAGGGTCCTGAAGGTTCTCGTGGTGCCGATGGTAATAATGGTTTTTCCA
 5 GGTGATGATGGTGAAAATGGCCTGGTTGGTATCCCTGGCGAACCAGGTCC
 AAAAGGCGCACGCGGTACACGCGGTGAACTGGGTAAAACCGGTGACTAC
 AAAGACGACGACGACAAAtaa (SEQ ID NO: 103)

[0324] The polynucleotide of SEQ ID NO: 103 was subcloned into vector pET28a,
 expressed host *E. coli* cells and the truncated *Chondrosia reniformis* fibrillar collagen
 10 l was purified as described herein. The purified fibrillary collagen produced a clear
 band on SDS-PAGE and an anti-FLAG western was observed at around 40
 kilodaltons. There were no existing bands that appear at that location on the gel in the
 absence of expression of this protein.

**Truncated *Chondrosia reniformis* (Kidney sponge) Fibrillar Collagen 2 with
 15 DsbA secretion and FLAG tag**

[0325] The amino acid sequence of truncated *Chondrosia reniformis* fibrillar
 collagen 2 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 104. The
 DsbA secretion tag is encoded by nucleotides 1-57 of SEQ ID NO: 105 and the amino
 acid sequences are amino acids 1-19 of SEQ ID NO: 104. The fibrillary collagen
 20 nucleotide sequences are nucleotides 58-1323 of SEQ ID NO: 105 and the amino acid
 sequences are amino acids 20-441 of SEQ ID NO: 104. The FLAG nucleotide
 sequences are nucleotides 1324-1350 of SEQ ID NO: 105 and the amino acid
 sequences are amino acids 442-450 of SEQ ID NO: 105.

MKKIWLALAGLVLAFFSASAGRGGPAGLQGAAGNPGDPGDRGQAGEIGLPGT
 25 EGQRGQGGSRGDDGIGGQSGTDGPDNDGVAGIRGARGEPPGATGPEGAAGQ
 KGDRGRFGEQGRPGNDGPPGRRGRVGNLGETGAEGDEGTRGYTGDRGPEGA
 IGISGVTGNPGPQGIGKPPGDTGHPGRQGPGSGPQGPPGIPGTDGLTIHNLKPPS
 QFFDATSSSDPLTDAVVESILKSFQYAELEIDLTKKPDGTMKYPAISCDDLHK
 DYPQLPSGNYTLDPNGGCKNDAFETYCEFNNSVKMCLTPKIPTLLPMGTYKY
 30 YVNSEGY YSPNDFGLNLRFFEYYGSVTQLKFLQTKATRV TQTIRVLCKNYDP
 LHKQPVFIGMNDETVMDEPRMEENQCQYFNGLSAHVELELSSNDPSYLP IYE
 MRLYLGRKTNEELGIELGDLCFEYGDYKDDDDK (SEQ ID NO: 104)

[0326] The nucleic acid sequence of truncated *Chondrosia reniformis* fibrillar
 collagen 2 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 105.

ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
 TCGGCGGGTTCGTGGCGGTCCGGCAGGTCTGCAGGGTGCTGCAGGTAATCC
 TGGCGACCCTGGCGATCGTGGTCAGGCAGGCGAAATTGGTCTGCCAGGCA
 CCGAAGGTCAGCGTGGTCAAGGTGGTTCACGTGGTGATGACGGTATTGGT
 5 GGTGAGAGCGGCACCGATGGCGATCCGGGTAACGATGGTGTTGCAGGTAT
 TCGTGGTGCACGCGGAGAACCTGGTGCCACCGGACCTGAAGGTGCAGCCG
 GTCAGAAAGGTGATCGTGGCCGTTTTGGCGAACAGGGTCGTCCGGGAAAT
 GATGGTCCACCGGGTCGCCGTGGCCGTGTGGGCAATCTGGGTGAAACAGG
 TGCCGAAGGTGATGAAGGCACCCGTGGTTATACAGGTGACCGTGGACCGG
 10 AAGGCGCAATTGGTATTAGCGGTGTGACCGGTAATCCGGGTCCACAGGGC
 ATTAAAGGCCCTCCGGGTGATACGGGTTCATCCGGGTTCGTGAGGACCGAG
 CGGTCCGCAAGGACCACCGGTATTCCAGGTACAGATGGCCTGACCATTC
 ATAATCTGATTAAACCGCCTAGCCAGTTTTTTGATGCAACCAGCAGCAGC
 GATCCGCTGACCGATGCAGTTGTTGAAAGCATTCTGAAATCTTTTCAGTAT
 15 GCCGAGCTGGAAATTGACCTGACCAAAAAACCGGATGGCACCATGAAAT
 ATCCGGCAATTAGCTGTGATGATCTGCACAAAGATTATCCGCAGCTGCCG
 AGCGGTAATTATACCCTGGATCCGAATGGTGGTTGTAAAAATGATGCCTTT
 GAAACCTATTGCGAGTTCAACAATAGCGTGAAAATGTGTCTGACCCCGAA
 AATTCCGACACTGCTGCCGATGGGCACCTATAAATACTATGTTAATAGCG
 20 AGGGTTACTACAGCCCGAATGATTTTGGTCTGAATCTGCGCTTTTTTGAGT
 ATTATGGTAGCGTTACCCAGCTGAAATTTCTGCAGACCAAAGCAACCCGT
 GTTACCCAGACCATTCGTGTTCTGTGTAAAACTATGATCCGCTGCATAAA
 CAGCCGGTTTTTTATTGGTATGAATGACGAAACCGTTATGGATGAACCGCG
 TATGGAAGAAAATCAGTGCCAGTATTTTAACGGTCTGAGCGCACATGTTG
 25 AACTGGAAGTGAAGCAGCAATGATCCGAGCTATCTGCCGATTTATGAAATG
 CGTCTGTATCTGGGTCGTAAAACCAATGAAGAACTGGGCATTGAACTGGG
 CGATCTGTGTTTTGAATATGGTGACTACAAAGACGACGACGACAAAtaa
 (SEQ ID NO:105)

[0327] The polynucleotide of SEQ ID NO: 105 was subcloned into vector pET28a,
 30 expressed host *E. coli* cells and the truncated *Chondrosia reniformis* fibrillar collagen
 2 was purified as described herein. The purified fibrillary collagen produced a clear
 band on SDS-PAGE and an anti-FLAG western was observed at around 55
 kilodaltons. There were no existing bands that appear at that location on the gel in the
 absence of expression of this protein.

Truncated *Chondrosia reniformis* (Kidney sponge) Non-Fibrillar Collagen 1 with DsbA secretion and FLAG tag

[0328] The amino acid sequence of truncated *Chondrosia reniformis* non-fibrillar collagen 1 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 106. The DsbA secretion tag is encoded by nucleotides 1-57 of SEQ ID NO: 107 and the amino acid sequences are amino acids 1-19 of SEQ ID NO: 106. The non-fibrillar collagen nucleotide sequences are nucleotides 58-831 of SEQ ID NO: 107 and the amino acid sequences are amino acids 20-277 of SEQ ID NO: 106. The FLAG nucleotide sequences are nucleotides 832-858 of SEQ ID NO: 107 and the amino acid sequences are amino acids 278-286 of SEQ ID NO: 106.

MKKIWLALAGLVLAFAASAETSSKVALMTVLVVITGALIEGTSTIRGSTHV
NRGLRKRQTSEDNCEAVKVGLPGRDGGREGPPGPPGPAGRDGRDAVCSNQTT
GLGAKGDRGPPGTPGFPGEVGRPGLPGADGIPGPQGERGAVGPGGKPGPRGE
VGTPGADGADGATGATGVQGPDGAKGEKGASGTAGLKGEKGDTCIPDSNST
LGMPGTPGAGGSKGQKGESGIVGPKGERGEIGTPGHPGFRGADGEPGHKGVP
GRAGAQQDRGDPGDDGLTG DYKDDDDK (SEQ ID NO: 106)

[0329] The nucleic acid sequence of truncated *Chondrosia reniformis* non-fibrillar collagen 1 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 107.

ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTAGTTTTAGCGTTTAGCGCA
TCGGCGGAAAAAACCAGCAGCAAAGTTGCACTGATGACCGTTCTGGTTGT
TATTACCGGTGCACTGATTATTGAAGGCACCAGCATTACCCGTGGTAGCA
CCCATGTTAATCGTGGTCTGCGTAAACGTCAGACCAGCGAAGATAATTGT
GAAGCAGTTAAAGTTGGTCTGCCAGGTCGTGATGGTCGTGAAGGTCCTCC
GGGTCCGCCTGGTCCGGCTGGCAGAGATGGCCGTGATGCAGTTTGTAGCA
ATCAGACCACCGGTCTGGGTGCAAAAGGTGATCGTGGTCCGCCAGGTACA
CCGGGTTTTCCGGGTGAAGTTGGCCGTCCGGGTCCACCGGGTGCAGATGG
TATTCCGGGTCTCAGGGTGAACGTGGTGCAGTTGGTCCTGGTGGTAAAC
CTGGTCCGCGTGGTGAAGTGGGCACCCCTGGTGCCGATGGCGCAGATGGT
GCAACCGGTGCGACCGGTGTTCAAGGTCCTGATGGTGCCAAAGGCGAAAA
AGGTGCAAGCGGCACCGCAGGTCTGAAAGGTGAGAAAGGCGATACCTGT
ATTCCGGATAGCAATAGCACCCCTGGGTATGCCTGGTACACCAGGTGCCGG
TGGTAGCAAAGGCCAGAAAGGTGAAAGTGGTATTGTTGGTCCGAAAGGC
GAACGCGGTGAAATTGGCACACCGGGTCATCCTGGTTTTCTGGTGGTGC
TGGTGAACCAGGTCATAAAGGTGTTCCGGGTCTGCCGGTGGCGCAGGGTG

ATCGCGGTGATCCGGGTGATGATGGTCTGACCGGTGACTACAAAGACGAC
GACGACAAAtaa (SEQ ID NO: 107)

- [0330] The polynucleotide of SEQ ID NO: 107 was subcloned into vector pET28a, expressed host *E. coli* cells and the truncated *Chondrosia reniformis* non-fibrillar collagen 1 was purified as described herein. The purified non-fibrillar collagen produced a clear band on SDS-PAGE and an anti-FLAG western was observed at around 30 kilodaltons. There were no existing bands that appear at that location on the gel in the absence of expression of this protein.

Truncated *Chondrosia reniformis* (Kidney sponge) Non Fibrillar Collagen 2 with DsbA secretion and FLAG tag

- [0331] The amino acid sequence of truncated *Chondrosia reniformis* non-fibrillar collagen 2 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 108. The DsbA secretion tag is encoded by nucleotides 1-57 of SEQ ID NO: 109 and the amino acid sequences are amino acids 1-19 of SEQ ID NO: 108. The non-fibrillar collagen nucleotide sequences are nucleotides 58-1509 of SEQ ID NO: 109 and the amino acid sequences are amino acids 20-503 of SEQ ID NO: 108. The FLAG nucleotide sequences are nucleotides 1510-1536 of SEQ ID NO: 109 and the amino acid sequences are amino acids 504-512 of SEQ ID NO: 108.

MKKIWLALAGLVLAFFSASAGFPGAPGADGAPGQKGELGAVGPQGTPGLSGP
SGPTGPPGPKGVRGAPGSSGAKGDAGNPGDDGPVGPQGVPGVDGSPGQKGE
TGRVGPRGHDGNGTPGEDGATGFPGPDGAKGEKGTSGTAGLKGEKGDTCP
DSNSTLGMPGTPGAGWSKGQKGESGIVGPKGEKGEIGTPGPPGFRGADGEPG
QRGEPGRAGAQGERGAPGNNGRDGFPGDPGADGAPGQKGELGAIGHPGFSG
PSGPSGPTGPPGPKGVRGAQGRPGDRGSPGDVGPIGAPGPPGADGVPGLTGV
QGRDGPKGESASSGAVYVRWGRITCPSGADVVSRAAGAKYDHSGGTSD
HHCLPNNPQYLSDDTNALGAQLYGVVEYIRDSSPYNSLDQSDMPCVVCNA
NGRSQLLMVPARYTCPTGWSREYYGYMMSEGKAKNREGKTTICMDFSAE
AVPGSGANTNPSPGIMMRANCNGLACPPYQSNTPLTCAVCTKGDKDDDDK
(SEQ ID NO: 108)

- [0332] The nucleic acid sequence of truncated *Chondrosia reniformis* non-fibrillar collagen 2 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 109.
- ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
TCGGCGGGTTTTCTGGCGCTCCGGGTGCCGACGGTGCTCCGGGTCAAAA
AGGTGAACTGGGTGCCGTGGGTCCGCAGGGCACTCCGGGTCTGAGTGGTC

CTAGTGGTCCGACCGGTCCACCAGGTCCAAAAGGCGTGCGTGGTGCACCG
 GGTAGCAGCGGAGCCAAAGGTGATGCAGGTAACCCTGGTGTATGACGGTCC
 GGTTGGTCCACAGGGCGTTCCAGGTGTTGATGGTAGCCCTGGCCAAAAGG
 GTGAAACCGGTTCGTGTGGGTCCCTCGTGGTTCATGATGGTATTAATGGCACC
 5 CCAGGTGAAGATGGTGCACAGGCTTTCCAGGTCCGGATGGCGCAAAGGG
 TGAGAAGGGCACCAGCGGTACAGCTGGCCTGAAGGGCGAAAAGGGCGAT
 ACATGCATCCCGGATTCAAATTCAACACTGGGCATGCCAGGTACGCCTGG
 CGCAGGTTGGAGTAAAGGACAAAAAGGCGAATCAGGCATTGTGGGACCT
 AAAGGCGAGAAGGGTGAGATTGGTACTCCGGGACCGCCAGGCTTTCGCGG
 10 TGCAGACGGCGAACC GGTCAGCGTGGCGAACCTGGTTCGTGCAGGCGCA
 CAAGGTGAACGCGGAGCCCCTGGTAATAATGGACGTGATGGCTTTCCTGG
 TGATCCAGGTGCAGATGGCGCACCTGGCCAGAAAGGCGAACTGGGAGCA
 ATTGGTCATCCGGGATTTAGCGGTCCGTCAGGTCCGAGCGGACCGACAGG
 TCCTCCTGGACCGAAAGGTGTACGTGGCGCACAGGGTCGTCTGGCGATC
 15 GTGGCAGTCCAGGTGATGTGGGTCCGATTGGTGCACCTGGTCCTCCAGGT
 GCGGACGGCGTGCCTGGTTTAACAGGTGTGCAGGGTCGCGACGGTCCTAA
 AGGTGAATCAGCAAGCAGCGGTGCAGTTTATGTTTCGTTGGGGTCGTACCA
 CCTGTCCTAGCGGAGCAGATGTTGTTTATAGCGGTTCGCGCAGCCGGTGCA
 AAATATGATCATTCAGGTGGCACCTCAGATCATCATTGTCTGCCGAATAAT
 20 CCGCAGTATCTGAGCGAAGATGATACCAATGCACTGGGTGCACAGCTGTA
 TGGTGTGGAATATGAAATTCGTGATCGTAGCAGCCCGTATAATAGCCTGG
 ATCAGAGCGATATGCCGTGTGTTGTTTGTAAATGCAAATGGTTCGTAGCCAG
 CTGCTGATGGTTCCGGCACGTTATACATGCCCCGACCGGTTGGAGCCGTGA
 ATATTATGGTTATATGATGAGCGAAGGCCAAAATCGCGAAGGTC
 25 GTAAAACCACCATTTGTATGGATTTTAGCGCAGAAGCAGTTCCTGGTAGC
 GGTGCAAATACCAATCCGAGTCCGGGTATTATGATGCGTGCAAATTGTAA
 TGGTCTGGCATGTCCGCCTTATCAGAGCAATACACCGCTGACCTGTGCCGT
 TTGTACCAAAGGTGACTACAAAGACGACGACGACAAAtaa (SEQ ID NO:
 109)

- 30 **[0333]** The polynucleotide of SEQ ID NO: 109 was subcloned into vector pET28a,
 expressed host *E. coli* cells and the truncated *Chondrosia reniformis* non-fibrillar
 collagen 2 was purified as described herein. The purified fibrillary collagen produced
 a clear band on SDS-PAGE and an anti-FLAG western was observed at around 60

kilodaltons. There were no existing bands that appear at that location on the gel in the absence of expression of this protein.

Example 13: Truncated *Rhincodon typus* (whale shark) Collagen

Truncated *Rhincodon typus* (whale shark) Collagen Type 1 alpha 1 truncation 1

5 with DsbA secretion and FLAG tag

[0334] The amino acid sequence of truncated *Rhincodon typus* collagen type1 truncation 1 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 110. The DsbA secretion tag is encoded by nucleotides 1-57 of SEQ ID NO: 111 and the amino acid sequences are amino acids 1-19 of SEQ ID NO: 110. The collagen

10 nucleotide sequences are nucleotides 58-630 of SEQ ID NO: 111 and the amino acid sequences are amino acids 20-210 of SEQ ID NO: 110. The FLAG nucleotide sequences are nucleotides 631-657 of SEQ ID NO: 111 and the amino acid sequences are amino acids 211-219 of SEQ ID NO: 110.

MKKIWLALAGLVLAFFSASAGPAGAKGPSGDIGRPGESGSPGARGHSGQPGR
 15 GIAGNQGLPGTAGEEGRTPPPGAGLRGQAGMMGFPGPKGAAGLPGKPGDR
 GNVGLAGPRGAPGKDGEVGAQGGPVAGPTGPRGETGLAGSVGFQGMPPGS
 GAAGEPGKPGNQGLRGDAGSPGMIGPRGERGLPGERGASGAQGLLGPRTS
 GAPGLGDYKDDDDK (SEQ ID NO: 110)

[0335] The nucleic acid sequence of truncated *Rhincodon typus* collagen type1 truncation 1 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 111.

20 ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTAGTTTTAGCGTTTAGCGCA
 TCGGCGGGTCCGGCAGGCGCAAAAGGTCCGAGCGGTGATATTGGTCGTCC
 GGGTGAAAGCGGTAGTCCGGGTGCACGTGGTCATAGCGGTACGCCTGGTC
 GTACCGGTATTGCAGGTAATCAGGGTCTGCCTGGTACAGCCGGTGAAGAA
 25 GGTCGCACCGGTCCGCCAGGTCCTGCAGGTCTGCGTGGTCAGGCAGGTAT
 GATGGGTTTTCCGGGTCCGAAAGGTGCAGCGGGTCTGCCAGGCAAACCGG
 GTGATCGTGGTAATGTTGGTCTGGCTGGTCCGCGTGGTGCACCGGGTAAA
 GATGGTGAAGTTGGTGCACAGGGTCTCCGGGTGTTGCAGGTCCGACCGG
 TCCTCGTGGTGAAACCGGTCTGGCAGGTAGCGTTGGTTTTTCAGGGTATGCC
 30 AGGTCCGTCAGGTGCAGCAGGCGAACCTGGTAAACCGGGTAACAGGGC
 CTGCGTGGTGATGCCGGTTCACCGGGTATGATTGGTCCACGCGGTGAACG
 TGGCCTGCCTGGCGAACGTGGTGCAGCGGTGCACAAGGTCTGCTGGGTC
 CACGTGGCACCTCAGGCGCACCAGGTCTGGGTGACTACAAAGACGACGAC
 GACAAAtaa (SEQ ID NO: 111)

[0336] The polynucleotide of SEQ ID NO: 111 was subcloned into vector pET28a, expressed host *E. coli* cells and the truncated *Rhincodon typus* collagen type 1 truncation 1 was purified as described herein. The purified collagen produced a clear band on SDS-PAGE and an anti-FLAG western was observed at around 25
 5 kilodaltons. There were no existing bands that appear at that location on the gel in the absence of expression of this protein.

Truncated *Rhincodon typus* (whale shark) Collagen Type 6 alpha 1 truncation 2 with DsbA secretion and FLAG tag

[0337] The amino acid sequence of truncated *Rhincodon typus* collagen type 6
 10 truncation 2 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 112. The DsbA secretion tag is encoded by nucleotides 1-57 of SEQ ID NO: 113 and the amino acid sequences are amino acids 1-19 of SEQ ID NO: 112. The collagen nucleotide sequences are nucleotides 58-684 of SEQ ID NO: 113 and the amino acid sequences are amino acids 20-228 of SEQ ID NO: 112. The FLAG nucleotide
 15 sequences are nucleotides 685-711 of SEQ ID NO: 113 and the amino acid sequences are amino acids 229-237 of SEQ ID NO: 112.

MKKIWLALAGLVLAFAASAQGIPGSAGKEGGKGDGPGLGSPGKPGPDGLRGF
 AGARGLPGAAGPPGLKGAEGPMGAPGLTGSTGERGPNGPAGAIGLPGRPGGP
 GPPGPVGEKGDPGDKGLPGPAGDDGVQGAMGLPGPIGSQGPPGDYGDKGEL
 20 GKPGQKGSKGDKGESGPPGPIGIQGPIGHPGPIGSDGSPGLRGYLGMRGQKGD
 DGIRGLPGSAGPVGLQGLPGGDYKDDDDK (SEQ ID NO: 112)

[0338] The nucleic acid sequence of truncated *Rhincodon typus* collagen type 6
 truncation 2 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 113.
 ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
 25 TCGGCGCAGGGTATTCCGGGTAGCGCAGGTAAAGAAGGTGGTAAAGGCG
 ATCCGGGTCCGCTGGGTTCACCGGGTAAACCGGGTCCTGATGGTCTGCGT
 GGTTTTGCCGGTGACGTGGTCTGCCTGGTGCAGCAGGTCCGCCTGGTCTG
 AAAGGTGCCGAAGGTCCGATGGGTGCTCCGGGTCTGACCGGTAGCACCGG
 TGAACGCGGTCCGAATGGTCCGGCAGGCGCAATTGGTCTGCCAGGTCTGTC
 30 CTGGTGGTCCGGTCTCCTGGTCCGGTTGGTGAAAAAGGTGATCCTGGT
 GATAAAGGCCTGCCTGGTCTGCGGTGATGATGGTGTTCAGGGTGCCAT
 GGGCTTACCGGTCCGATTGGTAGCCAGGGTCCTCCGGGTGATTATGGCG
 ATAAAGGTGAACTGGGTAAACCTGGCCAGAAAGGTAGCAAAGGTGACAA
 AGGCGAAAGCGGTCCGCCAGGTCCGATCGGCATTCAGGGTCCTATTGGTC

ATCCAGGTCCAATTGGTTCAGATGGCTCACCGGGACTGCGTGGCTATCTG
GGTATGCGTGGACAGAAAGGTGATGACGGTATTCGTGGCCTGCCAGGTAG
TGCAGGTCCGGTGGGTCTGCAGGGACTGCCTGGTGGTGAATAAAGACG
ACGACGACAAAtaa (SEQ ID NO: 113)

- 5 [0339] The polynucleotide of SEQ ID NO: 113 was subcloned into vector pET28a, expressed host *E. coli* cells and the truncated *Rhincodon typus* collagen type 6 truncation 2 was purified as described herein. The purified collagen produced a clear band on SDS-PAGE and an anti-FLAG western was observed at around 35 kilodaltons. There were no existing bands that appear at that location on the gel in the absence of expression of this protein.

Truncated *Rhincodon typus* (whale shark) Collagen Type 6 alpha 1 truncation 3 with DsbA secretion and FLAG tag

- [0340] The amino acid sequence of truncated *Rhincodon typus* collagen type 6 alpha 1 truncation 3 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 114. The DsbA secretion tag is encoded by nucleotides 1-57 of SEQ ID NO: 115 and the amino acid sequences are amino acids 1-19 of SEQ ID NO: 114. The collagen nucleotide sequences are nucleotides 58-735 of SEQ ID NO: 115 and the amino acid sequences are amino acids 20-245 of SEQ ID NO: 114. The FLAG nucleotide sequences are nucleotides 736-762 of SEQ ID NO: 115 and the amino acid sequences are amino acids 246-254 of SEQ ID NO: 114.

MKKIWLALAGLVLAFAASAKGETGEAGDPGTPGEPGIAGPKGDVGDKG DAG
PPGAAGPAGVKGPPGEDGAKGDVGPAGFPDGPPTGEPGVPGMDGGVGEKG
SLGDPGLTGPRGASGEPGPPGSPGKRGP GPAGPEGREGLKGSKGSPGQEGPV
GRTGPIGPQGSPGNVGP KGLRGIPGPTGEQGLLGPPGQAGPPGPMGPPGM PGL
25 RGAQGLKGDKGHVGLIGLIGPPGEMGEKGDQGLPGIQGDYKDDDDK (SEQ
ID NO: 114)

- [0341] The nucleic acid sequence of truncated *Rhincodon typus* collagen type 6 alpha 1 truncation 3 with DsbA secretion and FLAG tag is disclosed in SEQ ID NO: 115.
- 30 ATGAAAAAGATTTGGCTGGCGCTGGCTGGTTTAGTTTTAGCGTTTAGCGCA
TCGGCGAAAGGTGAAACCGGTGAAGCGGGTGATCCGGGTACACCGGGTG
AACCTGGTATTGCAGGTCCGAAAGGTGATGTTGGTGATAAAGGTGACGCA
GGTCCGCCTGGTGCAGCAGGTCCGGCAGGCGTTAAAGGTCCTCCGGGTGA
AGATGGTGCAAAAGGCGACGTTGGTCCTGCAGGTTTTCTGGCGATCCGG

GTCCGACTGGTGAACCGGGTGTGCCAGGTATGGATGGTGGTGTGGGTGAA
AAAGGTAGCCTGGGTGATCCTGGTCTGACCGGTCCGCGTGGCGCAAGTGG
TGAACCAGGTCCACCGGGTAGTCCGGGTAAACGTGGTCCTCCTGGACCGG
CTGGTCCGGAAGGTCTGTAAGGTCTGAAAGGTAGCAAAGGTTACACGGGT
5 CAAGAAGGTCCGGTTGGTCTGTAACCGGTCCGATTGGTCCGCAGGGCTCACC
GGGTAATGTTGGTCCTAAAGGTCTGCGTGGTATTCCGGGTCTACAGGCG
AACAGGGTCTGCTGGGTCCGCCAGGCCAAGCAGGTCTCCAGGTCTATG
GGTCCACCTGGTATGCCTGGCCTGCGTGGTGCCAGGGCCTGAAAGGCGA
TAAAGGCCATGTTGGTCTGATTGGCCTGATTGGTCCACCAGGTGAAATGG
10 GAGAAAAAGGCGATCAGGGCCTGCCTGGTATTCAGGGTGACTACAAAGA
CGACGACGACAAAtaa (SEQ ID NO: 115)

[0342] The polynucleotide of SEQ ID NO: 115 was subcloned into vector pET28a, expressed host *E. coli* cells and the truncated *Rhincodon typus* collagen type1 truncation 1 was purified as described herein. The purified collagen produced a clear
15 band on SDS-PAGE and an anti-FLAG western was observed at around 25 kilodaltons. There were no existing bands that appear at that location on the gel in the absence of expression of this protein.

What is claimed is:

1. A non-naturally occurring collagen selected from the group consisting of jellyfish collagen, human, *Chondrosia reniformis* (kidney sponge), and *Rhincodon typus* (whale shark).
2. The non-naturally occurring collagen of claim 1, wherein the non-naturally occurring collagen is truncated.
3. The non-naturally occurring truncated collagen of claim 2, wherein the collagen is truncated by an internal truncation of between 50 amino acids and 300 amino acids.
4. The non-naturally occurring collagen of any of claims 1 to 3, wherein the amino acid sequence of the collagen is selected from the group consisting of SEQ ID NO: 10, SEQ ID NO: 12, SEQ ID NO: 14, SEQ ID NO: 16, SEQ ID NO: 18, SEQ ID NO: 20, SEQ ID NO: 74, SEQ ID NO: 76, SEQ ID NO: 78, SEQ ID NO: 80, SEQ ID NO: 82, SEQ ID NO: 84, SEQ ID NO: 86, SEQ ID NO: 89, SEQ ID NO: 91, SEQ ID NO: 92, SEQ ID NO: 94, SEQ ID NO: 96, SEQ ID NO: 102, SEQ ID NO: 104, SEQ ID NO: 106, SEQ ID NO: 108, SEQ ID NO: 110, and SEQ ID NO: 112.
5. The non-naturally occurring collagen of any of claims 1 to 4, wherein the collagen further comprises amino acid sequences selected from the group consisting of a secretion tag, histidine tag, green fluorescent protein, protease cleavage site, and a Beta-lactamase protein.
6. The non-naturally occurring collagen of claim 5, wherein the secretion tag is DsbA.
7. The non-naturally occurring collagen of any of claims 1 to 6, wherein the collagen further comprises one or more amino acid trimer repeats of the sequence glycine-glutamic acid-lysine (GEK) and/or glycine-aspartic acid-lysine (GDK).
8. The non-naturally occurring collagen of claim 7, wherein the non-naturally occurring collagen comprises between 2 and 50 amino acid trimer repeats.
9. The non-naturally occurring collagen of any of claims 1 to 8, wherein the non-naturally occurring collagen is a jellyfish collagen.
10. A composition comprising between 0.005% and 30% w/w the non-naturally occurring collagen of any of claims 1 to 9, wherein said composition

stimulates the growth of fibroblast cells, and/or stimulates synthesis of procollagen, and/or decreases the formation of thymine-thymine (TT) dimer formation.

11. The composition of claim 10, wherein the composition comprises between 0.005% and 1% non-naturally occurring collagen.

5 12. The composition of claim 10, wherein the composition comprises between 0.01% and 1% non-naturally occurring collagen.

13. The composition of claim 10, wherein the composition comprises between 0.02% and 0.5% non-naturally occurring collagen.

14. The composition of any of claims 10 to 13, wherein the composition is
10 a topical composition, said topical composition further comprising at least one additional ingredient comprising a topical carrier and/or a preservative.

15. The composition of claim 14, wherein the topical composition is a mask.

16. The topical composition of claims 14 or 15, wherein the topical carrier
15 is selected from the group consisting of liposome, biodegradable microcapsule, lotion, spray, aerosol, dusting powder, biodegradable polymer, mineral oil, triglyceride oil, silicone oil, glycerin, glycerin monostearate, alcohols, emulsifying agents, liquid petroleum, white petrolatum, propylene glycol, polyoxyethylene, polyoxypropylene, wax, sorbitan monostearate, polysorbate, cetyl ester wax, cetearyl alcohol, 2-
20 octyldodecanol, benzyl alcohol, cyclomethicone, cyclopentasiloxane, and water.

17. The topical composition of any of claims 14 to 16, wherein the preservative is selected from the group consisting of tocopherol, diiodomethyl-p-tolylsulfone, 2-Bromo-2-nitropropane-1,3-diol, cis isomer 1-(3-chloroallyl)-3,5,7-triaza-1-azoniaadamantane chloride, glutaraldehyde, 4,4-dimethyl oxazolidine, 7-
25 Ethylbicyclooxazolidine, methyl paraben, sorbic acid, Germaben II, rosemary extract, and EDTA.

18. A method of decreasing skin damage, promoting the repair of damaged skin, protecting the skin against UV damage, or increasing viability of skin cells, the method comprising the step of applying the composition of any of claims 1 to 17 to
30 the skin or skin cell of a subject.

19. The method of claim 18, wherein the viability of fibroblast cells present in the subject's skin is increased.

20. The method of claim 18, wherein the synthesis of procollagen by fibroblast cells present in the subject's skin is increased.

21. A non-naturally occurring elastin selected from the group consisting of a jellyfish elastin, human elastin, *Chondrosia reniformis* (kidney sponge) elastin, or *Rhincodon typus* elastin.
22. The non-naturally occurring elastin of claim 21, wherein the non-naturally occurring elastin is truncated.
23. The non-naturally occurring truncated elastin of claim 22, wherein the elastin is truncated by a truncation of at least 50 amino acids.
24. The non-naturally occurring elastin of any of claims 21 to 23, wherein the amino acid sequence of the elastin is selected from the group consisting of SEQ ID NO: 31, SEQ ID NO: 33, SEQ ID NO: 35, SEQ ID NO: 37, SEQ ID NO: 39, SEQ ID NO: 41, SEQ ID NO: 43, SEQ ID NO: 45, SEQ ID NO: 47, SEQ ID NO: 49, SEQ ID NO: 51, SEQ ID NO: 53, SEQ ID NO: 55, SEQ ID NO: 57, SEQ ID NO: 59, SEQ ID NO: 61, SEQ ID NO: 63, SEQ ID NO: 65, SEQ ID NO: 67, SEQ ID NO: 69, SEQ ID NO: 71, SEQ ID NO: 98, and SEQ ID NO: 100.
25. The non-naturally occurring elastin of any of claims 21 to 24, wherein the elastin further comprises amino acid sequences selected from the group consisting of a secretion tag, histidine tag, green fluorescent protein, protease cleavage site, and a Beta-lactamase protein.
26. The non-naturally occurring elastin of claim 25, wherein the secretion tag is DsbA.
27. The non-naturally occurring elastin of any of claims 21 to 26, wherein the elastin further comprises one or more amino acid trimer repeats of the sequence glycine-glutamic acid-lysine (GEK) and/or glycine-aspartic acid-lysine (GDK)
28. The non-naturally occurring elastin of claim 27, wherein the non-naturally occurring elastin comprises between 2 and 50 amino acid trimer repeats.
29. The non-naturally occurring elastin of any of claims 21 to 28, wherein the non-naturally occurring elastin is a human.
30. A composition comprising between 0.005% and 30%w/w the non-naturally occurring elastin of any of claims 21 to 29, wherein said composition stimulates the growth of fibroblast cells, and/or stimulates synthesis of procollagen.
31. The composition of claim 30, wherein the composition comprises between 0.005% and 1% non-naturally occurring elastin.
32. The composition of claim 30, wherein the composition comprises between 0.01% and 1% non-naturally occurring elastin.

33. The composition of claim 30, wherein the composition comprises between 0.02% and 0.5% non-naturally occurring Elastin.

34. The composition of any of claims 30 to 33, wherein the composition is a topical composition, said topical composition further comprising at least one
5 additional ingredient comprising a topical carrier and/or a preservative.

35. The composition of claim 34, wherein the topical composition is a mask.

36. The topical composition of claim 34 or 35, wherein the topical carrier is selected from the group consisting of liposome, biodegradable microcapsule, lotion,
10 spray, aerosol, dusting powder, biodegradable polymer, mineral oil, triglyceride oil, silicone oil, glycerin, glycerin monostearate, alcohols, emulsifying agents, liquid petroleum, white petrolatum, propylene glycol, polyoxyethylene, polyoxypropylene, wax, sorbitan monostearate, polysorbate, cetyl ester wax, cetearyl alcohol, 2-octyldodecanol, benzyl alcohol, cyclomethicone, cyclopentasiloxane, and water.

37. The topical composition of any of claims 34 to 36, wherein the preservative is selected from the group consisting of tocopherol, diiodomethyl-p-tolylsulfone, 2-Bromo-2-nitropropane-1,3-diol, glutaraldehyde, 4,4-dimethyl
15 oxazolidine, 7-Ethylbicyclooxazolidine, methyl paraben, sorbic acid, Germaben II, rosemary extract, and EDTA.

38. A method of decreasing skin damage, promoting the repair of damaged
20 skin, or protecting skin against UV damage, the method comprising the step of applying the composition of any of claims 21 to 37 to the skin of a subject.

39. The method of claim 38, wherein the viability of fibroblast cells or keratinocytes present in the subject's skin is increased.

40. The method of claim 38, wherein the synthesis of procollagen by
25 fibroblast cells present in the subject's skin is increased.

41. A polynucleotide encoding a non-naturally occurring collagen, wherein the polynucleotide is selected from the group consisting of SEQ ID NO: 9, SEQ ID
30 NO: 11, SEQ ID NO: 13, SEQ ID NO: 15, SEQ ID NO: 17, SEQ ID NO: 19, SEQ ID NO: 73, SEQ ID NO: 75, SEQ ID NO: 77, SEQ ID NO: 79, SEQ ID NO: 81, SEQ ID NO: 83, SEQ ID NO: 85, SEQ ID NO: 90, SEQ ID NO: 93, SEQ ID NO: 95, SEQ ID NO: 97, SEQ ID NO: 103, SEQ ID NO: 105, SEQ ID NO: 107, SEQ ID NO: 109, SEQ ID NO: 111, SEQ ID NO: 113, and SEQ ID NO: 105.

42. The polynucleotide of claim 41, wherein the polynucleotide is a vector.

43. The polynucleotide of claim 41 or 42, wherein the polynucleotide further comprises nucleic acids selected from the group consisting of nucleic acids that encode a secretion tag, histidine tag, green fluorescent protein, protease cleavage site, and a Beta-lactamase protein.
- 5 44. The polynucleotide of any of claims 41 to 43, wherein the polynucleotide further comprises polynucleotides that encode one or more amino acid trimer repeats of the sequence glycine-glutamic acid-lysine (GEK) and/or glycine-aspartic acid-lysine (GDK).
45. A host cell comprising the polynucleotide of any of claims 41 or 45.
- 10 46. The host cell of claim 48, wherein the host cell traffics the non-naturally occurring collagen to the periplasmic space of the host cell.
47. The host cell of claim 45 or 46, wherein the host cell produces jellyfish collagen.
48. The host cell of any of claims 45 to 47, wherein the host cell is gram
15 negative bacteria.
49. The method of claim 48, wherein the host cell is *E. coli*.
50. The method of claim 49, wherein the *E. coli* is a switched *E. coli*.
51. A method of producing a non-naturally occurring collagen, the method comprising the steps of:
- 20 a. cultivating the host cell of any of claims 45 to 50 in a culture medium; and
- b. isolating the non-naturally occurring collagen from the host cell.
52. A polynucleotide encoding a non-naturally occurring elastin, wherein
25 the polynucleotide is selected from the group consisting of SEQ ID NO: 34, SEQ ID NO: 36, SEQ ID NO: 38, SEQ ID NO: 40, SEQ ID NO: 42, SEQ ID NO: 44, SEQ ID NO: 46, SEQ ID NO: 48, SEQ ID NO: 50, SEQ ID NO: 52, SEQ ID NO: 54, SEQ ID NO: 56, SEQ ID NO: 58, SEQ ID NO: 60, SEQ ID NO: 62, SEQ ID NO: 64, SEQ ID NO: 66, SEQ ID NO: 68, SEQ ID NO: 70, SEQ ID NO: 72, SEQ ID NO: 99, and
30 SEQ ID NO:101.
53. The polynucleotide of claim 52, wherein the polynucleotide is a vector.
54. The polynucleotide of claim 52 or 53, wherein the polynucleotide further comprises nucleic acids selected from the group consisting of nucleic acids

that encode a secretion tag, histidine tag, green fluorescent protein, protease cleavage site, and a Beta-lactamase protein.

55. The polynucleotide of any of claims 52 to 54, wherein the polynucleotide further comprises polynucleotides that encode one or more amino acid trimer repeats of the sequence glycine-glutamic acid-lysine (GEK) and/or glycine-aspartic acid-lysine (GDK).

56. A host cell comprising the polynucleotide of any of claims 52 to 55.

57. The host cell of claim 56, wherein the host cell traffics the non-naturally occurring collagen to the periplasmic space of the host cell.

58. The host cell of claim 56 or 57, wherein the host cell produces jellyfish collagen.

59. The host cell of any of claims 56 to 58, wherein the host cell is gram negative bacteria.

60. The method of claim 59, wherein the host cell is *E. coli*.

61. The method of claim 60, wherein the *E. coli* is a switched *E. coli*.

62. A method of producing a non-naturally occurring elastin, the method comprising the steps of:

- a. cultivating the host cell of any of claims 56 to 61 in a culture medium; and
- b. isolating the non-naturally occurring collagen from the host cell.

63. A method of decreasing the production of inflammatory cytokines by a skin cell, the method comprising the step of applying the composition of any of claims 1 to 17 to the skin cell.

64. The method of claim 63, wherein the inflammatory cytokine is IL-1a.

65. The method of claim 63, wherein the skin cell is a keratinocyte.

66. A method of increasing viability of skin cells, the method comprising the step of applying the composition of any of claims 1 to 17 to the skin or skin cell of a subject.

67. The method of claim 66, wherein the viability of keratinocytes present in the subject's skin is increased.

68. The method of claim 66, wherein the viability of fibroblasts present in the subject's skin is increased.

69. A method of protecting skin cells against the effects of exposure to urban dust, the method comprising the step of applying the composition of any of claims 1 to 17 to skin cells, wherein the viability of the skin cells is increased.

70. The method of claim 69, wherein the skin cell is a keratinocyte or a
5 fibroblast.