

Preparation of colored melamine-formaldehyde condensation products

5 The present invention relates to an improved process for preparing colored melamine-formaldehyde condensation products by mixing pigments or dyes into a reaction mixture comprising starting compounds for preparing the melamine-formaldehyde condensation products.

10

The present invention further relates to colored melamine-formaldehyde condensation products and to their use for producing colored articles, in particular fibers and webs.

15 EP-A 523485 describes melamine-formaldehyde condensation products produced with or without inclusion in the reaction mixture of additives such as pigments or dyes. The disadvantage of this unspecific procedure is that inhomogeneously colored condensation products are obtained for some applications, in particular in
20 fiber and web manufacture. Furthermore, from experience to date, the spinning solutions frequently contain bits which can cause blockage of the pipework and orifices.

It is an object of the present invention to provide an improved
25 process for preparing colored melamine-formaldehyde condensation products that is free of the abovementioned disadvantages.


We have found that this object is achieved by a process for preparing colored melamine-formaldehyde condensation products by
30 mixing pigments or dyes into a reaction mixture comprising starting compounds for preparing the melamine-formaldehyde condensation products, which comprises

(A) dispersing a mixture consisting essentially of

35

(a) a substituted melamine of the formula I

40



I,

45

where X^1 , X^2 and X^3 are each selected from the group consisting of $-\text{NH}_2$, $-\text{NHR}^1$ and $-\text{NR}^1\text{R}^2$, and X^1 , X^2 and X^3 are not all $-\text{NH}_2$, and R^1 and R^2 are each selected from the group consisting of hydroxy- C_2 - C_{10} -alkyl,

hydroxy-C₂-C₄-alkyl-(oxa-C₂-C₄-alkyl)_n, where n is from 1 to 5, and amino-C₂-C₁₂-alkyl, or mixtures of melamines I, and

5 (b) if desired, formaldehyde or formaldehyde-supplying compounds in a molar ratio of formaldehyde to melamines I within the range from 40:1 to 0,

(c) a pigment or dye, and

10

(d) if desired, phenol, unsubstituted or substituted by radicals selected from the group consisting of C₁-C₉-alkyl and hydroxyl, C₁-C₄-alkanes substituted by 2 or 3 phenol groups, di(hydroxyphenyl) sulfones or mixtures thereof,

15

the pigment or dye being added in an amount within the range from 0.01 to 30% by weight, based on (a) and (b), and the phenol in an amount within the range from 0 to 5 mol%, based on (a) and (b),

20

by intensive stirring until there are no longer any pigment agglomerates $\geq 1 \mu\text{m}$,

25 and then


(B) admixing the mixture prepared in (A) with melamine and if desired with further phenol, substituted melamine I and formaldehyde or formaldehyde-supplying compounds, the amounts being chosen so that the molar ratio of melamines (melamine and (a)) to (b) is within the range from 1:1.15 to 1:4.5, the pigment or dye is present in an amount within the range from 0.01 to 5% by weight, based on melamine and (a) and (b), and the phenol is present in an amount within the range from 0 to 5 mol%, based on melamine and (a) and (b), and then condensing in a conventional manner.

We have also found colored melamine-formaldehyde condensation products and their use for producing colored articles, in particular fibers and webs.

40

First step (A) of the process for the present invention comprises dispersing a mixture consisting essentially of

45 (a) a substituted melamine of the formula I



I,

5

where X^1 , X^2 and X^3 are each selected from the group consisting of $-NH_2$, $-NHR^1$ and $-NR^1R^2$, and X^1 , X^2 and X^3 are not all $-NH_2$, and R^1 and R^2 are each selected from the group consisting of hydroxy- C_2 - C_{10} -alkyl, hydroxy- C_2 - C_4 -alkyl-(oxa- C_2 - C_4 -alkyl) $_n$, where n is from 1 to 5, and amino- C_2 - C_{12} -alkyl, or mixtures of melamines I, and

10

(b) if desired, formaldehyde or formaldehyde-supplying compounds in a molar ratio of formaldehyde to melamines I within the range from 40:1 to 0, preferably from 25:1 to 0,

15

(c) a pigment or dye, and


(d) if desired, phenol, unsubstituted or substituted by radicals selected from the group consisting of C_1 - C_9 -alkyl and hydroxyl, C_1 - C_4 -alkanes substituted by 2 or 3 phenol groups, di(hydroxyphenyl) sulfones or mixtures thereof, the pigment or dye being added in an amount within the range from 0.01 to 30, preferably from 0.5 to 15, % by weight, based on (a) and (b), and the phenol in an amount within the range from 0 to 5, preferably from 0.2 to 2, mol%, based on (a) and (b), by intensive stirring until there are no longer any pigment agglomerates $\geq 1 \mu m$.

25

30

Suitable for use as substituted melamines of the general formula I

35



I,

are those in which X^1 , X^2 and X^3 are each selected from the group consisting of $-NH_2$, $-NHR^1$ and $-NR^1R^2$, but X^1 , X^2 and X^3 are not all $-NH_2$, and R^1 and R^2 are each selected from the group consisting of hydroxy- C_2 - C_{10} -alkyl, hydroxy- C_2 - C_4 -alkyl-(oxa- C_2 - C_4 -alkyl) $_n$, where n is from 1 to 5, and amino- C_2 - C_{12} -alkyl.

45

Hydroxy- C_2 - C_{10} -alkyl is preferably hydroxy- C_2 - C_6 -alkyl such as 2-hydroxyethyl, 3-hydroxy-n-propyl, 2-hydroxyisopropyl,

4-hydroxy-n-butyl, 5-hydroxy-n-pentyl, 6-hydroxy-n-hexyl, 3-hydroxy-2,2-dimethylpropyl, preferably hydroxy-C₂-C₄-alkyl such as 2-hydroxyethyl, 3-hydroxy-n-propyl, 2-hydroxyisopropyl and 4-hydroxy-n-butyl, particularly preferably 2-hydroxyethyl and
 5 2-hydroxyisopropyl.

Hydroxy-C₂-C₄-alkyl-(oxa-C₂-C₄-alkyl)_n preferably has n from 1 to 4, particularly preferably n 1 or 2 such as 5-hydroxy-3-oxapentyl, 5-hydroxy-3-oxa-2,5-dimethylpentyl, 5-hydroxy-3-oxa-
 10 1,4-dimethylpentyl, 5-hydroxy-3-oxa-1,2,4,5-tetramethylpentyl, 8-hydroxy-3,6-dioxaoctyl.

Amino-C₂-C₁₂-alkyl is preferably amino-C₂-C₈-alkyl, such as 2-aminoethyl, 3-aminopropyl, 4-aminobutyl, 5-aminopentyl,
 15 6-aminohexyl, 7-aminoheptyl or 8-aminooctyl. particularly preferably 2-aminoethyl or 6-aminohexyl, very particularly preferably 6-aminohexyl.

Particularly suitable substituted melamines for the present
 20 invention include for example the following compounds:
 2-hydroxyethylamino-substituted melamines such as
 2-(2-hydroxyethylamino)-4,6-diamino-1,3,5-triazine, 2,4-di(2-hydroxyethylamino)-6-amino-1,3,5-triazine, 2,4,6-tris(2-hydroxyethylamino)-1,3,5-triazine, 2-hydroxyisopropylamino-substituted
 25 melamines such as 2-(2-hydroxyisopropylamino)-4,6-diamino-1,3,5-triazine, 2,4-di(2-hydroxyisopropylamino)-6-amino-1,3,5-triazine, 2,4,6-tris(2-hydroxyisopropylamino)-1,3,5-triazine,
 5-hydroxy-3-oxapentylamino-substituted melamines such as
 2-(5-hydroxy-3-oxapentylamino)-4,6-diamino-1,3,5-triazine,
 30 2,4-di(5-hydroxy-3-oxapentylamino)-6-amino-1,3,5-triazine, 2,4,6-tris(5-hydroxy-3-oxapentylamino)-1,3,5-triazine,
 6-aminohexylamino-substituted melamines such as
 2-(6-aminohexylamino)-4,6-diamino-1,3,5-triazine,
 2,4-di(6-aminohexylamino)-6-amino-1,3,5-triazine,
 35 2,4,6-tris(6-aminohexylamino)-1,3,5-triazine or mixtures thereof,
 for example a mixture of 10 mol% of 2-(5-hydroxy-3-oxapentylamino)-4,6-diamino-1,3,5-triazine, 50 mol% of
 2,4-di(5-hydroxy-3-oxypentylamino)-6-amino-1,3,5-triazine and
 40 40 mol% of 2,4,6-tris(5-hydroxy-3-oxapentylamino)-1,3,5-triazine.

40 Formaldehyde is generally used in the form of an aqueous solution having a concentration from for example 40 to 50% by weight or in the form of compounds which donate formaldehyde, for example in the form of oligomeric or polymeric formaldehyde in solid form,
 45 such as paraformaldehyde, 1,3,5-trioxane or 1,3,5,7-tetroxocane.

5

Suitable phenols include phenols containing one or two hydroxyl groups such as phenol, unsubstituted or substituted by radicals selected from the group consisting of C₁-C₉-alkyl and hydroxyl and also C₁-C₄-alkanes substituted by 2 or 3 phenol groups,
5 di(hydroxyphenyl) sulfones or mixtures thereof.

Preferred phenols include for example phenol, 4-methylphenol, 4-tert-butylphenol, 4-n-octylphenol, 4-n-nonylphenol, pyrocatechol, resorcinol, hydroquinone, 2,2-bis(4-hydroxyphenyl)-
10 propane or 4,4'-dihydroxydiphenyl sulfone, particularly preferably phenol, resorcinol and 2,2-bis(4-hydroxyphenyl)-propane.

The dyes employed in the process of the present invention come
15 from the class of the azo, anthraquinone, coumarin, methine or azamethine, quinophthalone or nitro dyes. They either are free of ionic groups or carry carboxyl and/or sulfo groups.

Suitable dyes which are free of ionic groups will now be more
20 particularly described.

Suitable azo dyes include in particular monoazo or disazo dyes, for example those with a diazo component derived from an aniline or from a five-membered aromatic heterocyclic amine which has
25 from one to three hetero atoms selected from the group consisting of nitrogen, oxygen and sulfur in the heterocyclic ring and may be fused with a benzene, thiophene, pyridine or pyrimidine ring.

Important monoazo or disazo dyes include for example those whose
30 diazo component is derived for example from an aniline or from a heterocyclic amine of the pyrrole, furan, thiophene, pyrazole, imidazole, oxazole, isoxazole, thiazole, isothiazole, triazole, oxadiazole, thiadiazole, benzofuran, benzothiophene, benzimidazole, benzoxazole, benzothiazole, benzisothiazole,
35 pyridothiophene, pyrimidothiophene, thienothiophene or thienothiazole series.

Of particular suitability are those diazo components which come from an aniline or from a heterocyclic amine of the pyrrole,
40 thiophene, pyrazole, thiazole, isothiazole, triazole, thiadiazole, benzothiophene, benzothiazole, benzisothiazole, pyridothiophene, pyrimidothiophene, thienothiophene or thienothiazole series.


Also of importance are azo dyes with a coupling component of the aniline, aminonaphthalene, aminothiazole, diaminopyridine or hydroxypyridone series.

5 Of particular importance are azo dyes of the formula IIIa




10 where

D^1 is a radical of the formula



K is hydroxyphenyl or a radical of the formula



20 where

- L¹ is nitro, cyano, C₁-C₆-alkanoyl, benzoyl, C₁-C₆-alkylsulfonyl, substituted or unsubstituted phenylsulfonyl or a radical of the formula -CH=T, where T is hydroxyimino, C₁-C₄-alkoxyimino or a radical of an acidic-CH compound,
- 25
- L² is hydrogen, C₁-C₆-alkyl, halogen, hydroxyl, mercapto, unsubstituted or phenyl- or C₁-C₄-alkoxy-substituted C₁-C₆-alkoxy, substituted or unsubstituted phenoxy, unsubstituted or phenyl-substituted C₁-C₆-alkylthio, substituted or unsubstituted phenylthio, C₁-C₆-alkylsulfonyl or substituted or unsubstituted phenylsulfonyl,
- 30
- L³ is cyano, C₁-C₄-alkoxycarbonyl or nitro,
- 35
- L⁴ is hydrogen, C₁-C₆-alkyl or phenyl,
- L⁵ is C₁-C₆-alkyl or phenyl,
- 40
- L⁶ is hydrogen, cyano, C₁-C₄-alkoxycarbonyl, C₁-C₆-alkanoyl, thiocyanato or halogen,
- L⁷ is nitro, cyano, C₁-C₆-alkanoyl, benzoyl, C₁-C₄-alkoxy-carbonyl, C₁-C₆-alkylsulfonyl, substituted or unsubstituted phenylsulfonyl or a radical of the formula -CH=T, where T is as defined above,
- 45

- 5 L⁸ is hydrogen, C₁-C₆-alkyl, cyano, halogen, unsubstituted or phenyl- or C₁-C₄-alkoxy-substituted C₁-C₆-alkoxy, unsubstituted or phenyl-substituted C₁-C₆-alkylthio, substituted or unsubstituted phenylthio, C₁-C₆-alkylsulfonyl, substituted or unsubstituted phenylsulfonyl or C₁-C₄-alkoxycarbonyl,
- 10 L⁹ is cyano, unsubstituted or phenyl-substituted C₁-C₆-alkyl, unsubstituted or phenyl-substituted C₁-C₆-alkylthio, substituted or unsubstituted phenyl, thienyl, C₁-C₄-alkylthienyl, pyridyl or C₁-C₄-alkylpyridyl,
- L¹⁰ is phenyl or pyridyl,
- 15 L¹¹ is trifluoromethyl, nitro, C₁-C₆-alkyl, phenyl, unsubstituted or phenyl-substituted C₁-C₆-alkylthio or C₁-C₆-dialkylamino,
- L¹² is C₁-C₆-alkyl, phenyl, 2-cyanoethylthio or 2-(C₁-C₄-alkoxycarbonyl)ethylthio,
- 20 L¹³ is hydrogen, nitro or halogen,
- L¹⁴ is hydrogen, cyano, C₁-C₄-alkoxycarbonyl, nitro or halogen,
- 25 L¹⁵, L¹⁶ and L¹⁷ are identical or different and each is independently of the others hydrogen, C₁-C₆-alkyl, C₁-C₆-alkoxy, halogen, nitro, cyano, substituted or unsubstituted C₁-C₄-alkoxycarbonyl, C₁-C₆-alkylsulfonyl, substituted or unsubstituted phenylsulfonyl or substituted or unsubstituted phenylazo,
- 30 R¹ and R² are identical or different and each is independently of the other hydrogen, substituted or unsubstituted C₁-C₆-alkyl, with or without interruption by 1 or 2 oxygen atoms in ether function, C₅-C₇-cycloalkyl or C₃-C₆-alkenyl,
- 35 R³ is hydrogen, C₁-C₆-alkyl or C₁-C₆-alkoxy,
- 40 R⁴ is hydrogen, C₁-C₆-alkyl, C₁-C₆-alkoxy, C₁-C₆-alkylsulfonylamino, substituted or unsubstituted C₁-C₆-alkanoylamino or benzoylamino,
- R⁵ and R⁶ are identical or different and each is independently of the other hydrogen or C₁-C₆-alkyl,
- 45 R⁷ is hydrogen, substituted or unsubstituted phenyl or thienyl,

R⁸ is hydrogen or C₁-C₆-alkyl,





R⁹ is cyano, carbamoyl or acetyl,

- 5 R¹⁰, R¹¹ and R¹² are identical or different and each is independently of the others substituted or unsubstituted C₁-C₁₂-alkyl, with or without interruption by 1 to 3 oxygen atoms in ether function, C₅-C₇-cycloalkyl, substituted or unsubstituted phenyl, C₃-C₆-alkenyl, substituted or unsubstituted benzoyl, C₁-C₈-alkanoyl, C₁-C₆-alkylsulfonyl or substituted or unsubstituted phenylsulfonyl, or R¹¹ and R¹² together with the nitrogen atom joining them together are a 5- or 6-membered saturated heterocyclic radical with or without further hetero atoms, and

15

R¹³ is hydrogen or C₁-C₆-alkyl.

- Suitable anthraquinone dyes come for example from the class of the 1-aminoanthraquinones. They conform for example to the
20 formula Va, Vb, Vc or Vd



45


where

A¹ is hydrogen, C₁-C₈-alkyl or substituted or unsubstituted phenyl,

5 A² is hydroxyl or the radical NH-A¹,

A³ is hydrogen or nitro,

A⁴ is halogen, hydroxyphenyl, C₁-C₄-alkoxyphenyl or a radical of the formula



where G¹ is oxygen or sulfur and G² is hydrogen or C₁-C₈-mono-alkylsulfamoyl whose alkyl chain may be interrupted by 1 or 2 oxygen atoms in ether function,

15

one of the two radicals A⁵ and A⁶ is hydroxyl and the other is NH-A¹ or A⁵ and A⁶ are each hydrogen,


20 A⁷ is hydrogen or C₁-C₈-alkyl with or without interruption by from 1 to 3 oxygen atoms in ether function,

one of the two radicals A⁸ and A⁹ is hydroxyl and the other is aniline, and


25 G³ is oxygen or imino.

Suitable coumarin dyes come for example from the class of the 7-dialkylaminocoumarins. They conform for example to the formula VIa, VIb or VIc

30




35



40



45



where

- W¹ and W² are independently of each other C₁-C₄-alkyl,
 W³ is benzimidazol-2-yl, 5-chlorobenzoxazol-2-yl, benzothia-
 5 zol-2-yl, 4-hydroxyquinazolin-2-yl or 5-phenyl-1,3,4-thia-
 diazol-2-yl, and
 W⁴ is C₁-C₈-alkyl.

Suitable methine or azamethine dyes come for example from the
 10 class of the triazolopyridines or pyridines. They conform for
 example to the formula VIIa or VIIb




20 where

- X is nitrogen or CH,
 Q¹ is C₁-C₂₀-alkyl with or without substitution and with or
 25 without interruption by one or more oxygen atoms in ether
 function, substituted or unsubstituted phenyl or hydroxyl,
 Q² is a 5-membered aromatic heterocyclic radical,
 Q³ is hydrogen, cyano, carbamoyl, carboxyl or C₁-C₄-alkoxy-
 carbonyl,
 30 Q⁴ is oxygen or a radical of the formula C(CN)₂, C(CN)COOE¹ or
 C(COOE¹)₂, where E¹ is in each case C₁-C₈-alkyl with or
 without interruption by 1 or 2 oxygen atoms in ether
 function,
 Q⁵ is hydrogen or C₁-C₄-alkyl,
 35 Q⁶ is C₁-C₂₀-alkyl with or without substitution and with or
 without interruption by one or more oxygen atoms in ether
 function, substituted or unsubstituted phenyl, hydroxyl or a
 radical of the formula NE²E³, where E² and E³ are identical or
 40 different and each is independently of the other hydrogen,
 substituted or unsubstituted C₁-C₁₂-alkyl, C₅-C₇-cycloalkyl,
 substituted or unsubstituted phenyl, substituted or unsub-
 substituted pyridyl, substituted or unsubstituted
 C₁-C₁₂-alkanoyl, C₁-C₁₂-alkoxycarbonyl, substituted or
 unsubstituted C₁-C₁₂-alkylsulfonyl, C₅-C₇-cycloalkylsulfonyl,
 45 substituted or unsubstituted phenylsulfonyl, substituted or
 unsubstituted pyridylsulfonyl, substituted or unsubstituted
 benzoyl, pyridylcarbonyl or thienylcarbonyl, or E² and E³

together with the nitrogen atom joining them together are unsubstituted or C₁-C₄-alkyl-substituted succinimido, unsubstituted or C₁-C₄-alkyl-substituted phthalimido or a five- or six-membered saturated heterocyclic radical with or without further hetero atoms.


The dyes of the formula VIIa or VIIb can exist in a plurality of tautomeric forms which are all encompassed by the claims. For example, the compounds of the formula VIIa (where Q⁴ = oxygen and Q⁵ = methyl) can exist inter alia in the following tautomeric forms:




20

Q² can be derived for example from components of the pyrrole, thiazole, thiophene or indole series.

Important Q² radicals are for example those of the formulae VIIIa to VIIId



40




where

45

m is 0 or 1,


- E^4 and E^5 are identical or different and are each independently of the other hydrogen or else the abovementioned radical R^1 , except for hydroxyl, or together with the nitrogen atom joining them together are a 5- or 6-membered saturated heterocyclic radical with or without further hetero atoms,
- E^6 is hydrogen, halogen, C_1 - C_8 -alkyl, unsubstituted or C_1 - C_4 -alkyl- or C_1 - C_4 -alkoxy-substituted phenyl, unsubstituted or C_1 - C_4 -alkyl- or C_1 - C_4 -alkoxy-substituted benzyl, cyclohexyl, thienyl, hydroxyl or mono-(C_1 - C_8 -alkyl)amino,
- E^7 and E^8 are independently of each other hydrogen, hydroxyl, unsubstituted or phenyl- or C_1 - C_4 -alkylphenyl-substituted C_1 - C_8 -alkyl, unsubstituted or phenyl- or C_1 - C_4 -alkylphenyl-substituted C_1 - C_8 -alkoxy, C_1 - C_8 -alkanoylamino, C_1 - C_8 -alkyl-sulfonylamino or mono- or di(C_1 - C_8 -alkyl)aminosulfonylamino,
- E^9 is cyano, carbamoyl, mono- or di(C_1 - C_8 -alkyl)carbamoyl, C_1 - C_8 -alkoxycarbonyl or substituted or unsubstituted phenyl, and
- E^{10} is halogen, hydrogen, C_1 - C_4 -alkyl, C_1 - C_4 -alkoxy, C_1 - C_4 -alkylthio, unsubstituted or C_1 - C_4 -alkyl- or C_1 - C_4 -alkoxy-substituted phenyl or thienyl.

Particularly suitable quinophthalone dyes have a quinoline ring which is either unsubstituted or halogen-substituted in ring position 4. They conform for example to the formula IX



where G^4 is hydrogen, chlorine or bromine.

A suitable nitro dye conforms for example to the formula X



Any alkyl or alkenyl appearing in the abovementioned formulae may be straight-chain or branched.

Any substituted alkyl appearing in the abovementioned formulae may have as substituents for example, unless otherwise stated, cyclohexyl, phenyl, C₁-C₄-alkylphenyl, C₁-C₄-alkoxyphenyl, halophenyl, C₁-C₈-alkanoyloxy, C₁-C₈-alkylaminocarbonyloxy, C₁-C₂₀-alkoxycarbonyl, C₁-C₂₀-alkoxycarbonyloxy, in which case the alkyl chain in the last two radicals mentioned may be interrupted by from 1 to 4 oxygen atoms in ether function and/or may be phenyl- or phenoxy-substituted, cyclohexyloxy, phenoxy, halogen, hydroxyl or cyano. The number of substituents in substituted alkyl is generally 1 or 2.

In any oxygen-interrupted alkyl appearing in the abovementioned formulae the number of interrupting oxygen atoms in ether function, unless otherwise stated, is preferably from 1 to 4, especially 1 or 2.

Any substituted phenyl or pyridyl appearing in the abovementioned formulae may have as substituents for example, unless otherwise stated, C₁-C₈-alkyl, C₁-C₈-alkoxy, halogen, especially chlorine or bromine, nitro or carboxyl. The number of substituents in substituted phenyl or pyridyl is generally from 1 to 3.

Examples will now be mentioned of the radicals in the formulae II to V.

L², L⁴, L⁵, L⁸, L⁹, L¹¹, L¹², L¹⁵, L¹⁶, L¹⁷, R¹, R², R³, R⁴, R⁵, R⁶, R⁸, R¹⁰, R¹¹, R¹² and R¹³ are each for example methyl, ethyl, propyl, isopropyl, butyl, isobutyl, sec-butyl, pentyl, isopentyl, neopentyl, tert-pentyl, hexyl or 2-methylpentyl.

L⁹ may also be for example benzyl or 1- or 2-phenylethyl.

L², L⁸, L⁹ and L¹¹ may each also be for example methylthio, ethylthio, propylthio, isopropylthio, butylthio, isobutylthio, pentylthio, hexylthio, benzylthio or 1- or 2-phenylethylthio.

L² and L⁸ may each also be for example phenylthio, 2-methylphenylthio, 2-methoxyphenylthio or 2-chlorophenylthio.

L², L⁸, L¹⁵, L¹⁶, L¹⁷, R³ and R⁴ may each also be for example methoxy, ethoxy, propoxy, isopropoxy, butoxy, isobutoxy, sec-butoxy, pentyloxy, isopentyloxy, neopentyloxy, tert-pentyloxy, hexyloxy or 2-methylpentyloxy.

L⁶ is and each of L², L⁸, L¹³, L¹⁴, L¹⁵, L¹⁶ and L¹⁷ may further also be for example fluorine, chlorine or bromine.

15

L⁷ is and each of L¹, L², L⁸, L¹⁵, L¹⁶, L¹⁷, R¹⁰, R¹¹ and R¹² may further also be for example methylsulfonyl, ethylsulfonyl, propylsulfonyl, isopropylsulfonyl, butylsulfonyl, isobutylsulfonyl, sec-butylsulfonyl, pentylsulfonyl, 5 isopentylsulfonyl, neopentylsulfonyl, hexylsulfonyl, phenylsulfonyl, 2-methylphenylsulfonyl, 2-methoxyphenylsulfonyl or 2-chlorophenylsulfonyl.

L³ is and each of L⁶, L⁷, L⁸, L¹⁴, L¹⁵, L¹⁶ and L¹⁷ may further also 10 be for example methoxycarbonyl, ethoxycarbonyl, propoxycarbonyl, isopropoxycarbonyl, butoxycarbonyl, isobutoxycarbonyl or sec-butoxycarbonyl.

L¹⁵, L¹⁶ and L¹⁷ may each also be for example 2-phenoxyethoxy- 15 carbonyl, 2- or 3-phenoxypropoxycarbonyl, 2- or 4-phenoxybutoxycarbonyl, phenylazo, 4-nitrophenylazo or 2,4-dinitro-6-bromophenylazo.

L² and L⁸ may each also be for example 2-methoxyethoxy, 20 2-ethoxyethoxy, 2- or 3-methoxypropoxy, 2- or 3-ethoxypropoxy, 2- or 4-methoxybutoxy, 2- or 4-ethoxybutoxy, 5-methoxypentyloxy, 5-ethoxypentyloxy, 6-methoxyhexyloxy, 6-ethoxyhexyloxy, benzyloxy or 1- or 2-phenylethoxy.

25 L¹¹ may also be for example dimethylamino, diethylamino, dipropylamino, diisopropylamino, dibutylamino, dipentylamino, dihexylamino or N-methyl-N-ethylamino.


L¹² may also be for example 2-methoxycarbonylethylthio or 30 2-ethoxycarbonylethylthio.

R¹, R², R¹¹, R¹² and R¹³ may each also be for example cyclopentyl, cyclohexyl or cycloheptyl.

35 L⁹ may also be for example phenyl, 2-, 3- or 4-methylphenyl, 2,4-dimethylphenyl, 2-, 3- or 4-methoxyphenyl, 2-, 3- or 4-chlorophenyl, 2- or 3-methylthienyl or 2-, 3- or 4-methylpyridyl.

40 L¹, L⁶ and L⁷ may each also be for example formyl, acetyl, propionyl, butyryl, pentanoyl or hexanoyl.

In a -CH=T radical L¹ or L⁷ where T is derived from an acidic-CH compound H₂T said acidic-CH compounds H₂T can for example be 45 compounds of the formula



where

20 Z^1 is cyano, nitro, C_1 - C_4 -alkanoyl, substituted or unsubstituted benzoyl, C_1 - C_4 -alkylsulfonyl, substituted or unsubstituted phenylsulfonyl, C_1 - C_4 -alkoxycarbonyl, C_3 - C_4 -alkenyloxycarbonyl, phenoxy carbonyl, carbamoyl, mono- or di(C_1 - C_4 -alkyl)-carbamoyl, substituted or unsubstituted phenylcarbamoyl, substituted or unsubstituted phenyl, 2-benzothiazolyl,

25 2-benzimidazolyl, 5-phenyl-1,3,4-thiadiazol-2-yl or 2-hydroxy-3-quinoxaliny,

Z^2 is C_1 - C_4 -alkyl, C_1 - C_4 -alkoxy or C_3 - C_4 -alkenyloxy,

30 Z^3 is C_1 - C_4 -alkoxycarbonyl, C_3 - C_4 -alkenyloxycarbonyl, phenylcarbamoyl or 2-benzimidazolyl,

Z^4 is cyano, C_1 - C_4 -alkoxycarbonyl or C_3 - C_4 -alkenyloxycarbonyl,

35 Z^5 is hydrogen or C_1 - C_6 -alkyl,

Z^6 is hydrogen, C_1 - C_4 -alkyl or phenyl, and

Z^7 is C_1 - C_4 -alkyl.

40

Attention is drawn to the radical derived from compounds of the formula XIa, XIb or XIc where Z^1 is cyano, C_1 - C_4 -alkanoyl, C_1 - C_4 -alkoxycarbonyl or C_3 - C_4 -alkenyloxycarbonyl, Z^2 is C_1 - C_4 -alkyl, C_1 - C_4 -alkoxy or C_3 - C_4 -alkenyloxy, Z^3 is C_1 - C_4 -alkoxycarbonyl

45 or C_3 - C_4 -alkenyloxycarbonyl and Z^4 is cyano.

17

Particular attention is drawn to the radical derived from compounds of the formula XIa, XIb or XIc where Z^1 is cyano, C_1-C_4 -alkoxycarbonyl or C_3-C_4 -alkenyloxycarbonyl, Z^2 is C_1-C_4 -alkoxy or C_2-C_4 -alkenyloxy, Z^3 is C_1-C_4 -alkoxycarbonyl or C_3-C_4 -alkenyloxycarbonyl and Z^4 is cyano.

R^{10} , R^{11} and R^{12} may each also be for example heptyl, octyl, 2-ethylhexyl, nonyl, decyl, undecyl, dodecyl, 4,7-dioxanonyl, 4,8-dioxadecyl, 4,6-dioxaundecyl, 3,6,9-trioxaundecyl, 4,7,10-trioxaundecyl or 4,7,10-trioxadodecyl.

R^1 , R^2 , R^{10} , R^{11} and R^{12} may each also be for example 2-methoxyethyl, 2-ethoxyethyl, 2-propoxyethyl, 2-butoxyethyl, 2-isobutoxyethyl, 2- or 3-methoxypropyl, 1-methoxyprop-2-yl, 2- or 3-ethoxypropyl or 2- or 3-propoxypropyl, 3,6-dioxaheptyl, 3,6-dioxaoctyl, 4,7-dioxaoctyl, 2-hydroxyethyl, 3-hydroxypropyl, 4-hydroxybutyl, 2-cyclohexyloxyethyl, 2- or 3-cyclohexyloxypropyl, 2- or 4-cyclohexyloxybutyl, 2-phenoxyethyl, 2-phenoxypropyl, 3-phenoxypropyl, 4-phenoxybutyl, 2-methoxycarbonylethyl, 2-ethoxycarbonylethyl, 2- or 3-methoxycarbonylpropyl, 2- or 3-ethoxycarbonylpropyl, 2- or 3-butoxycarbonylpropyl, 4-methoxycarbonylbutyl, 4-ethoxycarbonylbutyl, 2-cyanoethyl, 2- or 3-cyanopropyl, 4-cyanobutyl, 2-cyclohexylethyl, 2- or 3-cyclohexylpropyl, benzyl, 1- or 2-phenylethyl, 2-acetyloxyethyl, 2-propionyloxyethyl, 2- or 3-acetyloxypropyl, prop-2-en-1-yl, 2-methyl-prop-2-en-1-yl, but-2-en-1-yl or but-3-en-1-yl.

R^{11} and R^{12} combined with the nitrogen atom joining them together into a five- or six-membered saturated heterocyclic radical with or without further hetero atoms may be for example pyrrolidinyl, piperidinyl, morpholinyl, thiomorpholinyl, thiomorpholinyl S,S-dioxide, piperazinyl or N-(C_1-C_4 -alkyl)piperazinyl, such as N-methyl- or N-ethyl-piperazinyl.

R^{10} , R^{11} and R^{12} may each also be for example formyl, acetyl, propionyl, butyryl, isobutyryl, pentanoyl, hexanoyl, heptanoyl, octanoyl, 2-ethylhexanoyl, benzoyl, 2-, 3- or 4-methylbenzoyl, 2-, 3- or 4-methoxybenzoyl or 2-, 3- or 4-chlorobenzoyl.

Examples will now be mentioned of the radicals in the formulae Va to Vd.

A¹ and A⁷ are each for example methyl, ethyl, propyl, isopropyl, butyl, isobutyl, sec-butyl, tert-butyl, pentyl, isopentyl, neopentyl, tert-pentyl, hexyl, 2-methylpentyl, heptyl, 1-ethylpentyl, octyl, 2-ethylhexyl or isooctyl.

5

A⁷ may also be for example 2-methoxyethyl, 2-ethoxyethyl, 2-propoxyethyl, 2-isopropoxyethyl, 2-butoxyethyl, 2- or 3-methoxypropyl, 2- or 3-ethoxypropyl, 2- or 3-propoxypropyl, 2- or 3-butoxypropyl, 2- or 4-methoxybutyl, 2- or 4-ethoxybutyl, 2- or 4-propoxybutyl, 3,6-dioxahexyl, 3,6-dioxaoctyl, 4,8-dioxanonyl, 3,7-dioxaoctyl, 3,7-dioxanonyl, 4,7-dioxaoctyl, 4,7-dioxanonyl, 2- or 4-butoxybutyl, 4,8-dioxadecyl, 3,6,9-trioxadecyl or 3,6,9-trioxaundecyl.

15 A¹ may also be for example phenyl, 2-, 3- or 4-methylphenyl, 2-, 3- or 4-ethylphenyl, 2-, 3- or 4-propylphenyl, 2-, 3- or 4-isopropylphenyl, 2-, 3- or 4-butylphenyl, 2,4-dimethylphenyl, 2-, 3- or 4-methoxyphenyl, 2-, 3- or 4-ethoxyphenyl, 2-, 3- or 4-isobutoxyphenyl or 2,4-dimethoxyphenyl.

20

A⁴ is for example fluorine, chlorine, bromine, 2-, 3- or 4-methoxyphenyl or 2-, 3- or 4-ethoxyphenyl.

G² is for example methylsulfamoyl, ethylsulfamoyl, propylsulfamoyl, isopropylsulfamoyl, butylsulfamoyl, pentylsulfamoyl, hexylsulfamoyl, heptylsulfamoyl, octylsulfamoyl or 4-oxahexylsulfamoyl.

Examples will now be mentioned of the radicals in the formulae
30 VIA to VIC.

W¹, W² and W⁴ are each for example methyl, ethyl, propyl, isopropyl, butyl, isobutyl, sec-butyl or tert-butyl.

35 W⁴ may also be for example pentyl, isopentyl, neopentyl, tert-pentyl, hexyl, 2-methylpentyl, heptyl, 1-ethylpentyl, octyl, 2-ethylhexyl or isooctyl.

Examples will now be mentioned of the radicals in the formulae
40 VIIa and VIIb.

Q¹, Q⁵, Q⁶, E¹, E², E³, E⁴, E⁵, E⁶, E⁷, E⁸ and E¹⁰ are each for example methyl, ethyl, propyl, isopropyl, butyl, isobutyl, sec-butyl or tert-butyl.

45

Q¹, Q⁶, E¹, E², E³, E⁴, E⁵, E⁶, E⁷ and E⁸ may each also be for example pentyl, isopentyl, neopentyl, tert-pentyl, hexyl, 2-methylpentyl, heptyl, 1-ethylpentyl, octyl, 2-ethylhexyl or isooctyl.

5

Q¹, E² and E³ may each also be for example nonyl, isononyl, decyl, isodecyl, undecyl or dodecyl.

Q¹ may also be for example tridecyl, isotridecyl, tetradecyl, pentadecyl, hexadecyl, heptadecyl, octadecyl, nonadecyl, eicosyl (the above designations isooctyl, isononyl, isodecyl and isotridecyl are trivial names derived from the oxo process alcohols - cf. Ullmann's Enzyklopädie der technischen Chemie, 4th Edition, Volume 7, pages 215 to 217, and Volume 11, pages 435 and 436), 2-methoxycarbonylethyl, benzyl, 1- or 2-phenylethyl, 3-benzyloxypropyl, phenoxymethyl, 6-phenoxy-4-oxahexyl, 8-phenoxy-4-oxaoctyl, 2-, 3- or 4-chlorophenyl or 2-, 3- or 4-carboxyphenyl.

Q¹ and E¹ may each also be for example 2-methoxyethyl, 2-ethoxyethyl, 2-propoxyethyl, 2-isopropoxyethyl, 2-butoxyethyl, 2- or 3-methoxypropyl, 2- or 3-ethoxypropyl, 2- or 3-propoxypropyl, 2- or 3-butoxypropyl, 2- or 4-methoxybutyl, 2- or 4-ethoxybutyl, 2- or 4-propoxybutyl, 3,6-dioxaheptyl, 3,6-dioxaoctyl, 4,8-dioxanonyl, 3,7-dioxaoctyl, 3,7-dioxanonyl, 4,7-dioxaoctyl, 4,7-dioxanonyl, 2- or 4-butoxybutyl or 4,8-dioxadecyl.

Q¹ may also be for example 3,6,9-trioxadecyl, 3,6,9-trioxaundecyl, 3,6,9-trioxadodecyl, 3,6,9,12-tetraoxatridecyl, 3,6,9,12-tetraoxatetradecyl, 11-oxahexadecyl, 13-butyl-11-oxaheptadecyl or 4,11-dioxapentadecyl.

Q³, E², E³ and E⁹ are each for example methoxycarbonyl, ethoxycarbonyl, propoxycarbonyl, isopropoxycarbonyl, butoxycarbonyl, isobutoxycarbonyl or sec-butoxycarbonyl.

E⁹ may also be for example mono- or dimethylcarbamoyl, mono- or diethylcarbonyl, mono- or dipropylcarbonyl, mono- or diisopropylcarbonyl, mono- or dibutylcarbonyl or N-methyl-N-butylcarbonyl.

E⁷, E⁸ and E¹⁰ may each also be for example methoxy, ethoxy, propoxy, isopropoxy, butoxy, isobutoxy or sec-butoxy.

45

E¹⁰ may also be for example methylthio, ethylthio, propylthio, isopropylthio, butylthio, isobutylthio or sec-butylthio.

Q¹, E², E³ and E¹⁰ may each also be for example phenyl, 2-, 3- or
 5 4-methylphenyl, 2-, 3- or 4-ethylphenyl, 2-, 3- or
 4-propylphenyl, 2-, 3- or 4-isopropylphenyl, 2-, 3- or
 4-butylphenyl, 2,4-dimethylphenyl, 2-, 3- or 4-methoxyphenyl, 2-,
 3- or 4-ethoxyphenyl, 2-, 3- or 4-isobutoxyphenyl or
 2,4-dimethoxyphenyl.

10

Q¹, E² and E³ may each also be for example 2-hydroxyethyl, 2- or
 3-hydroxypropyl, 2-cyanoethyl, 2- or 3-cyanopropyl,
 2-acetyloxyethyl, 2- or 3-acetyloxypropyl, 2-isobutyryloxyethyl,
 2- or 3-isobutyryloxypropyl, 2-methoxycarbonylethyl, 2- or
 15 3-methoxycarbonylpropyl, 2-ethoxycarbonylethyl, 2- or
 3-ethoxycarbonylpropyl, 2-methoxycarbonyloxyethyl, 2- or
 3-methoxycarbonyloxypropyl, 2-ethoxycarbonyloxyethyl, 2- or
 3-ethoxycarbonyloxypropyl, 2-butoxycarbonyloxyethyl, 2- or
 3-butoxycarbonyloxypropyl, 2-(2-phenylethoxycarbonyloxy)ethyl,
 20 2- or 3-(2-phenylethoxycarbonyloxy)propyl,
 2-(2-ethoxyethoxycarbonyloxy)ethyl or 2- or
 3-(2-ethoxyethoxycarbonyloxy)propyl.

E² and E³ may each also be for example pyridyl, 2-, 3- or
 25 4-methylpyridyl, 2-, 3- or 4-methoxypyridyl, formyl, acetyl,
 propionyl, butyryl, isobutyryl, pentanoyl, hexanoyl, heptanoyl,
 octanoyl, 2-ethylhexanoyl, methylsulfonyl, ethylsulfonyl,
 propylsulfonyl, isopropylsulfonyl, butylsulfonyl,
 cyclopentylsulfonyl, cyclohexylsulfonyl, cycloheptylsulfonyl,
 30 phenylsulfonyl, tolylsulfonyl, pyridylsulfonyl, benzoyl, 2-,
 3- or 4-methylbenzoyl, 2-, 3- or 4-methoxybenzoyl,
 thien-2-ylcarbonyl, thien-3-ylcarbonyl, cyclopentyl, cyclohexyl
 or cycloheptyl.


35 E² and E³ or E⁴ and E⁵ combined with the nitrogen atom joining
 them together into a five- or six-membered saturated heterocyclic
 radical with or without further hetero atoms may be for example
 pyrrolidinyl, piperidinyl, morpholinyl, piperazinyl or N-(C₁-C₄-
 alkyl)piperazinyl.

40

Particularly suitable monoazo dyes are those of the formula IIa
 where D¹ is a radical of the formula IIIb.

Particularly suitable monoazo dyes further include those of the
 45 formula IIa where K¹ is a radical of the formula IVa or IVd.

Particular attention is drawn to monoazo dyes of the formula IIb



10 where

L^1 is nitro, cyano, C_1 - C_6 -alkanoyl or a radical of the formula $-CH=T$ where T is a radical of an acidic-CH compound,

15 L^2 is C_1 - C_6 -alkyl, halogen, unsubstituted or phenyl- or C_1 - C_4 -alkoxy-substituted C_1 - C_6 -alkoxy,

L^3 is cyano, C_1 - C_4 -alkoxycarbonyl or nitro,

20 R^1 and R^2 are independently of each other hydrogen, substituted or unsubstituted C_1 - C_6 -alkyl with or without interruption by 1 or 2 oxygen atoms in ether function, or C_3 - C_6 -alkenyl,

R^3 is hydrogen, C_1 - C_6 -alkyl or C_1 - C_6 -alkoxy, and

25

R^4 is hydrogen, C_1 - C_6 -alkyl, C_1 - C_6 -alkoxy, C_1 - C_6 -alkylsulfonylamino or substituted or unsubstituted C_1 - C_6 -alkanoylamino.

Particularly suitable methine or azamethine dyes conform to the
30 formula VIIa or VIIb where R^5 is methyl.

Particularly suitable methine or azamethine dyes further conform to the formula VIIa or VIIb where Q^5 is cyano.

35 Particularly suitable methine or azamethine dyes further conform to the formula VIIa or VIIb where Q^4 is oxygen.

Particularly suitable azamethine dyes further conform to the formula VII where X is nitrogen.

40

Particularly suitable methine dyes further conform to the formula VII where X is CH.

Particularly suitable methine or azamethine dyes further conform
45 to the formula VIIa or VIIb where Q^2 is a radical of the pyrrole, thiazole or thiophene series.

Particularly suitable methine or azamethine dyes further conform to the formula VIIa where Q^1 is C_1 - C_{12} -alkyl with or without substitution by C_1 - C_6 -alkanoyloxy, C_1 - C_8 -alkoxycarbonyl, whose alkyl chain may be interrupted by 1 or 2 oxygen atoms in ether function, phenyl or C_1 - C_4 -alkylphenyl and with or without interruption by 1 or 2 oxygen atoms in ether function.

Particularly suitable methine or azamethine dyes further conform to the formula VIIb where Q^6 is a radical of the formula NE^2E^3 where E^2 and E^3 are independently of each other substituted or unsubstituted C_1 - C_{12} -alkanoyl or substituted or unsubstituted benzoyl or else E^2 is hydrogen.

Particular attention is drawn to methine or azamethine dyes of the formula VIIb where Q^6 is a radical of the formula NE^2E^3 where E^2 and E^3 are independently of each other C_1 - C_8 -alkanoyl or benzoyl or else E^2 is hydrogen.

Particular attention is further drawn to methine or azamethine dyes of the formula VIIa where Q^1 is alkyl, alkoxyalkyl, alkanoyloxyalkyl or alkoxycarbonylalkyl, which radicals have up to 12 carbon atoms each, unsubstituted or methyl-substituted benzyl or unsubstituted or methyl-substituted phenyl.

Particular attention is further drawn to methine or azamethine dyes of the formula VIIa or VIIb where Q^2 is a radical of the abovementioned formula VIIIA or VIIIC, especially VIIIA, where

E^4 and E^5 are independently of each other alkyl, alkoxyalkyl, alkanoyloxyalkyl or alkoxycarbonylalkyl, which radicals have up to 12 carbon atoms each, hydrogen, unsubstituted or methyl-substituted benzyl or unsubstituted or methyl-substituted phenyl,

E^6 is hydrogen, C_1 - C_4 -alkyl, unsubstituted or C_1 - C_4 -alkyl- or C_1 - C_4 -alkoxy-substituted phenyl, benzyl or thienyl,

E^9 is cyano,

E^{10} is halogen, hydrogen, C_1 - C_4 -alkyl, C_1 - C_4 -alkoxy, C_1 - C_4 -alkyl-thio, unsubstituted or C_1 - C_4 -alkyl-substituted phenyl or thienyl, and

n is 0.

Particularly suitable quinophthalone dyes conform to the formula IX where G^4 is hydrogen or bromine.

The monoazo dyes of the formula IIa are known per se and have been described in large numbers, for example in K. Venkataraman,

The Chemistry of Synthetic Dyes, Vol. VI, Academic Press, New York, London, 1972, or EP-A-201 896.

The anthraquinone dyes of the formula Va to Vc are likewise known
5 per se and described for example in D.R. Waring, G. Hallas, The Chemistry and Application of Dyes, pages 107 to 118, Plenum Press, New York, London, 1990.

The coumarin dyes of the formula VIa to VIc are likewise known
10 per se and described for example in Ullmann's Enzyklopädie der technischen Chemie, 4th Edition, Volume 17, page 469.

The methine or azamethine dyes of the formula VIIa and VIIb are likewise known per se and described for example in US-A-5 079 365
15 and WO-A-9219684.

The quinophthalone dyes of the formula IX are likewise known per se and described for example in EP-83 553.

20 The nitro dye of the formula X is commonly referred to as C.I. Disperse Yellow 42 (10 338).

Suitable dyes with carboxyl and/or sulfo groups will now be more particularly described. These dyes are in particular azo or
25 anthraquinone dyes.

Of azo dyes, it is monoazo or disazo dyes, which may also be metallized, which are notable, in particular those which have from 1 to 6 carboxyl and/or sulfo groups.

30


Important azo dyes are for example those whose diazo component is derived from an aniline or aminonaphthalene.

Important azo dyes further include for example those whose
35 coupling component is derived from an aniline, naphthalene, pyrazolone, aminopyrazole, diaminopyridine, pyridone or acylacetarylde.

Specific examples include metal-free or metallized (metal
40 complexes) azo dyes of the phenyl-azo-naphthalene, phenyl-azo-1-phenylpyrazol-5-one, phenyl-azo-benzene, naphthyl-azo-benzene, phenyl-azo-aminonaphthalene, naphthyl-azo-naphthalene, naphthyl-azo-1-phenylpyrazol-5-one, phenyl-azo-pyridone, phenyl-azo-aminopyridine, naphthyl-azo-pyridone,
45 naphthyl-azo-aminopyridine or stilbyl-azo-benzene series.

The azo dyes may additionally contain a reactive group, for example the radical of the formula

5



10 which is linked either to the diazo component or to the coupling component via a substituted or unsubstituted amino group.

Of particular importance are azo dyes of the formula IIC


15




(IIC),

where D^2 is a radical of the formula


20




(XIIa)



(XIIb)



(XIIc)



(XIId)

25

30


35

40

45


25

5



(XIIe)

or




(XIIIf)


and

10 K² is a radical of the formula


15



(XIIIa)




(XIIIb)




(XIIIc)


20



(XIIId)




(XIIIe)




(XIIIIf)

25


30



(XIIIg)




(XIIIh)




(XIIIi)

35

40




(XIIIj)




(XIIIk)

45



or



10

where

- a is 0, 1, 2 or 3,
 b is 0, 1 or 2,
 15 c is 0 or 1,

U¹ is hydrogen, methyl, ethyl, methoxy, ethoxy, acetyl, cyano, carboxyl, hydroxysulfonyl, C₁-C₄-alkoxycarbonyl, hydroxyl, carbamoyl, C₁-C₄-monoalkylcarbamoyl or -dialkylcarbamoyl, 20 fluorine, chlorine, bromine or trifluoromethyl,

U² is hydrogen, methyl, ethyl, methoxy, ethoxy, cyano, carboxyl, hydroxysulfonyl, acetylamino, C₁-C₄-alkoxycarbonyl, carbamoyl, C₁-C₄-monoalkylcarbamoyl or -dialkylcarbamoyl, fluorine, 25 chlorine, nitro, sulfamoyl, C₁-C₄-monoalkylsulfamoyl or -dialkylsulfamoyl, C₁-C₄-alkylsulfonyl, phenylsulfonyl or phenoxy, and

U³ is a direct bond, oxygen, sulfur or the group -NHCO-, 30 -NH-CO-NH-, -CONH-, -CO-, -NHSO₂-, -SO₂NH-, -SO₂-, -CH=CH-, -CH₂-CH₂-, -CH₂-, -NH-, or -N=N-,

V¹ is hydrogen or C₁-C₄-alkyl,

35 V² is hydrogen, C₁-C₄-alkyl or phenyl which may be substituted by C₁-C₅-alkyl, C₁-C₄-alkoxy, chlorine, bromine or hydroxysulfonyl,

V³ is hydrogen or C₁-C₄-alkyl which may be substituted by 40 hydroxyl, cyano, carboxyl, hydroxysulfonyl, sulfato, methoxycarbonyl, ethoxycarbonyl or acetoxy,

V⁴ is hydrogen, C₁-C₄-alkyl which may be hydroxyl-, cyano-, carboxyl-, hydroxysulfonyl-, sulfato-, methoxycarbonyl-, ethoxy- 45 carbonyl- or acetoxy-substituted, benzyl or phenyl which may

be substituted by C₁-C₄-alkyl, C₁-C₄-alkoxy, chlorine or hydroxysulfonyl,

- V⁵ is C₁-C₆-alkylureido, phenylureido, which may be chlorine-, methyl-, methoxy-, nitro-, hydroxysulfonyl- or carboxyl-substituted, C₁-C₆-alkanoylamino, which may be hydroxysulfonyl- or chlorine-substituted, cyclohexanoylamino, benzoylamino, which may be chlorine-, methyl-, methoxy-, nitro-, hydroxysulfonyl- or carboxyl-substituted, or hydroxyl,
- 5
- V⁶ is hydrogen, C₁-C₆-alkyl, which may be phenyl-, C₁-C₄-alkoxy-, hydroxyl-, phenoxy- or C₁-C₄-alkanoyloxy-substituted, C₅-C₇-cycloalkyl, hydroxysulfonylphenyl, C₁-C₄-alkanoyl, carbamoyl, C₁-C₄-monoalkylcarbamoyl or -dialkylcarbamoyl, phenylcarbamoyl or cyclohexylcarbamoyl,
- 10
- 15
- V⁷ is methoxy, ethoxy, chlorine, bromine, hydroxysulfonyl, acetylamino, amino, ureido, methylsulfonylamino, ethylsulfonylamino, dimethylaminosulfonylamino, methylamino, ethylamino, dimethylamino or diethylamino,
- 20
- V⁸ is hydrogen, methyl, ethyl, methoxy, ethoxy, hydroxysulfonyl, chlorine or bromine,
- 25
- M is the radical of a benzene or naphthalene ring,
- V⁹ is methyl, carboxyl, C₁-C₄-alkoxycarbonyl or phenyl,
- V¹⁰ C₁-C₄-alkyl, cyclohexyl, benzyl or phenyl which may be substituted by fluorine, chlorine, bromine, methyl, methoxy, nitro, hydroxysulfonyl, carboxyl, acetyl, acetylamino, methylsulfonyl, sulfamoyl or carbamoyl,
- 30
- V¹¹ is hydrogen or C₁-C₄-alkyl which may be substituted by methoxy, ethoxy or cyano,
- 35
- V¹² is hydrogen, methyl, hydroxysulfonylmethyl, hydroxysulfonyl, cyano or carbamoyl,
- 40
- V¹³ is hydrogen, C₁-C₄-alkyl which may be phenyl-, hydroxysulfonylphenyl-, hydroxyl-, amino-, methoxy-, ethoxy-, carboxyl-, hydroxysulfonyl-, acetylamino-, benzoylamino- or cyano-substituted, cyclohexyl, phenyl which may be carboxyl-, hydroxysulfonyl-, benzoylamino-, acetylamino-, methyl-, methoxy-, cyano- or chlorine-substituted, or amino which is substituted by phenyl, C₁-C₄-alkyl, acetyl or benzoyl,
- 45

- V¹⁴ is C₁-C₄-alkyl, phenyl, hydroxyl, cyano, acetyl, benzoyl, carboxyl, methoxycarbonyl, carbamoyl or hydroxysulfonylmethyl and
- 5 V¹⁵ is hydrogen, chlorine, bromine, acetylamino, amino, nitro, hydroxysulfonyl, sulfamoyl, methylsulfonyl, phenylsulfonyl, carboxyl, methoxycarbonyl, acetyl, benzoyl, carbamoyl, cyano or hydroxysulfonylmethyl,
- 10 with the proviso that at least one carboxyl and/or sulfo group is present in the molecule.
- Aromatic amines which are suitable for use as diazo components and which are derived from the formula XIIa, XIIb, XIIc or XIId
- 15 are for example aniline, 2-methoxyaniline, 2-methylaniline, 4-chloro-2-aminoanisole, 4-methylaniline, 4-methoxyaniline, 2-methoxy-5-methylaniline, 2,5-dimethoxyaniline, 2,5-dimethylaniline, 2,4-dimethylaniline, 2,5-diethoxyaniline, 2-chloroaniline, 3-chloroaniline, 4-chloroaniline,
- 20 2,5-dichloroaniline, 4-chloro-2-nitroaniline, 4-chloro-2-methylaniline, 3-chloro-2-methylaniline, 4-chloro-2-aminotoluene, 4-phenylsulfonylaniline, 2-ethoxy-1-naphthylamine, 1-naphthylamine, 2-naphthylamine, 4-methylsulfonylaniline, 2,4-dichloroaniline-5-carboxylic acid,
- 25 2-aminobenzoic acid, 4-aminobenzoic acid, 3-aminobenzoic acid, 3-chloroaniline-6-carboxylic acid, aniline-2- or -3- or -4-sulfonic acid, aniline-2,5-disulfonic acid, aniline-2,4-disulfonic acid, aniline-3,5-disulfonic acid, 2-aminotoluene-4-sulfonic acid, 2-aminoanisole-5-sulfonic acid, 2-ethoxyaniline-
- 30 5-sulfonic acid, 2-ethoxyaniline-4-sulfonic acid, 4-hydroxy-sulfonyl-2-aminobenzoic acid, 2,5-dimethoxyaniline-4-sulfonic acid, 2,4-dimethoxyaniline-5-sulfonic acid, 2-methoxy-5-methylaniline-4-sulfonic acid, 4-aminoanisole-3-sulfonic acid, 4-aminotoluene-3-sulfonic acid, 2-aminotoluene-5-sulfonic acid,
- 35 2-chloroaniline-4-sulfonic acid, 2-chloroaniline-5-sulfonic acid, 2-bromo-aniline-4-sulfonic acid, 2,6-dichloroaniline-4-sulfonic acid, 2,6-dimethylaniline-3- or -4-sulfonic acid, 3-acetylamino-aniline-6-sulfonic acid, 4-acetylaminoaniline-2-sulfonic acid, 1-aminonaphthalene-3-sulfonic acid, 1-aminonaphthalene-4-sulfonic
- 40 acid, 1-aminonaphthalene-5-sulfonic acid, 1-aminonaphthalene-6-sulfonic acid, 1-aminonaphthalene-7-sulfonic acid, 1-aminonaphthalene-3,7-disulfonic acid, 1-aminonaphthalene-3,6,8-trisulfonic acid, 1-aminonaphthalene-4,6,8-trisulfonic acid, 2-naphthylamine-
- 45 5-sulfonic acid, or -6- or -8-sulfonic acid, 2-aminonaphthalene-3,6,8-trisulfonic acid, 2-aminonaphthalene-6,8-disulfonic acid, 2-aminonaphthalene-1,6-disulfonic acid,

- 2-aminonaphthalene-1-sulfonic acid,
 2-aminonaphthalene-1,5-disulfonic acid,
 2-aminonaphthalene-3,6-disulfonic acid,
 2-aminonaphthalene-4,8-disulfonic acid, 2-aminophenol-4-sulfonic
 5 acid, 2-aminophenol-5-sulfonic acid, 3-aminophenol-6-sulfonic
 acid, 1-hydroxy-2-aminonaphthalene-5,8- or -4,6-disulfonic acid,
 4-aminodiphenylamine, 4-amino-4'-methoxydiphenylamine,
 4-amino-4'-methoxydiphenylamine-3-sulfonic acid,
 4-(2'-methylphenylazo)-2-methylaniline, 4-aminoazobenzene,
 10 4'-nitrophenylazo-1-aminonaphthalene,
 4-(6'-hydroxysulfonylnaphthylazo)-1-aminonaphthalene,
 4-(2',5'-dihydroxysulfonylphenylazo)-1-aminonaphthalene,
 4'-amino-3'-methyl-3-nitrobenzophenone, 4-aminobenzophenone,
 4-(4'-aminophenylazo)benzenesulfonic acid,
 15 4-(4'-amino-2'-methoxyphenylazo)benzenesulfonic acid,
 4-(4'-amino-3'-methoxyphenylazo)benzenesulfonic acid and
 2-ethoxy-1-naphthylamine-6-sulfonic acid.

- Aromatic diamines which are suitable for use as tetrazo
 20 components and which are derived from the formula XIIe or XIIf
 are for example 1,3-diaminobenzene, 1,3-diaminobenzene-4-sulfonic
 acid, 1,4-diaminobenzene, 1,4-diaminobenzene-2-sulfonic acid,
 1,4-diamino-2-methylbenzene, 1,4-diamino-2-methoxybenzene,
 1,3-diamino-4-methylbenzene, 1,3-diaminobenzene-5-sulfonic acid,
 25 1,3-diamino-5-methylbenzene, 1,6-diaminonaphthalene-4-sulfonic
 acid, 2,6-diaminonaphthalene-4,8-disulfonic acid,
 3,3'-diaminodiphenyl sulfone, 4,4'-diaminodiphenyl sulfone,
 4,4'-diaminostilbene-2,2'-disulfonic acid, 2,7'-diaminodiphenyl
 sulfone, 2,7'-diaminodiphenyl sulfone-4,5-disulfonic acid,
 30 4,4'-diaminobenzophenone, 4,4'-diamino-3,3'-dinitrobenzophenone,
 3,3'-diamino-4,4'-dichlorobenzophenone, 4,4'- or
 3,3'-diaminobiphenyl, 4,4'-diamino-3,3'-dichlorobiphenyl,
 4,4'-diamino-3,3'-dimethoxy- or -3,3'-dimethyl- or
 -2,2'-dimethyl- or -2,2'-dichloro- or -3,3'-diethoxybiphenyl,
 35 4,4'-diamino-3,3'-dimethyl-6,6'-dinitrobiphenyl,
 4,4'-diaminobiphenyl-2,2'- or -3,3'-disulfonic acid,
 4,4'-diamino-3,3'-dimethyl- or -3,3'-dimethoxy- or
 -2,2'-dimethoxybiphenyl-6,6'-disulfonic acid, 4,4'-diamino-2,2',
 5,5'-tetrachlorobiphenyl, 4,4'-diamino-3,3'-dinitrobiphenyl,
 40 4,4'-diamino-2,2'-dichloro-5,5'-dimethoxybiphenyl,
 4,4'-diaminobiphenyl-2,2'- or -3,3'-dicarboxylic acid,
 4,4'-diamino-3,3'-dimethylbiphenyl-5,5'-disulfonic acid,
 4,4'-diamino-2-nitrobiphenyl, 4,4'-diamino-3-ethoxy- or
 -3-hydroxysulfonylbiphenyl,
 45 4,4'-diamino-3,3'-dimethylbiphenyl-5-sulfonic acid,
 4,4'-diaminodiphenylmethane,
 4,4'-diamino-3,3'-dimethyldiphenylmethane, 4,4'-diamino-2,2',

3,3'-tetramethyldiphenylmethane, 4,4'-diaminodiphenylethane, 4,4'-diaminostilbene or 4,4'-diaminodiphenylmethane-3,3'-dicarboxylic acid.

- 5 K² is for example an aniline, such as o- or m-toluidine, o- or m-anisidine, cresidine, 2,5-dimethylaniline, 2,5-dimethoxyaniline, m-aminoacetanilide, 3-amino-4-methoxyacetanilide, 3-amino-4-methylacetanilide, m-aminophenylurea, N-methylaniline, N-methyl-m-toluidine, 10 N-ethylaniline, N-ethyl-m-toluidine, N-(2-hydroxyethyl)aniline or N-(2-hydroxyethyl)-m-toluidine.

- K² may also be for example a naphtholsulfonic acid, such as 1-naphthol-3-sulfonic acid, 1-naphthol-4-sulfonic acid, 15 1-naphthol-5-sulfonic acid, 1-naphthol-8-sulfonic acid, 1-naphthol-3,6-disulfonic acid, 1-naphthol-3,8-disulfonic acid, 2-naphthol-5-sulfonic acid, 2-naphthol-6-sulfonic acid, 2-naphthol-7-sulfonic acid, 2-naphthol-8-sulfonic acid, 2-naphthol-3,6-disulfonic acid, 2-naphthol-6,8-disulfonic acid, 20 2-naphthol-3,6,8-trisulfonic acid, 1,8-dihydroxynaphthalene-3,6-disulfonic acid, 2,6-dihydroxynaphthalene-8-sulfonic acid or 2,8-dihydroxynaphthalene-6-sulfonic acid.

- 25 K² may also be for example a naphthylamine, such as 1-naphthylamine, N-phenyl-1-naphthylamine, N-ethyl-1-naphthylamine, N-phenyl-2-naphthylamine, 1-naphthol, 2-naphthol, 1,5-dihydroxynaphthalene, 1,6-dihydroxynaphthalene, 1,7-dihydroxynaphthalene or 2,7-dihydroxynaphthalene.

30

- K² may also be for example an aminonaphthalenesulfonic acid, such as 1-naphthylamine-6-sulfonic acid, 1-naphthylamine-7-sulfonic acid, 1-naphthylamine-8-sulfonic acid, 2-naphthylamine-3,6-disulfonic acid, 35 2-naphthylamine-5,7-disulfonic acid or 2-naphthylamine-6,8-disulfonic acid.

- K² may also be for example an aminonaphtholsulfonic acid, such as 1-amino-5-hydroxynaphthalene-7-sulfonic acid, 40 1-amino-8-hydroxynaphthalene-4-sulfonic acid, 1-amino-8-hydroxynaphthalene-2,4-disulfonic acid, 1-amino-8-hydroxynaphthalene-3,6-disulfonic acid, 1-amino-8-hydroxynaphthalene-4,6-disulfonic acid, 2-amino-5-hydroxynaphthalene-7-sulfonic acid, 45 2-amino-8-hydroxynaphthalene-6-sulfonic acid, 2-amino-8-hydroxynaphthalene-3,6-disulfonic acid, 2-amino-5-hydroxynaphthalene-1,7-disulfonic acid,

- 1-acetylamino-8-hydroxynaphthalene-3,6-disulfonic acid,
 1-benzoylamino-8-hydroxynaphthalene-3,6-disulfonic acid,
 1-acetylamino-8-hydroxynaphthalene-4,6-disulfonic acid,
 1-benzoylamino-8-hydroxynaphthalene-4,6-disulfonic acid,
 5 1-acetylamino-5-hydroxynaphthalene-7-sulfonic acid,
 2-methylamino-8-hydroxynaphthalene-6-sulfonic acid,
 2-methylamino-8-hydroxynaphthalene-6-sulfonic acid or 2-(3'- or
 4'-hydroxysulfonylphenyl)amino-8-hydroxynaphthalene-6-sulfonic
 acid.
- 10
 K² may also be for example a pyrazolone, such as 1-phenyl-,
 1-(2'-chlorophenyl)-, 1-(2'-methoxyphenyl)-,
 1-(2'-methylphenyl)-, 1-(1',5'-dichlorophenyl)-,
 1-(2',6'-dichlorophenyl)-, 1-(2'-methyl-6'-chlorophenyl)-,
 15 1-(2'-methoxy-5'-methylphenyl)-,
 1-(2'-methoxy-5'-hydroxysulfonylphenyl)-,
 1-(2',5'-dihydroxysulfonylphenyl)-, 1-(2'-carboxyphenyl)-,
 1-(3'-hydroxysulfonylphenyl)-, 1-(4'-hydroxysulfonylphenyl)- or
 1-(3'-sulfamoylphenyl)-3-carboxypyrazol-5-one, 1-(3'- or
 20 4'-hydroxysulfonylphenyl)-, 1-(2'-chloro-4'- or
 -5'-hydroxysulfonylphenyl)-1-(2'-methyl-4'-hydroxysulfonyl-
 phenyl)-, 1-(2',5'-dichlorophenyl)-1-(4',8'-dihydroxysulfonyl-
 1-naphthyl)-, 1-(6'-hydroxysulfonyl-1-naphthyl)-3-methyl-
 pyrazol-5-one, ethyl 1-phenylpyrazol-5-one-3-carboxylate, ethyl
 25 pyrazol-5-one-3-carboxylate or pyrazol-5-one-3-carboxylic acid.

- K² may also be for example an aminopyrazole, such as 1-methyl-,
 1-ethyl-, 1-propyl-, 1-butyl-, 1-cyclohexyl-, 1-benzyl- or
 1-phenyl-5-aminopyrazole, 1-(4-chlorophenyl)- or
 30 1-(4'-methylphenyl)-5-aminopyrazole and
 1-phenyl-3-methyl-5-aminopyrazole.

- K² may also be for example a pyridone, such as 1-ethyl-2-hydroxy-
 4-methyl-5-carbamoylpyrid-6-one, 1-(2'-hydroxyethyl)-2-hydroxy-
 35 4-methyl-5-carbamoylpyrid-6-one, 1-phenyl-2-hydroxy-4-methyl-
 5-carbamoylpyrid-6-one, 1-ethyl-2-hydroxy-4-methyl-5-cyanopyrid-
 6-one, 1-ethyl-2-hydroxy-4-methyl-5-hydroxysulfonylmethylpyrid-
 6-one, 1-methyl-2-hydroxy-4-methyl-5-cyanopyrid-6-one, 1-methyl-
 2-hydroxy-5-acetylpyrid-6-one,
 40 1,4-dimethyl-2-hydroxy-5-cyanopyrid-6-one,
 1,4-dimethyl-5-carbamoylpyrid-6-one, 2,6-dihydroxy-
 4-ethyl-5-cyanopyridine, 2,6-dihydroxy-4-ethyl-5-
 carbamoylpyridine, 1-ethyl-2-hydroxy-4-methyl-5-
 hydroxysulfonylmethylpyrid-6-one,
 45 1-methyl-2-hydroxy-4-methyl-5-methylsulfonylpyrid-6-one or

1-carboxymethyl-2-hydroxy-4-ethyl-5-phenylsulfonylpyrid-6-one.

Instead of the azo dyes of the formula IIc the process of the invention may also employ the corresponding metal complex dyes.


Suitable complexing metals here are in particular copper, cobalt, chromium, nickel and iron of which copper, cobalt or chromium are preferred. Of particular suitability are the symmetrical or asymmetrical 1:1 or 1:2 chromium complexes. The metallized groups are each preferably ortho to the azo group, for example in the form of o,o-dihydroxy-, o-hydroxy-o'-carboxy-, o-carboxy-o'-amino- or o-hydroxy-o'-amino-azo-groups.

Preference is given to dyes of formula IIc where D² is a radical of the formula XIIa, XIIb, XIIc, XIId, XIIe or XIIf where U¹ is hydrogen, methyl, methoxy, carboxyl, hydroxysulfonyl, hydroxyl or chlorine, U² is hydrogen, methyl, methoxy, carboxyl, hydroxysulfonyl, acetyl amino or chlorine and U³ is -CO-, -SO₂-, -CH=CH-, -CH₂-CH₂-, -CH₂- or -N=N-.

Preference is further given to dyes of formula IIc where the radical K² is derived from coupling components which have sulfo and/or carboxyl groups and which couple ortho or para to a hydroxyl and/or amino group. Specific examples of such coupling components are 2-acetyl amino-5-hydroxynaphthalene-7-sulfonic acid, 2-acetyl amino-8-hydroxynaphthalene-6-sulfonic acid, 1-acetyl amino-8-hydroxynaphthalene-3,6-disulfonic acid, 1-benzoylamino-8-hydroxynaphthalene-3,6-disulfonic acid, 1-acetyl amino-8-hydroxynaphthalene-4,6-disulfonic acid or 1-benzoylamino-8-hydroxynaphthalene-4,6-disulfonic acid.

Preference is given to azo dyes of the formula XIV

35



(XIV),

40


where B¹ is hydrogen, C₁-C₄-alkyl, C₁-C₄-alkoxy, chlorine or hydroxysulfonyl and K³ is the radical of a coupling component of the naphthalene, pyrazolone or pyridone series.

45

33

Particular preference is further given to azo dyes of the formula XV

5




10


where D² is as defined above and B² is hydroxysulfonyl in ring position 3 or 4.

Particular preference is further given to azo dyes of the formula XVI

20



25




30

where D² is as defined above and the amino group is in ring position 6 or 7.


Useful compounds further include those of the formula XVII

40



where D² is as defined above and d and e independently of each other are 0, 1 or 2.

Useful compounds further include those of the formula XVIII




10 where B² is as defined above and one of B³ and B⁴ is D², which has the abovementioned meaning, and the other is 3-amino-6-hydroxysulfonylphenyl or else both B³ and B⁴ are 3-amino-6-hydroxysulfonylphenyl.


15 Also of particular suitability is the symmetrical 1:2 chromium complex dye based on the azo dye 1-(2-hydroxy-4-hydroxysulfonyl-6-nitronaphth-1-ylazo)-2-hydroxy-naphthalene.

20 The process of the present invention may also employ acid anthraquinone dyes. Such anthraquinones are known per se and described for example in K. Venkataraman, The Chemistry of Synthetic Dyes, Vol. II, Academic Press, New York, 1952.

25 Preference is given to acid anthraquinone dyes of the series of the 1,4-diaminoanthraquinones. They conform for example to the formula XVIII



where P¹ is amino or a radical of formula



where P^2 and P^3 are independently of each other hydrogen or methyl and one of P^4 and P^5 is hydrogen or methyl and the other is hydroxysulfonyl.

- 5 The second step of the process of the present invention, step (B), comprises admixing the mixture prepared in step (A) with melamine and if desired with further phenol, substituted melamine I and formaldehyde or formaldehyde-supplying compounds, the amounts being chosen so that the molar ratio of melamines
- 10 (melamine and (a)) to (b) is within the range from 1:1.15 to 1:4.5, preferably from 1:1.8 to 1:3.0, the pigment or dye is present in an amount within the range from 0.01 to 5, preferably from 0.1 to 2, % by weight, based on melamine and (a) and (b), and the phenol being present in an amount within the range from 0 to
- 15 5, preferably from 0.2 to 2, mol%, based on melamine and (a) and (b).

- When fibers are to be produced, it is particularly preferable for the amount of substituted melamine I (component (a)) to be within
- 20 the range from 1 to 50, preferably from 5 to 15, very particularly preferably from 7 to 12, mol%, based on the sum total of melamine and substituted melamine I, and preferably for from 0.1 to 9.5, particularly preferably from 1 to 5, mol%, based on melamine and (a) and (b), of one of the above-recited phenols
- 25 or mixtures thereof to be used.

- The entire mixture is then condensed in a conventional manner as described for example in EP-A 523 485, EP-A 355 760 or Houben-Weyl, vol. 14/2, Georg Thieme Verlag, Stuttgart, 1963, pp.
- 30 357.

The reaction temperatures are generally chosen to be within the range from 20 to 150°C, preferably from 40 to 140°C.

- 35 The reaction pressure is generally not critical. It is generally within the range from 100 to 500 kPa, preferably 100 to 300 kPa.

- The reaction can be carried out with or without solvent. When an aqueous formaldehyde solution is used, generally no solvent is
- 40 added. When formaldehyde bound in solid form is used, the solvent used is normally water and the amount used generally ranges from 5 to 40, preferably from 15 to 25, % by weight, based on the total amount of monomers used.

- 45 Furthermore, the polycondensation is generally carried out in a pH range above 7. Preference is given to the pH range from 7.5 to

10.0, particularly preferably from 8 to 10.

In addition, the reaction mixture may have added to it small amounts of customary additives such as alkali metal sulfites, for example sodium disulfite and sodium sulfite, alkali metal formates, for example sodium formate, alkali metal citrates, for example sodium citrate, phosphates, polyphosphates, urea, dicyandiamide or cyanamide. They can be added as pure individual compounds or as mixtures with one another, in each case without a solvent or as aqueous solutions, before, during or after the condensation reaction.

Other modifiers are amines and also amino alcohols such as diethylamine, ethanolamine, diethanolamine or 2-diethylaminoethanol.

Further possible additives include fillers, emulsifiers and blowing agents.

The fillers used can be for example fibrous or pulverulent inorganic reinforcing agents or fillers such as glass fibers, metal powders, metal salts or silicates, for example kaolin, talc, baryte, quartz or chalk. Emulsifiers used are generally the customary nonionic, anionic or cationic organic compounds having long-chain alkyl radicals. When processing the uncured resins into foams the blowing agent used can be for example pentane.

The polycondensation can be carried out continuously or batchwise, for example in an extruder (see EP-A-355 760), in a conventional manner.

The production of articles by curing the condensation products of the present invention is customarily effected by addition of small amounts of acids such as formic acid, sulfuric acid or ammonium chloride.

To produce fibers, the melamine resin of the present invention is generally spun in a conventional manner, for example after addition of a curing agent, at room temperature in a rotospinning apparatus and subsequently the uncured fibers are cured in a heated atmosphere, or the spinning takes place in a heated atmosphere with simultaneous evaporation of the water used as solvent and curing of the condensate. Such a process is described in detail in DE-A 23 64 091.

Webs are generally produced from waddings by needling in a conventional manner. The waddings are generally produced by customary methods, for example on a roller card.

- 5 The fibers and webs colored according to the present invention are preferably used in occupational safety and fire protection, for example for manufacturing boilersuits (disadvantage to date: flameproofed cotton loses its flame resistance on repeated washing), wall coverings (for example for public buildings in
10 which flame resistance is of paramount importance) and also more lightweight clothing for firefighters.

- In a preferred embodiment, black covering webs and fabrics are manufactured for engine compartment insulation. The advantages
15 over the corresponding prior art webs are higher thermal stability (sustained use temperature resistance at about 200°C), the low flammability and also the fact that, unlike other fibers and webs, no flameproofing is required.

- 20 The advantages of the process of the present invention reside in making available homogeneously colored melamine-formaldehyde condensation products which, in particular on spinning into fibers, do not form fisheyes.

- 25 Example 1 (condensation resin without added color)

A mixture of 1871 g of melamine, 620 g of an 80% strength by weight mixture of 10 mol% of mono-, 50 mol% of bis- and 40 mol% of trishydroxyoxapentylmelamine, 472.8 g of paraformaldehyde,
30 38.2 g of phenol and 15.4 ml of diethylethanolamine was condensed at 98°C in the course of 150 min to a viscosity of 500 P·as. Following addition of 1% by weight of formic acid, the resin was spun in a conventional manner.

- 35 Example 2 (batch condensation resin)

95 g of RCC class pigment grade carbon black (DEGUSSA) were finely dispersed over 30 min by means of an Ultraturax in a mixture of 1128.8 g of 40% strength by weight formaldehyde, 633 g
40 of an 80% strength by weight mixture of 10 mol% of mono-, 50 mol% of bis- and 40 mol% of trishydroxyoxapentylmelamine, followed by the addition of 1746.4 g of melamine, 472.8 g of paraformaldehyde, 38.2 g of phenol, 15.4 ml of diethylethanolamine and 185 g of water. A pH of 9.4 was set with
45 25% strength by weight NaOH solution. The mixture was condensed

at 98°C to a viscosity of 250 Pa·s and then immediately cooled down to room temperature.

Solids content (theor.): 77%

5 Final viscosity: 430 Pa·s

The black condensation resin was mixed with a colorless condensation resin (see Example 1) in a ratio of 1:5 and spun in a conventional manner.

10

Example 3

17.2 g of Pigment Red 3 (C.I. 12120) were finely dispersed over 30 min by means of an Ultraturax in a mixture of 733 g of 40% strength by weight formaldehyde and 411 g of an 80% strength by weight mixture of 10 mol% of mono-, 50 mol% of bis- and 40 mol% of trishydroxyoxapentylmelamine, followed by the addition of 1134 g of melamine, 307 g of paraformaldehyde, 24.8 g of phenol, 5.0 ml of diethylethanolamine and 107 g of water. A pH of 8.9 was set with 25% strength by weight NaOH solution. The mixture was condensed at 98°C to a viscosity of 250 Pa·s and then immediately cooled down to room temperature.

Solids content (theor.): 77%

25 Final viscosity: 310 Pa·s

The orange condensation resin was spun in a conventional manner.

Example 4

30

8.2 g of Pigment Yellow 183 (C.I. 18792) were finely dispersed over 30 min by means of an Ultraturax in a mixture of 733 g of 40% strength by weight formaldehyde and 411 g of an 80% strength by weight mixture of 10 mol% of mono-, 50 mol% of bis- and 40 mol% of trishydroxyoxapentylmelamine, followed by the addition of 1134 g of melamine, 307 g of paraformaldehyde, 24.8 g of phenol, 5.0 ml of diethylethanolamine and 107 g of water. A pH of 8.9 was set with 25% strength by weight NaOH solution. The mixture was condensed at 98°C to a viscosity of 250 Pa·s and then immediately cooled down to room temperature.

Solids content (theor.): 77%

Final viscosity: 510 Pa·s

45 The yellow condensation resin was spun in a conventional manner.

Example 5

8.2 g of Pigment Blue (15:3) (C.I. 74160) were finely dispersed over 30 min by means of an Ultraturax in a mixture of 733 g of 5 40% strength by weight formaldehyde and 411 g of an 80% strength by weight mixture of 10 mol% of mono-, 50 mol% of bis- and 40 mol% of trishydroxyoxapentylmelamine, followed by the addition of 1134 g of melamine, 307 g of paraformaldehyde, 24.8 g of phenol, 5.0 ml of diethylethanolamine and 107 g of water. A pH of 10 8.9 was set with 25% strength by weight NaOH solution. The mixture was condensed at 98°C to a viscosity of 225 Pa·s and then immediately cooled down to room temperature.

Solids content (theor.): 77%

15 Final viscosity: 495 Pa·s

The blue condensation resin was spun in a conventional manner.

Example 6 (without aqueous formaldehyde, masterbatch)

20

90 g of RCC class pigment grade carbon black (DEGUSSA) were finely dispersed over 30 min by means of an Ultraturax in a mixture of 662 g of an 80% strength by weight mixture of 10 mol% of mono-, 50 mol% of bis- and 40 mol% of trishydroxyoxapentyl- 25 melamine and 704 g of water, followed by the addition of 1814.4 g of melamine, 960.8 g of paraformaldehyde, 39.7 g of phenol, 8.0 ml of diethylethanolamine. A pH of 8.8 was set with 25% strength by weight NaOH solution. The mixture was condensed at 98°C to a viscosity of 660 Pa·s and then immediately cooled down 30 to room temperature.

Solids content (theor.): 77%

Final viscosity: 690 Pa·s

35 The black condensation resin was mixed with a colorless condensation resin (see Example 1) in a ratio of 1:5 and spun in a conventional manner.

Example 7

40

Colorless condensation resin of Example 1 was admixed with 2% by weight of a curing agent mixture (mixture of 35% strength by weight formic acid, 2% by weight of an 80% strength by weight mixture of 10 mol% of mono-, 50 mol% of bis- and 40 mol% of 45 trishydroxyoxapentylmelamine and 20% by weight of RCC class

40

pigment grade carbon black from Degussa, intensively mixed and subsequently spun.

The viscosity measurements were carried out with a cone-plate viscometer (from Epprecht Instruments & Controls), measuring cone "type D", at a temperature of 20°C and a shear gradient of 20/sec.

The fibers were spun by the process described in DE-A-23 64 091.

10 Example 8

a) To determine the thermal stability, DIN 53 857 was followed to test a fabric produced from the fibers of Example 2 at various temperatures. The results are given in the Table below.


b) For comparison, a fabric composed of preoxidized polyacrylonitrile (SIGRAFIL® from Sigri) was tested similarly to (a). The result is given in the Table below.

Table - Thermal stability

Fiber type	Residence time	Temperature	Breaking strength (rel. to breaking strength at start of test)
Black fibers of Example 2	6 h	250°C	110%
Black fibers of Example 2	1 h	300°C	110%
SIGRAFIL®	6 h	250°C	50%
SIGRAFIL®	1 h	300°C	0%

We claim:

1. A process for preparing colored melamine-formaldehyde
 5 condensation products by mixing pigments or dyes into a reaction mixture comprising starting compounds for preparing the melamine-formaldehyde condensation products, which comprises (A) dispersing a mixture consisting essentially of
 10 (a) a substituted melamine of the formula I



I,

- 15 where X^1 , X^2 and X^3 are each selected from the group consisting of $-\text{NH}_2$, $-\text{NHR}^1$ and $-\text{NR}^1\text{R}^2$, and X^1 , X^2 and X^3 are not all $-\text{NH}_2$, and R^1 and R^2 are each selected from the group consisting of hydroxy- C_2 - C_{10} -alkyl,
 20 hydroxy- C_2 - C_4 -alkyl-(oxa- C_2 - C_4 -alkyl) $_n$, where n is from 1 to 5, and amino- C_2 - C_{12} -alkyl, or mixtures of melamines I, and
 25 (b) if desired, formaldehyde or formaldehyde-supplying compounds in a molar ratio of formaldehyde to melamines I within the range from 40:1 to 0,
 30 (c) a pigment or dye, and
 (d) if desired, phenol, unsubstituted or substituted by radicals selected from the group consisting of
 35 C_1 - C_9 -alkyl and hydroxyl, C_1 - C_4 -alkanes substituted by 2 or 3 phenol groups, di(hydroxyphenyl) sulfones or mixtures thereof,

the pigment or dye being added in an amount within the range from 0.01 to 30% by weight, based on (a) and (b), and the
 40 phenol in an amount within the range from 0 to 5 mol%, based on (a) and (b),

by intensive stirring until there are no longer any pigment
 45 agglomerates $\geq 1 \mu\text{m}$,

and then



(B) admixing the mixture prepared in (A) with melamine and if desired with further phenol, substituted melamine I and formaldehyde or formaldehyde-supplying compounds, the amounts being chosen so that the molar ratio of melamines (melamine and (a)) to (b) is within the range from 1:1.15 to 1:4.5, the pigment or dye is present in an amount within the range from 0.01 to 5% by weight, based on melamine and (a) and (b), and the phenol is present in an amount within the range from 0 to 5 mol%, based on melamine and (a) and (b), and then condensing in a conventional manner.

2. A process as claimed in claim 1 wherein the dye used belongs to the class of the azo dyes, anthraquinone dyes, coumarin dyes or methione or azamethine dyes.

3. Colored melamine-formaldehyde condensation products obtainable by the process of claim 1 or 2.

4. The use of the colored melamine-formaldehyde condensation products of claim 3 for producing colored articles, in particular fibers and webs.

5. Colored articles, in particular fibers and webs, obtainable by the use of claim 4.

6. The use of a black web as claimed in claim 5 for manufacturing covering webs and fabrics as engine compartment insulation.

