

ABSTRACT

[PROBLEM] To provide a flame-retardant polyamide resin composition which has flame retardancy at a UL94V-0 level in a wide range of thickness, causes less bleeding of a flame retardant, and is also excellent in heat discoloration resistance, moldability, snap-fit properties of parts, and the like. [SOLUTION] A flame-retardant polyamide resin composition characterized by: containing a polyamide resin (A) and a melamine cyanurate (B), containing 90 to 98 parts by mass of the polyamide resin (A), and 2 to 10 parts by mass of the melamine cyanurate (B) based on a total of 100 parts by mass of the components (A) and (B), and the polyamide resin (A) contains 55 to 85% by mass of a polyamide 66 resin (A1) and 15 to 45% by mass of a polyamide 6 resin (A2), and containing 0.01 to 1 parts by mass of a phosphorus-based antioxidant (C), 0.01 to 1 parts by mass of a hindered phenol-based antioxidant (D), and 0.1 to 1 parts by mass of a fatty acid, and metal salt-based lubricant (E) having 22 or less carbon atoms based on a total of 100 parts by mass of the components (A) and (B).