CLAIMS

1. A waterborne basecoat composition comprising 20 to 30 parts by weight of an acrylic resin, 5 to 10 parts by weight of a polyurethane dispersion resin, 1 to 10 parts by weight of an acrylic urethane dispersion resin, 0.1 to 5 parts by weight of a urethane resin, 1 to 5 parts by weight of a melamine-based curing agent and 1 to 5 parts by weight of an oxazoline-based curing agent,

wherein the polyurethane dispersion resin has a viscosity at 25℃ of 10 to 50 cps, and

wherein the urethane resin has a viscosity at 25℃ of 2,000 to 4,000 cps.

2. The waterborne basecoat composition according to claim 1, wherein the acrylic resin has a hydroxyl value (OHv) of 5 to 50 mgKOH/g, an acid value (Av) of 5 to 50 mgKOH/g, a glass transition temperature (Tg) of -30 to 30°C, and a viscosity at 25°C of 20 to 600 cps.

3. The waterborne basecoat composition according to claim 1, wherein the polyurethane dispersion resin has a solid content (NV) of 20 to 50 wt% based on the total weight of the dispersion resin.

4. The waterborne basecoat composition according to claim 1, wherein the acrylic urethane dispersion resin has a viscosity at 25°C of 10 to 90 cps, a glass transition temperature (Tg) of -30 to 30°C, an acid value (Av) of 1 to 25 mgKOH/g, and the solid content (NV) of 20 to 50 wt% based

on a total weight of the dispersion resin.

5. The waterborne basecoat composition according to claim 1, wherein the urethane resin is a urethane diol-based compound and has a hydroxyl value of 200 to 500 mgKOH/g, and the solid content of 80 to 95 wt% based on the total weight of the resin.