

- 1 -

**SYSTEMS AND METHODS FOR THE HIGH TEMPERATURE
APPLICATION OF PUMPABLE FIBROUS REFRACTORY MATERIAL**

FIELD OF THE INVENTION

5 The present invention relates generally to systems and methods whereby fibrous refractory material may be applied onto surfaces of high temperature process vessels while at or near their operational high temperatures.

BACKGROUND AND SUMMARY OF THE INVENTION

10 High temperature process vessels (e.g., furnaces, kilns, smelters and the like) are employed in a variety of industries. Typically, the wall surfaces of such high temperature process vessels have an internal coating or lining formed of a solid high temperature refractory material. Such internal refractory coatings or linings may sometimes need to be repaired, especially during the latter part of their operational duty cycles.

15 One well known technique to repair refractory wall surfaces of high temperature process vessels while at or near their high operational temperatures is colloquially referred to as "ceramic welding". More specifically, ceramic welding techniques are carried out while the refractory lining is still hot so as to minimize downtime of the process vessel and to preclude cracking of the lining which might occur on cooling
20 below its operational temperatures. In ceramic welding, a stream of welding particles (usually a particulate mixture of metals and metal oxides) is propelled in a stream of a gaseous fluid, preferably air, through a fluid (typically water) cooled elongate lance. The particles impinge on
25 the area of the refractory lining to be welded and, due to the elevated

- 2 -

temperature of such lining, the particles fuse to form a ceramic weld thereat. In use, the lance is inserted into the process vessel while at or near its high operational temperatures, for example, at or near several hundreds of degrees Fahrenheit (e.g., about 500⁰F) to up to several thousands of degrees Fahrenheit (e.g., from 1000 to up to about 3000⁰F).
5 The operator physically holds the proximal end of the lance outside the process vessel, and manipulates the lance as to position the distal end adjacent the area in need of welding. The operator is therefore shielded from the extreme high temperatures existing within the process vessel,
10 but is nonetheless capable of directing the stream of particulates toward the refractory lining inside the vessel by virtue of the liquid-cooled lance. (See generally, U.S. Patent No. 3,684,560, the entire content of which is expressly incorporated hereinto by reference.)

Some refractory linings are fibrous structures which have, prior to
15 the present invention, not been repaired using ceramic welding or other hot repair techniques. In this regard, unlike the particulate materials which can be entrained in pressurized gas and propelled through the thermally protected lance, the precursor fibrous refractory material is typically in the form of a relatively viscous pumpable paste material. As
20 such, the material can only be atomized just prior to being applied onto a surface. For such reason, fibrous refractory materials have previously been applied to process vessel surfaces while cold.

It would therefore be highly desirable if pumpable viscous (e.g., paste-like) fibrous refractory materials could be applied onto the internal
25 surfaces while hot (i.e., while the process vessel is at or near its high operational temperatures). It is towards providing such techniques and systems that the present invention is directed.

- 3 -

Broadly, the present invention is embodied in systems and methods whereby pumpable viscous fibrous material may be applied onto surfaces of high temperature process vessels while hot (i.e., while at or near such vessels' high operational temperatures of several hundreds up to several thousands of degrees Fahrenheit).

More specifically, according to a preferred system for repairing fibrous refractory on walls of a high temperature process vessel according to the present invention, there are provided a lance having a nozzle structure at a distal end thereof, and a pump system for pumping a pumpable fibrous refractory material to the nozzle. The lance has length sufficient to allow the lance to be inserted into the high temperature process vessel so that the nozzle structure is adjacent an area in need of repair while an operator holds a proximal end thereof outside the vessel.

Most preferably, the lance of the present invention will include a material supply tube in communication with the nozzle structure for directing the pumpable fibrous material from the pump system to the nozzle structure. Inlet and discharge cooling liquid conduits are provided in the lance to allow circulation of a coolant (e.g., water) through the lance to protect the lance from high temperatures within the process vessel. Importantly, an atomizing tube is provided as a component part of the lance so as to be in thermal communication therewith. The atomizing tube has an inlet at the proximal end of the lance so as to be positioned outside the process vessel, and a discharge end at which fluid communicates with the material supply tube adjacent the nozzle structure. Introduction of an atomizing gas through the tube will therefore atomize the fibrous pumpable material upon discharge through the nozzle structure.

- 4 -

In use, according to the method of repairing a fibrous refractory wall of a high temperature process vessel according to the present invention, a protective liquid-cooled lance having an atomizing tube in thermal communication therewith is inserted into the process vessel while
5 the process vessel is at or near its high operational temperature so that a nozzle structure of the lance at a distal end thereof is positioned adjacent to an area of the process vessel wall in need of repair, and so that the lance may be manipulated from outside the process vessel during repair of the wall thereof. A viscous fibrous refractory material may then be
10 pumped from a source thereof from the proximal end of the lance to the nozzle structure at the distal end of the lance, while an atomizing gas is directed through the atomizing tube. In such a manner, the atomizing gas causes the flowable fibrous refractory material to be discharged from the nozzle structure of the lance in the form of an atomized spray.
15 Manipulating the lance from outside the process vessel will thereby cause the atomized spray of the flowable fibrous material to contact the wall of the process vessel thereby repairing the same.

These, as well as other, aspects and advantages of the present invention will become more clear from the following detailed description of
20 the preferred exemplary embodiments thereof.

BRIEF DESCRIPTION OF THE ACCOMPANYING DRAWINGS

Reference will hereinafter be made to the accompanying drawings, wherein like reference numerals throughout the various FIGURES denote like structural elements, and wherein;

- 5 -

FIGURE 1 is a schematic representation of a representative embodiment of a system in accordance with the present invention in use to repair the fibrous refractive lining of a high temperature process vessel;

5 FIGURE 2 is cross-sectional view of one embodiment of a liquid-cooled lance in accordance with the present invention;

FIGURE 3 is cross-sectional view of the lance depicted in FIGURE 2 as taken along line 3-3 therein;

FIGURE 4 is a cross-sectional view of another embodiment of a liquid-cooled lance in accordance with the present invention; and

10 FIGURE 5 is a cross-sectional view of the lance depicted in FIGURE 4 as taken along line 5-5 therein.

DETAILED DESCRIPTION OF THE INVENTION

An exemplary system 10 for applying a pumpable viscous fiber-containing refractory material onto interior wall surfaces of a high temperature process vessel 12 while "hot" (i.e., while the vessel 12 is at or
15 near its high operational temperatures) is depicted in accompanying FIGURE 1. The system 10 generally includes a fluid-cooled lance 14, a source 16 of pumpable viscous fibrous refractory material, and a pump 18 to transfer the material from the source 16 thereof to an material inlet tube
20 14-1 at the proximal end of the lance 14.

Virtually any gas or liquid coolant may be employed to thermally protect the lance 14. Preferably, the coolant fluid is water, but any other coolant gas or liquid may be employed as may be desired for the particular repair operation. For convenience, water will hereinafter be
25 referenced as the coolant and thus the lance 14 will hereinafter

- 6 -

sometimes be referred to as "water-cooled" as use of a water as a coolant is typically preferred.

At its proximal end, the lance 14 also includes an inlet conduit arm 14-2 for introducing cooling water into the lance 14, and a discharge conduit arm 14-3 to allow the cooling water to be discharged therefrom. An atomizing line 14-4 traces the lance 14 along its length to allow pressurizing air to be directed to a distally located atomizing nozzle structure 14-5. As will be discussed in greater detail below, the distal nozzle 14-5 of the lance 14 allows atomized fibrous material to be sprayed onto the interior wall surfaces of the process vessel 12.

The lance 14 depicted in FIGURE 1 is shown in greater detail in accompanying FIGURES 2 and 3. In this regard, the lance 14 is formed generally of concentrically disposed inner and outer cooling tubes 20, 22 which collectively and concentrically surround material supply tube 24. The inner and outer cooling tubes 20, 22 are respectively fluid connected to the inlet and outlet conduit arms 14-2 and 14-3, while the material supply tube 24 is fluid-connected to the material inlet 14-1. As noted briefly above, the lance 14 is of sufficient length to allow the operator to stand physically outside the process vessel 12 during operation, while permitting the atomized pumpable material to be applied to the desired locations on the interior wall surfaces of the vessel.

The cooling tubes 20, 22 and material supply tube 24 are blocked at their distalmost ends by means of plug member 25. Cooling water flow in the tubes 20, 22 thus communicates respectively with the inner and outer stub tubes 20-1, 22-1, while material flow in the supply tube 24 communicates with the material stub tube 24-1 which is connected to the nozzle plug 26 so that material may be expelled through the nozzle

- 7 -

opening 26-1. The inner cooling stub tube 20-1 terminates proximally of the nozzle plug 26. As such, cooling water introduced into the lance via the conduit arm 14-2 flows in the annular space between the inner tube 20 and the material supply tube 24, and is redirected into the inner stub tube 20-1. The cooling water then flows into the annular space defined between the inner and outer stub tubes 20-1, 20-2 by virtue of the former terminating in advance of the nozzle plug 26. As such, the cooling water is returned to the discharge conduit arm 14-3 within the annular space defined between the inner and outer cooling tubes 20, 22.

Important to the present invention is the presence of the rigid atomizing line 14-4 which is physically fixed to, and hence is in thermal communication with, the outer cooling tube 22. Thus, the atomizing air within the line 14-4 is cooled along its entire length by virtue of the cooling water circulating within the annular space between the inner and outer cooling tubes 20, 22, respectively (i.e., since the tube 14-4 is in thermal communication with the outer tube 22). The terminal end 14-4a of the tube 14-4 is redirected through the plug 25 so as to be disposed concentrically within the material supply stub tube 24-1. As such, the pumpable fibrous material being supplied to the stub tube 24-1 via the inlet tube 24 is atomized by the pressurized air discharged from the terminal end 14-4a of tube 14-4 and thereby sprayed from the nozzle opening 26-1 of the nozzle plug 26 onto the wall of the vessel 12. A valve 14-4b is preferably provided at the proximal portion of the lance 14 so as to allow the operator to control the atomization of the fibrous material.

An alternative embodiment of a lance 30 in accordance with the present invention is depicted in accompanying FIGURES 4 and 5. In this regard, it will be observed that the lance 14 depicted in FIGURES 2 and 3 is especially useful in directing an atomized spray of pumpable fibrous

- 8 -

material laterally (e.g., at a right angle) relative to the lance's elongate axis, whereas the lance 30 allows the atomized pumpable fibrous material to be sprayed generally in the same direction as the lance's elongate axis. As such, the lances 14, 30 may be used as desired to apply the pumpable
5 fibrous material onto discrete portions of the interior walls of the process vessel 12.

Similar to the lance 14 described previously, the lance 30 depicted in FIGURES 4 and 5 likewise has a material inlet tube 30-1 (similar to the tube 14-1), and cooling water inlet and outlet conduits 30-2 and 30-3
10 (similar to the conduits 14-2, 14-3, respectively). The material inlet tube 30-1 is fluid connected to a material supply tube 32 which is concentrically surrounded by a cooling water outlet tube 34 fluid-connected to the water inlet conduit 30-2. Multiple cooling water supply tubes 36a, 36b and 36c are positioned physically within the annular space defined between the
15 material supply tube 32 and the cooling water outlet tube 34 (see FIGURE 5).

Cooling water supplied into the inlet conduit 30-2 thus enters the proximal ends of the tubes 36a-36c. (It will be appreciated in this regard that, because of the cross-sectioning of the lance 30 in FIGURE 4, only
20 the tubes 36a and 36b are visible therein.) Since the terminal ends of tubes 36a-36c terminate proximally of the nozzle plug 38 at the distalmost end of the lance 30, the cooling water will then flow within the annular space defined between the material supply tube 32 and the cooling water outlet tube 34, and then into the cooling water outlet conduit 30-3

25 The atomizing line 40 is, like the tubes 36a-36c, disposed physically in the annular space defined between the material supply tube 32 and the cooling water outlet tube 34. Thus, the atomizing line 40 is in

- 9 -

direct thermal communication with the cooling water which flows in such annular space thereby protecting the same from the high temperature environment within the process vessel 12. The distal end 40-1 of the atomizing line 40 projects into the material supply tube 32 proximally
5 upstream of the nozzle plug 38. Most preferably, the distal end 40-1 of the atomizing line 40 is aligned coaxially with the nozzle opening 38-1 and the elongate axis of the lance 30. A valve 42 is preferably provided in the atomization tube 40 at the proximal portion of the lance 30 so as to allow the operator to control the atomization of the fibrous material.

10 The particular pumpable fibrous material that may be handled by the systems and techniques of the present invention is not critical. A variety of pumpable refractory fibrous materials are known in the art and commercially available from a number of sources. For example, the pumpable fibrous materials commercially available from Unifrax
15 Corporation of Niagara Falls, New York may be employed successfully. In general, such pumpable fibrous materials have a putty-like consistency (e.g., a viscosity of about _____ cP or greater) with a wet density of between about 65 to about 90 lb/ft³ (typically between about 70 to about 85 lb/ft³) containing between about 20 to about 60% solids (fibers).

20 While the invention has been described in connection with what is presently considered to be the most practical and preferred embodiment, it is to be understood that the invention is not to be limited to the disclosed embodiment, but on the contrary, is intended to cover various modifications and equivalent arrangements included within the spirit and
25 scope of the appended claims.

- 10 -

CLAIMS:

1. A system for repairing fibrous refractory on walls of a high temperature process vessel comprising:
 - a lance having a nozzle structure at a distal end thereof, and
 - a pump system for pumping a pumpable fibrous refractory material to the nozzle, wherein
 - said lance has length sufficient to allow the lance to be inserted into the high temperature process vessel so that the nozzle structure is adjacent an area in need of repair while an operator holds a proximal end thereof outside the vessel, and wherein
 - said lance includes:
 - (i) a material supply tube in communication with said nozzle structure for directing the pumpable fibrous material from the pump system to the nozzle structure,
 - (ii) inlet and discharge conduits to allow circulation of a coolant through the lance to protect the lance from high temperatures within the process vessel, and
 - (iii) an atomizing tube having an inlet at the proximal end of the lance so as to be positioned outside the process vessel, and a discharge end which fluid communicates with the material supply tube adjacent the nozzle structure so as to atomize the fibrous pumpable material upon discharge through the nozzle structure.

- 11 -

2. The system of claim 1, wherein said atomizing tube is affixed to a surface of one of said inlet and discharge conduits so as to be in thermal communication therewith.

3. The system of claim 1 or claim 2, wherein said material supply tube is concentrically positioned within said inlet conduit so as to define an annular space therebetween, and wherein said atomizing tube is positioned within said annular space.

4. The system of any preceding claim, wherein said nozzle structure is positioned so as to direct a stream of atomized pumpable fibrous refractory material laterally relative to the lance.

5. The system of any preceding claim, wherein said nozzle structure is positioned so as to direct a stream of atomized pumpable fibrous refractory material longitudinally relative to the lance.

6. A thermally protected lance for repairing fibrous refractory on walls of a high temperature process vessel comprising:

a tubular lance structure of sufficient length between proximal and distal ends thereof to allow insertion of the tubular lance structure into a high temperature process vessel while at or near its operational temperature so that the distal end of the tubular lance structure is adjacent a site on a wall of the process vessel to be repaired while allowing an operator of the lance to manipulate the same outside the process vessel during repair thereof;

- 12 -

a supply tube within the tubular lance structure for supplying a pumpable fibrous refractory material to the distal end of the lance; and

an atomizing tube in thermal contact with the tubular lance structure along the length thereof so as to be thermally protected thereby from the high operational temperature of the process vessel for providing an atomizing gas to the distal end of the lance proximally of the distal end of the tubular lance structure to thereby cause an atomized spray of the pumpable fibrous refractory material to be discharged therefrom and onto the walls of the process vessel.

7. The lance of claim 6, further comprising inlet and discharge coolant conduits to allow circulation of a coolant through the lance to protect the lance from high temperatures within the process vessel.

8. The lance of claim 7, wherein said atomizing tube is affixed to a surface of one of said inlet and discharge coolant conduits so as to be in thermal communication therewith.

9. The lance of claim 7 or claim 8, wherein said material supply tube is concentrically positioned within said inlet coolant conduit so as to define an annular space therebetween, and wherein said atomizing tube is positioned within said annular space.

10. The lance of any one of claims 7 to 9, further comprising a nozzle structure at said distal end of said tubular lance structure.

- 13 -

11. The lance of claim 10, wherein said nozzle structure is positioned so as to direct a stream of atomized pumpable fibrous refractory material laterally relative to the lance.

12. The lance of claim 10 or claim 11, wherein said nozzle structure is positioned so as to direct a stream of atomized pumpable fibrous refractory material longitudinally relative to the lance.

13. A method of repairing a fibrous refractory wall of a high temperature process vessel, comprising the steps of:

- (a) inserting a thermally protected lance having an atomizing tube in thermal communication therewith into the process vessel while said process vessel is at or near its high operational temperature so that a nozzle structure of the lance at a distal end thereof is positioned adjacent to an area of the process vessel wall in need of repair, and so that the lance may be manipulated from outside the process vessel during repair of the wall thereof;
- (b) pumping a viscous fibrous refractory material from a source thereof from the proximal end of the lance to the nozzle structure at the distal end of the lance;
- (c) directing an atomizing gas through the atomizing tube so that the atomizing gas causes the fibrous refractory material to be discharged from the nozzle structure of the lance in the form of an atomized spray; and
- (d) manipulating the lance from outside the process vessel so as to cause the atomized spray of the fibrous material to

- 14 -

contact the wall of the process vessel thereby repairing the same.

14. The method of claim 13, which comprises circulating a liquid coolant through the lance within liquid inlet and discharge conduits..

15. The method of claim 14, which comprises fixing the atomizing tube to a surface of one of said liquid inlet and discharge conduits.

16. The method of claim 14 or claim 15, which comprises pumping the fibrous refractory material through a material supply tube positioned concentrically within said liquid inlet conduit, and positioning the atomizing tube within an annular space defined between said material supply tube and said liquid inlet conduit.

17. The method of any one of claims 13 to 16, which comprises directing the atomized spray of the material generally transversely relative to the lance

18. The method of any one of claims 13 to 17, which comprises directing the atomized spray of material generally axially relative to the lance.