

DESCRIPTION

PROCESS FOR PRODUCTION OF SYNDIOTACTIC PROPYLENE POLYMER
TECHNICAL FIELD

[0001]

5 The present invention relates to a process for producing
a syndiotactic propylene polymer by solution polymerizing
propylene singly or monomers, in which propylene is contained
as an essential component, in a specific solvent in the presence
of a catalyst containing a metallocene compound in a specific
10 temperature range.

TECHNICAL BACKGROUND

[0002]

 Syndiotactic polypropylene has high transparency and
surface gloss and also excellent flexibility as compared with
15 conventional isotactic polypropylene. Therefore, it is desired
that the syndiotactic propylene is used for new uses in which
conventional isotactic polypropylene cannot be used, in addition
to uses such as films, sheets, fibers, injection molded products
and blow molded products that are known to be the uses of
20 conventional isotactic polypropylene.

[0003]

 It is conventionally known that syndiotactic
polypropylene can be produced by a method of polymerization at
a low temperature using a catalyst made from a vanadium compound

and an organoaluminum compound. In the conventional method, however, the obtained polymers do not exhibit sufficient properties because the polymer does not have sufficient high syndiotacticity and sufficient high melting point.

5 [0004]

Under the circumstances, a method for producing syndiotactic polypropylene using a polymerization catalyst comprising a metallocene compound in order to enhance syndiotacticity has been studied hard. For example, J.A.Ewen
10 and others disclose a method of polymerizing propylene syndiospecifically using a catalyst comprising isopropyl(cyclopentadienyl-1-fluorenyl)hafnium dichloride and aluminoxane (Non-patent document 1). JP-A-H4(1992)-80214 (Patent document 1) discloses that polypropylene having high
15 syndiotacticity can be produced using, as a catalyst, a metallocene compound with a specific structure having two transition metal atoms in the molecule. JP-A-H5(1993)-209019 (Patent document 2) discloses a method that a syndiotactic propylene copolymer is produced using a catalyst comprising a
20 specific aluminoxane and a metallocene compound typified by [phenyl(methyl)methylene](9-fluorenyl)(cyclopentadienyl)hafnium dichloride, at a temperature of from -40 to 150°C in a solution, in a suspension or in a gas phase. JP-A-H8(1996)-67713 (Patent document 3) discloses that a method

of producing syndiotactic polypropylene using, as a co-catalyst,
a borate and a metallocene compound such as
rac-2,2-dimethyldimethylpropylidene(1- η^5 -cyclopentadienyl)(1- η^5 -fluorenyl)dichlorozirconium, in a diluted hydrocarbon
5 suspension. WO01/19877 (Patent document 4) discloses a method
of producing syndiotactic polypropylene using a polymerization
catalyst comprising a metallocene compound having a specific
structure and methyl aluminoxane in the pamphlet. Moreover,
JP-A-2002-510358 (Patent document 5) discloses a method of
10 producing syndiotactic polypropylene by propylene bulk
polymerization using, as a catalyst, isopropylidene
(cyclopentadienyl) (3,6-di-tert-butylfluorenyl) zirconium
dichloride and methyl aluminoxane in Example 11.

[0005]

15 Any of the above known techniques does not disclose a
process for producing syndiotactic polypropylene having high
stereoregularity (syndiotacticity) and high melting point by
solution polymerization in an industrial scale.

Patent Document 1: JP-A-H4(1992)-080214

20 Patent Document 2: JP-A-H5(1993)-209019

Patent Document 3: JP-A-H8(1996)-067713

Patent Document 4: Pamphlet of WO01/019877

Patent Document 5: JP-A-2002-510358

Non-Patent Document 1: J. Am. Chem. Soc. 1988, 110, 6255

DISCLOSURE OF THE INVENTION

PROBLEMS TO BE SOLVED BY THE INVENTION

[0006]

The present invention was made in order to solve the above
5 subjects. It is an object of the present invention to provide
a process for producing a syndiotactic propylene polymer with
high polymerization activity efficiently by a solution
polymerization method without deposition of polymers excluding
a state of white turbidity of solution, and a production process
10 capable of conducting the above production continuously,
provided that these processes could not be attained
conventionally.

MEANS FOR SOLVING THE PROBLEMS

[0007]

15 Under the circumstances, the present inventors have been
earnestly studied on a process for efficiently producing a
propylene polymer having high syndiotacticity and a high melting
point, which has been desired to contribute to plastic industries
greatly. As a result, they found that when an α -olefin such as
20 propylene is solution polymerized in a specific solvent in a
specific temperature range using an olefin polymerization
catalyst comprising a specific metallocene catalyst, a
syndiotactic propylene polymer having high syndiotacticity, a
high melting point and a sufficiently high molecular weight can

be solution polymerized with good polymerization activity without deposition of polymers excluding a state of white turbidity in polymerization, not only at ordinary temperature but also in a high temperature range suitable for industrial scales, and the polymer can be also produced continuously. Thus, the present invention has been accomplished.

[0008]

That is, the present invention relates to:

a process for producing a syndiotactic propylene polymer having a syndiotactic pentad fraction (rrrr fraction), as measured by ^{13}C -NMR, of at least 85%, a melting point (T_m), as measured by DSC, of from 145°C to 170°C , and an intrinsic viscosity $[\eta]$ of 0.1 to 10 dl/g, which process comprises a step (P_1) of solution polymerizing a propylene singly or at least one monomer selected from a propylene, ethylene and an α -olefin having 4 to 10 carbon atoms at a polymerization temperature (T_R) of from 30°C to 250°C in the presence of an olefin polymerization catalyst which comprises;

(A) a bridged metallocene compound represented by the following formula (I), and

(B) at least one compound selected from

(b-1) an organoaluminum oxy compound,

(b-2) a compound capable of forming an ion pair by reaction with the metallocene compound (A), and

(b-3) an organoaluminum compound.

[0009]

[Chem. 1]



5 [0010]

In the formula (I), M is a titanium atom, a zirconium atom or a hafnium atom, Q is selected from a halogen atom, a hydrocarbon group, an anion ligand and a neutral ligand coordinatable with a lone electron pair, j is an integer of 1 to 4, R^a and R^b may be identically or differently a single nuclear or polynuclear hydrocarbon residue capable of forming a sandwich structure together with M, Y is a carbon atom or a silicon atom, and R^c and R^d may be the same or different from each other, is selected from hydrogen, a hydrocarbon group and a silicon atom-containing group and further may be bonded each other to form a ring.

10

15

EFFECT OF THE INVENTION

[0011]

According to the process for producing the syndiotactic propylene polymer of the present invention, when propylene is solution polymerized singly, or α-olefins in which propylene is contained as an essential component and are solution polymerized in a specific solvent in a specific temperature range in the

20

presence of a catalyst comprising a specific metallocene compound, an α -olefin polymer having high syndiotacticity, a high melting point and a sufficiently high molecular weight can be prepared with good polymerization activity at not only
5 ordinary temperature but also high temperatures.

[0012]

According to the process for producing the syndiotactic propylene polymer of the present invention, since solution polymerization can proceed without deposition of polymers
10 excluding a state of white turbidity of solution, the continuous production thereof can be performed.

BRIEF DESCRIPTION OF THE DRAWING

[0013]

Fig. 1 is an example showing the relation of the polymer
15 concentration, the temperature and the solution viscosity of a solution of the solvent A of syndiotactic polypropylene.

Fig. 2 is a graph that a temperature difference between an equilibrium melting temperature (T_M) and a solution polymerization temperature (T_R) is plotted to the T_R with respect
20 to Examples 1 to 8 and Comparative Examples 1 to 5. In the graph, the meanings of the marks are as follows. $\diamond$: a polymer deposited during the solution polymerization. Δ : a fine polymer deposited during the solution polymerization and the solution turned into a white-turbidity state. $\circ$: the solution polymerization

proceeded in a uniform state.

BEST MODE FOR CARRYING OUT THE INVENTION

[0014]

The process for producing a syndiotactic propylene polymer
5 according to the present invention is a process for producing
a syndiotactic propylene polymer having a syndiotactic pentad
fraction (rrrr fraction), as measured in ^{13}C -NMR, of at least
85%, a melting point (T_m), as measured in DSC, of from 145°C to
170°C, and an intrinsic viscosity $[\eta]$ of 0.1 to 10 dl/g, which
10 process comprises a step (P_1) of solution polymerizing propylene
singly or propylene and at least one monomer selected from
ethylene and an α -olefin having 4 to 10 carbon atoms at a
polymerization temperature (T_R) of from 30°C to 250°C in the
presence of an olefin polymerization catalyst which comprises;
15 (A) a bridged metallocene compound represented by the following
formula (I), and
(B) at least one compound selected from
(b-1) an organoaluminum oxy compound,
(b-2) a compound capable of forming an ion pair by reaction
20 with the metallocene compound (A), and
(b-3) an organoaluminum compound.

[0015]

[Chem. 2]



[0016]

In the formula (I), M is a titanium atom, a zirconium atom or a hafnium atom, Q is selected from a halogen atom, a hydrocarbon group, an anion ligand and a neutral ligand coordinatable with a lone electron pair, j is an integer of 1 to 4, R^a and R^b may be identically or differently a single nuclear or polynuclear hydrocarbon residue capable of forming a sandwich structure together with M, Y is a carbon atom or a silicon atom, and R^c and R^d may be the same or different from each other, is selected from hydrogen, a hydrocarbon group and a silicon atom-containing group and further may be bonded each other to form a ring.

[0017]

The production process of the present invention is characterized in that the above polymerization step (P₁) is preferably carried out continuously, and following the polymerization step (P₁), a post-treatment step (P₂) is carried out in such a way that the polymerization solution transferred from the polymerization step is optionally heated to the temperature not lower than the polymerization temperature and not higher than 250°C, and a flash procedure is carried out at a pressure of from 0.00 to 0.5 MPaG to distill away the solvent.

[0018]

With respect to the two steps for constituting the process for producing the syndiotactic propylene polymer of the present invention, namely the solution polymerization step (P_1) and the
5 post treatment step (P_2) subsequently performed after the solution polymerization step, the best mode for carrying out the present invention is described. Thereafter, the properties of the syndiotactic propylene polymer obtainable by the production process of the present invention will be described.

10 [0019]

[1] Solution polymerization step (P_1)

With respect to the step which is essential and constitutes the process for producing the syndiotactic propylene polymer of the present invention, namely the solution polymerization step
15 (P_1), the best mode for carrying out the present invention will be described together with the description of the polymerization catalyst for carrying out the step, the solution polymerization method in the presence of the polymerization catalyst, and the properties of a polymer obtainable by the solution
20 polymerization, in this order.

[0020]

[1-1] Polymerization catalyst

The polymerization catalyst of the present invention comprises (A) a metallocene compound, and (B) at least one

compound selected from (b-1) an organoaluminum oxy compound,
 (b-2) a compound capable of forming an ion pair by reacting with
 the metallocene compound (A), and (b-3) an organoaluminum
 compound. [In the following description, (A) the metallocene
 5 compound is simply referred to as "(A) component" or "metallocene
 compound", and (B) at least one compound selected from (b-1) the
 organoaluminum oxy compound, (b-2) the compound capable of
 forming an ion pair by reacting with the metallocene compound
 (A), and (b-3) the organoaluminum compound is simply referred
 10 to as "(B) component", "co-catalyst" or "co-catalyst
 component".]

[0021]

(A) Bridged metallocene compound

The bridged metallocene compound of the present invention
 15 is a bridged metallocene compound represented by the formula (I).
 In the formula (I), M is a titanium atom, a zirconium atom or
 a hafnium atom, Q is selected from a halogen atom, a hydrocarbon
 group, an anion ligand and a neutral ligand coordinatable with
 a lone electron pair, j is an integer of 1 to 4, R^a and R^b may
 20 be identically or differently a single nuclear or polynuclear
 hydrocarbon residue capable of forming a sandwich structure
 together with M, Y is a carbon atom or a silicon atom, and R^c
 and R^d may be the same or different from each other, and is an
 atom or substituent selected from hydrogen, a hydrocarbon group


and a silicon atom-containing group.

[0022]

Among the bridged metallocene compounds represented by the formula (I), from the viewpoint of their polymerization properties, availability, and excellent properties of the obtainable polymer, metallocene compounds having Cs symmetry to a center atom M are preferred, and further, a bridged metallocene compound represented by the following formula (II) is preferably used.

10 [0023]

[Chem. 3]



[0024]

In the formula (II), R^1 , R^2 , R^3 and R^4 each are selected from hydrogen and a hydrocarbon group (f1), preferably a hydrocarbon group of 1 to 20 carbon atoms (f1'), and a silicon atom-containing group (f2), more preferably a silicon atom-containing group (f2') of 1 to 20 carbon atoms.

[0025]

The hydrocarbon group (f1) is alkyl, alkenyl, alkynyl or aryl groups, which each contains only carbon and hydrogen. The hydrocarbon groups (f1) may include groups having alicyclic groups or an aromatic ring, which are obtainable by replacing any two adjacent hydrogen atoms simultaneously, and groups in which a part of hydrogen directly bonded to these carbon atoms is substituted with a hetero atom-containing hydrocarbon group replaced with a halogen atom, an oxygen-containing group, a nitrogen-containing group or a silicon atom-containing group. Examples of the hydrocarbon groups (f1') of 1 to 20 carbon atoms are linear chain hydrocarbon groups such as methyl, ethyl, n-propyl, allyl, n-butyl, n-pentyl, n-hexyl, n-heptyl, n-octyl, n-nonyl, or n-decanyl; branched hydrocarbon groups such as isopropyl, t-butyl, amyl, 3-methylpentyl, 1,1-diethylpropyl, 1,1-dimethylbutyl, 1-methyl-1-propylbutyl, 1,1-dipropylbutyl, 1,1-dimethyl-2-methylpropyl and 1-methyl-1-isopropyl-2-methylpropyl; cyclic saturated hydrocarbon groups such as cyclopentyl, cyclohexyl, cycloheptyl, cyclooctyl, norbornyl and adamantyl; cyclic unsaturated hydrocarbon groups such as phenyl, naphthyl, biphenyl, phenanthryl and anthracenyl, and their nuclear alkyl substituted groups; saturated hydrocarbon groups substituted with an aryl group such as benzyl or cumyl; hetero atom-containing hydrocarbon groups such as methoxy, ethoxy,

phenoxy, N-methylamino, trifluoromethyl, tribromomethyl, pentafluoroethyl and pentafluorophenyl.

[0026]

The silicon atom-containing groups (f2) are, for example, groups in which cyclic carbon atoms in a cyclopentadienyl group bond to silicon atoms covalently and directly, and specific examples of those are alkylsilyl group and arylsilyl group. Examples of the silicon atom-containing groups (f2') having 1 to 20 carbon atoms include trimethylsilyl group and triphenylsilyl group.

[0027]

From the viewpoint of producing the syndiotactic propylene polymer having a high stereoregularity (syndiotacticity) and a high melting point by solution polymerization in accordance with the production process of the present invention, the bridged metallocene compound represented by the formula (I) is preferably a metallocene compound having Cs symmetry. That is to say, it is preferable that R^1 and R^4 are the same atoms or the same groups, and R^2 and R^3 are the same atoms or the same groups, or are bonded to form a ring. It is more preferable that R^1 and R^4 are hydrogen atoms. It is particularly preferable that all of R^1 , R^2 , R^3 and R^4 are hydrogen atoms. Moreover, R^5 and R^{12} are the same atoms or the same groups, R^6 and R^{11} are the same atoms or the same groups, R^7 and R^{10} are the same atoms or the

same groups, and R^8 and R^9 are the same atoms or the same groups.

[0028]

R^5 , R^8 , R^9 and R^{12} are each selected from hydrogen, the hydrocarbon groups (f1), preferably the hydrocarbon groups having 1 to 20 carbon atoms (f1'), and the silicon atom-containing groups (f2), preferably the silicon atom-containing groups having 1 to 20 carbon atoms (f2'), and they may be the same or different from each other, and the adjacent groups may be bonded each other to form a ring. R^6 and R^7 are the same atoms or groups selected from hydrogen, hydrocarbon groups and silicon atom-containing groups, and may be bonded each other to form a ring. R^{10} and R^{11} are the same atoms or groups selected from hydrogen, hydrocarbon groups, and silicon atom-containing groups, and they may be bonded each other to form a ring, provided that R^6 , R^7 , R^{10} and R^{11} are not hydrogen atoms simultaneously. R^{17} and R^{18} are the same atoms or groups selected from hydrocarbon groups and silicon atom-containing groups, and may be bonded each other to form a ring.

[0029]

From the viewpoint of synthesizing the syndiotactic polypropylene having a high stereoregularity (syndiotacticity) and a high melting point by solution polymerization in accordance with the production process of the present invention, it is preferable that both R^7 and R^{10} are not hydrogen atoms, and more

preferable that all of R^6 , R^7 , R^{10} and R^{11} are not hydrogen atoms. Particularly, in the case that R^6 and R^{11} are hydrocarbon groups and the adjacent groups do not form a ring, it is preferable that [1] R^6 and R^{11} are each independently a hydrocarbon group having
5 at least two carbon atoms, more preferably three or more carbon atoms, particularly preferably four or more carbon atoms, or [2] a silicon atom-containing group. It is preferable that R^7 and R^{12} are each a hydrocarbon group having at least two carbon atoms, more preferably three or more carbon atoms, particularly
10 preferably four or more carbon atoms. Especially, R^7 and R^{12} are each a sterically bulky alkyl group or aralkyl group having 4 to 20 carbon atoms.

[0030]

When all of R^6 , R^7 , R^{10} and R^{11} are not hydrogen atoms, R^6
15 and R^{11} are each preferably an aryl group or substituted aryl group.

[0031]

R^{17} and R^{18} are each selected from the hydrocarbon groups (f1), preferably the hydrocarbon groups (f1') having 1 to 20
20 carbon atoms, or the silicon atom-containing groups (f2), preferably the silicon atom-containing groups (f2') having 1 to 20 carbon atoms, and may be the same or different from each other, and the substituents may be bonded to form a ring.

[0032]

M is a titanium atom, zirconium atom or hafnium atom, Y is a carbon atom or silicon atom, Q's are identically or differently selected from a halogen, hydrocarbon group, anion ligand and neutral ligand capable of coordinating with a lone
 5 electron pair, and j is an integer of 1 to 4.

[0033]

Specific examples of the halogen are fluorine atom, chlorine atom, bromine atom and iodine atom. Examples of the hydrocarbon group are methyl, ethyl, n-propyl, isopropyl,
 10 2-methylpropyl, 1,1-dimethylpropyl, 2,2-dimethylpropyl, 1,1-diethylpropyl, 1-ethyl-1-methylpropyl, 1,1,2,2-tetramethylpropyl, sec-butyl, t-butyl, 1,1-dimethylbutyl, 1,1,3-trimethylbutyl, neopentyl, cyclohexylmethyl, cyclohexyl and 1-methyl-1-cyclohexyl.
 15 Specific examples of neutral, conjugated or non-conjugated dienes having not more than 10 carbon atoms are s-cis or s-trans- η^4 -1,3-butadiene, s-cis or s-trans- η^4 -1,4-diphenyl-1,3-butadiene, s-cis or s-trans- η^4 -3-methyl-1,3-pentadiene, s-cis or
 20 s-trans- η^4 -1,4-dibenzyl-1,3-butadiene, s-cis or s-trans- η^4 -2,4-hexadiene, s-cis or s-trans- η^4 -1,3-pentadiene, s-cis or s-trans- η^4 -1,4-ditolyl-1,3-butadiene and s-cis or s-trans- η^4 -1,4-bis(trimethylsilyl)-1,3-butadiene. Specific examples of the anion ligand are alkoxy groups such as methoxy,

t-butoxy and phenoxy; carboxylate groups such as acetate and benzoate; and sulfonates such as mesylate and tosylate. Specific examples of the neutral ligand capable of coordinating with a lone electron pair are organic phosphoric compounds such as trimethyl phosphine, triethyl phosphine, triphenyl phosphine and diphenyl methyl phosphine; and ethers such as tetrahydrofuran, diethylether, dioxane and 1,2-dimethoxy ethane.

[0034]

10 The compounds as defined above are catalysts generally having a Cs symmetric structure.

[0035]

Specific examples of the component (A) satisfying the above definition will be shown below, but the scope of the present invention is not limited by the examples.

The examples of the component (A) include:

cyclopropylidene(cyclopentadienyl)(3,6-di-t-butylfluorenyl)zirconium	dichloride,
cyclobutylidene(cyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium	dichloride,
cyclopentylidene(cyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium	dichloride,
cyclohexylidene(cyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium	dichloride,

- cycloheptylidene(cyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride,
- dibenzylmethylenecyclopentadienyl)(3,6-di-tert-butylfluorenyl)zirconium dichloride,
- 5 dibenzylmethylenecyclopentadienyl)(octamethyloctahydrodibenzofluorenyl)zirconium dichloride,
- di-n-butylmethylenecyclopentadienyl)(2,7-dimethyl-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- di-n-butylmethylenecyclopentadienyl)(2,7-di(2,4,6-trimethylphenyl)-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- 10 di-n-butylmethylenecyclopentadienyl)(2,7-diphenyl-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- di-n-butylmethylenecyclopentadienyl)(2,7-di(3,5-dimethylphenyl)-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- 15 di-n-butylmethylenecyclopentadienyl)(2,3,6,7-tetra-tert-butylfluorenyl)zirconium dichloride,
- di-n-butylmethylenecyclopentadienyl)(2,7-di(4-methylphenyl)-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- di-n-butylmethylenecyclopentadienyl)(2,7-dinaphthyl-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- 20 di-n-butylmethylenecyclopentadienyl)(2,7-di(4-tert-butylphenyl)-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- diisobutylmethylenecyclopentadienyl)(2,7-dimethyl-3,6-di-tert-butylfluorenyl)zirconium dichloride,

- diisobutylmethylene(cyclopentadienyl) (2,7-di(2,4,6-trimethylphenyl)-3,6-di-tert-butylfluorenyl) zirconium dichloride,
- diisobutylmethylene(cyclopentadienyl) (2,7-diphenyl-3,6-di-tert-butylfluorenyl) zirconium dichloride,
- 5 diisobutylmethylene(cyclopentadienyl) (2,7-di(3,5-dimethylphenyl)-3,6-di-tert-butylfluorenyl) zirconium dichloride,
- diisobutylmethylene(cyclopentadienyl) (2,3,6,7-tetra-tert-butylfluorenyl) zirconium dichloride,
- diisobutylmethylene(cyclopentadienyl) (2,7-di(4-methylphenyl)-3,6-di-tert-butylfluorenyl) zirconium dichloride,
- 10 diisobutylmethylene(cyclopentadienyl) (2,7-dinaphthyl-3,6-di-tert-butylfluorenyl) zirconium dichloride,
- diisobutylmethylene(cyclopentadienyl) (2,7-di(4-tert-butylfluorenyl)-3,6-di-tert-butylfluorenyl) zirconium dichloride,
- 15 dibenzylmethylene(cyclopentadienyl) (2,7-dimethyl-3,6-di-tert-butylfluorenyl) zirconium dichloride [sometimes referred to as 1,3-diphenylisopropylidene(cyclopentadienyl) (2,7-dimethyl-3,6-di-tert-butylfluorenyl) zirconium dichloride, hereinafter, the second name will be omitted.],
- 20 dibenzylmethylene(cyclopentadienyl) (2,7-di(2,4,6-trimethylphenyl)-3,6-di-tert-butylfluorenyl) zirconium dichloride,
- dibenzylmethylene(cyclopentadienyl) (2,7-diphenyl-3,6-di-tert-butylfluorenyl) zirconium dichloride,
- dibenzylmethylene(cyclopentadienyl) (2,7-di(3,5-dimethylphenyl)-3,6-di-tert-butylfluorenyl) zirconium dichloride,

- 1)-3,6-di-tert-butylfluorenyl) zirconium dichloride,
 dibenzylmethylenecyclopentadienyl (2,3,6,7-tetra-tert-butyl
 fluorenyl) zirconium dichloride,
 dibenzylmethylenecyclopentadienyl (2,7-di(4-methylphenyl)-3
 5 ,6-di-tert-butylfluorenyl) zirconium dichloride,
 dibenzylmethylenecyclopentadienyl (2,7-dinaphthyl-3,6-di-ter
 tert-butylfluorenyl) zirconium
 dichloride, dibenzylmethylenecyclopentadienyl (2,7-di(4-tert
 -butylphenyl)-3,6-di-tert-butylfluorenyl) zirconium
 10 dichloride,
 diphenethylmethylenecyclopentadienyl (2,7-dimethyl-3,6-di-t
 tert-butylfluorenyl) zirconium dichloride,
 diphenethylmethylenecyclopentadienyl (2,7-diphenyl-3,6-di-t
 tert-butylfluorenyl) zirconium dichloride,
 15 di(benzhydryl)methylenecyclopentadienyl (2,7-dimethyl-3,6-d
 i-tert-butylfluorenyl) zirconium dichloride,
 di(benzhydryl)methylenecyclopentadienyl (2,7-diphenyl-3,6-d
 i-tert-butylfluorenyl) zirconium dichloride,
 di(cumyl)methylenecyclopentadienyl (2,7-dimethyl-3,6-di-ter
 20 t-butylfluorenyl) zirconium dichloride,
 di(cumyl)methylenecyclopentadienyl (2,7-diphenyl-3,6-di-ter
 t-butylfluorenyl) zirconium dichloride,
 di(1-phenethyl)methylenecyclopentadienyl (2,7-dimethyl-3,6-
 di-tert-butylfluorenyl) zirconium dichloride,

- di(1-phenyl-ethyl)methylene(cyclopentadienyl)(2,7-diphenyl-3,
6-di-tert-butylfluorenyl)zirconium dichloride,
- di(cyclohexylmethyl)methylene(cyclopentadienyl)(2,7-dimethyl-3,
6-di-tert-butylfluorenyl)zirconium dichloride,
- 5 di(cyclohexylmethyl)methylene(cyclopentadienyl)(2,7-diphenyl-3,
6-di-tert-butylfluorenyl)zirconium dichloride,
- di(cyclopentylmethyl)methylene(cyclopentadienyl)(2,7-dimethyl-3,
6-di-tert-butylfluorenyl)zirconium dichloride,
- di(cyclopentylmethyl)methylene(cyclopentadienyl)(2,7-diphenyl-3,
6-di-tert-butylfluorenyl)zirconium dichloride,
- 10 di(naphthylmethyl)methylene(cyclopentadienyl)(2,7-dimethyl-3,
6-di-tert-butylfluorenyl)zirconium dichloride,
- di(naphthylmethyl)methylene(cyclopentadienyl)(2,7-diphenyl-3,
6-di-tert-butylfluorenyl)zirconium dichloride,
- 15 di(biphenylmethyl)methylene(cyclopentadienyl)(2,7-dimethyl-3,
6-di-tert-butylfluorenyl)zirconium dichloride,
- di(biphenylmethyl)methylene(cyclopentadienyl)(2,7-diphenyl-3,
6-di-tert-butylfluorenyl)zirconium dichloride,
- (benzyl)(n-butyl)methylene(cyclopentadienyl)(2,7-dimethyl-3,
6-di-tert-butylfluorenyl)zirconium dichloride,
- 20 (benzyl)(n-butyl)methylene(cyclopentadienyl)(2,7-diphenyl-3,
6-di-tert-butylfluorenyl)zirconium dichloride,
- (benzyl)(cumyl)methylene(cyclopentadienyl)(2,7-dimethyl-3,
6-di-tert-butylfluorenyl)zirconium dichloride,

- (benzyl)(cumyl)methylene(cyclopentadienyl)(2,7-diphenyl-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- cyclopropylidene(cyclopentadienyl)(2,7-dimethyl-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- 5 cyclopropylidene(cyclopentadienyl)(2,7-diphenyl-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- cyclobutylidene(cyclopentadienyl)(2,7-dimethyl-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- cyclobutylidene(cyclopentadienyl)(2,7-diphenyl-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- 10 cyclopentylidene(cyclopentadienyl)(2,7-dimethyl-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- cyclopentylidene(cyclopentadienyl)(2,7-diphenyl-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- 15 cyclohexylidene(cyclopentadienyl)(2,7-dimethyl-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- cyclohexylidene(cyclopentadienyl)(2,7-diphenyl-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- cycloheptylidene(cyclopentadienyl)(2,7-dimethyl-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- 20 cycloheptylidene(cyclopentadienyl)(2,7-diphenyl-3,6-di-tert-butylfluorenyl)zirconium dichloride,
- dibenzylmethylene(cyclopentadienyl)(2,7-dimethyl-3,6-dimethyl-1-butylfluorenyl)zirconium dichloride,

- di-n-butylmethylenecyclopentadienyl (2,7-dimethyl-3,6-dimethyl-butylfluorenyl) zirconium dichloride,
- dibenzylmethylenecyclopentadienyl (2,7-dimethyl-3,6-dicumyl-butylfluorenyl) zirconium dichloride,
- 5 di-n-butylmethylenecyclopentadienyl (2,7-dimethyl-3,6-dicumyl-butylfluorenyl) zirconium dichloride,
- dibenzylmethylenecyclopentadienyl (2,7-dimethyl-3,6-di(trimethylsilyl)-butylfluorenyl) zirconium dichloride,
- 10 di-n-butylmethylenecyclopentadienyl (2,7-dimethyl-3,6-di(trimethylsilyl)-butylfluorenyl) zirconium dichloride,
- dibenzylmethylenecyclopentadienyl (2,7-dimethyl-3,6-diphenyl-butylfluorenyl) zirconium dichloride,
- 15 dibenzylmethylenecyclopentadienyl (2,7-dimethyl-3,6-diphenyl-butylfluorenyl) zirconium dichloride,
- dibenzylmethylenecyclopentadienyl (2,7-dimethyl-3,6-dibenzyl-butylfluorenyl) zirconium dichloride,
- 20 dibenzylmethylenecyclopentadienyl (2,7-dimethyl-3,6-dimethyl-butylfluorenyl) zirconium dichloride,
- di-n-butylmethylenecyclopentadienyl (2,7-dimethyl-3,6-dimethyl-butylfluorenyl) zirconium dichloride,
- diphenylmethylenecyclopentadienyl (2,7-dimethyl-3,6-di-tert-butylfluorenyl) zirconium dichloride,

- diphenylmethylene(cyclopentadienyl) (2,7-diphenyl-3,6-di-tert-butylfluorenyl) zirconium dichloride,
- di(p-tolyl)methylene(cyclopentadienyl) (2,7-dimethyl-3,6-di-tert-butylfluorenyl) zirconium dichloride,
- 5 di(p-tolyl)methylene(cyclopentadienyl) (2,7-diphenyl-3,6-di-tert-butylfluorenyl) zirconium dichloride,
- di(p-chlorophenyl)methylene(cyclopentadienyl) (2,7-dimethyl-3,6-di-tert-butylfluorenyl) zirconium dichloride,
- 10 di(p-chlorophenyl)methylene(cyclopentadienyl) (2,7-diphenyl-3,6-di-tert-butylfluorenyl) zirconium dichloride,
- di(m-chlorophenyl)methylene(cyclopentadienyl) (2,7-dimethyl-3,6-di-tert-butylfluorenyl) zirconium dichloride,
- di(m-chlorophenyl)methylene(cyclopentadienyl) (2,7-diphenyl-3,6-di-tert-butylfluorenyl) zirconium dichloride,
- 15 di(p-bromophenyl)methylene(cyclopentadienyl) (2,7-dimethyl-3,6-di-tert-butylfluorenyl) zirconium dichloride,
- di(p-bromophenyl)methylene(cyclopentadienyl) (2,7-diphenyl-3,6-di-tert-butylfluorenyl) zirconium dichloride,
- di(m-trifluoromethyl-phenyl)methylene
- 20 (cyclopentadienyl) (2,7-dimethyl-3,6-di-tert-butylfluorenyl) zirconium dichloride, di(m-trifluoromethyl-phenyl)methylene
- (cyclopentadienyl) (2,7-diphenyl-3,6-di-tert-butylfluorenyl) zirconium dichloride, di(p-trifluoromethyl-phenyl)methylene
- (cyclopentadienyl) (2,7-dimethyl-3,6-di-tert-butylfluorenyl) z

irconium dichloride, di(p-trifluoromethyl-phenyl)methylene
 (cyclopentadienyl) (2,7-diphenyl-3,6-di-tert-butylfluorenyl)z
 irconium dichloride, di(p-tert-butyl-phenyl)methylene
 (cyclopentadienyl) (2,7-dimethyl-3,6-di-tert-butylfluorenyl)z
 5 irconium dichloride, di(p-tert-butyl-phenyl)methylene
 (cyclopentadienyl) (2,7-diphenyl-3,6-di-tert-butylfluorenyl)z
 irconium dichloride, di(p-n-butyl-phenyl)methylene
 (cyclopentadienyl) (2,7-dimethyl-3,6-di-tert-butylfluorenyl)z
 irconium dichloride, di(p-n-butyl-phenyl)methylene
 10 (cyclopentadienyl) (2,7-diphenyl-3,6-di-tert-butylfluorenyl)z
 irconium dichloride,
 di(p-biphenyl)methylene(cyclopentadienyl) (2,7-dimethyl-3,6-d
 i-tert-butylfluorenyl) zirconium dichloride,
 di(p-biphenyl)methylene(cyclopentadienyl) (2,7-diphenyl-3,6-d
 15 i-tert-butylfluorenyl) zirconium dichloride,
 di(1-naphthyl)methylene(cyclopentadienyl) (2,7-dimethyl-3,6-d
 i-tert-butylfluorenyl) zirconium dichloride,
 di(1-naphthyl)methylene(cyclopentadienyl) (2,7-diphenyl-3,6-d
 i-tert-butylfluorenyl) zirconium dichloride,
 20 di(2-naphthyl)methylene(cyclopentadienyl) (2,7-dimethyl-3,6-d
 i-tert-butylfluorenyl) zirconium dichloride,
 di(2-naphthyl)methylene(cyclopentadienyl) (2,7-diphenyl-3,6-d
 i-tert-butylfluorenyl) zirconium dichloride,
 di(naphthylmethyl)methylene(cyclopentadienyl) (2,7-dimethyl-3

,6-di-tert-butylfluorenyl) zirconium dichloride,
 di(naphthylmethyl)methylene(cyclopentadienyl) (2,7-diphenyl-3
 ,6-di-tert-butylfluorenyl) zirconium dichloride,
 di(p-isopropylphenyl)methylene(cyclopentadienyl) (2,7-dimethy
 5 1-3,6-di-tert-butylfluorenyl) zirconium dichloride,
 di(p-isopropylphenyl)methylene(cyclopentadienyl) (2,7-dipheny
 1-3,6-di-tert-butylfluorenyl) zirconium dichloride,
 di(biphenylmethyl)methylene(cyclopentadienyl) (2,7-dimethyl-3
 ,6-di-tert-butylfluorenyl) zirconium dichloride,
 10 di(biphenylmethyl)methylene(cyclopentadienyl) (2,7-diphenyl-3
 ,6-di-tert-butylfluorenyl) zirconium dichloride,
 diphenylsilylene(cyclopentadienyl) (2,7-dimethyl-3,6-di-tert-
 butylfluorenyl) zirconium dichloride, and
 diphenylsilylene(cyclopentadienyl) (2,7-diphenyl-3,6-di-tert-
 15 butylfluorenyl) zirconium dichloride.


[0036]

Among the above compounds, it is preferred to use the
 compounds in which R^6 and R^{11} are each an aryl group such as phenyl
 group, tolyl group, t-butylphenyl group, dimethylphenyl group,
 20 trimethylphenyl group and biphenyl group, or a substituted aryl
 group because of giving a syndiotactic propylene polymer having
 a high melting point. In the examples of the present invention,
 which is to be described later, a compound used was
 dibenzylmethylene(cyclopentadienyl) (2,7-diphenyl-3,6-di-tert

-butylfluorenyl)zirconium dichloride represented by the following formula (III) in which both of R^6 and R^{11} at the 2 position and at the 7 position in the fluorenyl group are phenyl groups, both of R^7 and R^{10} at the 3 position and at the 6 position in the fluorenyl group are t-butyl groups, and both of R^{17} and R^{18} present in carbon atoms in the bridged part are benzyl groups.

[0037]

[Chem. 4]



10 [0038]

Examples of the component (A), further, may include compounds obtainable by replacing "zirconium" with "hafnium" or "titanium" in the above compounds, and bridged metallocene compounds obtainable by replacing "dichloride" with "difluoride", and bridged metallocene compounds obtainable by replacing "dibromide", "di-iodide" or "dichloride" with "dimethyl" or "methylethyl".

[0039]

The above bridged metallocene compounds (A) can be produced by a known method. The production method thereof is not particularly limited. Examples of the known production

20

method are a production method disclosed in WO2001/27124 and a method disclosed in WO2004/087775 both filed by the present applicant. These metallocene compounds may be used singly or two or more may be optionally combined for use.

5 [0040]

The polymerization catalyst of the present invention comprises (A) the metallocene compound, and (B) at least one compound selected from (b-1) the organoaluminum oxy compound, (b-2) the compound capable of forming an ion pair by reaction
10 with the metallocene compound (A), and (b-3) the organoaluminum compound. Furthermore, it is possible to optionally use a support type catalyst in which the component (A) and/or the component (B) are supported on (C) a particulate carrier, as the polymerization catalyst of the present invention. Moreover,
15 (D) the organic compound component to be described later may be optionally used simultaneously.

[0041]

(B) Component

(b-1) Organoaluminum oxy compound


20 As (b-1) the organoaluminum oxy compound of the present invention (sometimes referred to as "component (b-1)" in the following description), conventionally known aluminoxane may be used as it is.

Examples thereof may include aluminoxane represented by

the following formula (IV):

[0042]

[Chem.5]




5 [0043]

in the formula (IV), R's are each independently a hydrocarbon group of 1 to 10 carbon atom(s), and n is an integer of 2 or more, and/or may include aluminoxane represented by the following formula (V):

10 [0044]

[Chem.6]



[0045]

in the formula (V), R is a hydrocarbon group of 1 to 10 carbon atom(s), and n is an integer of 2 or more. Particularly, it is desired to use aluminoxane in which R is a methyl group, namely methylaluminoxane, and n is 3 or more, preferably at least 10. These aluminoxanes may include some organoaluminum compounds. Moreover, it is possible to suitably use organoaluminum oxy compounds as disclosed in JP-A-H2(1990)-167305, and aluminoxanes having at least two kinds of alkyl groups as

15

20


disclosed in JP-A-H2(1990)-24701 and JP-A-H3(1991)-103407.

[0046]

Furthermore, modified methyl aluminoxanes represented by the following formula (VI) can be exemplified as the
5 organoaluminum oxy compound of the present invention.

[0047]

[Chem.7]



[0048]

10 in the formula (VI), R is a hydrocarbon group of 1 to 10 carbon atom(s), and m and n are each an integer of 2 or more.

The modified methyl aluminoxanes are prepared using trimethylaluminum and alkyl aluminums except for trimethyl aluminum. Such modified methyl aluminoxanes (VI) are
15 occasionally referred to as MMAOs. MMAOs may be prepared by, for example, a method as described in USP4960878 or commercially available ones can be used as they are. For example, MMAOs of the formula (VI) in which R is an isobutyl group, prepared by using trimethyl aluminum and triisobutyl aluminum, are
20 commercially produced by Tohso Fine Chem Co., Ltd. in the trade names of MMAO or TMAO. MMAO is an aluminoxane having improved solubility to various solvents and storage stability. Specifically, MMAO has a property that it is soluble in aliphatic

hydrocarbons and alicyclic hydrocarbons different to aluminoxanes insoluble or slightly soluble in benzene, such as the compounds represented by the formulas (IV) and (V). Therefore, when there is a demand that a solvent having a high
 5 load to the environment, such as benzene or the like is not used, the above modified methyl aluminoxane is preferably used.


[0049]

(b-2) Compound capable of forming an ion pair by reacting with the bridged metallocene compound (A)

10 Examples of the compound (b-2) capable of forming an ion pair by reacting with the bridged metallocene compound (A) (hereinafter sometimes referred to as "ionizing ionic compound" or "component (b-2)") may include Lewis acid, an ionizing ionic compound, a borane compound and a carborane compound, as
 15 described in JP-A-H1(1989)-501950 and the like. Examples thereof, further, may include a heteropoly compound and an isopoly compound. The ionizing ionic compound preferably used in the present invention is a compound represented by the formula (VII).

20 [0050]

[Chem. 8]



[0051]


In the formula (VII), examples of R^{+e} are H^+ , carbenium cation, oxonium cation, ammonium cation, phosphonium cation, cycloheptyl trienyl cation and ferrocenium cation having a transition metal. R^f , R^g , R^h and R^j may be the same or different from each other and are each an organic group, preferably an aryl group.

[0052]

(b-3) Organoaluminum compound

Examples of the organoaluminum compound (b-3) for constituting the olefin polymerization catalyst (hereinafter, sometimes abbreviated to "component (b-3)" may include organoaluminum compounds represented by the following formula (VIII).

15 [0053]



In the formula, R^a and R^b may be the same or different from each other and are each a hydrocarbon group having 1 to 15 carbon atoms, preferably 1 to 4 carbon atoms, X is a halogen atom, $0 < m \leq 3$, $0 \leq n < 3$, $0 \leq p < 3$, $0 \leq q < 3$ and $m+n+p+q = 3$.

Specific examples of the component (b-3) are linear chain trialkyl aluminums such as trimethyl aluminum, triethyl aluminum, tri-n-butyl aluminum, trihexyl aluminum and trioctyl aluminum; branched trialkyl aluminums such as triisopropyl aluminum,

triisobutyl aluminum, tri-sec-butyl aluminum, tri-tert-butyl aluminum, tri-2-methylbutyl aluminum, tri-3-methylhexyl aluminum and tri-2-ethylhexyl aluminum; tricycloalkyl aluminums such as tricyclohexyl aluminum and tricyclooctyl aluminum;

5 triaryl aluminums such as triphenyl aluminum and tritolyl aluminum; dialkylaluminum hydrides such as diisopropyl aluminum hydride and diisobutyl aluminum hydride; alkenyl aluminums such as isoprenyl aluminums represented by the formula $(i-C_4H_9)_xAl_y(C_5H_{10})_z$ (wherein x, y and z are each a positive number and $z \leq 2x$) and the like; alkyl aluminum alkoxides such as isobutyl

10 aluminum methoxide and isobutyl aluminum ethoxide; dialkyl aluminum alkoxides such as dimethyl aluminum methoxide, diethyl aluminum ethoxide and dibutyl aluminum butoxide; alkyl aluminum sesqui-alkoxides such as ethyl aluminum sesquiethoxide and butyl

15 aluminum sesquibutoxide; partially alkoxylated alkyl aluminums having an average composition represented by the formula $R^a_{2.5}Al(OR^b)_{0.5}$ and the like;

alkyl aluminum aryloxides such as diethyl aluminum phenoxide and diethyl aluminum (2,6-di-t-butyl-4-methyl

20 phenoxide); dialkyl aluminum halides such as dimethyl aluminum chloride, diethyl aluminum chloride, dibutyl aluminum chloride, diethyl aluminum bromide and diisobutyl aluminum chloride; alkyl aluminum sesquihalides such as ethyl aluminum sesquichloride, butyl aluminum sesquichloride and ethyl aluminum sesquibromide;

partially halogenated alkyl aluminums of alkyl aluminum dihalides, such as ethyl aluminum dichloride, or the like; dialkyl aluminum hydrides such as diethyl aluminum hydride, and dibutyl aluminum hydride; partially hydrogenated alkyl aluminums of alkyl aluminum dihydrides, such as ethyl aluminum dihydride and propyl aluminum dihydride, or the like; and partially alkoxyated and halogenated alkyl aluminums such as ethyl aluminum ethoxy chloride, butyl aluminum butoxy chloride and ethyl aluminum ethoxy bromide.

10 [0054]

From the viewpoint of availability, it is preferred to use any one of trimethyl aluminum, triethyl aluminum and triisobutyl aluminum as the organoaluminum compound (b-3).

[0055]

15 In the present invention, from the viewpoint of improving the polymerization activity and the properties of the obtainable syndiotactic propylene polymer, it is preferred to use any one of the following [c1] to [c4] as the component (B);

[c1] the component (B) comprising only (b-1) the organoaluminum oxy compound,

[c2] the component (B) comprising (b-1) the organoaluminum oxy compound, and (b-3) the organoaluminum compound,

[c3] the component (B) comprising (b-2) the compound forming an ion pair by reacting with the bridged metallocene compound (A),

and (b-3) the organoaluminum compound, and [c4] the component (B) comprising (b-1) the organoaluminum oxy compound, and (b-2) the compound forming an ion pair by reacting with the bridged metallocene compound (A).

5 [0056]

When the metallocene compound of the formula (I) in which Y is a silicon atom is used, (b-2) the compound forming an ion pair by reacting with the bridged metallocene compound (A) is not used as the component (B) for constituting the olefin
10 polymerization catalyst of the present invention, as described above. Therefore, among [c1] to [c4], [c1] and [c2] only are employed for the preferred components (B).

[0057]

The olefin polymerization catalyst of the present
15 invention may further comprise the carrier (C) together with (A) the metallocene compound represented by the formula (I), and (B) at least one compound selected from (b-1) the organoaluminum oxy compound, (b-2) the compound capable of forming an ion pair by reaction with the metallocene compound (A), and (b-3) the
20 organoaluminum compound, if necessary.

[0058]

(C) Carrier

The carrier (C) optionally used in the present invention (hereinafter sometimes abbreviated to "component (C)") is an

inorganic or organic compound, and a granular or fine particulate solid. Examples of the inorganic compound are porous oxides such as SiO_2 and Al_2O_3 ; inorganic halides such as MgCl_2 , MgBr_2 , MnCl_2 and MnBr_2 ; clays, clay minerals or ion exchange layer compounds
5 such as montmorillonite, Vermiculite, pectolite, teniolite and synthetic mica.

[0059]

Examples of the organic compounds are granular or fine particulate organic solids having a particle diameter of from
10 3 to 300 μm , preferably 10 to 300 μm . Specific examples thereof may include (co)polymers, which essentially comprise an α -olefin of 2 to 14 carbon atoms such as ethylene, propylene, 1-butene and 4-methyl-1-pentene, (co)polymers, which essentially
comprise vinyl cyclohexane or styrene; and polymers having a
15 polar functional group obtainable by copolymerizing or graft polymerizing these polymers with a polar monomer such as acrylic acid, acrylic acid ester or maleic anhydride, or modified polymers thereof.

[0060]

20 The polymerization catalyst of the present invention may contain an organic compound component (D) (hereinafter sometimes abbreviated to "component (D)"), if necessary. The component (D) is used in order to control the polymerization capability and the physical properties of the obtainable polymer. Examples

of the component (D) are alcohols, phenol compounds, carboxylic acid, phosphorus compounds and sulfonic acid salts.

[0061]

Next, the process for preparing the polymerization catalyst for producing the syndiotactic propylene polymers, which catalyst comprises the components (A) and (B), and optionally the component (C) and/or the component (D) is described. Further, the method for adding them to a polymerizer is also described.

10 [0062]

When the polymerization catalyst comprises only the component (A) and the component (B), a process for adding the components (A) and (B) to a polymerizer simultaneously or in an arbitrary order is employed. In this process, at least two components of the catalyst components may be previously contacted.

[0063]

In carrying out the solution polymerization of propylene singly or monomers, in which propylene is contained as essential component, by using the polymerization catalyst, the component (A) is used in an amount of from 10^{-9} to 10^{-1} mol, preferably 10^{-8} to 10^{-2} mol per 1 L of the reaction volume.

[0064]

The component (b-1) is used in an amount such that the molar

ratio $[(b-1)/M]$ of component (b-1) to all transition metal atoms M in the component (A) is usually from 0.01 to 5,000, preferably 0.05 to 2,000. The component (b-2) is used in an amount such that the molar ratio $[(b-2)]/M$ of aluminum atom in component (b-2) to all transition metal atoms M in the component (A) is usually from 1.0 to 5,000, preferably 1.0 to 2,000. The component (b-3) is used in an amount such that the molar ratio $[(b-3)/M]$ of component (b-3) to all transition metal atoms M in the component (A) is usually from 1 to 10,000, preferably 1 to 5,000.

[0065]

Inert hydrocarbon solvent and Amount of solvent in polymerization

Examples of the inert hydrocarbon solvent used in the production process of the present invention may include aliphatic hydrocarbons such as propane, butane, pentane, hexane, heptane, octane, decane, kerosene, hydrogenated naphtha and ISOPAR-E (Trade Mark) solvent (mixed solvent of C_8 - C_{12} aliphatic) available by Exxon Chemicals; alicyclic hydrocarbons such as cyclopentene, cyclohexane and methylcyclopentane; and aromatic hydrocarbons such as benzene, toluene and xylene. Among them, hydrocarbons having 5 to 12 carbon atoms are preferred. In the present invention, it is important that when the inert hydrocarbon solvent having at least one structure selected from

a branched structure (k-1), a ring structure (k-2) and an aromatic ring structure (k-3) in the molecule is used as the inert hydrocarbon solvent, the equilibrium melting temperature (T_M) can be decreased, and as a result, homogenous continuous solution polymerization reaction can be carried out without high temperature conditions. The present inventors considered that this is because, in the solvent having at least one structure selected from the structures (k-1) to (k-3), the solubility parameter (δ_1) of the solvent represented by the formula (Eq-1) to be described later approaches to the solubility parameter ($15.6 \text{ MPa}^{1/2}$) of a syndiotactic propylene polymer described in Carl L. Yaws, "Chemical properties Handbook" Chapter 14, McGraw-Hill, 1999, and/or the molar volume (V_l) of the solvent is small. The branched structure (k-1) is a structure having a ternary carbon atom or a quaternary carbon atom. The cyclic structure (k-2) is a cyclic polymethylene skeleton. The solvent preferably has three structures of the branched structure (k-1), the cyclic structure (k-2) and the linear chain structure. The linear chain structure is a structure such that at least three methylene skeletons link linearly (namely it is not a cyclic structure).

[0066]

The three kinds of structures (k-1) to (k-3) may be present in the same molecule or plural molecules. From the viewpoint

of availability, three kinds of hydrocarbons, namely the branched hydrocarbon (y-1) having a branched structure, the cyclic aliphatic hydrocarbon (y-2) having a cyclic structure and the aromatic hydrocarbon (y-3) are generally mixed with a linear chain hydrocarbon appropriately and then submitted to use. From the recent viewpoint of decrease of the load to the environment and the viewpoint of minimizing the influence on health of the human body for production workers, it is not preferable to use the aromatic hydrocarbon (y-3) having the aromatic cyclic structure (k-3). However, the use thereof does not limit the present invention as long as equipments taking sufficient measures for the environmental problems and the health problems for human body are used.

[0067]

Preferable examples of the solvents are inert hydrocarbons containing at least 90 % by volume of at least one hydrocarbon selected from cyclopentane, n-hexane, isohexane, methylcyclopentane, cyclohexane and n-heptane.

[0068]

Although the amount of the inert hydrocarbon solvent used is limited by factors such as miscibility of the solvent with a monomer, the solvent generally is fed continuously in an amount such that the polymer content per polymerization solution unit volume in a polymerizer (hereinafter, simply

abbreviated to "polymer content (PC)") is from 5 g/L to 500 g/L, preferably 10 g/L to 400 g/L, more preferably 15 g/L to 300 g/L, considering the range of the volume fraction (V_2). When the concentration is less than 5 g/L, the production speed capable of enduring practical production cannot be attained, while when it is over 500 g/L, it is possible that a part of the polymer is deposited during the polymerization to hinder the regular continuous-polymerization. Therefore, the concentration departing from the above range is not preferable.

The volume fraction (v_2) of non-dimensional unit of the polymer in the formula (Eq-1) or the formula (Eq-2) can be converted to the polymer content (PC) using the densities of the polymer and the solvent.

[0069]

In the preferred embodiment of the solution polymerization step (P_1) according to the present invention, the inert hydrocarbon solvent, the solvent amount and the polymerization temperature (T_R), and the equilibrium melting temperature (T_M) derived from the following formula (Eq-2) satisfy the following formula (Eq-1), preferably the following formula (Eq-1'), more preferably the following formula (Eq-1''). That is to say, it is very important in the present invention that the inert hydrocarbon solvent and the solvent amount are determined in order that the polymerization temperature (T_R) determined by the

method to be described later is always higher than the temperature which is 45°C lower than the equilibrium melting temperature (T_M).

[0070]

5 [Formula 1]

$$T_M - T_R \leq 45^\circ\text{C} \quad \cdots (\text{Eq-1})$$

[0071]

[Formula 2]

$$T_M - T_R \leq 43^\circ\text{C} \quad \cdots (\text{Eq-1}')$$

10 [0072]

[Formula 3]

$$T_M - T_R \leq 40^\circ\text{C} \quad \cdots (\text{Eq-1}'')$$

[0073]

[Formula 4]

$$T_M = \frac{6,700 + 49 \times (\delta_1 - 15.6)^2 \times (1 - v_2)^2}{\frac{49 \times R}{V_1} \times (1 - v_2) + \frac{6,700}{T_m}} \quad \cdots (\text{Eq-2})$$

15

[0074]

T_M : Equilibrium melting temperature [K]

T_m : Melting point of syndiotactic propylene polymer [K]

δ_1 : Solubility parameter of solvent [$(\text{MPa})^{1/2}$]

20 V_1 : Molar volume of solvent [cm^3/mol]

v_2 : Volume fraction of syndiotactic propylene polymer [-]

R : Gas constant [$\text{J/K}\cdot\text{mol}$]

The formula (Eq-2) is derived by substituting the fusion

enthalpy ΔH_u (6,700 J/mol) of syndiotactic polypropylene measured by the present applicant, the molar volume value V_u (49 cm³/mol) of a unit of the polypropylene represented by the following formula (IX) and the published solubility parameter δ_2 (15.6 J/mol) of the polypropylene for the formula (Eq-3) derived from the Flory-Huggins theory about solution-solid equilibrium of polymer.

[0075]

[Formula 5]

$$T_M = \frac{\Delta H_u + V_u \times (\delta_1 - \delta_2)^2 \times (1-v_2)^2}{\frac{V_u \times R}{V_1} \times (1-v_2) + \frac{\Delta H_u}{T_m}} \quad \text{----- (Eq-3)}$$

[0076]

[Chem. 9]



[0077]

In the table 1, supposing that the polymerization temperature is 50°C, and the polymer volume fraction (v_2) is 0.10 (the polymer concentration corresponds to 86 g/L) and 0.15 (the polymer concentration corresponds to 129 g/L), T_M and the temperature difference ($T_M - T_R$) concerning typical hydrocarbon solvents were calculated. In the calculation, the molar volume (V_1) of the solvent and the solubility parameter (δ_1) of the solvent were taken from the values described in Carl L. Yaws,

"Chemical Properties Handbook", Chapter 14, McGraw-Hill, 1999.

When the polymer volume fraction (v_2) is 0.10, solvents suitable to the formula (Eq-1) are fifteen kinds of solvents including spiropentane, cyclopentane, isopentane, n-pentane, benzene,

5 cyclohexane, methylcyclopentane, n-hexane, 1,1-dimethylcyclopentane, cis-1,2-dimethylcyclopentane, trans-1,2-dimethylcyclopentane, cis-1,3-dimethylcyclopentane, trans-1,3-dimethylcyclopentane, ethylcyclopentane and methylcyclohexane. However, from the table 1, it is found that

10 when the polymer concentration is increased and v_2 is 0.15, the suitable solvents are limited to the six kinds of solvents including spiropentane, cyclopentane, n-pentane, benzene, cyclohexane and methylcyclopentane. The scope of the claims of the present invention are not limited by the hydrocarbon
15 compounds described in Table 1, which are shown as one example of the calculation method.

[0078]

[Table 1]

[Table 1]

Typical names of hydrocarbon compounds	$v_2 = 0.1$		$v_2 = 0.15$	
	Polymer concentration = 86 g/L		Polymer concentration = 129 g/L	
	$T_M [^{\circ}\text{C}]$	$T_M - T_R [^{\circ}\text{C}]$	$T_M [^{\circ}\text{C}]$	$T_M - T_R [^{\circ}\text{C}]$
spiropentane	73.35	23.35	77.15	27.15
cyclopentane	74.97	24.97	78.65	28.65
isopentane	93.69	43.69	96.44	46.44
n-pentane	89.59	39.59	92.72	42.72
benzene	89.01	39.01	91.12	41.12
cyclohexane	85.25	35.25	88.56	38.56
methylcyclopentane	85.76	35.76	89.17	39.17
2,2-dimethylbutane	102.18	52.18	104.55	54.55
2,3-dimethylbutane	97.16	47.16	99.97	49.97
n-hexane	94.71	44.71	97.77	47.77
2-methylpentane	97.62	47.62	100.43	50.43
3-methylpentane	95.45	45.45	98.41	48.41
toluene	97.14	47.14	99.19	49.19
cycloheptane	95.17	45.17	97.92	47.92
1,1-dimethylcyclopentane	93.78	43.78	96.92	46.92
cis-1,2-dimethylcyclopentane	93.07	43.07	96.20	46.20
trans-1,2-dimethylcyclopentane	94.03	44.03	97.16	47.16
cis-1,3-dimethylcyclopentane	94.49	44.49	97.61	47.61
trans-1,3-dimethylcyclopentane	94.26	44.26	97.38	47.38
ethylcyclopentane	93.97	43.97	97.04	47.04
methylcyclohexane	93.51	43.51	96.61	46.61
2,2-dimethylpentane	104.95	54.95	107.38	57.38
2,3-dimethylpentane	100.52	50.52	103.32	53.32
2,4-dimethylpentane	104.44	54.44	106.94	56.94
3,3-dimethylpentane	102.09	52.09	104.74	54.74
3-ethylpentane	99.63	49.63	102.49	52.49
n-heptane	100.32	50.32	103.18	53.18
2-methylhexane	101.57	51.57	104.34	54.34
3-methylhexane	100.54	50.54	103.37	53.37
2,2,3-trimethylbutane	103.62	53.62	106.12	56.12

5 [0079]

When the solvent to be submitted to solution

polymerization comprises at least two kinds of inert hydrocarbons, for example in the case of two hydrocarbons, it is possible to determine the equilibrium melting temperature (T_M) using the following formula (Eq-4).

5 [0080]

[Formula 6]

$$T_M = \frac{\Delta H_u - V_u [v_1 v_2 (\delta_1 - \delta_2)^2 - (v_1 + v_2) \{ v_1 (\delta_1 - \delta_p)^2 + v_2 (\delta_2 - \delta_p)^2 \}]}{\frac{\Delta H_u}{T_m} + V_u R \left(\frac{v_1}{V_1} + \frac{v_2}{V_2} \right)} \quad \text{---- (Eq-4)}$$

[0081]

In the formula (Eq-4), ΔH_u , V_u , T_M and R are the same as those in the formula (Eq-3), v_1 and v_2 show volume fractions of the solvent 1 and the solvent 2 respectively, V_1 and V_2 show molar volume of the solvent 1 and solvent 2 respectively, and δ_1 , δ_2 and δ_p are solubility parameters of the solvent 1, the solvent 2 and syndiotactic polypropylene, respectively.

15 The equilibrium melting temperature T_M of the mixed solvent used in the example or the comparative example to be described later is determined using the formula (Eq-4) and the partially expanded formula thereof.

[0082]

20 In the particularly preferred embodiment of the solution polymerization step (P_1) according to the present invention, the volume fraction (v_2) of the syndiotactic propylene polymer in

the formula (Eq-2) is from 0.005 to 0.50, preferably 0.01 to 0.40, more preferably 0.15 to 0.30. When the volume fraction (v_2) is less than 0.005, the production speed is low and thereby the production process is hardly carried out industrially. On the other hand, the volume fraction (v_2) over 0.50 decreases the range of selection of the available solvent, which satisfies the formula (Eq-1) of relations of the equilibrium melting temperature (T_M) determined from the formula (Eq-2) and the polymerization temperature (T_R). Therefore, the volume fraction (v_2) of over 0.50 is not preferred.

[0083]

[1-2] Polymerization process

The "solution polymerization" according to the present invention includes not only completely homogeneous solution polymerization such that polymerization is carried out at a specific temperature in a condition of polymers substantially dissolved in the inert hydrocarbon solvent completely but also partially heterogeneous solution polymerization such that polymerization is carried out in a white-turbidity state in which fine polymers are deposited partly. As the homogeneity of the solution, namely the transparency is higher, in the polymerization, it is easier to carry out solution polymerization of syndiotactic polypropylene according to the present invention and to carry out the continuous production by

the solution polymerization, and moreover, the occurrence of operation trouble caused by deposited polymers can be decreased. Therefore, the homogenous condition is more preferred. The present invention is not limited to the solution polymerization
5 in a complete homogeneous condition as long as polymers having aimed quality can be obtained.

[0084]

Monomer(s) used in the solution polymerization step (P₁) of the present invention is propylene only or a mixed olefin
10 comprising or propylene as an essential component. In the present invention, the meaning of "essential component" is defined by the fact that the propylene concentration in the mixed olefin is not less than 50 mol%, preferably not less than 70 mol%, more preferably not less than 80 mol%. It is possible to
15 optionally use, as the other olefins other than propylene, olefins having 2 to 10 carbon atoms such as ethylene, 1-butene, 2-butene, 1-pentene, 3-methyl-1-butene, 1-hexene, 1-heptene, 1-octene, 1-decene, 3-methyl-1-pentene, 4-methyl-1-pentene. From the viewpoint of availability, ethylene, 1-butene, 1-hexene,
20 1-octene and 4-methyl-1-pentene are used. Furthermore, in the solution polymerization of the present invention, it is possible to use a known molecular weight modifier such as hydrogen molecule or the like.

[0085]

In the process for producing the syndiotactic propylene polymer of the present invention, the characteristics in the process of the solution polymerization step (P_1) are the following two points.

5 [0086]

1) The step is carried out by the solution polymerization
[0087]

2) The polymerization is carried out at a temperature in the specific range.

10 [0088]

Each of the characteristics is described in detail below.
[0089]

The polymerization step (P_1) of the present invention is carried out in a solution condition, preferably continuously.

15 That is to say, in the polymerization step (P_1), propylene singly or monomers in which propylene is contained as the essential component, the solvent and the polymerization catalyst are continuously fed each alone or mixed into a polymerizer with forced stirring capable of attaining complete mixing, to carry

20 out polymerization, and then the polymer solution is taken out continuously, and transported to the post-treatment step (P_2) as described later. In the polymerization step (P_1), polymerization temperature is regulated by removing polymerization heat generated in such a way that vapor, in the

polymerizer, of the monomer(s) and the solvent is passed a condenser to be condensed through a pipe whose opening is in the gas phase space of the polymerizer upper part, and the condensed solution is returned to the polymerizer, and thereby evaporation latent heat is removed.

[0090]

In the continuous polymerization, the average retention time, which varies depending on conditions such as the shape of the polymerizer, the catalyst type, the catalyst concentration and the polymerization temperature, is generally from 5 min to 4 hr, preferably 10 min to 3 hr, more preferably 15 min to 2.5 hr.

[0091]

As the continuous polymerizer, one polymerizer may be used, or two or more polymerizers may be aligned linearly for use. In the later case, the polymerizers each may have different polymerization conditions capable of attaining different polymer properties.

[0092]

In the polymerization step (P_1) of the present invention, although the polymerization temperature (T_R) varies depending on the polymer content (PC) per volume of the polymerization solution in the polymerizer as described later, the polymerization is carried out at a temperature generally from

30°C to 250°C, preferably 40°C to 200°C, more preferably 40°C to 150°C. When the temperature is lower than 30°C, the possibility that the amount of deposited polymers is increased by internal or external disturbance in the polymerizer is increased, and the polymerization temperature is largely under to the lower limit of the optimum temperature of the post-treatment step (P_2) to be described later. On this account, it is necessary to employ a temperature-increasing step before the polymer solution is continuously fed to the post-treatment step (P_2) and thereby process economy is often damaged. Accordingly, the temperature of lower than 30°C is not preferable. When the temperature is over 250°C, there is a possibility that thermal decomposition of the polymer itself is induced. Accordingly, the temperature of over 250°C is not preferable also.

[0093]

In the polymerization step (P_1), the polymerization temperature (T_R) preferably satisfies the following formula (Eq-5), more preferably the following formula (Eq-6). When the solution polymerization progresses at a polymerization temperature satisfying the formulas, the solution is always kept homogeneously during the polymerization, and thereby the continuous production can be attained without troubles which disturb continuous operation, caused by deposition of solid

polymers, such as pipe clogging, and the syndiotactic propylene polymers having stable qualities can be constantly prepared.

[0094]

$$(T_{\min} - 45) < T_R < (T_{\min} + 50) \quad \dots \text{ (Eq-5)}$$

$$5 \quad (T_{\min} - 40) < T_R < (T_{\min} + 40) \quad \dots \text{ (Eq-6)}$$

In the formulas (Eq-5) and (Eq-6), $T_{\min}$ ($^{\circ}\text{C}$) is the lowest temperature of when the solution viscosity and the temperature of a syndiotactic propylene polymer solution generated by solution polymerization show a linear relationship. $T_{\min}$ usually shows a different value depending on the polymer content (PC) or the molecular weight of an aimed syndiotactic propylene polymer. Normally, the lowest temperature $T_{\min}$, at which the temperature and the solution viscosity satisfy the linear relationship is determined by a method of separately preparing an aimed syndiotactic propylene polymer in a small scale and measuring a relationship between the temperature and the solution viscosity of the polymer content (PC) of the designed polymer, or by using relationships such as a known Mark-Houwink formula. For example, Fig. 1 shows the fact that in the syndiotactic polypropylene having an intrinsic viscosity $[\eta]$ of 1.6 dl/g and a melt flow rate (MFR) of 4 g/10 min, when PC is 200 g/L, $T_{\min}$ is 83°C , when PC is 100 g/L, $T_{\min}$ is 80°C , when PC is 50 g/L, $T_{\min}$ is 70°C , and when PC is 30 g/L, $T_{\min}$ is 62°C , and further, when in each polymer concentration PC, at a temperature

not lower than $T_{\min}$, the solution viscosity and the temperature have a linear straight-line relationship. In the usual polymerization operation, the polymerization temperature (T_R) is set to be higher than the equilibrium melting temperature (T_M).

5 [0095]

Therefore, the polymerization in the solution polymerization step (P_1) is carried out usually in the following steps.

[0096]

10 [Step 1] The quality (T_m) of an aimed syndiotactic propylene polymer is determined.

[0097]

[Step 2] The inert hydrocarbon solvent is selected and the equilibrium melting temperature (T_M) is determined by substituting the molar volume (V_1) of the solvent, the solubility parameter (δ) of the solvent and the volume fraction (v_2) of the syndiotactic propylene polymer for the formula (Eq-2) or the formula (Eq-4). The volume fraction (v_2) is selected from the range of 0.005 to 0.50.

20 [0098]

[Step 3] The polymerization temperature (T_R) is determined according to the formula (Eq-5).

[0099]

[Step 4] When the relation between the equilibrium melting

temperature (T_M) and the polymerization temperature (T_R) does not satisfy the formula (Eq-1), the above step is repeated with respect to other solvent having different molar volume (V_1) and/or solubility parameter (δ). The polymerization condition
5 satisfying the formula (Eq-1) is determined by changing the volume fraction (v_2) of the syndiotactic propylene polymer in the range of 0.005 to 0.50 or by varying the polymerization temperature (T_R) in the range of inequality expression of the formula (Eq-5).

10 [0100]

The polymerization pressure in the polymerization step (P_1) is a value, which varies depending on the polymerization temperature or the amount of the solvent used and can be determined to the arbitrary range. Usually, the pressure is more
15 than 0 to 10 MPaG, preferably to 8 MPaG, more preferably to 6 MPaG.

[0101]

[2] Post-treatment step (P_2)

The process for producing the syndiotactic propylene
20 polymer of the present invention is characterized by, following the polymerization step (P_1), preferably carrying out the post-treatment step (P_2) such that the polymerization solution transported from the polymerization step is optionally heated to the temperature range of not lower than the polymerization

temperature and not higher than 250°C, and then the solvent is distilled off by flash operation under a pressure of 0.00 to 0.5 MPa in a flash vessel. In the transportation line from the polymerization step (P_1) to the post-treatment step (P_2), it is preferable to employ a method of transporting the polymer solution (S) by introducing a hydrocarbon having 5 to 12 carbon atoms with pressure at an arbitrary position. As the hydrocarbon having 5 to 12 carbon atoms, the solvent same as the inert hydrocarbon solvent submitted to the solution polymerization reaction is preferably used. In this method, the solvent temperature is set to the range of from the polymerization temperature (T_R) to $T_R + 50^\circ\text{C}$. In the injection to the line, the pressure is usually set to a range from the internal pressure of the polymerization reactor to 10 MPaG.

15 [0102]

The preferred embodiment of the flash operation according to the present invention is described below.

[0103]

In the post-treatment step of the present invention, the continuous flash operation is carried out at a vapor temperature in a flash vessel of from 90 to 250°C, preferably 90 to 220°C, more preferably 90 to 200°C, at an internal pressure of the flash vessel of from 0.00 to 0.5 MPa·G, preferably 0.01 to 0.3 MPa·G. The vapor flashed is discharged continuously from the flash

vessel and thereby the monomer and the solvent are recovered. The flash operation of the present invention can decrease the content of the solvent remained in the polymer to the sufficiently low level capable of pelletizing the polymer.

5 Usually, the polymer obtained after flashing contains the solvent in an amount of not more than 2000 weight ppm, preferably not more than 1000 weight ppm, more preferably not more than 500 weight ppm.

[0104]

10 In the post-treatment of the present invention, a system of controlling the temperature of the polymer solution continuously discharged from the polymerizer is provided in order to regulate the vapor temperature in the flash vessel to the above range, and a pressure control device of controlling
15 the pressure of the polymer solution is provided. The polymer solution satisfying a prescribed temperature and a prescribed pressure (hereinafter, sometimes referred to as "polymerization solution for flash" is prepared using the system and the device and then continuously injected into the flash vessel. In the
20 continuous line of connecting the polymerizer and the flash vessel, a heating system capable of heating with jacket steam or the like and pressure controlling bulbs for controlling the pressure are usually provided. However, there is no limitation on these systems in the present invention.

[0105]

The temperature of the polymer solution for flash is from 100 to 250°C, preferably 100 to 220°, more preferably 120 to 200°C.

[0106]

5 The pressure of the polymer solution continuously injected into the flash vessel is from 1.0 to 10 MPa·G, preferably 2.0 to 8.0 MPa·G, more preferably 3.0 to 6.0 MPa·G.

[0107]

10 When the temperature and the pressure of the polymer solution for flash continuously injected into the flash vessel satisfy the above ranges, continuous production can be carried out effectively without marring the qualities of resulting polymers in the post-treatment of the present invention.

[0108]

15 The polymer obtained by the separation of the monomer and the solvent through the flash operation is pelletized by a conventionally known method. For example, it is preferable to employ the method which comprises an extrusion step of extruding a molten polymer, which is continuously discharged from the flash
20 vessel into a strand state, through a nozzle of an extruder, a cut step of preparing pellets by cutting the strand product extruded with a cutter having a rotating blade, a cooling step of cooling the cut pellets in a state of contacting with water, and a dehydration step of separating the cooled pellets and water

by a centrifugal dehydrator. However, the method in the present invention is not limited to the method described above.

[0109]

5 [3] Syndiotactic propylene polymer obtainable by the production process of the present invention

The syndiotactic propylene polymer of the present invention generally has a skeleton derived from propylene in an amount of not less than 90 mol%, preferably from 93 mol% to 100 mol%, and satisfies all the following properties [1] to [3],
10 preferably all the following properties [1] to [6], and further has excellent moldability, heat resistance, transparency, blocking resistance and balance between mechanical properties and strength.

[1] The syndiotactic pentad fraction (rrrr fraction) as measured
15 by ^{13}C -NMR is not less than 85%, preferably not less than 90%, more preferably not less than 93%, further preferably not less than 94%.

[2] The intrinsic viscosity $[\eta]$ measured at 135°C in decalin is from 0.1 to 10 dl/g, preferably 0.3 to 7 dl/g, more preferably
20 0.5 to 5 dl/g.

[3] The melting point (T_m) determined by a differential scanning calorimeter is not lower than 145°C, preferably not lower than 145°C and not higher than 170°C, more preferably not lower than 150°C and not higher than 170°C, further preferably not lower

than 155°C and not higher than 170°C, especially preferably not less than 156°C and not higher than 170°C.

[4] The heat of fusion (ΔH) is not less than 40 mJ/mg, preferably not less than 50 mJ/mg, more preferably not less than 52 mJ/mg, especially preferably not less than 55 mJ/mg.

[5] The isothermal crystallization temperature T_{iso} as determined by a differential scanning calorimeter and the semi-crystallization time in the isothermal crystallization $t_{1/2}$ satisfy the following formula (Eq-7), preferably the following formula (Eq-8), more preferably the following formula (Eq-9) in the range $110 \leq T_{iso} \leq 150$ (°C).

[0110]

[Formula 7]

$$1.67 \times 10^{-4} \exp(0.10 \times T_{iso}) \leq t_{1/2} \leq 5.56 \times 10^{-4} \exp(0.12 \times T_{iso}) \quad (\text{Eq-7})$$

[0111]

[Formula 8]

$$1.67 \times 10^{-4} \exp(0.10 \times T_{iso}) \leq t_{1/2} \leq 3.71 \times 10^{-4} \exp(0.12 \times T_{iso}) \quad (\text{Eq-8})$$

[0112]

[Formula 9]

$$1.67 \times 10^{-4} \exp(0.10 \times T_{iso}) \leq t_{1/2} \leq 2.23 \times 10^{-4} \exp(0.12 \times T_{iso}) \quad (\text{Eq-9})$$

[0113]

[6] The amount of a part soluble in n-decane is not more than 1 wt%, preferably not more than 0.8 wt%, more preferably not more than 0.6 wt%.

[0114]

From the viewpoint of improving the capabilities of a molded article and moldability, the syndiotactic propylene polymer of the present invention, further, satisfies the following properties [7] and [8] preferably in addition to the properties [1] to [6].

[7] The melt flow rate as determined at 230°C under a load of 2.16 kg in accordance with ASTM D-1238 is from 0.01 to 50 g/10 min, preferably 0.1 to 30 g/10 min.

[8] The molecular weight distribution (M_w/M_n) as measured by Gel permeation chromatography (GPC) is from 1.5 to 20, preferably 2.0 to 10.

[0115]

The syndiotactic propylene polymer of the present invention is optionally blended with additives such as weather stabilizer, heat stabilizer, antistatic agent, anti-slipping agent, anti-blocking agent, forming agent, crystallization assistant, anti-fogging agent, transparent nucleating agent, lubricant, pigment, dye, plasticizer, antiaging agent, hydrochloric acid absorbent, oxidation inhibitor, mold releasing agent, impact improver or anti-UV agent. Thereafter, the polymer is molded by known heat molding methods, for example, extrusion molding, injection molding, inflation molding, extrusion laminating molding, cast molding, blow molding,

extrusion blow molding, injection blow molding, press molding, vacuum molding, calender molding, foaming molding or powder slash molding. In the results, molded articles useful for various uses can be prepared.

5 EXAMPLES

[0116]

Hereinafter, the present invention will be described in more detail with reference to the following examples, but the present invention is not restricted by the examples. In the
10 examples, various physical properties were determined in the following manners.

[0117]

Melt flow rate (MFR)

The melt flow rate was measured at 230°C under a load of
15 2.16 kg in accordance with ASTM D-1238.

[0118]

Intrinsic viscosity $[\eta]$

The intrinsic viscosity was measured at 135 °C in a decalin solvent. Namely, about 20 mg of a polymer was dissolved in 15
20 ml of decalin and a specific viscosity η_{sp} was measured in an oil bath at 135°C. To the decalin solution, 5 ml of a decalin solvent was added and the decalin solution was diluted, and then a specific viscosity η_{sp} was measured in the same manner. This diluting operation and the measurement of specific viscosity η_{sp}

were further repeated twice, and when the concentration (C) is extrapolated into 0, the value η_{sp}/C was determined as an intrinsic viscosity (referred to the following formula).

$$[\eta] = \lim (\eta_{sp}/C) \quad (C \rightarrow 0)$$

5 [0119]

Amount of n-decane soluble

To 5 g of a polymer sample, 200 ml of n-decane was added and the sample was dissolved with heat at 145°C for 30 min. The resulting solution was cooled to 20°C over about 3 hr, and allowed
 10 to stand for 30 min. Thereafter, a deposit (n-decane insoluble) was separated by filtration. The filtrate was introduced into about 3 times the filtrate amount of acetone and thereby a component dissolved in n-decane was deposited. The deposit was separated by filtration from acetone and then dried. When the
 15 filtrate was concentrated and dried, no residue was observed. The amount of the n-decane soluble was determined by the following formula.

Amount of n-decane soluble (wt%)

$$= [\text{Weight of deposit} / \text{Weight of sample}] \times 100$$

20 [0120]

Molecular weight distribution (Mw/Mn)

The molecular weight distribution (Mw/Mn) was determined using a gel permeation chromatograph Alliance GPC-2000 model manufactured by Waters Co., Ltd in the following manner. As a

separation column, two columns of TSK gel GNH6-HT and two columns of TSK gel GNH6-HTL were used (any column had a diameter of 7.5 mm and a length of 300 mm). The column temperature was 140°C, o-dichlorobenzene (manufactured by Wako Pure Chemical Industries, Ltd.) was used as a mobile phase, and 0.025 % by weight of BHT (manufactured by Takeda Pharmaceutical Co., Ltd.) was used as an oxidation inhibitor, the mobile phase was moved at a rate of 1.0 ml/min, the sample concentration was 15 mg/10 ml, the amount of the sample injected was 500 micro liter, and a differential refractive index detector was used as a detector. For the standard polystyrenes having a molecular weight satisfying $M_w < 1000$ and $M_w > 4 \times 10^6$, polystyrene manufactured by Tohso Co., Ltd. was used, and for ones having a molecular weight satisfying $1000 \leq M_w \leq 4 \times 10^6$, polystyrene manufactured by Pressure Chemical Co., was used.

[0121]

Melting point (T_m) and Heat of fusion (ΔH)

The melting point (T_m) and heat of fusion (ΔH) were determined using DSC Pyris1 or DSC7 manufactured by Perkin Elmer Inc. About 5 mg of a sample was packed in a special aluminum pan, the temperature was increased to 200°C in a nitrogen atmosphere (nitrogen flow rate: 20 ml/min), and was kept at 200°C for 10 min. Thereafter, the sample was cooled at a rate of 10°C/min to 30°C. The temperature was kept at 30°C for 5 min,

and then was increased to 200°C at a rate of 10°C/min. At this time, the melting point was determined from a peak top of a crystalline melt peak, and the heat of fusion was determined from an integrating value of a crystalline melt peak.

5 [0122]

In the propylene polymers described in the examples of the present invention, when two peaks were observed, the low temperature side peak was regarded as T_{m1} and the high temperature side peak was defined as T_{m2} , and T_{m2} was defined as the melting point (T_m).

[0123]

Half time of Isothermal crystallization ($t_{1/2}$)

About 5 mg of a sample was packed in a special aluminum pan, and the temperature of the sample was increased using DSC
15 Pyris1 or
DSC7 manufactured by Perkin Elmer Inc. from 30° C to 200°C at a rate of 320°C/min and then kept at 200°C for 5 min. Thereafter, the temperature was decreased from 200°C to the temperature of isothermal crystallization 110°C at a rate of 320°C/min. From
20 the DSC curve obtained by keeping each isothermal crystallization temperature, a half time of crystallization ($t_{1/2}$) was obtained. The half time of crystallization ($t_{1/2}$) was determined by taking the starting time for the isothermal crystallization process (the time that the temperature reached

the isothermal crystallization temperature from 200°C) as $t=0$. The $t_{1/2}$ is usually determined in the above manner. However, for example, when crystallization was not caused at a certain isothermal crystallization temperature, for example at 110°C, measurement was expediently carried out at several points at an isothermal crystallization temperature not higher than 110°C and the half time of crystallization ($t_{1/2}$) was determined by the extrapolation value.

[0124]

The solvents for solution polymerization used in the examples and comparative examples according to the present invention are as follows:

cyclohexane,

n-heptane,

solvent A; a mixed solvent which comprises n-hexane (60 to 65 % by volume), isohexane (10 to 19 % by volume), methylcyclopentane (18 to 22 % by volume) and other aliphatic hydrocarbon components (0 to 3 % by volume), and

solvent B; a mixed solvent which comprises isohexane (95 to 100 % by volume and n-hexane (0 to 5 % by volume).

The isohexane which is a constituent of the solvents A and B is a mixed solvent of 2-methylpentane and 3-methyl pentane (in a volume ratio of about 2/1).

[0125]

[Synthetic Example 1]

Dibenzylmethylenecyclopentadienyl (2,7-diphenyl-3,6-di-tert-butylfluorenyl)zirconium dichloride was produced in the following manner.

5 [0126]

(i) Synthesis of 2,7-dibromo-3,6-di-tert-butyl-fluorene

In a nitrogen atmosphere, 15.22 g (54.7 mmol) of 3,6-di-tert-butyl-fluorene synthesized in accordance with a method described in Bull. Chem. Soc. Jpn., 59, 97 (1986) and 170 mL of propylene carbonate were added to a 300 mL three-neck flask, and stirred. To the solution, 20.52 g (115 mmol) of imide N-bromosuccinate was added and the mixture was stirred while heating at 80°C for 5 hr. Thereafter, the reaction mixture was spontaneously cooled, and then was added to 800 mL of water and stirred at room temperature for 15 min. After the stirring, a solid deposited was separated by filtration. The resulting solid was washed with 10 mL of ethanol five times. Thereafter, to the solid, a mixed solution of n-hexane and a small amount of dichloromethane was added and the mixture was heated to 60°C, thereby the solid was dissolved in the solution completely. The solution was then allowed to stand over night at -20°C. The crystal deposited was washed with 5 mL of hexane three times to prepare an aimed product (in an amount of 21.16 g in a yield of 76%). The identification of the aimed product was carried out

by ^1H NMR and FD-MS spectrum.

^1H NMR (270 MHz, CDCl_3 , TMS): δ 1.60 (s, tBu(Flu), 18H), 3.75 (s, Flu-9H, 2H), 7.73 (s, Flu, 2H), 7.81 (s, Flu, 2H).

MS (FD) : M/z 436 (M+).

5 [0127]

(ii) Synthesis of 2,7-diphenyl-3,6-di-tert-butyl-fluorene

In a nitrogen atmosphere, 8.15 g (18.7 mmol) of 2,7-dibromo-3,6-di-tert-butyl-fluorene and 1.08 g (0.93 mmol) of $\text{Pd}(\text{PPh}_3)_4$ were added to a 300 mL three-neck flask, and then 10 120 mL of dehydrated 1,2-dimethoxyethane was added and the mixture was stirred at room temperature for 20 min. To the solution obtained, 20 mL of ethanol solution containing 5.01 g (41.1 mmol) of phenyl boric acid was added and the mixture was stirred at room temperature for 20 min, and then 37.4 mL (74.8 15 mmol) of a 2.0 mol/L sodium carbonate aqueous solution was added. Thereafter, the mixture was refluxed while heating for 18 hr and cooled spontaneously, and then quenched with dilute hydrochloric acid in an ice bath. The soluble part was extracted by adding ether, and the organic layer was washed with a saturated sodium 20 hydrogen carbonate aqueous solution twice, with water twice and with saturated brine twice, and then dried with magnesium sulfate. Thereafter, the solvent was distilled off and the resulting solid was separated with a column chromatography to prepare an aimed product (in an amount of 4.36 g in a yield of 54%). The

identification of the aimed product was carried out by ^1H -NMR and FD-MS spectrum.

^1H -NMR (270 MHz, CDCl_3 , TMS): δ 1.29 (s, tBu(Flu), 18H), 3.78 (s, Flu-9H, 2H), 7.16 (s, Flu, 2H), 7.34 (br, PhFlu, 10H), 7.97 (s, Flu, 2H).

MS (FD) : M/z 430 (M+).

[0128]

(iii) Synthesis of 6,6-dibenzofulvene

In a nitrogen atmosphere, 8.0 g (121 mmol) of cyclopentadiene and 100 mL of dehydrated tetrahydrofuran were added to a 500 mL three-neck flask, and stirred. The mixed solution was cooled in an ice bath, and 80 mL (125.6 mmol) of a 1.57 mmol/L hexane solution of n-butyl lithium was added. Thereafter, the mixture was stirred at room temperature for 3 hr and the resulting white slurry was cooled in an ice bath, and then a solution prepared by dissolving 25.0 g (118 mmol) of 1,3-diphenyl-2-propanone in 50 mL of dehydrated tetrahydrofuran was added. Thereafter, the mixture was stirred at room temperature for 12 hr, and the resulting yellow solution was quenched with a saturated ammonium chloride aqueous solution. 100 mL of n-hexane was added to the solution and thereby the soluble part was extracted. The organic phase was washed with water and saturated brine, and then dried with magnesium sulfate. The solvent was distilled off, and the

residue was purified with a column chromatography to prepare an aimed yellow solid (in an amount of 3.7 g in a yield of 12%). The identification of the aimed product was carried out by ^1H -NMR. ^1H -NMR (270 MHz, CDCl_3 , TMS): δ 3.69 (s, PhCH_2 , 4H), 6.60-6.72 (m, Cp, 4H), 7.13-7.32 (m, PhCH_2 , 10H).

[0129]

(iv) Synthesis of dibenzylmethylene (cyclopentadienyl) (2,7-diphenyl-3,6-di-tert-butylfluorene)

In a nitrogen atmosphere, 30 mL of dehydrated tetrahydrofuran was added to 1.60 g (3.71 mmol) of 2,7-diphenyl-3,6-di-tert-butylfluorene and the mixture was stirred. The solution obtained was cooled in an ice bath, and then 2.65 mL (4.13 mmol) of a 1.56 mol/L hexane solution of n-butyl lithium was added to the solution and the mixture was stirred at room temperature for 2 hr. The resulting red solution was cooled to -78°C in a dry ice-methanol bath, and 20 mL of tetrahydrofuran containing 1.06 g (4.10 mmol) of 6,6-dibenzofurvene was dropped over 20 min to the solution. Thereafter, the mixture was stirred for 18 hr while the temperature was gradually increased to room temperature. To the resulting red-black solution, 60 mL of 1N hydrochloric acid was added, and thereby the reaction was terminated. The separation of the liquid was carried out by adding 80 mL of diethylether, and thereby the soluble part was extracted. This organic layer

was washed with saturated sodium hydrogen carbonate aqueous solution twice, with water twice, and with saturated brine once, and then dried with magnesium sulfate. The solvent was distilled off and a white-yellow powdery aimed product was obtained (in
 5 an amount of 0.59 g in a yield of 23%) by purification with silica gel chromatography. The identification of the aimed product was carried out by ^1H -NMR and FD-MS spectrum.

^1H -NMR (270 MHz, CDCl_3 , TMS): δ 1.25 (s, tBu(Flu), 18H), 2.66 (br, CpH, 1H), 3.22 (br, CH_2Ph , 4H), 4.41 (br, Flu-9H, 1H), 5.85-6.51
 10 (m, Cp, 4H), 6.82-7.40 (m, Ph(Flu) and CH_2Ph and Flu, 22H), 7.67 (s, Flu, 2H).

MS (FD) : M/z 688 (M+).

[0130]

(v) Synthesis of dibenzylmethylene(cyclopentadienyl)(2,7-diphenyl-3,6-di-tert-butylfluorenyl)zirconium dichloride
 15

In a nitrogen atmosphere, 0.59 g (0.855 mmol) of dibenzylmethylene(cyclopentadienyl)(2,7-diphenyl-3,6-di-tert-butylfluorene, and 40 mL of dehydrated diethylether were added to a 100 mL Schlenk tube and stirred. This mixed slurry solution
 20 was cooled in an ice bath, and 1.21 mL (1.88 mmol) of a 1.56 mol/L hexane solution of n-butyl lithium was added to the slurry solution, and the mixture was stirred for 45 hr while the temperature was increased to room temperature gradually. The red reaction liquid was cooled to -78°C in a dry ice-methanol

bath, and then 0.200 g (0.858 mmol) of zirconium tetrachloride was added thereto. Thereafter, the solution was stirred for 42 hr while the temperature was increased to room temperature gradually, to prepare a reddish and orange suspension liquid.

5 The solvent was distilled off under a reduced pressure and then the resultant was dissolved in n-hexane in a nitrogen atmosphere, passed through a glass filter packed with Celite, and then washed with n-hexane. The orange powder insoluble in n-hexane was subjected to extraction by dichloromethane. The solvent of the
10 soluble part in dichloromethane was distilled off and the residue was washed with diethylether/cold n-pentane, and dried to prepare the aimed product as an orange powder (in an amount of 515 mg in a yield of 71 %). The identification of the aimed product was carried out by ^1H -NMR and FD-MS spectrum.

15 ^1H -NMR (270 MHz, CDCl_3 , TMS): δ 1.30 (s, tBu(Flu), 18H), 3.82 (d, $J=15.5$ Hz, CH_2Ph , 2H), 3.93 (d, $J=15.5$ Hz, CH_2Ph , 2H), 5.80 (t, $J=2.6$ Hz, Cp, 2H), 6.25 (t, $J=2.6$ Hz, Cp, 2H), 6.97-7.34 (m, Ph(Flu) and CH_2Ph , 20H), 7.37 (s, Flu, 2H), 8.32 (s, Flu, 2H).
MS (FD) : M/z 848(M+).

20 [0131]

[Example 1]

To a 1 L internal volume stainless steel autoclave thoroughly purged with nitrogen, 150 mL of cyclohexane and 150 mL of n-heptane were fed and the internal temperature of the

autoclave was kept at 45°C for 20 min while passing propylene in an amount of 30 L/hr. On the other hand, to a 30 mL internal volume side-arm flask thoroughly purged with nitrogen, a magnetic stirrer was put and the flask was charged with 212.3 mmol (3.46 mol/L in terms of aluminum atom) of a hexane slurry of TMAO-341 (manufactured by Tohso Fine Chem Co., Ltd.) and 0.5 μ mol of dibenzylmethylene(cyclopentadienyl) (2,7-diphenyl-3,6-di-tert-butylfluorenyl)zirconium dichloride prepared in Synthetic Example 1, and then further charged with n-heptane. The mixture was stirred for 1 hr. The resulting solution was added to a mixed solvent of cyclohexane and n-heptane (volume ratio of 1:1) in a stainless steel autoclave through which propylene had been passed, and polymerization was started. Thereafter, the polymerization was carried out at 50°C for 1 hr while the total pressure was kept to 0.5 MPa-G by passing only propylene continuously. Since the control of exothermic heat during the polymerization was easy, the mixture in the autoclave was presumed to be in a homogenous condition in the polymerization. After the completion of polymerization, the pressure was released while keeping the temperature at 50°C to be brought into ordinary pressure. Thereafter, unreacted propylene was purged while keeping the temperature at 50°C. It was confirmed that the polymer solution was in a homogenous condition, by the visual

observation for the polymer solution in the autoclave after a top plate of the autoclave was opened. The resulting uniform polymer solution was put into an excess amount of methanol to deposit a polymer. The polymer was dried under a reduced pressure at 80°C for 12 hr and 30.61 g of the polymer was obtained. The polymerization activity of the polypropylene polymerization was 61.2 kg/mmol-Zr•hr, and the resulting polymer had an intrinsic viscosity $[\eta]$ of 1.66 dl/g, MFR of 3.4 g/10 min, T_{m1} of 155°C, T_{m2} of 160°C, a rrrr fraction of 94.3% and an amount of the n-decane soluble of not more than 0.6 % by weight. The equilibrium melting temperature (T_M) determined from the formula (Eq-1) and the difference ($T_M - T_R$) between T_M and the polymerization temperature (T_R) according to the present invention are summarized in Table 2.

[0132]

[Example 2]

The procedure of the Example 1 was repeated except that 300 mL of n-heptane was used as a solvent for solution polymerization, and the internal temperature of the autoclave was kept at 60°C before and during the polymerization reaction. It was difficult to say that the control of exothermic heat during the polymerization was easy, but the polymerization could be carried out while controlling the polymerization condition,

therefore it was presumed that the polymerization proceeded in a state (white-turbidity state) that a part of the polymer was deposited. After the completion of polymerization, the pressure was released while keeping the temperature at 60°C to be brought into ordinary pressure. Thereafter, unreacted propylene was purged while keeping the temperature at 60°C. It was confirmed that the polymer solution was in a white-turbidity state, by the visual observation for the polymer solution in the autoclave after a top plate of the autoclave was opened. The amount of the resulting polymer was 26.80 g. The polymerization activity of the polypropylene polymerization was 53.6 kg/mmol-Zr·hr, and the resulting polymer had an intrinsic viscosity $[\eta]$ of 1.47 dl/g, MFR of 6.9 g/10 min, T_{m1} of 152°C, T_{m2} of 158°C and an amount of the n-decane soluble of not more than 0.6 % by weight. The equilibrium melting temperature (T_M) determined from the formula (Eq-1) and the difference ($T_M - T_R$) between T_M and the polymerization temperature (T_R) according to the present invention are summarized in Table 2.

[0133]

20 [Example 3]

The procedure of the Example 1 was repeated except that 75 mL of cyclohexane and 225 mL of n-heptane were used as a solvent for solution polymerization. It was difficult to say that the control of exothermic heat during the polymerization was easy,

but the polymerization could be carried out while controlling the polymerization condition, it was presumed the polymerization proceeded in a white-turbidity state that a part of the polymer was deposited. After the completion of polymerization, the pressure was released while keeping the temperature at 50°C to be brought into ordinary pressure. Thereafter, unreacted propylene was purged while keeping the temperature at 50°C. It was confirmed that the polymer solution was in a white-turbidity state, by the visual observation for the polymer solution in the autoclave after a top plate of the autoclave was opened. The amount of the resulting polymer was 10.54 g. The polymerization activity of the polypropylene polymerization was 21.1 kg/mmol-Zr·hr, and the resulting polymer had an intrinsic viscosity $[\eta]$ of 1.70 dl/g, MFR of 3.2 g/10 min, T_{m1} of 155°C, and T_{m2} of 161°C. The equilibrium melting temperature (T_M) determined from the formula (Eq-1) and the difference ($T_M - T_R$) between T_M and the polymerization temperature (T_R) according to the present invention are summarized in Table 2.

[0134]

20 [Example 4]

The procedure of the Example 1 was repeated except that 300 mL of cyclohexane was used as a solvent for solution polymerization. Since the control of exothermic heat during the polymerization was easy, it was presumed the polymerization

proceeded in a homogenous condition. After the completion of polymerization, the pressure was released while keeping the temperature at 50°C to be brought into ordinary pressure. Thereafter, unreacted propylene was purged while keeping the temperature at 50°C. It was confirmed that the polymer solution was in a homogenous condition, by the visual observation for the polymer solution in the autoclave after a top plate of the autoclave was opened. The amount of the resulting polymer was 41.23 g. The polymerization activity of the polypropylene polymerization was 82.5 kg/mmol-Zr·hr, and the resulting polymer had an intrinsic viscosity $[\eta]$ of 1.50 dl/g, MFR of 6.1 g/10 min, T_{m1} of 151°C and T_{m2} of 159°C. The equilibrium melting temperature (T_M) determined from the formula (Eq-1) and the difference ($T_M - T_R$) between T_M and the polymerization temperature (T_R) according to the present invention are summarized in Table 2.

[0135]

[Comparative Example 1]

The procedure of the Example 1 was repeated except that 300 mL of n-heptane was used as a solvent for solution polymerization, and the internal temperature of the autoclave was kept at 40°C before and during the polymerization reaction. After the start of polymerization, the removal of heat in a polymerizer became difficult and then the polymerization was

stopped. After the stop of polymerization, the pressure was released while keeping the temperature at 40°C to be brought into ordinary pressure. Thereafter, unreacted propylene was purged while keeping the temperature at 40°C. It was confirmed that a significant amount of a polymer deposited, by the visual observation for the polymer solution in the autoclave after a top plate of the autoclave was opened. The amount of the resulting polymer was 26.22 g. The polymerization activity of the polypropylene polymerization was 52.4 kg/mmol-Zr·hr, and the resulting polymer had an intrinsic viscosity $[\eta]$ of 2.12 dl/g, MFR of 1.2 g/10 min, T_{m1} of 157°C and T_{m2} of 162°C. The equilibrium melting temperature (T_M) determined from the formula (Eq-1) and the difference ($T_M - T_R$) between T_M and the polymerization temperature (T_R) according to the present invention are summarized in Table 2.

[0136]

[Comparative Example 2]

The procedure of the Example 1 was repeated except that the internal temperature of the autoclave was kept at 40°C before and during the polymerization reaction, and the polymerization time was changed to 55 min. After the start of polymerization, the removal of heat in a polymerizer became difficult and then the polymerization was stopped. After the stop of polymerization, the pressure was released while keeping the

temperature at 40°C to be brought into ordinary pressure. Thereafter, unreacted propylene was purged while keeping the temperature at 40°C. It was confirmed that a significant amount of a polymer was deposited, by the visual observation for the polymer solution in the autoclave after a top plate of the autoclave was opened. The amount of the resulting polymer was 59.95 g. The polymerization activity of the propylene polymerization was 130.8 kg/mmol-Zr·hr, and the resulting polymer had an intrinsic viscosity $[\eta]$ of 1.86 dl/g, MFR of 2.2 g/10 min, T_{m1} of 156°C and T_{m2} of 161°C. The equilibrium melting temperature (T_m) determined from the formula (Eq-1) and the difference ($T_m - T_R$) between T_m and the polymerization temperature (T_R) according to the present invention are summarized in Table 2.

[0137]

[Comparative Example 3]

The procedure of the Example 1 was repeated except that 300 mL of cyclohexane was used as a solvent for solution polymerization, and the internal temperature of the autoclave was kept at 40°C before and during the polymerization reaction. After the start of polymerization, the removal of heat in a polymerizer became difficult and then the polymerization was stopped. After the stop of polymerization, the pressure was released while keeping the temperature at 40°C to be brought into

ordinary pressure. Thereafter, unreacted propylene was purged while keeping the temperature at 40°C. It was confirmed that a significant amount of a polymer was deposited, by the visual observation for the polymer solution in the autoclave after a top plate of the autoclave was opened. The amount of the resulting polymer was 76.13 g. The polymerization activity of the propylene polymerization was 152.3 kg/mmol-Zr·hr, and the resulting polymer had an intrinsic viscosity $[\eta]$ of 1.78 dl/g, MFR of 3.1 g/10 min, and T_{m1} of 157°C. The equilibrium melting temperature (T_M) determined from the formula (Eq-1) and the difference ($T_M - T_R$) between T_M and the polymerization temperature (T_R) according to the present invention are summarized in Table 2.

[0138]

15 [Example 5]

The procedure of the Example 1 was repeated except that 300 mL of the solvent B was used as a solvent for solution polymerization and the internal temperature of the autoclave was kept at 60°C before and during the polymerization reaction. Since the control of exothermic heat during the polymerization was easy, it was presumed that the polymerization proceeded in a homogenous condition. After the completion of polymerization, the pressure was released while keeping the temperature at 60°C to be brought into ordinary pressure. Thereafter, unreacted

propylene was purged while keeping the temperature at 60°C. It was confirmed that the polymer solution was in a homogenous condition, by the visual observation for the polymer solution in the autoclave after a top plate of the autoclave was opened.

5 The amount of the resulting polymer was 21.61 g. The polymerization activity of the polypropylene polymerization was 43.2 kg/mmol-Zr·hr, and the resulting polymer had an intrinsic viscosity $[\eta]$ of 1.41 dl/g, MFR of 7.5 g/10 min, T_{m1} of 149°C and T_{m2} of 157°C. The equilibrium melting temperature (T_M)
10 determined from the formula (Eq-1) and the difference ($T_M - T_R$) between T_M and the polymerization temperature (T_R) according to the present invention are summarized in Table 2.

[0139]

[Example 6]

15 The procedure of the Example 1 was repeated except that 150 mL of cyclohexane and 150 mL of the solvent B were used as a solvent for solution polymerization. Since the control of exothermic heat during the polymerization was easy, it was presumed that the polymerization proceeded in a homogenous
20 condition. After the completion of polymerization, the pressure was released while keeping the temperature at 50°C to be brought into ordinary pressure. Thereafter, unreacted propylene was purged while keeping the temperature at 50°C. It was confirmed that the polymer solution was in a homogenous

condition, by the visual observation for the polymer solution in the autoclave after a top plate of the autoclave was opened. The amount of the resulting polymer was 37.29 g. The polymerization activity of the polypropylene polymerization was 74.6 kg/mmol-Zr·hr, and the resulting polymer had an intrinsic viscosity $[\eta]$ of 1.55 dl/g, MFR of 5.0 g/10 min, T_{m1} of 154°C and T_{m2} of 159°C. The equilibrium melting temperature (T_M) determined from the formula (Eq-1) and the difference ($T_M - T_R$) between T_M and the polymerization temperature (T_R) according to the present invention are summarized in Table 2.

[0140]

[Comparative Example 4]

The procedure of the Example 1 was repeated except that 300 mL of the solvent B was used as a solvent for solution polymerization. After the start of polymerization, the removal of heat in a polymerizer became difficult and then the polymerization was stopped. After the stop of polymerization, the pressure was released while keeping the temperature at 50°C to be brought into ordinary pressure. Thereafter, unreacted propylene was purged while keeping the temperature at 50°C. It was confirmed that a significant amount of a polymer was deposited, by the visual observation for the polymer solution in the autoclave after a top plate of the autoclave was opened. The amount of the resulting polymer was 37.92 g. The

polymerization activity of the polypropylene polymerization was 75.8 kg/mmol-Zr·hr, and the resulting polymer had an intrinsic viscosity $[\eta]$ of 1.73 dl/g, MFR of 3.1 g/10 min, T_{m1} of 154°C and T_{m2} of 159°C. The equilibrium melting temperature (T_M) determined from the formula (Eq-1) and the difference ($T_M - T_R$) between T_M and the polymerization temperature (T_R) according to the present invention are summarized in Table 2.

[0141]

[Comparative Example 5]

10 The procedure of the Example 1 was repeated except that 75 mL of cyclohexane and 225 mL of the solvent B were used as a solvent for solution polymerization. After the start of polymerization, the removal of heat in a polymerizer became difficult and then the polymerization was stopped. After the
15 stop of polymerization, the pressure was released while keeping the temperature at 50°C to be brought into ordinary pressure. Thereafter, unreacted propylene was purged while keeping the temperature at 50°C. It was confirmed that a significant amount of a polymer was deposited, by the visual observation for the
20 polymer solution in the autoclave after a top plate of the autoclave was opened. In the visual observation of syndiotactic polypropylene separately prepared in a glass vessel, a significant amount of a polymer deposited in the above polymerization conditions. The amount of the resulting polymer

was 47.07 g. The had a polymerization activity of the polypropylene polymerization was 94.1 kg/mmol-Zr·hr, and the resulting polymer had an intrinsic viscosity $[\eta]$ of 1.63 dl/g, MFR of 3.8 g/10 min, T_{m1} of 154°C and T_{m2} of 159°C. The equilibrium melting temperature (T_M) determined from the formula (Eq-1) and the difference ($T_M - T_R$) between T_M and the polymerization temperature (T_R) according to the present invention are summarized in Table 2.

[0142]

10 [Example 7]

The procedure of the Example 1 was repeated except that 300 mL of the solvent A was used as a solvent for solution polymerization, and the internal temperature of the autoclave was kept at 60°C before and during the polymerization. Since the control of exothermic heat during the polymerization was easy, it was presumed that the polymerization proceeded in a homogenous condition. After the completion of polymerization, the pressure was released while keeping the temperature at 60°C to be brought into ordinary pressure. Thereafter, unreacted propylene was purged while keeping the temperature at 60°C. It was confirmed that the polymer solution was in a homogenous condition, by the visual observation for the polymer solution in the autoclave after a top plate of the autoclave was opened. The amount of the resulting polymer was 22.84 g. The

polymerization activity of the polypropylene polymerization was 45.7 kg/mmol-Zr·hr, and the resulting polymer had an intrinsic viscosity $[\eta]$ of 1.42 dl/g, MFR of 8.0 g/10 min, T_{m1} of 149°C and T_{m2} of 157°C. The equilibrium melting temperature (T_M) determined from the formula (Eq-1) and the difference ($T_M - T_R$) between T_M and the polymerization temperature (T_R) according to the present invention are summarized in Table 2.

[0143]

[Example 8]

10 The procedure of the Example 1 was repeated except that 300 mL of the solvent A was used as a solvent for solution polymerization. It was difficult to say that the control of exothermic heat during the polymerization was easy, but the polymerization could be carried out while controlling the
15 polymerization condition, it was presumed that the polymerization proceeded in a white-turbidity state that a part of the polymer was deposited. After the completion of polymerization, the pressure was released while keeping the temperature at 50°C to be brought into ordinary pressure.
20 Thereafter, unreacted propylene was purged while keeping the temperature at 50°C. It was confirmed that the polymer solution was in a white-turbidity state, by the visual observation for the polymer solution in the autoclave after a top plate of the autoclave was opened. The amount of the resulting polymer was

31.03 g. The polymerization activity of the polypropylene polymerization was 62.1 kg/mmol-Zr·hr, and the resulting polymer had an intrinsic viscosity $[\eta]$ of 1.70 dl/g, MFR of 4.6 g/10 min, T_{m1} of 154°C and T_{m2} of 160°C. The equilibrium melting temperature (T_m) determined from the formula (Eq-1) and the difference ($T_m - T_R$) between T_m and the polymerization temperature (T_R) according to the present invention are summarized in Table 2.

[0144]

[Table 2]

	Solvent for solution polymeri- zation (volume ratio)	Polymeri- zation tempera- ture (T_R)	Condition of solution during polymeri- zation	Volume fraction of polymer (v_2)	Equili- brium melting tempera- ture (T_M)	$T_M - T_R$
		$^{\circ}\text{C}$			$^{\circ}\text{C}$	$^{\circ}\text{C}$
Ex. 1	cyclohexane/ n-heptane mixed solvent (50:50)	50	dis- solution	0.12	92.35	42.35
Ex. 2	n-heptane	60	white-turbidity state	0.10	100.4	40.4
Ex. 3	cyclohexane/ n-heptane mixed solvent (25:75)	50	white-turbidity state	0.04	91.63	41.63
Ex. 4	cyclohexane	50	dis- solution	0.16	89.19	39.19
Ex. 5	solvent B	60	dis- solution	0.08	95.81	35.81
Ex. 6	cyclohexane/ solvent B mixed solvent (50:50)	50	dis- solution	0.14	90.91	40.91
Ex. 7	solvent A	60	dis- solution	0.09	91.93	31.93
Ex. 8	solvent A	50	white-turbidity state	0.12	93.81	43.81
Com. Ex. 1	n-heptane	40	deposition	0.10	100.4	60.4
Com. Ex. 2	cyclohexane/ n-heptane mixed solvent (50:50)	40	deposition	0.23	99.59	59.59
Com. Ex. 3	cyclohexane	40	deposition	0.30	98.9	58.9
Com. Ex. 4	solvent B	50	deposition	0.15	99.8	49.8
Com. Ex. 5	cyclohexane/ solvent B mixed solvent (25:75)	50	deposition	0.18	97.02	47.02

[0145]

[Example 9]

To one feed opening of a 310 L volume continuous polymerizer,
5 the solvent A dehydrated to be purified was fed at a rate of 75
L/hr, and to another feed opening, a hexane slurry of TMA-341
(125 mmol/L in terms of aluminum atom) manufactured by Tohso Fine
Chem Co., Ltd. was fed at a rate of 0.1 L/hr and a solution of
solvent A (0.25 mmol/L) of dibenzylmethylen
10 (cyclopentadienyl) (2,7-diphenyl-3,6-di-tert-butylfluorenyl)
zirconium dichloride prepared in Synthetic Example 1 was fed at
a rate of 0.4 L/hr continuously (total of the solvent A was 75.5
L/hr). Simultaneously, to the other feed opening of the
polymerizer, propylene was continuously fed at a rate of 12.4
15 kg/hr and continuous solution polymerization was carried out at
a polymerization temperature of from 60 to 70°C, under the total
pressure of from 0.5 to 0.7 MPaG at a retention time of 1.0 hr.
The control of exothermic heat during the polymerization was
extremely easy. It was confirmed the polymer solution was in
20 a homogenous condition from an inspection watch window with which
the polymerizer was equipped.

[0146]

The solution of solvent A of polypropylene produced in the
polymerizer was continuously discharged at a flow rate of 100

L/hr through a draining port provided on the polymerizer bottom and introduced into a connecting pipe whose jacket part was heated with a 25 kg/cm² steam so that the temperature of the solution of solvent A of polypropylene was kept at from 70 to 180°C. On the position just close to the connecting pipe, a feed opening for injecting methanol, which was a catalyst quencher, was provided and methanol was joined together with the solution of solvent A by injecting at a rate of about 0.1 L/hr. The solution of solvent A kept at about 180°C in the connecting pipe equipped with the steam jacket was continuously transported into a flash vessel at a rate of about 100.1 L/hr while regulating the opening of a pressure controlling valve provided at the end of the connecting pipe so that the pressure was kept to be about 4 MpaG. In the transportation to the flash vessel, the solution temperature and the opening of a pressure controlling valve were set so that the pressure in the flash vessel was kept to be about 0.1 MpaG, and the temperature of the vapor part in the flash vessel was kept to be about 190°C. As a result, a polypropylene was obtained at a production rate of 7.0 to 8.0 kg/hr. The polymerization activity of polypropylene polymerization was 67.1 kg/mmol-Zr•hr, and the resulting polypropylene had a number average molecular weight of 92,000 and a weight average molecular weight of 19,9000, as measured by GPC, an intrinsic viscosity $[\eta]$ of 1.5 dl/g, T_{m1} of 148°C, T_{m2} of 156°C, a rrrr

fraction of 93.1% and an amount of the n-decane soluble of not more than 0.6 % by weight.

[0147]

[Comparative Example 6]

5 The continuous polymerization was carried out in the condition of Example 1 except that the polymerization temperature was 30°C. After 5 hr from the start of the polymerization, the removal of heat in the polymerizer became difficult and the polymerization was stopped.

10 [0148]

[Example 10]

To one feed opening of a 310 L volume continuous polymerizer, the solvent A dehydrated and purified was fed at a rate of 33 L/hr and cyclohexane was fed at a rate of 33 L/hr, and to another
15 feed opening, TMAO-341 (150 mmol/L in terms of aluminum atom), and a solution of the solvent A (0.30 mmol/L) of dibenzylmethylenecyclopentadienyl (2,7-diphenyl-3,6-di-tert-butylfluorenyl) zirconium dichloride prepared in Synthetic Example 1 at a rate of 0.15 L/hr were fed continuously
20 (the total solvent: 66 L/hr). Simultaneously, to the other feed opening of the polymerizer, propylene was continuously fed at a rate of 15.9 kg/hr and continuous solution polymerization was carried out at a polymerization temperature of 55°C, under the total pressure of 0.7 MPaG for a retention time of 1.0 hr. The

control of exothermic heat during the polymerization was extremely easy. It was confirmed that the polymer solution was in a homogenous condition, from an inspection window with which polymerizer was equipped.

5 The solution of the solvent A of polypropylene produced in the polymerizer was continuously discharged in a flow rate of 100 L/hr through a draining port provided on the polymerizer bottom and introduced into a connecting pipe whose jacket part was heated with a 25 kg/cm² steam so that the temperature of the
10 solution of the solvent A of polypropylene was kept at from 70 to 180°C. On the position just close to the connecting pipe, a feed opening for injecting methanol, which was a catalyst quencher, was provided and methanol was joined together with the hexane solution by injecting at a rate of about 10 L/hr. The
15 hexane solution kept at about 180°C in the connecting pipe equipped with the stream jacket was continuously transported into a flash vessel at a rate of about 100 L/hr while regulating the opening of a pressure controlling valve provided at the end of the connecting pipe so that the pressure was kept to be about
20 4 MpaG. In the transportation to the flash vessel, the solution temperature and the opening of the pressure controlling valve were set so that the pressure in the flash vessel was kept to be about 0.1 MpaG, and the temperature of the vapor part in the flash vessel was kept to be about 190°C. As a result, a

polypropylene was obtained in a production rate of 4.0 to 6.0 kg/hr. The polymerization activity of the polypropylene polymerization was 95.6 kg/mmol-Zr·hr, and the resulting polypropylene had an MFR of 4.9 g/10 min, T_{m1} of 154°C and T_{m2} of 160°C.

[0149]

[Example 11]

To one feed opening of a 1.0 L volume continuous polymerizer, the solvent A dehydrated and purified was fed at a rate of 0.32 L/hr, and to another feed opening, a hexane slurry of TMAO-341 (50 mmol/L in terms of aluminum atom) and a solvent A-containing solution (0.1 mmol/L) of dibenzylmethylenecyclopentadienyl (2,7-diphenyl-3,6-di-tert-butylfluorenyl) zirconium dichloride at a rate of 0.012 L/hr were fed continuously (the total of the solvents: 0.65 mL/hr). Simultaneously, to the other feed opening of the polymerizer, propylene was continuously fed at a rate of 327 ml/hr and

continuous solution polymerization was carried out at a polymerization temperature of 50°C, under the total pressure of 3.6 MPaG for a retention time of 1.0 hr. The control of exothermic heat during the polymerization was extremely easy.

- 5 It was confirmed that the polymer solution was in a homogenous condition, from an inspection window with which the polymerizer was equipped.

The polypropylene solution of the solvent A produced in the polymerizer was continuously discharged at a flow rate of
10 1 L/hr through a draining port provided on the polymerizer bottom and introduced into a connecting pipe whose jacket part was heated with a 10 kg/cm² steam so that the solution of solvent A of polypropylene was kept at a temperature from 50 to 80°C. On the position just close to the connecting pipe, a feed opening
15 for injecting methanol, which was a catalyst quencher, was provided and methanol was joined together with the solution of solvent A by injecting at a rate of about 0.15 L/hr. The hexane solution kept at about 70°C in the connecting pipe equipped with the stream jacket was continuously transported into a flash
20 vessel at a rate of about 1 l/hr while regulating the opening of a pressure controlling valve provided at the end of the connecting pipe so that the pressure was kept to be about 3.6 MpaG. In the transportation to the flash vessel, the opening of the pressure controlling valve was set so that the pressure

in the flash vessel was kept to be about 3.6 MpaG. As a result, a polypropylene was obtained in a production rate of 70g/hr. The polymerization activity of the polypropylene polymerization was 95.6 kg/mmol-Zr·hr, and the resulting polypropylene had an MFR of 4.3 g/10 min, T_{m1} of 154°C, T_{m2} of 160°C, and a rrrr fraction of 95.2%.

[0150]

[Example 12]

To one feed opening of a 2000 L volume (working volume of 600 L) continuous polymerizer, a mixed solvent of cyclohexane and the solvent B (mixing ratio of 1:1), which are dehydrated and purified, was fed at a rate of 370 L/hr, and to another feed opening, a pre-mixed solution of the solvent B (0.30 mmol/L) of a hexane slurry of TMAO-341 (150 mmol/L in terms of aluminum atom) manufactured by Tohso Fine Chem Co., Ltd. and a solution of solvent B (0.30 mmol/L) of dibenzylmethylenecyclopentadienyl (2,7-diphenyl-3,6-di-tert-butylfluorenyl)

zirconium dichloride were continuously fed at a rate of 0.32 L/hr (total solution: 370.32 L/hr). Simultaneously, to the other feed opening of the polymerizer, propylene was continuously fed at a rate of 85.0 kg/hr and continuous solution polymerization was carried out at a polymerization temperature of from 55 to 57°C, under the total pressure of from 0.7 to 0.75 MPaG for a retention time of 1.0 hr. The control of exothermic heat during the polymerization was extremely easy. It was confirmed that the polymer solution was in a homogenous condition, from an inspection window with which the polymerizer was equipped.

The polypropylene mixed solution of cyclohexane and the solvent B (mixing ratio of 1:1) produced in the polymerizer was continuously discharged at a flow rate of 600 L/hr through a draining port provided on the polymerizer bottom and introduced into a connecting pipe which jacket part was heated with a 3 to 25 kg/cm² steam so that the polypropylene mixed solution of cyclohexane and the solvent B (mixing ratio of 1:1) was kept at a temperature from 150 to 190°C. On the position just close to the connecting pipe, a feed opening for injecting methanol, which was a catalyst quencher, was provided and methanol was joined together with the mixed solvent of cyclohexane and the solvent B (mixing volume ratio of 1:1) by injecting at a rate of about 0.75 L/hr. The mixed solution of cyclohexane and the solvent B (mixing ratio: 1:1) kept at about 190°C in the connecting pipe

equipped with the stream jacket was continuously transported into a flash vessel at a rate of about 600.75 L/hr while regulating the opening of a pressure controlling valve provided at the end of the connecting pipe so that the pressure was kept to be about 4.3 MpaG. In the transportation to the flash vessel, the solution temperature and the opening of the pressure controlling valve were set so that the pressure in the flash vessel was kept to be about 0.1 MpaG, and the temperature of the vapor part in the flash vessel was kept to be about 180°C. As a result, a polypropylene was obtained in a production rate of 20 to 25 kg/hr. The polymerization activity of the polypropylene polymerization was 257 kg/mmol-Zr·hr, and the resulting polypropylene had a number average molecular weight of 104,000 and a weight average molecular weight of 197,000, as measured by GPC, an intrinsic viscosity $[\eta]$ of 1.54 dl/g, T_{m1} of 155°C, T_{m2} of 160°C and a rrrr fraction of 92.7%.

POSSIBILITY OF INDUSTRIAL USE

[0153]

Syndiotactic propylene polymers having a narrow composition distribution, a high melting point and a high molecular weight can be prepared with high activity and high efficiency by the production process with the solution polymerization according to the present invention. The resulting polymers are raw material resins useful in the field

of various molding materials such as films and the like. Therefore, the production process of the present invention has a great influence on the industrial world.

CLAIMS

1. A process for producing a syndiotactic propylene polymer having a syndiotactic pentad fraction (rrrr fraction), as measured by ^{13}C -NMR, of at least 85%, a melting point (T_m), as measured by DSC, of from 145°C to 170°C , and an intrinsic viscosity $[\eta]$ of 0.1 to 10 dl/g, which process comprises a step (P₁) of solution polymerizing, without deposition of polymers, propylene singly or propylene and at least one monomer selected from ethylene and an α -olefin having 4 to 10 carbon atoms at a polymerization temperature (T_R) of from 30°C to 250°C in an inert hydrocarbon solvent in the presence of an olefin polymerization catalyst which comprises;

(A) a bridged metallocene compound represented by the following formula (I), and

(B) at least one compound selected from

(b-1) an organoaluminum oxy compound,

(b-2) a compound capable of forming an ion pair by reacting with the metallocene compound (A), and

(b-3) an organoaluminum compound.

[Chem.1]



in which M is a titanium atom, a zirconium atom or a hafnium atom,


Q is selected from a halogen atom, a hydrocarbon group, an anion ligand and a neutral ligand coordinatable with a lone electron pair, j is an integer of 1 to 4, R^a and R^b may be identically or differently a single nuclear or polynuclear hydrocarbon residue capable of forming a sandwich structure together with M, Y is a carbon atom or a silicon atom, and R^c and R^d may be the same or different from each other, is selected from hydrogen, a hydrocarbon group and a silicon atom-containing group and further may be bonded each other to form a ring, wherein the polymerization temperature (T_R), and the equilibrium melting temperature (T_M) satisfy the following formula (Eq-1)

$$T_M - T_R \leq 45^\circ\text{C} \quad \dots(\text{Eq-1})$$

2. The process as claimed in claim 1 wherein the step (P₁) is carried out continuously.
3. The process as claimed in claim 1 or 2 wherein the inert hydrocarbon solvent is a hydrocarbon having 5 to 12 carbon atoms.
4. The process as claimed in any one of claims 1 to 3 wherein the inert hydrocarbon solvent has at least one structure selected from a branched structure, a ring structure and an aromatic structure in the molecule.
5. The process as claimed in any one of claims 1 to 4 wherein the inert hydrocarbon solvent comprises at least one selected from a branched hydrocarbon having a branched structure, a cyclic aliphatic hydrocarbon having a ring structure and an aromatic hydrocarbon.
6. The process as claimed in any one of claims 1 to 5 wherein the bridged metallocene compound (A) shows C_s symmetry.

7. The process as claimed in any one of claims 1 to 6 wherein the bridged metallocene compound (A) is represented by the following formula (II);

[Chem.2]



5

in which R^1 , R^2 , R^3 , R^4 , R^5 , R^6 , R^9 and R^{12} each are selected from hydrogen, a hydrocarbon group, and a silicon atom-containing group and they may be the same or different from each other, and adjacent groups may be bonded to form a ring; R^6 and R^7 are the same atoms or groups selected from hydrogen, a hydrocarbon group and a silicon atom-containing group, and may be bonded to form a ring; R^{10} and R^{11} are the same atoms or groups selected from hydrogen, a hydrocarbon group and a silicon atom-containing group, and may be bonded to form a ring; R^6 , R^7 , R^{10} and R^{11} are not hydrogen atoms simultaneously; R^{17} and R^{18} each are an alkyl group, an aralkyl group, an aryl group or a substituted aryl group, may be identical or different each other, and may be bonded to form a ring; M is a titanium atom, a zirconium atom or a hafnium

10

15

atom; Y is a carbon atom or a silicon atom; Q is a combination of identically or differently selected from a halogen atom, a hydrocarbon group, an anion ligand and a neutral ligand coordinatable with a lone electron pair; and j is an integer of 1 to 4.

8. The process as claimed in claim 7, wherein all of R^6 , R^7 , R^{10} and R^{11} of the bridged metallocene compound (A) represented by the formula (II) are not hydrogen atoms.

9. The process as claimed in any one of claims 1 to 8 wherein the syndiotactic propylene polymer has a melt flow rate (MFR), as measured at 230°C under a load of 2.16 kg, of 0.1 to 50 g/10 min.

10. The process as claimed in claim 1 to 9, wherein the syndiotactic propylene polymer has a syndiotactic pentad fraction (rrrr fraction), as measured by ^{13}C -NMR, of at least 93%.

11. The process as claimed in any one of claims 1 to 10, which further comprises, following the polymerization step (P_1), a post-treatment step (P_2) of optionally heating a polymer solution (S) discharged from the polymerization step to the temperature not lower than the polymerization temperature and not higher than 250°C, and then carrying out flash procedure at a pressure in a flash vessel of from 0.00 to 0.5 MPa·G thereby distilling off the solvent and the monomer.

12. The process as claimed in any one of claims 1 to 11, wherein at any position of a transporting line from the polymerization step (P_1) to the post-treatment step (P_2), the polymer solution (S) is transported by introducing with pressure a hydrocarbon having 5 to 12 carbon atoms.

13. The process as claimed in claim 12, wherein the hydrocarbon having 5 to 12 carbon atoms is the solvent same as the inert hydrocarbon solvent submitted to the solution polymerization reaction.

ABSTRACT

It is an object of the present invention to provide a process for producing a syndiotactic propylene polymer with high polymerization activity and high efficiency by a solution
5 polymerization method without deposition of polymers (excluding a white state), and a production process capable of conducting the above production continuously, provided that these processes could not be attained conventionally.

The present invention is:

- 10 a process for producing a syndiotactic propylene polymer having a syndiotactic pentad fraction (rrrr fraction), as measured by ^{13}C -NMR, of at least 85%, a melting point (T_m), as measured by DSC, of from 145°C to 170°C, and an intrinsic viscosity $[\eta]$ of 0.1 to 10 dl/g, which process comprises a step
15 (P_1) of solution polymerizing propylene singly or propylene and at least one monomer selected from ethylene and an α -olefin having 4 to 10 carbon atoms at a polymerization temperature (T_R) of from 30°C to 250°C in an inert hydrocarbon solvent in the presence of an olefin polymerization catalyst which comprises;
20 (A) a bridged metallocene compound represented by the following formula (I), and
(B) at least one compound selected from
(b-1) an organoaluminum oxy compound,
(b-2) a compound capable of forming an ion pair by reacting

with the metallocene compound (A), and

(b-3) an organoaluminum compound.

[Chem.1]



5 in which M is a titanium atom or the like, Q is a halogen atom
 or the like, j is an integer of 1 to 4, R^a and R^b may be identically
 or differently a single nuclear or polynuclear hydrocarbon
 residue capable of forming a sandwich structure together with
 M, Y is a carbon atom or a silicon atom, and R^c and R^d may be
 10 the same or different from each other, is selected from hydrogen,
 a hydrocarbon group and a silicon atom-containing group and
 further may be bonded each other to form a ring.