

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
26 June 2003 (26.06.2003)

PCT

(10) International Publication Number
WO 03/051508 A1

(51) International Patent Classification⁷: **B01J 21/08**,
21/12, 21/14, 23/00, 23/08, C07C 209/16

(21) International Application Number: PCT/US02/38649

(22) International Filing Date: 4 December 2002 (04.12.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/340,658 14 December 2001 (14.12.2001) US
10/124,925 18 April 2002 (18.04.2002) US

(71) Applicant: **HUNTSMAN PETROCHEMICAL CORPORATION** [US/US]; Legal Department, 7114 North Lamar Blvd., Austin, TX 78752 (US).

(72) Inventors: **RENKEN, Terry, L.**; 11103 Yucca Ddrive, Austin, TX 78759 (US). **FORKNER, Matthew, W.**; 9002 Braesgate, Austin, TX 78717 (US).

(74) Agents: **WHEWELL, Christopher, J.** et al.; Huntsman Corporation, 7114 North Lamar, Austin, TX 78752 (US).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: ADVANCES IN AMINATION CATALYSIS

(57) Abstract: Provided herein are catalysts useful in reductive amination, which include nickel, copper, zirconium and/or chromium, oxygen, and tin. The presence of the tin increases the selectivity of the catalyst in reductive aminations over the catalysts of the prior art.



WO 03/051508 A1