

DIMETHYLALUMINUM HYDRIDE COMPOSITION, PROCESS FOR PRODUCING
THE SAME AND METHOD OF REDUCING VISCOSITY OF
DIMETHYLALUMINUM HYDRIDE

FIELD OF THE INVENTION

The present invention relates to a dimethylaluminum hydride composition, a process for producing the same and a method of reducing the viscosity of dimethylaluminum hydride. More particularly, it relates to a dimethylaluminum hydride composition having a viscosity of not more than about 2000 mPa·s ("mPa·s is equivalent to "centipoise") at normal temperature (25°C), which is superior in handling properties, a process for producing the same and a method of reducing the viscosity of dimethylaluminum hydride to not more than about 20000 mPa·s at normal temperature under atmospheric pressure.

BACKGROUND OF THE INVENTION

Dimethylaluminum hydride (hereinafter abbreviated to "DMAH") is mainly used as an aluminum raw material in a chemical vapor deposition process (e.g. metal organic chemical vapor deposition, metal organic molecular beam epitaxy, etc.). In the process, the dimethylaluminum hydride is introduced into a vapor deposition device according to a method (1) comprising supplying a carrier gas

0 08 16 17
pat. 16, 17

such as hydrogen whose flow is controlled by a mass flow controller into a DMAH solution in a storage container, bubbling the solution by the carrier gas and then introducing the bubbled carrier gas saturated with DMAH into a vapor deposition device; method (2) comprising directly heating a DMAH storage container to evaporate DMAH at a temperature below its boiling point and introducing DMAH vapor into a vapor deposition device while controlling the flow using a mass flow controller; and method (3) comprising pressurizing a DMAH storage container using a carrier gas such as hydrogen or nitrogen, transferring DMAH in the container to an evaporator in the liquid state, heating DMAH in the evaporator to evaporate DMAH and supplying a carrier gas to introduce DMAH vapor into a vapor deposition device.

However, DMAH has the following problems on use. That is, it is difficult to transfer DMAH from a storage container to the device to be used and to conduct bubbling at the time of the vapor deposition reaction because DMAH has high viscosity, i.e., from several thousands to several ten thousands at room temperature. From the manufacturing point of view, it is difficult to transfer or deactivate DMAH as compared with other normal organic aluminums because DMAH has a self-ignition property and high viscosity. A method of reducing the viscosity of dimethylaluminum hydride has thus been desired.

01-128112

SUMMARY OF THE INVENTION

Under these circumstances, the present inventors have intensively studied methods of reducing the viscosity of dimethylaluminum hydride even at normal temperature under atmospheric pressure. As a result, it has been found that a remarkable effect of reducing the viscosity of DMAH is obtained when a very small amount of a Lewis base is added to DMAH. Thus, the present invention has been accomplished.

An object of the present invention is to provide a dimethylaluminum hydride composition having a low viscosity at normal temperature under atmospheric pressure, which is easily handled.

Another object of the present invention is to provide a process for producing the same.

Still another object of the present invention is to provide a method of reducing the viscosity of dimethylaluminum hydride.

These objects as well as other objects and advantages of the present invention will become apparent to those skilled in the art from the following description.

In summary, the present invention provides a dimethylaluminum hydride composition having a viscosity of not more than about 2000 mPa·s at 25°C, comprising dimethylaluminum hydride and at least one Lewis base in an amount of 0.01 to 10 % by weight of dimethylaluminum

hydride, and a process for producing the same.

The present invention further provides a method of reducing the viscosity of dimethylaluminum hydride to not more than about 2000 mPa·s at normal temperature (25°C) under atmospheric pressure, which comprises adding at least one Lewis base to dimethylaluminum hydride in an amount of 0.01 to 10 % by weight of dimethylaluminum hydride.

DETAILED DESCRIPTION

The present invention relates to a DMAH composition comprising dimethylaluminum hydride and a Lewis base in an amount of usually from 0.01 to about 10 % by weight, preferably from about 0.03 to about 1.0 % by weight, based on DMAH, wherein the viscosity of the DMAH composition at normal temperature (25°C) is not more than about 2000 mPa·s, normally not more than about 1000 mPa·s, and preferably from about 10 to about 500 mPa·s. Such a composition is extremely superior in handling properties.

According to a typical process for producing the DMAH composition, a Lewis base is added in the amount of usually from 0.01 to about 10 % by weight, preferably from about 0.03 to about 1.0 % by weight based on DMAH, followed by mixing.

The DMAH to be used is not a specific one, and is DMAH having a viscosity of more than 2000 mPa·s at normal

temperature, normally from several thousands to several ten thousands mPa's, particularly from about 4000 to 20000 mPa's and more particularly from about 4000 to 10000 mPa's at normal temperature (25 °C), which is commercially available or obtainable by a known synthetic method, for example, by reacting dimethylaluminum chloride with alkali metal hydride or by reacting trimethylaluminum with lithium aluminum hydride (e.g., USP 4,924,019 and J. Am. Chem. Soc. 75, 835 (1953)).

The Lewis base used in the present invention refers to a compound having at least one single pair of electrons and which can be coordinated with DMAH. Examples of the Lewis base include organic compounds containing at least one element selected from the element groups Vb and VIb in the Periodic Table and organic compounds containing at least one element selected from N, P, As, O and S. Specific examples thereof include ethers such as diethyl ether, dibutyl ether, methyl butyl ether, anisole, diphenyl ether, benzyl ether, dimethoxyethane, diethoxyethane, tetrahydrofuran and dioxane; amines such as triethylamine, trioctylamine, dimethylpropylamine, dimethyldodecylamine, dimethylaminotrimethylsilane, dimethylallylamine, diisopropylethylamine, dimethylaniline, benzylethylaniline, tetramethylethylenediamine, tetramethyldiaminopropane and tetramethylhexamethylenediamine; heterocyclic compounds

having at least one nitrogen atom in a ring structure such as pyridine, dimethylaminopyridine, collidine, pyrazine, dimethylpyrazine, pyrazole, quinoline, isoquinoline, triazine, triazole, quinaldine, imidazole and benzylmethylimidazole; sulfides such as dimethyl sulfide, diethyl sulfide and diphenyl sulfide; heterocyclic compounds having at least one sulfur atom in a ring structure such as thiophene; phosphines such as triethylphosphine and triphenylphosphine; organoarsine such as triethylarsine, etc. Among them, diethyl ether, dibutyl ether, tetrahydrofuran, triethylamine, dimethyldodecylamine and dimethylaniline are preferred.

The Lewis base may be normally added to DMAH at normal temperature in an amount of usually from about 0.01 to about 10 % by weight, preferably from about 0.03 to about 1 % by weight of DMAH, followed by mixing. After the operation, there can be obtained a DMAH composition having a viscosity of not more than about 2000 mPa.s even at normal temperature (25 °C) under atmospheric pressure, which is superior in handling properties.

The upper limit of the amount of the Lewis base may be usually decided by the permissible purity of DMAH as limited by its application.

When the Lewis base is added in an amount of from 0.01 to 1 % by weight of DMAH, a sufficient effect of reducing

the viscosity of the resulting composition can usually be obtained in handling DMAH at normal temperature, i.e. a viscosity of not more than about 2000 mPa.s, preferably not more than about 1000 mPa.s, and more preferably not more than about 500 mPa.s.

The Lewis base to be used can suitably be selected depending on the application of the DMAH. The Lewis bases containing oxygen generally have a better effect in reducing the viscosity. When even a very small amount of oxygen impurity exerts a deleterious influence on the use of the DMAH composition, other Lewis bases such as compounds containing at least one nitrogen atom (i.e. amines and heterocyclic compounds having nitrogen atom in a ring structure) are preferably used.

A process comprising adding the Lewis base to DMAH, followed by mixing, is only shown as an example of a process for producing the DMAH composition according to the present invention. As a matter of course, the process of previously adding the Lewis base at the time of synthesizing DMAH may be used in the present invention if the amount of the Lewis base in the DMAH composition is sufficient for the purpose of reducing the viscosity.

The DMAH composition whose viscosity is reduced according to the present invention may be used as an aluminum raw material in the chemical vapor deposition

process after introduction into a vapor deposition device according to a method comprising bubbling a carrier gas such as hydrogen gas in a solution comprising the DMAH composition to form a vapor of DMAH, or a method comprising heating a solution comprising the DMAH composition in an evaporator to evaporate DMAH and supplying a carrier gas therein.

The method for evaporating the DMAH composition, method for introducing into the vapor deposition device, method for using in the vapor deposition device and devices used for these methods may be methods or devices which have hitherto been known, and are not specifically limited.

As described above, a DMAH composition of the present invention has a viscosity of not more than about 2000 mPa·s at normal temperature, normally not more than about 1000 mPa·s, which is superior in handling properties. The viscosity of DMAH can be easily reduced by an extremely simple operation of adding a very small amount of a Lewis base to DMAH. Therefore, the industrial utility value of the DMAH composition as the aluminum raw material in the chemical vapor deposition process is quite significant.

The following Examples and Comparative Example further illustrate the present invention in detail but are not to be construed to limit the scope thereof.

In the present invention, analysis of concentration of

ether in DMAH and viscosity analysis of DMAH were conducted by the method described below.

Analysis of ether: After DMAH was diluted with dodecane, the resulting solution was hydrolyzed. Then, the content of the ether (diethyl ether and THF) in water, dodecane and gas were respectively determined by gas chromatography, and the content was converted into the ether concentration to DMAH. As the amount of the ether calculated by the above analysis was found to be identical to the amount actually added, all of the amounts of Lewis base in the Examples and of heptane in the Comparative Example are shown by the amounts added.

Viscosity analysis of DMAH: After DMAH as a sample was supplied to one of two containers connected to each other with a capillary, an inert gas was introduced into this container under pressure and transferred to another container. At this point, the transfer amount and time were measured, and then they were substituted into the Poiseuille's equation to determine viscosity.

Example 1

Diethyl ether was added to commercially available DMAH (17 g) (manufactured by Sumitomo Chemical Industries Co., Ltd., viscosity: 7700 mPa·s, purity of 99.999 % calculated from inorganic material analysis) in the amount shown in Table 1 and, after stirring with a magnetic stirrer, the

viscosity of the resulting DMAH composition was measured at room temperature (25 °C). The results are shown in Table 1.

<Table 1>

Experiment No.	Amount of diethyl ether added	Viscosity of DMAH composition
1	None	7700
2	0.09	300
3	0.13	180
4	0.64	45
5	4.28	19

The amount of diethyl ether added is represented by % by weight based on DMAH.

Example 2

According to the same manner as that described in Example 1 except for adding THF in place of diethyl ether in the amount shown in Table 2, the mixture was stirred with a magnetic stirrer, and then the viscosity of the resulting DMAH composition was measured at room temperature (25 °C). The results are shown in Table 2.

<Table 2>

Experiment No.	Amount of THF added	Viscosity of DMAH composition
1	None	7700
2	0.03	1200
3	0.15	135

Example 3

According to the same manner as that described in Example 1 except for adding triethylamine in place of diethyl ether in the amount shown in Table 3, the mixture was stirred with a magnetic stirrer, and then the viscosity of the resulting DMAH composition was measured at room temperature (25 °C). The results are shown in Table 3.

<Table 3>

Experiment No.	Amount of triethylamine added	Viscosity of DMAH composition
1	None	7700
2	0.14	1100
3	0.71	140

Comparative Example 1

According to the same manner as that described in Example 1 except for adding heptane in place of diethyl

ether in the amount shown in Table 4, the mixture was stirred with a magnetic stirrer, and then the viscosity of the resulting DMAH composition was measured at room temperature (25 °C). The results are shown in Table 4.

<Table 4>

Experiment No.	Amount of heptane added	Viscosity of DMAH composition
1	None	7700
2	2.9	5600
3	17.1	1500
4	31.4	640

Example 4

N,N-dimethylaniline was added to commercially available DMAH (17 g) (manufactured by Sumitomo Chemical Industries Co., Ltd., viscosity: 10000 mPa·s, purity of 99.999 % calculated from inorganic material analysis) in the amount shown in Table 5 and, after stirring with a magnetic stirrer, the viscosity of the resulting DMAH composition was measured at room temperature (25°C). The results are shown in Table 5.

<Table 5>

Experiment No.	Amount of N,N-dimethylaniline	Viscosity of DMAH composition
1	None	10000
2	0.10	860
3	0.25	220

What is claimed is:

1. A dimethylaluminum hydride composition having a viscosity of not more than about 2000 mPa·s at 25 °C, comprising dimethylaluminum hydride and at least one Lewis base in an amount of from 0.01 to 10 % by weight based on the dimethylaluminum hydride.
2. The dimethylaluminum hydride composition according to claim 1, wherein the amount of the Lewis base contained is from 0.03 to 1.0 % by weight based on dimethylaluminum hydride.
3. The dimethylaluminum hydride composition according to claim 1, wherein the viscosity is not more than 1000 mPa·s at 25 °C.
4. The dimethylaluminum hydride composition according to claim 2, wherein the viscosity is not more than 500 mPa·s at 25 °C.
5. The dimethylaluminum hydride composition according to claim 1, wherein the Lewis base is an organic compound containing at least one element selected from element groups Vb and VIb in the Periodic Table.
6. The dimethylaluminum hydride composition according to claim 1, wherein the Lewis base is an organic compound containing at least one element selected from the group consisting of N, P, As, O and S.
7. The dimethylaluminum hydride composition according



* C L M S *

to claim 1, wherein the Lewis base is selected from the group consisting of diethyl ether, dibutyl ether, methyl butyl ether, anisole, diphenyl ether, benzyl ether, dimethoxyethane, diethoxyethane, tetrahydrofuran, dioxane, triethylamine, trioctylamine, dimethylpropylamine, dimethyldodecylamine, dimethylaminotrimethylsilane, dimethylallylamine, diisopropylethylamine, dimethylaniline, benzylethylaniline, tetramethylethylenediamine, tetramethyldiaminopropane, tetramethylhexamethylenediamine, pyridine, dimethylaminopyridine, collidine, pyrazine, dimethylpyrazine, pyrazole, quinoline, isoquinoline, triazine, triazole, quinaldine, imidazole, benzylmethylimidazole, dimethyl sulfide, diethyl sulfide, diphenyl sulfide, thiophene, triethylphosphine, triphenylphosphine and triethylarsine.

8. The dimethylaluminum hydride composition according to claim 7, wherein the Lewis base is selected from the group consisting of diethyl ether, dibutyl ether, tetrahydrofuran, triethylamine, dimethyldodecylamine and dimethylaniline.

9. A process for producing a dimethylaluminum hydride composition having a viscosity of not more than about 2000 mPa.s at 25 °C, which comprises adding at least one Lewis base to dimethylaluminum hydride in an amount of from 0.01 to 10 % by weight of the dimethylaluminum hydride.



THIS SHEET HAS BEEN
REPLACED

10. A method of reducing the viscosity of dimethylaluminum hydride to not more than about 2000 mPa·s, which comprises adding at least one Lewis base to dimethylaluminum hydride in an amount of 0.01 to 1 % by weight of the dimethylaluminum hydride.

11. The method according to claim 10, wherein the amount of the Lewis base is from 0.03 to 1.0 % by weight based on the dimethylaluminum hydride.

12. The method according to claim 10, wherein the viscosity is not more than 1000 mPa·s at 25 °C.

13. The method according to claim 10, wherein the viscosity is not more than 500 mPa·s at 25 °C.

14. The method according to claims 10, wherein the Lewis base is an organic compound containing at least one element selected from groups Vb and VIb in the Periodic Table.

15. The method according to claim 10, wherein the Lewis base is an organic compound containing at least one element selected from the group consisting of N, P, As, O and S.

16. The method according to claim 10, wherein the Lewis base is selected from the group consisting of diethyl ether, dibutyl ether, methyl butyl ether, anisole, diphenyl ether, benzyl ether, dimethoxyethane, diethoxyethane, tetrahydrofuran, dioxane, triethylamine, trioctylamine,



dimethylpropylamine, dimethyldodecylamine,
dimethylaminotrimethylsilane, dimethylallylamine,
diisopropylethylamine, dimethylaniline, benzylethylaniline,
tetramethylethylenediamine, tetramethyldiaminopropane,
tetramethylhexamethylenediamine, pyridine,
dimethylaminopyridine, collidine, pyrazine,
dimethylpyrazine, pyrazole, quinoline, isoquinoline,
triazine, triazole, quinaldine, imidazole,
benzylmethylimidazole, dimethyl sulfide, diethyl sulfide,
diphenyl sulfide, thiophene, triethylphosphine,
triphenylphosphine and triethylarsine.

17. The dimethylaluminum hydride composition according
to claim 16, wherein the Lewis base is selected from the
group consisting of diethyl ether, dibutyl ether,
tetrahydrofuran, triethylamine, dimethyldodecylamine and
dimethylaniline.

This Sheet Has Been Replaced



* C L M S *

0-027022

Abstract of the disclosure

DIMETHYLALUMINUM HYDRIDE COMPOSITION, PROCESS FOR PRODUCING
THE SAME AND METHOD OF REDUCING VISCOSITY OF
DIMETHYLALUMINUM HYDRIDE

The present invention provides a dimethylaluminum hydride composition having a viscosity of not more than about 2000 mPa·s at 25°C, comprising dimethylaluminum hydride and at least one the Lewis base in an amount of from 0.01 to 10 % by weight based on dimethylaluminum hydride. The resulting dimethylaluminum hydride composition is superior in handling properties. The present invention also provides a method for reducing the viscosity of dimethylaluminum hydride.

REPLACEMENT SHEET

12 JAN 1998

Substitute sheet - 12 January 1998

- 16 -

10. Use of a dimethylaluminum hydride composition according to any one of claims 1 to 8 as an aluminum raw material in a chemical vapor deposition process.

5 11. A dimethylaluminum hydride composition according to claim 1 substantially as hereinbefore described in any one of Examples 1 to 4.

12. A process according to claim 9 substantially as 10 hereinbefore described in any one of Examples 1 to 4.



* C L M S *

ment: all