

☒ Description : paged to paged
☒ Claim(s) : paged 31 to paged 34
☐ Drawing(s) : paged to paged
☐ Abstract : paged to paged

ABSORBENT ARTICLE HAVING A STABILIZING ABSORBENT ELEMENT

Field of the Invention

5

The present invention relates to an absorbent article for absorbing body fluids such as menstrual fluid, vaginal discharge and/or urine, and more particularly, to an absorbent article having a stabilizing element which is resistant to wet collapse, and provides the article with enhanced resistance to bunching and inward collapse due to lateral compressive forces imparted by a user's thighs so that a central absorbent portion of the article maintains contact with the perineal area of the user and thus reduces the probability of leakage and failure.

Background of the Invention

Conventional full-size sanitary protection and feminine hygiene products such as sanitary napkins, adult incontinence devices, etc., typically contain an absorbent element, a fluid-pervious body-contacting element and a fluid-impervious undergarment-facing element. These articles are intended to absorb body fluid from the wearer and retain the fluid in order to prevent the fluid from soiling the wearer's garments. Unfortunately, conventional feminine hygiene articles do not adequately fulfill women's protection requirements. Sanitary napkins generally have the capability of absorbing between 50 and 100 grams of fluid. However, soiling of a wearer's garments still occurs even when only 5 to 10 grams of fluid has been deposited on the absorbent articles. One of the primary reasons why

soiling occurs is that conventional napkins do not properly conform to the perineal area of a woman's body. When there is a space between the user and the pad, body fluid exudate tends to travel along the contours of the body and results in soiling of the undergarment.

One factor that contributes to poor fit and lack of conformity is napkin instability. When a compression force is applied to a sanitary napkin (e.g., by the lateral compressive forces of a user's thighs), the napkin tends to fold or bunch resulting in a smaller area of contact with the user's body resulting in a gap between the absorbent article and the user's body. The napkin center may also become depressed, i.e., move in a direction downward and away from the user's body. Fluid may then travel along the body and bypass the napkin resulting in soiling of the undergarment.

An additional factor that contributes to poor fit centers on the misconception that the outer genital area of females, longitudinally between the thighs in the areas of the urethral and vaginal openings, is curved; when in fact it is essentially flat or planar. Thus, there has been a tendency on the part of some inventors to develop curved products, wrongly assuming that the centermost portions of such a product will fit closely to the body.

For example, European Patent No. 091,412 depicts an absorbent product having an absorbent core which is convex in the center and has elasticized side margins. U.S. Patent No. 4,770,657 to Ellis also describes a curved sanitary napkin with elasticized side edges.

Another example of a curved sanitary napkin is illustrated in WO 88/04547 to Thoren which discloses a design in which elastic means are prestretched. This causes the napkin to be resiliently distorted so that the sides assume a convex shape when held against the user's body. Upon application of pressure, the shape will flatten out. However, when the pressure is reduced or eliminated, the napkin resumes its curved shape. Further this design lacks a structural element and, therefore, when wetted, will collapse and move away from the user and cause soiling of the undergarment.

Several prior art patents discuss absorbent systems which attempt to address the soiling problem in different ways. One method is to create a resilient and/or stabilized absorbent system in order to prevent the napkin from bunching when worn. For example, U.S. Patent No. 4,195,634 to DiSalvo describes a "stiffener means" which is incorporated into the napkin and positioned between the absorbent core and the barrier along the entire length of the pad to resist side compression. However, this design is deficient in that the stiffening/stabilizing element is located below the absorbent medium. The absorbent medium tends to collapse when exposed to fluid, causing it to move away from the wearer, despite the presence of the stiffener means. Furthermore, since the stiffener means is not conformable, it will not adapt to the body and will be uncomfortable to wear.

U.S. Patent No. 4,405,326 to Lenggham describes a design which is similarly deficient. U.S. Patent No. 4,217,901 to Bradstreet also describes a crush-resistant sanitary napkin, but does not specifically address the

issue of body-fit.

European Patent Applications 0 335 252 and 0 335 253 to Buell describe a disposable absorbent article having a flexure-resistant, deformation element that is not moisture-sensitive. The deformation element has a convex upward configuration when the napkin is worn and pressed inward by the thighs. The proposed design relies on the lateral compressive forces of the wearer's thighs to form a convex upward configuration. However, this design is also flawed with respect to maintaining body-fit and conformation since the convex configuration cannot consistently be controlled by thigh movement, as the napkin's ability to conform to the body relies heavily upon placement of the absorbent article and the wearer's anatomy. Furthermore, there is no means to insure that the absorbent article will stay in place at the appropriate portion of the anatomy. In addition, if the deformation element is not moisture-sensitive, the deformation element cannot be placed near the pad's surface because it cannot absorb fluid. Thus, the absorbent material in the pad which is closer to the body than the deformation element will tend to collapse when exposed to fluid, and move away from the body.

Other attempts to address the problems of bunching and absorbent collapse have suggested an increase in the thickness of the central portion of the absorbent element. Others suggest interlabial products that have a portion fitting between the labia, close to the vaginal orifice. For example, U.S. Patent No. 4,490,147 to Pierce describes a sanitary napkin having a raised center with absorbent pads which are arranged parallel to one another in a pyramid-shaped bundle. The pads are

movable with respect to one another and are encased by a liquid pervious cover material. However, such a napkin will not conform to the perineal cavity, particularly at the front and back. The pyramid shape may also cause
5 fluid to roll off the napkin's edge and cause soiling of the wearer's undergarment.

U.S. Patents Nos. 4,631,062 and 4,804,380 to Lassen generally describe self-conforming napkins for partial
10 labial disposition. The napkin contains a posterior region, including a raised profile for placement intermediate the wearer's labia majora and a flattened front portion for placement exterior of the clitoris and pubic mons. However, these products would tend to move
15 during wear and can easily become dislodged from the vestibule. Furthermore, interlabial napkins tend to be uncomfortable to wear for most women.

Another raised center napkin design is described in
20 U.S. Patent No. 2,662,527 to Jacks which discloses an absorbent pad having a main body member of absorbent material and a second absorbent material secured on the face of the main member. The second absorbent material is narrower and shorter than the main member and has
25 dimensions designed to allow it to fit between the labia. Such a design would tend to collapse when exposed to fluid and would be extremely likely to move in relation to the body of the wearer.

30 Similarly, a napkin described in U.S. Patent No. 3,406,689 to Hicks, has a dual discrete layer system in which the two pads are separated from one another and are freely movable with respect to each other. The two pads are installed separately, would tend to move and

are extremely inconvenient. Fluid may also travel from one pad to the edge of the other, resulting in staining the wearer's undergarment. U.S. Patent No. 4,433,972 to Malfitano also contains two pads, although the top pad
5 is hourglass in shape.

U.S. Patent No. 4,425,130 to Desmarais describes a sanitary napkin having a primary menstrual absorbent pad and a "panty protector" which are joined. Such a design
10 has the same types of deficiencies as those described above with regard to compound pads. For example, the panty protector member is intended to protect the user's garments from being soiled by fluids which are expelled from the primary menstrual pad or which inadvertently
15 pass the primary pad. However, this design may encourage fluid to wick to the edge of the panty protector and transfer to the user's garment. It is also possible for the panty protector to fold in and contact the face of the primary menstrual pad. Fluid
20 may then transfer to the user's panty if the panty folds up and around the edges of the panty protector, especially if the panty protector is thin.

Patent publication No. WO 92/07535 to Visscher and
25 Osborn discloses a liquid pervious spacing structure which moves the top body-facing cover sheet away from the absorbent core of the napkin. The spacing structure has an uncompressed and a compressed configuration and an upper and lower portion. However, the components of
30 this construction are unlikely to remain separated when exposed to fluid, due to wet-collapse.

Other products which are designed to protect undergarments from staining with body fluid are those

having side extensions that can wrap around a panty
crotch. Examples of such products are described in U.S.
Patent No. 3,397,697 to Rickard, U.S. Patent No..
4,285,343 to McNair, U.S. Patents Nos. 4,589,876 and
5 4,687,478 to Van Tilburg and EP Publication No. 0426235
to Osborn. Yet other examples of such designs are
described in U.S. Patent No. 4,608,407 to Mattingly,
U.S. Patent No. 4,911,701 to Mavinkurve and U.S. Patent
No. 4,900,320 to McCoy. However, these references
10 disclose methods for inhibiting undergarment staining .
which do not involve napkin fit and conformability.

Fluid migration along the body is a key element of
soiling. Fluid migration generally occurs when fluid is
15 not immediately absorbed into an absorbent article.
Accordingly, the better an absorbent article can
maintain contact with the body, the less likely that the
fluid will leak or migrate away from the absorbent
article and cause soiling.

20

SUMMARY OF THE INVENTION

It is an object of this invention to provide an
absorbent article, such as a sanitary napkin, which is
25 capable of conforming to the body and capturing fluid as
it leaves the body.

It is another object of this invention to provide
an absorbent article which is resistant to lateral
30 compressive forces which may be imparted by a user's
thighs.

Yet another object of this invention is to provide
an absorbent article which is comfortable, resilient,

resistant to wet collapse, yet highly absorbent.

In accordance with the present invention, there has been provided an absorbent article having longitudinal sides and transverse ends, a body-facing surface and a garment-facing surface, the article comprising:

- a) a fluid-permeable cover on the body-facing surface;
- b) a fluid-impermeable barrier on the garment-facing surface;
- c) a fluid-absorbent core containing wood pulp fluff between the fluid-permeable cover and the fluid impermeable barrier, the fluid-absorbent core having a central region and transverse ends and a thickness of at least 0.20 inches; and
- d) a stabilizing absorbent element adjacent an upper portion of the central region of the absorbent core, wherein the stabilizing element is capable of absorbing fluids and remaining stable when wet, and wherein the stabilizing element has a lateral width in a range of from at least 0.5 inches to less than 1.75 inches.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 shows the absorbent article of this invention in plan view from the body-facing side of the article.

Figure 2 is a cross-sectional view of the absorbent article shown in Figure 1 taken along the line 2-2.



Figure 3 is a cross-sectional view of the absorbent article shown in Figure 1 taken along the line 3-3.

DETAILED DESCRIPTION OF THE INVENTION

5

10 The present invention is directed to an absorbent article which is characterized as having a relatively thick fluid absorbent core, i.e. at least 0.20 inches thick, and an absorbent stabilizing element having a lateral width in a range of from at least 0.5 inches to less than 1.75 inches. It is considered an important feature of the present invention that the stabilizing element have a lateral width in the above critical dimensions. More specifically, it has now been found that the use of an absorbent stabilizing element with these dimensions, in combination with a relatively thick absorbent pulp fluff core, provides enhanced resistance to bunching and inward collapse due to lateral compressive forces imparted by a user's thighs.

20

25 When placed in an undergarment, the absorbent article of this invention provides a stable, resilient absorbent portion adjacent the labia majora and the vaginal orifice and will permit the central portion of the absorbent article to maintain an intimate fit against the labia majora. The stabilizing element provides resilience and resistance to wet-collapse in the area where it is needed, i.e., near the vaginal orifice or urethra, where the body fluid exits the user and impinges on the absorbent article.

30

Thus, the absorbent articles of this invention provide enhanced leakage protection due to better body fit without sacrificing comfort.



As illustrated in Figures 1-3, the absorbent articles 5 of this invention comprise the following elements:

- 5 a) a fluid-permeable cover 10 on the body-facing surface 20 of the article,
- b) a fluid-impermeable backsheet 30,
- c) an absorbent core 40 between the cover and backsheet comprising wood pulp fluff and a center portion 60 containing a stabilizing element 70, and
- 10 optionally a preferential bending zone 50.

Fluid-permeable cover sheet

The fluid-permeable cover sheet 10 may be composed of a woven or non-woven fibrous fabric or an apertured plastic sheet. The fibrous fabric may comprise

15 cellulosic fibers such as cotton or rayon, polyolefin fibers such as polyethylene, polypropylene, polyester, and combinations thereof. It may be an entangled fabric, modified-entangled fabric, spun-bond fabric,

20 melt-blown fabric, thermally bonded fabric or chemically bonded fabric.

Apertured plastic covers are well-known in the art. The cover may be selected from sheets known as Dri-weave

25 (U.S. Patent No. 4,324,246), Reticulon® (U.S. Patent No. 4,690,679) or Apex™ (U.S. Patent Application No. 07/744744), all herein incorporated by reference in their entirety.

30 Other suitable fluid-permeable cover sheets include absorbent, porous, dry-laid, nonwoven webs or scrim type materials such as those described in U.S. Pat. No. 4,880,419 to I.S. Ness and in U.S. Pat. No. 3,044,467 to Campau, in U.S. Pat. No. 3,463,154 to Hendricks and in

U.S. Pat. No. 3,570,491 to Sneider (herein incorporated by reference in their entirety).

5 Other suitable fluid-permeable cover sheets for use
on the absorbent articles of the present invention
include nonwovens made from hydrophobic fibers which
have been coated with an adhesive or have been subjected
to heat and/or pressure to fuse the individual fibers to
each other such as those described in U.S. 4,795,455 to
10 T. J. Luceri, in E.P. 354,502 to S. Cadioux, in E.P.
70,163 to A. T. Mays, and in U.S. 4,368,323 to R. P.
James (herein incorporated by reference in their
entirety). Such materials tend to have only limited
absorption thereby allowing passage to lower layers for
15 absorption and retention. As a result, the fluid is
wicked away from the body, leaving the surface of the
body-contacting layer feeling drier to the touch.

The use of hydrophobic fibers for the body
20 contacting, or cover, layer allows fluid to pass through
to the absorbent layers beneath yet does not retain
moisture on the surface layer, thus providing greater
comfort since the wearer feels dry for a longer period
of time. The desirability of such a feature has been
25 disclosed in U.S. 3,838,692 to Levesque (herein
incorporated by reference in its entirety) which
describes a chemical method of providing porosity to
hydrophobic materials.

30 Fluid-impermeable backsheet

The fluid-impermeable backsheet 30 may be a
nonwoven or woven fabric treated to become impervious to
fluid. Typically, though, the backsheet 30 is a plastic
sheet comprised of polyethylene or polypropylene. Such

layers are disclosed, for example, in U.S. 4,731,066 to Korpman.

Absorbent core

5 The absorbent core 40, comprises wood pulp fluff, and may optionally contain other cellulosic material or commonly used absorbent materials, and is generally rectangular in shape, and is preferably hourglass shaped wherein a central region of the core, intermediate of
10 the transverse ends of the core, has a width which is narrower than the width of the transverse ends. Such cores are taught, for example, in U.S. 4,552,618 to Kopolow and U.S. 4,536,432 to Holtman and in British patent 2,189,705 to Mesek, incorporated herein by
15 reference in their entirety. In a preferred embodiment, the absorbent core 40 contains additional pulp in the central region to raise this area in an upward, body contacting direction. Such additional thickness of pulp may be added between the absorbent core 40 and the
20 stabilizing element 120. This configuration will raise the stabilizing element 120, and thus the body-facing surface of the absorbent article, closer to the body. Resistance to wet collapse may be enhanced by compressing the additional pulp or optionally the entire
25 absorbent core prior to use.

 Additionally, the absorbent core 40 may utilize a variety of fluid immobilizing materials, e.g., superabsorbing polymers or sphagnum moss, as a reservoir
30 layer to increase fluid capacity or minimize the overall thickness of the absorbent article. Typically, these fluid immobilizing materials are not used alone, but in conjunction with cellulosic pulp fluff in order to provide extra absorbency for heavy fluid flow and to

provide bulk to keep the article closer to the user's body. Such materials are taught by in U.S. 4,507,122 to Y. Levesque; in U.S. 4,494,963 to S. Dabi; in U.S. 4,880,419 to I. S. Ness; in U.S. 4,443,492 to J. Roller; hereby incorporated by reference in their entirety.

While such fluid immobilizing materials have the ability to absorb many times their weight in body fluid, their rate of absorption is relatively slow. Typically, a transfer layer 80 functions to quickly absorb fluid and hold it until a slower absorbing reservoir layer 90 can accept it. Thus, it is often preferred that a transfer layer 80 be incorporated between the cover sheet 10 and the upper body facing surface of the absorbent core 40. The transfer layer 80 functions to rapidly draw fluid from the fluid-permeable cover sheet 10 and transport it to the absorbent stabilizing element and/or to that portion of the core into which the bulk of the fluid will eventually be absorbed, often referred to as a reservoir layer 90. Thus, placement of the transfer layer 90 in the absorbent article would be between the cover sheet 10 and the reservoir layer 90. Acceptable transfer layers 80 are those made from cellulosic materials, such as wood pulp, and an adhesive like binder. The basis weight of such materials would range from about 20-200 g/m². More preferably, they would range from about 50-150 g/m². Still more preferably, they would range from about 75-100 g/m². Still other suitable materials are discussed in U.S. patent application no. 08/075254, commonly assigned and herein incorporated by reference in its entirety. Such materials, aside from those specifically disclosed in serial no. 08/075254, are well

known in the art.

Stabilizing element

5 The stabilizing element 120 is absorbent, resilient
and stable, i.e. it maintains its shape in the wet
state. The stabilizing element 120 should be resistant
to wet-collapse in both the lateral or X-direction
(herein defined as that direction transverse to the
longitudinal edges 100) and the Z-direction (herein
10 defined as the direction normal to the cover sheet 10).
The wet collapse in the Z-direction should be less than
10% at 0.2 psi and less than 25% at 0.5 psi. It should
have a deformation measurement of less than 15% in the
dry state and less than 35% in the wet state in
15 accordance with the Wet and Dry Deformation Tests
described in the Examples below.

20 Body-contact is important because it helps to
inhibit expressed fluid from travelling along the body,
e.g, the user's thighs, to soil the user's clothes.
Since the stabilizing element 120 is resilient and does
not collapse in a wet state, it thus enhances contact
between the absorbent article 5 and the user's body at
that point where fluid exits the body.

25 The resilient, absorbent stabilizing element 120 is
preferably flexure resistant. Flexure resistance is
generally measured by peak bending stiffness which is
more fully discussed in U.S. 5,171,302 to Buell, which
30 is incorporated herein in its entirety. The resilient,
absorbent stabilizing element 120 of the present
invention preferably has a peak bending stiffness of at
least 250 grams, preferably greater than 400 grams, and
most preferably greater than 600 grams.



Suitable materials for use as the stabilizing element 120 are selected from the group consisting of sphagnum moss, calendered pulp, a composite of sphagnum moss and calendered pulp, and a composite of calendered pulp and superabsorbent material. These materials may comprise a single layer of the above materials, or may comprise multi-layered laminates. Alternatively, more than one stabilizing element may be used in the absorbent article on the invention. In a most preferred embodiment, the stabilizing element 120 comprises a calendered, multi-layer laminate of sphagnum peat moss which has been sandwiched between an upper and lower layer of pulp fibers.

The width of the stabilizing element 120 is considered to be a critical element of the present invention. The stabilizing element 120 must have a width sufficient to provide stability and resistance to lateral compression to the central portion of the absorbent article. Suitable widths are generally at least 0.5 inches, and less than 1.75 inches. It is preferred that the width of the stabilizing element 120 should generally approximate the dimensions of the labia majora so as to cover the area from which fluid will exit the body. Accordingly, the stabilizing element 120 may have a width in a range of from 0.5 to 1.75 inches, preferably in a range of from 0.75 to 1.25 inches, and most preferably, the stabilizing element 120 should have a width of about 1 inch.

The length of the stabilizing element 120 is not, per se, critical to the invention, provided of course that it has a length sufficient to provide stability and resistance to lateral compression to the central portion



of the absorbent article. Suitable lengths are generally at least about 2 inches, and may be as long as the absorbent article. It is preferred that the length be less than that of the article 5 as a whole, and most preferably, the length and width of the stabilizing element 120 should conform generally to the longitudinal and lateral dimensions of the labia majora so as to cover the area from which fluid will exit the body. Accordingly, the stabilizing element 120 may have a length in a range of from 2 to 4 inches, preferably in a range of from 2.5 to 3.5 inches, and most preferably, the stabilizing element 120 should have a length of about 3 inches and a width of about 1 inch. While the lengths of absorbent articles can vary widely, the foregoing preferred lengths generally correspond to less than about 80% of the article 5 length and, more preferably, between about 25-50% of the article 5 length.

20 The absorbent core 40 contains a central portion 60 which is located near the center of article 5, which is defined by the portion between the longitudinal edges 100 and is preferably approximately midway between the transverse edges 110. The central portion 60 would then be positioned, when in use, closest to the point where fluid exits the body. It is considered an important feature of the present invention that the stabilizing element 120 be located adjacent the central portion 60 and be slightly above a plane defined by the longitudinal edges 100 to keep in close contact with the body.



Preferential bending zones

In an optional embodiment, the fluid-absorbent core contains two preferential bending zones. The stabilizing element is preferably in the center portion between the two preferential bending zones wherein the preferential bending zone(s) 50 are in a region outside the transverse ends of the stabilizing element 120, and are most preferably located at the end(s) 130 of the stabilizing element 120. This allows the absorbent article 5 to cup at the front and back of the user while maintaining an essentially planar or flat configuration in the perineal area (when viewing the longitudinal edges of the article 5 from a longitudinal cross section - see for example Figure 2), thus allowing the stabilizing element 120 in the central portion 60 of the article 5 to conform to the shape of the user's body. Most preferred are bending zones 50 which are transverse to the longitudinal axis of the absorbent article 5 and extend from one longitudinal side 100 to the other.

The bending location and profile of the napkin 5 should be such that the central portion 60 maintains an almost linear longitudinal profile when the ends of the napkin 5 are deflected by a specified amount. Example 3 below describes the testing for characterization of such preferential bending zones 50. It is undesirable to have the central portion 60 cup or curve as the napkin 5 would move away from the user and protection would be sacrificed. The bending zone 50 may occur by a change in the flexibility of the napkin 5 along its length or it may occur due to a seam, space or embossment anywhere in those portions of the absorbent article 5 including the stabilizing element 120.

An additional method of forming the preferential bending zones 50 involves changing the density of the absorbent article 5 such that the density of a stabilizing element 120 having a length which is less than that of the absorbent article is much greater than that of the absorbent core near the transverse ends 110. Changing the density may occur by changing the thickness of the absorbent article 5 in the z-direction or by changing the basis weights of the materials in those parts of the absorbent article 5 adjacent the central portion 60.

The absorbent article 5 may also be pre-shaped such that the napkin 5, prior to use, has a bend located at the preferential bending zones. Such pre-shaping may be accomplished, for example by placing elastic in the flanged side margins of longitudinal edges 100 of the napkin 5 as disclosed in commonly assigned U.S. Patent Application Serial No. 07/766699, and which is hereby incorporated herein by reference in its entirety.

The absorbent articles of this invention optionally, but preferably, contain attachment tabs and/or side cuffs along the longitudinal sides of the absorbent core. These attachment tabs are preferably of dimensions such that their longitudinal edges are shorter than the longitudinal dimensions of the stabilizing element so as not to impede the article's bending along the preferential bending zones located adjacent the stabilizing element.

Attachment tabs 140 possess adhesive means to hold the article 5 securely to the crotch portion of a user's undergarment so that the stabilizing element 120

maintains intimate contact with the body. The attachment tabs 140 also serve to prevent the user's undergarment from contacting the longitudinal sides 100 of the central portion 60 by restraining the side edges of the crotch portion of the user's undergarment. It is preferred, however, that the line of juncture of the attachment tabs 140 not extend beyond the preferential bending zones 50 as this would inhibit bending of the article 5. The attachment tabs 140 may be attached to the longitudinal sides 100 of the article 5 or they may be located on the garment facing side inward from the longitudinal edges as disclosed more fully in U.S. 4,900,320 to McCoy, which incorporated herein by reference in its entirety.

It is preferable that the line of juncture between the tabs 140 and the napkin 5 be less than 7 inches. It is more preferable that the line of juncture be between 3 and 6 inches.

It is also preferred that the absorbent article 5 be hourglass shaped having arcuate lateral sides with the front and rear portions wider than the central portion 60. This configuration will also help to stabilize the article 5 by inhibiting shifting from front to back.

In order to demonstrate the features of this invention, the following non-limiting examples below are submitted. In all instances the napkins manufactured for testing in the examples utilized a perforated plastic film (PE/EVA or PE) for the cover (either 0.54 or 1.0 oz/yd²), a transfer layer of 90 g/m² airlaid, latex bonded pulp fabric, a wetlaid cellulosic absorbent



having a basis weight of 325 g/m², a core of wood pulp fluff underneath (garment side) of a sphagnum moss absorbent board, and a PE/EVA film barrier layer.

5 Example 1 - Z-direction Deformation Test

10 The test described below was designed to simulate the z-direction pressure exerted on a sanitary napkin by a wearer's body. Ideally, the napkin should not collapse in the z-direction when exposed to body fluids, such as menstrual fluid, and body pressure. As demonstrated below, conventional napkins are subject to such collapse.

15 Ten napkins were prepared according to the teachings of the specification and compared to ten control napkins, commercially available from Proctor & Gamble under the trademark ALWAYS PLUS MAXI. Each sample was conditioned at 70° ± 2° F and 50 ± 2% RH for 24 hours prior to the test. Such conditions were
20 maintained throughout the testing. The test is further described below. The discussion will detail how each sample was tested.

25 An AMES gauge #91-013, with a 1.125 inch diameter foot weighing 12.7 grams, was calibrated using standard blocks under a standard 56.7 gram weight (the total weight corresponds to a pressure of 0.15 psi). The foot of the gauge was raised and the sample was placed on the anvil. The foot was then lowered gently onto the center
30 of the sample and allowed to remain for 15 seconds before taking a reading. This is the initial thickness W_1 .



The weight on the AMES gauge was then increased to 85.3 grams (this plus the weight of the foot corresponds to a pressure of 0.22 psi). The thickness of the sample was again measured and noted as thickness W_2 .

5

The center of the sample was marked where the foot of the gauge was resting. The sample was removed and cc of synthetic menstrual fluid (SMF) was introduced to the marked area using a syringe. The fluid was added slowly enough so that it did not spill outside the marked area. The sample was then immediately placed on the AMES gauge with a weight of 85.3 grams. The thickness of the sample was noted then and for each minute thereafter until there was no change in the thickness of the sample. (In all samples, the thickness ceased to change after 4 minutes). This final thickness was recorded as W_3 .

10

15

20

All pressure was then removed from the sample by removing it from the AMES gauge, and it was allowed to stand for 15 minutes. After 15 minutes the sample was placed in the AMES gauge and a weight of 56.7 grams was introduced. The thickness under this pressure was recorded as W_4 .

25

From these four readings it is possible to calculate the % reduction in thickness normal use (%RT) by the following equation:

$$\%RT = (W_2 - W_3) / W_2 \times 100$$

30

From these four readings it is also possible to calculate the % delayed reduction in thickness (%DR) by the following equation:

$$\%DR = (W_1 - W_4) / W_1 \times 100$$

21

SUBSTITUTE SHEET (RULE 26)

This Sheet Has Been Replaced



Ten additional napkins were prepared according to the teachings of the specification and compared to an additional ten control napkins, commercially available from Proctor & Gamble under the trademark ALWAYS PLUS
5 MAXI. The procedure described above was repeated, except that the test pressure, W_2 was measured using a 226.8 gram weight (corresponding to a total pressure of 0.53 psi).

10 Table 1 shows the results obtained under a test pressure of 0.22 psi. Table 2 shows the results obtained under a test pressure of 0.53 psi.



TABLE 1
TEST PRESSURE AT 0.22 PSI

		Test		Control		
5		%RT	%DR	%RT	%DR	
		7.496	4.210	30.769	30.320	
		7.192	5.980	29.725	28.012	
		3.580	-1.300	26.375	26.179	
		5.187	-1.408	29.566	23.994	
		5.650	1.284	24.296	21.407	
		3.571	-3.102	24.160	23.566	
		10.069	4.232	23.414	24.606	
		6.666	0.160	24.437	23.557	
		4.566	-2.215	23.455	22.606	
10		6.593	-0.356	23.411	22.186	
		Mean	6.057	0.747	25.961	24.643
		S.D.	1.988	3.090	2.945	2.776



TABLE 2
TEST PRESSURE AT 0.53 PSI

5	10	15	Test		Control	
			%RT	%DR	%RT	%DR
			24.750	23.279	36.538	32.132
			26.615	22.684	37.681	31.288
			28.740	27.632	36.501	35.453
			27.490	25.333	34.904	34.407
			26.556	27.682	35.088	27.190
			23.390	23.611	38.021	37.215
			19.408	17.139	36.678	38.587
			21.839	17.949	37.343	29.566
			18.868	15.120	35.528	34.153
			22.901	20.886	39.082	34.894
Mean		24.056	22.131	36.736	33.489	
S.D.		3.370	4.324	1.335	3.476	



Example 2 - X-direction Deformation Test

The objective of this test is to determine the deformation resistance of a sanitary napkin or any absorbent article in X-direction (the direction
5 transverse to the longitudinal axis across the plane of the napkin) in terms of a loss in napkin width in both wet and dry states. Generally the tests consists of holding a napkin around the inner cylinder of an Instron deformation test apparatus. It is compressed and then
10 allowed to recover from its deformation for 2 cycles. The loss in width as a result of compression and relaxation is a measure of the deformation resistance of the napkin in X-direction.

15 The apparatus used for the test was: 1. Instron Model 1122 Universal Tester; 2. a custom jig (Figure 4) with an 8 inch diameter cylinder and upper and lower jaws which are shaped to resemble a human thigh; 3. 100 Kg load cell; 4. vernier caliper; 5. 25cc graduated
20 cylinder; 6. plexiglas plate (0.511 thick) with an oblong center opening of 0.75" x 1.50"; 7. a 3 inch wide knitted fabric (45% polyester/45% cotton/10% Lycra spandex) which simulates an undergarment crotch; 8.

25 Ten napkins were prepared according to the teachings of the specification and ten control napkins, commercially available from Proctor & Gamble under the trademark ALWAYS MAXI PLUS, were purchased. Each sample was conditioned at $70^{\circ} \pm 2^{\circ}$ F and $50 \pm 2\%$ RH for 24
30 hours prior to the test. Such conditions were maintained throughout the testing. The test is further described below. The discussion will detail how each sample was tested.



- The gap between the upper and lower compression surfaces of the custom jig was set at 0.8 inch. The return limit on the Instron console was set at 2.2 inches. The crosshead speed was set at 5 in./minute.
- 5 The test direction was set to "up" and was pressed so that the crosshead starts moving, stopping when reaching a 3 inch gap spacing (0.8 Inch initial gap + 2.2 inch crosshead travel).
- 10 The instrument was then calibrated by setting the load scale dial to 2 Kg and zeroing the pen on the chart. A 1 Kg weight was then placed on the lower cylinder ring jaw and pen was adjusted using the "calibration knob" so that the pen rested on the 1 Kg
- 15 line. The 1 Kg weight was then removed. If the pen returns back to the zero position on the chart, it means the instrument has been calibrated. If needed, the "balance knob" is used to bring the pen back to zero.
- 20 The 3 inch wide fabric was cut such that the grain of the fabric was perpendicular to the direction of travel. A 4 inch long test sample element was cut from the center of each sanitary napkin to be tested. The width of each test sample was the width of the absorbent
- 25 system in the napkin. The width of the test element was measured using a Vernier caliper and was recorded as initial width L_1 .
- 30 The release paper, which is on the garment facing side, was removed from the sample. The sample was then placed with the garment facing side down into the center of the inner surface of the loop to be formed on the Jig with the side edges of the fabric enveloping the sample edges. The sample was secured on the fixture in such a



way that it was in direct contact with the jig surface and centered between the curved jaws.

5 The cycle counter was set to "2" so that the test sample could be compressed for 2 cycles. The return limit on the console was set to "2.25." The maximum and minimum limits were set to "2.20" and "0.00" respectively. The test direction was set to "down", and the crosshead speed was set to 5 in./minute.

10 The Instron was started. After the crosshead had compressed the sample for 2 cycles and stopped, the sample was is removed and the width again measured and is recorded as final width L_2 .

15 Napkins were also tested in the wet state by preparing the samples as described above. However, prior to positioning the sample on the jig, SMF was applied to the center of the test element. This was
20 done by placing the plexiglas plate over the center of the sample. The SMF cc of fluid was poured from the graduated cylinder into the oblong opening of the plate placed on to the sample. Once the fluid was absorbed, the sample was allowed to remain at test conditions for
25 1 minute and then L_1 and L_2 measured as described above.

 The percentage of amount of x-direction deformation (%XD) was calculated as follows:

$$\%XD = (L_1 - L_2) / L_1 \times 100$$

30

 Table 3 shows the results obtained in the dry state. Table 4 shows the results obtained in the wet state.



TABLE 3
% LOSS IN WIDTH IN X-DIRECTION IN DRY STATE

	<u>TEST</u>			<u>CONTROL</u>		
	<u>L1</u>	<u>L2</u>	<u>%XD</u>	<u>L1</u>	<u>L2</u>	<u>%XD</u>
5	1.99	1.70	14.57	1.65	1.44	12.73
	1.89	1.61	14.81	1.72	1.36	20.93
	1.91	1.71	10.47	1.75	1.30	26.47
	1.96	1.74	11.22	1.72	1.40	18.60
10	1.91	1.78	6.80	1.70	1.49	13.53
	1.83	1.60	12.57	1.78	1.39	21.91
	1.84	1.65	10.33	1.71	1.34	21.64
	1.81	1.68	7.18	1.74	1.46	16.09
	1.83	1.65	9.84	1.65	1.41	14.54
15	1.82	1.65	9.34	1.74	1.46	16.09
Mean =			10.71	18.24		
S.D. =			2.71	4.42		

20

TABLE 4
% LOSS IN WIDTH IN X-DIRECTION IN WET STATE

	<u>TEST</u>			<u>CONTROL</u>		
	<u>L1</u>	<u>L2</u>	<u>%XD</u>	<u>L1</u>	<u>L2</u>	<u>%XD</u>
5	1.86	1.27	31.72	1.69	0.98	42.01
	1.84	1.23	33.15	1.69	0.93	44.97
	1.90	1.32	30.53	1.65	0.99	40.00
	1.83	1.28	30.05	1.67	0.98	41.32
10	1.87	1.33	28.88	1.68	1.06	36.90
	1.80	1.26	30.00	1.64	1.00	39.02
	1.85	1.28	30.81	1.64	0.87	46.95
	1.78	1.23	30.90	1.66	0.93	43.98
	1.83	1.28	30.05	1.67	0.94	43.71
15	1.83	1.23	32.79	1.61	0.93	42.24
Mean =			30.89	42.11		
S.D. =			1.32	2.97		

20 As is clear from both Table 3 and Table 4, the
napkin as described in this invention offers more
resistance to deformation in X-direction as compared to
conventional napkins. The conventional napkins, which
mainly consist of pulp, undergo deformation in
25 X-direction in both dry as well as wet states. This
phenomenon, called bunching, reduces the effective
surface area of the absorbent system available for the
capture of bodily fluid. The severe deformation in
X-direction, therefore, potentially can lead to higher
30 chances of undergarment staining.

Example 3 - Bending Test

Bending zones were created by embossing
transversely across the samples at each end of the

stabilizing element (defined as the ends of the sphagnum board) and by decreasing the thickness of the pads both fore and aft of the stabilizing element. This example consists of two parts. The first part demonstrates
5 where the preferential bending zones are located upon application of force along the longitudinal axis. The second part demonstrates the difference in bending resistance between a tab with a 2.75 inch line of
10 juncture between the tab and the napkin and a tab with a five inch line of juncture between the tab and the napkin.

SUBSTITUTE SHEET (RULE 26)

This Sheet Has Been Replaced



**WHAT IS CLAIMED IS:**

1. An absorbent article having longitudinal sides and transverse ends, a body-facing surface and a garment-facing surface said article comprising:
- 5 a) a fluid-permeable cover on said body-facing surface;
- b) a fluid-impermeable barrier on said garment-facing surface;
- 10 c) a fluid-absorbent core containing wood pulp fluff between the fluid-permeable cover and the fluid impermeable barrier, said fluid-absorbent core having a central region and transverse ends and a thickness of at least
- 15 about 0.20 inches; and
- d) a stabilizing absorbent element adjacent an upper portion of the central region of the absorbent core, wherein the stabilizing element is capable of absorbing fluids and
- 20 remaining stable when wet, and wherein the stabilizing element has a lateral width in a range of from at least about 0.5 inches to less than about 1.75 inches.
- 25 2. The absorbent article of claim 1 wherein the absorbent core has an hour glass shape wherein the central region of the absorbent core has a narrower lateral width than the transverse ends of the absorbent core.
- 30 3. The absorbent article of claim 1 wherein the stabilizing element is selected from the group consisting of sphagnum moss, calendered pulp, a composite of sphagnum moss and calendered pulp, and a





composite of calendered pulp and superabsorbent material.

4. The absorbent article of claim 1 wherein the
5 stabilizing element has a length which is substantially
equivalent to the length of the absorbent article.
5. The absorbent article of claim 1 wherein the
10 stabilizing element has a length in a range of from
about 2 to about 4 inches.
6. The absorbent article of claim 5 wherein the
15 stabilizing element has a length in a range of from
about 2.5 to about 3.5 inches.
7. The absorbent article of claim 5 wherein the
stabilizing element has a length of about 3 inches and a
width of about 1 inch.
8. The absorbent article of claim 7 wherein the
20 stabilizing element is sphagnum.
9. The absorbent article of claim 7 wherein the
25 stabilizing element has a peak bending moment of at
least about 250 grams.
10. The absorbent article of claim 9 wherein the
30 stabilizing element has a peak bending moment of greater
than about 400 grams.
11. The absorbent article of claim 9 wherein the
stabilizing element has a peak bending moment of greater
than about 600 grams.





12. The absorbent article of claim 1 wherein the stabilizing element has a resistance to wet collapse of less than about 10% at 0.2 psi.
- 5 13. The absorbent article of claim 1 wherein the stabilizing element has a resistance to wet collapse of less than about 25% at 0.5 psi.
- 10 14. An absorbent article having longitudinal sides and transverse ends, a body-facing surface and a garment-facing surface said article comprising:
- a) a fluid-permeable cover on said body-facing surface;
 - b) a fluid-impermeable barrier on said garment-facing surface;
 - 15 c) a fluid-absorbent core containing wood pulp fluff adjacent said fluid-permeable cover, said fluid-absorbent core having a thickness of at least about 0.20 inches and an hour-glass shape wherein a central portion located inward of said transverse ends has a narrower lateral width than said transverse ends;
 - 20 d) an absorbent, resilient, stabilizing element between the fluid-permeable cover and the central portion of the absorbent core, the
 - 25 stabilizing element further comprising a multi-layer laminate of sphagnum moss and wood pulp fibers having a lateral width of at least about 0.5 inches to less than 1.75 inches, and
 - 30 a length of about 3 inches.
15. The absorbent article of claim 14 wherein the stabilizing element has a peak bending moment of at least about 250 grams.





16. The absorbent article of claim 14 the stabilizing element has a peak bending moment of greater than about 400 grams.
- 5 17. The absorbent article of claim 14 wherein the stabilizing element has a resistance to wet collapse of less than about 10% at 0.2 psi.
- 10 18. The absorbent article of claim 14 wherein the stabilizing element has a resistance to wet collapse of less than about 25% at 0.5 psi.

