Claims

1. A sealable resin sheet for sealing an element, the sealable resin sheet containing thermosetting resin, ~~and further containing~~ a layered silicate compound and an inorganic filler other than the layered silicate compound, wherein an upper limit of a content ratio of the layered silicate compound in the sealable resin sheet is 6 mass% and a lower limit of a content ratio of the inorganic filler other than the layered silicate compound in the sealable resin sheet is 50 mass%.

2. The sealable resin sheet according to Claim 1, wherein the layered silicate compound is smectite.

3. The sealable resin sheet according to Claim 1, wherein the layered silicate compound has a surface modified by an organic component.

4. The sealable resin sheet according to Claim 2, wherein the layered silicate compound has a surface modified by an organic component.

5. The sealable resin sheet according to Claim 1, wherein an upper limit of the content ratio of the~~further containing an~~ inorganic filler other than the layered silicate compound in the sealable resin sheet is~~an amount of 50 mass% or more and~~ 90 mass% or less.

6. The sealable resin sheet according to Claim 2, wherein an upper limit of the content ratio of the~~further containing an~~ inorganic filler other than the layered silicate compound in the sealable resin sheet is~~an amount of 50 mass% or more and~~ 90 mass% or less.

7. The sealable resin sheet according to Claim 3, wherein an upper limit of the content ratio of the~~further containing an~~ inorganic filler other than the layered silicate

compound in the sealable resin sheet is~~an amount of 50 mass% or more and~~ 90 mass% or less.

8. The sealable resin sheet according to Claim 4, wherein an upper limit of the content ratio of the~~further containing an~~ inorganic filler other than the layered silicate compound in the sealable resin sheet is~~an amount of 50 mass% or more and~~ 90 mass% or less.

9. The sealable resin sheet according to Claim 1, wherein a lower limit of the~~a~~ content ratio of the layered silicate compound is 3 mass% or more~~ and 10 mass% or less~~.

10. The sealable resin sheet according to Claim 2, wherein a lower limit of the~~a~~ content ratio of the layered silicate compound is 3 mass% or more~~ and 10 mass% or less~~.

11. The sealable resin sheet according to Claim 3, wherein a lower limit of the~~a~~ content ratio of the layered silicate compound is 3 mass% or more~~ and 10 mass% or less~~.

12. The sealable resin sheet according to Claim 4, wherein a lower limit of the~~a~~ content ratio of the layered silicate compound is 3 mass% or more~~ and 10 mass% or less~~.

13. The sealable resin sheet according to Claim 5, wherein a lower limit of the~~a~~ content ratio of the layered silicate compound is 3 mass% or more~~ and 10 mass% or less~~.

14. The sealable resin sheet according to Claim 6, wherein a lower limit of the~~a~~ content ratio of the layered silicate compound is 3 mass% or more~~ and 10 mass% or less~~.

15. The sealable resin sheet according to Claim 7, wherein a lower limit of the~~a~~ content ratio of the layered silicate compound is 3 mass% or more~~ and 10 mass% or less~~.

16. The sealable resin sheet according to Claim 8, wherein a lower limit of the~~a~~ content ratio of the layered silicate compound is 3 mass% or more~~ and 10 mass% or less~~.