

[Abstract]

This electrical steel sheet contains: as a chemical composition, in a unit of mass%, 2.5% to 3.9% of Si; 0.001% to 3.0% of Al; and 0.05% to 5.0% of Mn, the remainder being Fe and impurities, and, on one surface or both surfaces thereof, an
5 insulating coating containing a curing accelerator is formed.

FIG. 4