

(19) World Intellectual Property Organization
International Bureau




(43) International Publication Date
11 January 2001 (11.01.2001)

PCT

(10) International Publication Number
WO 01/02612 A1

- (51) International Patent Classification⁷: C22C 1/00, B22D 17/00
- (21) International Application Number: PCT/US00/01516
- (22) International Filing Date: 21 January 2000 (21.01.2000)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
09/347,871 6 July 1999 (06.07.1999) US
- (71) Applicant: THIXOMAT, INC. [US/US]; 620 Technology Drive, Ann Arbor, MI 48108 (US).
- (72) Inventors: LEBEAU, Stephen, E.; 41512 Ladywood Court, Northville, MI 48167 (US). WALUKAS, D., Matthew; 2234 George Avenue, Ypsilanti, MI 48198 (US). DECKER, Raymond, F.; 3065 Provincial, Ann Arbor, MI 48104 (US).
- (74) Agents: SOSENKO, Eric, J. et al.; Harness, Dickey & Pierce, P.L.C., P.O. Box 828, Bloomfield Hills, MI 48303 (US).
- (81) Designated States (*national*): AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, UZ, VN, YU, ZA, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).
- Published:
— With international search report.
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: ACTIVATED FEEDSTOCK



(57) Abstract: An alloy feedstock for semi-solid metal injection molding. The alloy feedstock is an alloy material in particulate form and has a heterogeneous structure, a temperature range at 20% of the height of the peak of the main melting reaction greater than 40 °C, and having a ratio of the height of the peak of the eutectic reaction to the height of the main melting reaction of less than 0.5.

WO 01/02612 A1