

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08G 18/30, C08K 3/00, B01J 37/00		A1	(11) International Publication Number: WO 98/03569
			(43) International Publication Date: 29 January 1998 (29.01.98)
(21) International Application Number: PCT/GB97/01956			(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).
(22) International Filing Date: 21 July 1997 (21.07.97)			
(30) Priority Data: 9615373.9 22 July 1996 (22.07.96) GB			
(71) Applicants (for all designated States except US): DOW BENELUX N.V. [NL/NL]; Acrt Van Nesstraat 45, NL-3012 CA Rotterdam (NL). DOW CHEMICAL COMPANY LIMITED [GB/GB]; Lakeside House, Stockley Park, Uxbridge, Middlesex UB11 1BE (GB).			
(72) Inventors; and (75) Inventors/Applicants (for US only): GRUNBAUER, Henri, J., M. [NL/NL]; Schorpioen 45, NL-4501 HC Oostburg (NL). BROOS, Jacobus, A., F. [NL/NL]; Karel Doormanlaan 43, NL-4535 BP Temeuzen (NL). PICKIN, Kevin [GB/GB]; 6 Chestnut Road, Mollington, Banbury, Oxon OX17 18 (GB).			
(74) Agent: RAYNOR, John; W.H. Beck, Greener & Co., 7 Stone Buildings, Lincoln's Inn, London WC2A 3SZ (GB).			Published With international search report.
(54) Title: POLYISOCYANATE-BASED POLYMER COMPRISING METAL SALTS AND PREPARATION OF METAL POWDERS THEREFROM			
(57) Abstract			
A polyisocyanate-baser polymer having dispersed therein a metal salt, obtained by reacting an organic polyisocyanate with an aqueous composition of a metal salt. The polymer comprises the metal salt in an amount of from at least 10 weight percent based on total weight of the dry salt with the weight of the polyisocyanate-based polymer including salt therein. The polymer on calcination provides a metal-containing powder having an average particle size of 1 micrometer or less. Such metal-containing powders are of value in the preparation of industrial catalysts, ceramics, electronic components, or as fillers in plastics, paints or cosmetics.			