

ABSTRACT**SINTERED TITANIUM-GRAPHITE HAVING IMPROVED WEAR RESISTANCE
FOR IMPLANT APPLICATIONS**

A process for producing sintered titanium-graphite having improved wear resistance and low frictional characteristics is described. The said process which produces titanium-graphite composites having a triphasic structure with controlled porosity and a graphite lubricating film, comprises sintering a mixture of titanium and graphite powders in which the percentage of graphite may vary from 4 to 8 percent at temperatures from about 800°C. to 1600°C, for about 1/2 to 2 hours, under a compaction pressure of 0.17 to 0.62 MPa. The composites have applications in biomedical engineering and other fields of engineering due to their biocompatibility, strength and improved wear resistance. (Fig. 2 is to be published) —

ABSTRACT**SINTERED TITANIUM-GRAPHITE COMPOSITE HAVING IMPROVED
WEAR RESISTANCE AND LOW FRICTIONAL CHARACTERISTICS**

A process for producing sintered titanium-graphite having improved wear resistance and low frictional characteristics is described. The said process which produces titanium-graphite composites having a triphasic structure with controlled porosity and a graphite lubricating film, comprises sintering a mixture of titanium and graphite powders in which the percentage of graphite may vary from 4 to 8 percent at temperatures from about 800°C. to 1600°C, for about 1/2 to 2 hours, under a compaction pressure of 0.17 to 0.62 MPa. The composites have applications in biomedical engineering and other fields of engineering due to their biocompatibility, strength and improved wear resistance.

(Fig. 2 is to be published)