



159159

USE OF PULSED VOLTAGE IN A PLASMA REACTOR

5

PRIORITY CLAIM

This application claims the benefit of the filing date of United States Patent Application Serial Number 09/640,449, filed August 17, 2000, for "USE OF PULSED VOLTAGE IN A PLASMA REACTOR".

10

TECHNICAL FIELD

Field of the Invention: The present invention relates to plasma reactor apparatus and processes. More specifically, the present invention relates to spiking the voltage to a semiconductor substrate pedestal during a portion of a positive voltage power bias oscillation cycle to reduce or eliminate the detrimental effects of feature charging during the operation of a plasma reactor.

BACKGROUND

State of the Art: Higher performance, lower cost, increased miniaturization of electronic components, and greater density of integrated circuits are ongoing goals of the computer industry. One commonly used technique to increase the density of integrated circuits involves stacking of multiple layers of active and passive components one atop another to allow for multilevel electrical interconnection between devices formed on each of these layers. This multilevel electrical interconnection is generally achieved with a plurality of metal-filled vias ("contacts") extending through dielectric layers which separate the component layers from one another. These vias are generally formed by etching through each dielectric layer by etching methods known in the industry, such as plasma etching. Plasma etching is also used in the forming of a variety of features for the electronic components of integrated circuits.

In plasma etching, a glow discharge is used to produce reactive species, such as atoms, radicals, and/or ions, from relatively inert gas molecules in a bulk gas, such as a fluorinated gas, such as CF₄, CHF₃, C₂F₆, CH₂F₂, SF₆, or other freons, and mixtures thereof, in combination with a carrier gas, such as Ar, He, Ne, Kr, O₂, or mixtures thereof. Essentially, a plasma etching process comprises 1) reactive species are



G00002

-2-

generated in a plasma from the bulk gas, 2) the reactive species diffuse to a surface of a material being etched, 3) the reactive species are absorbed on the surface of the material being etched, 4) a chemical reaction occurs which results in the formation of a volatile by-product, 5) the by-product is desorbed from the surface of the material being etched, and 6) the desorbed by-product diffuses into the bulk gas.

As illustrated in drawing FIG. 4, an apparatus 200 used in the plasma etching process consists of an etching chamber 202 in electrical communication with a first AC power source 204. The etching chamber 202 further includes a pedestal 206 to support a semiconductor substrate 208 and an electrode 212 opposing the pedestal 206. The electrode 212 is in electrical communication with a second AC power source 214. The pedestal 206 may have either a AC (alternating current) bias source or DC (direct current) bias source 216.

In the etching chamber 202, a plasma 222 is maintained by inductively coupling energy from the first power source 204 into the plasma 222 which comprises mobile, positively and negatively charged particles. An electric field, or bias voltage, develops in a sheath layer 224 around the plasma 222, accelerating the electrons and ions (not shown) toward the semiconductor substrate 208 by electrostatic coupling.

To assist with the etching, the potential difference between the plasma 222 and the semiconductor substrate 208 can be modulated by applying an oscillating bias power from the pedestal power bias source 216 to the pedestal 206, as illustrated in drawing FIG. 5 (showing the voltage profiles during such oscillation). During the positive voltage phase 232, the substrate collects electron current from electrons that have enough energy to cross the sheath. The difference between the instantaneous plasma potential and the surface potential defines the sheath potential drop. Since the plasma potential is more positive than the surface potential, this drop has a polarity that retards electron flow. Hence, only electrons with energy larger than this retarding potential are collected by the substrate. During the negative voltage phase 234, positive ions are collected by the substrate. These ions are accelerated by the sheath voltage drop and strike the substrate.

However, it is known that the plasma etching process (as well as ion implantation and other charge beam processes) may cause damage to the semiconductor substrate and to the devices and circuits formed therein or thereon. In particular,

-3-

electrical charging is a well known problem which can occur during the plasma processing of semiconductor devices leading to the degradation of the device performance.

Illustrated in drawing FIG. 6 is the phenomena of electrical charging on a semiconductor device in the process of a plasma etch. A material layer 244 to be etched is shown layered over a semiconductor substrate 242. A patterned photoresist layer 246 provided on the material layer 244 for the etching of a via. During plasma etching process, the patterned photoresist layer 246 and material layer 244 are bombarded with positively charged ions 248 and negatively charged electrons 252 (*i.e.*, the reactive species). This bombardment results in a charge distribution being developed on the patterned photoresist layer 246 and/or the semiconductor substrate 242. This charge distribution is commonly called "feature charging".

In order for feature charging to occur, the positively charged ions 248 and the negatively charged electrons 252 must become separated from one another. The positively charged ions 248 and negatively charged electrons 252 become separated by virtue of the structure being etched. As the structure (in this example a via 254) is formed by etching, the aspect ratio (height to width ratio) becomes greater and greater. During plasma etching, the positively charged ions 248 are accelerated (*e.g.*, as a result of a DC bias at the semiconductor substrate 242), toward the patterned photoresist layer 246 and the material layer 244 in a relatively perpendicular manner, as illustrated by the arrows adjacent positively charged ions 248. The negatively charged electrons 252, however, are less affected by the DC bias at the semiconductor substrate 242 and, thus, move in a more random isotropic manner, as depicted by the arrows adjacent negatively charged electrons 252. This results in an accumulation of a positive charge at a bottom 256 of via 254 because, on average, positively charged ions 248 are more likely to travel vertically toward the substrate than are negatively charged electrons 252. Thus, any structure with a high enough aspect ratio tends to charge more negatively at photoresist layer and an upper portion of the material layer 244 to a distance A (*i.e.*, illustrated with "-" indica) and more positively at the via bottom 256 and the sidewalls of the via 254 proximate the via bottom 256 (*i.e.*, illustrated with "+" indica).

-4-

As shown in drawing FIG. 7, the positively charged via bottom 256 deflects the positively charged ions 248 away from the via bottom 256 and toward the sidewalls 258 of the via 254, as a result of charge repulsion. The deflection results in an etching of the sidewalls 258 proximate the via bottom 256, known as "notching". Furthermore, the presence of the positively charged via bottom 256 slows the positively charged ions 248 as they approach the positively charged via bottom 256 thereby reducing etching efficiency.

As shown in drawing FIG. 8, the negatively charged photoresist layer 246 and the upper portion of the material layer 244 deflects the negatively charged electrons 252 away from entering the via 254 or slows the negatively charged electrons 252 as they enter the via 254, both caused by charge repulsion and both of which reduce etching efficiency.

Thus, it can be appreciated that it would be advantageous to develop an apparatus and a process of utilizing a plasma reactor which eliminates or lessens the effect of feature charging, while using inexpensive, commercially-available, semiconductor device fabrication components and without requiring complex processing steps.

DISCLOSURE OF INVENTION

The present invention relates to an apparatus and method of both increasing the energy of electrons striking a material on a semiconductor substrate and reorienting electrons generated in a plasma reactor to strike a material on a semiconductor substrate in a substantially perpendicular trajectory, both of which reduce feature charging.

One embodiment of the present invention comprises an etching chamber in electrical communication with a first power source. The etching chamber further includes a pedestal to support a semiconductor substrate and an electrode opposing the pedestal. The electrode is in electrical communication with a first power source. The pedestal is in electrical communication with a second power source and a pulsed power source. When triggered, the pulsed power source delivers a timed, positive voltage spike to the pedestal. The power bias source is preferably in electrical communication with the second power source with a signal line.

-5-

As previously discussed, the potential difference between the plasma and the semiconductor substrate can be modulated by applying an oscillating bias power from the pedestal power bias source to the semiconductor substrate. During the positive voltage phase, the substrate collects electron current from electrons that have enough energy to cross the sheath. The difference between the instantaneous plasma potential and the surface potential defines the sheath potential drop. Since the plasma potential is more positive than the surface potential, this drop has a polarity that retards electron flow. Hence, only electrons with energy larger than this retarding potential are collected by the substrate. During the negative voltage phase 232, positive ions are collected by the substrate. These ions are accelerated by the sheath voltage drop and strike the substrate.

Negatively charged electrons are less affected by the typical DC bias at the semiconductor substrate than are positively charged ions, and, thus, move in a more random manner, as depicted by the arrows adjacent negatively charged electrons. However, providing a positive voltage spike to the pedestal according to the present invention alters the potential difference between the potential of the plasma and potential of the semiconductor substrate for a part of the positive voltage phase. The voltage spiking of the pedestal, thus, reorients the trajectory of negatively charged electrons into a more perpendicular path with respect to the semiconductor substrate. The reoriented trajectories results more negatively charged electrons entering into a feature (such as a via being etched into a material layer over a semiconductor substrate) and results in an increases the energy of the negatively charge electrons incident on the material layer to be etched, both of which increase etching efficiency. Additionally, the strong positive field at bottom of the via (i.e., illustrated with "+" indica) accelerates the negatively charged electrons toward the via which results in the negatively charged electron striking the bottom of the via with higher energy. The increase in negatively charged electrons entering the via also reduces feature charging because the negative charge which tends to build up at the photoresist layer and an upper portion of the material layer, as previously discussed, penetrates deeper into the via a distance A' (i.e., illustrated with "-" indica). The deeper penetration of the negative charge distributes the negative charge over a greater volume or area, thereby reducing the local intensity of the negative charge which reduces or eliminates negative charge's tendency to repel the

-6-

negatively charged electrons from the via. Further, the deeper penetration of the negative charge reduces the positive charge build up at the side walls of the via, thereby reducing, minimizing, or eliminating the previously discussed detriment affect on the positively charged ions entering the via. In other words, providing a positive voltage spike to the pedestal reduces, minimizes or eliminates the problems associated with feature charging.

The delivery of the positive voltage spike is preferably controlled by the power output of the pulsed power source. Thus, when the power output of the second power source reaches a predetermined level, a signal is sent from the second power source (or from a sensor (not shown) coupled with the second power source) to the pulsed power source via the signal line. When the signal is received by the pulsed power source, the pulsed power source provides a positive voltage spike to the pedestal for a predetermined duration of time.

It is, of course, understood that if the second power source is capable of providing a positive voltage spike, the pulsed power source will not be necessary. When the power output of the second power bias source reached, a positive voltage spike is generated by the second power source and delivered to the pedestal for a predetermined duration of time.

Thus, the present invention is capable of providing a simple and controllable method of affecting the quality and efficiency of plasma etching and is easily implemented on most existing plasma reactors.

Although the examples presented are directed to the formation of a via , it is understood that present invention may be utilized in a variety of feature formation and plasma processes.

25

BRIEF DESCRIPTION OF DRAWINGS

While the specification concludes with claims particularly pointing out and distinctly claiming that which is regarded as the present invention, the advantages of this invention can be more readily ascertained from the following description of the invention when read in conjunction with the accompanying drawings in which:

30

-7-

FIG. 1 is a schematic of a plasma etching apparatus according to the present invention;

FIG. 2 is an idealized graph of an oscillating voltage profile of plasma etching apparatus pedestal according to the present invention;

5 FIG. 3 is a cross-sectional view of a via during an etching process according to the present invention;

FIG. 4 is a schematic of a prior art plasma etching apparatus;

FIG. 5 is an idealized graph of a prior art oscillating voltage profile of plasma etching apparatus pedestal;

10 FIG. 6 is a cross-sectional view of a via during a prior art etching process which results in the phenomena of feature charging;

FIG. 7 is a cross-sectional view of a via during a prior art etching process wherein feature charging results in the deflection of positively charged ions away from the bottom of the via and toward the sidewalls of the via; and

15 FIG. 8 is a cross-sectional view of a via during a prior art etching process wherein feature charging results in the deflection of negatively charged electrons away from entering the via or slows the negatively charged electrons as they enter the via.

BEST MODE(S) FOR CARRYING OUT THE INVENTION

20 Illustrated in drawing FIG.'s. 1 through 3 are various schematics, views, and graphs of the present invention. It should be understood that the illustrations are not meant to be actual views of any particular semiconductor device, but are merely idealized representations which are employed to more clearly and fully depict the formation of contact interfaces in the present invention than would otherwise be possible. Additionally, elements common between drawing FIG.'s. 1 through 3 retain the same numerical designation.

As illustrated in drawing FIG. 1, one embodiment of an etching apparatus 100 of the present invention comprises an etching chamber 102 in electrical communication with a first power source 104, such as an AC power source, a microwave power source, etc.. The etching chamber 102 further includes a pedestal 106 to support a
30 semiconductor substrate 108 and an electrode, typically a coil or coils, 112 opposing the

-8-

pedestal 106. The electrode 112 is in electrical communication with power source 114. The pedestal 106 is in electrical communication with a second power source 116.

In the etching chamber 102, a plasma 122 is maintained by inductively coupling energy from the first power source 104 into the plasma 122 which comprises mobile, positively and negatively charged particles. An electric field, or bias voltage, develops in a sheath layer 124 around the plasma 122, accelerating the electrons and ions (not shown) toward the semiconductor substrate 108 by electrostatic coupling.

The pedestal 106 is further in electric communication with a secondary pulsed source 126. When triggered, the secondary pulsed source 126 delivers a positive voltage spike to the pedestal 106. The second power source 116 is preferably in electrical communication with the secondary pulsed source 126 with a signal line 132.

As previously discussed, the potential difference between the plasma 122 and the semiconductor substrate 108 can be modulated by applying an oscillating bias power from the pedestal pulsed power source 126 to the semiconductor substrate 108, as illustrated in drawing FIG. 2 (showing the voltage profile during such oscillation). During the positive voltage phase 134, the deposition of the reactant species onto the semiconductor substrate 108 proceeds at a high rate. During the negative voltage phase 136, the diffusion of reaction by-products away from the semiconductor substrate 108 proceeds at a high rate. However, as also illustrated in drawing FIG. 2, the present invention comprises the delivery of a positive power spike to the pedestal 106 during the positive voltage phase 134 (i.e., during the time the electrons flow to the wafer) for a duration 138 of time.

A previously discussed and illustrated in prior art drawing FIG. 6, negatively charged electrons 252 are less affected by the typical DC bias at the semiconductor substrate than are positively charged ions, and, thus, move in a more random manner, as depicted by the arrows adjacent negatively charged electrons 252 in prior art drawing FIG. 6. However, the delivery of a positive voltage spike to the pedestal 106, according to the present invention, alters the potential difference between the potential of the plasma 122 and potential of the semiconductor substrate 108 for a part of the positive voltage phase 134, as shown in drawing FIG. 2. The delivery of the positive voltage spike to the pedestal 106, thus, reorients the trajectory of negatively charged electrons 142 into a more perpendicular path with respect to the semiconductor substrate 108, as

-9-

shown in drawing FIG. 3. The reoriented trajectories results more negatively charged electrons 142 toward the semiconductor substrate 108 and entering into the feature, specifically shown as an opening or via 144 being etched through a photoresist material 140 into a material layer 146 over a semiconductor support 148, and results in an increases the energy of the negatively charge electrons 142 incident on the material layer 146, both of which increase etching efficiency. Additionally, a strong positive field at bottom of the opening or via 144 (i.e., illustrated with "+" indica) which results from the positive voltage spike accelerates the negatively charged electrons 142 toward the bottom of the via 144 which results in the negatively charged electron striking the bottom of the via 144 with higher energy (i.e., the use of the positive voltage spike permits control of the driving force for the electron acceleration). The increase in negatively charged electrons 142 entering the opening or via 144 also reduces feature charging because the negative charge which tends to build up at photoresist layer 140 and an upper portion of the material layer 146, as previously discussed, penetrates deeper into the via a distance A' (i.e., illustrated with "-" indica). The deeper penetration of the negative charge distributes the negative charge over a greater area, thereby reducing or eliminating its detrimental affect on the negatively charged electrons 142. Further, the deeper penetration of the negative charge reduces the positive charge build up at the side walls adjacent the via 152, thereby reducing or eliminating the previously discussed detriment affect on the positively charged ions entering the via 144. In other words, the positive voltage spike on the pedestal 106 reduces, minimizes or eliminates the problems associated with feature charging.

Referring to drawing FIG. 1, the secondary pulsed power source 126 is preferably controlled by the power output of the second power source 116. Thus, when the power output of second power source 116 reaches a predetermined level, a signal is sent from the second power source 116 (or from a sensor (not shown) coupled with the second power source 116) to the pulsed power source 126 via the signal line 132. When the signal is received by the pulsed power source 126, the pulsed power source 126 delivers a positive voltage spike to the pedestal 106 for a predetermined duration of time. Thus, the positive voltage spike can be controlled to occur at any point and for any duration during the high voltage cycle to achieve the desired etching results for a particular semiconductor material.

-10-

It is, of course, understood that if the second power source 116 is capable of providing a positive voltage spike, the pulsed power source 126 will not be necessary. When the power output of the second power source 116 is reached, a positive voltage spike is generated by the second power source 116 and delivered to the pedestal 106 for
5 a predetermined duration of time.

It is, yet further understood, that an internal device, such as a microprocessor, may control both the oscillations of the second power source 116 and the delivery of the power spike, whether generated by the second power source 116 or the pulsed power source 126.

10 Thus, the present invention is capable of providing a simple and controllable method of affecting the quality and efficiency of plasma etching and is easily implemented on most existing plasma reactors. The present invention is useful in etching apertures having a length to diameter ratio of 5:1 or greater in insulating materials deposited by plasma enhanced chemical vapor deposition techniques. Such
15 insulating materials including oxides, nitrides, polymers, combinations thereof, etc. Furthermore, although the examples presented are directed to the formation of an opening or via, it is understood that present invention may be utilized in a variety of feature formation and plasma processes.

Having thus described in detail preferred embodiments of the present invention,
20 it is to be understood that the invention defined by the appended claims is not to be limited by particular details set forth in the above description as many apparent variations thereof are possible without departing from the spirit or scope thereof.

-11-

CLAIMS

What is claimed is:

1. A plasma reactor comprising a reactor chamber including a pedestal for supporting a semiconductor substrate, and a power source in electrical communication
5 with said pedestal, wherein said power source is adapted to deliver a voltage spike to said pedestal.
2. A plasma reactor comprising:
a reactor chamber;
10 a first power source in electrical communication with said reactor chamber;
a pedestal disposed within said reactor chamber for supporting a semiconductor substrate thereon;
a second power source in electrical communication with said pedestal, said second power source adapted to deliver a voltage spike to said pedestal;
15 an electrode disposed within said reaction chamber and opposing said pedestal; and
a pulsed power source in electrical communication with said pedestal.
3. A plasma reactor comprising a reactor chamber including a pedestal for supporting a semiconductor substrate, a power source in electrical communication with
20 said pedestal, and a secondary pulsed power source in electrical communication with said pedestal.
4. A plasma reactor comprising:
a reactor chamber;
25 a first power source in electrical communication with said reactor chamber;
a pedestal disposed within said reactor chamber for supporting a semiconductor substrate thereon;
a second power source in electrical communication with said pedestal;
an electrode disposed within said reaction chamber and opposing said pedestal, said first
30 power source in electrical communication with said electrode; and
a pulsed power source in electrical communication with said pedestal.

-12-

5. A method of operating a plasma reactor comprising:
providing a plasma reactor including a pedestal for supporting a semiconductor substrate
and a power source in electrical communication with said pedestal;
delivering an electrical signal to said pedestal from said power source, wherein a voltage
5 of said electrical signal oscillates between a positive voltage phase and a negative
voltage phase; and
delivering a positive voltage spike to said pedestal during said electrical signal positive
voltage phase.
- 10 6. The method of claim 5, wherein said delivering said positive voltage
spike to said pedestal further comprises:
monitoring said voltage of said positive voltage phase until said voltage reaches a
selected voltage; and
delivering said positive voltage spike to said pedestal for a duration of time during said
15 electrical signal positive voltage phase when said selected voltage is reached.
7. The method of claim 5, wherein said delivering said positive voltage
spike to said pedestal comprising generating a positive voltage spike within said power
source and delivering said positive voltage spike to said pedestal during said electrical
20 signal positive voltage phase.
8. The method of claim 5, wherein said delivering said positive voltage
spike to said pedestal comprising generating a positive voltage spike within a secondary
power source and delivering said positive voltage spike to said pedestal during said
25 electrical signal high voltage phase.
9. A method of forming an opening for a semiconductor device utilizing a
plasma reactor chamber including a pedestal for supporting a semiconductor substrate
and a power source in electrical communication with said pedestal, said pedestal
30 including a switch in electrical communication therewith for opening and closing an
electrical path, said method comprising:

-13-

placing a semiconductor substrate on said pedestal, said semiconductor substrate having a material layer thereover and a photoresist layer patterned on said material layer;

generating a plasma above said semiconductor substrate;

- 5 delivering an electrical signal to said pedestal from said power source, wherein a voltage of said electrical signal oscillates between a positive voltage phase and a negative voltage phase; and

delivering a positive voltage spike to said pedestal during said electrical signal positive voltage phase.

10

10. The method of claim 9, wherein said delivering said positive voltage spike to said pedestal further comprises:

monitoring said voltage of said positive voltage phase until said voltage reaches a selected voltage; and

- 15 delivering said positive voltage spike to said pedestal for a selected duration of time during said electrical signal positive voltage phase when said selected voltage is reached.

11. The method of claim 9, wherein said delivering said positive voltage
20 spike to said pedestal comprising generating a positive voltage spike within said power source and delivering said positive voltage spike to said pedestal during said electrical signal positive voltage phase.

12. The method of claim 9, wherein said delivering said positive voltage
25 spike to said pedestal comprises generating a positive voltage spike within a pulsed power source and delivering said positive voltage spike to said pedestal during said electrical signal positive voltage phase.

13. A method of forming an opening in an insulating material deposited using
30 a plasma enhanced chemical vapor deposition technique for a semiconductor device utilizing a plasma reactor chamber including a pedestal for supporting a semiconductor substrate and a power source in

-14-

electrical communication with said pedestal, said pedestal including a switch in electrical communication therewith for opening and closing an electrical path, said method comprising:

- 5 placing a semiconductor substrate on said pedestal, said semiconductor substrate having a material layer thereover and a photoresist layer patterned on said material layer;
- generating a plasma above said semiconductor substrate;
- delivering an electrical signal to said pedestal from said power source, wherein a voltage of said electrical signal oscillates between a positive voltage phase and a negative
- 10 voltage phase;
- delivering a positive voltage spike to said pedestal during said electrical signal positive voltage phase; and
- forming at least a portion of an opening in an insulating material.

- 15 14. The method of claim 13, wherein said delivering said positive voltage spike to said pedestal further comprises:
- monitoring said voltage of said positive voltage phase until said voltage reaches a selected voltage; and
- delivering said positive voltage spike to said pedestal for a selected duration of time
- 20 during said electrical signal positive voltage phase when said selected voltage is reached.

- 15 15. The method of claim 13, wherein said delivering said positive voltage spike to said pedestal comprising generating a positive voltage spike within said power source and delivering said positive voltage spike to said pedestal during said electrical signal positive voltage phase.

16. The method of claim 13, wherein said delivering said positive voltage spike to said pedestal comprises generating a positive voltage spike within a pulsed
- 30 power source and delivering said positive voltage spike to said pedestal during said electrical signal positive voltage phase.

-15-

17. A method of forming an opening in an insulating material deposited using a plasma enhanced chemical vapor deposition technique for a semiconductor device utilizing a plasma reactor chamber including a pedestal for supporting a semiconductor substrate and a power source in electrical communication with said pedestal, said pedestal including a switch in electrical communication therewith for opening and closing an electrical path, said method comprising:
- 5 placing a semiconductor substrate on said pedestal, said semiconductor substrate having a material layer thereover and a photoresist layer patterned on said material layer;
- 10 generating a plasma above said semiconductor substrate;
- delivering an electrical signal to said pedestal from said power source, wherein a voltage of said electrical signal oscillates between a positive voltage phase and a negative voltage phase;
- 15 delivering a positive voltage spike to said pedestal during said electrical signal positive voltage phase; and
- forming at least a portion of an opening in an insulating material, said portion of an opening having a ratio of height to diameter of at least 5:1.
- 20 18. The method of claim 17, wherein said delivering said positive voltage spike to said pedestal further comprises:
- monitoring said voltage of said positive voltage phase until said voltage reaches a selected voltage; and
- delivering said positive voltage spike to said pedestal for a selected duration of time
- 25 during said electrical signal positive voltage phase when said selected voltage is reached.
19. The method of claim 17, wherein said delivering said positive voltage spike to said pedestal comprising generating a positive voltage spike within said power source and delivering said positive voltage spike to said pedestal during said electrical signal positive voltage phase.
- 30

-16-

20. The method of claim 17, wherein said delivering said positive voltage spike to said pedestal comprises generating a positive voltage spike within a pulsed power source and delivering said positive voltage spike to said pedestal during said electrical signal positive voltage phase.

5

21. A method of forming an opening in an insulating material for a semiconductor device utilizing a plasma reactor chamber including a pedestal for supporting a semiconductor substrate and a power source in electrical communication with said pedestal, said pedestal including a switch in electrical communication therewith for opening and closing an electrical path, said method comprising:

10 placing a semiconductor substrate on said pedestal, said semiconductor substrate having a material layer thereover and a photoresist layer patterned on said material layer, said material layer deposited by plasma enhanced chemical vapor deposition;

15 generating a plasma above said semiconductor substrate;

delivering an electrical signal to said pedestal from said power source, wherein a voltage of said electrical signal oscillates between a positive voltage phase and a negative voltage phase;

20 delivering a positive voltage spike to said pedestal during said electrical signal positive voltage phase; and

forming at least a portion of an opening in an insulating material.

22. The method of claim 21, wherein said delivering said positive voltage spike to said pedestal further comprises:

25 monitoring said voltage of said positive voltage phase until said voltage reaches a selected voltage; and

delivering said positive voltage spike to said pedestal for a selected duration of time during said electrical signal positive voltage phase when said selected voltage is

30 reached.

-17-

23. The method of claim 21, wherein said delivering said positive voltage spike to said pedestal comprising generating a positive voltage spike within said power source and delivering said positive voltage spike to said pedestal during said electrical signal positive voltage phase.

5

24. The method of claim 21, wherein said delivering said positive voltage spike to said pedestal comprises generating a positive voltage spike within a pulsed power source and delivering said positive voltage spike to said pedestal during said electrical signal positive voltage phase.

10

25. A method of forming an opening in an insulating material for a semiconductor device utilizing a plasma reactor chamber including a pedestal for supporting a semiconductor substrate and a power source in electrical communication with said pedestal, said pedestal including a switch in electrical communication therewith for opening and closing an electrical path, said method comprising:

15

placing a semiconductor substrate on said pedestal, said semiconductor substrate having a material layer thereover and a photoresist layer patterned on said material layer, said material layer deposited by plasma enhanced chemical vapor deposition, said material including one of an oxide material, a nitride material, and a polymer;

20

generating a plasma above said semiconductor substrate;

delivering an electrical signal to said pedestal from said power source, wherein a voltage of said electrical signal oscillates between a positive voltage phase and a negative voltage phase;

25

delivering a positive voltage spike to said pedestal during said electrical signal positive voltage phase; and

forming at least a portion of an opening in an insulating material.

30

26. The method of claim 25, wherein said delivering said positive voltage spike to said pedestal further comprises:

-18-

monitoring said voltage of said positive voltage phase until said voltage reaches a selected voltage; and
delivering said positive voltage spike to said pedestal for a selected duration of time during said electrical signal positive voltage phase when said selected voltage is reached.

27. The method of claim 25, wherein said delivering said positive voltage spike to said pedestal comprising generating a positive voltage spike within said power source and delivering said positive voltage spike to said pedestal during said electrical signal positive voltage phase.

28. The method of claim 25, wherein said delivering said positive voltage spike to said pedestal comprises generating a positive voltage spike within a pulsed power source and delivering said positive voltage spike to said pedestal during said electrical signal positive voltage phase.

29. A method of forming an opening in an insulating material deposited using a plasma enhanced chemical vapor deposition technique for a semiconductor device utilizing a plasma reactor chamber including a pedestal for supporting a semiconductor substrate and a power source in electrical communication with said pedestal, said pedestal including a switch in electrical communication therewith for opening and closing an electrical path, said method comprising:
placing a semiconductor substrate on said pedestal, said semiconductor substrate having a material layer thereover and a photoresist layer patterned on said material layer;
generating a plasma above said semiconductor substrate;
delivering an electrical signal to said pedestal from said power source, wherein a voltage of said electrical signal oscillates between a positive voltage phase and a negative voltage phase;
delivering a positive voltage spike to said pedestal during said electrical signal positive voltage phase; and

-19-

forming at least a portion of an opening having an aspect ratio of height to diameter of greater than 5:1 in an insulating material.

30. The method of claim 29, wherein said delivering said positive voltage spike to said pedestal further comprises:
5 monitoring said voltage of said positive voltage phase until said voltage reaches a selected voltage; and
delivering said positive voltage spike to said pedestal for a selected duration of time during said electrical signal positive voltage phase when said selected voltage is
10 reached.

31. The method of claim 29, wherein said delivering said positive voltage spike to said pedestal comprising generating a positive voltage spike within said power source and delivering said positive voltage spike to said pedestal during said electrical
15 signal positive voltage phase.

32. The method of claim 29, wherein said delivering said positive voltage spike to said pedestal comprises generating a positive voltage spike within a pulsed power source and delivering said positive voltage spike to said pedestal during said
20 electrical signal positive voltage phase.

33. A method of forming an opening in an insulating material deposited using a plasma enhanced chemical vapor deposition technique for a semiconductor device utilizing a plasma reactor chamber including a
25 pedestal for supporting a semiconductor substrate and a power source in electrical communication with said pedestal, said pedestal including a switch in electrical communication therewith for opening and closing an electrical path, said method comprising:
placing a semiconductor substrate on said pedestal, said semiconductor substrate having
30 a material layer thereover and a photoresist layer patterned on said material layer;
generating a plasma above said semiconductor substrate;

-20-

delivering an electrical signal to said pedestal from said power source, wherein a voltage of said electrical signal oscillates between a positive voltage phase and a negative voltage phase;

delivering a positive voltage spike to said pedestal during said electrical signal positive voltage phase; and
5 forming at least a portion of an opening in an insulating material, said portion of an opening having a ratio of height to diameter of at not less than 5:1.

34. The method of claim 33, wherein said delivering said positive voltage
10 spike to said pedestal further comprises:
monitoring said voltage of said positive voltage phase until said voltage reaches a selected voltage; and
delivering said positive voltage spike to said pedestal for a selected duration of time during said electrical signal positive voltage phase when said selected voltage is
15 reached.

35. The method of claim 33, wherein said delivering said positive voltage spike to said pedestal comprising generating a positive voltage spike within said power source and delivering said positive voltage spike to said pedestal during said electrical
20 signal positive voltage phase.

36. The method of claim 33, wherein said delivering said positive voltage spike to said pedestal comprises generating a positive voltage spike within a pulsed power source and delivering said positive voltage spike to said pedestal during said
25 electrical signal positive voltage phase.

37. A method of forming an opening in an insulating material for a semiconductor device utilizing a plasma reactor chamber including a pedestal for supporting a semiconductor substrate and a power source in
30 electrical communication with said pedestal, said pedestal including a switch in electrical communication therewith for opening and closing an electrical path, said method comprising:

-21-

- placing a semiconductor substrate on said pedestal, said semiconductor substrate having a material layer thereover and a photoresist layer patterned on said material layer, said material layer deposited by plasma enhanced chemical vapor deposition;
- 5 generating a plasma above said semiconductor substrate;
- delivering an electrical signal to said pedestal from said power source, wherein a voltage of said electrical signal oscillates between a positive voltage phase and a negative voltage phase;
- delivering a positive voltage spike to said pedestal during said electrical signal positive
- 10 voltage phase; and
- forming at least a portion of an opening in an insulating material having an aspect ratio of height to diameter of at least 5:1.

38. The method of claim 37, wherein said delivering said positive voltage
- 15 spike to said pedestal further comprises:
- monitoring said voltage of said positive voltage phase until said voltage reaches a selected voltage; and
- delivering said positive voltage spike to said pedestal for a selected duration of time during said electrical signal positive voltage phase when said selected voltage is
- 20 reached.

39. The method of claim 37, wherein said delivering said positive voltage spike to said pedestal comprising generating a positive voltage spike within said power source and delivering said positive voltage spike to said pedestal during said electrical
- 25 signal positive voltage phase.

40. The method of claim 37, wherein said delivering said positive voltage spike to said pedestal comprises generating a positive voltage spike within a pulsed power source and delivering said positive voltage spike to said pedestal during said
- 30 electrical signal positive voltage phase.

-22-

41. A method of forming an opening in an insulating material for a semiconductor device utilizing a plasma reactor chamber including a pedestal for supporting a semiconductor substrate and a power source in electrical communication with said pedestal, said pedestal including a switch in electrical communication therewith for opening and closing an electrical path, said method comprising:
- 5 placing a semiconductor substrate on said pedestal, said semiconductor substrate having a material layer thereover and a photoresist layer patterned on said material layer, said material layer deposited by plasma enhanced chemical vapor deposition, said material including one of an oxide material, a nitride material, and a polymer;
- 10 generating a plasma above said semiconductor substrate;
- delivering an electrical signal to said pedestal from said power source, wherein a voltage of said electrical signal oscillates between a positive voltage phase and a negative voltage phase;
- 15 delivering a positive voltage spike to said pedestal during said electrical signal positive voltage phase; and
- forming at least a portion of an opening in an insulating material having an aspect ratio of height to diameter of at least 5:1.
- 20
42. The method of claim 41, wherein said delivering said positive voltage spike to said pedestal further comprises:
- monitoring said voltage of said positive voltage phase until said voltage reaches a selected voltage; and
- 25 delivering said positive voltage spike to said pedestal for a selected duration of time during said electrical signal positive voltage phase when said selected voltage is reached.
43. The method of claim 41, wherein said delivering said positive voltage spike to said pedestal comprising generating a positive voltage spike within said power source and delivering said positive voltage spike to said pedestal during said electrical signal positive voltage phase.
- 30

-23-

44. The method of claim 41, wherein said delivering said positive voltage spike to said pedestal comprises generating a positive voltage spike within a pulsed power source and delivering said positive voltage spike to said pedestal during said electrical signal positive voltage phase.