

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
25 June 2009 (25.06.2009)

PCT

(10) International Publication Number
WO 2009/077287 A1

(51) International Patent Classification:
C08F 210/06 (2006.01) *C08J 5/18* (2006.01)

(BE). ANGELINI, Antonella [IT/IT]; via del Castelluccio
15, I-44020 Ferrara (IT).

(21) International Application Number:
PCT/EP2008/065907

(74) Agent: GAVERINI, Gaetano; Piazzale Donegani 12,
I-44100 Ferrara (IT).

(22) International Filing Date:
20 November 2008 (20.11.2008)

(81) Designated States (*unless otherwise indicated, for every kind of national protection available*): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
07150085.4 18 December 2007 (18.12.2007) EP
61/008,476 20 December 2007 (20.12.2007) US

(71) Applicant (*for all designated States except US*): BASELL
POLIOLEFINE ITALIA S.R.L. [IT/IT]; Via Pergolesi
25, I-20124 Milano (IT).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): PELLEGATTI,
Giampaolo [IT/IT]; Via Virgili 30, I-44030 Boara (Fer-
rara) (IT). GRAZZI, Michele [IT/IT]; Via Ranuzzi
225B, I-44100 Casaglia (Ferrara) (IT). KOKEL, Nicolas
[FR/BE]; Avenue Champel 4, B-1640 Rhode-SaintGenèse

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

(54) Title: COPOLYMERS OF PROPYLENE WITH HEXENE-1 AND BLOWN FILMS OBTAINED FROM THEM

(57) Abstract: A copolymer of propylene with hexene-1 containing from 5 to 9% by weight of recurring units derived from hexene-1, having a melting temperature from 125°C to 140°C and Melt Flow Rate (ASTM D1238, 230°C/2.16 Kg) from 0.1 to 3 g/10 min., is used to produce blown films having valuable mechanical and optical properties.

WO 2009/077287 A1