

Abstract:

There are disclosed a method of preparing a prepreg comprising the steps of a impregnation process in which a thermosetting resin varnish is impregnated into a fiber base material and a
5 drying step in which a solvent of the impregnated thermosetting resin varnish in the fiber base material is vaporized and the resin is semi-cured, wherein the drying step is carried out by moving the fiber base material into which the thermosetting resin
10 varnish is impregnated with a tensile force of 3.0 N/cm or less; and a prepreg prepared by the method.



162162



G00002