

Description

Field of the Invention

5 This invention pertains to a method for forming silica-containing glass using precursor material produced by a sol-gel process, and to glass bodies produced by the method.

Background of the Invention

10 Much effort has recently been expended on producing glass by sol-gel processes. For a recent partial review of the field, see, for instance, D. R. Uhlmann et al, in Better Ceramics Through Chemistry, Materials Research Society Symposia Proceedings, Vol. 32, C. J. Brinker et al, editor, (1984), pp. 59-70.

Sol-gel methods for producing glass precursor material can be divided into techniques that form a gel using pre-existing colloidal particles (e.g., fumed silica), and into techniques that form a gel by hydrolization and polymerization of appropriate chemical compounds. This application is concerned with techniques in
15 the latter category, and with a combination of the two techniques. The techniques of concern herein will be collectively referred to as "polymerization" techniques.

Polymerization techniques may result in gel formation even though a classical sol may not have been formed in the process. It is customary, however, to refer to these processes as sol-gel processes. Typically, gels formed by polymerization techniques are among the monolithic gels. Such a gel may be pictured as a continuous molecular network, having a sponge-like structure, with liquid occluded in the interstices of the "sponge".

Prominent among the known polymerization techniques is the alkoxide method, which is reviewed, for instance, by S. Sakka, Treatise on Material Science and Technology, Vol. 22, Academic Press (1982), pp. 129-167. See also L. C. Klein et al, Soluble Silicate, ACS Symposium Series, Vol. 194, American Chemical
25 Society (1982), pp. 293-304.

Briefly, the alkoxide method comprises mixing an alkoxide, typically a silicon alkoxide such as tetraethylorthosilicate (TEOS), an alcohol such as ethanol, and water. An electrolyte such as HCl or NH_4OH may also be added. Mixing of the components results in formation of a clear "sol", with hydrolysis occurring rapidly, followed by polymerization, a result of which is increasing viscosity of the sol, with the
30 viscous sol becoming an elastic gel in which all of the liquid phase is occluded by a substantially continuous network of the solid phase. Typically, the gel is dried, resulting in formation of a porous, relatively rigid solid, which can be transformed into a glass by sintering at a temperature substantially below the conventional softening temperature of the glass. If desired, absorbed water and hydroxyl ions can be removed, prior to or during sintering, by means of a known chlorine treatment. The alkoxide process can be
35 used to produce doped high-silica glass and some mixed oxide glasses, provided the dopants or other necessary constituents are available in alkoxide form or in the form of water or alcohol-soluble salts.

Various techniques are known for producing a glass body from material produced by the alkoxide method. Among these techniques are the double dispersion method of U.S. Patent 4,419,115, and the particle fusion technique of U.S. Patent 3,954,431. See also S. Sudo et al, Technical Digest, Fourth International Conference on Integrated Optics and Optical Fiber Communications, Tokyo (1983), 27A3-4. The technique of the '431 patent comprises forming a glass body by fusing alkoxide-derived glass particles to a glass substrate by means of an oxygen plasma torch.

Among the advantages of the alkoxide process are its relatively low processing temperature and its potential for economical production of high purity glass. The conventional alkoxide process also has several shortcomings. For instance, it is frequently difficult to produce chemically homogeneous doped or mixed oxide glasses by means of the alkoxide process. In such multi-component glass systems, homogeneity generally can be achieved only if the hydrolization rates of all precursor materials are substantially the same. This, however, is rarely the case. In order to deal with this problem, methods for prehydrolyzing slowly hydrolyzing species have been proposed. Use of such methods complicates the overall process; and, despite their use, controlled gelation is generally difficult to achieve in multi-component systems. A further technique for dealing with different hydrolization rates of precursor materials is disclosed in U.S. Patent 4,477,580.

Among other shortcomings of the alkoxide process is the requirement that all precursor materials be in solution. However, some important precursors (e.g. TEOS) are substantially insoluble in water. Therefore, it is frequently required to add an otherwise unnecessary constituent (e.g., ethyl alcohol) to the system to facilitate dissolution. Furthermore, alkoxides typically are synthesized from simpler metal halides, e.g., SiCl_4 . Such processing obviously results in a product that is more costly, and frequently is less pure, than

the starting metal halide. The alkoxide process also typically is relatively difficult to control reliably, since a host of parameters (e.g., pH, temperature, pressure, volume, composition, catalyst, degree of agitation, and sequence and rate of combination) all affect the outcome. Another disadvantage is the often excessively long gelation time, which can be, in some circumstances, days to weeks, and rarely is less than several hours.

Among the articles that can potentially comprise a sol/gel-derived glass body is optical fiber drawn from a fiber preform. Such fiber typically is silica-based and comprises a core contactingly surrounded by a cladding, with the former having a higher refractive index than the latter to achieve guiding of electromagnetic radiation of an appropriate wavelength, e.g., in the range 0.7-1.6 μm . The refractive index difference is produced, for instance, by incorporating an up-dopant (a dopant which increases the refractive index, e.g., GeO_2) into the core region and/or incorporating a down-dopant (a dopant which decreases the refractive index, e.g., fluorine) into the cladding.

Other examples of articles that can potentially comprise a sol/gel derived glass body are lenses and prisms, and high silicas glass tubes such as are used as substrate tubes in the MCVD process and in many other industrial processes, e.g., in semiconductor processing.

In view of the potential advantages of producing glass by a sol-gel process, a method for forming a monolithic gel that is free of many of the shortcomings of the prior art polymerization processes, especially of the alkoxide process, would be of great significance. This application discloses such a method.

Summary of the Invention

We are disclosing a polymerization technique for forming silica-containing gel that can use a relatively inexpensive precursor material that is available in extremely pure form. The inventive technique can produce very rapid gelation, generally is relatively insensitive to such parameters as temperature, volume, pH, and degree of agitation, permits formation of extremely homogeneous silica-containing gels (including such gels having compositions unattainable by prior art polymerization techniques), and results in a gel having properties that make it suitable for partitioning by simple means to result in particles of a predetermined average size and having a narrow size distribution.

The invention provides a convenient method for producing a glass body, including a glass body of nonuniform refractive index such as an optical fiber preform or an optical fiber. Such glass bodies can be produced by consolidation of a porous gel-derived body, by accretion of gel-derived particles, or by any other appropriate technique, e.g., by extrusion from a crucible. The inventive method can make possible production of gel-derived glass that typically is not subject to "bloating" during high temperature processing, e.g., during fiber drawing.

The novel polymerization technique for forming silica-containing gel, to be referred to as the "vapogel" technique, comprises introducing a gas stream comprising one or more metal halides (at least one of which is a silicon halide) into an aqueous medium such that a silicon-containing gel is formed.

In one exemplary embodiment of the inventive glass-forming method, substantially dry, porous, silica-containing particles are produced from the thus produced gel by, e.g., partitioning of the gel by pushing it through a screen (the resulting particles typically are approximately equiaxed) and drying of the resultant gel particles. The dry porous particles can be consolidated at elevated temperature, such that homogeneous glass particles are formed. From the thus produced glass particles (or from the dry porous particles) a glass body is formed by, e.g., plasma fusion or by extrusion. In another exemplary embodiment of the inventive method, the gel is not partitioned into particles. Instead, a gel body of predetermined shape and size is produced, and the gel body is then dried and consolidated, resulting in a glass body of desired shape and dimensions.

The gas introduced into the aqueous medium comprises one or more silicon halides (e.g., SiCl_4 , SiF_4 , $\text{SiCl}_{4-2}\text{F}_2$, SiBr_4), and furthermore may comprise one or more other metal halides (preferably metal chlorides such as GeCl_4 , SnCl_4 , TiCl_4 , ZnCl_4 , PbCl_2 , or SbCl_3 , but not excluding fluorides, iodides, or bromides). It typically also comprises one or more carrier gases such as O_2 , He, Ar, or N_2 .

The aqueous medium may contain water soluble salts (e.g., aluminum nitrate or chloride, tin chloride, ammonium phosphate, sodium carbonate, ammonium pentaborate, and ammonium bifluoride) or acids (e.g., H_3PO_3 , H_3BO_3) that contains ions that are to be incorporated into the gel. The aqueous medium may also contain suspended particles such as fumed silica (exemplarily, 8-50% by weight fumed SiO_2 of surface areas typically in the range 100-300 m^2/gm) that are to be incorporated into the vapogel. The pH of the aqueous medium may be adjusted by addition of a minor amount of a simple acid such as HCl. The

aqueous medium typically is at or near room temperature, but may be cooled or heated lightly if so desired, and advantageously is agitated during gas introduction. The rate of gas introduction is believed not to be critical. Illustratively, we have used rates of 1-50 gms/min SiO_2 equivalent to form high silica gels.

Vapogel-derived particles (bodies) can be dried (e.g., by heating to about 150°C , the vaporization temperature of HCl), and the resulting porous particles (bodies) fired to consolidate the porous particles (bodies) into homogenous (i.e., essentially pore-free) glass particles (bodies). Firing can take place in the air or, preferably, at least partly in a chlorine- and/or fluorine-containing dehydration atmosphere.

A homogeneous glass body, e.g., a preform from which an optical fiber can be drawn by a known process, can be produced from the consolidated or unconsolidated particles by any suitable process. A currently preferred process is plasma fusion, as exemplified by U. S. Patent 3,954,431. Exemplarily, the particles can be fused to the cylinder surface of a rotating glass rod (produced by any appropriate process, e.g., MCVD, VAD, OVPO) having a refractive index that is greater than that of the glass particles (or having a central high index region surrounded by a peripheral lower index region) resulting in formation of a substantially cylindrical glass body having a core region of relatively larger refractive index that is surrounded by cladding region of relatively smaller refractive index. The refractive index of the glass formed by particle fusion need not be constant but can vary in any desired fashion. Such variation can be attained by appropriate variation of the compositions of the particles introduced into the fusion region, as will be appreciated by those skilled in the art.

Glass produced by the vapogel process typically is substantially free of bubble formation upon heating the glass above its consolidation temperature. Since the presence of even a small number of bubbles in a glass body frequently is unacceptable (e.g., in optical components, including optical fibre), and since prior art gel-derived glass frequently experiences substantial bubble formation upon heating of the glass to a temperature substantially above its consolidation temperature, the substantial absence of bubble formation in vapogel-derived glass is considered to be a significant aspect of the invention.

We have also discovered that the introduction of liquid SiCl_4 into an aqueous medium, can result in formation of a monolithic gel that can be processed in substantially the same manner as vapogel to produce a glass body. Use of a less acidic medium typically results in more rapid gelation, as does a decrease in the $\text{H}_2\text{O}/\text{SiCl}_4$ ratio. For practical reasons, we currently prefer a ratio of at least 30, and a $\text{pH} < 1$. The optimal ratio depends somewhat on sol volume and mixing conditions.

Brief Description of the Drawings

FIGS. 1 and 2 are schematic representations of exemplary embodiments of the inventive process;

FIG. 3 schematically depicts an exemplary embodiment of the vapogel process;

FIG. 4 shows viscosities as a function of time for an exemplary prior art gelation process;

FIG. 5 shows the viscosity as a function of time for an exemplary embodiment of the inventive gelation process; and

FIGS. 6 and 7 schematically depict exemplary apparatus for producing a glass body such as an optical fiber preform.

Detailed Description

FIG. 1 schematically shows the principal steps in an exemplary embodiment of the inventive glass-forming process. The exemplary gaseous silicon halide (e.g., gaseous SiCl_4), prepared, for instance, by bubbling O_2 , Ar, or other carrier gas through semiconductor grade redistilled liquid SiCl_4 in a known manner, is continuously injected (together with carrier gas) into the aqueous medium, e.g., distilled room temperature water in a suitable container. At some characteristic composition, the viscosity of the resulting sol increases (typically within seconds) from e.g., about 0.01 to more than about 10^7 poise, and gelation occurs. The resultant elastic gel may then be partitioned, e.g., by removing the gel body from the container and pushing it through a noncontaminating screen, resulting in particles that have a relatively narrow size distribution. The gel particles are then dried, e.g., by heating to at least about 150°C in a slight vacuum. Drying typically produces considerable shrinkage of the particles, with the resulting dry porous particles typically being about 1/3-1/2 of the linear size of the gel particles. The dry porous particles may then be consolidated, e.g., by placing them into a refractory container and heating them to a temperature above (e.g., by about 150 - 300°C) T_g , the glass transition temperature. An exemplary temperature range for high silica glass is 900 - 1400°C . Consolidation may result in a small further size decrease of the particles, and typically does not produce significant agglomeration of particles. The thus produced homogeneous glass particles are then fused to form a glass body. For instance, the particles can be loaded into a feeder and

fused into a glass boule by means of a plasma torch. Vapogel-derived dry porous particles may also be fused to a glass body, or fused in a crucible and extruded therefrom, thus eliminating the particle consolidation step.

Other embodiments of the vapogel glass-forming process are also contemplated, and one such further embodiment is schematically depicted in FIG. 2. After injection of the gaseous metal halide(s) into the aqueous medium the thus produced sol is cast into an appropriate mold and permitted to gel in the mold. When the gel has attained the desired mechanical properties, the gel body is removed from the mold, dried and consolidated. Since shrinkage during drying and consolidation typically is substantially isotropic, the shape of the thus produced glass body is substantially the same as that of the gel body. As will be appreciated by those skilled in the art, due care has to be exercised during drying and consolidation to prevent fracturing of the body.

FIG. 3 schematically depicts the principal process steps of an exemplary embodiment of the vapogel process. Oxygen is introduced at a controlled rate into bubbles 30 and 31 by means of mass flow controller 32. The bubbles contain liquid SiCl_4 and GeCl_4 , respectively maintained at an appropriate temperature T_2 - (not necessarily the same for both bubblers). Each bubbler has a condenser section, maintained at a temperature $T_1 < T_2$ which insures that no liquid enters the heated vapor lines leading from the bubblers to 32. The flow meters in 32 are under control of computer 33, which receives inputs from one or more of the following: the controller 32, viscosity measuring means 34, temperature monitoring means 35, scattered light detection means 36, and balance 37. The metered flows of $\text{O}_2 + \text{SiCl}_4$ and $\text{O}_2 + \text{GeCl}_4$ are introduced into a heated vapor line that conducts the gas mixture to water-containing vessel 38. The water has some appropriate initial temperature (e.g., 20°C) but the temperature typically rises during introduction of the precursor gases, unless cooling means are provided. The sol typically is agitated during precursor introduction, by means not shown, to facilitate homogenization. The reaction can be monitored with light scattering means (comprising, exemplarily, He-Ne laser 39 and the scattered light detector 36) and/or with viscosity measuring means (e.g., a Brookfield viscometer). Determining the mass accretion of the sol by means of a balance can give further useful process information.

It is one of the major virtues of the inventive vapogel process that it can produce gels (and therefore gel-derived glass) of compositions unattainable by prior art polymerization gel processes. For instance, by appropriately adjusting the proportion of SiCl_4 and GeCl_4 in the injected gas we have produced glasses ranging in composition from 100% SiO_2 to more than 70 mol% GeO_2 , remainder SiO_2 .

The aqueous medium can be pure H_2O , or slightly acidified water (e.g., 0.5 ml $\text{HCl}/100$ ml H_2O). Presently, it is not considered useful to have a basic aqueous medium. Furthermore, the aqueous medium may comprise one or more metal salts or metal-containing acids dissolved therein. For instance, we have produced aluminosilicate glass (Al-content $>5\%$ mol %) by injection SiCl_4 gas into water in which AlCl_3 was dissolved. The aqueous medium may also contain pre-existing colloidal particles (e.g., fumed SiO_2), may be at room temperature, cooled to any temperature above the freezing point of the medium, or even heated slightly. Typically, it is advantageous to stir or otherwise agitate the medium during gas injection, to insure rapid and homogeneous hydrolysis.

The rate of metal halide injection was found to be not critical. In one series of experiments we have injected SiCl_4 into 100 ml water at rates varying from 1 to 15 g/min SiO_2 equivalent without detectable change of the amount of SiO_2 which was incorporated in the gel. We have also injected SiCl_4 at rates as high as 50 g/min SiO_2 equivalent into 3000 ml water and achieved normal gelation, and we believe that even higher relative injection rates are possible.

Injection can be continued until gelation occurs, or it can be terminated prior to gelation. In the former case, we have observed that, in many cases, gelation occurs when the $\text{H}_2\text{O}/\text{SiO}_2$ ratio is about 30 mols/mol. In the latter case gelation occurs after a time that generally depends on, inter alia, the composition of the sol, the temperature, and the surface atmosphere.

Gelation generally is substantially independent of batch size, all other relevant factors being equal. Thus, we believe that quite large quantities (e.g., > 20 l) of gel can be produced in one batch. If gas delivery systems of sufficient capacity are available, such quantities of gel can be produced in times as short as a few minutes. For instance, with continuous injection to gelation, about 2200 g of SiO_2 equivalent are required to produce 20l of vapogel. If the gas delivery system injects the gas at a rate of 550 g/min SiO_2 equivalent then gelation will occur after only about 4 minutes.

Gel formation is accompanied by increasing viscosity of the sol. FIG. 4 shows exemplary plots of viscosity vs. time for a representative prior art sol-gel process, namely, formation of a silica gel by means of the alkoxide process involving mixing TEOS, ethanol, and water. The variable in FIG. 4 is pH, with longer gel times corresponding to a more acidic solution.

FIG. 5 exemplarily shows viscosity vs. time for a particular embodiment of the vapogel process, in which SiCl_4 was injected into 100 ml H_2O (containing 0.5 ml HCl) at a rate of about 10 gms SiO_2 equivalent/minute. The viscosity increased within a few seconds from about 0.01 poise to more than 10^7 poise, with gelation occurring less than 5 minutes after the start of gas injection. This is to be compared with the processes of FIG. 4, in which gelation time typically is hours. The short gelation times that are achievable with the inventive process are of economic significance and are considered to be an important aspect of the inventive process.

Immediately after gelation, the gel texture (which may be related to the mechanical strength of the material) may not be suitable for further processing. However, a suitable texture generally is reached within about one hour (typically < 6 hours) from the onset of gelation. The gel body typically is then removed from the vessel in which it was formed, and is either dried in bulk or partitioned into particles of an appropriate size and then dried. Drying of appropriately shaped gel bodies can be carried out by known techniques, substantially in the same way prior art monolithic gel bodies are dried.

In currently preferred embodiments of the inventive method, the gel is partitioned into particles of a substantially predetermined size. This can be done by any appropriate technique, including pushing the gel through a screen, rapid drying leading to spontaneous disintegration, and quenching (e.g., in water) of a hot gel body that also leads to spontaneous disintegration. Rapid heating can, inter alia, be by means of microwaves. Particles produced by spontaneous disintegration of the vapogel-produced gel typically have a relatively narrow size distribution, and average size frequently in the range 0.5-1 mm.

It is currently believed that these advantageous attributes of vapogel-produced gel are at least in part a consequence of the mechanical properties of the gel. In particular, vapogel-produced gel bodies typically are mechanically relatively weak (i.e., having a breaking stress in the range from about 1×10^4 to about $5 \times 10^6 \text{ N/m}^2$), and are substantially elastic (i.e., application, and subsequent removal, of a stress equal to 90% of the breaking stress of a body results in a corresponding permanent strain [a strain which persists for at least 2 hours] of no more than about 10%). Furthermore, the volumetric porosity of the dried gel typically is in the range from about 10% to about 90%, with pore sizes in the dried gel typically such as to yield a surface area in the range from about $10 \text{ m}^2/\text{g}$ to about $1000 \text{ m}^2/\text{g}$.

The gel is dried by some appropriate technique, such as heating in a furnace, in air, in an inert atmosphere (e.g., Ar, He), or under partial vacuum. Exemplarily, the drying program comprises maintaining the gel particles (or gel body) at a temperature in the range $150\text{--}300^\circ \text{C}$ in a partial vacuum.

The porous dried particles (or porous dried body) can then be consolidated into homogeneous glass particles (or into a homogeneous glass body). Consolidation temperatures may depend on the material composition. For instance, SiO_2 particles advantageously are consolidated at temperatures in the range $900\text{--}1400^\circ \text{C}$, whereas SiO_2 -based particles that contain GeO_2 advantageously are consolidated in the range $900\text{--}1200^\circ \text{C}$.

As will be appreciated by those skilled in the art, for at least some applications (e.g., optical fiber), it is desirable to remove essentially all adsorbed water molecules and hydroxyl ions (OH) from the material. Typically, this is accomplished by exposing the heated porous material to a Cl_2 -containing atmosphere in a known manner. Such dehydration treatment frequently is (but need not be) combined with consolidation.

The vapogel-derived dry porous particles or homogeneous glass particles can be used, in a known manner, as feedstock for producing a glass body, e.g., an optical fiber preform. See, for instance, U.S. Patent 3,954,431, which discloses a particularly advantageous technique namely, a technique that uses a plasma as heat source. Techniques based on the use of a combustion heat source (e.g., $\text{O}_2\text{--H}_2$ flame) are possible, but are not preferred for the manufacture of the core and adjacent region of preforms for low loss optical fiber.

FIG. 6 schematically depicts exemplary apparatus for forming a glass body (e.g., an optical fibre preform from which an optical fiber can be drawn by a known technique) by fusion of vapogel-derived glass particles in a plasma torch 69. In this exemplary apparatus, the plasma torch, comprises a fused silica mantle 62 connected by a tube 61 to a gas source 60 which feeds the gas desired for the plasma discharge 64 into the mantle. The plasma is excited by means of RF coil 63 and an RF generator that is not shown. The particles are directed into the plasma region by a tube 66 from powder source 65, e.g., a vibratory powder feeder which continuously introduces a regulated quantity of powder into a stream of He. The powder-gas stream 67 issuing from 66 is directed at the top portion of the axially forming glass boule 68. Boule formation is started by directing 67 against the top surface of glass bait 70. The bait is supported by means not shown, and is rotated to promote the symmetry of the boule. The bait is lowered so as to keep the position of the top of 68 constant relative to the apparatus.

FIG. 7 shows a further exemplary embodiment of apparatus for forming a glass body by fusion of vapogel-derived glass particles by means of a plasma torch. The apparatus is substantially as shown in FIG. 6, except that the gas-particle stream 67 is directed at the circumference of the rotating glass boule 71 and fused thereto. The boule is formed by, e.g., initially providing a glass bait rod and fusing particles to the circumference of the bait rod. The embodiment of FIG. 7 thus results in formation of a compound boule comprising a preproduced central (e.g., the core of a fiber preform) portion and an overcladding, exemplarily glass of lower refractive index than the central portion.

Example 1:

A stream of O_2 and $SiCl_4$ was introduced into a beaker containing 3500 ml of deionized water. The gas stream was produced by flowing the O_2 through a bubbler assembly consisting of a 3000-ml PYREX container with a PYREX condenser. The temperature of the bubbler was set at $57.5^\circ C$, and the condenser temperature at $55^\circ C$. Heated TEFLON tubing was used to carry the $SiCl_4$ -containing gas stream. The $SiCl_4$ flow rate was approximately 1000 cc/min. The water in the beaker was initially at room temperature, was being stirred with TEFLON-coated stirbar, and was open to the atmosphere. A He-Ne laser beam was directed horizontally through the contents of the beaker, and a silicon photodetector was placed at 90° to the beam, to detect light scattered in the sol. The intensity of the scattered light was monitored by means of a lock-in amplifier, gelation being indicated by a very rapid rise in the detected intensity. Gelation occurred in less than eight minutes. The gas flow was terminated at gelation. The temperature of the sol at gelation was about $70^\circ C$. After aging of the gel for about two hours (during which time the mechanical strength of the gel increased), the gel was removed from the beaker and grated by means of an 18-mesh TEFLON screen. The resulting gel particles were placed in a PYREX jar and dried at $250^\circ C$ for about six hours in a partial vacuum. This resulted in removal of essentially all water from the gel particles, and shrinkage such that the post-drying average linear particle size was about 0.5 mm. The total weight of the SiO_2 particles was about 180 gm. The particles were consolidated by firing in air in an electric resistance furnace for two hours at $1350^\circ C$. The resulting glass particles were essentially bubble-free, and the size distribution remained substantially unchanged. Substantially no agglomeration occurred. A glass body was produced by plasma fusing the glass particles to a rotating horizontal fused silica bait rod, in a manner substantially as depicted in FIG.

Examples 2-13:

The composition of the glasses (in mol% of the oxide formed from the given precursor) produced in Examples 2-13 are listed in Table I. The procedure for forming the glass particles in Examples 2, 3 and 5 was substantially as described in Example 1, except as noted below. The thus formed glass particles are plasma fused to a vertical bait rod substantially as depicted in FIG. 6.

In Example 2, a $GeCl_4$ bubbler was also provided. The $GeCl_4$ bubbler temperature was $64^\circ C$, the condenser temperature was $56^\circ C$, the flow rates were such that the combined metal chloride flow rate was about 1000 cc/min, and the consolidation temperature was $1100^\circ C$.

In Examples 3 and 5, the $AlCl_3$, and $AlCl_3$ and $NaCl$, respectively, were dissolved in the deionized water prior to the introduction of the $O_2/SiCl_4$ gas into the water.

The procedure to be used in forming the glasses of Examples 4, and 6-13 is substantially as described in Example 1, except as noted below.

TABLE I

Example No.	Precursor									
	SiCl ₄	SnP ₄	GeCl ₄	TiCl ₄	SnCl ₄	AlCl ₃	NaCl	NH ₄ B ₅ O ₈ ·H ₂ O	H ₃ PO ₃	H ₃ BO ₃
2	20		20							
3	20					20				
4	26				5					
5	75					20	5			
6	25					10		5		
7	91		4						5	
8	26			5						
9	26						5			
10		100								
11	20						4			
12	24		1							15
13	26								5	

In Examples 6, 7, 9, 11, 12 and 13, the precursors other than SiCl₄ (and GeCl₄, where appropriate) are dissolved in the deionized water prior to introduction of the O₂/SiCl₄ gas into the water.

In examples 7 and 12, a GeCl_4 bubbler as described in Example 2 is used, and the consolidation temperature is 1100°C .

In example 10, all PYREX vessels are replaced by TEFLON-coated vessels.

5 Example 14:

A silica glass body is produced substantially as described in Example 1, except that the particles are not consolidated prior to being fed into the plasma flame.

10 Example 15:

A silica glass body is produced substantially as described in Example 1, except that about 1500 g of colloidal fumed silica (surface area about $200\text{ m}^2/\text{g}$) are suspended in the 3500 ml deionized water prior to introduction of the SiCl_4 gas.

15 Example 16:

On the inside of a commercial 46 by 50 mm fused silica substrate tube is deposited (by plasma-assisted MCVD) in a known manner pure silica cladding material and germania-doped silica core material such that, after collapsing the tube, a 22.6 mm diameter glass rod with a step index profile ($\Delta = 0.8\%$, core diameter about 3.2 mm deposited cladding diameter about 12.8 mm) results. Fused silica particles (average size 0.5 μm), produced substantially as described in Example 1, are fused to the thus produced glass rod by means of an RF plasma torch, in a manner generally as depicted in FIG. 7, such that a 50 mm diameter preform results. From the thus produced preform single mode optical fiber (125 μm diameter, 8 μm core diameter) is drawn in a known manner. The fiber has loss below 1 dB/km at 1.3 μm .

Claims

1. A method of producing a silica-containing glass body, the method comprising forming a silica-containing gel and producing the glass body from the gel; CHARACTERISED IN THAT the method comprises introducing a gas stream into an aqueous medium, the gas stream comprising an effective concentration of a gaseous silicon halide, such that the silica-containing gel is formed from the aqueous medium.
2. Method of claim 1, CHARACTERISED BY selecting the gaseous silicon halide from the group consisting of SiCl_4 and SiF_4 .
3. Method of claim 1 or 2, CHARACTERISED IN THAT the gas stream is caused to comprise a gas selected from the group consisting of SnCl_4 , TiCl_4 , ZrCl_4 , PbCl_2 , SbCl_3 , GeCl_4 , BCl_3 and PCl_3 .
4. Method of claims 1, 2 or 3 CHARACTERISED BY dissolving at least one member of the group consisting of AlCl_3 , NaCl , $\text{NH}_4\text{B}_5\text{O}_8 \cdot \text{H}_2\text{O}$, H_3PO_3 , and H_3BO_3 in the aqueous medium.
5. Method of claim 1, 2, 3 or 4 CHARACTERISED IN THAT the aqueous medium is caused to comprise pre-existing colloidal particles.
6. Method of claim 5 CHARACTERISED IN THAT the aqueous medium is caused to comprise fumed silica.
7. Method of claim 1, 2, 3, 4, 5 or 6 CHARACTERISED BY producing substantially dry porous first particles from the gel.
8. Method of claim 7, CHARACTERISED BY consolidating the first particles into glass particles.
9. Method of claim 7 or 8, CHARACTERISED BY fusing the first particles or the glass particles to a glass substrate.

In examples 7 and 12, a GeCl_4 bubbler as described in Example 2 is used, and the consolidation temperature is 1100°C .

In example 10, all PYREX vessels are replaced by TEFLON-coated vessels.

5 Example 14:

A silica glass body is produced substantially as described in Example 1, except that the particles are not consolidated prior to being fed into the plasma flame.

10 Example 15:

A silica glass body is produced substantially as described in Example 1, except that about 1500 g of colloidal fumed silica (surface area about $200\text{ m}^2/\text{g}$) are suspended in the 3500 ml deionized water prior to introduction of the SiCl_4 gas.

15

Example 16:

On the inside of a commercial 46 by 50 mm fused silica substrate tube is deposited (by plasma-assisted MCVD) in a known manner pure silica cladding material and germania-doped silica core material such that, after collapsing the tube, a 22.6 mm diameter glass rod with a step index profile ($\Delta = 0.8\%$, core diameter about 3.2 mm deposited cladding diameter about 12.8 mm) results. Fused silica particles (average size 0.5 μm), produced substantially as described in Example 1, are fused to the thus produced glass rod by means of an RF plasma torch, in a manner generally as depicted in FIG. 7, such that a 50 mm diameter preform results. From the thus produced preform single mode optical fiber (125 μm diameter, 8 μm core diameter) is drawn in a known manner. The fiber has loss below 1 dB/km at 1.3 μm .

Claims

1. A method of producing a silica-containing glass body, the method comprising forming a silica-containing gel and producing the glass body from the gel; CHARACTERISED IN THAT the method comprises introducing a gas stream into an aqueous medium, the gas stream comprising an effective concentration of a gaseous silicon halide, such that the silica-containing gel is formed from the aqueous medium.
2. Method of claim 1, CHARACTERISED BY selecting the gaseous silicon halide from the group consisting of SiCl_4 and SiF_4 .
3. Method of claim 1 or 2, CHARACTERISED IN THAT the gas stream is caused to comprise a gas selected from the group consisting of SnCl_4 , TiCl_4 , ZrCl_4 , PbCl_2 , SbCl_3 , GeCl_4 , BCl_3 and PCl_3 .
4. Method of claims 1, 2 or 3 CHARACTERISED BY dissolving at least one member of the group consisting of AlCl_3 , NaCl , $\text{NH}_4\text{B}_5\text{O}_8 \cdot \text{H}_2\text{O}$, H_3PO_3 , and H_3BO_3 in the aqueous medium.
5. Method of claim 1, 2, 3 or 4 CHARACTERISED IN THAT the aqueous medium is caused to comprise pre-existing colloidal particles.
6. Method of claim 5 CHARACTERISED IN THAT the aqueous medium is caused to comprise fumed silica.
7. Method of claim 1, 2, 3, 4, 5 or 6 CHARACTERISED BY producing substantially dry porous first particles from the gel.
8. Method of claim 7, CHARACTERISED BY consolidating the first particles into glass particles.
9. Method of claim 7 or 9, CHARACTERISED BY fusing the first particles or the glass particles to a glass substrate.



10. Method of claim 7, CHARACTERISED BY forming the first particles by a process that comprises partitioning the gel such that gel particles having a relatively narrow size distribution are formed, and further comprising substantially drying the gel particles.
- 5 11. Method of claim 10, CHARACTERISED BY partitioning the gel by mechanical partitioning means.
12. Method of claim 7, 10 or 11, further CHARACTERISED BY contacting the first particles with an atmosphere that comprises Cl_2 .
- 10 13. Method of claim 1, 2, 3, 4, 5 or 6 CHARACTERISED BY forming a gel body, substantially drying the gel body, whereby the porous body is formed, and consolidating the porous body, such that the glass body results.
14. Method of claim 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12 or 13 CHARACTERISED IN THAT the glass body is an optical fiber, and wherein the method comprises drawing an optical fiber from an intermediate glass body.
- 15

Revendications

1. Un procédé de fabrication d'un corps en verre contenant de la silice, ce procédé comprenant la formation d'un gel contenant de la silice et la fabrication du corps en verre à partir du gel; CHARACTERISE EN CE QUE le procédé comprend l'introduction d'un écoulement de gaz dans un milieu aqueux, l'écoulement de gaz ayant une concentration effective d'un halogénure de silicium gazeux qui est telle que le gel contenant de la silice se forme à partir du milieu aqueux.
- 25 2. Le procédé de la revendication 1, CHARACTERISE PAR la sélection de l'halogénure de silicium gazeux dans le groupe qui comprend SiCl_4 et SiF_4 .
- 30 3. Procédé selon la revendication 1 ou 2, CHARACTERISE PAR le fait que l'écoulement de gaz comprend un gaz qui est sélectionné dans le groupe comprenant SnCl_4 , TiCl_4 , ZrCl_4 , PbCl_2 , SbCl_3 , GeCl_4 , BCl_3 et PCl_3 .
- 35 4. Procédé selon les revendications 1, 2 ou 3, CHARACTERISE PAR la dissolution dans le milieu aqueux d'au moins un membre du groupe comprenant AlCl_3 , NaCl , $\text{NH}_4\text{B}_5\text{O}_8 \cdot \text{H}_2\text{O}$, H_3PO_3 et H_3BO_3 .
5. Procédé selon la revendication 1, 2, 3 ou 4, CHARACTERISE PAR le fait qu'on introduit dans le milieu aqueux des particules colloïdales préexistantes.
- 40 6. Procédé selon la revendication 5, CHARACTERISE PAR le fait qu'on introduit dans le milieu aqueux de la silice sous forme de particules de suie.
7. Procédé selon la revendication 1, 2, 3, 4, 5 ou 6, CHARACTERISE PAR la fabrication de premières particules poreuses pratiquement sèches à partir du gel.
- 45 8. Procédé selon la revendication 7, CHARACTERISE PAR la consolidation des premières particules pour donner des particules de verre.
9. Procédé selon la revendication 7 ou 8, CHARACTERISE PAR la fusion des premières particules ou des particules de verre sur un substrat en verre.
- 50 10. Procédé selon la revendication 7, CHARACTERISE PAR la formation des premières particules par un processus qui comprend le fractionnement du gel, de façon à former des particules de gel ayant une distribution de taille relativement étroite, et comprenant en outre l'opération qui consiste à sécher pratiquement les particules de gel.
- 55 11. Procédé selon la revendication 10, CHARACTERISE PAR le fractionnement du gel par des moyens de fractionnement mécaniques.



12. Procédé selon la revendication 7, 10 ou 11, CARACTERISE en outre par la mise en contact des premières particules avec une atmosphère qui contient Cl_2 .

13. Procédé selon la revendication 1, 2, 3, 4, 5 ou 6, CARACTERISE EN CE QUE : on forme un bloc de gel, on sèche pratiquement le bloc de gel, ce qui a pour effet de former un bloc poreux, et on consolide le bloc poreux, de façon à obtenir le corps en verre.

14. Procédé selon la revendication 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12 ou 13, CARACTERISE EN CE QUE le bloc de verre est une fibre optique, et le procédé comprend l'étirage d'une fibre optique à partir d'un bloc de verre intermédiaire.

Patentansprüche

1. Verfahren zur Herstellung eines Quarz enthaltenden Glaskörpers, bei dem ein Quarz enthaltendes Gel gebildet und der Glaskörper aus dem Gel hergestellt wird, dadurch gekennzeichnet, daß ein Gasstrom in ein wäßriges Medium eingeführt wird und der Gasstrom eine wirksame Konzentration eines gasförmigen Siliciumhalids umfaßt, derart, daß das Quarz enthaltende Gel aus dem wäßrigen Medium gebildet wird.

2. Verfahren nach Anspruch 1, gekennzeichnet durch Auswählen des gasförmigen Siliciumhalids aus der aus SiCl_4 und SiF_4 bestehenden Gruppe.

3. Verfahren nach Anspruch 1 oder 2, dadurch gekennzeichnet, daß der Gasstrom ein Gas umfaßt, das aus der aus SnCl_4 , TiCl_4 , ZrCl_4 , PbCl_2 , SbCl_3 , GeCl_4 , BCl_3 und PCl_3 bestehenden Gruppe gewählt wird.

4. Verfahren nach Anspruch 1, 2 oder 3, gekennzeichnet durch Auflösen wenigstens eines Mitglieds der aus AlCl_3 , NaCl , $\text{NH}_4\text{B}_5\text{O}_8 \cdot \text{H}_2\text{O}$, H_3PO_3 und H_3BO_3 bestehenden Gruppe in dem wäßrigen Medium.

5. Verfahren nach Anspruch 1, 2, 3 oder 4, dadurch gekennzeichnet, daß das wäßrige Medium im voraus vorhandene kolloidale Partikel enthält.

6. Verfahren nach Anspruch 5, dadurch gekennzeichnet, daß das wäßrige Medium verdampfes Quarzglas enthält.

7. Verfahren nach Anspruch 1, 2, 3, 4, 5 oder 6, gekennzeichnet durch Herstellen im wesentlichen trockener, poröser, erster Partikel aus dem Gel.

8. Verfahren nach Anspruch 7, dadurch gekennzeichnet, daß die ersten Partikel zu Glaspartikeln verfestigt werden.

9. Verfahren nach Anspruch 7 oder 8, dadurch gekennzeichnet, daß die ersten Partikel oder die Glaspartikel zu einem Glassubstrat verschmolzen werden.



10. Verfahren nach Anspruch 7,
dadurch gekennzeichnet,
daß die ersten Partikel durch eine Prozeß gebildet werden, der eine Aufteilung des Gels derart umfaßt,
daß Gelpartikel mit einer verhältnismäßig engen Größenverteilung gebildet werden, und ferner ein
weitgehendes Trocknen der Gelpartikel vorsieht.

11. Verfahren nach Anspruch 10,
dadurch gekennzeichnet,
daß das Gel durch mechanische Aufteilungsmittel aufgeteilt wird.

12. Verfahren nach Anspruch 7, 10 oder 11,
ferner dadurch gekennzeichnet,
daß die ersten Partikel mit einer Atmosphäre in Kontakt gebracht werden, die Cl_2 umfaßt.

13. Verfahren nach Anspruch 1, 2, 3, 4, 5 oder 6,
gekennzeichnet durch
Bilden eines Gelkörpers, weitgehendes Trocknen des Gelkörpers, wodurch der poröse Körper gebildet
wird, und Verfestigen des porösen Körpers, derart, daß sich der Glaskörper ergibt.

14. Verfahren nach Anspruch 1, 2, 3, 4, 5, 6, 7, 8, 9, 10, 11, 12 oder 13,
dadurch gekennzeichnet,
daß der Glaskörper eine optische Faser ist und
daß das Verfahren das Ziehen einer optischen Faser aus einem Glaszwischenkörper umfaßt.

