

ABSTRACT OF THE DISCLOSURE

SLURRY POLYMERIZATION PROCESS

A process to control the heat transfer coefficient in slurry olefin polymerization processes comprising shocking the polymerization reactor is provided. This shock comprises quickly decreasing and then restoring to normal operating conditions, the higher alpha-olefin comonomer to ethylene monomer weight feed ratio.