

**THERMOPLASTIC RESIN COMPOSITIONS FOR USE IN INTERGRAL
MOLDING WITH SILICONE RUBBER AND INTEGRALLY MOLDED PARTS**

ABSTRACT

5 A thermoplastic resin composition comprising 100 parts
by weight of a thermoplastic resin and 2 to 12 parts by
weight of a thermoplastic resin oligomer containing 0.1 to
35% by weight of an aliphatic unsaturated group is molded
with silicone rubber to form an integrally molded part. The
10 thermoplastic resin composition maintains the inherent
properties of the thermoplastic resin and firmly bonds with
silicone rubber.

Figure 6