


Abstract

A multi-pack aqueous coating composition prepared by mixing (A) a base coating composition containing, as a binder component, a water-dispersible copolymer having a hydroxyl number of 5 to 200 mg KOH/g, (B) a crosslinking agent containing a compound having at least two isocyanate groups in one molecule in such an amount that the isocyanate group is contained in the range of 0.2 to 3.0 moles per one mole of the hydroxyl group contained in the base coating composition (A), and (C) an organosilicate represented by the following general formula:



where R is same or different and is hydrogen atom or a monovalent hydrocarbon group having 1 to 10 carbon atoms, and/or its condensate in the range of 0.1 to 50 parts by weight per 100 parts by weight of a total amount of a resin solid content of the base coating composition (A) and a solid content of the crosslinking agent (B).

This Sheet Has Been Replaced

