

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08G 18/48, 18/40, 18/63, 65/26 // (C08G 18/48, 101:00) ✓		A1	(11) International Publication Number: ✓ WO 97/27236 (43) International Publication Date: 31 July 1997 (31.07.97) ✓
(21) International Application Number: ✓ PCT/EP97/00306 (22) International Filing Date: 23 January 1997 (23.01.97) ✓ (30) Priority Data: ✓ 08/592,087 ✓ 26 January 1996 (26.01.96) ✓ US ✓ (71) Applicant (for all designated States except MN): ARCO CHEMICAL TECHNOLOGY, L.P. [US/US]; Two Greenville Crossing, Suite 238, 4001 Kennett Pike, Greenville, DE 19807 (US). ✓ (71) Applicant (for MN only): ARCO CHEMIE TECHNOLOGIE NEDERLAND B.V. [NL/NL]; Theemsweg 14, NL-3197 KM Botlek Rotterdam (NL). ✓ (72) Inventor: HAGER, Stanley; 5310 Edgebrook Road, Cross-lanes, WV 25313 (US). ✓ (74) Agent: CROPP, John, Anthony, David; Mathys & Squire, 100 Gray's Inn Road, London WC1X 8AL (GB).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.	
(54) Title: POLY(OXYPROPYLENE/OXYETHYLENE) RANDOM POLYOLS USEFUL IN PREPARING FLEXIBLE HIGH RESILIENCE FOAM WITH REDUCED TENDENCIES TOWARD SHRINKAGE AND FOAM PREPARED THEREWITH ✓			
(57) Abstract High resilience polyurethane foams exhibiting little or no shrinkage may be prepared from low unsaturation double metal cyanide catalyzed polyoxyalkylene polyols in amounts greater than 20 weight percent of the total polyol component, when low unsaturation poly(oxypropylene/oxyethylene) random polyols having less than 35 weight percent of an all polyoxypropylene block catalyzed by double metal cyanide catalysts and one or more external random polyoxypropylene/polyoxyethylene blocks each containing 2 weight percent or more oxyethylene moieties, and an unsaturation of less than 0.02 meq/g are employed.			