

(51) International Patent Classification:

C08F 230/08 (2006.01)

(21) International Application Number:

PCT/US2012/026213

(22) International Filing Date:

23 February 2012 (23.02.2012)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

61/447,164 28 February 2011 (28.02.2011) US

(71) Applicant (for all designated States except US):

COOPERVISION INTERNATIONAL HOLDING COMPANY, LP [GB/BB]; Edghill House, Wildey Business Park, Suite 2, St. Michael (BB).

(72) Inventors; and

(75) Inventors/Applicants (for US only): FRANCIS, Charles A. [US/US]; c/o Coopervision, Inc., 5870 Stoneridge Drive, Suite 1, Pleasanton, CA 94588 (US). ZHENG, Ying [CN/US]; c/o Coopervision, Inc., 5870 Stoneridge Drive, Suite 1, Pleasanton, CA 94588 (US). XU, Yuan [US/US]; c/o Coopervision, Inc., 5870 Stoneridge Drive, Suite 1, Pleasanton, CA 94588 (US). YAO, Li [US/US]; c/o Coopervision, Inc., 5870 Stoneridge Drive, Suite 1, Pleasanton, CA 94588 (US). BACK, Arthur [AU/US]; c/o Coopervision, Inc., 5870 Stoneridge Drive, Suite 1, Pleasanton, CA 94588 (US). HONG, Ye [US/US]; c/o Coopervision, Inc., 5870 Stoneridge Drive, Suite 1, Pleasanton, CA 94588 (US). CHEN, Charlie [US/US]; c/o Coopervision, Inc., 5870 Stoneridge Drive, Suite 1, Pleasanton, CA 94588 (US).

sion, Inc., 5870 Stoneridge Drive, Suite 1, Pleasanton, CA 94588 (US).

(74) Agent: KILYK, Luke A.; Kilyk & Bowersox, P.L.L.C., 400 Holiday Court, Suite 102, Warrenton, VA 20186 (US).



(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— without international search report and to be republished upon receipt of that report (Rule 48.2(g))

(54) Title: DIMENSIONALLY STABLE SILICONE HYDROGEL CONTACT LENSES



(57) Abstract: Dimensionally stable silicone hydrogel contact lenses are described. The lenses are derived from a polymerizable composition including a first siloxane monomer represented by formula (1): wherein m of formula (1) represents one integer from 3 to 10, n of formula (1) represents one integer from 1 to 10, R¹ of formula (1) is an alkyl group having from 1 to 4 carbon atoms, and each R² of formula (1) is independently either a hydrogen atom or a methyl group; the lenses also include units derived from a second siloxane monomer represented by formula (2): wherein R₁ of formula (2) is selected from either hydrogen atom or a methyl group; R₂ of formula (2) is selected from either of hydrogen atom or a hydrocarbon group having 1 to 4 carbon atoms; m of formula (2) represents an integer of from 0 to 10; n of formula (2) represents an integer of from 4 to 100; a and b represent integers of 1 or more; a+b is equal to 20-500; b/(a+b) is equal to 0.01-0.22; the configuration of siloxane units includes a random configuration, the second siloxane monomer having a number average molecular weight of at least 3,000 daltons that is present in the polymerizable composition in an amount such that ratio of the first siloxane monomer to the second siloxane monomer is at least 2:1 based on unit parts by weight. Batches of silicone hydrogel contact lenses and methods of making silicone hydrogel contact lenses are also described.