CLAIMS

1. A curable coating agent composition comprising: a silicone oligomer (A) having a hydrolyzable functional group; a condensation reaction catalyst (B); a silane compound (C); and an organic solvent (D), wherein the component (C) contains at least one or more of a silane compound (c1) having a primary amino group and a hydrolyzable functional group and at least one or more of a silane compound (c2) having a secondary amino group and a hydrolyzable functional group.

2. The curable coating agent composition according to claim 1, containing 0.1 to 20 parts by mass of the component (c1) and 0.1 to 20 parts by mass of the component (c2) with respect to 100 parts by mass of the component (A).

3. The curable coating agent composition according to claim 1 or 2, wherein the component (A) contains a silicone oligomer (a1) having a hydrolyzable functional group having a viscosity of 91 to 300 mm^2/s at 25°C and a silicone oligomer (a2) having a hydrolyzable functional group having a viscosity of 7 to 90 mm^2/s at 25°C.

4. The curable coating agent composition according to any one of claims 1 to 3, wherein the component (B) is at least one selected from the group consisting of phosphoric acid, an organoaluminum compound, an organotitanium compound, an organozirconium compound, an organozinc compound, an organotin compound, and an organocobalt compound.

5. The curable coating agent composition according to any one of claims 1 to 4, wherein the component (B) is at least one selected from the group consisting of an organoaluminum compound and an organotitanium compound.

6. The curable coating agent composition according to any one of claims 1 to 5, wherein the hydrolyzable functional group of the component (A) is an alkoxysilyl group.

7. The curable coating agent composition according to any one of claims 1 to 6, forming a coating on a surface of any of metal, glass, ceramics, plastic, and fiber.

8. The curable coating agent composition according to any one of claims 1 to 7, wherein the component (c1) is 3-aminopropyltrimethoxysilane and the component (c2) is N-phenyl-3-aminopropyltrimethoxysilane.

9. The curable coating agent composition according to any one of claims 1 to 8, containing 0.5 to 10 parts by mass of the component (c1) and 0.5 to 10 parts by mass of the component (c2) with respect to 100 parts by mass of the component (A).

10~~8~~. A cured coating film obtained by curing the curable coating agent composition according to any one of claims 1 to~~—7~~ 9.