

PCT SG 9700564-9
RTMP'S COPY



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁶: C04B 11/00, 11/024, 16/02, 16/06, 28/14, E04B 1/74	A1	(11) International Publication Number: WO 96/05149 (43) International Publication Date: 22 February 1996 (22.02.96)
(21) International Application Number: PCT/US95/09703 (22) International Filing Date: 8 August 1995 (03.08.95) (30) Priority Data: 08/287,392 8 August 1994 (08.08.94) US (71) Applicant: VSG INTERIORS, INC. [US/US]; 125 South Franklin Street, Chicago, IL 60606-4678 (US). (72) Inventor: BAIG, Mirza, A.; 9415 Meadow Lane, Des Plaines, IL 60016 (US). (74) Agent: KEEFER, Timothy, J.; Ladas & Parry, 224 South Michigan Avenue, Chicago, IL 60604 (US).		(81) Designated States: AM, AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LT, LU, LV, MD, MG, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TT, UA, UG, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG). Published <i>With international search report.</i>
(54) Title: A GYPSUM/CELLULOSIC FIBER ACOUSTICAL TILE COMPOSITION (57) Abstract An acoustical tile composition based on a gypsum/cellulosic fiber composition which can replace all or a portion of the mineral wool normally present in acoustical ceiling tiles. The gypsum/cellulosic fiber composition is combined with a lightweight aggregate material and a binder to form a composition which is used in a water-felting process to manufacture acoustical ceiling tiles and panels. The preferred source of the cellulosic fiber is a composite gypsum/cellulose fiber material which is prepared by mixing the gypsum and cellulosic fiber material with sufficient water to form a dilute slurry which is then heated under pressure to calcine the gypsum, converting it to an alpha calcium sulfate hemihydrate. The resulting composite material comprises cellulosic fibers physically interlocked with calcium sulfate crystals. Another source of both gypsum and cellulosic fibers is waste (scrap) gypsum wallboard. Expanded perlite is the preferred lightweight aggregate material.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LJ	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

9700564-9

A GYPSUM/CELLULOSIC FIBER ACOUSTICAL TILE COMPOSITIONFIELD OF THE INVENTION

This invention relates to acoustical tile compositions useful in manufacturing acoustical tiles and panels for ceiling applications. More particularly, this invention relates to acoustical tile compositions based on a gypsum/cellulosic fiber composition which can replace all or a portion of the mineral wool normally present in acoustical ceiling tiles. The invention also relates to a novel gypsum/cellulosic fiber/lightweight aggregate material composition which is used in a water-felting process to manufacture acoustical ceiling tiles and panels.

BACKGROUND OF THE INVENTION

The water-felting of dilute aqueous dispersions of mineral wool and lightweight aggregate is a commercial process for manufacturing acoustical ceiling tile. In this process, a dispersion of mineral wool, lightweight aggregate, binder and other ingredients as desired or necessary is flowed onto a moving foraminous support wire, such as that of a Fourdrinier or Oliver mat forming machine for dewatering. The dispersion dewaterers first by gravity and then vacuum suction means; the wet mat is dried in heated convection drying ovens, and the dried

-2-

material is cut to the desired dimensions and optionally top coated, such as with paint, to produce acoustical ceiling tiles and panels.

For many years, acoustical ceiling tile has also been made by a wet pulp molded or cast process such as described in U.S. Patent No. 1,769,519. According to the teaching of this patent, a molding composition comprising granulated mineral wool fibers, fillers, colorants and a binder, in particular a starch gel, is prepared for molding or casting the body of the tile. This mixture or composition is placed upon suitable trays which have been covered with paper or a metallic foil and then the composition is screeded to a desired thickness with a screed bar or roller. A decorative surface, such as elongated fissures, may be provided by the screed bar or roller. The trays filled with the mineral wool pulp or composition are then placed in an oven to dry or cure the composition. The dried sheets are removed from the trays and may be treated on one or both faces to provide smooth surfaces, to obtain the desired thickness and to prevent warping. The sheets are then cut into tiles of a desired size.

In our U.S. Patent No. 5,320,677 we disclose a composite material and method for making it wherein ground gypsum is calcined under pressure in a dilute slurry in the presence of a cellulosic fiber. The

-3-

uncalcined, ground gypsum and the cellulosic fiber are mixed together with sufficient water to form a dilute slurry which is then heated under pressure to calcine the gypsum, converting it to calcium sulfate alpha hemihydrate. The resulting co-calcined material consists of the cellulosic fiber physically interlocked with calcium sulfate crystals. This interlocking not only creates a good bond between the calcium sulfate and the cellulosic fiber, it also prevents migration of the calcium sulfate away from the cellulosic fiber when the alpha hemihydrate is subsequently rehydrated to the dihydrate (gypsum).

The co-calcined gypsum/cellulosic fiber material can be dried immediately before it cools to provide a stable, rehydratable alpha hemihydrate composite for later use. Alternatively, the co-calcined material can be directly converted into a usable product by separating the excess water which is not needed for rehydration, forming the composite particles into a desired shape or form, and then rehydrating the particles to a set and stabilized gypsum/cellulosic fiber composite material.

Mineral wool acoustical tiles are very porous which is necessary to provide good sound absorption.

The prior art (U.S. Patent Nos. 3,498,404; 5,013,405 and 5,047,120) also discloses that mineral

-4-

fillers, such as expanded perlite, may be incorporated into the composition to improve sound absorbing properties and to provide light weight.

It is an object of this invention to provide an improved acoustical tile composition for making acousticles having acoustical properties comparable to the mineral wool tiles made by a water-felting process.

The present invention provides a composition suitable for making acoustical tiles consisting essentially of gypsum; cellulosic fiber; a lightweight aggregate material and a binder in which on a dry solids basis there is at least about 15% by weight of gypsum and at least 13% by weight of cellulose fiber.

The present invention also provides the wetted composition suitable for making acoustical tiles consisting essentially of mineral wool, gypsum, cellulosic fiber, a lightweight aggregate material and a binder, in which on a dry solids basis there is at least about 10% by weight of mineral wool, at least about 10% by weight of gypsum and at least 13% by weight of cellulose fiber. A particularly preferred composition employs a gypsum/cellulosic fiber composite material in which the gypsum and cellulosic fiber are co-calcined under pressure to physically interlock the cellulosic fiber with the

-5-

calcium sulfate crystals. The acoustical tiles made from the compositions of this invention have acceptable physical properties for use in suspended ceiling systems. In addition, the compositions which contain waste newsprint and/or waste (scrap) gypsum wallboard are environmental friendly.

DETAILED DESCRIPTION OF THE INVENTION

The acoustical tile compositions of this invention are based on using a gypsum/cellulosic fiber composition as a replacement, either partial or complete, for mineral wool in manufacturing ceiling tiles or panels using a water-felting process. In addition to the gypsum and cellulosic fiber, the composition also contains a lightweight aggregate material and a binder, and it may also contain other additives, such as clay, flocculant and surfactant, normally included in acoustical ceiling tile formulations. As noted above, the composition may contain some mineral wool (in reduced amount), however, it has been found that the compositions of this invention can be used to make mineral wool-free acoustical tiles and panels.

One of the key ingredients in the novel acoustical tile composition of this invention is gypsum (calcium sulfate dihydrate). The solubility of the gypsum in the processing slurry enables the gypsum to function as a flocculant in the

-6-

formulation. This flocculating function provides uniform distribution of fine particles (clay, gypsum, perlite and starch) in the wet mat during the processing. In the absence of this flocculating action, the fine and high density particles tend to migrate to the bottom of the mat during processing which adversely affects drainage of the water from the wet mat. The presence of gypsum in the formulation also provides de-agglomeration of the mineral fiber (if present) and cellulose fiber slurries. The de-agglomeration or dispersant function provided by the gypsum enables the processing of a higher slurry consistency (% solids) which reduces the amount of water to be removed from the mat and increases the production rate. The higher slurry consistency also enables the entrainment of more air during formation of the mat, and this improves the sound absorption property in the dried product.

In addition to the processing benefits provided by the gypsum, it also improves the properties of the acoustical tile. The presence of the gypsum, replacing the mineral wool fiber (partial or complete) in the formulation, provides a significant improvement in the surface hardness of the panels. The improved surface hardness of the ceiling panels also provides good surface texturing (e.g. fissuring,

-7-

perforation, etc.). The higher level of cellulose fiber may also contribute to these improvements. The surface smoothness of the acoustical panels may also be improved by the gypsum whereby sanding of the surface after drying may be eliminated. The gypsum in the panels also provides improved fire properties.

It has also been found that the gypsum/cellulosic fiber formulation does not springback (swell) after the wet pressing and drying operations compared to formulations containing mineral fiber. The non-swelling characteristics of the mineral wool-free ceiling tile indicates that the dry mat thickness can be precisely determined or controlled during the wet pressing operation, thereby eliminating the need to apply a filler coat or to sand the dry mat to control the thickness for finishing the panel.

The gypsum source may be calcium sulfate dihydrate, either uncalcined or calcined to hemihydrate and then rehydrated. Alternatively, the gypsum source may be calcium sulfate hemihydrate (with or without co-calcining) or calcium sulfate anhydrite. As more fully discussed below, the gypsum may be co-calcined with a cellulose fiber material to form a composite material of cellulose fibers interlocked with calcium sulfate crystals.

-8-

Another key ingredient in the novel acoustical tile compositions of this invention is the cellulosic fiber. Several types of cellulosic fiber have been evaluated in these compositions. It is well known to use newsprint in acoustical tile formulations, and both hammermilled and hydropulped newsprint have been evaluated in these compositions. Refined paper fibers and wood fiber may also be used as the source of the cellulosic fiber, however, it has been found that ceiling tiles made with wood fiber, either softwood or hardwood, are more difficult to cut with a knife at the installation site. Furthermore, wood fibers are a more expensive source of the cellulosic fiber.

A preferred source of the cellulosic fiber is a composite gypsum/cellulose fiber material which has been co-calcined as disclosed in U.S. Patent No. 5,320,677. As disclosed therein, uncalcined gypsum and either wood or paper fibers are mixed together with sufficient water to form a dilute slurry which is then heated under pressure to calcine the gypsum, converting it to an alpha calcium sulfate hemihydrate. The resulting composite material comprises cellulosic fibers physically interlocked with calcium sulfate crystals. The composite material can be dried immediately before it cools to provide a stable, but rehydratable calcium sulfate

-9-

hemihydrate, or the composite material slurry can be used directly in manufacturing the acoustical tile. It has been found that the use of co-calcined gypsum/cellulose fiber composite material provides an acoustical tile composition having greater mat solids retention and better wet lap strength, however, it does drain slower and is harder to cut with a knife than tiles made with gypsum physically blended with paper fiber (newsprint), especially if the longer and stronger wood fibers are used.

Another source of both gypsum and cellulosic fibers is waste (scrap) gypsum wallboard. It has been found that the scrap wallboard can be ground into gypsum particles and paper fibers which can be physically mixed with the other ingredients in an acoustical formulation to provide a slurry useful in a water-felting process for preparing a ceiling tile.

Alternatively, the ground scrap wallboard can be used as a feed material in a co-calcining process, and the co-calcined composite gypsum/paper fiber material can be used in a formulation for preparing a ceiling tile by water-felting.

A third key ingredient in the novel acoustical tile compositions of this invention is a lightweight aggregate material. Expanded perlite is preferred for its low cost and performance. This is not a novel ingredient, for it is well known in the art to

-10-

use expanded perlite in acoustical tile compositions.

The expanded perlite provides porosity in the composition which enhances acoustical properties. It has been found that a medium grade expanded perlite provides sufficient porosity and acceptable texturability. An expanded perlite material commercially available from Silbrico Corporation under the designation 3-S perlite has been found acceptable. The medium grade expanded perlite contains perlite particles that are similar in size to granulated mineral wool. Equivalents of the expanded perlite such as vermiculite, glass beads, diatomite or exfoliated clays may also be used as substitutes for the perlite or in combination therewith.

The fourth key ingredient, which also is not novel in acoustical compositions, is a binder. It is well known to use starch as a binder in mineral wool based acoustical tiles. A starch gel may be prepared by dispersing starch particles in water and heating the slurry until the starch is fully cooked and the slurry thickens to a viscous gel. A portion of the cellulosic fibers may be incorporated into the starch slurry prior to cooking. The cooking temperature of the starch slurry should be closely monitored to assure full swelling of the starch granules. A representative cooking temperature for corn starch is

-11-

about 180°F. (82°C.) to about 195°F. (90°C.). Starch may also be used as a binder without pre-cooking the starch to form a gel.

A latex binder may be used in place of the starch or in combination with the starch binder. Many of the latex binders useful in acoustical ceiling formulations are disclosed in U.S. Patent No. 5,250,153. As set forth therein, one of the problems with acoustical panels employing a starch binder is excessive sag, especially in high humidity conditions. It is well known in the art to use thermoplastic binders (latexes) in acoustical tiles based on mineral wool. These latex binders may have a glass transition temperature ranging from about 30°C. to about 110°C. Examples of latex binders include polyvinyl acetate, vinyl acetate/acrylic emulsion, vinylidene chloride, polyvinyl chloride, styrene/acrylic copolymer and carboxylated styrene/butadiene. A kraft paper gel formed by refining the paper fibers may also be used as a binder.

In addition to the four principal ingredients, the acoustical compositions of this invention may also contain inorganic fillers such as clay, mica, wollastonite, silica and other lightweight aggregates, surfactants and flocculants. These

-12-

ingredients are well known in acoustical tile compositions.

The acoustical tile compositions of this invention consist essentially of gypsum, cellulose fiber, a lightweight aggregate material and a binder which can be present, preferably, in the following amounts:

<u>Ingredient</u>	<u>Weight Percent</u>
Gypsum	15-45%
Cellulose Fiber	13-30%
Lightweight Aggregate	25-60%
Binder	3-15%

In some of the examples which follow, soluble gypsum was added to the slurry water prior to incorporating the dry ingredients into the slurry. The reason for this prior addition of gypsum to the slurry water is that gypsum dissolves in water, and the prior addition of gypsum to the slurry water gives better retention of the dry gypsum ingredient in the dried product. Otherwise, it may be necessary to increase the amount of dry gypsum in the ingredient mix to compensate for gypsum going into solution.

Example 1

Acoustical ceiling tiles were prepared to evaluate replacing mineral fiber in a conventional

-13-

water-felted formulation and process. The mineral fiber was replaced with gypsum and wood fiber at 25, 50, 75 and 100% levels. Some tiles were made in which the gypsum and wood fiber were co-calcined prior to incorporation into the acoustical formulation, and other tiles were made in which the gypsum and wood fiber were just physically mixed with the other ingredients without co-calcining. The ratio of gypsum to wood fiber was 85:15 percent by weight in all formulations.

The wood fiber was a softwood obtained from the International Paper Pilot Rock facility. The expanded perlite was Silbrico Corporation 3-S grade.

In addition to the wood fiber, cellulosic fibers were also supplied by shredded newspaper. 1500 grams of water was added to the required amount of newspaper and mixed at high speed in an industrial blender. Corn starch was used as the binder. The flocculant was GEN DRIV 162, and 4 grams of the flocculant were added to 1000 milliliters of deionized water and mixed for at least 2 hours. The surfactant was NEODOL 25-3.

The gypsum and wood fiber were calcined together in a reactor at 15% solids consistency. The calcination was carried out in accordance with the procedures disclosed in U.S. Patent No. 5,320,677. After co-calcining, excess water was removed from the

-14-

composite material by applying a vacuum thereto, afterwhich the composite material was allowed to hydrate fully to calcium sulfate dihydrate (gypsum) prior to drying at 120°F. overnight to constant weight. Another batch of gypsum/wood fiber was co-calcined as previously described, except that after removal of the excess water by vacuum, the composite material was immediately dried at 250°F. for 30 minutes to avoid hydration, followed by drying at 120°F. overnight to constant weight. In this composite material, the calcium sulfate was in the hemihydrate form. After drying, the gypsum/wood fiber composites, in both dihydrate and hemihydrate forms, were broken down in a twin shell blender prior to incorporation into the acoustical tile composition.

In the water-felting process used to make the acoustical tiles, the feed slurry during mat formation was held at 4% solids. This 4% solids consistency was also used in making the control tile which contained 100% mineral fiber and no gypsum/wood fiber. The following formulations (in weight percent) were used to make the tiles:

TABLE 1

Ingredients	Control		Experimental					
	100% M-F		75% M-F		50% M-F		25% M-F	
	0% G/WF	0% G/WF	25% G/WF	50% G/WF	50% G/WF	75% G/WF	75% G/WF	0% M-F 100% G/WF
Mineral Fiber	37.58		28.18	18.79		9.39		0
Gypsum	0		7.98	15.97		23.9		31.94
Wood Fiber	0		1.41	2.82		4.22		5.64
Expand. Perlite	34.83		34.83	34.83		34.83		34.83
Newspaper	15.91		15.91	15.91		15.91		15.91
Total Cellu- losic Fiber	15.91		17.32	18.73		20.13		21.55
CTS-1 Clay	3.54		3.54	3.54		3.54		3.54
Starch	8.01		8.01	8.01		8.01		8.01
Flocculant	0.06		0.06	0.06		0.06		0.06
Surfactant	0.08		0.08	0.08		0.08		0.08

-16-

The evaluation procedures included board formation and processing, drainage time, pressing, drying and the effect on the physical properties of the acoustical tiles. In general, there was no significant difference in the formation of the mat. After mixing all of the ingredients at a 4% solids consistency, the slurry was poured in a Tappi Box and gently mixed with a 12 inch by 12 inch perforated plunger to disperse the solids uniformly. After the mat was formed in the box, vacuum was applied to the wet mat. It took about 30 seconds for the vacuum to reach 20 inches of mercury, afterwhich the vacuum was released and two drainage times were recorded. The first drainage time was when the water totally disappeared from the surface of the mat, and the second drainage time was when the vacuum dial indicator dropped to 5 inches of mercury. At this stage, the vacuum system was turned off, and the wet mat was removed from the Tappi Box and weighed prior to pressing. The vacuum dewatered boards were pressed to 5/8 inch thickness and dried.

The wet mats were dried in an oven at 600°F. for 30 minutes, and thereafter, the oven temperature was lowered to 350°F. and the tiles were dried for an additional 90 minutes. Prior to drying, a study was performed to determine whether the wet mats could be dried without calcining the gypsum therein. It was determined that the mats could be dried in an oven as recited above without calcining the gypsum to hemihydrate or anhydrite.

-17-

After drying, all of the test specimens were cut and subjected to 75°F./50% Relative Humidity conditions for at least 24 hours prior to testing. The specimens were tested for the following:

- 1) density, thickness and MOR strength
- 2) acoustical properties (NRC)
- 3) dimensional stability (water absorption)

The following results were recorded (results are based on an average of 4 specimens in each set unless otherwise indicated):

-18-

TABLE 1D

Density, Thickness, Strength (MOR)						
	No. of	%		Thickness	Density	MOR
	<u>Samples</u>	<u>MF/WE</u>		<u>inch</u>	<u>(lb./ft³)</u>	<u>(psi)</u>
Control	29	100	0	0.627	10.05	53
(100% MF)						
	10	75	25	0.600	9.86	55
Gypsum/	10	50	50	0.602	9.95	56
Wood (Not	10	25	75	0.591	10.05	63
Co-Calcin.)	9	0	100	0.590	10.15	83
	10	75	25	0.630	10.05	48
Dihydrate	10	50	50	0.593	9.99	57
Composite						
(Co-Calcin.)	6	25	75	0.591	9.64	57
	10	0	100	0.559	10.22	63
	10	75	25	0.602	9.76	58
Hemihydrate	10	50	50	0.597	9.39	55
Composite						
(Co-Calcin.)	10	25	75	0.571	9.46	57
	7	0	100	0.568	9.32	53

TABLE 1E

Acoustical Properties
Dihydrate Composite

		Frequency				NRC (avg.)
		250 Hz	500 Hz	1000 Hz	2000 Hz	
Control	Db Drop	32	27	21.5	22	
	Absorbance	0.266	0.392	0.546	0.532	0.434
75% MF/25% GWF	Db Drop	29.5	24	21	21	
	Absorbance	0.326	0.476	0.562	0.560	0.481
50% MF/50% GWF	Db Drop	29	24.5	20	19.5	
	Absorbance	0.332	0.469	0.599	0.606	0.501
25% MF/75% GWF	Db Drop	29.5	22.5	21.5	19.5	
	Absorbance	0.332	0.518	0.546	0.613	0.502
100% GWF	Db Drop	29	23	18.5	19	
	Absorbance	0.339	0.503	0.636	0.621	0.525

TABLE 1F
 Dimensional Stability
 Dihydrate Composite (Avg. 6 Samples)

	% H ₂ O Absorption <u>1 - Hour</u>	% H ₂ O Absorption <u>4 - Hours</u>	% Thickness Increase <u>4 - Hours</u>
Control	387.96	404.14	- 0.540
75% MF/25% GWF	386.48	396.15	0.035
50% MF/50% GWF	390.23	399.90	- 0.412
25% MF/75% GWF	388.10	400.66	- 0.066
100% GWF	388.61	400.50	- 0.121

-21-

The drainage time was not affected when 25% of the mineral fiber was replaced by gypsum and wood fiber; however, the drainage was slightly adversely affected as the gypsum/wood fiber level increased, especially at 100% hemihydrate composite. The thickness of the dewatered mat slightly decreased when the gypsum/wood fiber level increased.

The difference in moisture content, after vacuum dewatering and pressing, was insignificant. The thickness of all of the wet mats was controlled at 0.55 inches during pressing. It appeared that wet pressing only controls the thickness of the mat and does not dewater the mat.

The drying data indicates that some gypsum filtered through the screen with excess water during the mat formation and vacuum dewatering. The average weight loss in the control mats was about 5.5%, whereas the weight loss in the mats containing the gypsum/wood fiber was substantially greater. Gypsum settled in the bottom of the mats during mat formation.

The dried tiles containing the gypsum/wood fiber were also slightly warped, and the warpage was severe when the mineral filler was totally replaced with the uncalcined gypsum/wood fiber. However, there was no warpage in the tiles made by replacing the mineral fiber with a co-calcined dihydrate or hemihydrate composite.

The MOR strength of the tiles containing gypsum/wood fiber was comparable to the control, even though the density was slightly lower (probably due to the gypsum lost during the mat

-22-

formation). The thickness of the tiles containing the gypsum/wood fiber was lower due to the low specific volume for gypsum, which did not spring back during drying as did the 100% mineral fiber tiles.

Duplicate samples of Control and experimental tiles with mineral fiber replaced by gypsum/wood fiber dihydrate composite (co-calcined) were tested for NRC using the Impedance tube method. The samples were not perforated, fissured or painted.

In general, the NRC ratings for the tiles containing the gypsum/wood fiber were better than the control, especially for the tiles wherein all of the mineral fiber was replaced.

In the test for dimensional stability, there was no significant difference in the one and four hour water absorption values. As noted previously, very little water (about 2%) was removed from the tiles during wet pressing. About 78% moisture was evaporated during drying, however, this produced excessive pores in the tiles. However, during the dimensional stability test, water penetrated into the pores of the tiles resulting in high water absorption.

Example 2

Waste (scrap) gypsum wallboard was evaluated as a source of gypsum and paper fiber (co-calcined) in acoustical ceiling tiles. The waste wallboard was ground into small particles. Though some large paper pieces were present, these were broken during the calcining and the agitation required to keep the slurry in suspension during the calcining. The scrap gypsum wallboard slurry was co-calcined with additional waste

-23-

(hydropulped) newspaper, whereby the slurry consisted of 15% dry weight of paper fiber and 85% by weight of gypsum. These were co-calcined at a 15% solids consistency, and the calcination was carried out as disclosed in U.S. Patent No. 5,320,677.

After the calcination, the gypsum/paper fiber composite material was discharged from the reactor with the gypsum in its hemihydrate form. Two acoustical ceiling tiles were made by dewatering (vacuum) the slurry, after mixing with expanded perlite and corn starch, and then pressing the wet mat to remove additional excess water and to control the thickness of the tiles prior to drying. The tiles were dried at 600°F. for 30 minutes, followed by 90 minutes at 650°F.

The following tables represent the formulation and the recorded MOR strength:

TABLE 2 A

Ingredient	Tile NO. 1		Tile NO. 2	
	Wgt. (gms.)	Wgt. %	Wgt. (gms.)	Wgt. %
Gypsum (hemihydrate)	158.1	39.4	607.8	66.4
Waste Paper	85.9	21.4	167.0	18.3
Expanded Perlite	137.0	34.2	120.0	13.1
Corn Starch	20.0	5.0	20.0	2.2
Slurry Consis. (solids %)	4		6	

-24-

TABLE 2 B

<u>Tile Sample</u>	<u>Thickness</u> <u>inch</u>	<u>Density</u> <u>(lbs./ft.³)</u>	<u>MOR</u> <u>(psi)</u>
1a	0.632	7.5	68
1b	0.619	7.5	62
1c	0.623	7.4	67
1d	0.630	7.4	78
Avg.	0.626	7.45	69
2a	0.620	20.4	168
2b	0.645	21.1	179
2c	0.642	20.5	159
2d	0.643	20.2	154
Avg.	0.638	20.6	165
Control (Typical Mineral Fiber Tile)	0.62	11	65

Tile No. 1 which had a density suitable for use as an acoustical ceiling tile also had a MOR comparable to the control.

Example 3

Two ceiling tiles were made using ground scrap gypsum wallboard. There were large paper pieces in the ground wallboard. The ceiling tiles were produced by substituting the ground gypsum wallboard and additional newspaper fiber in a mineral fiber board formulation. The tiles were produced by mixing all of the ingredients for 3 minutes in an aqueous slurry (4% solids). After mixing, the slurry was formed into a wet mat, dewatered under vacuum, and wet pressed to control the thickness and to remove some excess water prior to drying. The processing was comparable to using a mineral fiber formulation except that drainage time was slightly longer. After drying,

-25-

there were still large pieces of paper in the tiles. The dried tiles were subjected to 75°F/50% relative humidity conditions for at least 24 hours prior to testing for MOR strength.

The following tables represent the formulation and the recorded MOR strength:

TABLE 3 A

<u>Ingredients</u>	<u>Weight (grams)</u>	<u>Weight %</u>
Gypsum (scrap board)	167.696	41.924
Paper Fiber (scrap board)	10.704	2.676
Newspaper Fiber (additional)	64.0	16.0
Total Paper Fiber	74.704	18.676
Expanded Perlite	120	30
Clay (CTS-1)	17.6	4.4
Starch	20	5
Flocculant (Gendriv)		0.06
Surfactant (Neodol 25-3)		0.08

TABLE 3 B

<u>Tile Sample</u>	<u>Thickness (inch)</u>	<u>Density (lbs./ft.³)</u>	<u>MOR (psi)</u>
1 a	0.578	10.2	46
1 b	0.570	10.4	55
1 c	0.565	10.4	45
1 d	0.572	10.1	43
1 e	0.590	10.4	47
Avg.	0.575	10.3	47
2 a	0.578	10.1	51
2 b	0.599	10.2	60
2 c	0.588	10.0	48
2 d	0.579	10.0	44
2 e	0.577	10.3	50
Avg.	0.584	10.1	51

-26-

This test data indicates that the MOR of these tiles (no co-calcination) was lower at higher density when compared to the same types of tiles (see Example 2) produced by co-calcining the same gypsum wallboard scrap material.

Example 4

Tests were conducted to evaluate 100% replacement of mineral wool in a ceiling tile formulation with a gypsum/cellulose fiber (co-calcined) composite material. In order to improve the cutability of the ceiling tile, the gypsum was co-calcined with fine (hydropulped) newsprint instead of wood fibers.

Gypsum and 20% by weight of shredded paper (newsprint) were calcined in accordance with the procedure disclosed in U.S. Patent No. 5,320,677. The shredded newsprint was soaked in water overnight, and then gypsum was added and mixed with the paper fiber slurry for at least 1 hour prior to calcining the slurry. After calcining, the excess water was removed (vacuum) and then the gypsum/paper fiber composite was dried to hemihydrate..

The following tables represent the formulations and the recorded MOR data:

TABLE 4 A

Ingredient	Formulation #1		Formulation #2		Formulation #3		Control	
	Wt. (gms.)	Wt. %	Wt. (gms.)	Wt. %	Wt. (gms.)	Wt. %	Wt. (gms.)	Wt. %
Gypsum (calcined)	142.3	37.2	142.3	35.4	142.3	36.3	0	
Paper Fiber (calcined)	30	7.8	30	7.5	30	7.65	0	
Newsprint	40	10.5	40	9.9	50	12.75		16.0
Expanded Perlite	150	39.2	150	37.3	150	38.2		30.0
Corn Starch	20	5.2	40	9.9	20	5.1		5.0
Mineral Fiber	0		0		0			44.6
Clay	0		0		0			4
Slurry Solids		7.8		8.1		7.4		

Standard flocculant and surfactant were used in all formulations.

17 grams of gypsum was added to the slurry water to control gypsum solubility.

-28-

TABLE 4 B

<u>Sample No.</u>	<u>Thickness</u> <u>(inch)</u>	<u>Density</u> <u>(lbs./ft.³)</u>	<u>MOR</u> <u>(psi)</u>	<u>Break Load</u> <u>(lbs.)</u>
Form. 1 a	0.637	9.5	30.2	4.08
1 b	0.630	9.2	26.8	3.55
1 c	0.636	9.2	23.5	3.17
1 d	0.639	9.3	26.7	3.63
1 e	0.682	9.7	30.4	4.71
Average	0.645	9.4	27.5	3.83
Form 2 a	0.626	9.7	37.9	4.95
2 b	0.630	9.8	35.4	4.68
2 c	0.636	9.8	35.1	4.73
2 d	0.652	10.1	43.5	6.16
Average	0.636	9.9	38.0	5.13
Form 3 a	0.627	9.8	40.9	5.36
3 b	0.621	9.6	31.1	4.00
3 c	0.619	9.5	30.1	3.85
3 d	0.625	9.6	31.9	4.16
3 e	0.653	9.9	44.4	6.31
Average	0.629	9.7	35.7	4.74
Control a	0.593	11.3	49.5	5.80
b	0.590	11.3	46.9	5.44
c	0.596	11.3	46.3	5.48
d	0.589	11.4	52.1	6.02
e	0.611	11.6	48.1	5.98
Average	0.596	11.4	48.6	5.74

-29-

After testing the samples for MOR strength, they were also tested for cutability using a wallboard knife. The control tiles (16% newsprint) cut clean, however, the gypsum/paper fiber tiles (17.4% newsprint) had very rough cuts.

Example 5

Further tests were carried out to determine the effect on tile cutability by reducing the paper fiber content in the formulation and also increasing the starch content to maintain the strength of the dry tile. It was believed that reducing the paper fiber content would adversely affect the strength. The experimental ceiling tiles were made using co-calcined gypsum and paper fiber (newsprint). After calcining an 80% gypsum and 20% newsprint slurry (15% solids), the slurry was dewatered (vacuum) and dried as a hemihydrate composite material. The hemihydrate composite was evaluated as a replacement for 100% of the mineral fiber. The shredded newsprint was soaked in water overnight and the next day it was mixed with gypsum to form the 15% solids slurry for calcining.

The following tables represent the formulations and the recorded strength data:

TABLE 5 A

Ingredients	Control #1		Formula #2		Formula #3		Formula #4	
	Wt. (gms.)	Wt. %	Wt. (gms.)	Wt. %	Wt. (gms.)	Wt. %	Wt. (gms.)	Wt. %
Mineral Fiber	178.4	44.6	0		0		0	
Expanded Perlite	120	30	150	39.8	150	39.5	150	39.8
Gypsum (calcined)	0		132.8	35.2	132.8	35.0	132.8	35.2
Paper Fiber (calcined)	0		28	7.4	28	7.4	28	7.4
Newsprint	64	16	36	9.6	29	7.6	21	5.6
Corn Starch	20	5	20	5.3	35	9.2	40	10.6
Clay	17.6	4.4	10	2.7	5	1.3	5	1.3
Slurry Solids		4.0		7.0		7.1		7.0

17 grams of gypsum was added to the slurry water to control gypsum solubility.

-31-

TABLE 5 B

<u>Sample No.</u>	<u>Thickness</u> <u>(inch)</u>	<u>Density</u> <u>(lb./ft.³)</u>	<u>Break Load</u> <u>(lbs.)</u>	<u>MOR</u> <u>(psi)</u>
Control 1 a	0.601	11.39	4.17	46.2
1 b	0.592	11.32	4.88	55.7
1 c	0.586	11.25	4.27	49.7
1 d	0.586	11.19	4.2	48.9
1 e	0.577	11.25	4.5	54.1
Average	0.588	11.28	4.4	50.9
Formula 2 a	0.515	10.58	3.65	55.0
2 b	0.521	10.55	3.27	48.2
2 c	0.525	10.58	4.02	58.3
2 d	0.541	11.02	3.65	49.9
Average	0.526	10.69	3.65	52.9
Formula 3 a	0.520	10.99	6.12	90.5
3 b	0.519	10.68	4.87	72.3
3 c	0.525	10.61	4.72	68.5
3 d	0.536	10.88	4.68	65.2
3 e	0.555	11.04	5.18	67.3
Average	0.531	10.84	5.11	72.8
Formula 4 a	0.538	10.98	5.53	76.4
4 b	0.517	10.80	4.18	62.6
4 c	0.519	10.67	4.25	63.1
4 d	0.519	10.81	4.05	60.1
4 e	0.547	11.01	4.73	63.2
Average	0.528	10.85	4.55	65.1

-32-

The ceiling tiles were also tested for wet strength by taking samples prior to oven drying. The experimental tiles with 17% and 15% total paper fiber handled very well, similar to the control. The tile with 13% paper fiber was somewhat weaker.

It was concluded that the ceiling tiles containing 15% to 17% paper fiber, 40% expanded perlite and 10% starch binder provided processing and physical properties comparable to the mineral fiber ceiling tile.

Example 6

The following formulations were used to compare using co-calcined gypsum/newsprint with a physical mixture of gypsum and newsprint without calcining:

TABLE 6 A

<u>Ingredient</u>	Control	Hemihydrate	Newsprint & <u>Gypsum</u>
	(Mineral <u>Fiber</u>)	Composite <u>(calcined)</u>	
Mineral Wool	44.6%	0	0
Expanded Perlite	30.0%	40%	40%
Tot. Paper Fiber (Newsprint)	16.0%	16%	20-22%
Gypsum	0	34%	32%
Corn Starch	5.0%	10%	7-9%
Clay	4.4%	0	0
Flocculant	0.06%	0.06	0
Surfactant	0.08%	0.08	0
Slurry Solids	4%	7%	7%

-33-

In preparing the ceiling tile mats, the surfactant (when used) was added to the desired amount of water and mixed. Then the newsprint (hydropulped) was added, followed by mixing. Then the expanded perlite and mineral wool (when used) was added with continued mixing. Finally, the clay (when used) and starch was added, with continued mixing for about 3 minutes until a homogeneous slurry was formed, after which the flocculant (when used) was added and mixing continued for another 15 seconds. In preparing the non-mineral wool ceiling tiles, the clay and mineral fiber were replaced with gypsum and newsprint.

The mat was formed by pouring the slurry into a Tappi Box where it was gently mixed, and thereafter there was gravity drainage and vacuum was applied to the wet mat to remove excess water. Then, the mat was wet pressed to the desired thickness (about 5/8 inch) in a static press, also removing additional excess water. The wet mat was tested for wet lap strength prior to drying. The mats were dried with steam at 600°F. for 30 minutes, followed by drying at 350°F. for 90 minutes.

It has been found that in the non-mineral wool formulation, the amount of paper fiber (newsprint) should be at least about 20% by weight for an acceptable mat formation. The formulation employing the co-calcined composite material did slightly increase the drainage time, especially at higher paper fiber content. There was no significant effect on drainage using the mixture of gypsum and newsprint even at levels as high as 22%.

-34-

The mat made with the hemihydrate composite material was easy to handle during processing and had wet lap strength comparable to the mineral fiber control, with both formulations containing 16% paper fiber. The composite material provided a mat in which the wet lap had good deflection during testing. After the testing, the wet lap break line was slightly hand pressed before drying, after which the wet lap line was completely healed. The mat made with a mixture of gypsum and newsprint generally had weaker wet lap strength, however, at a 20% newsprint level, it did have a wet lap strength comparable to the hemihydrate composite formulation at a 16% paper fiber content.

The weight retention in the tiles made with the hemihydrate composite was generally superior to the tiles made with a mixture of gypsum and newsprint. This indicates that there may have been loss of gypsum, as well as perlite segregation, in the mat formation using the mixture. As previously noted, both types of experimental tiles were harder to cut than the mineral fiber tile.

The densities of both types of experimental tiles were slightly higher than the control, due to the lower thickness of the mat. The lower thickness was the result of springback after pressing in the mineral fiber mat, whereas the gypsum/paper fiber mat did not spring back. The MOR strength of both types of experimental tiles was acceptable or better than the mineral fiber control tiles.

-35-

Example 7

The following formulations were used to evaluate the effect on cutability of hydropulped newsprint and gypsum (uncalcined) and the same newsprint and gypsum (calcined) as a complete replacement for mineral fiber:

TABLE 7A

Sample	Perlite		Starch		Newsprint		Gypsum	
	Grams	Wt. %	Grams	Wt. %	Grams	Wt. %	Grams	Wt. %
1	165	44	22.5	6	67.5	18	120	32
2	135	36	52.5	14	67.5	18	120	32
3	165	44	37.5	10	52.5	14	120	32
4	135	36	37.5	10	82.5	22	120	32
5	150	40	52.5	14	52.5	14	120	32
6	150	40	22.5	6	82.5	22	120	32
7	157.5	42	33.8	9	63.8	17	120	32
8	142.5	38	41.3	11	71.3	19	120	32
9	153.8	41	30	8	71.3	19	120	32
10	146.3	39	45	12	63.8	17	120	32
11	153.8	41	41.3	11	60	16	120	32
12	146.3	39	33.8	9	75	20	120	32
13	150	40	37.5	10	67.5	18	120	32

12 grams of gypsum was added to the slurry water to control gypsum solubility.

-37-

All of these formulations were formed into aqueous slurries having a 7% by weight solids content. In the case of the co-calcined gypsum/newsprint, the ratio of gypsum to newsprint was 85:15, and additional newsprint was added to provide the amount of newsprint set forth in the above formulation.

In evaluating the 13 sample tiles, the following data was recorded:

TABLE 7B

<u>Sample</u>	<u>Cutability</u> <u>Force</u>		<u>Type of Cut</u>	
	<u>Calcined</u>	<u>Uncalcined</u>	<u>Calcined</u>	<u>Uncalcined</u>
1	23.8	19.8	Very Rough	Very Rough
2	20.9	12.7	Rough	Clean
3	22.7	16.0	Very Rough	Very Rough
4	21.6	21.1	Rough	Very Rough
5	17.6	13.2	Rough	Rough
6	28.1	21.8	Very Rough	Very Rough
7	17.6	14.3	Slightly Rough	Slightly Rough
8	17.4	20.0	Slightly Rough	Slightly Rough
9	21.4	18.7	Clean	Slightly Rough
10	23.4	16.8	Slightly Rough	Clean
11	23.4	16.7	Slightly Rough	Clean
12	25.0	19.7	Rough	Rough
13	27.8	16.0	Rough	Clean

Cutability is a measure of two factors - how difficult it is to cut with a hand-held utility knife and the appearance of the cut. A two piece jig was designed to perform the cutability tests. One piece held a 3 inch by 4 inch ceiling tile sample in place and a standard utility blade was set at an

-38-

angle of 30° relative to the sample in the other piece. The cutability tests were performed on an Instron Universal Testing Machine with the unit operating in a tension mode and the crosshead speed set at 20 inches/minute. This test approximates the action of cutting a tile with a hand-held utility knife. Results are reported as the force required to cut the sample and a description of the appearance of the cut.

In comparison to the difficult to cut gypsum/newsprint formulations, all of the mineral fiber tiles had a clean cut and required an average force of about 11. As a result of the difficulty in cutting the tiles containing the co-calcined gypsum/newsprint composite or the physical mixture of gypsum and paper fiber (uncalcined), a tile formulation containing at least about 10% dry weight of mineral fiber has better cutting properties than the mineral wool-free tiles.

Example 8

A plant trial was performed using the following formulations, with the gypsum and hydropulped newsprint being physically mixed into the formulation without co-calcining:

TABLE 8A

Ingredients & Other Factors	Formulation	Formulation
	<u>A</u>	<u>B</u>
Expanded Perlite	39%	41%
Newsprint (hydropulped)	22%	20%
Gypsum	32%	32%
Starch	7%	7%
Solids Content	5.5%	5.5%
Line Speed (ft./min.)	30	30-34

-39-

The starting line speed (Formulation A) was 30 ft./min and this was increased to 34 ft./min. during the latter part of the second trial (Formulation B). The wet mats were dried with the following dryer temperature ranges after startup:

TABLE 8B

	<u>Dryer #1</u>	<u>Dryer #2</u>	<u>Dryer #3</u>	<u>Dryer #4</u>
Formulation A	790-802°F.	458-492°F.	409-471°F.	408-471°F.
Formulation B	788-821°F.	470-500°F.	419-454°F.	419-450°F.

The mats exhibited no warpage after drying, and all of the dry panels passed through the trimmers. Approximately 65,000 square feet of panels were produced.

The slurry consistency in both trials was about 5.5 weight % which appeared to be acceptable. The water did not separate from the stock when poured on a smooth surface (slump test). The slurry feed rate was maintained at approximately 400 gallons/minute during both trials. The wet mat was pressed to a thickness of about 0.610 inch prior to drying which removed some of the excess water. The final density of the dried panels was about 13 pounds/cubic foot.

Example 9

Another plant trial was performed in which 33% of the mineral fiber was replaced with gypsum and additional newsprint and a second formulation wherein all of the mineral fiber was replaced. The following formulations were used:

-40-

<u>TABLE 9A</u>		
<u>Ingredient</u>	<u>Formulation A</u>	<u>Formulation B</u>
Expanded Perlite	35%	39%
Newsprint (hydropulped)	16%	22%
Gypsum	12%	32%
Starch	10%	7%
Mineral Fiber	27%	0%

In both trials, the starting line speed was 30 ft./minute, however, due to the use of additional dilution water, the line speed was reduced to 28 ft./min. (Formulation A) and 27 ft./min. (Formulation B). The following data was recorded:

-41-

TABLE 9B

<u>Sample No. *</u>	<u>No. of Samples</u>	<u>Thickness (inch)</u>	<u>Density (lb./ft.³)</u>	<u>MOR (psi)</u>
1 & 2	6	0.622	11.0	136
3 & 4	6	0.626	14.0	223
5 & 6	6	0.639	12.0	167
7, 8 & 9	9	0.614	12.2	179
10	3	0.612	11.5	159
24 & 25	6	0.607	13.7	198
11	3	0.623	14.8	259
12	3	0.636	14.3	247
13, 14 & 15	9	0.637	13.4	223
16, 17 & 18	9	0.636	12.8	204
19 & 20	6	0.618	13.1	218
21 & 22	6	0.643	13.7	233

* Samples 1-10 were 33% mineral fiber replacement and 11-25 were 100%.

-42-

The warpage in both trials was minimal and all panels passed through the slitters. There was also minimal calcination of the gypsum in the dryers.

During the processing, the initial slurry consistency (33% replacement) was approximately 6.6% by weight of solids. Because of the high consistency, the slurry flow was not uniform and the wet mat cracked before vacuum dewatering. The slump test patty diameter was only 6.5 inches, indicating improper flow of the slurry. Addition of dilution water solved the slurry flow problem and reduced the slurry consistency to 5.4% solids. The slump test patty diameter was 9.5 inches (normal). Later in the trial, additional dilution water lowered the consistency to 4.9% solids, with no adverse effect on the mat formation.

In the 100% mineral fiber replacement trial, the initial slurry consistency was 6.3% solids. This caused some cracking in the mat formation which was resolved by adding dilution water, lowering the consistency to 5.4% solids and providing a 9.5 inch slump test patty diameter.

Example 10

A plant trial was run using the following formulation:

TABLE 10A

<u>Ingredient</u>	<u>Amount (wt.%)</u>
Expanded Perlite	43
Gypsum	32
Starch	5
Paper Fiber (newsprint)	20

-43-

The formulation consistency was about 5.5% solids and the gypsum/paper fiber were physically mixed into the slurry (without co-calcining). The newsprint was added as a slurry containing about 3% solids. The line speed was about 30 feet/minute, and the wet mat thickness was carefully maintained at about 0.6 inches using a combination of vacuum and pressing rolls.

The following data was recorded:

-44-

TABLE 10B

<u>Sample No.</u>	<u>Thickness</u> <u>(inch)</u>	<u>Density</u> <u>(lb./ft.³)</u>	<u>MOR</u> <u>(psi)</u>
1-a	0.614	15.0	162
1-b	0.617	14.9	160
1-c	0.611	15.1	162
2-a	0.614	13.1	127
2-b	0.608	13.2	132
2-c	0.607	13.2	141
3-a	0.602	13.7	146
3-b	0.602	13.6	145
3-c	0.604	13.7	146
4-a	0.607	12.9	135
4-b	0.609	12.9	137
4-c	0.610	12.9	137
5-a	0.615	13.1	124
5-b	0.605	13.2	121
5-c	0.611	13.2	128
6-a	0.623	12.4	142
6-b	0.624	12.2	141
6-c	0.624	12.3	142
7-a	0.624	13.9	152
7-b	0.621	13.9	159
7-c	0.622	13.9	153
8-a	0.626	13.9	161
8-b	0.625	13.9	157
8-c	0.623	14.0	162
9-a	0.631	13.0	140
9-b	0.624	13.2	150
9-c	0.622	13.2	144
10-a	0.616	13.0	146
10-b	0.617	13.0	145
10-c	0.622	13.1	144
11-a	0.618	15.4	162
11-b	0.612	15.6	171
11-c	0.616	15.4	168

The tiles made with this formulation did not warp and readily passed through the slitters. The dried tiles had excellent hardness compared to mineral fiber based tiles.



-45-
CLAIMS

1. A composition suitable for making acoustical tiles characterized in that it consists essentially of gypsum; cellulosic fiber; a lightweight aggregate material and a binder in which on a dry solids basis there is at least about 15% by weight of gypsum and at least 13% by weight of cellulose fiber.

2. The composition of claim 1, characterized in that the binder is starch present on a dry solids basis in an amount ranging from about 3 to about 15% by weight; the lightweight aggregate material is expanded perlite present on a dry solids basis in an amount of at least 25% by weight and the cellulose fiber is paper fiber present on a dry solids basis in an amount ranging from 13 to about 30% by weight.

3. The composition of claim 2, characterized in that the gypsum ranges from about 15 to about 45% by weight and the expanded perlite ranges from about 25 to about 60% by weight.

4. The composition of claim 1, characterized in that at least a portion of the gypsum and cellulosic fiber are in the form of a composite material which has been produced by calcining under pressure a dilute slurry of gypsum and cellulosic fiber.

5. The composition of claim 4, characterized in that the composite material is calcium sulfate alpha hemihydrate which has been co-calcined with the cellulosic fibers.



-46-

6. The composition of claim 5, characterized in that the cellulosic fibers are paper fibers.

7. The composition of claim 6, characterized in that a portion of the cellulose fibers are added to the composition as uncalcined fibers in addition to the calcined gypsum/cellulose fiber composite material.

8. The composition of claim 1, characterized in that a substantial portion of gypsum and a minor portion of the cellulose fiber are in the form of ground gypsum wallboard.

9. The composition of claim 1, characterized in that the cellulose fiber is paper and the major portion of the paper fiber is newsprint.

10. A composition suitable for making acoustical tiles characterized in that it consists essentially of mineral wool, gypsum, cellulosic fiber, a lightweight aggregate material and a binder, in which on a dry solids basis there is at least about 10% by weight of mineral wool, at least about 10% by weight of gypsum and at least 13% by weight of cellulose fiber.

11. The composition of claim 10, characterized in that the amount of mineral wool ranges from about 10% to about 30% by weight.

12. The composition of claim 10 or 11, characterized in that at least a portion of the gypsum and the cellulosic fiber are in the form of a composite material which has been produced by calcining under pressure a dilute slurry of gypsum and cellulosic fiber.

13. The composition of claim 10, 11 or 12, characterized in that a substantial portion of the gypsum



-47-

and a minor portion of the cellulose fiber are in the form of ground gypsum wallboard.

14. A acoustical tile formed with the composition of any of claims 1 to 13.