

Description

This invention concerns multi-stage polymer particles containing void space(s) therein which are useful as binding or opacifying agents in coating, impregnating and molding compositions.

Core-shell polymer particles are disclosed in US-A-4,427,836. The polymer particles of this patent are prepared by sequentially emulsion polymerizing a core monomer system comprising mon-
oethylenically unsaturated monomers, one of which has a carboxylic acid group and comprises at least 5% by weight of the core monomer system; polymerizing in the presence of the core polymer dispersion a shell monomer system which is permeable to aqueous volatile base selected from ammonia and amines; and neutralizing with ammonia or amine so as to swell said core and form particles which, when dried, contain a single void and cause opacity in compositions in which they are contained. US-A-4427836 requires that the carboxylic acid be present in the core in a polymeric form. The composition of the shell polymer is such as to be not permeable to fixed or permanent base according to said patent "so that films deposited from aqueous coating compositions comprising a volatile base-swollen core of the core/sheath polymer upon drying and resultant (at least partial) removal by volatilization of the base are not damaged by any permanent base present in the substrate coated or in solutions used later for cleaning the films." (Column 3, lines 35-41). Said patent teaches that "suitable swelling agents for acid-containing cores are ammonia, ammonium hydroxide, or a volatile lower aliphatic amine, such as trimethylamine, and triethylamine." Similarly, US-A-4468498 discloses core-shell polymers having a core of polymeric acid and being swellable by a volatile base.

US-A-4594363 discloses a process for making core-shell polymer particles similar to US-A-4427836 except that a fixed or permanent base is used to swell the particles. It also requires that the core be polymerized from at least 5% by weight of acid-functional monomer.

US-A-4469825 discloses core-shell polymers having cores which are swellable by acid.

High levels of copolymerized acid in the core polymer result in several disadvantages. One such disadvantage is that the acidic copolymers are polar and do not adsorb surfactants well, thus making them unstable and prone to coagulation or aggregation into larger particles. Another disadvantage is that the acidic core polymers have a high affinity for water. This affinity makes it difficult to encapsulate the core with the shell polymer because the core tends to remain at the polymer/water interface on the surface of the com-

posite particle.

The present invention eliminates the instability, coagulation and encapsulation problems of polymers having relatively high levels of copolymerized acid in the core. Applicants have discovered that swellable, multi-stage polymer particles can be prepared by introducing a non-polymeric carboxylic acid to an earlier stage of the particles. By introducing a non-polymeric acid to an earlier stage after polymerization of said earlier stage, (preferably after polymerization of the complete, multi-stage polymer) applicants have overcome the disadvantages of the core-shell polymers containing copolymerized acid in the core.

Accordingly the invention comprises:-
a process for manufacturing multi-stage polymer particles containing void space(s) therein, comprising the steps of

a) producing multi-stage polymer particles by sequential polymerization, which particles contain carboxylic acid functionality in at least one stage which is not the outer stage,

b) swelling said particles by contacting them with aqueous base, and

c) drying said particles,

characterized in that the carboxylic acid functionality present in said at least one stage of step a) is introduced by contacting said particles during or after polymerization of that stage with a non-polymerizable compound containing at least one carboxylic acid group.

A preferred process of the invention comprises

A) sequentially emulsion polymerizing polymer particles comprising two or more polymer stages wherein

1) each of said polymer stages is emulsion-polymerized from a monomer system comprising one or more ethylenically-unsaturated monomer(s) containing one or more $-HC=C-$ groups;

2) the outer polymer stage of said particles has a glass transition temperature of about $50^{\circ}C$ or greater;

3) at least one essentially low-acid, earlier polymer stage, other than said outer polymer stage 2), is prepared from a monomer system which contains less than about 5% by weight of monomers containing carboxylic acid functionality;

4) each polymer stage is different from any adjacent polymer stage by either about a one percent difference by weight in the amount of any ethylenically unsaturated monomer used therein or by a difference in number average molecular weight between said stage and said adjacent stage of at least about a factor of 2; and

5) the polymer stages of said particles having a Tg of about 50 °C or greater comprises at least about 60% by weight of said particles; B) contacting said polymer particles with a non-polymerizable compound containing at least one carboxylic acid group before, during or after polymerization of said outer polymer stage 2) to permit said acid-containing compound to be absorbed into said low-acid polymer stage 3); and C) swelling the resulting multi-stage polymer particles containing said absorbed acid-containing compound with water at or above the glass transition temperature of the neat polymer or glass transition temperature of the plasticized polymer of said outer polymer stage 2) by contacting said particles with base at pH sufficient to swell said polymer particles, so as to produce particles which, when dried, contain one or more void space(s) within said particles.

In the above preferred process, each of the polymer stages is sequentially emulsion polymerized from a monomer system comprising one or more ethylenically-unsaturated monomers having one or more groups of the formula $-HC=C<$. As used herein, the term "stage" refers to the polymer formed during each sequence of polymerization, with the outer or final stage being the last sequence of polymerization and earlier stages being the polymer formed during prior sequences of polymerization. Some suitable examples of ethylenically-unsaturated monomers are styrene, alpha-methylstyrene, vinyltoluene, ethylene, vinyl acetate, vinyl chloride, vinylidene chloride, acrylonitrile, acrylamide methacrylamide, acrylic acid and methacrylic acid (meth) acryloxypropionic acid, itaconic acid, aconitic acid, maleic acid or anhydride, fumaric acid, crotonic acid, monomethyl maleate, monomethyl fumarate, monomethyl itaconate, and various (C₁-C₂₀) alkyl or (C₃-C₂₀) alkenyl esters of (meth) acrylic acid. The expression (meth) acrylic acid is intended to serve as a generic expression embracing both acrylic acid and methacrylic acid; e.g., methyl (meth) acrylate, ethyl (meth) acrylate, butyl (meth) acrylate, 2-ethylhexyl (meth) acrylate, benzyl (meth) acrylate, lauryl (meth) acrylate, oleyl (meth) acrylate, palmityl (meth) acrylate, stearyl (meth) acrylate, and the like. Any of the polymer stages may optionally comprise as one component thereof a small amount of polyethylenically unsaturated monomer, such as ethylene glycol di (meth) acrylate, allyl (meth) acrylate, 1,3-butanediol di (meth) acrylate, diethylene glycol di (meth) acrylate, trimethylolpropane trimethacrylate, or divinylbenzene; the proportion thereof being in the range of about 0.1 to 20%, preferably 0.1% to about 3%, by weight based on the total monomer weight of said polymer stage.

Preferably each of the polymer stages is different from any immediately adjacent polymer stage by either about a one percent difference by weight in the amount of any ethylenically-unsaturated monomer used therein, or by a difference of at least about a factor of 2 in number average molecular weight between said stage and said adjacent stage. Thus, the polymer stages may be distinguishable by either by prescribed monomer difference or the prescribed molecular weight difference or both. Thus each or any stage would contain the prescribed amount of one or more of said ethylenically-unsaturated monomers which is not present in stages immediately adjacent to it, or said adjacent stage contains about one percent more or less of one or more monomers which is present in stages adjacent to it. Alternatively or additionally, each or any stage may have a number average molecular weight which is at least twice or less than one-half that of any adjacent stage. Adjacent polymer stage as used herein means a polymer stage which is immediately adjacent and which may be polymerized prior or subsequent to the stage referred to.

The polymer particles of this invention may contain at least one polymer stage other than the outer or final stage which is prepared from a monomer system which contains monomer(s) having carboxylic acid functionality, the amount of said monomer(s) preferably being less than about 5% by weight. Preferably, the monomer system for this low-acid polymer stage contains less than 2% of monomer(s) having carboxylic acid functionality. High levels of copolymerized carboxylic acid monomers in the earlier stages of these polymer particles have several disadvantages. One disadvantage is that the carboxylic acid copolymers are polar and do not adsorb surfactants effectively, thus, making them unstable and prone to coagulation or aggregation into undesirable larger particles. Additionally, the carboxylic acid-containing polymer stages have a high affinity for water which makes them difficult to encapsulate with other polymer stages. The present invention has overcome the above disadvantages by using little or no carboxylic acid monomer in this earlier polymer stage.

The outer or final polymer stage of the multi-stage particle may also be emulsion polymerized from a monomer system comprising one or more ethylenically-unsaturated monomer(s) containing one or more $-HC=C<$ group(s). Examples of suitable monomer for the outer polymer stage include the same monomers listed above for preparing the other polymer stages and as described in US-A-4427836. The specific monomers used and the relative proportions thereof in any outer polymer stage formed should be such that this stage is preferably permeable to bases. Similarly, any other

polymer stage which is formed subsequent to the stage or stages into which the carboxylic acid functionality is introduced or to be introduced should preferably be permeable to bases to allow the bases to diffuse through to that stage or stages in the subsequent neutralization step.

The final or outer polymer stage should desirably have a T_g of about 50°C or greater, but the T_g of the final polymer stage may be equal to, less than or greater than the T_g of the earlier polymer stages. Preferably, at least one polymer stage which is formed subsequent to the stage or stages incorporating acid functionality - such as low-acid polymer stage 3) in the preferred process - has a higher T_g than that stage. Preferably the acid-incorporating stage(s) have a T_g of 150°C or less; more preferably 90°C or less. Preferably it has a number average molecular weight of 10,000 or less. The polymer stages having a T_g of about 50°C or greater cumulatively preferably comprise at least about 60% by weight of the polymer particles.

The T_g of the polymer stages can be calculated using the Fox equation:

$$1/T_{g(A-B \text{ copolymer})} = \text{weight \% A}/T_{g(A)} + \text{weight \% B}/T_{g(B)}$$

Wherein: $T_{g(A-B \text{ copolymer})}$ is the glass transition temperature of the copolymer containing monomers A and B; and $T_{g(a)}$ and $T_{g(b)}$ the glass transition temperatures of homopolymers containing monomers A and B, respectively. Weight % A and Weight % B are the amount of monomers A and B in the final copolymer. The A-B copolymer may also represent a homopolymer. All temperatures are on the Kelvin scale.)

Glass transition temperatures for various homopolymers are available in many literature sources, including J. Brandrup and E. H. Immergut, *Polymer Handbook*, 2nd ed., John Wiley & Sons, New York, pp 139-192 (1975).

The first stage of emulsion polymerization in the process of the present invention may be the preparation of a seed polymer consisting of small dispersed polymer particles of minute size which form the nuclei on which the subsequent polymer stages are formed.

As is common to aqueous emulsion polymers, there is used a water-soluble, free-radical initiator, such as hydrogen peroxide, tert-butyl hydroperoxide, or an alkali metal (sodium, potassium or lithium) or ammonium persulfate or a mixture of such an initiator with a reducing agent (such as a sulfite; more specifically an alkali metal metabisulfite, hydrosulfite, or hyposulfite, or sodium formaldehyde sulfoxylate) to form a redox system. The amount of initiator may be from 0.01 to about 2% by weight

of the monomer charged and, in a redox system, a corresponding range (0.01 to about 2%) of reducing agent may be used. The temperature may be in the range of about 10°C to 100°C . In the case of the persulfate systems, the temperature is preferably in the range of 60°C to 90°C . In the redox system, the temperature is preferably in the range of about 30° to 70°C ., more preferably about 40° to 70°C ., most preferably in the range of about 55° to 70°C . The proportion of emulsifier may be zero, but, in the situation wherein a persulfate initiator is used, it can range up to about 5 weight percent, based on the weight of monomer charged to the first stage of polymerization. By carrying out the subsequent emulsion polymerization using a low level of emulsifier, the subsequent stages of polymer-formation deposit the most-recently formed polymer on the existing dispersed polymer particles resulting from the preceding step or stage. As a general rule, the amount of emulsifier should be kept between 20% to about 60% of the amount theoretically required to saturate the surface of the polymer particles present in the reaction mixture at any given time as described in US-A-2520959.

Any nonionic or anionic emulsifier may be used, either alone or in combination. Examples of nonionic emulsifiers include tert-octylphenoxyethylpoly(39)ethoxyethanol, dodecyloxypoly(10)ethoxyethanol, nonylphenoxyethylpoly(90)ethoxyethanol, polyethylene glycol 2000 monooleate, ethoxylated castor oil, polyoxyethylene (20) sorbitan monolaurate, sucrose monococoate, di(2-butyl)phenoxyethylpoly(20)ethoxyethanol, hydroxyethylcellulose-polybutyl acrylate graft copolymer, dimethyl silicone polyalkylene oxide graft copolymer, poly(ethylene oxide)-poly(butyl acrylate) block copolymer, block copolymers of propylene oxide and ethylene oxide, 2,4,7,9-tetramethyl-5-decyne-4,7-diol ethoxylated with 30 moles of ethylene oxide, N-polyoxyethylene(20)lauramide, N-lauryl-N-polyoxyethylene(30)amine, and poly(10)ethylene glycol dodecyl thioether. Examples of anionic emulsifiers include sodium lauryl sulfate, sodium dodecylbenzene sulfonate, potassium stearate, sodium dioctyl sulfosuccinate, sodium dodecyl-diphenyloxide disulfonate, nonylphenoxyethylpoly(10)ethoxyethyl sulfate ammonium salt, sodium styrene sulfonate, sodium dodecyl allyl sulfosuccinate, sodium or ammonium salts of phosphate esters of ethoxylated nonylphenol, sodium octoxynol-3-sulfonate, sodium cocoyl sarcosinate, sodium 1-alkyloxy-2-hydroxypropyl sulfonate, sodium alpha-olefin (C_{14} - C_{16}) sulfonate, sulfates of hydroxyalkanols, tetrasodium N-(1,2-dicarboxy ethyl)-N-octadecylsulfosuccinamate, disodium N-octadecylsulfosuccinamate, disodium alkylamido polyethoxy

sulfosuccinate, and disodium ethoxylated nonyl-phenol half ester of sulfosuccinic acid.

After the earlier polymer stage or stages are obtained, a subsequent stage or stages of emulsion polymerization is effected to form the outer or final polymer stage on the earlier polymer stages particles. This may be performed in the same reaction vessel in which formation of earlier polymer stages were accomplished or the reaction medium containing the dispersed earlier stage particles may be transferred to another reaction container. It is generally unnecessary to add emulsifier unless a poly-modal product is desired. The amount of polymer deposited to form the stages of polymer is generally such as to provide an overall size of the multistage polymer particle of about 0.07 to about 4.5 microns, preferably about 0.1 to about 3.5 microns, more preferably about 0.2 to about 2.0 microns, in unswollen condition (that is, before any neutralization to raise the pH to about 5 or higher). Preferably, the weight ratio of polymer stages having a Tg of about 50°C or greater comprises at least about 80% by weight of the complete multistage polymer particles.

In one embodiment of this invention the multistage polymer particles are optionally encapsulated by additional polymer having a Tg of about 25°C or less. Said additional polymer is prepared by emulsion polymerizing one or more monomer(s), preferably ethylenically unsaturated, in the presence of the multi-stage polymer. The same monomers as described earlier for preparing the earlier polymer stage can be used in preparing said additional polymer.

In carrying out the emulsion polymerization of the multi-stage polymer particles of this invention, reference can be made to US-A-4427836 for specific process conditions.

Before, during or after polymerization of the outer polymer stage, the polymer particles are contacted with a non-polymeric compound containing at least one carboxylic acid group for a sufficient period of time to allow the acid-containing compound to be absorbed into a previous polymer stage such as the low-acid polymer stage 3) in the preferred process. The acid-containing compound is desirably added after adjusting the polymer composition to pH 4 or less to reduce the compound's solubility in the aqueous phase and increase its solubility in the polymer. Preferably, the acid-containing compound has a solubility in water greater than 0.001% and less than about 2% at pH 5 or less and at the Tg of the final polymer stage. This solubility range is low enough to allow most of the acid-containing compound to absorb into the low-acid polymer stage, yet high enough so that it can diffuse through the aqueous phase to the polymer particles at a sufficient rate. Preferably, the

amount of acid-containing compounds which are useful for this invention include C₆-C₁₂ aliphatic monocarboxylic acids, dicarboxylic acids, and mixtures thereof. Specific examples of acid-containing compounds are benzoic acid, m-toluic acid, p-chlorobenzoic acid, o-acetoxybenzoic acid, azelaic acid, sebacic acid, octanoic acid, cyclohexanecarboxylic acid, lauric acid, and monobutyl phthalate.

The multi-stage polymer particles containing the non-polymerizable acid absorbed in one polymer stage are swollen when the particles are subjected to a base, usually at or above the Tg of the neat polymer or Tg of the plasticized polymer of said final polymer stage, which permeates said outer or final polymer stage and induces the polymer particles to swell with water. The amount of base used should adjust the pH of the polymer composition sufficiently to swell the polymer particles. Preferably the composition should be adjusted to a pH of 5.0 or greater, more preferably 6.0 or greater, and most preferably 7.0 or greater. When the water is removed by drying, the shrinkage of polymer stage contained the absorbed acid develops void space(s) within the polymer particles. Preferred examples of base are ammonia; volatile lower aliphatic amines, such as trimethylamine and triethylamine; potassium hydroxide; sodium hydroxide; lithium hydroxide; calcium hydroxide; ammonium complexes of zinc, copper, or silver; strontium hydroxide and barium hydroxide.

Preferably, the ratio of the acid-containing compound to the weight of the multi-stage polymer particles is from 1:2 to 1:50.

Preferably, the multi-stage polymer particles are further encapsulated by additional polymer having a glass transition temperature of less than 50°C, preferably less than 25°C by emulsion polymerizing one or more ethylenically unsaturated monomers containing one or more -HC=C< group(s) in the presence of said multi-stage polymer particles.

The present invention also provides a coating composition or article of manufacture comprising multi-stage polymer particles prepared by the process of the present invention.

If desired, the Tg of the neat polymer of the outer polymer stage can be lowered during the swelling step to a "plasticized Tg" with a plasticizing solvent to facilitate swelling of the polymer particles upon treatment with base. The plasticizing solvent also aids in penetration of the polymer by the base. Suitable amounts of plasticizing solvent are about 1 to about 100 parts by weight based on 100 parts by weight of polymer. Suitable solvents are any which will plasticize the final polymer stage; for example, hexanol, ethanol, 3-hydroxy-2,2,4-trimethylpentyl isobutyrate, toluene, and mix-

tures thereof.

The solvent can be added either before, after or with the addition of the base. In certain cases the monomer system itself can function as the plasticizing solvent for the polymer.

After being expanded by water to the desired extent, the usual procedure is to cool the swollen particles to a temperature below the T_g of said outer polymer stage. The water is then removed from the particles by drying at the lower temperature, resulting in the formation of microvoids within the particles. For best results, the water is removed rapidly from the polymer particles. Slow drying at high humidity may be detrimental to microvoid formation.

The multi-stage polymer particle dispersions of the present invention are useful in aqueous coating and impregnating compositions as opacifying agents in such compositions.

They are useful either as a supplement to, or replacement of, pigmentary matter and/or extenders therefor. For these purposes, the aqueous dispersions of the multi-stage polymer particles may be added directly to the coating and/or impregnating compositions. Alternatively, the multi-stage polymer particles may be isolated from the dispersions and dried to make them free-flowing in character so that they can be packaged, sold and shipped or stored before use. The dry powder thus obtained can also be used in coatings based on organic solvents provided the final polymer stage of the multi-stage polymer particles is not soluble in the organic solvent.

Besides being useful in water-based paints based on vinyl or acrylic polymer latices or aqueous solutions of vinyl or acrylic polymers (to replace all or part of opacifying pigments heretofore used, especially those of titanium dioxide), the microvoid-containing particulate polymers of the present invention may be used for similar purposes in other coating systems. These include resin-forming condensation products of thermosetting type, such as phenoplasts and aminoplasts, including urea-formaldehyde and melamine-formaldehyde, and other condensates (e.g., water-dispersible alkyd resins). In addition, polymodal heteropolymers of the present invention having a predominant proportion of the microvoid-containing large mode and a relatively minor proportion of a small mode, but also provide an adhesion-promoting action by way of the small mode.

The following examples are presented to further illustrate this invention. The examples are intended to be illustrative and are not limitative of the present invention. All parts and percentages are by weight unless otherwise indicated.

EXAMPLE I - PREPARATION OF POLY(ISOBUTYL METHACRYLATE) LOW-ACID STAGE

A 3-liter, round-bottomed flask with 4 necks was fitted with reflux condenser, paddle stirrer, thermometer and nitrogen inlet. 1500 grams of deionized water were added to the flask and stirred under a nitrogen atmosphere at 85°C. To the deionized water were added 3 grams of sodium persulfate and 40 grams of an acrylic seed latex having a 46.5% solids content and an average diameter of 95 nanometers. A monomer emulsion (140 g. of water, 6 g. of 23% sodium dodecylbenzene-sulfonic acid, 360 g. of isobutyl methacrylate and 40 g. of n-dodecyl mercaptan) was added over 2 hours along with 3 g. of sodium persulfate dissolved in 80 g. of water. The resultant latex was held at 85°C for 30 minutes, cooled and filtered. The resultant low-acid stage polymer latex had an 18.7% solid content, average particle diameter of 260 nanometers and a number average molecular weight of 2000 as measured by gel permeation chromatography.

EXAMPLE II - PREPARATION OF MULTI-STAGE POLYMER PARTICLES WITH BENZOIC ACID ABSORBED IN LOW-ACID STAGE BEFORE POLYMERIZATION OF FINAL STAGE

To 470 g. of deionized water, stirred under nitrogen in a flask equipped as in Example 1, was added 50 g. of the low-acid stage polymer latex from Example 1 along with 20 g. of benzoic acid. The mixture in the flask was heated to 80°C and then 1.2 g. of sodium persulfate dissolved in 10 g. of water was added. A monomer mixture of 46 g. of butyl methacrylate, 66.7 g. of methyl methacrylate and 2.3 g. of methacrylic acid was added slowly over a one-hour period to give a second polymer stage. After a 10-minute hold at 80°C to complete the polymerization, 115 g. of styrene were added over a one-hour period to form the final polymer stage. The 20 g. of 28% aqueous ammonia were added to swell the particles and the temperature was raised to 85°C for 30 minutes followed by cooling and filtration. The final latex product had a 28.9% solids content and pH of 9.4. Diluted latex was dried on a microscope slide and immersed in hydrocarbon oil ($n_D = 1.51$) and examined with an optical microscope at 900X. A single air void can be seen inside each particle as a dark circle. The swollen multi-stage polymer latex was incorporated into a film to measure the Kubelka-Munk scattering coefficient (S/mil) as described in US-A-4427836 S/mil of the resultant film was 0.12.

EXAMPLE III - PREPARATION OF MULTI-STAGE POLYMER PARTICLES WITH BENZOIC ACID ABSORBED IN LOW-ACID STAGE DURING POLYMERIZATION OF FINAL STAGE

Multi-stage polymer particles were prepared following the procedures of Example II, except that the benzoic acid was mixed with styrene and this mixture was added to the flask over a one-hour period. The resulting latex product had a 28.3% solids content, pH of 9.9 and S/mil of 0.16. Voids were noticeable in the dry polymer particles through examination under a microscope.

EXAMPLE IV - PREPARATION OF MULTI-STAGE POLYMER PARTICLES WITH BENZOIC ACID ABSORBED IN LOW-ACID STAGE AFTER POLYMERIZATION OF FINAL STAGE

Multi-stage polymer particles were prepared following the procedures of Example II, except that the benzoic acid was added to the flask immediately after addition of the styrene was complete. When the ammonia was added, the latex became thick and 100 grams of water were added. The resulting latex product had a 23.3% solids content, pH of 9.7 and S/mil of 0.13. Examination of dry polymer particles under a microscope showed a single void in each particle.

EXAMPLE V - PREPARATION OF MULTI-STAGE POLYMER PARTICLES HAVING BUTYL METHACRYLATE EARLIER STAGE AND AZELAIC ACID ABSORBED THEREIN

A low molecular weight, earlier stage latex was prepared following the procedures of Example I, except that 50 grams of an acrylic latex seed (41.3% solids, average diameter 57 nm) were used and isobutyl methacrylate was replaced with an equal amount of butyl methacrylate. The resulting latex has an 18.8% solids content and an average particle diameter of 150 nm.

This earlier stage latex was then used to prepare multi-stage polymer particles following the procedures of Example II, except that the amount of initial deionized water was increased to 700 grams and benzoic acid was replaced with azelaic acid. The resulting multi-stage latex product had a 23.8% solids content, pH of 9.4, average particle diameter of 470 nm, and S/mil of 0.20.

EXAMPLE VI

A high molecular weight earlier stage latex was prepared following the procedures of Example V, except that the n-dodecyl mercaptan was excluded. The resulting latex had a 17.4% solids content and

an average particle diameter of 156 nm.

This earlier stage latex was then used to prepare multi-stage polymer following the procedures of Example V. The resulting multi-stage latex product had a 24.4% solids content, pH of 9.2, average particle diameter of 482 nm, and S/mil of 0.15.

EXAMPLE VII - PREPARATION OF MULTI-STAGE POLYMER PARTICLES HAVING BUTYL ACRYLATE EARLIER STAGE

Multi-stage polymer particles were prepared following the procedures of Example VI, except that butyl methacrylate in the earlier stage was replaced with an equal amount of butyl acrylate. The resulting multi-stage latex product had a 23.4% solids content, pH of 9.4, average particle diameter of 503 nm and S/mil of 0.11.

EXAMPLE VIII - PREPARATION OF MULTI-STAGE POLYMER PARTICLES HAVING METHYL METHACRYLATE EARLIER STAGE

Multi-stage polymer particles were prepared following the procedures of Example V, except that butyl methacrylate in the earlier stage was replaced with an equal amount of methyl methacrylate. The resulting multi-stage latex product had a 24.0% solids content, pH of 9.3, average particle diameter of 477 nm, and S/mil of 0.08. The earlier polymer stage had an estimated Tg of 75°C.

EXAMPLE IX - PREPARATION OF MULTI-STAGE POLYMER PARTICLES HAVING STYRENE EARLIER STAGE

Multi-stage polymer particles were prepared following the procedures of Example V, except that butyl methacrylate in the earlier stage was replaced with an equal amount of styrene. The resulting multi-stage latex product had a 24.1% solids content, pH of 9.3, average particle diameter of 389 nm, and S/mil of 0.11. The earlier polymer stage had a measured Tg of 70°C by differential scanning calorimetry.

Claims

1. A process for manufacturing multi-stage polymer particles containing void space(s) therein, comprising the steps of
 - a) producing multi-stage polymer particles by sequential polymerization, which particles contain carboxylic acid functionality in at least one stage which is not the outer stage,

EXAMPLE III - PREPARATION OF MULTI-STAGE POLYMER PARTICLES WITH BENZOIC ACID ABSORBED IN LOW-ACID STAGE DURING POLYMERIZATION OF FINAL STAGE

Multi-stage polymer particles were prepared following the procedures of Example II, except that the benzoic acid was mixed with styrene and this mixture was added to the flask over a one-hour period. The resulting latex product had a 28.3% solids content, pH of 9.9 and S/mil of 0.16. Voids were noticeable in the dry polymer particles through examination under a microscope.

EXAMPLE IV - PREPARATION OF MULTI-STAGE POLYMER PARTICLES WITH BENZOIC ACID ABSORBED IN LOW-ACID STAGE AFTER POLYMERIZATION OF FINAL STAGE

Multi-stage polymer particles were prepared following the procedures of Example II, except that the benzoic acid was added to the flask immediately after addition of the styrene was complete. When the ammonia was added, the latex became thick and 100 grams of water were added. The resulting latex product had a 23.3% solids content, pH of 9.7 and S/mil of 0.13. Examination of dry polymer particles under a microscope showed a single void in each particle.

EXAMPLE V - PREPARATION OF MULTI-STAGE POLYMER PARTICLES HAVING BUTYL METHACRYLATE EARLIER STAGE AND AZELAIC ACID ABSORBED THEREIN

A low molecular weight, earlier stage latex was prepared following the procedures of Example I, except that 50 grams of an acrylic latex seed (41.3% solids, average diameter 57 nm) were used and isobutyl methacrylate was replaced with an equal amount of butyl methacrylate. The resulting latex has an 18.8% solids content and an average particle diameter of 150 nm.

This earlier stage latex was then used to prepare multi-stage polymer particles following the procedures of Example II, except that the amount of initial deionized water was increased to 700 grams and benzoic acid was replaced with azelaic acid. The resulting multi-stage latex product had a 23.8% solids content, pH of 9.4, average particle diameter of 470 nm, and S/mil of 0.20.

EXAMPLE VI

A high molecular weight earlier stage latex was prepared following the procedures of Example V, except that the n-dodecyl mercaptan was excluded. The resulting latex had a 17.4% solids content and

an average particle diameter of 156 nm.

This earlier stage latex was then used to prepare multi-stage polymer following the procedures of Example V. The resulting multi-stage latex product had a 24.4% solids content, pH of 9.2, average particle diameter of 482 nm, and S/mil of 0.15.

EXAMPLE VII - PREPARATION OF MULTI-STAGE POLYMER PARTICLES HAVING BUTYL ACRYLATE EARLIER STAGE

Multi-stage polymer particles were prepared following the procedures of Example VI, except that butyl methacrylate in the earlier stage was replaced with an equal amount of butyl acrylate. The resulting multi-stage latex product had a 23.4% solids content, pH of 9.4, average particle diameter of 503 nm and S/mil of 0.11.

EXAMPLE VIII - PREPARATION OF MULTI-STAGE POLYMER PARTICLES HAVING METHYL METHACRYLATE EARLIER STAGE

Multi-stage polymer particles were prepared following the procedures of Example V, except that butyl methacrylate in the earlier stage was replaced with an equal amount of methyl methacrylate. The resulting multi-stage latex product had a 24.0% solids content, pH of 9.3, average particle diameter of 477 nm, and S/mil of 0.08. The earlier polymer stage had an estimated Tg of 75°C.

EXAMPLE IX - PREPARATION OF MULTI-STAGE POLYMER PARTICLES HAVING STYRENE EARLIER STAGE

Multi-stage polymer particles were prepared following the procedures of Example V, except that butyl methacrylate in the earlier stage was replaced with an equal amount of styrene. The resulting multi-stage latex product had a 24.1% solids content, pH of 9.3, average particle diameter of 389 nm, and S/mil of 0.11. The earlier polymer stage had a measured Tg of 70°C by differential scanning calorimetry.

Claims

1. A process for manufacturing multi-stage polymer particles containing void space(s) therein, comprising the steps of
 - a) producing multi-stage polymer particles by sequential polymerization, which particles contain carboxylic acid functionality in at least one stage which is not the outer stage,





- b) swelling said particles by contacting them with aqueous base, and
- c) drying said particles,

characterized in that the carboxylic acid functionality present in said at least one stage of step a) is introduced by contacting said particles during or after polymerization of that stage with a non-polymerizable compound containing at least one carboxylic acid group.

2. A process for manufacturing multi-stage polymer particles according to claim 1, comprising

A) sequentially emulsion polymerizing polymer particles comprising two or more polymer stages wherein

- 1) each of said polymer stages is emulsion-polymerized from a monomer system comprising one or more ethylenically-unsaturated monomer(s) containing one or more -HC=C< groups;
- 2) the outer polymer stage of said particles has a glass transition temperature of about 50°C or greater;
- 3) at least one essentially low-acid, earlier polymer stage, other than said outer polymer stage 2), is prepared from a monomer system which contains less than about 5% by weight of monomers containing carboxylic acid functionality;
- 4) each polymer stage is different from any adjacent polymer stage by either about a one percent difference by weight in the amount of any ethylenically unsaturated monomer used therein or by a difference in number average molecular weight between said stage and said adjacent stage of at least about a factor of 2; and

5) the polymer stages of said particles having a T_g of about 50°C or greater comprises at least about 60% by weight of said particles;

B) contacting said polymer particles with a non-polymerizable compound containing at least one carboxylic acid group before, during or after polymerization of said outer polymer stage 2) to permit said acid-containing compound to be absorbed into said low-acid polymer stage 3); and

C) swelling the resulting multi-stage polymer particles containing said absorbed acid-containing compound with water at or above the glass transition temperature of the neat polymer or glass transition temperature of the plasticized polymer of said outer polymer stage 2) by contacting said particles with base at pH sufficient to swell said polymer particles, so as to produce particles

which, when dried, contain one or more void space(s) within said particles.

- 3. A process according to claim 1 wherein the polymer stage into which the carboxylic acid-containing compound is introduced has a glass transition temperature of 150°C or less, preferably 90°C or less, and/or a number average molecular weight of 10,000 or less.
- 4. A process according to claim 1 or 2 wherein the pH of the polymer particles is adjusted to pH 4 before contacting them with the non-polymerizable acid-containing compound.
- 5. A process according to any preceding claim wherein said non-polymerizable acid-containing compound has a solubility in water greater than 0.001 % and less than 2 % at pH 5 or less and at the T_g of the final polymer stage, and the ratio of the acid-containing compound to the weight of said multi-stage polymer particles is from 1 : 2 to 1 : 50.
- 6. A process according to any preceding claim wherein the non-polymerizable acid-containing compound is a $\text{C}_6\text{-C}_{12}$ aliphatic mono- or dicarboxylic acid.
- 7. A process according to claim 6 wherein the non-polymerizable acid-containing compound is benzoic acid, m-toluic acid, p-chlorobenzoic acid, o-acetoxybenzoic acid, azelaic acid, sebacic acid, octanoic acid, cyclohexanecarboxylic acid, lauric acid, or monobutyl phthalate.
- 8. A process according to any preceding claim wherein said multi-stage polymer particles are further encapsulated by additional polymer having a glass transition temperature of less than 50°C , preferably less than 25°C by emulsion polymerizing one or more ethylenically unsaturated monomers containing one or more -HC=C< group(s) in the presence of said multi-stage polymer particles.
- 9. A process according to any preceding claim wherein said base is ammonia; potassium hydroxide; sodium hydroxide; lithium hydroxide; calcium hydroxide; strontium hydroxide; barium hydroxide; volatile lower aliphatic amines; or ammonium complexes of zinc, copper or silver.
- 10. A process according to any preceding claim wherein the monomer(s) forming said multi-stage polymer particles are styrene, alpha-



methylestyren, vinyltoluene, ethylene, vinyl acetate, vinyl chloride, vinylidene chloride, acrylonitrile, acrylamide, methacrylamide, acrylic acid, methacrylic acid, acryloxypropionic acid, methacryloxypropionic acid, itaconic acid, aconitic acid, maleic acid, maleic anhydride, fumaric acid, crotonic acid, monomethyl maleate, monomethyl fumarate, monomethyl itaconate, or (C₁-C₂₀) alkyl or (C₈-C₂₀) alkenyl esters of acrylic or methacrylic acid.

11. A coating composition or article of manufacture comprising multi-stage polymer particles prepared by the process of any preceding claim.

Patentansprüche

1. Verfahren zur Herstellung von Mehrstufen-Polymerpartikeln mit ein oder mehr Hohlräumen darin, bei dem

- Mehrfach-Polymerpartikel durch Sequenzpolymerisation hergestellt werden, wobei die Partikel eine Carbonsäure-Funktionalität in mindestens einer Stufe enthalten, die nicht die äußere Stufe ist,
- die Partikel durch Inkontaktbringen mit einer wässrigen Base gequollen werden, und
- die Partikel getrocknet werden,

dadurch gekennzeichnet, daß die in mindestens einer Stufe von Schritt (a) vorliegende Carbonsäure-Funktionalität eingebracht wird, indem die Partikel während oder nach Polymerisation der Stufe mit einer nicht-polymerisierbaren Verbindung in Kontakt gebracht werden, die mindestens einen Carbonsäurerest enthält.

2. Verfahren zur Herstellung von Mehrstufen-Polymerpartikeln nach Anspruch 1, bei dem

(A) Polymerpartikel, umfassend zwei oder mehr Polymerstufen, sequentiell Emulsionspolymerisiert werden, worin

- jede der Polymerstufen aus einem Monomersystem Emulsionspolymerisiert wird, das ein oder mehr ethylenisch-ungesättigte Monomere mit ein oder mehr -HC=C<Resten umfaßt,
- die äußere Polymerstufe der Partikel eine Glasumwandlungstemperatur von etwa 50 °C oder höher hat,
- mindestens eine frühere, im wesentlichen Niedrigsäure-Polymerstufe anders als die äußere Polymerstufe (2) aus einem Monomersystem hergestellt wird, das weniger als etwa 5 Gew.-% von Monomeren mit einer Carbonsäure-Funktionalität enthält,
- jede Polymerstufe von einer benachbarten Polymerstufe entweder durch

etwa 1 Gew.-% Unterschied in der Menge eines darin verwendeten ethylenisch-ungesättigten Monomers oder durch einen Unterschied in dem Zahlendurchschnittsmolekulargewicht zwischen der Stufe und der benachbarten Stufe von mindestens einem Faktor von etwa 2 unterschiedlich ist, und

(5) die Polymerstufen der Partikel mit einem Tg von etwa 50 °C oder höher mindestens etwa 60 Gew.-%

der Partikel umfassen,

(B) die Polymerpartikel mit einer nicht-polymerisierbaren, mindestens einen Carbonsäure-Rest enthaltenden Verbindung vor, während oder nach Polymerisation der äußeren Polymerstufe (2) in Kontakt gebracht werden, wodurch die Säure-enthaltende Verbindung von der Niedrigsäure-Polymerstufe (3) absorbiert wird, und

(C) die erhaltenen Mehrstufen-Polymerpartikel, die die absorbierte Säure-enthaltende Verbindung enthalten, mit Wasser bei oder oberhalb der Glasumwandlungstemperatur des reinen Polymers oder bei oder oberhalb der Glasumwandlungstemperatur des plastifizierten Polymers der äußeren Polymerstufe (2) durch Inkontaktbringen der Partikel mit einer Base bei einem pH gequollen werden, der zur Quellung der Polymerpartikel ausreichend ist, wodurch Partikel hergestellt werden, die nach Trocknung ein oder mehr Hohlräume innerhalb der Partikel enthalten.

3. Verfahren nach Anspruch 1, worin die Polymerstufe, in die die Carbonsäure-enthaltende Verbindung eingebracht wird, eine Glasumwandlungstemperatur von 150 °C oder weniger, vorzugsweise 90 °C oder weniger, und/oder ein Zahlendurchschnittsmolekulargewicht von 10000 oder weniger hat.

4. Verfahren nach Anspruch 1 oder 2, worin der pH der Polymerpartikel auf pH 4 vor Inkontaktbringen dieser mit der nicht-polymerisierbaren, Säure-enthaltenden Verbindung eingestellt wird.

5. Verfahren nach einem der vorhergehenden Ansprüche, worin die nicht-polymerisierbare, Säure-enthaltende Verbindung eine Löslichkeit in Wasser größer als 0,001 % und weniger als 2 % bei pH 5 oder weniger und bei dem Tg der End-Polymerstufe hat, und das Verhältnis der Säure-enthaltenden Verbindung zu dem Gewicht der Mehrstufen-Polymerpartikel 1:2 bis 1:50 beträgt.



6. Verfahren nach einem der vorhergehenden Ansprüche, worin die nicht-polymerisierbare, Säure-enthaltende Verbindung eine C_6 - C_{12} aliphatische Mono- oder Dicarbonsäure ist. 5
7. Verfahren nach Anspruch 6, worin die nicht-polymerisierbare, Säure-enthaltende Verbindung Benzoesäure, m-Toluyisäure, p-Chlorbenzoesäure, o-Acetoxybenzoesäure, Azelainsäure, Sebacinsäure, Octylsäure, Cyclohexancarbonsäure, Laurinsäure oder Monobutylphthalat ist. 10
8. Verfahren nach einem der vorhergehenden Ansprüche, worin die Mehrstufen-Polymerpartikel ferner durch ein zusätzliches Polymer mit einer Glasumwandlungstemperatur von weniger als 50°C , vorzugsweise weniger als 25°C , durch Emulsionspolymerisation eines oder mehrerer ethylenisch-ungesättigter Monomere mit ein oder mehr $-\text{HC}=\text{C}-$ Resten in Gegenwart der Mehrstufen-Polymerpartikel verkapselt werden. 15
9. Verfahren nach einem der vorhergehenden Ansprüche, worin die Base Ammoniak, Kaliumhydroxid, Natriumhydroxid, Lithiumhydroxid, Calciumhydroxid, Strontiumhydroxid, Bariumhydroxid, flüchtige nieder-aliphatische Amine oder Ammoniumkomplexe von Zink, Kupfer oder Silber sind. 25
10. Verfahren nach einem der vorhergehenden Ansprüche, worin das (die) Mehrstufen-Polymerpartikel ausbildende(n) Monomer(e) Styrol, α -Methylstyrol, Vinyltoluol, Ethylen, Vinylacetat, Vinylchlorid, Vinylidenchlorid, Acrylonitril, Acrylamid, Methacrylamid, Acrylsäure, Methacrylsäure, Acryloxypropionsäure, Methacryloxypropionsäure, Itaconsäure, Aconitsäure, Maleinsäure, Maleinsäureanhydrid, Fumarsäure, Crotonsäure, Monomethylmaleat, Monomethylfumarat, Monomethylitaconat oder (C_1-C_{20}) Alkyl oder (C_3-C_{20}) Alkenylester von Acrylsäure oder Methacrylsäure ist (sind). 30
11. Beschichtungszusammensetzung oder Herstellungsartikel, umfassend Mehrstufen-Polymerpartikel, hergestellt durch das Verfahren nach einem der vorhergehenden Ansprüche. 45

Revendications

1. Procédé pour fabriquer des particules polymères à plusieurs stades contenant un ou plusieurs espaces creux, et comprenant les étapes consistant : 55

- a) à produire des particules polymères à plusieurs stades par polymérisation séquentielle, ces particules contenant une fonctionnalité acide carboxylique dans au moins un stade qui n'est pas le stade extérieur,
- b) à faire gonfler lesdites particules en les mettant en contact avec une base aqueuse, et
- c) à sécher lesdites particules,

caractérisé en ce que la fonctionnalité acide carboxylique présente dans ledit au moins un stade de l'étape a) est introduite par mise en contact desdites particules, pendant ou après la polymérisation du stade considéré, avec un composé non polymérisable contenant au moins un groupe acide carboxylique.

2. Procédé pour fabriquer des particules polymères à plusieurs stades selon la revendication 1, qui consiste :

A) à polymériser par polymérisation séquentielle en émulsion des particules polymères comprenant au moins deux stades polymères, où

- 1) chacun desdits stades polymères polymérisés par polymérisation en émulsion à partir d'un système de monomères comprenant un ou plusieurs monomères à insaturation éthylénique contenant un ou plusieurs groupes $-\text{HC}=\text{C}-$;
- 2) le stade polymère extérieur desdites particules a une température de transition vitreuse d'environ 50°C ou plus ;
- 3) au moins un stade polymère antérieur, essentiellement à faible teneur en acide, et autre que ledit stade polymère extérieur 2), est préparé à partir d'un système de monomères qui contient moins d'environ 5 % en poids de monomères contenant une fonctionnalité acide carboxylique ;

4) chaque stade polymère est différent de tout stade polymère immédiatement contigu, cette différence étant d'environ 1 % en poids pour ce qui est de la quantité de tout monomère à insaturation éthylénique qui y est utilisé, ou encore la différence, pour ce qui est de la masse moléculaire moyenne en nombre entre ledit stade et ledit stade immédiatement contigu, correspond au moins à un facteur égal à 2 ; et

5) les stades polymères desdites particules ayant une T_g d'environ 50°C ou plus comptent pour au moins environ 60 % en poids desdites particules ;

B) à mettre en contact lesdites particules polymères avec un composé non polymérisable

sable contenant au moins un groupe acide carboxylique, avant, pendant ou après la polymérisation dudit stade polymère extérieur 2), pour permettre audit composé contenant un acide d'être absorbé par ledit stade polymère 3) à faible teneur en acide ; et

C) à faire gonfler les particules polymères obtenues, à plusieurs stades, contenant ledit composé absorbé, contenant un acide, avec de l'eau à la température de transition vitreuse du polymère non additivé ou au-dessus de cette température, ou à la température de transition vitreuse du polymère plastifié dudit stade polymère extérieur 2), ou au-delà de cette température, par mise en contact desdites particules avec une base à un pH suffisant pour faire gonfler lesdites particules polymères, de façon à produire des particules qui, après séchage, contiennent un ou plusieurs espaces creux à l'intérieur desdites particules.

3. Procédé selon la revendication 1, dans lequel le stade polymère dans lequel est introduit le composé contenant un acide carboxylique à une température de transition vitreuse de 150 °C ou moins, de préférence de 90 °C ou moins, et/ou une masse moléculaire moyenne en nombre de 10 000 ou moins.

4. Procédé selon la revendication 1 ou 2, dans lequel le pH des particules polymères est ajusté à pH 4 avant leur mise en contact avec le composé non polymérisable contenant un acide.

5. Procédé selon l'une quelconque des revendications précédentes, dans lequel ledit composé non polymérisable contenant un acide a une solubilité dans l'eau supérieure à 0,001 % et inférieure à 2 % à pH 5 ou moins et à la Tg du stade polymère final, le rapport du composé contenant un acide à la masse desdites particules polymères à plusieurs stades étant de 1:2 à 1:50.

6. Procédé selon l'une quelconque des revendications précédentes, dans lequel le composé non polymérisable contenant un acide est un acide mono- ou dicarboxylique aliphatique en C₆-C₁₂.

7. Procédé selon la revendication 6, dans lequel le composé non polymérisable contenant un acide est l'acide benzoïque, l'acide métatoluïque, l'acide parachlorobenzoïque, l'acide orthoacétoxybenzoïque, l'acide azélaïque, l'acide

sébacique, l'acide octanoïque, l'acide cyclohexanecarboxylique, l'acide laurique ou le phthalate de monobutyle.

8. Procédé selon l'une quelconque des revendications précédentes, dans lequel lesdites particules à plusieurs stades sont en outre encapsulées par un polymère supplémentaire ayant une température de transition vitreuse inférieure à 50 °C et de préférence inférieure à 25 °C, par polymérisation en émulsion d'un ou plusieurs monomères à insaturation éthylénique contenant un ou plusieurs groupes -HC=C<, en présence desdites particules polymères à plusieurs stades.

9. Procédé selon l'une quelconque des revendications précédentes, dans lequel ladite base est l'ammoniac ; l'hydroxyde de potassium ; l'hydroxyde de sodium ; l'hydroxyde de lithium ; l'hydroxyde de calcium ; l'hydroxyde de strontium ; l'hydroxyde de baryum ; les amines aliphatiques inférieures volatiles ; ou les complexes d'ammonium du zinc, du cuivre ou de l'argent.

10. Procédé selon l'une quelconque des revendications précédentes, dans lequel le ou les monomères formant lesdites particules polymères à plusieurs stades sont le styrène, l'alpha-méthylstyrène, le vinyltoluène, l'éthylène, l'acétate de vinyle, le chlorure de vinyle, le chlorure de vinylidène, l'acétonitrile, l'acrylamide, le méthacrylamide, l'acide acrylique, l'acide méthacrylique, l'acide acryloxypropionique, l'acide méthacryloxypropionique, l'acide itaconique, l'acide aconitique, l'acide maléique, l'anhydride maléique, l'acide fumarique, l'acide crotonique, le maléate de monométhyle, le fumarate de monométhyle, l'itaconate de monométhyle, ou encore les esters alkyliques en C₁-C₂₀ ou alcényliques en C₃-C₂₀ de l'acide acrylique ou de l'acide méthacrylique.

11. Composition de revêtement ou article fabriqué comprenant des particules polymères à plusieurs stades préparées par le procédé selon l'une quelconque des revendications précédentes.

