

IMPROVED METHOD AND APPARATUS FOR SHAPING THERMOPLASTIC TUBES

This invention concerns tubes made of thermoplastic material and provides an improved method and apparatus for forming such tubes into
5 required shapes or configurations. As used herein, the term "tube" includes hoses, pipes and similar conduits, whether of single or multi-layer construction.

Tubes of plastics material are used in a wide number of applications and are commonly used in the automotive field as pipe connections for
10 vapour, vent, hydraulic, fuel, coolant or oil lines. In such applications, the tube is often required to be of a specific shape or configuration.

Previously, such shapes have been obtained by special inserts positioned within the tube to conform the tube to the required shape followed by a heating or curing stage to set the required shape following which the
15 insert is removed.

The use of such inserts has been considered essential to prevent the tube wall collapsing during shaping and this has restricted the shapes which can be produced. In particular, multiple bends cannot easily be obtained because of the complexity of the insert and the difficulty of removing the
20 insert.

It is an object of the present invention to provide an improved method and apparatus for shaping thermoplastics tubes which overcomes the aforementioned disadvantages.

According to a first aspect of the invention, we provide a method of
25 forming a bend in a tube of thermoplastic material comprising externally supporting the tube on at least one former to pre-form a bend corresponding substantially to a required bend configuration, locally heating the tube at the region of the bend by controlled emission of infra-red radiation from a remote infra-red source spaced from the former and from the tube so that
30 the thermoplastics material becomes sufficiently plastic to conform to the required bend configuration whilst holding the tube stationary on the former(s), cooling the tube to set the thermoplastics material and retain the required bend configuration whilst holding the tube stationary on the former(s), and removing the tube from the former(s) with the bend formed
35 therein.

By the invented method, the shaping of the selected tube is carried out by controlled infra-red heating whilst the tube is supported externally.

We have found that infra-red heating of the thermoplastic material whilst supporting the tube externally can be effected without collapsing the tube wall.

As a result, the problems of internally supporting the tube by special inserts as used in the prior art methods are avoided entirely.

Furthermore, by the invented method, the tube can be formed into complex shapes including multiple bends using one or more former(s) to support the tube externally.

Advantageously, the emission of infra-red radiation is controlled to provide a pulsed or intermittent emission.

In this way, a dwell time is provided between successive emissions of infra-red radiation allowing heat transfer of absorbed energy around the tube by conduction thereby ensuring uniform heating of the tube. As a result, over-heating and melting of the thermoplastics material is avoided.

Additionally or alternatively, the emission of infra-red radiation may be controlled by varying the power and/or intensity of the infra-red radiation.

Preferably, the emission of infra-red radiation is controlled to provide peak power at short wavelengths, preferably in the range 0.7 to 2.0 microns and more preferably at one micron.

As will be appreciated, the emission of infra-red radiation has to be controlled in accordance with the mass of thermoplastic material in the tube and the thermal characteristics of the tube dependent upon its diameter and wall thickness and the rate of heat transfer throughout the mass of the tube.

The emission of the infra-red radiation may be arranged to heat locally the tube simultaneously at a plurality of bend regions spaced apart along the length of the tube for conforming the tube to a multiple bend configuration.

Conveniently, cooling of the shaped tube to set the thermoplastics material in the required configuration is effected by applying a cooling medium externally and/or internally of the tube.

For example, the tube may be cooled by passing cool or ambient air over the exterior of the tube and/or through the interior of the tube.

Preferably, a source of blown air is used so that cooling is completed rapidly.

Other cooling fluids may be used in place of or in addition to air. For example a liquid coolant could be passed through the interior of the tube whilst subjecting the exterior of the tube to air or liquid cooling, for example by blowing air or spraying water over the exterior of the tube.

5 The desired configuration of the tube may be the final form as required for intended use of the tube or it may be an intermediate configuration. Where the configuration is an intermediate one, then further forming of the tube may take place by repeating the forming steps using a further specially shaped former(s) for supporting the tube externally in the
10 required configuration.

 According to a second aspect of the invention, we provide apparatus for forming a bend in a tube of thermoplastic material comprising former means for externally supporting the tube to pre-form a bend corresponding substantially to a required bend configuration, a remote source of infra-red
15 radiation spaced from the former means for local contactless heating of the tube at the bend region by controlled emission of infra-red radiation to soften the thermoplastics material for conformation to the required bend configuration whilst holding the tube stationary on the former means, and a source of cooling fluid for cooling the tube to set the thermoplastics material
20 and retain the required bend configuration whilst holding the tube stationary on the former means.

 In use of the apparatus to carry out the invented method, the selected length of tube is secured and held on the former means so as to conform to the required configuration. The tube is then subjected to the controlled
25 emission of infra-red radiation from the infra-red source for limited heating of the thermoplastic material sufficient to cause deformation of the material without permitting the material to reach a plastic stage in which the tubular walls melt to collapse inwardly. Finally, the tube is set in the required configuration by cooling the thermoplastic material.

30 Preferably, the infra-red radiation source is adapted for pulsed or intermittent operation providing a dwell time for thermal transfer of absorbed energy around the tube. As a result, substantially uniform heating of the material of the tube is achieved without reaching a near melting stage in which the tube wall would collapse.

35 Advantageously, pulsed or intermittent operation of the source is provided by control means programmable for timed operation of the source.

Alternatively or additionally, the control means may be responsive to thermal sensing devices located adjacent to the former means for controlling operation of the infra-red radiation source.

Preferably, the former means provides a guide surface for supporting
5 the tube in the required configuration.

Conveniently, the guide surface has a groove in which the tube is received when held in the required configuration.

The groove assists in preventing collapse of the tube wall for the controlled heating of the tube by the infra-red radiation.

10 Advantageously, the groove provides a seating complementary to the external profile of the tube and the depth of the groove is preferably at least $1/3$ the outer diameter (OD) of the tube. More preferably, the depth of the groove is at least $1/2$ the outer diameter and most preferably is in the range $3/5$ to $4/5$ the outer diameter of the tube.

15 Preferably, the former means is made of transparent material, for example polycarbonate or glass, that is substantially unaffected by the infra-red radiation employed for heating the tube.

Where the required configuration is a simple bend, the former means may comprise a member having an annular guide surface, for example a
20 wheel or cylinder.

For large or complex bends, the former means may comprise a member having a guide surface of special profile to conform to the required shape. Alternatively, the former means may comprise a plurality of members arranged such that the respective guide surfaces define the
25 required shape.

Advantageously, the former means is arranged to produce a bend having a radius slightly less than the required configuration to allow for relaxation (spring back) of the thermoplastic material on removal of the tube from the former.

30 Where the required configuration has multiple bends, a separate former may be provided for each bend and the formers arranged to allow the tube to be located in the required configuration for simultaneous formation of each bend.

In one preferred arrangement, the former means comprises a plurality
35 of formers mounted on a common support base and the length of tube is stretched over one or more of the formers defining the required

configuration with one or both ends of the tube being clamped or otherwise secured to resiliently bias the tube into supporting engagement with the former(s).

5 Advantageously, each former is detachably mounted on the base. In this way, a worn former can be removed for repair or replacement.

Additionally or alternatively, each former is preferably adjustably mounted for varying its position relative to the other formers.

10 As a result, by replacing one or more formers with different formers and/or by adjusting the position of one or more formers, the former means can be adapted to produce tubes having a range of configurations.

Preferably, the source of infra-red radiation comprises at least one lamp, for example a tungsten halogen lamp, arranged to direct emitted radiation towards the tube supported on the former means.

15 Conveniently, the source comprises an array of lamps angularly disposed around the former means so as to direct the emitted radiation towards the outer surface of the tube supported on the former.

20 Preferably, the or each lamp has an external reflector for directing accurately the emitted radiation towards the associated former. For example, each lamp may be positioned in the focal plane of the associated reflector.

Advantageously, the or each lamp is adjustably mounted for varying the position of the lamp relative to the former means. In this way, adjustment of the lamp(s) may be combined with adjustment of the former means to adapt the apparatus to different required configurations of tube.

25 In one construction, the or each lamp is slidably mounted on a pivotal support arm for selective adjustment of the spacing and/or angular position of the lamp relative to the former means.

30 The source of cooling fluid may be arranged to apply cooling fluid to the exterior and/or interior of the tube to achieve rapid cooling and quenching of the tube. Air is the preferred cooling fluid but other cooling fluids may be used.

The source of cooling fluid may be connected to at least one outlet such as a nozzle arranged to direct the cooling fluid over the exterior of the tube.

Preferably, a plurality of outlets are provided to direct cooling fluid over the tube supported on the former and the outlets are conveniently connected to a common source of cooling fluid.

Advantageously, the or each outlet is/are adjustable relative to the former means for accurately directing the cooling fluid towards the tube supported on the former means and/or for adapting the source of cooling fluid to different required configurations of tube. For example, the or each outlet may be rotatably and/or slidably mounted for altering the angular position and/or spacing relative to the former means.

Alternatively or additionally, the source of cooling fluid may be connected to one end of the tube to pass the cooling fluid through the interior of the tube.

Preferably, the source of cooling fluid is operable by control means programmable for timed operation of the source.

The invention will now be described in more detail by way of example only with reference to the accompanying drawings wherein:-

FIGURE 1 is a side view of a thermoplastics tube produced by the method and apparatus according to the invention;

FIGURE 2 is a side view of a jig for holding the tube in the required configuration;

FIGURE 3 is a front view of apparatus according to the invention showing the tube of Figure 1 supported on the jig of Figure 2;

FIGURE 4 is a plan view of the apparatus shown in figure 3 showing the jig at a load station (full lines) and at a heating and cooling station (broken lines);

FIGURE 5 is a section on the line 5-5 of Figure 4;

FIGURE 6 is a section on the line 6-6 of Figure 3;

FIGURE 7 shows an alternative former adapted for side heating; and

FIGURE 8 shows another former adapted for producing complex shapes.

Referring first to Figure 1, a thermoplastics tube 1 of polyamide is shown having offset parallel end portions 1a, 1b terminating in respective 180° bends 1c, 1d and an inclined centre portion 1e connected to the end portions 1a, 1b by respective 135° bends 1f, 1g.

The tube is of circular cross-section having an outer diameter of 8mm and a wall thickness of 1.00mm. The tube 1 is produced by cutting the

required length from an extrusion of the appropriate cross-section and heat forming the bends 1c, 1d, 1f, 1g by irradiation with infra-red radiation while holding the tube 1 in the required configuration followed by air cooling to set the tube 1 in the required configuration.

5 Figure 2 shows a jig 3 for holding the tube 1 in the required configuration for heat forming of the bends 1c, 1d, 1f, 1g. The jig 3 is mounted on a rectangular base or table 4 and comprises end formers 5,6 for each of the 180° bends 1c, 1d and intermediate formers 7,8 for each of the 135° bends 1f, 1g mounted by respective brackets 9,10,11,12.

10 Each former 5,6,7,8 has a curved guide surface 5a, 6a, 7a, 8a against which the tube 1 is resiliently held by securing releasably the ends of the tube 1 to respective tubular spigots 9a, 10a on the end former brackets 9,10. One spigot 9a is connected by a pipe 13 to an air supply (not shown) for passing cooling air through the tube 1.

15 Each curved guide surface 5a, 6a, 7a, 8a is of smaller radius than the bend 1c, 1d, 1f, 1g formed thereby to allow for relaxation (spring back) of the thermoplastics material on removal of the tube 1 from the jig 3.

Each former 5,6,7,8 has a peripheral groove 14,15,16,17 of which the base forms the guide surface 5a, 6a, 7a, 8a and the opposed sides support the tube 1 and prevent the tube wall collapsing inwards during heat forming of the bend. Each groove 14,15,16,17 has a depth of 5 to 6mm.

20 Each end former 5,6 and one intermediate former 7 is of annular shape, for example a wheel or disc. The other intermediate former 8 is of triangular shape additionally arranged to support the centre portion 1e of the tube 1 in a groove 18 along one side edge 8b.

25 The formers 5,6,7,8 are made of transparent material such as polycarbonate or glass that does not interfere with heating of the tube 1 and is not degraded to any significant extent by the short wave infra-red radiation employed for heating forming of the bends 1c, 1d, 1f, 1g.

30 The formers are releasably secured to the associated mounting bracket 9,10,11,12 for detaching the former for repair or replacement of a worn former or fitment of a different former.

In a modification, not shown, the formers 5,6,7,8 are adjustable relative to each other for supporting a length of tube in any selected one of a range of different configurations as may be required for alternative end uses of the shaped tube.

Referring now to Figures 3 to 6, apparatus is shown for heat forming the bends 1c, 1d, 1f, 1g of the tube 1 supported on the jig 3. The apparatus comprises an open-ended rectangular framework 19 having a top wall 20 and an intermediate wall 21 extending horizontally between opposed parallel side walls 22, 23 to define a longitudinally extending processing chamber 24.

The intermediate wall 21 has guides 25 on the upper surface 21a for slidably supporting the base 4 of the jig 3 for advancing movement of the jig 3 through the processing chamber 24.

As best shown in figure 4, the apparatus is arranged to receive the jig 3 at one end of the processing chamber 24 from a loading station 25 at which the tube 1 is located on the formers 5, 6, 7, 8 and to transfer the jig 3 to a heating/cooling station 26 at which the tube 1 is subjected to controlled heating by infra-red radiation followed by air cooling to set the tube 1 in the required configuration. The jig 3 is transferred from the heating/cooling station 26 to an unloading station 27 at the opposite end of the processing chamber 24 for removal of the formed tube 1. The drive for advancing the jig 3 may be a belt, chain or other suitable means (not shown) that is actuated by a control unit 28 mounted on side wall 22 externally of the chamber 24.

As best shown in Figure 5, a plurality of infra-red emitters 29 are mounted within the chamber 24 on the top, side and intermediate walls 20, 21, 22, 23 for irradiating the tube 1 supported on the formers 5, 6, 7, 8 at the heating/cooling station 26.

In this embodiment there are three emitters 29 for each end former 4, 5, 6 and two emitters for the intermediate formers 7, 8. The number and position of the emitters 29 may, however, be altered as desired to suit the size and shape of tube 1.

Each emitter 29 comprises an infra-red lamp 30 and associated reflector 31 for directing the infra-red radiation towards the tube 1. Suitable emitters 29 are tungsten-halogen lamps made from a tube of transparent quartz having a length and diameter chosen to meet the requirements of a given application.

The lamps 30 extend lengthwise of the processing chamber 24 parallel to the direction of movement of the jig 3 and transversely to the length of the tube 1 supported on the formers 5, 6, 7, 8.

Each lamp 30 is mounted at opposed ends by a pair of support arms 32. Each arm 32 is pivotally connected at one end to the adjacent framework wall 20,21,22,23 and is formed with a slot 32a at the other end in which the lamp 30 is slidably mounted for lengthwise adjustment along the arm 32. In this way, the angular position and/or spacing of each lamp 30 relative to the adjacent former 5,6,7,8 can be selected for best results.

In particular, the lamps 30 can be arranged to direct the infra-red radiation for localised heating of the tube 1 along its length to form the bends 1c,1d,1f,1g. Also, the position of the lamps 30 can be adapted for different tube configurations and the apparatus is not limited to the tube configuration shown in Figure 1.

Infra-red radiation emitted by the lamps 30 is directed towards and absorbed by the outer facing surface of the tube 1.

In this embodiment, the base 4 is shown mounting one jig 3 only for simplicity. It will be understood, however, that the length of the lamps 30 may be selected to allow a plurality of jigs 3 each comprising one or more formers to be mounted on the base 4 for heat forming several tubes 1 simultaneously. Alternatively, the jig 3 may be constructed and arranged to mount a plurality of tubes 1 in spaced relationship. For example, the formers may be of elongate form with the tubes 1 spaced apart along the length thereof.

The lamps 30 are controlled for pulsed or intermittent operation by the control unit 28 which is programmable for setting the duration of and interval between successive pulses or bursts of infra-red radiation.

In this way, uniform heating of the tube 1 around its circumference is obtained by allowing thermal conduction through the mass of the tube between each pulse or burst.

The timed operation of the lamps 30 is determined by a number of factors including the diameter of the tube 1, thickness of the tube wall, the thermoplastics material of the tube, the number, size and power of the lamps 30 etc., and is set to ensure that the tube 1 is only heated to a sufficient degree to soften the thermoplastics material for conforming to the required configuration and over-heating sufficient to melt the thermoplastic material and cause the tube wall to collapse is avoided.

On completion of the heating stage to form the bends 1c,1d,1f,1g, the tube 1 is rapidly cooled to set the required configuration.

The cooling is effected by blowing air or other suitable cooling gas onto the exterior of the tube 1 and/or through the interior of the tube 1 for a pre-set period of time controlled by programming the control unit.

5 For external cooling, a plurality of outlet nozzles 33 connected by supply pipes 34 to a source of blown air are arranged to direct the air onto the surface of the tube supported on the formers 5,6,7,8. For internal cooling, spigot 9a is connected by pipe 13 to the source of blown air for passing air through the interior of the tube 1.

10 In this embodiment, two nozzles 33 are associated with each end former 5,6 and one nozzle 33 with both of the intermediate formers 7,8. The number and arrangement of the outlet nozzles 33 may, however, be altered as desired to suit different tube configurations.

15 Additionally, the nozzles 33 may be adjustably mounted for altering the angular position and spacing relative to the adjacent former 5,6,7,8 to suit different tube configurations.

The nozzles 33 are positioned between the lamps 30 and the cooling stage is performed after the heating stage with the jig 3 at the same station 26 within the chamber 24. In this way rapid cooling of the tube 1 can be effected immediately following heating of the tube 1 sufficient to conform to the required shape.

For certain applications, however, it may be preferable to effect the heating and cooling stages at separate stations spaced apart lengthwise of the chamber 24. Such arrangement, reduces cycle times and may be employed advantageously for automated mass production.

25 As will be understood, the invented method and apparatus has many advantages over the prior art methods and apparatus for shaping thermoplastics tube. In particular, the use of internal formers is eliminated by the use of controlled infra-red heating whilst externally supporting the tube in the required configuration.

30 The emission of the infra-red radiation and the subsequent setting of the required configuration is controlled through a programmable control unit and can be set up to suit a wide range of different materials and requirements.

35 The apparatus can be adapted for different tube configurations by appropriate selection of the number, size, shape and arrangement of the formers to produce a jig for the required configuration.

A plurality of bases or tables 4 may be assembled to form an endless loop with adjoining edges of adjacent bases 4 articulated to each other by suitable pivot connections. In this way, empty jigs are automatically returned from the unloading station to the loading station for continuous operation under the control of the control unit. Such arrangement is particularly, suitable for mass production of tubes having a particular configuration.

Alternatively, the base or table 4 can be arranged and adapted for reciprocating movement of the jig between a common loading and unloading station and the processing station under the control of the control unit. This arrangement is more compact and may be preferred for short production runs where only a limited number of specially shaped tubes may be required.

The invention is not limited to the embodiment above-described, for example, the formers may be adapted for heating the tube 101 by infra-red radiation sources 130 arranged on one or both sides by the provision of suitable cut-outs 114a in the sides of the locating groove 114 as shown in Figure 7. These cut-outs should not exceed the depth of the groove and are preferably not more than half the depth of the groove.

Complex bend shapes may be produced by a former comprising a plurality of members 205 arranged to define the required profile with an array of infra-red heat sources 230 for heating the tube 201 as shown in Figure 8. Each of the members 205 may be mounted so as to be adjustable relative to the others for producing a range of different profiles.

Although the invention has been described with reference to a thermoplastics tube of polyamide, it will be understood that the invented method and apparatus has application to a wide range of thermoplastics materials including polyurethane, polyethylene, polypropylene, polyvinylchloride, polyacetal and other elastomers and copolymers of these thermoplastics.

Furthermore, tubes produced by the invented method and apparatus may comprise a single thermoplastics material or combinations of two or more different thermoplastics materials. For example, a tube wall comprising layers of different thermoplastics material may be obtained by co-extrusion of the thermoplastics material.

Additionally, tubes produced by the invented method and apparatus may be unreinforced as in the above embodiment or include a reinforcement.

For example, a reinforcement layer such as a metallic or non-metallic sleeve may be incorporated in the tube wall during manufacture. Alternatively, reinforcement material, such as glass or carbon fibre may be incorporated into the thermoplastics material forming the tube wall.

- 5 Tube produced by the invented method and apparatus may be used for a wide range of diverse applications including fuel pipes, fuel vapour pipes, ventilation pipes, drain pipes, vacuum pipes, coolant hoses and hydraulic hoses. Each of these applications may require specific grades of thermoplastics materials to be used with or without reinforcement as
- 10 mentioned above and/or end fittings at one or both ends to connect the tube for its intended use.



Claims:

1. A method of forming a bend in a tube of thermoplastic material comprises externally supporting the tube on at least one former to pre-form a bend corresponding substantially to a required bend configuration, locally
5 heating the tube at the region of the bend by controlled emission of Infra-red radiation from a remote infra-red source spaced from the former and from the tube so that the thermoplastics material becomes sufficiently plastic to conform to the required bend configuration whilst holding the tube stationary on the former(s), cooling the tube to set the thermoplastics material and
10 retain the required bend configuration whilst holding the tube stationary on the former(s), and removing the tube from the former(s) with the bend formed therein.
2. A method according to Claim 1 wherein the emission of infra-red radiation is controlled to provide a pulsed or intermittent emission.
- 15 3. A method according to Claim 1 or Claim 2 wherein the emission of infra-red radiation is controlled to vary the power and/or intensity.
4. A method according to any one of the preceding Claims wherein short wavelength infra-red radiation is used for heating the tube.
5. A method according to Claim 4 wherein short wavelength infra-red
20 radiation having peak energy emission in the range 0.7 to 2.0 microns is used for heating the tube.
6. A method according to Claim 5 wherein the peak energy emission of the infra-red radiation is at a wavelength of approximately 1 micron.
7. A method according to any one of the preceding Claims wherein local
25 heating of the tube is effected simultaneously at a plurality of bend regions spaced apart along the length of the tube for conforming the tube to a multiple bend configuration.
8. A method according to any one of the preceding Claims wherein cooling of the tube to set the thermoplastics material is effected by
30 directing cooling fluid over the exterior of the tube and/or through the interior of the tube.
9. A method according to Claim 8 wherein the tube is air cooled.
10. A method according to any one of the preceding Claims wherein the former(s) has a radius of curvature slightly less than the radius of curvature
35 of the required bend.



11. A method according to any one of the preceding Claims wherein the former(s) is made of transparent material.
12. A method of forming a bend in a thermoplastic tube comprises externally supporting the tube on a former to pre-form a bend corresponding substantially to a required bend configuration, softening the thermoplastic material for conformation to the required bend configuration whilst holding the tube stationary on the former by local contactless heating of the tube at the bend by pulsed or intermittent emission of short wave infra-red radiation, cooling the tube to set the thermoplastics material and retain the required bend configuration whilst holding the tube stationary on the former, and removing the tube from the former with the bend formed therein.
13. A method according to Claim 12 wherein local contactless heating of the tube is effected simultaneously at a plurality of bend regions spaced apart along the length of the tube for conforming the tube to a multiple bend configuration.
14. A method of forming a bend in a tube of thermoplastic material substantially as hereinbefore described.
15. Apparatus for forming a bend in a tube of thermoplastic material comprises former means for externally supporting the tube to pre-form a bend corresponding substantially to a required bend configuration, a remote source of infra-red radiation spaced from the former means for local contactless heating of the tube at the bend region by controlled emission of infra-red radiation to soften the thermoplastics material for conformation to the required bend configuration whilst holding the tube stationary on the former means, and a source of cooling fluid for cooling the tube to set the thermoplastics material and retain the required bend configuration whilst holding the tube stationary on the former means.
16. Apparatus according to Claim 15 wherein the infra-red radiation source is adapted for pulsed or intermittent emission of infra-red radiation.
17. Apparatus according to Claim 15 or Claim 16 including control means for controlling operation of the infra-red radiation source.
18. Apparatus according to Claim 17 wherein the control means is programmable for timed operation of the infra-red radiation source.
19. Apparatus according to any one of Claims 15 to 18 wherein the control means is responsive to thermal sensing devices located adjacent to the former means for controlling operation of the infra-red radiation source.

20. Apparatus according to any one of Claims 15 to 19 wherein the former means provides a guide surface for supporting the tube to form the required bend configuration.
21. Apparatus according to Claim 20 wherein guide surface comprise a
5 groove providing a seating complementary to the external profile of the tube
22. Apparatus according to Claim 21 wherein the depth of the groove is in the range $\frac{3}{5}$ to $\frac{4}{5}$ the outer diameter of the tube.
23. Apparatus according to Claim 21 or Claim 22 wherein the seating is provided with one or more cut-outs in the groove sidewall(s).
- 10 24. Apparatus according to Claim 23 wherein the or each cut-out has a depth not more than $\frac{1}{2}$ the depth of the groove.
25. Apparatus according to any one of Claims 15 to 24 wherein the former means is transparent.
26. Apparatus according to any one of Claims 15 to 25 wherein the former
15 means has a radius of curvature slightly less than the radius of the required bend.
27. Apparatus according to any one of Claims 15 to 26 wherein the former means is adapted for conforming the tube to any desired bend configuration.
28. Apparatus according to Claim 27 wherein the former means comprises
20 a plurality of adjustable and/or interchangeable formers.
29. Apparatus according to any one of Claims 15 to 28 wherein the former means is arranged for movement relative to the heating means and cooling means.
30. Apparatus according to Claim 29 wherein the former means is
25 positioned on a support base arranged for reciprocating movement between a loading/unloading station and a processing station.
31. Apparatus according to Claim 29 wherein the former means is positioned on a support base arranged for movement in an endless loop between a loading station, a processing station and an unloading station.
- 30 32. Apparatus according to any one of Claims 15 to 31 wherein the source of infra-red radiation comprises at least one lamp.
33. Apparatus according to Claim 32 wherein the source of infra-red radiation comprises an array of lamps angularly disposed around the former means.



34. Apparatus according to Claim 32 or Claim 33 wherein the or each lamp has an associated external reflector for directing the infra-red radiation towards the former means.
- 5 35. Apparatus according to Claim 34 wherein the or each lamp is positioned in the focal plane of the associated external reflector.
36. Apparatus according to any one of Claims 32 to 35 wherein the or each lamp is adjustably mounted for varying the position thereof relative to the former means.
- 10 37. Apparatus according to Claim 36 wherein the or each lamp is adjustable to vary the distance from and/or angular position relative to the former means.
38. Apparatus according to Claim 37 wherein the or each lamp is slidably mounted on pivotal support means for selective adjustment of the spacing and/or angular position of the lamp relative to the former means.
- 15 39. Apparatus according to any one of Claims 15 to 38 wherein the source of cooling fluid is adapted for directing cooling fluid over the exterior and/or through the interior of the tube.
40. Apparatus according to Claim 39 wherein the source of cooling fluid is connected to at least one outlet arrangement to direct cooling fluid over the exterior of the tube.
- 20 41. Apparatus according to Claim 40 comprising a plurality of outlets arranged to direct cooling fluid over the exterior of the tube.
42. Apparatus according to Claim 40 or Claim 41 wherein the or each outlet is adjustable to vary the distance from and/or angular position relative to the former means.
- 25 43. Apparatus according to any one of Claims 39 to 42 wherein the source of cooling fluid is connected to a spigot for one end of the tube to pass cooling fluid through the interior of the tube.
44. Apparatus according to any one of Claims 39 to 43 including control means for controlling operation of the cooling fluid source.
- 30 45. Apparatus according to Claim 44 wherein the control means is programmable for timed operation of the cooling fluid source.
46. Apparatus for forming a bend in a thermoplastic tube comprises former means for externally supporting a thermoplastic tube to pre-form a bend corresponding substantially to a required configuration, a remote source of infra-red radiation spaced from the former means for local
- 35



- contactless heating of the pre-formed bend by intermittent or pulsed emission of infra-red radiation to soften the thermoplastics material for conformation to the required bend configuration whilst holding the tube stationary on the former means, and a source of cooling fluid for cooling the
- 5 tube to set the thermoplastics material and retain the required bend configuration whilst holding the tube stationary on the former means.
47. Apparatus according to Claim 46 including means for controlling the duration of and interval between successive pulses or bursts of infra-red radiation.
- 10 48. Apparatus for forming a bend in a tube of thermoplastic material substantially as hereinbefore described with reference to the accompanying drawings.
49. A thermoplastic tube having a bend formed to a required configuration by the method according to any one of Claims 1 to 14.
- 15 50. A thermoplastic tube having a bend formed to a required configuration by the apparatus according to any one of Claims 15 to 48.
-