

18 OCT 2006

- 1 -

Polycarbonates and copolycarbonates of reduced water uptake and improved flowability, their preparation and use

The present invention provides polycarbonates and
5 copolycarbonates of reduced water uptake and improved
flowability, processes for their preparation and their use
for the production of particular products and the products
obtainable therefrom. The invention furthermore provides
new bisphenols and processes for their preparation and
10 their use.

Aromatic polycarbonates belong to the group of industrial
thermoplastics. They are distinguished by the combination
of the technologically important properties of
15 transparency, heat resistance and toughness.

To obtain high molecular weight polycarbonates by the phase
boundary process, the alkali metal salts of bisphenols are
reacted with phosgene in the two-phase mixture. The
20 molecular weight can be controlled by the amount of
monophenols, such as e.g. phenol or tert-butylphenol.
Practically exclusively linear polymers are formed in these
reactions. This can be demonstrated by end group analysis.
Branched polycarbonates are also obtained in this reaction
25 by the controlled use of so-called branching agents, as a
rule polyhydroxylated compounds.

For the preparation of polycarbonates by the phase boundary
process, reference may be made by way of example to H.
30 Schnell, Chemistry and Physics of Polycarbonates, Polymer
Reviews, vol. 9, Interscience Publishers, New York 1964 p.
33 et seq. and to Polymer Reviews, vol. 10, "Condensation
Polymers by Interfacial and Solution Methods", Paul W.

18 OCT 2006


- 2 -

Morgan, Interscience Publishers, New York 1965, chap. VIII, p. 325.

For the preparation of polycarbonates by the melt
5 transesterification process, the bisphenols are reacted with diaryl carbonates, usually diphenyl carbonate, in the presence of catalysts, such as alkali metal salts or ammonium or phosphonium compounds, in the melt.
The melt transesterification process is described, for
10 example, in the Encyclopedia of Polymer Science, vol. 10 (1969), Chemistry and Physics of Polycarbonates, Polymer Reviews, H. Schnell, vol. 9, John Wiley and Sons, Inc. (1964) and DE-C 10 31 512.

15 However, the polycarbonates and copolycarbonates already described in the prior art are unsatisfactory due to their water uptake and the limited dimensional stability thereby caused, or have the disadvantage that when used as data
20 carrier materials they can be of limited or non-optimum suitability at reading wavelengths in the blue or blue-green range.


There was therefore the object of providing polycarbonates and copolycarbonates and processes for their preparation
25 which avoid these disadvantages. This object is achieved, surprisingly, by the use of the bisphenol according to the invention, of the general formula (1)



in which

- R1 and R2 represent hydrogen or linear or branched C1-C10 alkyl, preferably hydrogen or linear or branched C1-C6 alkyl, particularly preferably hydrogen or linear or branched C1-C4 alkyl, very particularly preferably hydrogen and C1-alkyl,
- R3 represents hydrogen or linear or branched C1-C10 alkyl, preferably linear or branched C1-C10 alkyl, preferably linear or branched C1-C6 alkyl, particularly preferably linear or branched C1-C4 alkyl, very particularly preferably C1-alkyl,
- R4 to R12 represent hydrogen or linear or branched C1-C10 alkyl, preferably hydrogen or linear or branched C1-C6 alkyl, particularly preferably hydrogen or linear or branched C1-C4 alkyl, very particularly preferably hydrogen and C1-alkyl and
- n and m independently of one another represent an integer from 0 to 10, preferably from 1 to 8, particularly preferably from 1 to 6, very particularly preferably 2 to 4.

The bisphenol according to the invention is particularly preferably described by the general formula (2)



in which


5

R^{13} to R^{22} represents hydrogen or linear or branched C1-C4 alkyl and

n represents an integer from 1 to 6.

10

The structure described by the formula (3) is very particularly preferred.




15 Surprisingly, it has also been found in this context that the melt viscosity of the polycarbonates obtained has lower values than the prior art (at an otherwise comparable molecular weight) both at low and at higher shear rates. This is of importance in particular for the production of

20 relatively injection-moulded components, such as e.g. automobile screens. As a result, easier filling of the


moulds with the usual injection moulding machines is possible.

These bisphenols according to the invention can be prepared from phenol derivatives and ketones in an acid-catalysed reaction.

The synthesis of the bisphenols according to the invention is preferably carried out as a condensation reaction of corresponding phenols of the formula A and B



wherein R1 and R2 have the abovementioned meanings, individually or in a mixture, preferably individually, with alkyl-substituted ketones of the formula C



wherein

R3 to R12 have the abovementioned meanings, optionally but not necessarily in the presence of a sulfur-containing compound, preferably with the aid of an acid catalyst, particularly preferably an acid ion exchanger or hydrochloric acid, at temperatures preferably of between 0 and 100°C with a stoichiometric ratio of

18 OCT 2006

- 6 -

phenol derivative to ketone derivative of 15 : 1 to
2 : 1.

The phenols of the formulae A and B are known or can be
5 prepared by processes known from the literature, for
example by Friedel-Crafts alkylation (Organikum, Organisch-
chemisches Grundpraktikum, corrected reprint of the 20th
edition, Wiley-VCH, Weinheim, p. 355, 1999). Very many
phenols are also commercially obtainable (suppliers e.g.
10 Aldrich, Fluka, Acros etc.).

The ketones of the formula C are also known or can be
prepared by processes known from the literature, for
example by oxidation of the corresponding alcohols (in this
15 context see also: Cesare Ferri, Reaktionen der organischen
Synthese, Technische und präparative Herstellungs- und
Umwandlungsverfahren, Georg Thieme Verlag Stuttgart, p. 407
et seq., 1978). Very many ketones are also commercially
obtainable (suppliers e.g. Aldrich, Fluka, Acros, Alfa,
20 Avocado etc.).

The very particularly preferred compound 4-(2,2,6-
trimethylcyclohexyl)-2-butanone of the formula C can be
obtained commercially, for example, from Avocado, from Alfa
25 (a Johnson Matthey company, Karlsruhe, Germany),
ChemSampCo, Inc. Trenton, NJ, USA or from Pfaltz & Bauer,
Inc. Waterbury, CT, USA.


The synthesis is described, for example, in L.A. Fowley et
30 al., Tetrahedron Lett., 34(19), 3075, 1993 or in Helv.
Chim. Acta, 76(5), 2070, 1993.

The condensation is very particularly preferably carried out with hydrochloric acid as the acid catalyst at temperatures of between 0 and 60°C with a stoichiometric ratio of phenol' derivative to ketone derivative of 10 to 1, a mercaptan or thiocarboxylic acid compound (e.g. dodecylmercaptan, mercaptopropionic acid or thioacetic acid) preferably being present as the sulfur-containing compound, preferably only in about 0.01 to 25%, based on the ketone compound. The hydrochloric acid is very particularly preferably passed in as HCl gas.


The condensation can be carried out in bulk or in solution. Inert solvents, such as, for example, chlorinated hydrocarbons, such as methylene chloride or dichloroethane, or toluene, xylenes or chlorobenzenes, are employed here.

The reaction is particularly preferably carried out in bulk with an excess of phenol.

The present invention also provides polycarbonates and copolycarbonates which have been prepared using the bisphenols according to the invention, and the corresponding preparation processes. The polycarbonates and copolycarbonates which have been prepared using the bisphenols according to the invention and contain the structural units -O-D-O- derived from the compounds of the formulae 1 to 3 are represented by way of example, but not exclusively, by the general formulae (4a) and (4b)




4a



4b

wherein the radical O-E-O represents any desired
 diphenolate radicals, in which -E-, independently of one
 another, is an aromatic radical having 6 to 40 C atoms
 5 which can contain one or more aromatic nuclei or fused
 aromatic nuclei optionally containing heteroatoms and is
 optionally substituted by C1-C12-alkyl radicals or halogen
 and can contain aliphatic radicals, cycloaliphatic
 radicals, aromatic nuclei or heteroatoms as bridge members,
 10 and in which k represents an integer between 1 and 1,000,
 preferably between 1 and 800, particularly preferably
 between 1 and 600 and very particularly preferably between
 1 and 500 and especially preferably between 1 and 300, and
 m represents a fraction z/k and n represents a fraction (k-
 15 z)/k, wherein z represents numbers between 1 and k.



Preferred diphenolate units of the copolycarbonates
 according to the invention are derived from general
 structures of the formula (5),

20

in which R23 and R24 independently of one another represent
 H, linear or branched C1-C18 alkyl or alkoxy radicals,

halogen, such as Cl or Br, or an optionally substituted aryl or aralkyl radical, preferably H or linear or branched C1-C12 alkyl, particularly preferably H or C1-C8 alkyl radicals and very particularly preferably H or methyl,

5

R3 and R4 represent linear or branched C1-C10-alkyl and

X represents a single bond, -SO2-, -CO-, -O-, -S-, a C1- to C6-alkylene, C2- to C5-alkylidene or C5- to C6-

10 cycloalkylidene radical, which can be substituted by C1- to C6-alkyl, preferably methyl or ethyl radicals, or a C6- to C12-arylene radical, which can optionally be fused with further aromatic rings containing heteroatoms, and

15 o represents an integer between 1 and 1,000, preferably between 1 and 800, particularly preferably between 1 and 600 and very particularly preferably between 1 and 500 and especially preferably between 1 and 300, and p represents a fraction z/o and q represents a fraction $(o-z)/o$, wherein z
20 represents numbers between 1 and o and

n and m have the above mentioned meaning.

The diphenolate radicals O-E-O in formula (4b) and the
25 general diphenolate radicals in formula (5) are particularly preferably derived from the suitable diphenols also mentioned in the following.

Examples which may be mentioned of the diphenols on which,
30 in addition to the bisphenols according to the invention, the general formulae (4) and (5) are based are hydroquinone, resorcinol, dihydroxybiphenyls, bis-(hydroxyphenyl)-alkanes, bis-(hydroxyphenyl)-cycloalkanes,

18 OCT 2006

- 10 -

bis-(hydroxyphenyl) sulfides, bis-(hydroxyphenyl) ethers, bis-(hydroxyphenyl) ketones, bis-(hydroxyphenyl) sulfones, bis-(hydroxyphenyl)-sulfoxides, α,α' -bis-(hydroxyphenyl)-diisopropylbenzenes and nucleus-alkylated and nucleus-halogenated compounds thereof, and also α,ω -bis-(hydroxyphenyl)-polysiloxanes.

Preferred diphenols are, for example, 4,4'-dihydroxybiphenyl (DOD), 4,4'-dihydroxybiphenyl ether (DOD ether), 2,2-bis-(4-hydroxyphenyl)-propane (bisphenol A), 1,1-bis-(4-hydroxyphenyl)-3,3,5-trimethylcyclohexane (bisphenol TMC), 1,1-bis-(4-hydroxyphenyl)-cyclohexane, 2,4-bis-(4-hydroxyphenyl)-2-methylbutane, 1,1-bis-(4-hydroxyphenyl)-1-phenylethane, 1,1-bis-[2-(4-hydroxyphenyl)-2-propyl]-benzene, 1,3-bis-[2-(4-hydroxyphenyl)-2-propyl]-benzene (bisphenol M), 2,2-bis-(3-methyl-4-hydroxyphenyl)-propane, 2,2-bis-(3-chloro-4-hydroxyphenyl)-propane, bis-(3,5-dimethyl-4-hydroxyphenyl)-methane, 2,2-bis-(3,5-dimethyl-4-hydroxyphenyl)-propane, bis-(3,5-dimethyl-4-hydroxyphenyl) sulfone, 2,4-bis-(3,5-dimethyl-4-hydroxyphenyl)-2-methylbutane, 2,2-bis-(3,5-dichloro-4-hydroxyphenyl)-propane and 2,2-bis-(3,5-dibromo-4-hydroxyphenyl)-propane.

Particularly preferred diphenols are, for example, 2,2-bis-(4-hydroxyphenyl)-propane (bisphenol A), 4,4'-dihydroxybiphenyl (DOD), 4,4'-dihydroxybiphenyl ether (DOD ether), 1,3-bis-[2-(4-hydroxyphenyl)-2-propyl]-benzene (bisphenol M), 2,2-bis-(3,5-dimethyl-4-hydroxyphenyl)-propane, 1,1-bis-(4-hydroxyphenyl)-1-phenylethane, 2,2-bis-(3,5-dichloro-4-hydroxyphenyl)-propane, 2,2-bis-(3,5-dibromo-4-hydroxyphenyl)-propane, 1,1-bis-(4-

- 11 -

hydroxyphenyl)-cyclohexane and 1,1-bis-(4-hydroxyphenyl)-3,3,5-trimethylcyclohexane (bisphenol TMC).

2,2-Bis-(4-hydroxyphenyl)-propane (bisphenol A), 4,4'-
5 dihydroxybiphenyl (DOD), 1,3-bis-[2-(4-hydroxyphenyl)-2-propyl]-benzene (bisphenol M) and 1,1-bis-(4-hydroxyphenyl)-3,3,5-trimethylcyclohexane (bisphenol TMC) are very particularly preferred.

- 10 The diphenols can be used both by themselves and in a mixture with one another; both homopolycarbonates and copolycarbonates are included. The diphenols are known from the literature or can be prepared by processes known from the literature (see e.g. H. J. Buysch et al.,
15 Ullmann's Encyclopedia of Industrial Chemistry, VCH, New York 1991, 5th ed., vol. 19, p. 348).

The polycarbonates and copolycarbonates can also be branched. Certain small amounts, preferably amounts of
20 between 0.05 and 5 mol%, particularly preferably 0.1 to 3 mol%, very particularly preferably 0.1 to 2 mol%, based on the moles of diphenols employed, of trifunctional compounds, such as e.g. isatin-bisresol (IBC) or phloroglucinol, 4,6-dimethyl-2,4,6-tri-(hydroxyphenyl)-
25 hept-2-ene; 4,6-dimethyl-2,4,6-tri-(4-hydroxyphenyl)-heptane; 1,3,5-tri-(4-hydroxyphenyl)-benzene; 1,1,1-tri-(4-hydroxyphenyl)-ethane (THPE); tri-(4-hydroxyphenyl)-phenylmethane; 2,2-bis-[4,4-bis-(4-hydroxyphenyl)-cyclohexyl]-propane; 2,4-bis-(4-hydroxyphenyl-isopropyl)-
30 phenol; 2,6-bis-(2-hydroxy-5'-methyl-benzyl)-4-methylphenol; 2-(4-hydroxyphenyl)-2-(2,4-dihydroxyphenyl)-propane; hexa-(4-(4-hydroxyphenyl-isopropyl)-phenyl)-orthoterephthalic acid ester; tetra-(4-hydroxyphenyl)-

- 12 -

methane; tetra-(4-(4-hydroxyphenyl-isopropyl)-phenoxy)-methane; α,α,α -tris-(4-hydroxyphenyl)-1,3,5-triisopropylbenzene; 2,4-dihydroxybenzoic acid; trimesic acid; cyanuric chloride; 3,3-bis-(3-methyl-4-hydroxyphenyl)-2-oxo-2,3-dihydroindole; 1,4-bis-(4',4''-dihydroxytriphenyl)-methyl)-benzene and in particular: 1,1,1-tri-(4-hydroxyphenyl)-ethane and bis-(3-methyl-4-hydroxyphenyl)-2-oxo-2,3-dihydroindole are employed for this purpose. Isatin-biscresol and 1,1,1-tri-(4-hydroxyphenyl)-ethane and bis-(3-methyl-4-hydroxyphenyl)-2-oxo-2,3-dihydroindole are preferably employed as branching agents.

Branched structures result by the use of these branching agents. The resulting long-chain branching leads to rheological properties of the polycarbonates obtained, which manifests itself in a structural viscosity compared with linear types.

The present invention furthermore relates to a process for the preparation of the polycarbonates and copolycarbonates of the formulae (4a), (4b) and (5) according to the invention, characterized in that bisphenols and possibly branching agents are dissolved in an aqueous alkaline solution and are reacted with a source of carbonate, such as phosgene, optionally dissolved in a solvent, in a two-phase mixture of an aqueous alkaline solution, an organic solvent and a catalyst, preferably an amine compound. The reaction can also be carried out in several stages. Such processes for the preparation of polycarbonate are known in principle as two-phase boundary processes e.g. from H. Schnell, Chemistry and Physics of Polycarbonates, Polymer Reviews, vol. 9, Interscience Publishers, New York 1964,

p. 33 et seq. and from Polymer Reviews, vol. 10, "Condensation Polymers by Interfacial and Solution Methods", Paul W. Morgan, Interscience Publishers, New York 1965, chap. VIII, p. 325, and the fundamental conditions
5 are therefore familiar to the expert.

The concentration of the bisphenols in the aqueous alkaline solution here is 2 to 25 wt.%, preferably 2 to 20 wt.%, particularly preferably 2 to 18 wt% and very particularly
10 preferably 3 to 15 wt.%. The aqueous alkaline solution comprises water, in which hydroxides of alkali metals or alkaline earth metals are dissolved. Sodium hydroxide and potassium hydroxide are preferred.

15 If phosgene is used as the source of carbonate, the volume ratio of aqueous alkaline solution to organic solvent is 5:95 to 95:5, preferably 20:80 to 80:20, particularly preferably 30:70 to 70:30 and very particularly preferably 40:60 to 60:40. The molar ratio of bisphenol to phosgene
20 is less than 1:10, preferably less than 1:6, particularly preferably less than 1:4 and very particularly preferably less than 1:3. The concentration of the branched polycarbonates and copolycarbonates according to the invention in the organic phase is 1.0 to 25 wt.%,
25 preferably 2 to 20 wt.%, particularly preferably 2 to 18 wt.% and very particularly preferably 3 to 15 wt%.

The concentration of the amine compound, based on the amount of bisphenol employed, is 0.1 to 10 mol%, preferably
30 0.2 to 8 mol%, particularly preferably 0.3 to 6 mol% and very particularly preferably 0.4 to 5 mol%.

- 14 -

The source of carbonate is phosgene, diphosgene or triphosgene, preferably phosgene. In the case where phosgene is employed, a solvent can optionally be dispensed with and the phosgene can be passed directly into the
5 reaction mixture.

Catalysts which can be employed are tertiary amines, such as triethylamine or N-alkylpiperidines. Suitable catalysts are trialkylamines and 4-(dimethylamino)pyridine.



- 10 Triethylamine, tripropylamine, triisopropylamine, tributylamine, triisobutylamine, N-methylpiperidine, N-ethylpiperidine and N-propylpiperidine are particularly suitable.
- 15 Possible organic solvents are halogenated hydrocarbons, such as methylene chloride and/or chlorobenzene, dichlorobenzene, trichlorobenzene or mixtures thereof, or aromatic hydrocarbons, such as, e.g. toluene or xylenes.
- 20 The reaction temperature can be -5°C to 100°C, preferably 0°C to 80°C, particularly preferably 10°C to 70°C and very particularly preferably 10°C to 60°C.

Alternatively, the polycarbonates according to the
25 invention can also be prepared by the melt transesterification process. The melt transesterification process is described, for example, in the Encyclopedia of Polymer Science, vol. 10 (1969), Chemistry and Physics of Polycarbonates, Polymer Reviews, H. Schnell, vol. 9, John
30 Wiley and Sons, Inc. (1964) and DE-C 10 31 512.

In the melt transesterification process, the aromatic dihydroxy compounds already described in the phase boundary

process are transesterified with carbonic acid diesters with the aid of suitable catalysts and optionally further additives in the melt.

- 5 Carbonic acid diesters in the context of the invention are those of the formula (6) and (7)



wherein

10

R, R' and R'' independently of one another can represent H, optionally branched C1-C34-alkyl/cycloalkyl, C7-C34-alkaryl or C6-C34-aryl,

15 for example

diphenyl carbonate, butylphenyl phenyl carbonate, di-butylphenyl carbonate, isobutylphenyl phenyl carbonate, di-isobutylphenyl carbonate, tert-butylphenyl phenyl carbonate, di-tert-butylphenyl carbonate, n-pentylphenyl phenyl carbonate, di-(n-pentylphenyl) carbonate, n-hexylphenyl phenyl carbonate, di-(n-hexylphenyl) carbonate, cyclohexylphenyl phenyl carbonate, di-cyclohexylphenyl carbonate, phenylphenol phenyl carbonate, di-phenylphenol carbonate, isooctylphenyl phenyl carbonate, di-isooctylphenyl carbonate, n-nonylphenyl phenyl carbonate, di-(n-nonylphenyl) carbonate, cumylphenyl phenyl carbonate,

20

25

18 OCT 2006

- 16 -

di-cumylphenyl carbonate, naphthylphenyl phenyl carbonate,
di-naphthylphenyl carbonate, di-tert-butylphenyl phenyl
carbonate, di-(di-tert-butylphenyl) carbonate, dicumylphenyl
phenyl carbonate, di-(dicumylphenyl) carbonate, 4-
5 phenoxyphenyl phenyl carbonate, di-(4-phenoxyphenyl)
carbonate, 3-pentadecylphenyl phenyl carbonate, di-(3-
pentadecylphenyl) carbonate tritylphenyl phenyl carbonate
and di-tritylphenyl carbonate,

10 preferably

diphenyl carbonate, tert-butylphenyl phenyl carbonate, di-
tert-butylphenyl carbonate, phenylphenol phenyl carbonate,
di-phenylphenol carbonate, cumylphenyl phenyl carbonate and
15 di-cumylphenyl carbonate,

particularly preferably diphenyl carbonate.


Mixtures of the carbonic acid diesters mentioned can also
20 be employed.

The content of carbonic acid ester is 100 to 130 mol%,
preferably 103 to 120 mol%, particularly preferably 103 to
109 mol%, based on the dihydroxy compound.

25

Basic catalysts as described in the literature mentioned,
such as, for example, alkali metal and alkaline earth metal
hydroxides and oxides, and also ammonium or phosphonium
salts, called onium salts in the following, are employed in
30 the melt transesterification process as catalysts in the
context of the invention. Onium salts are preferably
employed here, particularly preferably phosphonium salts.

Phosphonium salts in the context of the invention are those of the formula (8)



wherein

5

R1-4 can be the same or different C1-C10-alkyls, C6-C10-aryls, C7-C10-aralkyls or C5-C6-cycloalkyls, preferably methyl or C6-C14-aryls, particularly preferably methyl or phenyl, and

10

X- can be an anion, such as hydroxide, sulfate, hydrogen sulfate, bicarbonate, carbonate, a halide, preferably chloride, or an alcoholate of the formula OR, wherein R can be C6-C14-aryl or C7-C12-aralkyl, preferably phenyl. Preferred catalysts are

15

tetraphenylphosphonium chloride, tetraphenylphosphonium hydroxide and tetraphenylphosphonium phenolate, particularly preferably tetraphenylphosphonium phenolate.

20

The catalysts are preferably employed in amounts of 10^{-8} to 10^{-3} mol, based on one mole of bisphenol, particularly preferably in amounts of 10^{-7} to 10^{-4} mol.

25

Further catalysts can be used by themselves or optionally in addition to the onium salt in order to increase the speed of the polymerization. These include salts of alkali metals and alkaline earth metals, such as hydroxides, alkoxides and aryloxides of lithium, sodium and potassium, preferably hydroxide, alkoxide or aryloxide salts of

30

- 18 -

sodium. Sodium hydroxide and sodium phenolate are most preferred. The amounts of the cocatalyst can be in the range from 1 to 200 ppb, preferably 5 to 150 ppb and most preferably 10 to 125 ppb, in each case calculated as sodium.

The transesterification reaction of the aromatic dihydroxy compound and the carbonic acid diester in the melt is preferably carried out in two stages. In the first stage melting of the aromatic dihydroxy compound and the carbonic acid diester takes place at temperatures of 80 to 250°C, preferably 100 to 230°C, particularly preferably 120 to 190°C under normal pressure in the course of 0 to 5 hours, preferably 0.25 to 3 hours. After addition of the catalyst, the oligocarbonate is prepared from the aromatic dihydroxy compound and the carbonic acid diester by distilling off the monophenol by applying a vacuum (down to 2 mm Hg) and increasing the temperature (to up to 260°C). The main amount of vapours are obtained from the process by this means. The oligocarbonate prepared in this way has a weight-average molecular weight M_w (determined by measurement of the rel. solution viscosity in methylene chloride or in mixtures of the same amounts by weight of phenol/o-dichlorobenzene calibrated by light scattering) in the range from 2,000 g/mol to 18,000 g/mol, preferably 4,000 g/mol to 15,000 g/mol.

In the second stage the polycarbonate is prepared in the polycondensation by further increasing the temperature to 250 to 320°C, preferably 270 to 295°C, under a pressure of < 2 mm Hg. The remainder of the vapours are removed from the process by this means.

The catalysts can also be employed in combination (two or more) with one another.

If alkali metal/alkaline earth metal catalysts are
5 employed, it may be advantageous to add the alkali metal/alkaline earth metal catalysts at a later point in time (e.g. after the oligocarbonate synthesis, in the polycondensation in the second stage).

10 The reaction of the aromatic dihydroxy compound and the carbonic acid diester to give the polycarbonate can be carried out discontinuously or, preferably, continuously in the context of the process according to the invention, for example in stirred tanks, thin film evaporators, falling
15 film evaporators, cascades of stirred tanks, extruders, kneaders, simple disc reactors and high-viscosity disc reactors.

Analogously to the phase boundary process, branched poly-
20 or copolycarbonates can be prepared by using polyfunctional compounds.

The molecular weights M_w of the branched polycarbonates and copolycarbonates according to the invention are in the
25 range from 6,000 to 200,000 g/mol, preferably between 6,000 and 100,000 g/mol, particularly preferably between 10,000 and 80,000 g/mol and very particularly preferably between 12,000 and 70,000 g/mol (determined by means of GPC and polycarbonate calibration).

30

Preferred, particularly preferred or very particularly preferred embodiments are those which use the parameters, compounds, definitions and explanations given under

preferred, particularly preferred or very particularly preferred or preferably etc.

However, the definitions, parameters, compounds and
5 explanations mentioned generally in the description or mentioned in preferred ranges can also be combined with one another as desired, that is to say between the particular ranges and preferred ranges.

10 The polycarbonates and copolycarbonates according to the invention can be worked up in a known manner and processed to any desired shaped articles, for example by extrusion, injection moulding or extrusion blow moulding.

15 Other aromatic polycarbonates and/or other aromatic polyester-carbonates and/or other aromatic polyesters can also be admixed to the polycarbonates and copolycarbonates according to the invention in a known manner, for example by compounding.

20

The conventional additives for these thermoplastics, such as fillers, UV stabilizers, heat stabilizers, antistatics and pigments, can also be added to the polycarbonates and copolycarbonates according to the invention in the
25 conventional amounts; if appropriate, the mould release properties, the flow properties and/or the flame resistance can also be improved by addition of external mould release agents, flow agents and/or flameproofing agents (e.g. alkyl and aryl phosphites, phosphates, -phosphanes and low
30 molecular weight carboxylic acid esters, halogen compounds, salts, chalk, quartz flour, glass fibres and carbon fibres, pigments and a combination thereof. Such compounds are described e.g. in WO 99/55772, p. 15 - 25, and in the

18 OCT 2006

- 21 -

corresponding chapters of the "Plastics Additives Handbook", ed. Hans Zweifel, 5th edition 2000, Hanser Publishers, Munich).

5 The polycarbonates and copolycarbonates according to the invention, optionally in a blend with other thermoplastics and/or conventional additives, when processed to any desired shaped articles/extrudates, can be employed in all instances where polycarbonates, polyester-carbonates and
10 polyesters which are already known are employed. On the basis of their profile of properties, they are suitable in particular as materials for injection moulding of relatively large mouldings, for example automobile screens. Due to the low water uptake and the associated improved
15 dimensional stability, however, they are also particularly suitable as substrate materials for optical data storage media, such as e.g. CDs, CD-Rs, DVDs, DVD-Rs, blue-ray discs or advanced optical discs (AOD), but can also be employed, for example, as films in the electrical sector,
20 as mouldings in vehicle construction and as sheets for covers in the safety sector. Further possible uses of the polycarbonates according to the invention are:

1. Safety panes, which as is known are necessary in many
25 areas of buildings, vehicles and aircraft, and as helmet shields.
2. Production of foils, in particular ski foils.
- 30 3. Production of blow mouldings (see, for example, US Patent 2 964 794), for example 1 to 5 gallon water bottles.

4. Production of transparent sheets, in particular hollow sheets, for example for covering buildings such as railway stations, greenhouses and lighting installations.
5. Production of optical data storage media.
6. For the production of traffic light housings or traffic signs.
7. For the production of foams (see, for example, DE-B 1 031 507).
8. For the production of filaments and wires (see, for example, DE-B 1 137 167 and DE-A 1 785 137).
9. As translucent plastics with a content of glass fibres for illumination purposes (see, for example, DE-A 1 554 020).
10. As translucent plastics with a content of barium sulfate, titanium dioxide and/or zirconium oxide or organic polymeric acrylate rubbers (EP-A 634 445, EP-A 269324) for the production of transparent and light-scattering mouldings.
11. For the production of precision injection moulding components, such as, for example, lens holders. Polycarbonates with a content of glass fibres, which optionally additionally comprise about 1 to 10 wt.% MoS₂, based on the total weight, are used for this.

12. For the production of optical equipment components, in particular lenses for photographic and film cameras (see, for example, DE-A 2 701 173).
- 5 13. As light transmission carriers, in particular as light conductor cables (see, for example, EP-A 0 089 801).
14. As electrical insulating materials for electrical conductors and for plug housings and plug connectors.
- 10 15. Production of mobile telephone housings with improved resistance to perfume, shaving lotion and skin perspiration.
- 15 16. Network interface devices.
17. As a carrier material for organic photoconductors.
18. For the production of lamps, e.g. searchlight lamps,
20 as so-called "head-lamps", diffusing screens or internal lenses, as well as long-distance lamps.
19. For medical uses, e.g. oxygenators, dialysers.
- 25 20. For foodstuffs uses, such as e.g. bottles, utensils and chocolate moulds.
21. For uses in the automobile sector where contact with fuels and lubricants may occur, such as, for example,
30 bumpers, optionally in the form of suitable blends with ABS or suitable rubbers.


22. For sports articles, such as e.g. slalom poles or ski boot buckles.
23. For household articles, such as e.g. kitchen sinks and letterbox housings.
24. For housings, e.g. electrical distribution cabinets.
25. Housings for electric toothbrushes and hairdryer housings.
26. Transparent washing machine portholes with improved resistance to the wash solution.
27. Safety glasses, visors or optical corrective glasses.
28. Lamp covers for kitchen equipment with improved resistance to kitchen vapour, in particular oil vapours.
29. Packaging films for medicaments.
30. Chip boxes and chip carriers.
31. For other uses, such as e.g. fattening stall doors or animal cages.
32. Safety helmets.
- This Application also provides the new (co)polycarbonates and shaped articles and extrudates obtainable therefrom.

- 25 -

The following examples are intended to illustrate the invention, but without limiting it.

Examples

Example 1


5 Synthesis of a bisphenol based on hydrogenated β -ionone:

105.9 g (1.13 mol) of freshly distilled phenol and 75 g
(0.38 mol) 4-(2,2,6-trimethylcyclohexyl)-2-butanone
10 (Avocado) are initially introduced into the reaction
vessel, and 7.5 g (0.037 mol) dodecylmercaptan (Acros) are
added as a catalyst. HCl gas is passed in at a constant
temperature of 26 to 28°C for 2 hours. For a condensation
which is as complete as possible, the mixture is then
15 subsequently stirred for a further 4 hours at room
temperature without further HCl gas being passed in. The
reaction mixture was then left to stand overnight at room
temperature. To remove the HCl residues, dry nitrogen was
passed through the solution at a temperature of 32 to 40°C
20 for 5 hours. For working up of the reaction mixture, the
excess phenol was distilled off first under a water pump
vacuum and finally at a max. temperature of 150°C under an
oil pump vacuum with a rotary disc pump. The crude product
was finally taken up in methylene chloride and the mixture
25 was washed neutral with water. After concentration of the
organic phase and drying of the residue, 122 g of product,
which was still contaminated, were obtained. For further
purification, the crude product was taken up in 150 ml
petroleum ether and the mixture was boiled for 2 hours.

- 27 -

During this operation the crude product became increasingly lighter in colour. After decanting, the product was boiled up again a total of 2 times with 150 ml n-hexane for 30 min. After decanting, a beige product is obtained, and was dried at 50°C in a vacuum drying cabinet.
Yield: 71.9 g (0.196 mol, 51.7% of theory)


Analysis:



- 10 • GC-MS gives a double signal lying very closely side by side (stereoisomers) each with the mass 366 (TMS-MW = 510).
- 15 • ¹H-NMR (400 MHz, TMS, DMSO) δ = 9.05 (s, 2OH), 6.95 (d, AA', 2Har), 6.65 (d, BB', 2Har), 2.0-1.78 (mm, 3H), 1.49 (s, 3H), 1.39-1.27 (m, 2H), 1.27-1.15 (m, 1H), 1.14-1.10 (m, 1H), 1.10-0.81 (m, 5H), 0.87 (s, 3H), 0.72 (s, 3H), 0.69-0.67 (d, 3H).

Example 2

a) Synthesis of the homopolycarbonate:



5 267 ml methylene chloride are added to a solution, which has been rendered inert with nitrogen, of 36.65 g (0.1 mol) bisphenol from example 1 and 8.8 g (0.22 mol) sodium hydroxide in 550 ml water. 0.45 g (0.003 mol or 3.0 mol%

10 with respect to the bisphenol) p-tert-butylphenol (BUP) is added in a one-stage procedure as a chain terminator. 14 ml (20.3 g, 0.205 mol) phosgene are added at a pH of 14 and a temperature of 16°C in the course of 10 minutes. In order not to allow the pH to fall below 12, 25 % strength

15 sodium hydroxide solution was added during the phosgenation. After the phosgenation and flushing with nitrogen has ended, 0.11 g (0.001 mol, 1 mol% with respect to the bisphenol) n-ethylpiperidine is added as a catalyst and the mixture is subsequently stirred for 1 hour. After

20 the aqueous phase has been separated off, the organic phase is acidified with phosphoric acid and washed neutral and salt-free with distilled water. After the polymer has been precipitated out in methanol, 34.2 g polycarbonate are obtained.

Analysis:

- Relative solution viscosity in methylene chloride (0.5 g/100 ml solution): 1.163 / 1.164

5

- GPC (calibration against BPA polycarbonate): molecular weight $M_w = 25,979$, $M_n = 8,750$, polydispersity $D = 2.97$

- Glass transition temperature T_g : 145°C

10

b) A homopolycarbonate with a higher molecular weight is prepared in an analogous manner (only a lower chain terminator concentration). A product with the following analytical data is obtained by this procedure:

15

Analysis:

- Relative solution viscosity in methylene chloride (0.5 g/100 ml solution): 1.230 / 1.230

20

- GPC (calibration against BPA polycarbonate): molecular weight $M_w = 31,424$, $M_n = 13,779$, polydispersity $D = 2.28$

- Glass transition temperature T_g : 149°C

25

Example 3

Determination of the viscosity as a function of the shear
5 rate (ISO 11443).

The polycarbonate obtained in example 2 is analysed
rheologically at 290°C. The following data are obtained in
this analysis:

10

Shear gradient [s-1]	Viscosity [Pas]
50	365
100	323
200	276
15 500	212
1,000	166
1,500	140

Example 4: (comparison example)

20


For comparison, a linear BPA polycarbonate (Makrolon 2608,
Bayer AG) with a molecular weight $M_w = 26,000$ is used
analogously to example 3.

25	Shear gradient [s-1]	Viscosity [Pas]
	50	688
	100	625
	200	563
	500	480
30	1,000	383
	1,500	318

As can be seen from the comparison of the viscosity data between example 3 and 4, at approximately the same molecular weight the melt viscosity at 290°C is lower over the entire range of the shear gradient. The polycarbonate according to the invention from example 2 thus flows more readily than the comparison material based on bisphenol A (Makrolon 2608).

Example 5:

- 10 Synthesis of copolycarbonates with bisphenol A with different compositions (50:50), (75:25), (25:75):



- a) 220 ml methylene chloride are added to a solution, which has been rendered inert with nitrogen, of 18.33 g (0.05 mol) bisphenol from example 1, 11.42 g (0.05 mol) bisphenol A and 8.8 g (0.22 mol) sodium hydroxide in 520 ml water. 0.45 g (0.003 mol or 3.0 mol% with respect to the bisphenol) p-tert-butylphenol (BUP) is added in a one-stage procedure as a chain terminator.

14 ml (20.6 g, 0.208 mol) phosgene are added at a pH of 14 and a temperature of 16°C in the course of 10 minutes. In order not to allow the pH to fall below 12, 25 % strength sodium hydroxide solution was added during the phosgenation. After the phosgenation and flushing with nitrogen has ended, 0.11 g (0.001 mol, 1 mol% with respect to the bisphenol) n-ethylpiperidine is added as a catalyst and the mixture is subsequently stirred for 1 hour. After the aqueous phase has been separated off, the organic phase is acidified with phosphoric acid and washed neutral and salt-free with distilled water. After the polymer has been precipitated out in methanol, 20.1 g polycarbonate are obtained.

15

Analysis 5a):

- Relative solution viscosity in methylene chloride (0.5 g/100 ml solution): 1.161 / 1.161
- 20 • GPC (calibration against BPA polycarbonate): molecular weight $M_w = 20,414$, $M_n = 5,926$, polydispersity $D = 3.44$
- Glass transition temperature T_g : 140°C

The following copolycarbonates which differ in their composition (bisphenol A to bisphenol from example 1) are prepared analogously to this procedure.

	Copolycarbonate example 1 [mol%]	Bisphenol A [mol%]	Bisphenol from
30	5b)	75	25
	5c)	25	75


The following polymers are obtained by this procedure:

Copolycarbonate	Eta rel	Mw	Mn	D	Tg[°C]
5b)	1.336	38,737	16,377	2.37	150
5c)	1.233	30,321	8,615	3.52	148

5

Example 6:

Synthesis of asymmetrically and symmetrically substituted bisphenols:



10

17.59 g (0.048 mol) bisphenol from example 1 and 153.8 g (1.42 mol) o-cresol are initially introduced into the reaction vessel, and 0.97 g (0.0048 mol) dodecylmercaptan is added as a catalyst. The mixture is homogenized at 40°C. HCl gas is then passed into the reaction mixture at 40°C for four hours. The mixture is subsequently stirred

18 OCT 2006

- 34 -

at this temperature for a further 1.5 hours without passing in further gas. The reaction mixture then remained overnight at room temperature. To remove the HCl residues, dry nitrogen was passed through the solution at room temperature for 1 hour. For working up of the reaction mixture, the excess cresol was distilled off first under a water pump vacuum and finally at a max. temperature of 150°C under an oil pump vacuum with a rotary disc pump. 18.6 g of product is obtained.

10 Analysis:

- GC-MS gives a triple signal lying very closely side by side (product mixture) with in each case the educt mass 366 (TMS-MW = 510), the product mass 380 (TMS-MW = 524) for the monosubstituted product and the product mass 394 (TMS-MW = 538) for the disubstituted product.
- The ratio of the GC-MS mass signals of the various (silylated) components is 0.600 (educt) : 1.295 (monosubst. product) : 1.0 (disubst. product).
- ¹H-NMR (400 MHz, TMS, DMSO): The previous AA'BB' splitting pattern for para-substituted aromatics in the aromatic resonance range at δ = 6.95 (d, AA', 2Har), 6.65 (d, BB', 2Har) (see example 1) changes into the typical splitting pattern for polysubstituted aromatics. Furthermore, in addition to δ = 9.00 (s, OH), a further signal occurs for a phenolic OH group at δ = 9.12 (s, OH). The expected signal for the methyl groups on the aromatic ring occurs at δ = 2.05 (s, CH₃).


Example 7:

70.36 g (0.192 mol) bisphenol prepared analogously to example 1 and 615.2 g (5.68 mol) o-cresol are initially introduced into the reaction vessel, and 3.88 g (0.0192 mol) dodecylmercaptan are added as a catalyst. The mixture is homogenized at 50°C. HCl gas is then passed into the reaction mixture at 50°C, and the temperature is lowered to 40°C immediately after a clear change in colour occurs. Passing in of the gas is maintained for 7 hours at this temperature. To remove the HCl residues, dry nitrogen was passed through the solution at room temperature for 1 hour. For working up of the reaction mixture, the excess cresol was distilled off first under a water pump vacuum and finally at a max. temperature of 150°C under an oil pump vacuum with a rotary disc pump. 59.45 g of product are obtained.

Analysis:


- GC-MS gives a signal for the disubstituted product with the mass 394 (TMS-MW = 538)
- The ratio of the GC-MS mass signals (area%) of the various (silylated) components is 0.38 (monosubst. product) : 94.58 (disubst. product).

- 36 -



Example 8

- 5 Synthesis of a bisphenol based on hydrogenated β -ionone with an ion exchanger:



- 110.25 g (1.17 mol) of freshly distilled phenol and 23 g (0.117 mol) 4-(2,2,6-trimethylcyclohexyl)-2-butanone (Avocado) are initially introduced into the reaction vessel, and 100 g of dried, active ion exchanger K1221 (Bayer AG, Leverkusen) are added as a catalyst. The

18 OCT 2006

- 37 -


mixture is stirred at a constant temperature of 70°C for 24 hours. Thereafter, the complete mixture is introduced on to a suction filter with polyacrylonitrile fabric and the catalyst is separated off. Rinsing was carried out with fresh phenol. The filtrate was freed from excess phenol first under a water pump vacuum and then under an oil pump vacuum at 90°C. After purification with petroleum ether analogously to example 1, the desired product is obtained in a yield of 20 g.

10

Analysis:

- ¹H-NMR (400 MHz, TMS, DMSO) data as under example 1

Example 9:



a) Synthesis of a copolycarbonate with bisphenol TMC (50:50):

5

220 ml methylene chloride are added to a solution, which has been rendered inert with nitrogen, of 18.33 g (0.05 mol) bisphenol from example 1, 15.52 g (0.05 mol) bisphenol TMC and 8.8 g (0.22 mol) sodium hydroxide in 420 ml water.

10 0.45 g (0.003 mol or 3.0 mol% with respect to the bisphenol) p-tert-butylphenol (BUP) is added in a one-stage procedure as a chain terminator. 14 ml (20.6 g, 0.208 mol) phosgene are added at a pH of 14 and a temperature of 16°C in the course of 10 minutes. In order not to allow the pH

15 to fall below 12, 25 % strength sodium hydroxide solution was added during the phosgenation. After the phosgenation and flushing with nitrogen has ended, 0.11 g (0.001 mol, 1

mol% with respect to the bisphenol) n-ethylpiperidine is added as a catalyst and the mixture is subsequently stirred for 1 hour. After the aqueous phase has been separated off, the organic phase is acidified with phosphoric acid and washed neutral and salt-free with distilled water. After the polymer has been precipitated out in methanol, 30.5 g polycarbonate are obtained.

Analysis:

10

- Relative solution viscosity in methylene chloride (0.5 g/100 ml solution): 1.147 / 1.148
- GPC (calibration against BPA polycarbonate): molecular weight $M_w = 16,986$, $M_n = 6,150$, polydispersity $D = 2.76$
- Glass transition temperature T_g : 181°C

b) Synthesis of a copolycarbonate with bisphenol TMC (30:70):

20

220 ml methylene chloride are added to a solution, which has been rendered inert with nitrogen, of 25.66 g (0.07 mol) bisphenol from example 1 (70 mol%), 9.31 g (0.03 mol) bisphenol TMC (30 mol%) and 8.8 g (0.22 mol) sodium hydroxide in 600 ml water. 0.45 g (0.003 mol or 3.0 mol% with respect to the bisphenol) p-tert-butylphenol (BUP) is added in a one-stage procedure as a chain terminator. 14 ml (20.6 g, 0.208 mol) phosgene are added at a pH of 14 and a temperature of 16°C in the course of 10 minutes. In order not to allow the pH to fall below 12, 25 % strength sodium hydroxide solution was added during

30

the phosgenation. After the phosgenation and flushing with nitrogen has ended, 0.11 g (0.001 mol, 1 mol% with respect to the bisphenol) n-ethylpiperidine is added as a catalyst and the mixture is subsequently stirred for 1 hour. After the aqueous phase has been separated off, the organic phase is acidified with phosphoric acid and washed neutral and salt-free with distilled water. After the polymer has been precipitated out in methanol, 34.1 g polycarbonate are obtained.

Analysis:

- Relative solution viscosity in methylene chloride (0.5 g/100 ml solution): 1.252 / 1.251
- GPC (calibration against BPA polycarbonate): molecular weight $M_w = 39,681$, $M_n = 12,350$, polydispersity $D = 3.21$
- Glass transition temperature T_g : 173°C

Example 10:

Determination of the water content of polycarbonates:

Water uptake and determination of the water content of polycarbonates from examples 2a), 5a) and 9a) after storage in a damp climate at 95% rh and a storage temperature of 30°C .

The water content is determined after various storage times by means of quantitative Karl-Fischer titration (coulometric titration).

18 OCT 2006

- 41 -

Storage times : 7 days and 14 days

Weathering : damp climate 95% rh and 30°C

Reproduction : 4 measurements per storage

5


<u>Polycarbonate</u>		<u>7 days [%]</u>	<u>14 days [%]</u>
Comparison sample			
Makrolon CD 2005, Bayer AG n.d.			0.32 - 0.34
	2a)	0.12 / 0.15	0.15 / 0.16
10	5a)	0.12 / 0.14	0.12 / 0.13
	9a)	0.21 / 0.23	0.20 / 0.21

The comparison with the prior art Makrolon CD 2005, a polycarbonate based on bisphenol A, shows a significantly lower water uptake in the polycarbonates according to the invention.

15

Claims:

1. A compound conforming to formula 1



in which

R^1 to R^{12} independently one of the other represents hydrogen or C_1 - C_{10} alkyl radical,
 n represents an integer of 0 to 10 and m represents an integer of 0 to 10.

2. The compound of Claim 1 wherein the radical is linear.
3. The compound of Claim 1 wherein the radical is branched.
4. A process for the preparation of the compound of Claim 1 comprising condensing in the presence of an acid catalyst at least one corresponding phenol with at least one alkyl-substituted ketone at 0 to 100°C at a stoichiometric ratio of phenol to ketone of 15 to 1 in the presence of a sulfur-containing compound.
5. A (co)polycarbonate containing structural units derived from the compounds of the formula 1.
6. A molded article comprising the (co)polycarbonate of Claim 4.
7. An extruded article comprising the (co)polycarbonate of Claim 4.