CLAIMS

1. An antifouling coating composition, comprising:
a copolymer A;


a polymer B, which is not a (meth)acrylate silyl ester copolymer; and

a plasticizer C; wherein:

the copolymer A is a copolymer of a monomer (a) and an ethylenically unsaturated monomer (b) other than the monomer (a);

the monomer (a) is represented by general formula (1);

[chemical formula 1]



（1）

in the general formula, R^1 is a methyl group, and R^2 to R^4 are the same or different and each represents a C3-C8 branched alkyl group or a phenyl group;

content of the monomer (a) is 15 to 35mass% with respect to a total mass of the monomer (a) and the monomer (b);

the polymer B is a (meth)acrylate ester polymer other than the copolymer A and has a weight average molecular weight of 20,000 to 100,000.

2 The antifouling coating composition according to claim 1, wherein the plasticizer C contains chlorinated paraffin.